

(19)



(11)

EP 2 047 306 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
13.12.2017 Bulletin 2017/50

(51) Int Cl.:
G02F 1/1345 (2006.01) G02B 1/11 (2015.01)
G02F 1/1335 (2006.01) G02B 5/30 (2006.01)

(21) Application number: **07793288.7**

(86) International application number:
PCT/KR2007/003633

(22) Date of filing: **27.07.2007**

(87) International publication number:
WO 2008/016242 (07.02.2008 Gazette 2008/06)

(54) POLARIZING PLATE AND LIQUID CRYSTAL DISPLAY USING THE SAME

POLARISATIONSPLATTE UND FLÜSSIGKRISTALLANZEIGE DAMIT

PLAQUE POLARISANTE ET ÉCRAN À CRISTAUX LIQUIDES UTILISANT UN TEL PLAQUE POLARISANTE

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR

- **PARK, Jong-Sung**
Cheongju-si, Chungcheongbuk-do 361-270 (KR)
- **KIM, Min-Su**
Cheongju-si, Chungcheongbuk-do 361-271 (KR)
- **KIM, Sung-Hyun**
Cheongju-si, Chungcheongbuk-do, 361-240 (KR)

(30) Priority: **31.07.2006 KR 20060072305**

(43) Date of publication of application:
15.04.2009 Bulletin 2009/16

(74) Representative: **Goddard, Heinz J.**
Boehmert & Boehmert
Anwaltpartnerschaft mbB
Pettenkofenstrasse 22
80336 München (DE)

(60) Divisional application:
12173147.5 / 2 503 366

(73) Proprietor: **LG Chem, Ltd.**
Youngdungpo-gu, Seoul 150-721 (KR)

(56) References cited:
JP-A- 2004 245 925 JP-A- 2005 004 995
JP-A- 2005 017 435 JP-A- 2005 128 520
JP-A- 2005 338 736 JP-A- 2006 011 409
JP-A- 2006 030 950 US-A1- 2005 249 962
US-A1- 2006 062 934

(72) Inventors:
• **PARK, Jae-Hong**
Cheongju-si, Chungcheongbuk-do 361-300 (KR)

EP 2 047 306 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**Technical Field**

5 **[0001]** The present invention relates to a polarizing plate and a liquid crystal display using the same. More particularly, the present invention pertains to a liquid crystal display that has an arrangement structure of protective films of polarizing plates useful to avoid light leakage, yellowing, and egg-mura and prevent moisture absorption, and a polarizing plate that is used in the liquid crystal display. This application claims priority from Korean Patent Application No. 10-2006-0072305 filed on July 31, 2006 in the KIPO.

Background Art

10 **[0002]** In a known polarizing plate, a triacetyl cellulose (TAC) film that acts as a protective film is adhered to a polarizing film in which iodine or dichromatic dyes are adsorbed and aligned on a polyvinyl alcohol (hereinafter, referred to as "PVA") polymer film by using adhesives. A known polarizing plate that includes triacetyl cellulose (TAC) films provided on both sides of a polarizing film is shown in Fig. 1. A pressure sensitive adhesive (PSA) layer is further provided on a side of the polarizing plate of Fig. 1 to apply the polarizing plate to the liquid crystal display. The liquid crystal display that includes the polarizing plate of Fig. 1 is shown in Fig. 2.

15 **[0003]** However, since the triacetyl cellulose (TAC) film has the high moisture absorptivity or moisture transmissivity, the polarizing plate that includes the triacetyl cellulose (TAC) film as the protective film is problematic in that a polarizing ability is reduced in a hot and humid atmosphere. Hence, a polarizing plate that includes a film having the low absorptivity or vapor transmissivity as a protective film has been suggested. Examples thereof include a polarizing plate that is shown in Fig. 3 and includes a cycloolefin resin film as an inner protective film provided on a liquid crystal cell of both sides of the polarizing plate.

20 **[0004]** However, in the related art, in the case where the triacetyl cellulose (TAC) film is disposed at an outermost edge of the liquid crystal display, since the triacetyl cellulose (TAC) film has a poor moisture prevention ability, the polyvinyl alcohol resin film that is vulnerable to moisture absorbs moisture. In this case, there are problems in that a polarizing ability is reduced due to a change in size of the polyvinyl alcohol resin film and light leakage occurs.

25 **[0005]** JP-A-2006/011409 discloses a polarizing plate wherein a triacetyl cellulose film is laminated on the polarizer, composed of polyvinyl alcohol and two colored material, as well as liquid crystal display using such polarizing plate.

30 **[0006]** JP-A-2004/245925 discloses a polarizing plate which is obtained by applying a protective film onto a polarizer consisting of polyvinyl alcohol-based resin film, as well as a liquid crystal display using such polarizing plate.

35 **[0007]** US 2006/0062934 A1 also discloses a polarizing plate on the basis of polyvinyl alcohol film and a triacetyl cellulose film attached thereto

[0008] JP 2005/338736 A discloses a polarizing plate on the basis of a polyvinyl alcohol film with eg. a polyethylene terephthalate film attached to one side and eg. a polyvinyl alcohol film attached to the other side, both having defined vapor transmissivity values.

[0009] JP 2005/128520 A also discloses a polarizing plate on the basis of a polyvinyl alcohol film with protective films on either side having defined vapor transmissivity values.

40 [Disclosure]

[Technical Problem]

45 **[0010]** Accordingly, there remains a need to develop a technology for preventing reduction in functions, particularly, durability of a polarizing plate, and problems such as light leakage, yellowing, and egg-mura in a hot and humid atmosphere.

50 [Technical Solution]

[0011] The present inventors have found the following facts. In a liquid crystal display that is provided with a liquid crystal cell and polarizing plates disposed on both sides of the liquid crystal cell, a protective film of the polarizing plate disposed at an outermost edge of the liquid crystal display, that is, an outer protective film of the polarizing plate, significantly affects the moisture absorptivity and the moisture transmissivity of the polarizing plate to prevent functions of the polarizing plate from being reduced in a humid atmosphere. However, a protective film abutting the liquid crystal cell of the polarizing plate, that is, an inner protective film of the polarizing plate, insignificantly affects the moisture absorptivity and the moisture transmissivity of the polarizing plate. Thus, it is possible to select various types of inner protective films in consideration of improvement in adhesion strength to the liquid crystal cell and prevention of light

leakage and egg-mura.

[0012] Therefore, it is an object of the present invention to provide a liquid crystal display that includes polarizing plates arranged so that durability is excellent in a humid atmosphere and prevents light leakage and egg-mura, and a polarizing plate used in the same.

[0013] In order to achieve the above object, the present invention provides a polarizing plate according to claim 1 and a liquid crystal display according to claim 5.

Advantageous Effects

[0014] A liquid crystal display comprising a polarizing plate according to the present invention is advantageous in that functions of a polarizing plate are insignificantly reduced and light leakage and egg-mura are prevented in a humid atmosphere. Furthermore, yellowing does not occur.

Brief Description of Drawings

[0015]

Fig. 1 illustrates a structure of a conventional polarizing plate;

Fig. 2 illustrates a structure of a liquid crystal display that includes a conventional polarizing plate;

Fig. 3 illustrates a structure of a liquid crystal display that includes a conventional polarizing plate;

Fig. 4 illustrates a structure of a liquid crystal display according to an embodiment of the present invention;

Figs. 5 to 10 illustrate structures of polarizing plates according to embodiments of the present invention;

Figs. 11 to 13 illustrate light leakage prevention of the liquid crystal display according to the type of outer and inner protective films of the polarizing plate;

Figs. 14 and 15 are graphs showing optical properties of the polarizing plates that are produced in Examples 1 and 2 before and after UV is radiated; and

Fig. 16 schematically illustrates a procedure of measuring the transmissivity of the polarizing plate.

Best Mode for Carrying out the Invention

[0016] Hereinafter, the present invention will be described in detail. A polarizing plate according to the invention is defined by claims 1-4. A liquid crystal display according to the invention is defined by claims 5-23.

[0017] A liquid crystal display according to the present invention includes a liquid crystal cell and a first polarizing plate and a second polarizing plate respectively provided on each side of the liquid crystal cell. In the liquid crystal display, the first polarizing plate and the second polarizing plate each includes a polyvinyl alcohol polarizing film and protective films provided on both sides of the polyvinyl alcohol polarizing film, the protective films that are provided on surfaces opposite to the liquid crystal cell of the first polarizing plate and the second polarizing plate each has the vapor transmissivity of 100 g/m²Day or less, and the protective films that are provided on surfaces abutting the liquid crystal cell of the first polarizing plate and the second polarizing plate each has the vapor transmissivity of more than 1,500 g/m²Day. The structure of the liquid crystal display according to the present invention is shown in Fig. 4, but the scope of the present invention is not limited thereto.

[0018] Additionally, in the liquid crystal display according to the present invention, the protective films that are provided on surfaces opposite to the liquid crystal cell of the first polarizing plate and the second polarizing plate each has the vapor transmissivity of 100 g/m²Day or less, the protective films that are provided on surfaces abutting the liquid crystal cell of the first polarizing plate and the second polarizing plate each has the vapor transmissivity of more than 200 g/m²Day, and the film having the vapor transmissivity of 100 g/m²Day or less contains a UV absorbing agent or a UV absorption layer is provided on an upper surface or a lower surface of the film having the vapor transmissivity of 100 g/m²Day or less.

[0019] In the present invention, the film that has the vapor transmissivity of 100 g/m²Day or less is used as the protective film of the polarizing plate that is disposed at an outermost edge of the liquid crystal display. Thus, reduction in functions of the polarizing plate in a humid atmosphere is very efficiently prevented as compared to a liquid crystal display in which the film having the vapor transmissivity of 100 g/m²Day or less is used, but is disposed at another position, for example, at an inner protective film of the polarizing plate shown in Fig. 3.

[0020] In addition, since the film having the vapor transmissivity of more than 1500 g/m² Day is used as the protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell, light leakage, yellowing, and egg-mura are desirably prevented. The term "egg-mura" means formation of an egg-shaped stain. In the case where the UV absorbing agent is added to the protective film of the polarizing film that is provided on the surface opposite to the liquid crystal cell or the UV absorption layer is provided on the protective film to ensure a UV absorption ability, even though

the film having the vapor transmissivity of more than 200 g/m²Day is used as the polarizer protective film that is provided on the surface abutting the liquid crystal cell, light leakage, yellowing, and egg-mura are desirably prevented.

5 [0021] In the present invention, a film where molecules of a polymer film formed by using polyvinyl alcohol are arranged in a predetermined direction and iodine or a dichromatic material is adsorbed may be used as the polyvinyl alcohol polarizing film that is an element constituting the first polarizing plate and the second polarizing plate. Examples of the film include a polyvinyl alcohol · iodine polarizing film that is formed by uniaxially stretching the film in a boric acid bath after iodine is adsorbed on the polyvinyl alcohol film, a polyvinyl alcohol · dye polarizing film that is formed by uniaxially stretching the film after a dichromatic dye is diffused and adsorbed on a polyvinyl alcohol film, a polyvinyl alcohol · polyvinylene polarizing film that has a polyvinylene structure and is formed by adsorbing iodine on a polyvinyl alcohol film and stretching the film, a polyvinyl alcohol · metal polarizing film that is formed by adsorbing metal such as silver, mercury, and iron on a polyvinyl alcohol film, a near-ultraviolet polarizing film that is formed by treating a polyvinyl alcohol film using a boric acid solution containing potassium iodide and sodium thiosulfate, and a polarizing film in which a dichromatic dye is added to a surface and/or an inside of a polyvinyl alcohol film that includes denatured polyvinyl alcohol having a cation group in a molecule thereof. However, the examples of the film are not limited thereto, and any film known in the related art may be used.

10 [0022] The method of producing the polyvinyl alcohol polarizing film is not limited. Examples of the method may include a method of adsorbing iodine ions after a polyvinyl alcohol film is stretched, a method of performing stretching after a polyvinyl alcohol film is dyed by using a dichromatic dye, a method of performing dyeing by means of a dichromatic dye after a polyvinyl alcohol film is stretched, a method of performing stretching after a dichromatic dye is printed on a polyvinyl alcohol film, a method of performing printing by means of a dichromatic dye after a polyvinyl alcohol film is stretched, and the like. Specific examples include a method of producing a polarizing film, which includes dissolving iodine in a potassium iodide solution to produce iodine ions, adsorbing the ions on a polyvinyl alcohol film, stretching the film, and immersing the stretched film in a 1 to 4% boric acid aqueous solution at 30 to 40°C; a method of producing a polarizing film, which includes treating a polyvinyl alcohol film by means of a boric acid, uniaxially stretching the film 3 to 7 times, immersing the film in a 0.05 to 5% dichromatic dye aqueous solution at 30 to 40°C to adsorb a dye on the film, and drying the film at 80 to 100°C to perform heat fixing; and the like.

15 [0023] In the present invention, the protective film that is provided on a side of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less is disposed at an outermost edge of the liquid crystal display according to the present invention to significantly prevent reduction in functions of the polarizing film due to moisture and light leakage and egg-mura. In the present invention, the vapor transmissivity is not limited, but may be a value that is measured at 40°C under a relative humidity condition of 90%.

20 [0024] In the film has the vapor transmissivity of 100 g/m²Day or less, the smaller the vapor transmissivity the better. Furthermore, if the film has the vapor transmissivity of more than 100 g/m²Day, it is difficult to protect the polarizing film from moisture. In the case of the film that has the vapor transmissivity of 100 g/m²Day or less, the vapor transmissivity is preferably 0.1 to 50 g/m²Day, and more preferably 0.5 to 10 g/m²Day.

25 [0025] The type of film that has the vapor transmissivity of 100 g/m²Day or less is not limited as long as the film has the vapor transmissivity which is in the above-mentioned range and does not negatively affect functions of the polarizing plate and the liquid crystal display. Non-limiting examples of the film that has the vapor transmissivity of 100 g/m²Day or less include COP (cycloolefin polymer), COC (cycloolefin copolymer), PNB (polynorbornene), and PET (polyethylene terephthalate).

30 [0026] It is preferable that the thickness of the film that has the vapor transmissivity of 100 g/m²Day or less be in the range of 30 to 100 micrometers.

35 [0027] In an embodiment of the present invention, the film that is provided on the surface abutting the liquid crystal cell of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 1,500 g/m²Day is combined with the film that has the vapor transmissivity of 100 g/m²Day or less to desirably prevent light leakage and egg-mura of the liquid crystal display, and various types of adhesives such as an adhesive containing a solvent may be used when the first polarizing plate or the second polarizing plate and the liquid crystal cell are adhered to each other or when the polarizing film and the protective film are adhered to each other.

40 [0028] In another embodiment of the present invention, the film that is provided on the surface abutting the liquid crystal cell of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day is combined with the film that contains a UV absorbing agent added thereto or has a UV absorption ability due to a UV absorption layer and has the vapor transmissivity of 100 g/m²Day or less to ensure the above-mentioned effects.

45 [0029] It is preferable that the protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell has the vapor transmissivity of more than 1,500 g/m²Day and 5,000 g/m²Day or less.

50 [0030] Since the film that has the vapor transmissivity of more than 1,500 g/m²Day is used in conjunction with the film that has the very low vapor transmissivity, that is, the vapor transmissivity of 100 g/m²Day or less, if the vapor transmissivity is less than 1,500 g/m²Day, it is difficult to vaporize the solvent in the case where the adhesive containing the solvent is used. Thus, there is a problem in that adhesion strength is reduced. The film having the vapor transmissivity

of more than 1,500 g/m²Day may be used as the protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell to reduce a drying time of the adhesive, thus improving the productivity. In addition, since a drying process can be performed at low temperatures, it is possible to prevent problems such as reduction alignment stability or change of colors of the polarizing film that may occur during the drying at high temperatures. In the case where the film that has the vapor transmissivity less than 1,500 g/m²Day is used as the protective film of the polarizing film provided on the surface abutting the liquid crystal cell, since it is difficult to desirably dry the adhesive used to adhere the polarizing film and the protective film to each other, stains or traces may be formed due to the adhesive. Furthermore, if a retention time in an oven is increased in order to perform the desirable drying, the productivity is reduced, and if the film is left at high temperatures, optical properties are reduced.

[0031] Additionally, the vapor transmissivity of the film having the vapor transmissivity of more than 1,500 g/m²Day may be controlled to 5,000 g/m²Day or less to reduce curling (curling of the polarizing plate) which may occur due to different moisture transmissivities of two protective films that protect a single polarizing film.

[0032] In the case where the film that has the vapor transmissivity of 100 g/m²Day or less has the UV absorption ability, if the vapor transmissivity of the protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell is more than 200 g/m²Day, it is possible to prevent yellowing which may occur when the sunlight is radiated over a long period of time. Thus, desired properties of the polarizing plate are obtained. In this case, however, it is preferable that the vapor transmissivity of the protective film of the polarizing film provided on the surface abutting the liquid crystal cell be more than 1500 g/m²Day.

[0033] The type of protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell is not limited as long as the film has the vapor transmissivity which is in the above-mentioned range and does not negatively affect functions of the polarizing plate and the liquid crystal display. In the present invention, a polyester film, a polyolefin film, an acetyl cellulose film, a polycarbonate film, a polyvinyl alcohol film, a polyether sulfone film, a polyarylate film, a polyimide film, a polyamide imide film, a polyamide film, and the like may be used. In order to ensure desirable performance of the polarizing film, an acetate resin such as triacetyl cellulose is preferably used so that an appearance and a flatness of the film are excellent and the vapor transmissivity is easily controlled to be in the above-mentioned range.

[0034] It is preferable that the thickness of the protective film of the polarizing film that is provided on the surface abutting the liquid crystal cell be in the range of 30 to 100 micrometers.

[0035] In the present invention, the films that are used as the protective films of the first polarizing plate and the second polarizing plate may be subjected to surface treatment in order to improve adhesion strength to the polyvinyl alcohol polarizing film or the liquid crystal cell.

[0036] In the present invention, the adhesion of the protective film and the polyvinyl alcohol polarizing film and the adhesion of the polarizing plate and the liquid crystal cell may be performed by using an adhesive which is known in the related art. Non-limiting examples thereof include a UV-curable adhesive, a solvent adhesive, an aqueous adhesive, a thermosetting adhesive, and the like. It is preferable to use the solvent or aqueous adhesive in views of productivity. Specifically, the polyvinyl alcohol adhesive, the polyurethane adhesive, and the like may be used. Particularly, in the present invention, in order to prevent light leakage at high temperatures, it is preferable to use a hard type adhesive in the polarizing plate.

[0037] In the polarizing plate that includes the polarizing film and the protective film, when the polarizing film and the protective film are laminated with each other by using the above-mentioned adhesive and then dried, the moisture content is set to be in a predetermined range to improve heat resistance of the polarizing plate. It is preferable that the moisture content after the polarizing plate is dried is 1 to 2 wt% based on a total weight of the polarizing plate.

[0038] In the present invention, when the protective films of the first polarizing plate and the second polarizing plate are produced, various types of additives such as a UV absorbing agent, an anti-blocking agent, a lubricant, an antistatic agent, and a stabilizer may be used if necessary.

[0039] Particularly, it is preferable to add the UV absorbing agent to the film that has the vapor transmissivity of 100 g/m²Day or less and is used as the outer protective film of the first polarizing plate or the second polarizing plate. Specifically, in order to ensure reliability of the polarizing plate in respects to UV, that is, in order to ensure the same polarizing efficiency after a predetermined time, it is preferable that a layer for protecting the polarizing film from UV be provided between a UV light source such as a backlight lamp (BLU Lamp) or solar light and the polarizing film. This is because the color of the polarizing plate is changed as the color of the protective film is changed. In addition, if UV is radiated, since the alignment property of iodine molecules is poor in the polarizing film, a contrast ratio of the liquid crystal display may be reduced with time or the color sense thereof may be changed with time. If the UV protective layer is not provided, it is difficult to use the polarizing plate due to reduction in polarizing efficiency.

[0040] Accordingly, in the present invention, the UV absorbing agent may be added to the protective film that is provided between the solar light and the polarizing film and is disposed to be closest to an observer or the protective film that is provided between the backlight lamp and the polarizing film and has the vapor transmissivity of 100 g/m² Day or less among the protective films for protecting the polarizing films. Furthermore, the UV absorption layer may be formed on an upper surface or a lower surface of the film that has the vapor transmissivity of 100 g/m²Day or less, which will be

described below. For example, the UV absorbing agent may be applied on the film that has the vapor transmissivity of 100 g/m²Day or less to form the UV absorption layer. Alternatively, in the case where the antireflection layer or the hard coating layer is formed on the film that has the vapor transmissivity of 100 g/m²Day or less, the UV absorbing agent may be added to the layers. The UV absorbing agent may be added to the adhesive layer that is used to adhere the polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less to each other. If the outer protective film of each of the polarizing plates has excellent resistance to UV, even though the inner protective film of each of the polarizing plates has relatively low resistance to UV, the inner protective film insignificantly affects a change in color of the polarizing plate. Particularly, it is important to provide resistance to UV to the protective film of the polarizing film that is disposed to be closest to an observer of the liquid crystal display, that is, the protective film that is provided between the solar light and the polarizing film.

[0041] Furthermore, in the liquid crystal display according to the present invention, one or more layers that are selected from the group consisting of an antireflection layer, a low reflection coating layer, a luminance improvement layer, an antistatic coating layer, and a hard coating layer may be further provided on the film that is disposed at an outermost edge of the liquid crystal display and the vapor transmissivity of 100 g/m² Day or less. The antireflection layer, the low reflection coating layer, the luminance improvement layer, the antistatic coating layer, or the hard coating layer may be provided on the surface that is opposite to the backlight of the liquid crystal display. The antireflection layer, the luminance improvement layer, or the hard coating layer may be provided on the surface abutting the backlight of the liquid crystal display. The UV absorbing agent may be further added to the layers of the liquid crystal display that is closest to an observer.

[0042] Specifically, the antireflection layer or the low reflection coating layer functions to prevent an observer from being dazzled in respects to the liquid crystal display. For example, the film that has the vapor transmissivity of 100 g/m²Day or less may be subjected to antireflection or low reflection coating to form the antireflection layer or the low reflection coating layer. Examples of a coating solution include, but are not limited to a composition comprising silica, an acryl binder, etc. The antireflection layer is also called as a layer incurring haze.

[0043] The UV absorption layer acts as a UV protective layer between the polarizing film and the UV light source to prevent discoloring of the polarizing plate due to UV. The UV absorbing agent may be added to the protective film of the polarizing film, particularly, the protective film of the polarizing film of the liquid crystal display that is disposed to be closest to an observer to form the UV absorption layer described above, the UV absorption layer may be applied on the protective film of the polarizing film or on another functional layer that is disposed on the protective film to form the UV absorption layer, or the UV absorbing agent may be added during the production of another functional layer to form the UV absorption layer. Alternatively, the UV absorbing agent may be added to the adhesive layer that is used to adhere the PVA polarizing film and the protective film to each other to form the UV absorption layer.

[0044] The luminance improvement layer functions to improve luminance of light that is emitted from the backlight. The luminance improvement film may be adhered to the protective film of the polarizing film, particularly, the protective film of the polarizing film that is disposed close to the backlight by using a pressure sensitive adhesive (PSA), or in the case where the luminance improvement film has the vapor transmissivity of 100 g/m²Day or less, the luminance improvement film may be directly adhered to the polarizing film.

[0045] The antistatic coating layer functions to prevent generation of inferior liquid crystal display modules due to static electricity, and coating may be performed to reduce surface resistance, thereby preventing static electricity from occurring on the surface of the polarizing plate. A coating solution that contains polythiophene may be used to form the antistatic coating layer, but the component contained in the coating solution is not limited thereto.

[0046] The hard coating layer functions to improve resistance to scratches of the liquid crystal display and easily remove stains formed by pens or the like. For example, when the liquid crystal modules (LCM) are produced and then transported to a liquid crystal display set maker, the film that is interposed between the polarizing film and the backlight may come into contact with the backlight sheet, thus forming defects. The defects may be confirmed by a vibration test. After a liquid crystal module is prepared and a 1.5 g weight is put on the liquid crystal module and vibrated for 1 hour, the liquid crystal module is operated to confirm nonuniform luminance or stains. The above-mentioned problems may occur in the case where hardness of the film that has the vapor transmissivity of 100 g/m²Day or less is low in the liquid crystal display according to the present invention. In order to prevent the above-mentioned problems from occurring, it is preferable that the film that has the vapor transmissivity of 100 g/ m²Day or less be subjected to hard coating. This prevents damage to the film which has the vapor transmissivity of 100 g/m²Day or less and is disposed at an outermost edge of the liquid crystal display, for example, the cycloolefin film, due to the low hardness during a process of adhering the liquid crystal module to the backlight. For example, a coating solution that contains an acryl binder, silica, or the like may be applied on the film that has the vapor transmissivity of 100 g/m²Day or less to form the hard coating layer, but the types of material and process during the formation of the hard coating layer are not limited thereto.

[0047] Furthermore, in the liquid crystal display according to the present invention, the film that is provided on the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day and the luminance improvement film that is provided on the film having the vapor transmissivity of more than 200 g/m²Day may be further provided

between the polyvinyl alcohol polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less of the first polarizing plate or the second polarizing plate. It is preferable that the film having the vapor transmissivity of more than 200 g/m²Day have the vapor transmissivity of more than 1,500 g/m²Day.

5 [0048] The type of liquid crystal cell that is used in the liquid crystal display according to the present invention is not limited but may be a liquid crystal cell known in the related art. In the present invention, an IPS-, TN-, or VA-mode liquid crystal cell may be used.

[0049] The liquid crystal display according to the present invention may further include an optical compensation film between the first polarizing plate and the liquid crystal cell and/or between the second polarizing plate and the liquid crystal cell if necessary.

10 [0050] The present invention provides a polarizing plate that is useful to the above-mentioned liquid crystal display.

[0051] According to an embodiment of the present invention, a polarizing plate includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer that is provided on the upper or lower surface
15 of the film having the vapor transmissivity of 100 g/m²Day or less. It is preferable that the film having the vapor transmissivity of more than 200 g/m²Day have the vapor transmissivity of more than 1,500 g/m² Day.

[0052] In the polarizing plate, one or more layers that are selected from the group consisting of an antireflection layer, a low reflection coating layer, a luminance improvement layer, an antistatic coating layer, and a hard coating layer may be further provided between the film having the vapor transmissivity of 100 g/m²Day or less and the UV absorption layer
20 or on the upper surface of the UV absorption layer. A UV absorbing agent may be added to the layers that are disposed close to an observer observing the liquid crystal display. Furthermore, in the polarizing plate, a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day and a luminance improvement film that is provided on an upper surface of the film having the vapor transmissivity of more than 200 g/m²Day may be further provided between the polyvinyl alcohol polarizing film and the film having the vapor
25 transmissivity of 100 g/m²Day or less.

[0053] Specific embodiments of the present invention will be described in detail with reference to the drawings, but the scope of the present invention is not limited thereto.

[0054] The polarizing plate according to the present invention may have the structure shown in Fig. 5. Specifically, the polarizing plate shown in Fig. 5 includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface
30 of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer and an antireflection layer or a low reflection coating layer that are provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less. The polarizing plate may be disposed to close to an observer observing the liquid crystal display.

[0055] The polarizing plate according to the present invention may have the structure shown in Fig. 6. Specifically, the polarizing plate shown in Fig. 6 includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface
35 of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer and an antireflection layer or a hard coating layer that are provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less. The polarizing plate may be disposed to close to the
40 backlight of the liquid crystal display.

[0056] The polarizing plate according to the present invention may have the structure shown in Fig. 7. Specifically, the polarizing plate shown in Fig. 7 includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface
45 of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer and a luminance improvement film that are provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less. The polarizing plate may be disposed to close to the backlight of the liquid crystal display.

[0057] The polarizing plate according to the present invention may have the structure shown in Fig. 9. Specifically, the polarizing plate shown in Fig. 9 includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface
50 of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer and an antistatic coating layer that are provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less. The polarizing plate may be disposed to close to an observer observing
55 the liquid crystal display.

[0058] The polarizing plate according to the present invention may have the structure shown in Fig. 10. Specifically, the polarizing plate shown in Fig. 10 includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of 100 g/m²Day or less, a film that is

provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, and a UV absorption layer and a hard coating layer that are provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less. The polarizing plate may be disposed to close to an observer observing the liquid crystal display.

5 [0059] According to another embodiment of the present invention, a polarizing plate includes a polyvinyl alcohol polarizing film, a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day, a luminance improvement film that is provided on an upper surface of the film having the vapor transmissivity of more than 200 g/m²Day, a film that is provided on the luminance improvement film and has the vapor transmissivity of 100 g/m²Day or less, a UV absorption layer that is provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less, and a film that is provided on a lower surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day. The polarizing plate having the above-mentioned structure is shown in Fig. 8.

10 [0060] Elements that constitute the polarizing plate according to the present invention are the same as those of the liquid crystal display. The polarizing plate according to the present invention may further include an adhesive layer that is provided on the surface of the film that is in contact with the liquid crystal cell and has the vapor transmissivity of more than 200 g/m²Day.

15 [0061] Furthermore, an adhesive layer may be provided between the polarizing film and the protective film of the polarizing plate to adhere the polarizing film and the protective film to each other. In this connection, a UV absorbing agent may be added to the adhesive layer that is interposed between the polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less.

Mode for the Invention

25 [0062] A better understanding of the present invention may be obtained in light of the following Examples which are set forth to illustrate, but are not to be construed to limit the present invention.

EXAMPLES 1 and 2 AND COMPARATIVE EXAMPLES 1 to 4

30 [0063] The liquid crystal modules that included liquid crystal cells and polarizing plates containing the protective films shown in the following Table 1 provided on both sides of the liquid crystal cell were produced. The IPS liquid crystal cell which was filled with the liquid crystal having the pre-tilt angle of 2°, the dielectric anisotropy Δε of +7, and the birefringence Δn of 0.1 and had the cell gap of 3.4 μm was used as the liquid crystal cell of the liquid crystal module. The polyvinyl alcohol polarizing film was used as the polarizing film of the liquid crystal module. The polarizing film and the protective film were adhered and the polarizing plate and the liquid crystal cell were adhered by using the adhesive where polyvinyl alcohol was dissolved in water. In the case where the UV absorbing agent (2,2-dihydroxy-4-methoxybenzophenone) was contained, the UV absorbing agent was added to the coating layer of the outer protective film.

Table 1
[Table 1]

[Table]

Test conditions of Examples 1 and 2 and Comparative Examples 1 to 4					
	Outer protective film of first polarizing plate	Inner protective film of first polarizing plate	Inner protective film of second polarizing plate	Outer protective film of second polarizing plate	UV absorbing agent
Example 1	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	Contained in outer protective film

(continued)

Test conditions of Examples 1 and 2 and Comparative Examples 1 to 4					
	Outer protective film of first polarizing plate	Inner protective film of first polarizing plate	Inner protective film of second polarizing plate	Outer protective film of second polarizing plate	UV absorbing agent
Comparative Example 1	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	Contained in outer protective film
Comparative Example 2	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	Contained in outer protective film
Comparative Example 3	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	Contained in outer protective film
Comparative Example 4	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	Contained in outer protective film
Example 2	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	TAC (vapor transmissivity 2400 g/m ² Day, moisture absorptivity 3.9%, and thickness 80 μm)	COP (vapor transmissivity 5 g/m ² Day, moisture absorptivity 0.1% or less, and thickness 60 μm)	None

[0064] The liquid crystal modules that were produced in Example 1 and Comparative Example 1 were left in a 80% chamber at 50°C for 72 hours and then discharged from the chamber. Four corners of the liquid crystal cell in the black mode state at normal temperature and the outskirts thereof were observed by the naked eye in views of a difference in luminance to evaluate prevention of light leakage. The procedures were repeated twice in respects to the liquid crystal module of Example 1 and three times in respects to the liquid crystal module of Comparative Example 1. The evaluation results are shown in Fig. 11.

[0065] The liquid crystal modules that were produced in Examples 1 and 2 and Comparative Examples 2 to 4 were left in a 80% chamber at 50°C for 24 hours and then discharged from the chamber. Four corners of the liquid crystal cell in the black mode state at normal temperature and the outskirts thereof were observed by the naked eye in views of a difference in luminance to evaluate prevention of light leakage. The evaluation results are shown in Fig. 12.

[0066] The liquid crystal modules that were produced in Examples 1 and 2 were left in a 80% chamber at 50°C for 240 hours and then discharged from the chamber. Four corners of the liquid crystal cell in the black mode state at normal temperature and the outskirts thereof were observed by the naked eye in views of a difference in luminance to evaluate

prevention of light leakage. The evaluation results are shown in Fig. 13.

[0067] In Comparative Examples 1 to 4, the light leakage was observed immediately after the liquid crystal modules were discharged from the chambers, and light leakage were growing worse at normal temperature. However, in Examples 1 and 2, even though the liquid crystal modules were left at normal temperature for 6 hours, the light leakage was not observed.

[0068] In addition, an antireflection layer (AG coating) was formed on a COP layer of each of the liquid crystal modules that were produced in Examples 1 and 2 and Comparative Examples 1 to 4, UV was radiated on the COP layer on which the antireflection layer was provided by using a UVA-340 lamp as the UV lamp for 150 hours, and the polarizing plate was observed. The yellowing was evaluated by using a UV-VIS Spectrophotometer (trade name: model U-3310, manufactured by Hitachi, Inc.). In this case, the yellowing did not occurred in Examples 1 and Comparative Examples 1 to 4, but yellowing occurred in Example 2.

[0069] Tc (cross transmissivity) and Ts (simple transmissivity) of each of the liquid crystal modules of Examples 1 and 2 were evaluated before and after radiation of UV, and the results are shown in Figs. 14 and 15. Tc (cross transmissivity) and Ts (simple transmissivity) were obtained by using the following procedure. A sample was perpendicularly fixed in respects to an optical axis of the spectrophotometer, and measurement was performed when the absorption axis of the sample was 45° and 135°. The measurement wavelength was in the range of 400 to 700 nm, and the measurement was performed at intervals of 10 nm to obtain T₄₅(λ), T₁₃₅(λ), TC₄₅(λ), and TC₁₃₅(λ) (see Fig. 16). Tc (cross transmissivity) and Ts (simple transmissivity) were calculated by using the obtained values based on the luminosity correction according to a 2° visual field XYZ system of the JIS Z 8701.

simple transmissivity :

$$T_s(\%) = Y = K \times \sum \{ S(\lambda) \times y(\lambda) \times (T_{45}(\lambda) + T_{135}(\lambda)) / 2 \} \quad (\Sigma = 400 \text{ to } 700 \text{ nm})$$

cross transmissivity :

$$T_c(\%) = K \times \sum \{ S(\lambda) \times y(\lambda) \times TC(\lambda) \} \quad (\Sigma = 400 \text{ to } 700 \text{ nm})$$

K : correction coefficient (0.09395)

S(λ) : relative spectral distribution of light source

y(λ) : metamerism coefficient

Table 2
[Table 2]

[Table]

Evaluation results of Examples 1 and 2 and Comparative Examples 1 to 4		
	Light leakage	Yellowing
Example 1	None	None
Comparative Example 1	Observed	None
Comparative Example 2	Observed	None
Comparative Example 3	Observed	None
Comparative Example 4	Observed	None
Example 2	None	Observed

[0070] From the results of Comparative Examples and Examples, it can be seen that in the case where the protective film of the polarizing film having the vapor transmissivity of 100 g/m²Day or less is disposed at an outermost edge of the liquid crystal display and the film having the vapor transmissivity of more than 1,500 g/m²Day is used as the protective film provided on another side of the polarizing film, light leakage is avoided. Furthermore, in the case where the protective film does not contain the UV absorbing agent, yellowing is prevented only when the UV absorbing agent is added to the film.

EXAMPLE 3 and COMPARATIVE EXAMPLE 5

[0071] The liquid crystal modules were produced by using the same procedure as Example 2, except that the polarizing plate contained the protective film shown in the following Table 3, and adhesive stains and traces were observed. After the polarizing plate was provided on the backlight unit (BLU) in an orthogonal state, a transmission inspection was performed to observe the adhesive stains by the naked eye, and a reflection inspection was performed to observe the traces by reflecting light emitted from a fluorescent lamp. The results are described in the following Table 3.

Table 3
[Table 3]

[Table]

Test conditions and results of Example 3 and Comparative Example 5				
	Outer protective films of first and second polarizing plates	Inner protective films of first and second polarizing plates	Adhesive stain	Trace
Example 3	COP (vapor transmissivity 3 g/m ² Day and thickness 60 μm)	TAC (vapor transmissivity 2400 g/m ² Day and thickness 80 μm)	8/20	2/20
Comparative Example 5	COP (vapor transmissivity 3 g/m ² Day and thickness 60 μm)	TAC (vapor transmissivity 1200 g/m ² Day and thickness 80 μm)	4/20	0/20

[0072] From the results of Table 3, it can be seen that in the case where the film having the vapor transmissivity of more than 1500 g/m²Day is used as the inner protective film like Example 3, Example 3 is better than Comparative Example 5 in terms of the adhesive stains and the traces.

EXAMPLE 4

[0073] In order to confirm degradation of optical properties in the case where the polarizing film was left at high temperatures to dry the adhesive, the following experiment was performed. After the polyvinyl alcohol polarizing film was attached to the glass substrate, optical properties such as Tc (cross transmissivity) and Ts (simple transmissivity) were measured before and after the resulting substrate was left at 80°C for 15 hours, and color values a and b were calculated. The color values were calculated by using the following procedure. First, the transmissivity of the polarizing plate at the absorption axis angle of 45° was measured to obtain X and Z values based on the luminosity correction (400 to 700 nm and 10 nm interval) according to a 2° visual field XYZ system of the JIS Z 8701.

$$X = K \times \sum \{ S(\lambda) \times x(\lambda) \times (T_{45}(\lambda) + T_{135}(\lambda)) / 2 \} \quad (\Sigma = 400 \text{ to } 700 \text{ nm})$$

$$Z = K \times \sum \{ S(\lambda) \times z(\lambda) \times (T_{45}(\lambda) + T_{135}(\lambda)) / 2 \} \quad (\Sigma = 400 \text{ to } 700 \text{ nm})$$

K = correction coefficient (0.09395)
 S(λ) : relative spectral distribution of light source
 x(λ) and z(λ) : metamerism coefficient
 Y : simple transmissivity (Ts)

[0074] The color values a and b were obtained by means of the following Equations using the obtained X and Z values.

$$a = 17.5 \times (1.02X - Y) / Y^{1/2}$$

$$b = 7 \times (Y - 0.847Z) / Y^{1/2}$$

Table 4

[Table 4]

[Table]

	Ts	Tc	a	b
Before heat resistant treatment	42.33	0.00311	-1.55	4.27
After heat resistant treatment	43.07	0.00934	-1.97	5.38

[0075] As shown in Table 4, optical properties are reduced in the case where the polarizing film was left at high temperatures.

[0076] In the case where the film having the vapor transmissivity of 1500 g/m²Day or less is used as the inner protective film of the polarizing film, the adhesive that is used to adhere the polarizing film and the protective film to each other is not easily dried. Thus, if the drying temperature of the adhesive is increased to desirably dry the adhesive, the optical properties of the polarizing film are reduced.

Claims

1. A polarizing plate for use with a liquid crystal cell to form a liquid crystal display comprising:

a polyvinyl alcohol polarizing film;

a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and

a film that is provided on a lower surface of the polyvinyl alcohol polarizing film, wherein the film provided on an upper surface of the polyvinyl alcohol polarizing film has the vapor transmissivity of 100 g/m² Day or less, the film provided on a lower surface of the polyvinyl alcohol polarizing film has the vapor transmissivity of more than 200 g/m² Day, wherein the upper surface of the polyvinyl alcohol polarizing film is that disposed in the direction to an outermost edge of the liquid crystal display; and the lower surface of the polyvinyl alcohol polarizing film is that abutting the liquid crystal cell, the polarizing plate further comprises a UV absorption layer that is provided on the upper or lower surface of the film having the vapor transmissivity of 100 g/m²Day or less, and a pressure sensitive adhesive layer that is provided on the film having the vapor transmissivity of more than 200 g/m² Day,

the film having the vapor transmissivity of 100 g/m²Day or less is a film that is made of a material selected from the group consisting of COP (cycloolefin polymer), COC (cycloolefin copolymer), PNB (polynorbornene), and PET (polyethylene terephthalate), and

the film having the vapor transmissivity of more than 200 g/m²Day is selected from the group consisting of a polyester film, a polyolefin film, an acetyl cellulose film, a polycarbonate film, a polyvinyl alcohol film, a polyether sulfone film, a polyarylate film, a polyimide film, a polyamide imide film, and a polyamide film.

2. The polarizing plate according to claim 1, wherein one or more layers that are selected from the group consisting of an antireflection layer, a low reflection coating layer, a luminance improvement layer, an antistatic coating layer, and a hard coating layer are further provided on the upper surface of the film having the vapor transmissivity of 100 g/m²Day or less or an upper surface of the UV absorption layer.

3. The polarizing plate according to claim 1, further comprising:

a film that is provided on an upper surface of the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day and a luminance improvement film that is provided on an upper surface of the film having the vapor transmissivity of more than 200 g/m²Day between the polyvinyl alcohol polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less.

4. The polarizing plate according to claim 1, wherein a moisture content of the polarizing plate is 1 to 2 wt% based on a total weight of the polarizing plate.

5. A liquid crystal display that includes a liquid crystal cell and a first polarizing plate according to any of claims 1 to 4 and a second polarizing plate according to any of claims 1 to 4 respectively provided on each side of the liquid crystal cell.

6. The liquid crystal display according to claim 5, wherein the film having the vapor transmissivity of more than 200 g/m²Day is a triacetyl cellulose film.
- 5 7. The liquid crystal display according to claim 5, wherein the first polarizing plate or the second polarizing plate and the liquid crystal cell, or the polyvinyl alcohol polarizing film and the protective film are adhered to each other by using a solvent adhesive or an aqueous adhesive.
- 10 8. The liquid crystal display according to claim 5, wherein the protective film of at least one polarizing plate of the first polarizing plate and the second polarizing plate contains one or more additives selected from the group consisting of a UV absorbing agent, an anti-blocking agent, a lubricant, an antistatic agent, and a stabilizer.
- 15 9. The liquid crystal display according to claim 5, wherein one or more layers that are selected from the group consisting of an antireflection layer, a low reflection coating layer, a UV absorption layer, a luminance improvement layer, an antistatic coating layer, and a hard coating layer are further provided on the film having the vapor transmissivity of 100 g/m²Day or less of at least one polarizing plate of the first polarizing plate and the second polarizing plate.
- 20 10. The liquid crystal display according to claim 5, further comprising:
a film that is provided on the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day and a luminance improvement film that is provided on the film having the vapor transmissivity of more than 200 g/m²Day between the polyvinyl alcohol polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less of at least one polarizing film of the first polarizing plate and the second polarizing plate.
- 25 11. The liquid crystal display according to claim 5, wherein an adhesive layer is provided between the polarizing film and the protective film of at least one polarizing plate of the first polarizing plate and the second polarizing plate and the adhesive layer contains a UV absorbing agent.
- 30 12. The liquid crystal display according to claim 5, wherein each moisture content of the first polarizing plate and the second polarizing plate is 1 to 2 wt% based on a total weight of the polarizing plate.
- 35 13. A liquid crystal display according to any of claims 5 - 12, wherein the protective films that are provided on surfaces abutting the liquid crystal cell of the first polarizing plate and the second polarizing plate each have the vapor transmissivity of more than 1,500 g/m²Day.
- 40 14. The liquid crystal display according to claim 13, wherein the film having the vapor transmissivity of more than 1,500 g/m²Day is a triacetyl cellulose film.
- 45 15. The liquid crystal display according to claim 13, wherein the first polarizing plate or the second polarizing plate and the liquid crystal cell, or the polyvinyl alcohol polarizing film and the protective film are adhered to each other by using a solvent adhesive or an aqueous adhesive.
- 50 16. The liquid crystal display according to claim 13, wherein the protective film of at least one polarizing plate of the first polarizing plate and the second polarizing plate contains one or more additives selected from the group consisting of a UV absorbing agent, an anti-blocking agent, a lubricant, an antistatic agent, and a stabilizer.
- 55 17. The liquid crystal display according to claim 13, wherein each of the films having the vapor transmissivity of 100 g/m²Day or less of the first polarizing plate and the second polarizing plate contains the UV absorbing agent.
18. The liquid crystal display according to claim 13, wherein one or more layers that are selected from the group consisting of an antireflection layer, a low reflection coating layer, a UV absorption layer, a luminance improvement layer, an antistatic coating layer, and a hard coating layer are further provided on the film having the vapor transmissivity of 100 g/m²Day or less of at least one polarizing plate of the first polarizing plate and the second polarizing plate and .
19. The liquid crystal display according to claim 18, wherein at least one layer of the layers that are provided on the film having the vapor transmissivity of 100 g/m²Day or less contains a UV absorbing agent.
20. The liquid crystal display according to claim 18, wherein the UV absorption layer is provided on each of the films having the vapor transmissivity of 100 g/m²Day or less of the first polarizing plate and the second polarizing plate.

21. The liquid crystal display according to claim 13, further comprising:

a film that is provided on the polyvinyl alcohol polarizing film and has the vapor transmissivity of more than 200 g/m²Day and a luminance improvement film that is provided on the film having the vapor transmissivity of more than 200 g/m²Day between the polyvinyl alcohol polarizing film and the film having the vapor transmissivity of 100 g/m²Day or less of at least one polarizing film of the first polarizing plate and the second polarizing plate.

22. The liquid crystal display according to claim 13, wherein an adhesive layer is provided between the polarizing film and the protective film of at least one polarizing plate of the first polarizing plate and the second polarizing plate and the adhesive layer contains a UV absorbing agent.

23. The liquid crystal display according to claim 13, wherein each moisture content of the first polarizing plate and the second polarizing plate is 1 to 2 wt% based on a total weight of the polarizing plate.

Patentansprüche

1. Polarisationsplatte zur Verwendung mit einer Flüssigkristallzelle, um ein Flüssigkristalldisplay zu bilden, umfassend:

einen Polyvinylalkoholpolarisationsfilm;
 einen Film, der auf einer oberen Fläche des Polyvinylalkoholpolarisationsfilms bereitgestellt ist, und
 einen Film, der auf einer unteren Fläche des Polyvinylalkoholpolarisationsfilms bereitgestellt ist,
 wobei der Film, der auf einer oberen Fläche des Polyvinylalkoholpolarisationsfilms bereitgestellt ist, das Dampfdurchlassvermögen von 100 g/m² Tag oder weniger aufweist,
 der Film, der auf einer unteren Fläche des Polyvinylalkoholpolarisationsfilms bereitgestellt ist, das Dampfdurchlassvermögen von mehr als 200 g/m² Tag aufweist,
 wobei die obere Fläche des Polyvinylalkoholpolarisationsfilms diejenige ist, die in der Richtung zu einer äußersten Kante des Flüssigkristalldisplays angeordnet ist; und die untere Fläche des Polyvinylalkoholpolarisationsfilms diejenige ist, die an die Flüssigkristallzelle anstößt,
 wobei die Polarisationsplatte ferner eine UV-Absorptionsschicht umfasst, die auf der oberen oder unteren Fläche des Films mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger bereitgestellt ist,
 und eine Haftklebstoffschicht, die auf dem Film mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag bereitgestellt ist,
 wobei der Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger ein Film ist, der aus einem Material ausgewählt aus der Gruppe bestehend aus COP (Cycloolefinpolymer), COC (Cycloolefincopolymer), PNB (Polynorbornen) und PET (Polyethylenterephthalat) hergestellt ist, und
 der Film mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag ausgewählt ist aus der Gruppe bestehend aus einem Polyesterfilm, einem Polyolefinfilm, einem Acetylcellulosefilm, einem Polycarbonatfilm, einem Polyvinylalkoholfilm, einem Polyethersulfonfilm, einem Polyarylatfilm, einem Polyimidfilm, einem Polyamidimidfilm und einem Polyamidfilm.

2. Polarisationsplatte nach Anspruch 1, wobei eine oder mehrere Schichten, die ausgewählt sind aus der Gruppe bestehend aus einer Antireflexionsschicht, einer Niedrigreflexionsbeschichtungsschicht, einer Luminanzverbesserungsschicht, einer antistatischen Beschichtungsschicht und einer Hartbeschichtungsschicht ferner auf der oberen Oberfläche des Films mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger oder einer oberen Fläche der UV-Absorptionsschicht bereitgestellt sind.

3. Polarisationsplatte nach Anspruch 1, weiter umfassend:

einen Film, der auf einer oberen Fläche des Polyvinylalkoholpolarisationsfilms bereitgestellt ist und das Dampfdurchlassvermögen von mehr als 200 g/m² Tag aufweist, und einen Luminanzverbesserungsfilm, der auf einer oberen Fläche des Films mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag zwischen dem Polyvinylalkoholpolarisationsfilm und dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger bereitgestellt ist.

4. Polarisationsplatte nach Anspruch 1, wobei ein Feuchtigkeitsgehalt der Polarisationsplatte 1 bis 2 Gew.-%, basierend auf einem Gesamtgewicht der Polarisationsplatte, ist.

EP 2 047 306 B1

5. Flüssigkristalldisplay, das eine Flüssigkristallzelle und eine erste Polarisationsplatte nach einem der Ansprüche 1 bis 4 und eine zweite Polarisationsplatte nach einem der Ansprüche 1 bis 4, bereitgestellt auf jeder Seite der Flüssigkristallzelle, einschließt.
- 5 6. Flüssigkristalldisplay nach Anspruch 5, wobei der Film mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag ein Triacetylcellulosefilm ist.
7. Flüssigkristalldisplay nach Anspruch 5, wobei die erste Polarisationsplatte oder die zweite Polarisationsplatte und die Flüssigkristallzelle, oder der Polyvinylalkoholpolarisationsfilm und der Schutzfilm aneinander unter Verwendung eines Lösungsmittelklebstoffs oder eines wässrigen Klebstoffs angefügt sind.
- 10 8. Flüssigkristalldisplay nach Anspruch 5, wobei der Schutzfilm wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte ein oder mehrere Additive enthält, die ausgewählt sind aus der Gruppe bestehend aus einem UV-Absorptionsmittel, einem Anti-Blockiermittel, einem Schmiermittel, einem Antistatikmittel und einem Stabilisator.
- 15 9. Flüssigkristalldisplay nach Anspruch 5, wobei eine oder mehrere Schichten, die ausgewählt sind aus der Gruppe bestehend aus einer Antireflexionsschicht, einer Niederreflexionsbeschichtungsschicht, einer UV-Absorptionsschicht, einer Luminanzverbesserungsschicht, einer antistatischen Beschichtungsschicht und einer Hartbeschichtungsschicht ferner bereitgestellt sind auf dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte.
- 20 10. Flüssigkristalldisplay nach Anspruch 5, weiter umfassend:
- 25 einen Film, der auf dem Polyvinylalkoholpolarisationsfilm bereitgestellt ist und das Dampfdurchlassvermögen von mehr als 200 g/m² Tag umfasst, und einen Luminanzverbesserungsfilm, der auf dem Film mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag zwischen den Polyvinylalkoholpolarisationsfilm und dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger wenigstens eines Polarisationsfilms der ersten Polarisationsplatte und der zweiten Polarisationsplatte bereitgestellt ist.
- 30 11. Flüssigkristalldisplay nach Anspruch 5, wobei eine Haftschiicht bereitgestellt ist zwischen dem Polarisationsfilm und dem Schutzfilm wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte, und wobei die Haftschiicht ein UV-Absorptionsmittel enthält.
- 35 12. Flüssigkristalldisplay nach Anspruch 5, wobei jeder Feuchtigkeitsgehalt der ersten Polarisationsplatte und der zweiten Polarisationsplatte 1 bis 2 Gew.-%, basierend auf einem Gesamtgewicht der Polarisationsplatte, ist.
- 40 13. Flüssigkristalldisplay nach einem der Ansprüche 5 bis 12, wobei die Schutzfilme, die auf Oberflächen bereitgestellt sind, die an die Flüssigkristallzelle der ersten Polarisationsplatte und der zweiten Polarisationsplatte anstoßen, jeweils das Dampfdurchlassvermögen von mehr als 1.500 g/m² Tag aufweisen.
14. Flüssigkristalldisplay nach Anspruch 13, wobei der Film mit dem Dampfdurchlassvermögen von mehr als 1.500 g/m² Tag ein Triacetylcellulosefilm ist.
- 45 15. Flüssigkristalldisplay nach Anspruch 13, wobei die erste Polarisationsplatte oder die zweite Polarisationsplatte und die Flüssigkristallzelle, oder der Polyvinylalkohlpolarisationsfilm und der Schutzfilm, aneinander durch Verwendung eines Lösungsmittelklebstoffs oder eines wässrigen Klebstoffs anhaften.
- 50 16. Flüssigkristalldisplay nach Anspruch 13, wobei der Schutzfilm wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte ein oder mehrere Additive enthält, die ausgewählt sind aus der Gruppe bestehend aus einem UV-Absorptionsmittel, einem Anti-Blockiermittel, einem Schmiermittel, einem Antistatikmittel und einem Stabilisator.
- 55 17. Flüssigkristalldisplay nach Anspruch 13, wobei jeder der Filme mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger der ersten Polarisationsplatte und der zweiten Polarisationsplatte das UV-Absorptionsmittel enthält.
18. Flüssigkristalldisplay nach Anspruch 13, wobei eine oder mehrere Schichten, die ausgewählt sind aus der Gruppe

bestehend aus einer Antireflexionsschicht, einer Niederreflexionsbeschichtungsschicht, einer UV-Absorptionsschicht, einer Luminanzverbesserungsschicht, einer antistatischen Beschichtungsschicht und einer Hartbeschichtungsschicht ferner bereitgestellt sind auf dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte.

5 19. Flüssigkristalldisplay nach Anspruch 18, wobei wenigstens eine Schicht der Schichten, die auf dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger bereitgestellt sind, ein UV-Absorptionsmittel enthält.

10 20. Flüssigkristalldisplay nach Anspruch 18, wobei die UV-Absorptionsschicht auf jeden der Filme mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger der ersten Polarisationsplatte und der zweiten Polarisationsplatte bereitgestellt ist.

21. Flüssigkristalldisplay nach Anspruch 13, weiter umfassend:

15 einen Film, der auf dem Polyvinylalkoholpolarisationsfilm bereitgestellt ist und das Dampfdurchlassvermögen von mehr als 200 g/m² Tag aufweist, und einen Luminanzverbesserungsfilm, der auf dem Film mit dem Dampfdurchlassvermögen von mehr als 200 g/m² Tag zwischen dem Polyvinylalkoholpolarisationsfilm und dem Film mit dem Dampfdurchlassvermögen von 100 g/m² Tag oder weniger wenigstens eines Polarisationsfilms der ersten Polarisationsplatte und der zweiten Polarisationsplatte bereitgestellt ist.

20 22. Flüssigkristalldisplay nach Anspruch 13, wobei eine Haftschrift zwischen dem Polarisationsfilm und dem Schutzfilm wenigstens einer Polarisationsplatte der ersten Polarisationsplatte und der zweiten Polarisationsplatte bereitgestellt ist und die Haftschrift ein UV-Absorptionsmittel enthält.

25 23. Flüssigkristalldisplay nach Anspruch 13, wobei jeder Feuchtigkeitsgehalt der ersten Polarisationsplatte und der zweiten Polarisationsplatte 1 bis 2 Gew.-%, basierend auf einem Gesamtgewicht der Polarisationsplatte, ist.

Revendications

30 1. Une plaque polarisante destinée à être utilisée avec une cellule de cristaux liquides pour former un écran à cristaux liquides comprenant :

un film polarisant d'alcool de polyvinyle ;

35 un film qui est fourni sur une surface supérieure du film polarisant d'alcool de polyvinyle et

un film qui est fourni sur une surface inférieure du film polarisant d'alcool de polyvinyle,

où le film fourni sur une surface supérieure du film polarisant d'alcool de polyvinyle dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour,

40 le film fourni sur une surface inférieure du film polarisant d'alcool de polyvinyle dont la transmissivité de vapeur est supérieure à 200 g/m² par jour,

où la surface supérieure du film polarisant d'alcool de polyvinyle est celle qui est disposée dans le sens d'un bord extrême de l'écran à cristaux liquides ; et la surface inférieure du film polarisant d'alcool de polyvinyle est celle qui aboute la cellule de cristaux liquides,

45 la plaque polarisante comprend en outre une couche d'absorption des UV qui est fournie sur la surface supérieure ou inférieure du film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour, et

une couche adhésive sensible à la pression qui est fournie sur le film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour,

le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour est un film qui est fait dans un matériau sélectionné dans le groupe constitué par COP (polymère de cyclooléfine), COC (copolymère de cyclooléfine), PNB (polynorbornène) et PET (téréphtalate de polyéthylène), et

50 le film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour est sélectionné dans le groupe constitué par un film de polyester, un film de polyoléfine, un film de cellulose d'acétyle, un film de polycarbonate, un film d'alcool de polyvinyle, un film de sulfone de polyéther, un film de polyarylate, un film de polyimide, un film de polyamide imide et un film de polyamide.

55 2. La plaque polarisante selon la revendication 1, où une ou plusieurs couches qui sont sélectionnées dans le groupe constitué par une couche antireflet, une couche de revêtement faiblement réfléchissant, une couche d'amélioration de luminance, une couche de revêtement antistatique et une couche de revêtement dur sont également fournies

sur la surface supérieure du film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour ou une surface supérieure de la couche d'absorption des UV.

3. La plaque polarisante selon la revendication 1, comprenant en outre :

un film qui est fourni sur une surface supérieure du film polarisant d'alcool de polyvinyle et dont la transmissivité de vapeur est supérieure à 200 g/m² par jour et un film d'amélioration de luminance qui est fourni sur une surface supérieure du film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour entre le film polarisant d'alcool de polyvinyle et le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour.

4. La plaque polarisante selon la revendication 1, où une teneur en humidité de la plaque polarisante est comprise entre 1 et 2% en poids sur la base d'un poids total de la plaque polarisante.

5. Un écran à cristaux liquides qui inclut une cellule de cristaux liquides et une première plaque polarisante selon l'une quelconque des revendications 1 à 4 et une deuxième plaque polarisante selon l'une quelconque des revendications 1 à 4 fournies respectivement sur chaque côté de la cellule de cristaux liquides.

6. L'écran à cristaux liquides selon la revendication 5, où le film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour est un film de cellulose triacétyle.

7. L'écran à cristaux liquides selon la revendication 5, où la première plaque polarisante ou la deuxième plaque polarisante et la cellule de cristaux liquides, ou le film polarisant d'alcool de polyvinyle et le film protecteur sont collés l'une à l'autre à l'aide d'un adhésif solvant ou d'un adhésif aqueux.

8. L'écran à cristaux liquides selon la revendication 5, où le film protecteur d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante contient un ou plusieurs additifs sélectionnés dans le groupe constitué par un agent absorbant les UV, un agent anti-bloquant, un lubrifiant, un agent antistatique et un stabilisant.

9. L'écran à cristaux liquides selon la revendication 5, où une ou plusieurs couches qui sont sélectionnées dans le groupe constitué par une couche antireflet, une couche de revêtement faiblement réfléchissant, une couche d'absorption des UV, une couche d'amélioration de luminance, une couche de revêtement antistatique et une couche de revêtement dur sont également fournies sur le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante.

10. L'écran à cristaux liquides selon la revendication 5, comprenant en outre :

un film qui est fourni sur le film polarisant d'alcool de polyvinyle et dont la transmissivité de vapeur est supérieure à 200 g/m² par jour et un film d'amélioration de luminance qui est fourni sur le film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour entre le film polarisant d'alcool de polyvinyle et le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour d'un ou de plusieurs films polarisants de la première plaque polarisante et la deuxième plaque polarisante.

11. L'écran à cristaux liquides selon la revendication 5, où une couche adhésive est fournie entre le film polarisant et le film protecteur d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante et la couche adhésive contient un agent absorbant les UV.

12. L'écran à cristaux liquides selon la revendication 5, où chaque teneur en humidité de la première plaque polarisante et de la deuxième plaque polarisante est comprise entre 1 et 2% en poids sur la base d'un poids total de la plaque polarisante.

13. Un écran à cristaux liquides selon l'une quelconque des revendications 5 - 12, où les films protecteurs qui sont fournis sur des surfaces qui aboutent la cellule de cristaux liquides de la première plaque polarisante et la deuxième plaque polarisante chacune dont la transmissivité de vapeur est supérieure à 1500 g/m² par jour.

14. L'écran à cristaux liquides selon la revendication 13, où le film dont la transmissivité de vapeur est supérieure à

1500 g/m² par jour est un film de cellulose triacétyle.

- 5
15. L'écran à cristaux liquides selon la revendication 13, où la première plaque polarisante ou la deuxième plaque polarisante et la cellule de cristaux liquides, ou le film polarisant d'alcool de polyvinyle et le film protecteur sont collés l'un à l'autre à l'aide d'un adhésif solvant ou d'un adhésif aqueux.
- 10
16. L'écran à cristaux liquides selon la revendication 13, où le film protecteur d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante contient un ou plusieurs additifs sélectionnés dans le groupe constitué par un agent absorbant les UV, un agent anti-bloquant, un lubrifiant, un agent antistatique et un stabilisant.
- 15
17. L'écran à cristaux liquides selon la revendication 13, où chacun des films dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour de la première plaque polarisante et de la deuxième plaque polarisante contient l'agent absorbant les UV.
- 20
18. L'écran à cristaux liquides selon la revendication 13, où une ou plusieurs couches qui sont sélectionnées dans le groupe constitué par une couche antireflet, une couche de revêtement faiblement réfléchissant, une couche d'absorption des UV, une couche d'amélioration de luminance, une couche de revêtement antistatique et une couche de revêtement dur sont également fournies sur le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante et.
- 25
19. L'écran à cristaux liquides selon la revendication 18, où une ou plusieurs des couches qui sont fournies sur le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour contiennent un agent absorbant les UV.
- 30
20. L'écran à cristaux liquides selon la revendication 18, où la couche d'absorption des UV est fournie sur chacun des films dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour de la première plaque polarisante et la deuxième plaque polarisante.
- 35
21. L'écran à cristaux liquides selon la revendication 13, comprenant en outre :
- un film qui est fourni sur le film polarisant d'alcool de polyvinyle et dont la transmissivité de vapeur est supérieure à 200 g/m² par jour et un film d'amélioration de luminance qui est fourni sur le film dont la transmissivité de vapeur est supérieure à 200 g/m² par jour entre le film polarisant d'alcool de polyvinyle et le film dont la transmissivité de vapeur est égale ou inférieure à 100 g/m² par jour d'au moins un film polarisant, soit la première plaque polarisante, soit la deuxième plaque polarisante.
- 40
22. L'écran à cristaux liquides selon la revendication 13, où une couche adhésive est fournie entre le film polarisant et le film protecteur d'au moins une plaque polarisante, soit la première plaque polarisante, soit la deuxième plaque polarisante et la couche adhésive contient un agent absorbant les UV.
- 45
23. L'écran à cristaux liquides selon la revendication 13, où chaque teneur en humidité de la première plaque polarisante et de la deuxième plaque polarisante est comprise entre 1 et 2% en poids sur la base d'un poids total de la plaque polarisante.
- 50
- 55

EP 2 047 306 B1

[Fig. 1]

TAC
PVA
TAC
PSA

[Fig. 2]

TAC
PVA
TAC
PSA
LIQUID CRYSTAL CELL
PSA
TAC
PVA
TAC

[Fig. 3]

TAC
PVA
COP
PSA
LIQUID CRYSTAL CELL
PSA
COP
PVA
TAC

[Fig. 4]

FILM 1 HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS
PVA
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 1,500 G/M ² DAY
PSA
LIQUID CRYSTAL CELL
PSA
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 1,500 G/M ² DAY
PVA
FILM 2 HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS

[Fig. 5]

REFLECTION PREVENTION LAYER OR LOW REFLECTION COATING LAYER
UV ABSORPTION LAYER
FILM HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)

[Fig. 6]

REFLECTION PREVENTION LAYER OR HARD COATING LAYER
UV ABSORPTION LAYER
FILM HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)

[Fig. 7]

LUMINANCE IMPROVEMENT FILM
UV ABSORPTION LAYER
FILM HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)

[Fig. 8]

UV ABSORPTION LAYER
FILM HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS
LUMINANCE IMPROVEMENT FILM
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)


[Fig. 9]

ANTISTATIC COATING LAYER
UV ABSORPTION LAYER
FILM 1 HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)

[Fig. 10]

HARD COATING LAYER
UV ABSORPTION LAYER
FILM 1 HAVING VAPOR TRANSMISSIVITY OF 100 G/M ² DAY OR LESS
PVA(POLARIZING FILM)
FILM HAVING VAPOR TRANSMISSIVITY OF MORE THAN 200 G/M ² DAY
PSA(ADHESIVE)

[Fig. 11]




[Fig. 12]

Light leakage observation while polarizer is left at normal temperature after stored at 50°C and 80% for 24 hours				
Time	0H	1H	3H	6H
Comparative Example 2				
Comparative Example 3				
Comparative Example 4				
Example 2				
Example 1				


[Fig. 13]

Light leakage observation while polarizer is left at normal temperature after stored at 50°C and 80% for 240 hours			
	0H	1H	3H
Example 1			
Example 2			

[Fig. 14]



[Fig. 15]



[Fig. 16]

SECTION	SIMPLE		PARALLEL		CROSS	
POSITION OF SAMPLE						
ANGLE OF ABSORPTION AXIS						
SIGN	$T_{45}(\lambda)$	$T_{135}(\lambda)$	$TP_{45}(\lambda)$	$TP_{135}(\lambda)$	$TC_{45}(\lambda)$	$TC_{135}(\lambda)$

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- KR 1020060072305 [0001]
- JP 2006011409 A [0005]
- JP 2004245925 A [0006]
- US 20060062934 A1 [0007]
- JP 2005338736 A [0008]
- JP 2005128520 A [0009]

专利名称(译)	偏光板和使用该偏光板的液晶显示器		
公开(公告)号	EP2047306B1	公开(公告)日	2017-12-13
申请号	EP2007793288	申请日	2007-07-27
[标]申请(专利权)人(译)	乐金化学股份有限公司		
申请(专利权)人(译)	LG化学有限公司.		
当前申请(专利权)人(译)	LG化学有限公司.		
[标]发明人	PARK JAE HONG PARK JONG SUNG KIM MIN SU KIM SUNG HYUN		
发明人	PARK, JAE-HONG PARK, JONG-SUNG KIM, MIN-SU KIM, SUNG-HYUN		
IPC分类号	G02F1/1345 G02B1/11 G02F1/1335 G02B5/30		
CPC分类号	G02B5/3033 G02B1/105 G02B1/11 G02B1/14 G02B1/16 G02F1/133528 G02F1/13452		
优先权	1020060072305 2006-07-31 KR		
其他公开文献	EP2047306A4 EP2047306A1		
外部链接	Espacenet		

摘要(译)

公开了一种液晶显示器，在其中使用偏振片。液晶显示器包括液晶盒和分别设置在液晶盒两侧的第一偏振片和第二偏振片。第一偏振片和第二偏振片各自包括聚乙烯醇偏振膜和设置在聚乙烯醇偏振膜两侧的保护膜，保护膜设置在与第一偏振片的液晶盒相对的表面上，第二偏振片各自具有100g / m²或更低的蒸汽透过率，并且设置在与第一偏振片和第二偏振片的液晶盒邻接的表面上。当设置在与第一偏振片和第一偏振板的液晶单元邻接的表面上第二偏振片各自具有大于200g / m²的蒸汽透过率时，保护膜设置在与第一偏振板的液晶单元邻接的表面上第二偏振片各自具有大于200g / m²的蒸汽透过率。

