



US 20020175335A1

(19) **United States**(12) **Patent Application Publication**
Lim(10) **Pub. No.: US 2002/0175335 A1**(43) **Pub. Date: Nov. 28, 2002**(54) **ARRAY SUBSTRATE FOR TRANSFLECTIVE
LIQUID CRYSTAL DISPLAY DEVICE AND A
FABRICATING METHOD THEREOF**(52) **U.S. Cl. 257/83**(76) **Inventor: Joo-Soo Lim, Gumi-si (KR)**(57) **ABSTRACT**


Correspondence Address:


MORGAN LEWIS & BOCKIUS LLP
1111 PENNSYLVANIA AVENUE NW
WASHINGTON, DC 20004 (US)(21) **Appl. No.: 10/152,072**(22) **Filed: May 22, 2002**(30) **Foreign Application Priority Data**

May 22, 2001 (KR) 2001-28119


Publication Classification(51) **Int. Cl.⁷ H01L 27/15**

An array substrate for a transflective liquid crystal display device includes a substrate having a display portion and a surrounding portion, a gate line on the substrate, a gate insulating layer covering the gate line, a data line on the gate insulating layer, a gate pad and a data pad within the surrounding portion, the gate pad connected to the gate line and the data pad connected to the data line, a switching device connected to the gate and data lines, a reflective electrode within the display portion and connected to the switching device, a reflective plate within the surrounding portion, a passivation layer on the reflective electrode and the reflective plate, and a transmissive electrode on the passivation layer and connected to the reflective electrode.







Related Art
FIG. 1A




Related Art
FIG. 1B




Related Art
FIG. 1C




Related Art
FIG. 1D




Related Art
FIG. 1E




Related Art
FIG. 1F




Related Art
FIG. 2




Related Art
FIG. 3



Related Art
FIG. 4



Related Art
FIG. 5



Related Art
FIG. 6




FIG. 7




FIG. 8




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 10D




FIG. 11




FIG. 12

ARRAY SUBSTRATE FOR TRANSMISSIVE LIQUID CRYSTAL DISPLAY DEVICE AND A FABRICATING METHOD THEREOF

[0001] The present invention claims the benefit of Korean Patent Application No. 2001-28119, filed in Korea on May 22, 2001, which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a liquid crystal display (LCD) device, and more particularly, to a transmissive LCD device for a mobile communication system, using a dispensing method.

[0004] 2. Description of the Related Art

[0005] In general, a liquid crystal display (LCD) device has a first substrate that includes a thin film transistor (TFT), a second substrate that includes a color filter layer, and a liquid crystal material layer interposed therebetween. Fabrication of a liquid crystal cell of the LCD device includes formation of a common electrode and a pixel electrode on opposing surfaces of the first and second substrates, respectively, and the liquid crystal material is injected through an injection hole between the first and second substrates. A polarizing plate is attached on an outer surface of each of the first and second substrates to complete the liquid crystal cell. Accordingly, image data is displayed by the LCD device by adjusting a voltage that is applied to the common and pixel electrodes to control transmittance of the liquid crystal cell.

[0006] The complete process for fabricating the liquid crystal cell includes a limited number of individual steps. In contrast, fabrication processes for forming the TFT on the first substrate and forming the color filter layer on the second substrate may be classified into a significant number of individual fabrication steps. The individual fabrication steps include processes of forming an orientation film, forming a cell gap, injecting liquid crystal material into the cell gap, and forming individual liquid crystal cells. The process for injecting liquid crystal material is performed through one of a dip method or a contact method. In the dip method, the bonded first and second substrates are dipped into a vessel containing the liquid crystal material, and a pressure difference between the bonded first and second substrates and the vessel causes injection of the liquid crystal material into the cell gap through the injection hole. In the contact method, the injection hole contacts a surface of the liquid crystal material in the vessel, and a pressure difference between the bonded first and second substrates and the vessel causes injection of the liquid crystal material into the cell gap through the injection hole. Both the dip method and the contact method are time consuming and may cause contamination of the injection hole, thereby deteriorating display quality of the LCD device.

[0007] To solve the above problems, a dispensing method is suggested wherein a sealant is printed along a boundary of an array substrate that includes a plurality of individual liquid crystal cells. Then, the liquid crystal material is dropped within a region defined by the sealant using a dispenser. Accordingly, processing time is reduced and a production yield is dramatically improved.

[0008] FIGS. 1A to 1C are plan views showing a fabricating process of a liquid crystal cell using a dispensing

method according to the related art, and FIGS. 1D to 1F are cross-sectional views of the fabrication process shown in FIGS. 1A to 1C according to the related art, respectively.

[0009] In FIGS. 1A and 1D, a first substrate 2 includes a plurality of unit cells "A" and a second substrate 4 (in FIGS. 1B and 1E) includes an array line (not shown), a pixel electrode (not shown), and a switching device (not shown). A sub-color filter layer (not shown) that corresponds to the pixel electrode and a black matrix (not shown) that corresponds to a space between the pixel electrodes are formed on the first substrate 2.

[0010] In FIGS. 1B and 1E, a sealant 6 is printed on the second substrate 4 corresponding to a boundary of the plurality of unit cells "A." A liquid crystal material 8 (in FIG. 1E) is dropped on an inner region of the sealant 6 using a dispenser, and the first substrate 2 is attached to the second substrate 4 to form a LCD panel 10 (in FIG. 1F).

[0011] In FIGS. 1C and 1F, a photo mask 12 (in FIG. 1F) includes a transmissive portion "B" and a blocking portion "C" that are disposed over the LCD panel 10 (in FIG. 1F) for hardening of the sealant 6 by exposure to ultraviolet (UV) light. The transmissive portion "B" corresponds to a position of the sealant 6 of the LCD panel 10, and the blocking portion "C" correspond to an interior position "D" of each of the unit cells "A" (in FIG. 1C). The interior "D" of each of the unit cells "A" provides a mask to prevent a channel region of the TFT on the second substrate 4 from being exposed to the ultraviolet light during the hardening of the sealant 6. Then, the first and second substrates 2 and 4 are fully attached through a subsequent hot press process. Finally, the attached substrates are cut (diced) into individual unit cells "A."

[0012] FIG. 2 is a plan view showing a second substrate of a unit cell according to the related art. In FIG. 2, a second substrate 20 includes a display portion "E" and a surrounding portion "F." A plurality of array lines (not shown), a plurality of switching devices (not shown), and a plurality of pixel electrodes (not shown) are formed within the display portion "E." A pad portion "J" is formed to extend from the plurality of array lines at the surrounding portion "F." The pad portion "J" is formed within a region that will be covered with a case of a mobile communication system.

[0013] FIG. 3 is a magnified plan view of partial regions "G", "H", and "I" of FIG. 2 according to the related art. In FIG. 3, a second substrate 20 includes a gate line 26 and a data line 28. The gate line 26 includes a gate pad 24 formed within a specific area at one end of the gate line 26. The gate line 26 crosses the data line 28 at a crossing point with an insulating layer (not shown) interposed therebetween, thereby defining a pixel region "P." The data line 28 includes a data pad 30 formed within a specific area at one end of the data line 28. In general, the gate pads 24 and the data pad 30 are disposed within the surrounding portion "F" of the second substrate 20, and an external signal is applied to the gate pad 24 and the data pad 30. A TFT "T" includes a gate electrode 32, an active layer 34 formed on the gate electrode 32, and a source electrode 36 and a drain electrode 38 formed on both ends of the active layer 34. The TFT "T" is disposed adjacent to the crossing point of the gate line 26 and the data line 28. A transmissive electrode 40 is formed on the pixel region "P" and is connected to the drain electrode 38 for applying the external signal that drives a

liquid crystal layer (not shown). The transmissive electrode **40** defines a reflective portion "K" and a transmissive portion "L," and includes a reflective electrode **40a** having a transmissive hole **42** and a transmissive electrode **40b** formed over or under the reflective electrode **40a** with an insulating layer (not shown) interposed therebetween. A sealant (not shown) is formed at the surrounding portion "F" (of FIG. 2) of the array substrate **20**.

[0014] FIG. 4 is a cross-sectional view taken along IV-IV of FIG. 3 according to the related art, and FIG. 5 is a cross-sectional view taken along V-V of FIG. 3 according to the related art. In FIG. 4, an LCD panel "M" for a mobile communication system **50** includes an attached array substrate **20** and a color filter substrate **52**, and a liquid crystal material layer **48** disposed therebetween. The LCD panel "M" may be classified into a display portion "E" and a surrounding portion "F." A backlight **54** is disposed under the LCD panel "M" and is used for a transmissive mode of the LCD panel "M." A case **56** covers the backlight **54** and the surrounding portion "F" of the LCD panel "M" in FIG. 5.

[0015] As shown in FIG. 5, an LCD device fabricated using the dispensing method, a black matrix **58** should not be formed within a region where the sealant **46** is formed. Accordingly, a width of the black matrix **58** at the surrounding portion "E" (in FIG. 4) is about one-half of a width for an LCD device fabricated using the injecting method.

[0016] FIG. 6 is a cross-sectional view illustrating a relationship between widths of a black matrix and a sealant according to the related art. In FIG. 6, a width of a surrounding portion is 2.8 mm and a width of a black matrix **58** is reduced to an amount " α " that is about one-half of a width of a black matrix for a LCD device fabricated by the injecting method. The black matrix **58** is spaced apart from a sealant **46** by an amount " β_1 ." For the sealant having a width of " γ ," since the sealant **46** is formed at a portion spaced apart from an edge of a mobile communication system by an amount " β_2 ," the surrounding portion of the mobile communication system is designed to have a width of " $\alpha + \beta_1 + \beta_2 + \gamma$."

[0017] However, as shown in FIG. 5, a light leakage phenomenon may occur in a mobile communication system having a structure according to the related art because light **60** of the backlight **54** under the LCD panel "M" (in FIG. 4) is emitted at a vicinity "S1" of the case **56** through a space "N" between the sealant **46** at the surrounding portion "F" of the LCD panel "M" (in FIG. 4) and the black matrix **58**. Therefore, a display quality of an LCD device according to the related art is deteriorated due to a difference in intensity at the surrounding portion of the LCD panel for the mobile communication system **50**. In order to decrease a size of the mobile communication system while maintaining a sufficient liquid crystal display area, an area of the display portion of the LCD panel should be kept constant and an area of the surrounding portion of the LCD panel should be reduced. Accordingly, an area of the black matrix is also reduced, thereby subjecting the mobile communication system to a light leakage phenomenon.

SUMMARY OF THE INVENTION

[0018] Accordingly, the present invention is directed to a liquid crystal display device that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

[0019] An object of the present invention is to provide a compact and high quality mobile communication system by reducing a light leakage phenomenon at a surrounding portion of an LCD panel.

[0020] Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

[0021] To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, an array substrate for a transmissive liquid crystal display device includes a substrate having a display portion and a surrounding portion, a gate line on the substrate, a gate insulating layer covering the gate line, a data line on the gate insulating layer, a gate pad and a data pad within the surrounding portion, the gate pad connected to the gate line and the data pad connected to the data line, a switching device connected to the gate and data lines, a reflective electrode within the display portion and connected to the switching device, a reflective plate within the surrounding portion, a passivation layer on the reflective electrode and the reflective plate, and a transmissive electrode on the passivation layer and connected to the reflective electrode.

[0022] In another aspect, a fabricating method of an array substrate for a transmissive liquid crystal display device includes forming a gate line on a substrate having a display portion and a surrounding portion, forming a gate insulating layer covering the gate line, forming a data line on the gate insulating layer, forming a gate pad and a data pad within the surrounding portion, the gate pad connected to the gate line and the data pad connected to the data line, forming a switching device connected to the gate and data lines, forming a reflective electrode within the display portion and connected to the switching device, forming a reflective plate within the surrounding portion, forming a passivation layer on the reflective electrode and the reflective plate, and forming a transmissive electrode on the passivation layer and connected to the reflective electrode.

[0023] In another aspect, a mobile communication system includes a transmissive liquid crystal display panel having a display portion and a surrounding portion including a reflective plate, a backlight unit adjacent to the transmissive liquid crystal panel, and a case enveloping the surrounding portion and the backlight unit.

[0024] In another aspect, a fabricating method for forming a mobile communication system includes forming a transmissive liquid crystal display panel having a display portion and a surrounding portion including a reflective plate, forming a backlight unit adjacent to the transmissive liquid crystal panel, and forming a case enveloping the surrounding portion and the backlight unit.

[0025] It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0026] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention. In the drawings:

[0027] **FIGS. 1A to 1C** are plan views showing a fabricating process of a liquid crystal cell using a dispensing method according to the related art; and **FIGS. 1D to 1F** are cross-sectional views of **FIGS. 1A to 1C**, respectively, according to the related art;

[0028] **FIG. 2** is a plan view showing a second substrate of a unit cell according to the related art;

[0029] **FIG. 3** is a magnified plan view of partial regions "G", "H," and "I" of **FIG. 2** according to the related art;

[0030] **FIG. 4** is a cross-sectional view taken along IV-IV of **FIG. 3** according to the related art;

[0031] **FIG. 5** is a cross-sectional view taken along V-V of **FIG. 3** according to the related art;

[0032] **FIG. 6** is a cross-sectional view illustrating a relationship between widths of a black matrix and a sealant according to the related art;

[0033] **FIG. 7** is a plan view of an exemplary array substrate for a transfective LCD device according to the present invention;

[0034] **FIG. 8** is a magnified schematic plan view showing regions "P," "Q," and "R" of **FIG. 7** according to the present invention;

[0035] **FIGS. 9A to 9D** are cross sectional views taken along IX-IX of **FIG. 8** and show an exemplary fabricating process according to the present invention;

[0036] **FIGS. 10A to 10D** are cross sectional views taken along X-X of **FIG. 8** and show the exemplary fabricating process according to the present invention;

[0037] **FIG. 11** is a cross-sectional view showing an exemplary display portion of a mobile communication system according to the present invention; and

[0038] **FIG. 12** is a cross-sectional view showing an exemplary surrounding portion of a mobile communication system according to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0039] Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

[0040] **FIG. 7** is a plan view of an exemplary array substrate for a transfective LCD device according to the present invention. In **FIG. 7**, an array substrate **118** for a transfective LCD device may include a display portion "E" for displaying images, and a surrounding portion "F" having a pad portion "G" for applying a signal to the display portion "E." A plurality of conductive lines (not shown) may be disposed within the display portion "E," and a plurality of

pads (not shown) having a specific area may be connected to an end of each of the plurality of conductive lines. Moreover, the pad portion "G" may be disposed along a first direction at a first side of the surrounding portion "F" and along a second direction at a second side of the surrounding portion "F" perpendicular to the first direction. An opaque metal plate **142** may be formed at a region "R" along the second direction at a first side of a portion "Q" that is opposite to a pad region "S" and along the first direction at a second side of the portion "Q." Moreover, the opaque metal plate **142** may be disposed along the first and second side of the portion "Q" opposite of the plurality of pads (not shown). The opaque metal plate **142** may not necessarily be connected to an electrical potential (i.e., electrically floating), and may be formed simultaneously with a reflective plate (not shown) of the array substrate **118**.

[0041] **FIG. 8** is a magnified schematic plan view of **FIG. 7** according to the present invention. In **FIG. 8**, an array substrate **118** for a transfective LCD device may include a gate line **122** having a gate pad **120** within the region "S" disposed along a first direction, and a data line **126** having a data pad **124** within the region "Q" disposed along a second direction perpendicular to the first direction, thereby defining a pixel region "P" at a cross point of the gate line **122** and the data line **126**. A TFT "T" may include an active layer **130**, a source electrode **132**, and a drain electrode **134** formed within a region adjacent to the crossing point of the gate line **122** and the data line **126**. A reflective electrode **138** may include a transmissive hole **136**, and may be connected to the drain electrode **134**. A transparent pixel electrode **140** may overlap the reflective electrode **138** with an insulating layer (not shown) interposed therebetween. In addition, a sealant (not shown) may be formed within the region "R" above the electrically floating reflective plate **142**.

[0042] **FIGS. 9A to 9D** are cross sectional views taken along IX-IX of **FIG. 8** and show an exemplary fabricating process according to the present invention, and **FIGS. 10A to 10D** are cross sectional views taken along X-X of **FIG. 8** and show the exemplary fabricating process according to the present invention.

[0043] In **FIG. 9A**, a gate line **122** (of **FIG. 8**), a gate electrode **128**, and a gate pad **120** (in **FIG. 8**) connected to the gate electrode **128** may be formed on a transparent substrate **118** by depositing and patterning a conductive material, for example. The conductive material may include at least one of a conductive metallic material group including aluminum (Al), aluminum alloy, chromium (Cr), molybdenum (Mo) and niobium (Nb). As shown in **FIGS. 9A and 10A**, a first insulating layer, i.e., a gate insulating layer **129**, may be formed on an entire surface of the substrate **118** by depositing at least one of inorganic insulating material group including silicon oxide (SiO₂) and silicon nitride (SiNx), for example. Next, an island-shaped active layer **130** may be formed on the gate insulating layer **129** by depositing and patterning an intrinsic amorphous silicon (a-Si:H) material, for example, and an ohmic contact layer **131** may be selectively formed on the island-shaped active layer **130** by depositing and patterning a doped amorphous silicon (n+ or p+ a-Si:H) material, for example. The ohmic contact layer **131** may be formed by an ion-doping process after depositing the intrinsic amorphous silicon (a-Si:H) material. Electric characteristics of the active layer **130** may be controlled depending upon a type of dopant used during ion-doping process. If the ohmic contact layer **131** is doped with an element of a Group III material such as B₂H₆, for example, the active layer **130** functions as a p-type semiconductor.

Alternatively, if the ohmic contact layer **131** is doped with an element of a Group V material such as PH_3 , for example, the active layer **130** functions as an n-type semiconductor. Accordingly, the element used during the ion-doping process may be selected based upon a desired application of the TFT "T."

[0044] Next, a source electrode **132** and a drain electrode **134** may be formed to overlap opposing end portions the ohmic contact layer **131**. A data line **126** may be formed over the substrate **118** by depositing and patterning at least one of a conductive material. The conductive material may include chromium (Cr), niobium (Nb), copper (Cu), antimony (Sb), tungsten (W) and aluminum alloy. The data line **126** may be connected to the source electrode **132**, thereby defining a pixel region "P" with the gate line **122** (of FIG. 7), and a data pad **124** (of FIG. 7) of a specific area may be connected to one end of the data line **126**. After forming the source and drain electrodes **132** and **134**, a process of eliminating the ohmic contact layer **131** exposed between the source and drain electrodes **132** and **134** may be performed.

[0045] In FIGS. 9B and 10B, a second insulating layer, i.e., an interlayer insulating layer **137**, may be formed on the entire surface of the substrate **118** by depositing at least one of an organic material group. The organic material group may include benzocyclobutene (BCB) and an acrylic resin. A first drain contact hole **141** may be formed by patterning the interlayer insulating layer **137**, thereby exposing a portion of the drain electrode **134**. Next, a reflective electrode **138** may be formed on the interlayer insulating layer **137** to have a transmissive hole **136** by depositing and patterning at least one of a conductive material group, for example. The reflective electrode **138** may be connected to the exposed portion of drain electrode **134**, and the conductive material group may include aluminum (Al) and an aluminum alloy having a high reflectance. As shown in FIG. 10B, a reflective plate **142** may be formed simultaneously with the formation of the reflective electrode **138** (in FIG. 9B), and may be electrically floating. The reflective plate **142** may be formed within a region opposite to a region having the gate and data pads.

[0046] In FIGS. 9C and 10C, a third insulating layer, i.e., a passivation layer **146**, may be formed on the entire surface of the substrate **128** having the reflective electrode **138** (in FIG. 9C) and the reflective plate **142** (in FIG. 10C). The passivation layer **146** may be formed by depositing at least one of an organic material group including benzocyclobutene (BCB) and an acrylic resin, for example. Next, a second drain contact hole **148** (in FIG. 9C) may be formed by etching the passivation layer **146**, thereby exposing a portion of the reflective electrode **138** contacting the drain electrode **134**.

[0047] In FIGS. 9D and 10D, a transmissive electrode **140** may be formed at the pixel region "P" (in FIG. 8) to be connected to the reflective electrode **138** by depositing and patterning at least one of a transparent conductive material group that includes indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), for example. Next, an orientation film **150** formed of a transparent polymer material such as polyimide, for example, may be formed on the transmissive electrode **140** (in FIG. 10D), thereby determining alignment characteristics of a later formed liquid crystal material layer.

[0048] FIG. 11 is a cross-sectional view showing an exemplary display portion of a mobile communication system according to the present invention, and FIG. 12 is a

cross-sectional view showing an exemplary surrounding portion of a mobile communication system according to the present invention.

[0049] In FIG. 11, a mobile communication system may include an LCD panel "S" having a first substrate **162**, a second substrate **118**, and a liquid crystal layer interposed therebetween. The first substrate **162** may be commonly referred to as a color filter substrate that may include a color filter layer **170** and a black matrix **172**, and the second substrate **118** may be commonly referred to as an array substrate and may include a TFT, a reflective electrode **138**, and a transmissive electrode **140**. The LCD panel "S" also may include a backlight unit **164** over an outer surface of the second substrate **118**, and a case **168** (in FIG. 12) enveloping the backlight unit **164** and a surrounding portion "O" of the LCD panel "S." The LCD panel "S" may include a display portion "E," which is not covered by the case **168** (in FIG. 12), and the surrounding portion "O," which is covered by the case **168**. As shown in FIG. 12, a reflective plate **142**, which may be electrically floating, may be formed under a sealant **178** of the surrounding portion "O" to reflect incident light **176** emitted from the backlight unit **164**. Accordingly, light leakage of the surrounding portion "O" within a vicinity "S2" of the case may be prevented.

[0050] It will be apparent to those skilled in the art that various modifications and variations can be made in the liquid crystal display device of the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An array substrate for a transmissive liquid crystal display device, comprising:

- a substrate having a display portion and a surrounding portion;
- a gate line on the substrate;
- a gate insulating layer covering the gate line;
- a data line on the gate insulating layer;
- a gate pad and a data pad within the surrounding portion, the gate pad connected to the gate line and the data pad connected to the data line;
- a switching device connected to the gate and data lines;
- a reflective electrode within the display portion and connected to the switching device;
- a reflective plate within the surrounding portion;
- a passivation layer on the reflective electrode and the reflective plate; and
- a transmissive electrode on the passivation layer and connected to the reflective electrode.

2. The array substrate according to claim 1, wherein the reflective plate is disposed within a first region opposite to a second region where the gate and data pads are disposed.

3. The array substrate according to claim 1, wherein the switching device includes a thin film transistor.

4. The array substrate according to claim 1, wherein the reflective plate and the reflective electrode are formed of a same layer.

5. The array substrate according to claim 1, wherein the passivation layer includes a contact hole exposing a portion of the reflective electrode.

6. The array substrate according to claim 5, wherein the transmissive electrode is connected to the reflective electrode through the contact hole.

7. The array substrate according to claim 1, wherein the transmissive electrode includes a transparent conductive material.

8. The array substrate according to claim 1, further comprising an interlayer insulating layer on the gate insulating layer and the switching device.

9. The array substrate according to claim 1, further comprising a sealant within the surrounding portion.

10. The array substrate according to claim 9, wherein the sealant is formed on the transmissive electrode.

11. The array substrate according to claim 10, wherein the sealant is formed over a portion of the reflective plate.

12. The array substrate according to claim 1, wherein the reflective plate electrically floats.

13. A fabricating method of an array substrate for a transfective liquid crystal display device, comprising:

forming a gate line on a substrate having a display portion and a surrounding portion;

forming a gate insulating layer covering the gate line;

forming a data line on the gate insulating layer;

forming a gate pad and a data pad within the surrounding portion, the gate pad connected to the gate line and the data pad connected to the data line;

forming a switching device connected to the gate and data lines;

forming a reflective electrode within the display portion and connected to the switching device;

forming a reflective plate within the surrounding portion;

forming a passivation layer on the reflective electrode and the reflective plate; and

forming a transmissive electrode on the passivation layer and connected to the reflective electrode.

14. The fabricating method according to claim 13, wherein the reflective plate is disposed within a first region opposite to a second region where the gate and data pads are disposed.

15. The fabricating method according to claim 13, wherein the switching device includes a thin film transistor.

16. The fabricating method according to claim 13, wherein forming the reflective plate and forming the reflective electrode are performed simultaneously.

17. The fabricating method according to claim 13, further comprising etching the passivation layer to form a contact hole exposing a portion of the reflective electrode.

18. The fabricating method according to claim 17, wherein the transmissive electrode is connected to the reflective electrode through the contact hole.

19. The fabricating method according to claim 13, wherein the transmissive electrode includes a transparent conductive material.

20. The fabricating method according to claim 13, further comprising forming an interlayer insulating layer on the gate insulating layer and the switching device.

21. The fabricating method according to claim 13, further comprising forming a sealant within the surrounding portion.

22. The fabricating method according to claim 21, wherein the sealant is formed on the transmissive electrode.

23. The fabricating method according to claim 21, wherein the sealant is formed over a portion of the reflective plate.

24. The fabricating method according to claim 13, wherein the reflective plate is electrically floating.

25. A mobile communication system, comprising:

a transfective liquid crystal display panel having a display portion and a surrounding portion including a reflective plate;

a backlight unit adjacent to the transfective liquid crystal panel; and

a case enveloping the surrounding portion and the backlight unit.

26. The mobile communication system according to claim 25, wherein a color filter layer, a transfective electrode, a gate line, and a data line are formed within the display portion.

27. The mobile communication system according to claim 26, wherein the transfective electrode includes a reflective electrode and a transmissive electrode.

28. The mobile communication system according to claim 27, wherein the reflective electrode and the transmissive electrode overlap.

29. The mobile communication system according to claim 28, wherein the reflective electrode includes a transmissive hole.

30. The mobile communication system according to claim 27, wherein the reflective plate and the reflective electrode are formed of a same layer.

31. A fabricating method for forming a mobile communication system, comprising:

forming a transfective liquid crystal display panel having a display portion and a surrounding portion including a reflective plate;

forming a backlight unit adjacent to the transfective liquid crystal panel; and

forming a case enveloping the surrounding portion and the backlight unit.

32. The fabricating method according to claim 31, further comprising forming a color filter layer, a transfective electrode, a gate line, and a data line within the display portion.

33. The fabricating method according to claim 32, wherein forming the transfective electrode includes forming a reflective electrode and a transmissive electrode.

34. The fabricating method according to claim 33, wherein the reflective electrode and the transmissive electrode overlap.

35. The fabricating method according to claim 33, wherein forming the reflective electrode includes forming a transmissive hole.

36. The fabricating method according to claim 33, wherein forming the reflective plate and forming the reflective electrode are simultaneously performed.

专利名称(译)	用于透反液晶显示装置的阵列基板及其制造方法		
公开(公告)号	US20020175335A1	公开(公告)日	2002-11-28
申请号	US10/152072	申请日	2002-05-22
[标]申请(专利权)人(译)	LIM JOO SOO		
申请(专利权)人(译)	LIM JOO-SOO		
当前申请(专利权)人(译)	LIM JOO-SOO		
[标]发明人	LIM JOO SOO		
发明人	LIM, JOO-SOO		
IPC分类号	G02F1/1335 H01L27/15		
CPC分类号	G02F1/133555		
优先权	1020010028119 2001-05-22 KR		
其他公开文献	US6649992		
外部链接	Espacenet USPTO		

摘要(译)

用于半透半反液晶显示装置的阵列基板，包括具有显示部分和周围部分的基板，基板上的栅极线，覆盖栅极线的栅极绝缘层，栅极绝缘层上的数据线，栅极焊盘周围部分内的数据焊盘，连接到栅极线的栅极焊盘和连接到数据线的数据焊盘，连接到栅极和数据线的开关装置，显示部分内的反射电极并连接到开关装置，周围部分内的反射板，反射电极和反射板上的钝化层，以及钝化层上的透射电极并连接到反射电极。

