



US 20040263756A1

(19) **United States**

(12) **Patent Application Publication**
Tak et al.

(10) **Pub. No.: US 2004/0263756 A1**

(43) **Pub. Date: Dec. 30, 2004**

(54) **LIQUID CRYSTAL DISPLAY AND THIN FILM TRANSISTOR ARRAY PANEL THEREFOR**

(30) **Foreign Application Priority Data**

Jun. 26, 2003 (KR)..... 2003-0041987

(75) **Inventors: Young-Mi Tak, Seoul (KR); Seung-Soo Baek, Seoul (KR); Dong-Gyu Kim, Yongin-si (KR)**

Publication Classification

(51) **Int. Cl.⁷ G02F 1/1343**

(52) **U.S. Cl. 349/145**

(57) **ABSTRACT**

A thin film transistor array panel is provided, which includes: a substrate; a plurality of first signal lines formed on the substrate; a plurality of second lines formed on the substrate, intersecting the first signal line, and including a plurality of curved portions having at least two curve points and a plurality of intermediate portions, the curved portions and the intermediate portions alternately connected; a plurality of pixel electrodes located substantially in areas defined by the first and the second signal lines; and a plurality of thin film transistors connected to the first and the second signal lines and the pixel electrodes.

Correspondence Address:

F. CHAU & ASSOCIATES, LLC
130 WOODBURY ROAD
WOODBURY, NY 11797 (US)

(73) **Assignee: SAMSUNG ELECTRONICS CO., LTD.**

(21) **Appl. No.: 10/877,673**

(22) **Filed: Jun. 25, 2004**




FIG. 1




FIG.2




FIG.4




FIG.5




FIG. 6




FIG. 7





FIG. 8



LIQUID CRYSTAL DISPLAY AND THIN FILM TRANSISTOR ARRAY PANEL THEREFOR

BACKGROUND OF THE INVENTION

[0001] (a) Field of the Invention

[0002] The present invention relates to a liquid crystal display and a thin film transistor array panel therefor.

[0003] (b) Description of the Related Art

[0004] A liquid crystal display (LCD) is one of the most widely used flat panel displays. An LCD includes a liquid crystal (LC) layer interposed between a pair of panels provided with field-generating electrodes. The LC layer is subject to an electric field generated by the electrodes and variations in the field strength change the molecular orientation of the LC layer, which in turn change the polarization of light passing through the LC layer. Appropriately disposed polarizer(s) change the light transmittance based on the polarization of the light.

[0005] One measure of LCD quality is a viewing angle that is defined by angle where the LCD exhibits a predetermined contrast ratio. Various techniques for enlarging the viewing angle have been suggested, including a technique utilizing a vertically aligned LC layer and providing cutouts or protrusions at the field-generating electrodes such as pixel electrodes and a common electrode.

[0006] However, cutouts and the protrusions reduce the aperture ratio. To increase aperture ratio, it has been suggested that the size of the pixel electrodes be maximized. However, maximization of the size of the pixel electrodes results in a close distance between the pixel electrodes, causing strong lateral electric fields between the pixel electrodes. The strong electric fields cause unwanted altering of the orientation of the LC molecules, yielding textures and light leakage and deteriorating display characteristics. The textures and the light leakage may be screened by a wide black matrix, which also reduces the aperture ratio.

[0007] In the meantime, the size of the pixel electrodes is increased as the LCD increases. The shape of the pixel electrodes is not recognized when the pitch of the pixel electrodes is small, for example, smaller than about 100 microns. However, the outline of the pixel electrodes defined by signal lines such as an oblique outline may be perceived when the pitch of the pixel electrodes becomes large, for example, larger than about 100 microns, thereby deteriorating display characteristics. In addition, the oblique shape of the pixel electrodes may weaken a driving electric field to liquid crystal molecules located at some positions to increase the response time.

SUMMARY OF THE INVENTION

[0008] A motivation of the present invention is to solve the above-described and other problems.

[0009] A thin film transistor array panel is provided, which includes: a substrate; a plurality of first signal lines formed on the substrate; a plurality of second lines formed on the substrate, intersecting the first signal line, and including a plurality of curved portions having at least two curve points and a plurality of intermediate portions, the curved portions and the intermediate portions alternately connected; a plurality of pixel electrodes located substantially in areas

defined by the first and the second signal lines; and a plurality of thin film transistors connected to the first and the second signal lines and the pixel electrodes.

[0010] Each of the curved portions of the data lines may include a plurality of rectilinear portions connected to each other and making angles of about 45 degrees with the gate lines in clockwise and counterclockwise manners, respectively.

[0011] The thin film transistor array panel may further include a plurality of third signal lines formed on the substrate, extending substantially parallel to the first signal lines, and overlapping the pixel electrodes to form storage capacitors.

[0012] The thin film transistors may include terminal electrodes connected to the intermediate portions of the second signal lines.

[0013] The pixel electrodes may have cutouts disposed on the data lines, each cutout bisecting a corresponding of the pixel electrodes into two partitions.

[0014] A thin film transistor array panel is provided, which includes: a substrate; a gate line formed on the substrate and including a gate electrode; a gate insulating layer formed on the gate line; a semiconductor layer formed on the gate insulating layer; a data line formed on the substrate and including a curved portion having at least two curved points and including a source electrode disposed on the semiconductor layer at least in part; a drain electrode disposed on the semiconductor layer at least in part and disposed opposite the source electrode; a passivation layer formed on the semiconductor layer; and a pixel electrode having an edge curved along the data line.

[0015] The curved portion of the data line may include a plurality of portions making a clockwise angle of about 45 degrees and a counterclockwise angle of about 45 degrees with respect to the gate line.

[0016] The thin film transistor array panel may further include a storage electrode line that extends substantially parallel to the gate line and has a storage electrode overlapping a conductor connected to the pixel electrode to form a storage capacitor.

[0017] The pixel electrode may be disposed on the passivation layer.

[0018] The first passivation layer may include organic or inorganic insulating material.

[0019] The thin film transistor array panel may further include a color filter formed on the first passivation layer.

[0020] The color filter may extend substantially parallel to the data line.

[0021] The semiconductor layer may have substantially the same planar shape as the data line, the source electrode, and the drain electrode except for a first portion.

[0022] A liquid crystal is provided, which includes: a first substrate; a gate line formed on the first substrate and including a gate electrode; a data line formed on the first substrate and including a curved portion having at least two curve points and an intersecting portion; a thin film transistor connected to the gate line and the data line; a pixel electrode connected to the thin film transistor; a second

substrate facing the first substrate; a common electrode formed on the second substrate; a liquid crystal layer disposed between the first and the second substrates; and at least a domain defining member formed on at least one of the first and the second substrates and partitioning the liquid crystal layer into a plurality of domains, each domain having two major edges substantially parallel to the curved portion of the data line.

[0023] The liquid crystal layer may have negative dielectric anisotropy and is vertically aligned.

[0024] The domain partitioning member may include a cutout in the pixel electrode or the common electrode.

BRIEF DESCRIPTION OF THE DRAWINGS

[0025] The present invention will become more apparent by describing embodiments thereof in detail with reference to the accompanying drawings in which:

[0026] FIG. 1 is a layout view of a TFT array panel for an LCD according to an embodiment of the present invention;

[0027] FIG. 2 is a layout view of a common electrode panel for an LCD according to an embodiment of the present invention;

[0028] FIG. 3 is a layout view of an LCD including the TFT array panel shown in FIG. 1 and the common electrode panel shown in FIG. 2;

[0029] FIG. 4 is a sectional view of the LCD shown in FIG. 3 taken along the line IV-IV';

[0030] FIG. 5 is a sectional view of the LCD shown in FIG. 3 taken along the lines V-V' and V'-V";

[0031] FIG. 6 is a layout view of an LCD according to another embodiment of the present invention;

[0032] FIG. 7 is a sectional view of the LCD shown in FIG. 6 taken along the line VI-VI';

[0033] FIG. 8 is a layout view of an LCD according to another embodiment of the present invention; and

[0034] FIG. 9 is a sectional view of the LCD shown in FIG. 8 taken along the line IX-IX'.

DETAILED DESCRIPTION OF EMBODIMENTS

[0035] The present invention now will be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. The present invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein.

[0036] In the drawings, the thickness of layers, films and regions are exaggerated for clarity. Like numerals refer to like elements throughout. It will be understood that when an element such as a layer, film, region or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present. In contrast, when an element is referred to as being "directly on" another element, there are no intervening elements present.

[0037] Now, liquid crystal displays and thin film transistor (TFT) array panels for LCDs according to embodiments of the present invention will be described with reference to the accompanying drawings.

[0038] An LCD according to an embodiment of the present invention is described in detail with reference to FIGS. 1-5.

[0039] FIG. 1 is a layout view of a TFT array panel for an LCD according to an embodiment of the present invention, FIG. 2 is a layout view of a common electrode panel for an LCD according to an embodiment of the present invention, FIG. 3 is a layout view of an LCD including the TFT array panel shown in FIG. 1 and the common electrode panel shown in FIG. 2, FIG. 4 is a sectional view of the LCD shown in FIG. 3 taken along the line IV-IV', and FIG. 5 is a sectional view of the LCD shown in FIG. 3 taken along the lines V-V' and V'-V".

[0040] An LCD according to an embodiment of the present invention includes a TFT array panel 100, a common electrode panel 200 facing the TFT array panel 100, and a LC layer 300 interposed between the TFT array panel 100 and the common electrode panel 200.

[0041] The TFT array panel 100 is now described in detail with reference to FIGS. 1, 4 and 5.

[0042] A plurality of gate lines 121 and a plurality of storage electrode lines 131 are formed on an insulating substrate 110.

[0043] The gate lines 121 extend substantially in a transverse direction and are separated from each other and transmit gate signals. Each gate line 121 includes a plurality of projections forming a plurality of gate electrodes 123 and an end portion 125 having a large area for contact with another layer or an external device.

[0044] The storage electrode lines 131 extend substantially in the transverse direction and they are substantially equidistant from adjacent gate lines 121. However, the storage electrode lines 131 may be closer to one of the adjacent gate lines 121. Each storage electrode line 131 includes a plurality of projections forming storage electrodes 133 having a shape of a chevron that is symmetrical with respect to the storage electrode line 131 and makes an angle of about 45 degrees with the storage electrode line 131. The storage electrode lines 131 are supplied with a predetermined voltage such as a common voltage, which is applied to a common electrode 270 on the common electrode panel 200 of the LCD.

[0045] The gate lines 121 and the storage electrode lines 131 have a multi-layered structure including two films having different physical characteristics, a lower film and an upper film. The upper film is preferably made of low resistivity metal including Al containing metal such as Al and Al alloy, Ag containing metal such as Ag and Ag alloy, or Cu containing metal such as Cu and Cu alloy for reducing signal delay or voltage drop in the gate lines 121 and the storage electrode lines 131. On the other hand, the lower film is preferably made of material such as Cr, Mo, Mo alloy, Ta, or Ti, which has good physical, chemical, and electrical contact characteristics with other materials such as indium tin oxide (ITO) or indium zinc oxide (IZO). A good exemplary combination of the lower film material and the upper film material is Cr and Al—Nd alloy. In FIGS. 4, the lower and the upper films of the gate electrodes 123 are indicated by reference numerals 231 and 232, respectively, the lower and the upper films of the end portions 125 are indicated by reference numerals 251 and 252, respectively, and the lower

and the upper films of the storage electrodes **133** are indicated by reference numerals **331** and **332**, respectively. Portions of the upper film **252** of the end portions **125** of the gate lines **121** are removed to expose the underlying portions of the lower films **251**.

[**0046**] The gate lines **121** and the storage electrode lines **131** may have a single layer structure or may include three or more layers.

[**0047**] In addition, the lateral sides of the gate lines **121** and the storage electrode lines **131** are inclined relative to a surface of the substrate **110**, and the inclination angle thereof ranges about 30-80 degrees.

[**0048**] A gate insulating layer **140** preferably made of silicon nitride (SiN_x) is formed on the gate lines **121** and the storage electrode lines **131**.

[**0049**] A plurality of semiconductor stripes **151** preferably made of hydrogenated amorphous silicon (abbreviated as "a-Si") or polysilicon are formed on the gate insulating layer **140**. Each semiconductor stripe **151** extends substantially in the longitudinal direction while it is curved periodically. Each semiconductor stripe **151** has a plurality of projections **154** branched out toward the gate electrodes **123**.

[**0050**] A plurality of ohmic contact stripes and islands **161** and **165** preferably made of silicide or n+hydrogenated a-Si heavily doped with n type impurity such as phosphorous (P) are formed on the semiconductor stripes **151**. Each ohmic contact stripe **161** has a plurality of projections **163**, and the projections **163** and the ohmic contact islands **165** are located in pairs on the projections **154** of the semiconductor stripes **151**.

[**0051**] The lateral sides of the semiconductor stripes **151** and the ohmic contacts **161** and **165** are inclined relative to the surface of the substrate **110**, and the inclination angles thereof are preferably in a range between about 30-80 degrees.

[**0052**] A plurality of data lines **171**, a plurality of drain electrodes **175**, and a plurality of storage capacitor conductors **177**, which are separated from each other, are formed on the ohmic contacts **161** and **165** and the gate insulating layer **140**.

[**0053**] The data lines **171** for transmitting data voltages extend substantially in the longitudinal direction and intersect the gate lines **121** and the storage electrode lines **131**. Each data line **171** has an end portion **179** having a large area for contact with another layer or an external device and it includes a plurality of sets of oblique portions and a plurality of longitudinal portions such that it curves periodically. A set of oblique portions includes four oblique portions connected in turn to form a character "W" rotated by a right angle and opposite ends of the set of oblique portions are connected to respective longitudinal portions. The oblique portions of the data lines **171** make an angle of about 45 degrees with the gate lines **121**, and the longitudinal portions cross over the gate electrodes **123**. The length of a set of oblique portions is about one to nine times the length of a longitudinal portion, that is, it occupies about 50-90 percents of the total length of the pair of oblique portions and the longitudinal portion.

[**0054**] Each longitudinal portion of the data lines **171** includes a plurality of projections such that the longitudinal

portion including the projections forms a source electrode **173** partly enclosing an end portion of a drain electrode **175**. Each set of a gate electrode **123**, a source electrode **173**, and a drain electrode **175** along with a projection **154** of a semiconductor stripe **151** form a TFT having a channel formed in the semiconductor projection **154** disposed between the source electrode **173** and the drain electrode **175**.

[**0055**] The storage capacitor conductors **177** overlap the storage electrodes **133** and have substantially the same shape as the storage electrodes **133**.

[**0056**] Instead of providing the storage capacitor conductors **177**, the drain electrodes **175** may extend to overlap the storage electrodes **133**. In this case, the drain electrodes **175** may have expansions overlapping the storage electrodes **133** and having substantially the same shape as the storage electrodes **133**.

[**0057**] The data lines **171** and the drain electrodes **175** also include a lower film **711** and **751** preferably made of Mo, Mo alloy or Cr and an upper film **712** and **752** located thereon and preferably made of Al containing metal. In **FIGS. 4 and 5**, the lower and the upper films of the source electrodes **173** are indicated by reference numerals **731** and **732**, respectively, and the lower and the upper films of the end portions **179** of the data lines **171** are indicated by reference numerals **791** and **792**, respectively. Portion of the upper films **792**, **752** of the expansions **179** of the data lines **171** and the drain electrodes **175** are removed to expose the underlying portions of the lower films **791** and **751**.

[**0058**] Like the gate lines **121** and the storage electrode lines **131**, the data lines **171** and the drain electrodes **175** have inclined lateral sides, and the inclination angles thereof range about 30-80 degrees.

[**0059**] The ohmic contacts **161** and **165** are interposed only between the underlying semiconductor stripes **151** and the overlying data lines **171** and the overlying drain electrodes **175** thereon and reduce the contact resistance therebetween.

[**0060**] A passivation layer **180** is formed on the data lines **171** and the drain electrodes **175**, and exposed portions of the semiconductor stripes **151**, which are not covered with the data lines **171** and the drain electrodes **175**. The passivation layer **180** is preferably made of photosensitive organic material having a good flatness characteristic, low dielectric insulating material such as a-Si:C:O and a-Si:O:F formed by plasma enhanced chemical vapor deposition (PECVD), or inorganic material such as silicon nitride and silicon oxide. The passivation layer **180** may have a double-layered structure including a lower inorganic film and an upper organic film.

[**0061**] The passivation layer **180** has a plurality of contact holes **181**, **183** and **187** exposing the drain electrodes **175**, the end portions **179** of the data lines **171**, and the storage capacitor conductors **177**, respectively. The passivation layer **180** and the gate insulating layer **140** have a plurality of contact holes **182** exposing the end portions **125** of the gate lines **121**. The contact holes **181**, **182**, **183** and **187** can have various shapes such as polygon or circle. The area of each contact hole **182** or **183** is preferably equal to or larger than about 0.5 mm×15 μm and not larger than about 2

mm×60 μm. The sidewalls of the contact holes **181**, **182**, **183** and **187** are inclined with an angle of about 30-85 degrees or have stepwise profiles.

[0062] A plurality of pixel electrodes **190** and a plurality of contact assistants **95** and **97**, which are preferably made of ITO or IZO, are formed on the passivation layer **180**. Alternatively, the pixel electrodes **190** may be made of transparent conductive polymer, and, for a reflective LCD, the pixel electrodes **190** are made of opaque reflective metal. In these cases, the contact assistants **192** and **199** may be made of material such as ITO or IZO different from the pixel electrodes **190**.

[0063] Each pixel electrode **190** is located substantially in an area enclosed by the data lines **171** and the gate lines **121**, and thus it also forms a twin chevron. Each pixel electrode **190** has a cutout **191** that bisects the pixel electrode **190** into left and right partitions **190a** and **190b** arranged in the transverse direction. Each cutout **191** includes four oblique portions that extending parallel to the data lines **171**. The pixel electrodes **190** cover the storage electrode lines **131** including the storage electrodes **133** and the storage capacitor conductors **177** and have chamfered edges substantially parallel to the cutouts **191**.

[0064] The pixel electrodes **190** are physically and electrically connected to the drain electrodes **175** through the contact holes **181** and to the storage capacitor conductors **177** through the contact holes **187** such that the pixel electrodes **190** receive the data voltages from the drain electrodes **175** and transmit the received data voltages to the storage capacitor conductors **177**. The pixel electrodes **190** supplied with the data voltages generate electric fields in cooperation with the common electrode **270**, which reorient liquid crystal molecules **310** disposed therebetween.

[0065] A pixel electrode **190** and a common electrode form a capacitor called a "liquid crystal capacitor," which stores applied voltages after turn-off of the TFT. An additional capacitor called a "storage capacitor," which is connected in parallel to the liquid crystal capacitor, is provided for enhancing the voltage storing capacity. The storage capacitors are implemented by overlapping the pixel electrodes **190** with the storage electrode lines **131**. The capacitances of the storage capacitors, i.e., the storage capacitances are increased by providing the projections (i.e., the storage electrodes **133**) at the storage electrode lines **131** for increasing overlapping areas, and by providing the storage capacitor conductors **177**, which are connected to the pixel electrodes **190** and overlap the storage electrodes **133**, under the pixel electrodes **190** for decreasing the distance between the terminals.

[0066] The pixel electrodes **190** overlap the data lines **171** as well as the gate lines **121** to increase aperture ratio.

[0067] The contact assistants **95** and **97** are connected to the exposed end portions **125** of the gate lines **121** and the exposed end portions **179** of the data lines **171** through the contact holes **182** and **183**, respectively. The contact assistants **95** and **97** protect the exposed portions **125** and **179** and complement the adhesiveness of the exposed portions **125** and **179** and external devices.

[0068] Finally, an alignment layer **11** is formed on the pixel electrodes **190** and the passivation layer **180**.

[0069] The description of the common electrode panel **200** follows with reference to FIGS. 2,4 and 5.

[0070] A light blocking member **220** called a black matrix is formed on an insulating substrate **210** such as transparent glass and it includes a plurality of oblique portions facing the oblique portions of the data lines **171** and a plurality of right-angled-triangular portions facing the TFTs and the longitudinal portions of the data lines **171** such that the light blocking member **220** prevents light leakage between the pixel electrodes **190** and defines open areas facing the pixel electrodes **190**. Each of the triangular portions of the light blocking member **220** has a hypotenuse parallel to a chamfered edge of a pixel electrode **190**.

[0071] A plurality of color filters **230** are formed on the substrate **210** and the light blocking member **220** and it is disposed substantially in the open areas defined by the light blocking member **220**. The color filters **230** disposed in adjacent two data lines **171** and arranged in the longitudinal direction may be connected to each other to form a stripe. Each color filter **230** may represent one of three primary colors such as red, green and blue colors.

[0072] An overcoat **250** preferably made of organic material is formed on the color filters **230** and the light blocking member **220**. The overcoat **250** protects the color filters **230** and gives a flat top surface.

[0073] A common electrode **270** preferably made of transparent conductive material such as ITO and IZO is formed on the overcoat **250**. The common electrode **270** is supplied with the common voltage and it has a plurality of pairs of chevron-like cutouts **271** and **272**.

[0074] Each of the cutouts **271** and **272** includes four oblique portions connected in turn, a transverse portion connected to one of the oblique portions, and a transverse or longitudinal portion connected to the other of the oblique portions. The oblique portions of the cutout **271/272** extend substantially parallel to the oblique portions of the data lines **171** and face a partition **190a/190b** of a pixel electrode **190** so that they may bisect the partition **190a/190b** into left and right halves. The transverse and the longitudinal portions of the cutout **271/272** are aligned with transverse and longitudinal edges of the pixel electrode **190**, respectively, and they make obtuse angles with the oblique portions of the cutout **271/272**. The cutouts **271** and **272** are provided for controlling the tilt directions of the LC molecules **310** in the LC layer **300** and preferably have a width in a range between about 9-12 microns. The cutouts **271** and **272** may be substituted with protrusions preferably made of organic material and preferably having width ranging about 5 microns to about 10 microns.

[0075] A homogeneous or homeotropic alignment layer **21** is coated on the common electrode **270**.

[0076] A pair of polarizers **12** and **22** are provided on outer surfaces of the panels **100** and **200** such that their transmissive axes are crossed and one of the transmissive axes is parallel to the gate lines **121**.

[0077] The LCD may further include at least one retardation film for compensating the retardation of the LC layer **300** and a backlight unit for providing light for the LCD.

[0078] The LC layer **300** has negative dielectric anisotropy and the LC molecules **310** in the LC layer **300** are

aligned such that their long axes are substantially vertical to the surfaces of the panels **100** and **200** in absence of electric field.

[0079] Upon application of the common voltage to the common electrode **270** and a data voltage to the pixel electrodes **190**, a primary electric field substantially perpendicular to the surfaces of the panels **100** and **200** is generated. The LC molecules **310** tend to change their orientations in response to the electric field such that their long axes are perpendicular to the field direction. In the meantime, the cutouts **191**, **271** and **272** of the pixel electrodes **190** and the common electrode **270** and the edges of the pixel electrodes **190** distort the primary electric field to have a horizontal component which determines the tilt directions of the LC molecules **310**. The horizontal component of the primary electric field is perpendicular to the edges of the cutouts **191**, **271** and **272** and the edges of the pixel electrodes **190**.

[0080] Accordingly, **16** sub-regions having various tilt directions, which are partitioned by edges of a pixel electrode **190**, three cutouts **191**, **271** and **272** partitioning the pixel electrode **190**, and three imaginary transverse lines passing through the meeting points of the oblique portions of the cutouts **271** and **272**, are formed in a pixel region of the LC layer **300**, which are located on the pixel electrode **190**. Each sub-region has two major edges defined by adjacent two of the cutouts **191**, **271** and **272** and the oblique edges of the pixel electrode **190**, which are spaced apart preferably from about 10 microns to about 30 microns. The number of the sub-regions in a pixel region is preferably four if the planar area of the pixel region is smaller than about 100×300 square microns, and, if not, it is preferably four or eight. The number of the sub-regions can be varied by changing the number of the cutouts **271** of the common electrode **270**, by providing cutouts at the pixel electrodes **190**, or by changing the number of curved points of the edges of the pixel electrodes **190**. The sub-regions are classified into a plurality of, preferably four, domains based on the tilt directions.

[0081] In the meantime, the direction of a secondary electric field due to the voltage difference between the pixel electrodes **190** is perpendicular to the edges of the cutouts **271**. Accordingly, the field direction of the secondary electric field coincides with that of the horizontal component of the primary electric field. Consequently, the secondary electric field between the pixel electrodes **190** enhances the determination of the tilt directions of the LC molecules **310**.

[0082] Since the LCD performs inversion such as dot inversion, column inversion, etc., adjacent pixel electrodes are supplied with data voltages having opposite polarity with respect to the common voltage and thus a secondary electric field between the adjacent pixel electrodes is almost always generated to enhance the stability of the domains.

[0083] Since the tilt directions of all domains make an angle of about 45 degrees with the gate lines **121**, which are parallel to or perpendicular to the edges of the panels **100** and **200**, and the 45-degree intersection of the tilt directions and the transmissive axes of the polarizers gives maximum transmittance, the polarizers can be attached such that the transmissive axes of the polarizers are parallel to or perpendicular to the edges of the panels **100** and **200** and it reduces the production cost.

[0084] Since the pixel electrodes **190** are curved several times with maintaining the angle between the oblique edges

of the pixel electrodes **190** and the gate lines **121**, the width of a rectangular area occupied by a pixel electrode **190** that is curved at least twice is much smaller than that occupied by a pixel electrode **190** that is curved once. In addition, the oblique portions of the data lines **171** that define the shape of the pixel electrodes **190** are short and connected in zigzag. Accordingly, the shape of the pixel electrodes **190** is not easily recognized and it is possible to obtain an electric field sufficient to drive the liquid crystal molecules.

[0085] The resistance increase of the data lines **171** due to the curving can be compensated by widening the data lines **171** since distortion of the electric field and increase of the parasitic capacitance due to the increase of the width of the data lines **171** can be compensated by maximizing the size of the pixel electrodes **190** and by adapting a thick organic passivation layer.

[0086] The LCD shown in FIGS. 1-5 can have several modifications.

[0087] The shapes and the arrangements of the cutouts or the protrusions may be varied depending on the design factors such as the size of pixels, the ratio of the transverse edges and the longitudinal edges of the pixel electrodes, the type and characteristics of the liquid crystal layer **3**, and so on.

[0088] A method of manufacturing the TFT array panel shown in FIGS. 1-5 according to an embodiment of the present invention will be now described in detail.

[0089] First, a lower conductive film preferably made of Cr, Mo, or Mo alloy and an upper conductive film preferably made of Al containing metal or Ag containing metal are sputtered in sequence on an insulating substrate **110** and they are wet or dry etched in sequence to form a plurality of gate lines **121**, each including a plurality of gate electrodes **123** and an expansion **125**, and a plurality of storage electrode lines **131** including a plurality of storage electrodes **133**.

[0090] After sequential chemical vapor deposition of a gate insulating layer **140** with thickness of about 1,500-5,000 Å, an intrinsic a-Si layer with thickness of about 500-2,000 Å, and an extrinsic a-Si layer with thickness of about 300-600 Å, the extrinsic a-Si layer and the intrinsic a-Si layer are photo-etched to form a plurality of extrinsic semiconductor stripes and a plurality of intrinsic semiconductor stripes **151** including a plurality of projections **154** on the gate insulating layer **140**.

[0091] Subsequently, two conductive films including a lower conductive film and an upper conductive film and having a thickness of 1,500-3,000 Å are sputtered in sequence and patterned to form a plurality of data lines **171**, each including a plurality of source electrodes **173** and an expansion **179**, a plurality of drain electrodes **175**, and a plurality of storage capacitor conductors **177**. The lower conductive film is preferably made of Cr, Mo, or Mo alloy, and the upper conductive film is preferably made of Al containing metal or Ag containing metal.

[0092] Thereafter, portions of the extrinsic semiconductor stripes, which are not covered with the data lines **171** and the drain electrodes **175**, are removed to complete a plurality of ohmic contact stripes **161** including a plurality of projections **163** and a plurality of ohmic contact islands **165** and to expose portions of the intrinsic semiconductor stripes **151**.

Oxygen plasma treatment preferably follows in order to stabilize the exposed surfaces of the semiconductor stripes **151**.

[0093] Next, a passivation layer **180** made of a photosensitive organic insulator is coated and exposed through a photo-mask having a plurality of transmissive areas and a plurality of slit areas disposed around the transmissive areas. Accordingly, portions of the passivation layer **180** facing the transmissive areas absorb the full energy of the light, while portions of the passivation layer **180** facing the slit areas partially absorb the light energy. The passivation layer **180** is then developed to form a plurality of contact holes **181** and **183** exposing portions of the drain electrodes **175** and portions of the expansions **179** of the data lines **171**, respectively, and to form upper portions of a plurality of contact holes **182** exposing portions of the gate insulating layer **140** disposed on the expansions **125** of the gate lines **121**. Since the portions of the passivation layer **180** facing the transmissive areas are removed to its full thickness, while the portions facing the slit areas remain to have reduced thickness, sidewalls of the contact holes **181**, **182** and **183** have stepped profiles.

[0094] After removing the exposed portions of the gate insulating layer **140** to expose the underlying portions of the expansions **125** of the gate insulating layer **140**, the exposed portions of the upper conductive films **752**, **792** and **252** of the drain electrodes **175**, the expansions **179** of the data lines **171**, and the expansions **125** of the gate lines **121** are removed to expose underlying portions of the lower conductive films **751**, **791** and **251** of the drain electrodes **175**, the expansions **179** of the data lines **171**, and the expansions **125** of the gate lines **121**.

[0095] Finally, a plurality of pixel electrodes **190** and a plurality of contact assistants **92** and **97** are formed on the passivation layer **180** and on the exposed portions of the lower conductive films **751**, **791** and **251** of the drain electrodes **175**, the expansions **125** of the gate lines **121**, and the expansions **179** of the data lines **171** by sputtering and photo-etching an IZO or ITO layer with thickness of about **400-500 Å**.

[0096] An LCD according to another embodiment of the present invention will be described in detail with reference to **FIGS. 6 and 7**.

[0097] **FIG. 6** is a layout view of an LCD according to another embodiment of the present invention, and **FIG. 7** is a sectional view of the LCD shown in **FIG. 6** taken along the line VI-VI'.

[0098] Referring to **FIGS. 6 and 7**, an LCD according to this embodiment also includes a TFT array panel **100**, a common electrode panel **200**, and a LC layer **300** interposed therebetween.

[0099] Layered structures of the panels **100** and **200** according to this embodiment are almost the same as those shown in **FIGS. 1-5**.

[0100] Regarding the TFT array panel **100**, a plurality of gate lines **121** including a plurality of gate electrodes **123** and a plurality of storage electrode lines **131** including a plurality of storage electrodes **133** are formed on a substrate **110**, and a gate insulating layer **140**, a plurality of semiconductor stripes **151** including a plurality of projections **154**,

and a plurality of ohmic contact stripes **161** including a plurality of projections **163** and a plurality of ohmic contact islands **165** are sequentially formed thereon. A plurality of data lines **171** including a plurality of source electrodes **173** and a plurality of drain electrodes **175** are formed on the ohmic contacts **161** and **165**, and a passivation layer **180** is formed thereon. A plurality of contact holes **181**, **182** and **183** are provided at the passivation layer **180** and the gate insulating layer **140**, and a plurality of pixel electrodes **190** and a plurality of contact assistants **95** and **97** are formed on the passivation layer **180**. An alignment layer **11** is formed thereon.

[0101] Regarding the common electrode panel **200**, a light blocking member **220**, a plurality of color filters **230**, an overcoat **250**, a common electrode **270**, and an alignment layer **21** are formed on an insulating substrate **210**.

[0102] Different from the LCD shown in **FIGS. 1-5**, each pixel electrode **190** has a pair of cutouts **191a** and **191b** extending from opposite edges of the pixel electrode **190** along a data line **171** to approach each other and thus the pixel electrode **190** is partitioned into left and right partitions **190a** and **190b** disposed opposite each other with respect to the data line **171** and connected by a connection **192** disposed on a center of the pixel electrode **190**.

[0103] Furthermore, each storage electrode line **131** has two stems extending in the transverse direction and placed near the gate lines **121**. The two stems are connected to each other through a plurality of connections extending along a gap between two adjacent pixel electrodes **190** and overlapping the pixel electrodes **190**, and one of the stems has the storage electrodes **133**.

[0104] Moreover, there is no storage capacitor conductor shown in **FIGS. 1-5** and each drain electrode **175** has an expansion overlapping a storage electrode **133** to form a storage capacitor.

[0105] The storage electrodes **133**, the expansions of the drain electrodes **175**, and the contact holes **181** exposing portions of the drain electrodes **175** have shapes of parallelogram.

[0106] In addition, the semiconductor stripes **151** have almost the same planar shapes as the data lines **171** and the drain electrodes **175** as well as the underlying ohmic contacts **161** and **165**. However, the projections **154** of the semiconductor stripes **151** include some exposed portions, which are not covered with the data lines **171** and the drain electrodes **175**, such as portions located between the source electrodes **173** and the drain electrodes **175**.

[0107] A manufacturing method of the TFT array panel according to an embodiment simultaneously forms the data lines **171**, the drain electrodes **175**, the semiconductors **151**, and the ohmic contacts **161** and **165** using one photolithography process.

[0108] A photoresist pattern for the photolithography process has position-dependent thickness, and in particular, it has first and second portions with decreased thickness. The first portions are located on wire areas that will be occupied by the data lines **171** and the drain electrodes **175** and the second portions are located on channel areas of TFTs.

[0109] The position-dependent thickness of the photoresist is obtained by several techniques, for example, by

providing translucent areas on the exposure mask **300** as well as transparent areas and light blocking opaque areas. The translucent areas may have a slit pattern, a lattice pattern, a thin film(s) with intermediate transmittance or intermediate thickness. When using a slit pattern, it is preferable that the width of the slits or the distance between the slits is smaller than the resolution of a light exposer used for the photolithography. Another example is to use reflowable photoresist. In detail, once a photoresist pattern made of a reflowable material is formed by using a normal exposure mask only with transparent areas and opaque areas, it is subject to reflow process to flow onto areas without the photoresist, thereby forming thin portions.

[0110] As a result, the manufacturing process is simplified by omitting a photolithography step.

[0111] Many of the above-described features of the LCD shown in **FIGS. 1-5** may be appropriate to the LCD shown in **FIGS. 6 and 7**.

[0112] An LCD according to another embodiment of the present invention will be described in detail with reference to **FIGS. 8 and 9**.

[0113] **FIG. 8** is a layout view of an LCD according to another embodiment of the present invention, and **FIG. 9** is a sectional view of the LCD shown in **FIG. 8** taken along the line IX-IX'.

[0114] Referring to **FIGS. 8 and 9**, an LCD according to this embodiment also includes a TFT array panel **100**, a common electrode panel **200**, and a LC layer **300** interposed therebetween.

[0115] Layered structures of the panels **100** and **200** according to this embodiment are almost the same as those shown in **FIGS. 1-5**.

[0116] Regarding the TFT array panel **100**, a plurality of gate lines **121** including a plurality of gate electrodes **123** and a plurality of storage electrode lines **131** including a plurality of storage electrodes **133** are formed on a substrate **110**, and a gate insulating layer **140**, a plurality of semiconductor stripes **151** including a plurality of projections **154**, and a plurality of ohmic contact stripes **161** including a plurality of projections **163** and a plurality of ohmic contact islands **165** are sequentially formed thereon. A plurality of data lines **171** including a plurality of source electrodes **173** and a plurality of drain electrodes **175** are formed on the ohmic contacts **161** and **165**, and a passivation layer **180** is formed thereon. A plurality of contact holes **181**, **182** and **183** are provided at the passivation layer **180** and the gate insulating layer **140**, and a plurality of pixel electrodes **190** and a plurality of contact assistants **95** and **97** are formed on the passivation layer **180**. An alignment layer **11** is formed thereon.

[0117] Regarding the common electrode panel **200**, a light blocking member **220**, a plurality of color filters **230**, an overcoat **250**, a common electrode **270**, and an alignment layer **21** are formed on an insulating substrate **210**.

[0118] Different from the LCD shown in **FIGS. 1-5**, a plurality of red, green and blue color filter stripes R, G and B are formed under the passivation layer **180**. Each of the color filter stripes R, G and B are disposed substantially between adjacent two the data lines **171** and extends in a longitudinal direction along the pixel electrodes **190** such

that it is periodically curved. The color filter stripes R, G and B are not disposed on a peripheral area which is provided with end portions **179** of the data lines **171**. The color filter stripes R, G and B have a plurality of openings placed on the drain electrodes **175** and the storage capacitor conductors **177** and having tapered sidewalls. Edges of adjacent color filter stripes R, G and B exactly match with each other. However, the edges may overlap to block the light leakage between the pixel areas.

[0119] Many of the above-described features of the LCD shown in **FIGS. 1-5** may be appropriate to the LCD shown in **FIGS. 8 and 9**.

[0120] Since the pixel electrodes **190** are curved several times with maintaining the angle between the oblique edges of the pixel electrodes **190** and the gate lines **121**, the width of a rectangular area occupied by a pixel electrode **190** that is curved at least twice is much smaller than that occupied by a pixel electrode **190** that is curved once. In addition, the oblique portions of the data lines **171** that define the shape of the pixel electrodes **190** are short and connected in zigzag. Accordingly, the shape of the pixel electrodes **190** is not easily recognized and it is possible to obtain an electric field sufficient to drive the liquid crystal molecules.

[0121] While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the art will appreciate that various modifications and substitutions can be made thereto without departing from the spirit and scope of the present invention as set forth in the appended claims.

What is claimed is:

1. A thin film transistor array panel comprising:

a substrate;

a plurality of first signal lines formed on the substrate;

a plurality of second lines formed on the substrate, intersecting the first signal line, and including a plurality of curved portions having at least two curve points and a plurality of intermediate portions, the curved portions and the intermediate portions alternately connected;

a plurality of pixel electrodes located substantially in areas defined by the first and the second signal lines; and

a plurality of thin film transistors connected to the first and the second signal lines and the pixel electrodes.

2. The thin film transistor array panel of claim 1, wherein each of the curved portions of the data lines comprises a plurality of rectilinear portions connected to each other and making angles of about 45 degrees with the gate lines in clockwise and counterclockwise manners, respectively.

3. The thin film transistor array panel of claim 1, further comprising a plurality of third signal lines formed on the substrate, extending substantially parallel to the first signal lines, and overlapping the pixel electrodes to form storage capacitors.

4. The thin film transistor array panel of claim 1, wherein the thin film transistors include terminal electrodes connected to the intermediate portions of the second signal lines.

5. The thin film transistor array panel of claim 1, wherein the pixel electrodes have cutouts disposed on the data lines, each cutout bisecting a corresponding of the pixel electrodes into two partitions.

6. A thin film transistor array panel comprising:

a substrate;

a gate line formed on the substrate and including a gate electrode;

a gate insulating layer formed on the gate line;

a semiconductor layer formed on the gate insulating layer;

a data line formed on the substrate and including a curved portion having at least two curved points and including a source electrode disposed on the semiconductor layer at least in part;

a drain electrode disposed on the semiconductor layer at least in part and disposed opposite the source electrode;

a passivation layer formed on the semiconductor layer; and

a pixel electrode having an edge curved along the data line.

7. The thin film transistor array panel of claim 6, wherein the curved portion of the data line comprises a plurality of portions making a clockwise angle of about 45 degrees and a counterclockwise angle of about 45 degrees with respect to the gate line.

8. The thin film transistor array panel of claim 6, further comprising a storage electrode line that extends substantially parallel to the gate line and has a storage electrode overlapping a conductor connected to the pixel electrode to form a storage capacitor.

9. The thin film transistor array panel of claim 6, wherein the pixel electrode is disposed on the passivation layer.

10. The thin film transistor array panel of claim 6, wherein the first passivation layer comprises organic or inorganic insulating material.

11. The thin film transistor array panel of claim 6, further comprising a color filter formed on the first passivation layer.

12. The thin film transistor array panel of claim 13, wherein the color filter extends substantially parallel to the data line.

13. The thin film transistor array panel of claim 6, wherein the semiconductor layer has substantially the same planar shape as the data line, the source electrode, and the drain electrode except for a first portion.

14. A liquid crystal display comprising:

a first substrate;

a gate line formed on the first substrate and including a gate electrode;

a data line formed on the first substrate and including a curved portion having at least two curve points and an intersecting portion;

a thin film transistor connected to the gate line and the data line;

a pixel electrode connected to the thin film transistor;

a second substrate facing the first substrate;

a common electrode formed on the second substrate;

a liquid crystal layer disposed between the first and the second substrates; and

at least a domain defining member formed on at least one of the first and the second substrates and partitioning the liquid crystal layer into a plurality of domains, each domain having two major edges substantially parallel to the curved portion of the data line.

15. The liquid crystal display of claim 14, wherein the liquid crystal layer has negative dielectric anisotropy and is vertically aligned.

16. The liquid crystal display of claim 14, wherein the domain partitioning member comprises a cutout in the pixel electrode or the common electrode.

* * * * *

专利名称(译)	液晶显示器及其薄膜晶体管阵列面板		
公开(公告)号	US20040263756A1	公开(公告)日	2004-12-30
申请号	US10/877673	申请日	2004-06-25
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	TAK YOUNG MI BAEK SEUNG SOO KIM DONG GYU		
发明人	TAK, YOUNG-MI BAEK, SEUNG-SOO KIM, DONG-GYU		
IPC分类号	G02F1/1343 G02F1/1333 G02F1/1362 G02F1/1368 G02F1/139 G09F9/30		
CPC分类号	G02F1/133707 G02F1/134336 G02F1/1393 G02F2001/136222		
优先权	1020030041987 2003-06-26 KR		
其他公开文献	US7342633		
外部链接	Espacenet USPTO		

摘要(译)

提供一种薄膜晶体管阵列面板，包括：基板；多个第一信号线形成在基板上；多个第二线形成在基板上，与第一信号线交叉，并包括多个具有至少两个弯曲点的弯曲部分和多个中间部分，弯曲部分和中间部分交替连接；多个像素电极，基本上位于由第一和第二信号线限定的区域中；多个薄膜晶体管连接到第一和第二信号线以及像素电极。

