



US007671953B2

(12) **United States Patent**
Ha

(10) **Patent No.:** **US 7,671,953 B2**
(45) **Date of Patent:** **Mar. 2, 2010**

(54) **SUBSTRATE FOR LIQUID CRYSTAL
DISPLAY**

(75) Inventor: **Kyoung Su Ha**, Seoul (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 595 days.

5,214,521 A *	5/1993	Kwon et al.	349/32
5,398,127 A *	3/1995	Kubota et al.	349/42
5,892,558 A *	4/1999	Ge et al.	349/43
6,317,175 B1 *	11/2001	Salerno et al.	349/45
6,610,997 B2 *	8/2003	Murade	257/72
6,628,367 B2 *	9/2003	Hirabayashi et al.	349/187
6,683,592 B1 *	1/2004	Murade	345/87
6,762,809 B1 *	7/2004	Murade	349/110

FOREIGN PATENT DOCUMENTS

(21) Appl. No.: **10/329,470**

JP	06-082832	3/1994
KR	2002002656 A *	1/2002

(22) Filed: **Dec. 27, 2002**

(65) **Prior Publication Data**

US 2003/0197828 A1 Oct. 23, 2003

* cited by examiner

Primary Examiner—Timothy Rude

(74) *Attorney, Agent, or Firm*—Birch, Stewart, Kolasch &
Birch LLP

(30) **Foreign Application Priority Data**

Apr. 17, 2002 (KR) 10-2002-0020939

(57) **ABSTRACT**

(51) **Int. Cl.**
G02F 1/1343 (2006.01)

(52) **U.S. Cl.** **349/139**

(58) **Field of Classification Search** 349/147,
349/148

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,913,531 A * 4/1990 Efron et al. 349/27

A substrate for a liquid crystal display includes: a line-shaped fine groove formed on the substrate; and a metal line at least formed within the fine groove. The substrate enables a decrease in the height difference between the metal line and the surface of the substrate, thereby enhancing reliability in manufacturing the liquid crystal display. In addition, the aperture ratio of the pixel is enhanced, brightness is enhanced, and high resolution is realized.

7 Claims, 5 Drawing Sheets




Fig. 1 (Prior Art)




Fig. 2 (Prior Art)




Fig. 3A (Prior Art)




Fig. 3B (Prior Art)





Fig. 4 (Prior Art)






FIG. 5




FIG. 6a




FIG. 6b




FIG. 7a




FIG. 7b

SUBSTRATE FOR LIQUID CRYSTAL DISPLAY

This nonprovisional application claims priority under 35 U.S.C. §119(a) on patent application Ser. No. 20939/2002 filed in Korea on Apr. 17, 2002, which is herein incorporated by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a substrate for a liquid crystal display, and more particularly, to a substrate for a liquid crystal display in which metal lines including a gate line and a data line are formed to be suitable for realizing a high resolution in a large-sized screen.

2. Discussion of the Background Art

Generally, a liquid crystal display (LCD) includes a TFT (thin film transistor) array substrate on which thin film transistors (TFTs) and pixel electrodes are arranged and a color filter substrate facing the TFT array substrate on which color filters and a common electrode are formed, and a liquid crystal injected into a space between the TFT array substrate and the color filter substrate. These LCDs display images by using an optical switching property of the liquid crystal interposed between the two substrates. In recent times, LCDs are increasing in popularity as a next generation display device to replace the cathode ray tube (CRT) because of their light weight and slim characteristics.

FIG. 1 is a plan view schematically showing a configuration of metal lines formed on a substrate for an LCD.

As shown in FIG. 1, a plurality of metal lines are formed on a substrate for an LCD. For instance, the metal lines include a plurality of gate lines **110a** to **110n** (**110**) formed in a length direction and a plurality of data lines **120a** to **120n** (**120**) formed in a width direction and perpendicularly crossed with the gate lines. A plurality of gate line pads **111a** to **111n** (**111**) into which gate driving signals for respective pixels are inputted, are formed at one end of the gate lines **110**. A plurality of data line pads **121a** to **121n** (**121**) into which data driving signals for respective pixels are inputted are formed at one end of the data lines **120**.

Here, unit pixel **130** is defined as a region in which a pair of gate lines are crossed with a pair of data lines.

In detail, the data lines **110** and the gate lines **120** are made of a conductive material and applies a driving current to the TFT element corresponding to the pixel **130**. The data lines **110** and the gate lines **120** are formed by a method including the steps of depositing a metal film and a photoresist film on a substrate on which TFTs are arranged, and selectively removing the photoresist film and the metal film through a photolithography process.

As time progresses, the metal line including these gate lines and data lines is becoming increasingly lengthened according to a trend of increasing the size of LCDs.

FIG. 2 is a perspective view of a metal line to depict the resistance characteristic of the metal line.

When the length of the metal line is l , the sectional area is A , and the conductivity is σ , a total resistance of the metal line R equals to $l/6A$. Accordingly, if the flowing current is I , a voltage drop ΔV in the metal line is expressed by the following equation: $\Delta V = IR = lI/6A$. This relation means that when the sectional area A (including elements of the thickness and the line width) of the gate line **110** and the data line **120** is constant, the voltage drop ΔV depends on the respective lengths of the gate line **110** and the data line **120**.

As a result, although an equal driving voltage is applied to the gate line pad **111a** and the data line pad **121a** from the drive IC (not shown) of the LCD, the voltages applied to the gate line **110** or the data line **120** varies at a specific location depending on the resistance. For example, according to the lengths of the gate lines **110** and the data lines **120**, a lower voltage is applied to a pixel (P_n of FIG. 1) further away from the pads **111a**, **121a** than a pixel (P_a of FIG. 1) placed nearer to the pads **111a**, **121a**. Accordingly, the pixel (P_n of FIG. 1) needs a longer charging time than the pixel (P_a of FIG. 1) when the pixels (P_n and P_a) are charged up to a specific electric charge. In other words, if the resistance increases, the current flowing through under the same voltage decreases, so that the charging time is lengthened.

The extended charging time causes a signal delay phenomenon in which the frequency for driving the LCD panel is lowered.

In order to solve this problem, it is necessary to decrease an overall resistance of the metal line by decreasing the length of the metal line, or increasing the sectional area of the metal line.

However, upon considering the trend in increasing a size of the LCDs, it is substantially difficult to shorten the length of the metal line.

A background art method for increasing the sectional area of the metal line, includes increasing the line width or increasing the thickness of the metal line.

However, if the line width of the metal line increases and the thickness decreases, little improvement in the height difference corresponding to the decrease in the thickness is obtained, but the lowering in the aperture ratio of the pixel due to the increase in the line width results. The lowering phenomenon in the aperture ratio is described with reference to FIG. 3.

FIG. 3a and FIG. 3b are sectional views of substrates for LCDs illustrating the variation in the aperture ratio depending on the increase in the line width of the metal line. Specifically, FIG. 3a shows a status prior to increasing the line width of the metal line, and FIG. 3b shows a status after the line width of the metal line increases.

The metal line for the gate line and the data line are generally made of an opaque metal. To this end, the increase in the line width allows the light transmission area of a substrate **320** to be decreased from $L1$ to $L2$. The decrease in the light transmission area causes more of the light irradiated from a backlight to be lost while light is transmitted from the substrate resulting in the aperture ratio of the pixel being lowered.

The occurrence of the aforementioned phenomenon is not restricted only to the transmission type LCD substrate but is applied to the reflection type LCD substrate likewise.

Of course, the problem of lowering in the aperture ratio can be resolved by increasing the thickness of the metal line instead of increasing the line width of the metal line.

FIG. 4 is a schematic view for illustrating that a crack is generated in the inorganic insulating film formed on the metal line.

As shown in FIG. 4, when the thickness of the metal line is increased, a serious height difference is generated between the metal line portion and the non-metal line portion. So, if the inorganic insulating film **330** is further deposited on the metal line **120**, a problem occurs in that a crack is generated in the inorganic insulating film **330**, so that many defective devices are mass-produced. Hence, the thickness of the metal line cannot be increased above a certain limit.

Because of the above problems, the background art method for forming the metal line has prevented process failures by decreasing the aperture ratio of the pixel so as to solve the signal delay problem.

However, in the manufacturing process of a large-sized, high brightness and high resolution LCD sought after at the present time, there is a problem in applying the aforementioned methods due to a limitation on the application. Especially, in order to realize a large-sized LCD, it is essentially required to decrease the resistance of the metal line.

SUMMARY OF THE INVENTION

To achieve these objects and other advantages and in accordance with the purpose of the invention, as embodied and broadly described herein, there is provided a substrate for a liquid crystal display. The substrate includes: a line-shaped fine groove formed on the substrate; and a metal line at least formed within the fine groove.

In an aspect of the present invention, there is provided a substrate for a liquid crystal display. The substrate includes: a plurality of first line-shaped fine grooves formed parallel to one another in a length direction on the substrate; a plurality of second line-shaped fine grooves formed parallel to one another in a width direction on the substrate; a first metal line at least formed within the first line-shaped fine grooves; and a second metal line at least formed within the second line-shaped fine grooves.

In another aspect of the present invention, there is provided a liquid crystal display. The liquid crystal display includes: a TFT array substrate including thin film transistors, pixel electrodes, a line for supplying current to the thin film transistors, and a fine groove formed on the TFT array substrate and in which the line is received to reduce a height difference between the line and the surface of the TFT array substrate; a color filter substrate facing the TFT array substrate, and on which a color filter and a common electrode are formed; and a liquid crystal layer interposed between the TFT array substrate and the color filter substrate.

According to the above liquid crystal display, it is possible to decrease the resistance of the metal line formed on the substrate.

In addition, the sectional area of the metal line can be increased and the resistance can be decreased, thereby achieving an objective of easily realizing a large-sized LCD.

It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the present invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the present invention and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the present invention and together with the description serve to explain principles of the present invention. In the drawings:

FIG. 1 is a plan view schematically showing a configuration of metal lines formed on a substrate for an LCD;

FIG. 2 is a perspective view of a metal line to depict the resistance characteristic of the metal line;

FIG. 3a and FIG. 3b are sectional views of substrates for LCDs illustrating the variation in the aperture ratio depending on the increase in the line width of the metal line;

FIG. 4 is a schematic view for illustrating that a crack is generated in the inorganic insulating film formed on the metal line;

FIG. 5 is a schematic view of metal lines formed on a substrate for a liquid crystal display according to an embodiment of the present invention;

FIG. 6 is a schematic sectional view of the first metal line shown in FIG. 5; and

FIG. 7 is a schematic sectional view of the second metal line shown in FIG. 5.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Reference will now be made in detail to a preferred embodiment of the present invention with reference to the attached drawings.

FIG. 5 is a schematic view of metal lines formed on a substrate for a liquid crystal display according to an embodiment of the present invention.

As shown in FIG. 5, a substrate **530** for a liquid crystal display according to the present invention includes a plurality of first fine grooves **511** formed parallel to each other in a length direction on the substrate, and a plurality of second fine grooves **521** formed parallel to each other in a width direction perpendicular to the length direction on the substrate. A first metal line **510** including a gate line is formed at least within the first fine groove and a second metal line **520** including a data line is formed at least within the second fine groove **521**.

Width and thickness of the first and second fine grooves **511** and **521** can be concretely determined by the line width and thickness of the first and second metal lines **510** and **520** formed on the first and second fine grooves **511** and **521**. For instance, in an LCD of the background art, the first and second metal lines **510** and **520** have a line width ranging from 7 μm to 20 μm and a thickness ranging from 1,000 $\text{\AA}$ to 4,000 $\text{\AA}$. Accordingly, the first and second fine grooves **511** and **521** are also formed to have a line width ranging from 7 μm to 20 μm and a thickness ranging from 1,000 $\text{\AA}$ to 4,000 $\text{\AA}$.

A manufacturing process of the substrate for a liquid crystal display is described with reference to FIG. 6.

FIG. 6 is a schematic sectional view of the first metal line shown in FIG. 5.

First, referring to FIG. 6a, a substrate **530** for forming TFTs and pixel electrodes is prepared. The substrate **530** is made of glass or plastic. A first fine groove **511** for the formation of a first metal line **510** including a gate line is formed in a length direction on the substrate **530**.

In the meanwhile, if the substrate **530** is made of glass, the first fine groove **511** can be formed by an etch process. If the substrate **530** is made of plastic, the first fine groove **511** can be formed by a molding process using a die.

If the first fine groove **511** is formed on the substrate **530** by the etch process or the molding process, a first metal line **510** is formed on the first fine groove **511**. In more detail, a conductive material, for instance, aluminum or an aluminum alloy is deposited on the substrate **530**, a photoresist film is coated on the conductive material, the photoresist film is patterned by a photolithography process, the underlying conductive material is selectively removed by an etch process with the patterned photoresist film as a mask, and the patterned photoresist film is then removed. The finally remaining conductive material pattern forms the first metal line **510**.

The substrate formed as above does not cause a height difference problem between the uppermost surface of the first metal line **510** and the upper surface of the substrate **530** although it uses a thicker metal line than the metal line of the

background art. Also, it is possible to further decrease the height difference by making the first fine groove **511** deeper. In other words, the height difference between the first metal line **510** and the substrate **530** decreases by the thickness of the substrate **530**.

Thus, as the height difference of the metal line **510** decreases, although an upper film such as an inorganic insulating film **610** is formed on the first metal line **510** as shown in FIG. **6b**, the possibility of a crack occurring in the inorganic insulating film **610** decreases remarkably, such that yield in the manufacturing process of the LCDS is enhanced. In addition, as shown in FIG. **6b**, since the sidewall of the metal line **510** is formed with a slope, the possibility of a crack occurring further decreases.

Also, since the metal line **510** decreases in line width but increases in thickness, it has an area that is equal to or greater than the area of the metal line in the background art. This means that resistance per unit length of the metal line decreases compared with the resistance of the background art.

In other words, the metal line according to the present invention achieves a low resistance characteristic and accordingly the signal delay and the signal distortion phenomenon due to the voltage drop in the metal line decrease remarkably.

FIG. **7** is a schematic sectional view of the second metal line shown in FIG. **5**.

Referring to FIG. **7a**, a substrate for a liquid crystal display includes a second fine groove **521** formed in a width direction on the substrate, an inorganic insulating film **710** formed on a predetermined portion of the substrate including the second fine groove **521**, and a second metal line **520** formed on the inorganic insulating film **710**. A passivation layer **720** is further formed on the second metal line **520** and the inorganic insulating film **710** as shown in FIG. **7b**.

Particularly, the second metal line **520** is formed on the inorganic insulating film **710** as shown in FIG. **7a**.

Here, the inorganic insulating film **710** is provided to insulate the first metal line **510** (FIG. **5**) and the second metal line **520** formed crosswise with the first metal line **510**. In more detail, the inorganic insulating film **710** is insertedly formed on a contact surface between the first metal line **510** and the second metal line **520** at the crossing portion of the first metal line **510** and the second metal line **520**, but is formed between the second fine groove **521** and the second metal line **520** as shown in FIGS. **7a** and **7b** at a region other than the crossing portion.

Since the inorganic insulating film **710** is formed in a recessed shape like the shape of the second fine groove **521**, although the second metal line **520** having a thickness greater than that of the background art is formed, the height difference decreases remarkably compared with the height difference in the background art. As a result, although an upper film such as the passivation layer **720** is formed, the possibility of crack occurrence decreases. Also, as shown in FIGS. **7a** and **7b**, since the side portions of the second metal line **520** are formed with a slope, the possibility in crack occurrence decreases remarkably.

In the meanwhile, the forming processes of the second metal line **520**, the inorganic insulating film **710** and the passivation layer **720** can be formed by the same method as that of the first metal line **510**.

Thus, although the first and second metal lines **510** and **520** according to the present invention have a thickness greater than a thickness of the lines in the background art, they have a height difference less than a height difference in the background art, due to the existence of the fine grooves. As a result, the quality of the upper films formed on the metal lines **510** and **520**, i.e., the inorganic insulating film **610** and the passi-

vation layer **720** is enhanced and the reliability in the manufacturing process is also improved.

In addition, the aperture ratio of the pixels and the luminance are enhanced, so that a high resolution can be obtained.

Further, it becomes possible to form the metal lines of the low resistance characteristic which is required in manufacturing a large-sized LCD without lowering of the aperture ratio or increase in the height difference.

In particular, in case the substrate of the present invention is used, a high quality large-sized LCD can be produced and a high resolution even in a small-sized LCD can be obtained.

The foregoing embodiment is merely exemplary and is not to be construed as limiting the present invention. The present teachings can be readily applied to other types of apparatuses. The description of the present invention is intended to be illustrative, and not to limit the scope of the claims. Many alternatives, modifications, and variations will be apparent to those skilled in the art.

What is claimed is:

1. A substrate for a liquid crystal display, the substrate comprising:

a plurality of first line-shaped fine grooves formed parallel to each other in a lengthwise direction on the substrate;

a plurality of gate lines, each of the gate lines formed to contact an entirety of a top surface and a sidewall surface within the corresponding first line-shaped fine groove and extended to a first portion higher than a surface of the substrate;

an inorganic insulating film formed on the substrate including the gate lines;

a plurality of second line-shaped fine grooves formed parallel to one another in a width direction on the substrate;

a plurality of data lines, each of the data lines formed to contact an entirety of a top surface and a sidewall surface within a recess portion of the inorganic insulating film corresponding to the second line-shaped fine groove and extended to a second portion higher than a surface of the inorganic insulating film; and

a passivation layer formed on the substrate including the data lines.

2. The substrate according to claim 1, wherein the first and second line-shaped fine grooves have a line width ranging from 7 μm to 20 μm .

3. The substrate according to claim 1, wherein the first and second line-shaped fine grooves have a thickness ranging from 1,000 $\text{\AA}$ to 4,000 $\text{\AA}$.

4. A liquid crystal display comprising:

a plurality of first line-shaped fine grooves formed parallel to each other in a lengthwise direction on the substrate;

a plurality of gate lines, each of the gate lines formed to contact an entirety of a top surface and a sidewall surface within the corresponding first line-shaped fine groove and extended to a first portion higher than a surface of the substrate;

an inorganic insulating film formed on the substrate including the gate lines;

a plurality of second line-shaped fine grooves formed parallel to one another in a width direction on the substrate;

a plurality of data lines, each of the data lines formed to contact an entirety of a top surface and a sidewall surface within a recess portion of the inorganic insulating film corresponding to the second line-shaped fine groove and extended to a second portion higher than a surface of the inorganic insulating film;

a passivation layer formed on the substrate including the data lines;

7

a color filter substrate facing the TFT array substrate and on which a color filter and a common electrode are formed; and

a liquid crystal layer interposed between the TFT array substrate and the color filter substrate.

5. The liquid crystal display according to claim 4, wherein the fine grooves are formed by an etch process when the TFT array substrate is made of glass.

8

6. The liquid crystal display according to claim 4, wherein the fine grooves are formed by a molding process using a die when the TFT array substrate is made of plastic.

7. The liquid crystal display according to claim 4, wherein the lines comprise an inclined side face.

* * * * *

专利名称(译)	用于液晶显示器的基板		
公开(公告)号	US7671953	公开(公告)日	2010-03-02
申请号	US10/329470	申请日	2002-12-27
[标]申请(专利权)人(译)	HA KYOUNG SU		
申请(专利权)人(译)	HA KYOUNG SU		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	HA KYOUNG SU		
发明人	HA, KYOUNG SU		
IPC分类号	G02F1/1343 G02F1/1345 G02F1/1362		
CPC分类号	G02F1/136286		
审查员(译)	粗鲁, TIMOTHY		
优先权	1020020020939 2002-04-17 KR		
其他公开文献	US20030197828A1		
外部链接	Espacenet USPTO		

摘要(译)

一种用于液晶显示器的基板，包括：形成在基板上的线形细槽；和至少在细槽内形成的金属线。基板能够减小金属线与基板表面之间的高度差，从而提高制造液晶显示器的可靠性。另外，增强了像素的开口率，增强了亮度，并且实现了高分辨率。

