



US006678018B2

(12) **United States Patent**
Park et al.

(10) **Patent No.:** **US 6,678,018 B2**
(45) **Date of Patent:** **Jan. 13, 2004**

(54) **THIN FILM TRANSISTOR ARRAY
SUBSTRATE FOR A LIQUID CRYSTAL
DISPLAY AND THE METHOD FOR
FABRICATING THE SAME**

5,482,173 A * 1/1996 Park et al. 216/23
5,907,379 A * 5/1999 Kim et al. 349/141
6,287,899 B1 * 9/2001 Park et al. 438/149
6,391,499 B1 * 5/2002 Kim et al. 430/5

(75) Inventors: **Woon-Yong Park**, Suwon (KR);
Hyeon-Hwan Kim, Cheonan (KR);
Dong-Hyeon Ki, Cheonan (KR)

* cited by examiner

(73) Assignee: **Samsung Electronics Co., Ltd.**, Suwon (KR)

Primary Examiner—Robert H. Kim
Assistant Examiner—David Y. Chung
(74) *Attorney, Agent, or Firm*—McGuireWoods LLP

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 335 days.

(57) **ABSTRACT**

A method for fabricating a thin film array substrate for a liquid crystal display includes steps of forming a gate line assembly and a common electrode line assembly on a first substrate. The gate line assembly includes a plurality of gate lines and gate pads, and the common electrode line assembly includes common signal lines and common electrodes. Thereafter, a gate insulating layer is formed on the first substrate, and a semiconductor pattern and an ohmic contact pattern are formed on the gate insulating layer. A data line assembly and pixel electrodes are then formed on the first substrate. The data line assembly includes a plurality of data lines, data pads, and source and drain electrodes. The pixel electrodes are connected to the drain electrodes while proceeding parallel to the common electrodes. A passivation layer is formed on the substrate. The passivation layer and the gate insulating layer are etched such that the gate pads and the data pads are exposed to the outside. At this time, the etching is performed after an assembly process where a second substrate is arranged to face the first substrate and assembled together and the passivation layer and the gate insulating layer are exposed outside of the second substrate.

(21) Appl. No.: **09/779,705**

(22) Filed: **Feb. 9, 2001**

(65) **Prior Publication Data**

US 2002/0057393 A1 May 16, 2002

(30) **Foreign Application Priority Data**

Feb. 10, 2000 (KR) 2000-6273
Apr. 24, 2000 (KR) 2000-21693

(51) **Int. Cl.**⁷ **G02F 1/136**

(52) **U.S. Cl.** **349/43; 349/141; 438/30**

(58) **Field of Search** 349/141, 149,
349/151, 152, 153, 187; 324/770; 257/59;
438/30

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,272,355 A * 12/1993 Namavar et al. 257/3

14 Claims, 37 Drawing Sheets




FIG.1




FIG.2




FIG.3




FIG. 5




FIG. 6A




FIG. 6B




FIG. 7B




FIG. 8




FIG.10




FIG. 11




FIG. 12




FIG. 13A




FIG.13B




FIG. 14A




FIG. 14B




FIG.16




FIG.17




FIG. 18A




FIG. 18B




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24A




FIG. 24B




FIG. 24C




FIG. 25A




FIG. 25B




FIG. 26




FIG. 27




FIG. 28A




FIG. 28B




FIG. 29




FIG. 30




FIG. 31




FIG. 32A




FIG. 32B




FIG. 33A




FIG. 33B




FIG. 34A




FIG. 34B




FIG. 35A




FIG. 35B





FIG. 35C



1

**THIN FILM TRANSISTOR ARRAY
SUBSTRATE FOR A LIQUID CRYSTAL
DISPLAY AND THE METHOD FOR
FABRICATING THE SAME**

BACKGROUND OF THE INVENTION

(a) Field of the Invention

The present invention relates to a thin film transistor (TFT) array substrate for a liquid crystal display, and a method for fabricating the same.

(b) Description of the Related Art

A liquid crystal display is one of flat panel display devices that has been currently used in a most extensive manner. The liquid crystal display has two substrates, and a liquid crystal layer sandwiched between the substrates. One of the substrates is provided with thin film transistors (TFTs), and pixel electrodes. The TFT array substrate is fabricated through forming thin films on the substrate, and repeatedly performing photolithography on the thin films.

The number of masks employed in the photolithography process that represents the number of processing steps becomes to be a critical factor to reduce the production cost. In order to lower the production cost, it is required that the number of masks for the photolithography process should be reduced.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a method for fabricating a TFT array substrate for a liquid crystal display, which involves simplified processing steps.

This and other objects may be achieved by a method for fabricating a TFT array substrate for a liquid crystal display where a data line assembly, pixel electrodes and a semiconductor pattern are formed at only one photolithography process.

The method for fabricating a TFT array substrate for a liquid crystal display includes the step of forming a gate line assembly and a common electrode line assembly on a first substrate. The gate line assembly includes a plurality of gate lines and gate pads, and the common electrode line assembly includes common signal lines and common electrodes. Thereafter, a gate insulating layer is formed on the first substrate, and a semiconductor pattern and an ohmic contact pattern are formed on the gate insulating layer. A data line assembly and pixel electrodes are then formed on the first substrate. The data line assembly includes a plurality of data lines, data pads, and source and drain electrodes. The pixel electrodes are connected to the drain electrodes while proceeding parallel to the common electrodes. A passivation layer is formed on the substrate. The passivation layer and the gate insulating layer are etched such that the gate pads and the data pads are exposed to the outside. At this time, the etching is performed after an assembly process where a second substrate is arranged to face the first substrate, and the passivation layer and the gate insulating layer are exposed externally to the second substrate.

Alternatively, the step of exposing the gate and the data pads may be performed after the step of injecting liquid crystal molecules in-between the first and the second substrates facing each other, and sealing the gap between the first and second substrates. Furthermore, a sealant may be partially coated onto the gate and the data pads.

The steps of forming the data line assembly, the pixel electrodes, the ohmic contact pattern and the semiconductor

2

pattern are made through photolithography based on one photoresist pattern having different thickness. The photoresist pattern has a first portion placed between the source and the drain electrodes with a predetermined thickness, a second portion for forming the data line assembly and the pixel electrodes that is thicker than the first portion, and a third portion that is thinner than the first portion.

The photoresist pattern is formed using a mask with a thin film with a light transmission of 20 to 50% corresponding to the first portion of the photoresist pattern, and a thin film with a light transmission of 3% or less corresponding to the second portion of the photoresist pattern.

Alternatively, the photoresist pattern may be made using a mask with a minute pattern corresponding to the area between the source and the drain electrodes while bearing an opening width smaller than the resolution of a light exposing device. The minute pattern may be either a slit pattern or a mosaic pattern with an opening width of 2 μm or less.

Furthermore, supplemental data lines are formed at the step of forming the gate line assembly, and first contact holes exposing the supplemental data lines are formed at the step of forming the gate insulating layer. The steps of forming the ohmic contact pattern, the semiconductor pattern and the first contact holes are made through a photolithography based on one photoresist pattern having different in thickness. The photoresist pattern has a first portion corresponding to the ohmic contact pattern and the semiconductor pattern with a predetermined thickness, a second portion that is thicker than the first portion, and a third portion corresponding to the first contact holes that is thinner than the first portion.

The pixel electrodes are formed in a linear shape while proceeding parallel to the common electrodes.

The method further includes the step of forming one or more light interception patterns to be placed at the same plane as the gate lines with the same material such that each light interception pattern is separated from the gate line and positioned close to the neighboring subsidiary data line while proceeding parallel thereto. The pixel electrodes are partially overlapped with the light interception patterns. Alternatively, the pixel electrodes may be spaced apart from the light interception patterns by 2 μm or less.

The method further includes the steps of forming a gate short circuit line such that the gate short circuit line is connected to the gate pads, forming a second contact hole at the gate insulating layer such that the second contact hole exposes the gate short circuit line, and forming a data short circuit line such that the data short circuit line is connected to the data pads, the data short circuit line being connected to the gate short circuit line through the second contact hole.

In the meantime, the liquid crystal display includes a first substrate, and a gate line assembly and a common electrode line assembly formed on the first substrate. The gate line assembly includes a plurality of gate lines proceeding in the horizontal direction and gate pads connected to the gate lines, and the common electrode line assembly includes common signal lines proceeding parallel to the gate lines and common electrodes connected to the common signal lines while proceeding in the vertical direction. A gate insulating layer covers the gate line assembly and the common electrode line assembly, and a semiconductor pattern is formed on the gate insulating layer. An ohmic contact pattern is formed on the semiconductor pattern. A data line assembly and pixel electrodes are further formed at the first substrate. The data line assembly includes a plurality of data lines formed on the gate insulating layer and the ohmic

contact pattern while crossing over the gate lines to form pixel regions, data pads connected to the data lines, source electrodes being parts of or branched from the data lines, and drain electrodes separated from the source electrodes. The pixel electrodes are connected to the drain electrodes at the pixel regions while proceeding parallel to the common electrodes. A passivation layer covers the data line assembly and the pixel electrodes. A second substrate faces the first substrate. The gate insulating layer and the passivation layer exposed externally to the second substrate and the data pads are removed.

The ohmic contact pattern has the same shape as the data line assembly and the pixel electrodes, and the semiconductor pattern has the same shape as the data line assembly and the pixel electrodes except for the area between the source and the drain electrodes.

Furthermore, subsidiary data lines are formed at the same plane as the gate line assembly with the same material, and first contact holes are formed on the gate insulating layer while exposing the subsidiary data lines.

Each pixel electrode is formed with two or more linear electrode portions, and each linear electrode portion is positioned close to the neighboring data line. Both ends of the linear electrode portions are connected to each other such that the pixel electrode bears a ring shape.

Furthermore, one or more light interception patterns are separated from the gate lines, and positioned close to the subsidiary data lines while proceeding parallel to the subsidiary data lines. The pixel electrodes are partially overlapped with the light interception patterns. Alternatively, the pixel electrodes are spaced apart from the light interception patterns by $2\ \mu\text{m}$ or less.

On the other hand, in another method of fabricating a TFT array substrate for a liquid crystal display according to the present invention, the shadow frame is used to prevent the semiconductor layer, or the gate insulating layer from being deposited on the gate pad portion.

The method of fabricating a thin film transistor array substrate for a liquid crystal display includes the step of forming a gate line assembly and a common electrode line assembly on a substrate including a display areas and a peripheral areas. The gate line assembly comprises a plurality of gate lines and gate electrode of the display areas, and gate pads of the peripheral areas, and the common electrode line assembly comprises common signal lines and common electrodes of the display areas. Next, a gate insulating layer covering the gate line assembly exposing the portions of the gate pads is formed, and the a semiconductor pattern and an ohmic contact pattern are formed on the gate insulating layer. A data line assembly and pixel electrodes are then formed on the substrate. The data line assembly includes a plurality of data lines, and source and drain electrodes of the display areas, and data pads of the peripheral areas. The pixel electrodes are connected to the drain electrodes while proceeding parallel to the common electrodes. Here, when forming a gate insulating layer, the shadow frame having a first blocking deposition areas is used to prevent the gate insulating layer from being deposited on the gate pad portion having the gate pads of the peripheral areas.

The shadow frame may have a second blocking deposition areas to prevent the gate insulating layer, the semiconductor pattern, or the ohmic contact pattern from being deposited on the data pad portion having the data pads of the peripheral areas.

The data line assembly, the pixel electrodes, the ohmic contact pattern and the semiconductor pattern may be made

through photolithography based on one photoresist pattern having a different thickness. It is preferable that the photoresist pattern has a first portion placed between the source and the drain electrodes with a predetermined thickness, a second portion for forming the data line assembly and the pixel electrodes that is thicker than the first portion, and a third portion that is thinner than the first portion.

The data line assembly, the ohmic contact pattern and the semiconductor pattern may be made through a photolithography process using one mask. First, the gate insulating layer, a semiconductor layer, an ohmic contact layer, and a conductor layer are deposited, and a photoresist layer is coated on the conductor layer. Next, the photoresist layer is exposed to light through the mask to form a photoresist pattern such that the second portion lies on the data line assembly by developing the photoresist layer. The data line assembly, the ohmic contact layer pattern, and the semiconductor pattern respectively made of the conductor layer, the ohmic contact layer and the semiconductor layer are formed by removing a portion of the conductor layer under the third portion, the semiconductor layer and the ohmic contact layer thereunder, the first portion, the conductor layer and the ohmic contact layer under the first portion, and a partial thickness of the second portion, and the photoresist pattern is removed. In detail, the portion of the conductor layer under the third portion is removed by dry or wet etching to expose the ohmic contact layer, and the ohmic contact layer under the third portion, the semiconductor layer thereunder and the first portion are dry-etched to obtain a complete semiconductor pattern along with exposing the gate insulating layer under the third portion and the conductor layer under the first portion. The conductor layer under the first portion and the ohmic contact layer thereunder are removed to obtain a complete data wire and complete ohmic contact layer pattern.

The shadow frame may be used to prevent the semiconductor layer, the ohmic contact layer, or the conductor layer from being deposited on the gate pad portion of the peripheral areas when depositing the semiconductor layer, the ohmic contact layer, and the conductor layer, and the photoresist pattern may have a fourth portion placed on the gate pad portions, and having the thickness of the first, the second, or the third portion.

A mask used for forming the photoresist pattern has a first, a second, and a third part. It is preferable that the transmittance of the third part is higher than the first and the second parts, the transmittance of the first part is higher than the second part, the photoresist pattern is made of positive photoresist, and the mask is aligned such that the first, the second, and the third parts respectively face the first, the second, and the third portions of the photoresist pattern in an exposing step.

It is preferable that the first part of the mask includes a partially transparent layer, or a plurality of slit patterns smaller than the resolution of the exposure device used in the exposing step, and the first portion is formed by reflow.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings in which like reference symbols indicate the same or the similar components, wherein:

FIG. 1 is a cross sectional view of a liquid crystal display with upper and lower substrates according to the present invention;

FIG. 2 is a plan view of the liquid crystal display shown in FIG. 1;

FIG. 3 is a flow diagram illustrating the steps of fabricating the liquid crystal display shown in FIG. 1;

FIG. 4 is a plan view of a TFT array substrate for a liquid crystal display according to the first preferred embodiment of the present invention;

FIG. 5 is a cross sectional view of the TFT array substrate taken along the V-V' line of FIG. 4;

FIG. 6A is another plan view of the TFT array substrate shown in FIG. 4;

FIG. 6B is a cross sectional view of the TFT array substrate taken along the VIb-VIb' line of FIG. 6A;

FIG. 7A is still another plan view of the TFT array substrate shown in FIG. 4;

FIGS. 7B to 10 are cross sectional views of the TFT array substrate taken along the VIIb-VIIb' line of FIG. 7A sequentially illustrating the steps of fabricating the TFT array substrate;

FIG. 11 is a plan view of a TFT array substrate according to the second preferred embodiment of the present invention;

FIG. 12 is a cross sectional view of the TFT array substrate taken along the XII-XII' line of FIG. 11;

FIG. 13A is another plan view of the TFT array substrate shown in FIG. 11;

FIG. 13B is a cross sectional view of the TFT array substrate taken along the XIIIb-XIIIb' line of FIG. 13A;

FIG. 14A is still another plan view of the TFT array substrate shown in FIG. 11;

FIGS. 14B to 17 are cross sectional views of the TFT array substrate taken along the XIVb-XIVb' line of FIG. 14A;

FIG. 18A is still another plan view of the TFT array substrate shown in FIG. 11; and

FIG. 18B is a cross sectional view of the TFT array substrate taken along the XVIIIb-XVIIIb' line of FIG. 18A.

FIG. 19 is a plan view of a substrate partitioned to manufacture a TFT array substrate for an LCD according to an embodiment of the present invention.

FIG. 20 is a layout view of a TFT array substrate for an LCD according to an embodiment of the present invention.

FIG. 21 is a layout view of a TFT array substrate for an LCD according to the third embodiment of the present invention, and an enlarged view of a portion mainly including a pixel and pads of the FIG. 20.

FIGS. 22 and 23 are cross-sectional views respectively taken along the line XXII-XXII' and XXIII-XXIII' of the FIG. 21.

FIG. 24A is a layout view of a TFT array substrate in the first manufacturing step according to the third embodiment of the present invention.

FIGS. 24B and 24C are respectively the cross-sectional views taken along the line XXIVb-XXIVb' and XXIVc-XXIVc' of the FIG. 24A.

FIGS. 25A and 25B are the cross-sectional views respectively taken along the line XXIVb-XXIVb' and XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 24B and 24C.

FIG. 26 is a plan view of a shadow frame used in a manufacturing of a TFT array substrate for an LCD according to an embodiment of the present invention.

FIG. 27 is the cross-sectional view taken along the line XXIVc-XXIVc' of the FIG. 24A in a manufacturing step

following the FIG. 24C according to the fourth embodiment of the present invention.

FIGS. 28A and 28B are the cross-sectional views respectively taken along the line XXIVb-XXIVb' and XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 25A and 25B.

FIGS. 29 to 31 are the cross-sectional views taken along the line XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIG. 25C according to the fifth, the sixth and the seventh embodiments of the present invention, respectively.

FIGS. 32A and 32B are the cross-sectional views respectively taken along the line XXIVb-XXIVb' and XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 28A and 28B.

FIGS. 33A and 33B are the cross-sectional views taken along the line XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 29 and 30.

FIGS. 34A and 34B are the cross-sectional views respectively taken along the line XXIVb-XXIVb' and XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 32A and 32B.

FIGS. 35A to 35C are the cross-sectional views taken along the line XXIVc-XXIVc' of the FIG. 24A in a manufacturing step following the FIGS. 33A, 31 and 33B, respectively.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Preferred embodiments of this invention will be explained with reference to the accompanying drawings.

FIG. 1 is a cross sectional view of a liquid crystal display with upper and lower substrates according to the present invention, and FIG. 2 is a plan view of the liquid crystal display shown in FIG. 1.

As shown in the drawings, the lower substrate 1 is provided with a plurality of TFTs (referred to hereinafter as the "TFT array substrate"), and the upper substrate 4 with color filters (referred to hereinafter as the "color filter substrate"). Electrodes 2 and 5 are provided at the inner surfaces of the TFT array substrate 1 and the color filter substrate 4 facing each other to form electric fields. Alignment films 3 and 6 are formed on the electrodes 2 and 5, and rubbed in a predetermined direction. Liquid crystal molecules 7 are injected in-between the alignment layers 3 and 6. Polarizing plates 8 and 9 are attached to the external surfaces of the respective substrates 1 and 4 such that the polarizing axes thereof are perpendicular to each other.

As shown in FIG. 2, the size of the TFT array substrate 1 is larger than that of the color filter substrate 4. Pads are formed at the periphery of the TFT array substrate 1 to transmit external signals to the required lines, and exposed externally to the color filter substrate 4.

FIG. 3 illustrates the steps of forming a liquid crystal cell in the process of fabricating the above-structured liquid crystal display.

A sealant of thermal hardening resin is printed onto one of the substrates, for example, onto the color filter substrate, to attach the color filter substrate to the TFT array substrate such that the substrates are spaced apart from each other with a predetermined distance. Thereafter, spacers of a predetermined size are spread onto the TFT array substrate to maintain the distance between the substrates in accurate and constant manners. The TFT array substrate and the color filter substrate are then assembled such that the pixel elec-

trodes of the TFT substrate correspond to the color filters of the color filter substrate, and hot-pressed. Liquid crystal molecules are injected in-between the substrates through an injection hole, and the injection hole is sealed.

FIG. 4 is a plan view of a TFT array substrate for a liquid crystal display according to a first preferred embodiment of the present invention, and FIG. 5 is a cross sectional view of the TFT array substrate taken along the V-V' line of FIG. 4.

As shown in the drawings, a gate line assembly and a common electrode line assembly are formed on an insulating substrate 10 with a metallic or conductive material such as Al or Al alloy, Mo or MoW alloy, Cr, and Ta. The gate line assembly includes scanning signal lines or gate lines 21 proceeding in the horizontal direction, and gate pads 23 connected to the ends of the gate lines 21 to receive scanning signals from the outside and transmit them to the gate lines 21. Parts of the gate lines 21 functions as gate electrodes 22. The common electrode line assembly includes common signal lines 24, and common electrodes 25 and 26. Each common signal line 24 is interposed between the neighboring gate lines 21 such that it is positioned close to the front gate line 21 while proceeding parallel thereto. The common electrodes 25 and 26 are branched from the common signal line 24 while proceeding perpendicular thereto. Alternatively, the gate line assembly may be formed with a double or triple-layered structure. In this case, it is preferable that one layer is formed with a low resistance material, and the other layer with a material bearing good contact characteristics with other materials.

A gate insulating layer 30 is formed on the gate line assembly and the common electrode line assembly with silicon nitride (SiNx).

A semiconductor pattern 41 is formed on the gate insulating layer 30 with hydrogenated amorphous silicon. Ohmic contact patterns 51 and 52 are formed on the semiconductor pattern 41 with amorphous silicon doped by n type impurities such as phosphorous (P) in high concentration.

A data line assembly and a pixel electrode line assembly are formed on the ohmic contact patterns 51 and 52 with a conductive material such as Cr, Al and Al alloy. The data line assembly includes data lines 61 proceeding in the vertical direction to form pixel regions together with the gate lines 21, data pads 64 connected to the one-sided ends of the data lines 61 to receive picture signals from the outside, and source electrodes 62 being parts of the data lines 61, and drain electrodes 63 separated from the source electrodes 62. The pixel electrode line assembly includes pixel signal lines 65 connected to the drain electrodes 63 at the pixel regions while proceeding perpendicular thereto, and a pixel electrode 66 connected to each pixel signal line 65 such that it is positioned between the neighboring common electrodes 25 and 26 while proceeding parallel thereto. Alternatively, the data line assembly and the pixel electrode line assembly may be formed with a double or triple-layered structure as in the gate line assembly and the common electrode line assembly.

A passivation layer 70 is formed on the data line assembly and the pixel electrode line assembly. As shown in FIGS. 4 and 5, the passivation layer 70 at the pad portions is removed together with the gate insulating layer 30 such that the gate pads 23 and the data pads 64 are exposed to the outside. The gate insulating layer 30 and the passivation layer 70 over the gate pads 23 are all removed, but the gate insulating layer 30 under the data pads 64 remains. The passivation layer 70 may be formed with silicon nitride or acryl-based organic insulating material.

A method for fabricating the TFT array substrate will be now explained with reference to FIGS. 6A to 10.

As shown in FIGS. 6A and 6B, a conductive layer with a thickness of 1000–3000 Å is deposited onto a substrate 10 through sputtering, and patterned to form a gate line assembly and a common electrode line assembly. The gate line assembly includes gate lines 21, and gate pads 23. The data line assembly includes common signal lines 24 proceeding parallel to the gate lines 21, and common electrodes 25 and 26 connected to the common signal lines 24. Parts of the gate lines 21 functions as gate electrodes 22.

Thereafter, as shown in FIGS. 7A and 7B, a gate insulating layer 30 with a thickness of 1500–5000 Å, a semiconductor layer 40 with a thickness of 500–2000 Å and an ohmic contact layer 50 with a thickness of 300–600 Å are sequentially deposited onto the substrate 10 through chemical vapor deposition (CVD), and a metallic conductive layer 60 with a thickness of 1500–3000 Å is deposited onto the ohmic through sputtering. A photoresist film with first and second portions 91 and 92 differentiated in thickness is then formed on the conductive layer 60.

The first and second photoresist portions 91 and 92 have different thickness depending on the positions. This can be achieved by either a mask with films bearing different light transmissions, or a mask with a slit or mosaic pattern.

In the former case, the mask has a transparent substrate, a thin film formed on the substrate with a light transmission of 3% or less corresponding to the area of a data line assembly and a pixel electrode line assembly, and a thin film with a light transmission of 20–50% corresponding to the TFT channel area. The first portion 91 of the photoresist film corresponding to the area of a data line assembly and a pixel electrode line assembly is the thickest. The second portion 92 of the photoresist film corresponding to the TFT channel area is thinner than the first portion 91. And the remaining portion of the photoresist film is entirely removed.

In the latter case, the mask has a transparent substrate, and a slit or mosaic pattern formed on the substrate corresponding to the TFT channel area. The opening width of the slit or mosaic pattern is established to be 2 μm or less, which is smaller than the resolution of a light exposing device.

Thereafter, the photoresist film, and the underlying layers are etched. In this etching process, the data line assembly, the pixel electrode line assembly and the underlying layers are left out at the area A, a semiconductor pattern 41 is left out at the channel area C, and the gate insulating layer 30 is exposed at the remaining area B where the conductive layer 60, the ohmic contact layer 50 and the semiconductor layer 40 are removed.

First, as shown in FIG. 8, the conductive layer 60 at the B area is removed through etching such that the underlying ohmic contact layer 50 is exposed. In this process, the conductive layer 60 is etched by either dry etching or wet etching but the photoresist film 91 and 92 need to be hardly etched. However, the dry etching method may etch the photoresist film 91 and 92 together with the conductive layer 60 because it is difficult to find a suitable selective etching condition. In this case, the thickness of the second photoresist portion 92 should be set thick enough to prevent from being removed while exposing the underlying conductive layer 60.

Consequently, as shown in FIG. 8, the conductive layer 60 at the B area is removed while exposing the underlying ohmic contact layer 50, and a conductive pattern 67 is formed at the TFT channel area C, and at the area A for a data line assembly and a pixel electrode assembly. At this time,

the conductive pattern **67** has the same shape as the data line assembly and the pixel electrode line assembly except that the source and the drain electrodes **62** and **63** are not yet separated from each other. In the case of dry etching, the photoresist film **91** and **92** is also etched by a predetermined thickness.

Thereafter, as shown in FIG. 9, the ohmic contact layer **50** at the B area and the underlying semiconductor layer **40** are simultaneously removed through dry etching together with the second photoresist portion **92**. The etching is performed in a condition that the photoresist film **91** and **92**, the ohmic contact layer **50** and the semiconductor layer **40** (the semiconductor layer and the ohmic contact layer bearing little etching selectivity) are simultaneously etched, but the gate insulating layer **30** is not etched. Particularly, it is preferable that the etching with respect to the photoresist film **91** and **92** and the semiconductor layer **40** should be performed under nearly the same etching conditions. When etching ratios with respect to the photoresist film **91** and **92** and the semiconductor layer **40** are the same, the thickness of the second photoresist portion **92** should be set the same as the sum of the thickness of the semiconductor layer **40** and the ohmic contact layer **50**.

Consequently, as shown in FIG. 9, the second photoresist portion **92** at the channel area C is removed while exposing the conductive pattern **67**, and the ohmic contact layer **50** and the semiconductor layer **40** at the B area are removed while exposing the underlying gate insulating layer **30**. Meanwhile, the first photoresist portion **91** at the A area is also etched such that the thickness thereof becomes to be thinner. In this step, a semiconductor pattern **41** is completed. Reference numeral **53** indicates the ohmic contact pattern under the conductive pattern **67**.

The photoresist residue on the conductive pattern **67** at the channel area C is removed by ashing. Plasma gas containing oxygen gas as the main component or microwave may be used for the ashing.

As shown in FIG. 10, the conductive pattern **67** at the channel area C and the underlying ohmic contact pattern **53** is etched out. Both of the conductive pattern **67** and the ohmic contact pattern **53** may be removed by dry etching, or only the ohmic contact pattern **53** is removed by dry etching and the conductive pattern **67** is removed by wet etching. At this time, the semiconductor pattern **41** may be partially removed and may become thinner. The first photoresist portion **91** is also etched by a predetermined thickness. The etching should be performed not to etch the gate insulating layer **30**. The first photoresist portion **91** is preferably thick enough to prevent the underlying data line assembly and pixel electrode line assembly from being exposed through etching.

Consequently, the source and drain electrodes **62** and **63** are separated from each other while completing a data line assembly and ohmic contact patterns **51** and **52**.

Finally, the first photoresist portion **91** at the area A is removed. Alternatively, the first photoresist portion **91** may be removed after the conductive pattern **67** at the channel area C is removed, but the underlying ohmic contact pattern **57** is not yet removed.

Furthermore, if the data line assembly is formed of a material well adapted for the dry etching, the ohmic contact patterns **51** and **52**, the semiconductor pattern **41**, the data line assembly and the pixel electrode line assembly may be completed at only one etching process by controlling the thickness of the photoresist film. That is, when the conductive layer **60**, the ohmic contact layer **50** and the semicon-

ductor layer **40** at the B area are etched, the second photoresist pattern **92** and the underlying ohmic contact layer **50** at the C area are etched, and the first photoresist pattern at the A area is partially etched.

In this way, the data line assembly and the pixel electrode line assembly are formed. Thereafter, as shown in FIGS. 4 and 5, silicon nitride is deposited onto the substrate **10** through CVD, or an organic insulating material is spin-coated onto the substrate **10** to thereby form a passivation layer **70** with a thickness of 2000 Å or more. The passivation layer **70** is etched together with the gate insulating layer **30** such that the gate pads **23** and the data pads **64** are exposed to the outside. As shown in FIG. 2, the exposed portion of the TFT array substrate may be removed through dry etching after the assembly process, or after the process of sealing the liquid crystal injection hole. Tape automated bonding (TAB) ICs are attached to the pad portions completely exposed through removing the passivation layer **70** or the gate insulating layer **30**. At this time, it is preferable that a sealant is coated onto the pad area exposed through the ICs to prevent possible device failure due to the environmental factors.

As described above, in this preferred embodiment, the data line assembly, the pixel electrode line assembly, the ohmic contact pattern and the semiconductor layer are formed through only one photolithography process, and the process of exposing the pad portions is made after the assembly process or the process of sealing the liquid crystal injection hole. This results in simplified processing steps.

FIGS. 11 and 12 illustrate the structure of a TFT array substrate for a liquid crystal display according to a second preferred embodiment of the present invention.

As shown in the drawings, a gate line assembly, subsidiary data lines **125**, first and second light interception patterns **1261** and **1262**, and a common electrode line assembly are formed on an insulating substrate **110** with a metallic or conductive material such as Al or Al alloy, Mo or MoW alloy, Cr, and Ta. The gate line assembly includes scanning signal lines or gate lines **121** proceeding in the horizontal direction, gate pads **123** connected to the end portions of the gate lines **121** to receive scanning signals from the outside and transmit them to the gate lines **121**, and a gate short circuit line **1242** connected to the gate pads **123** via connectors **1241** while proceeding in the vertical direction. Parts of the gate lines **121** functions as gate electrodes **122**. Each subsidiary data line **125** is separately disposed between the neighboring gate lines **121** while proceeding perpendicular thereto. The first and second light interception patterns **1261** and **1262** are placed at both sides of the subsidiary data line **125** while proceeding parallel thereto. The common electrode line assembly includes upper and lower common signal lines **127** and **128**, and common electrodes **129**. The upper and lower common signal lines **127** and **128** are disposed between the neighboring gate lines **121** while each being positioned close to the relevant gate line **121** and proceeding parallel thereto. Each common electrode **129** interconnects the upper and lower common signal lines **127** and **128** in the vertical direction while being centrally positioned between the neighboring subsidiary data lines **125**. The gate short circuit line **1242** interconnecting all of the gate lines **121** disperses static electricity occurring at the process.

The gate line assembly, the subsidiary data lines **125**, the light interception patterns **1261** and **1262**, and the common electrode line assembly may be formed with a double or triple-layered structure. In this case, it is preferable that one

layer is formed with a low resistance material, and the other layer with a material bearing good contact characteristics with other materials.

A silicon nitride-based gate insulating layer **130** is formed on the gate line assembly, the subsidiary data lines **125**, the light interception patterns **1261** and **1262**, and the common electrode line assembly while covering the latter. The gate insulating layer **130** is provided with first to third contact holes **131**, **132** and **133** exposing the subsidiary data lines **125**, the gate pads **123** and the gate short circuit line **1242**, respectively.

A semiconductor pattern **141** is formed on the gate insulating layer **130** with hydrogenated amorphous silicon. Ohmic contact patterns **151** and **152** are formed on the semiconductor pattern **141** with amorphous silicon doped with n type impurities such as phosphorous (P).

A data line assembly, pixel electrodes **161**, and subsidiary gate pads **167** are formed on the ohmic contact patterns **151** and **152** with a conductive material such as Mo or MoW alloy, Cr, Al or Al alloy, and Ta. The data line assembly includes data lines **162** proceeding in the vertical direction, source electrodes **163** positioned over the gate lines **121** as parts of the data lines **162**, drain electrodes **164** positioned opposite to the source electrodes **163** with respect to the TFT channels, data pads **165** connected to the one sided ends of the data lines **162** to receive picture signals from the outside, and a data short circuit line **1662** connected to the data pads **165** via connectors **1661** while proceeding in the horizontal direction. The data short circuit line **1662** for preventing device failure due to discharge of static electricity is connected to the gate short circuit line **1242** via a contact hole **133**. Therefore, even though static electricity is generated either to the gate line assembly or to the data line assembly, such a static electricity can be dispersed throughout all of the relevant lines. The short circuit lines **1242** and **1662** are later removed through cutting the substrate along the dotted line **100** shown in FIG. **11**. The pixel electrodes **161** are overlapped with the upper and lower common signal lines **127** and **128**, and the first and second light interception patterns **1261** and **1262** at their peripheral portions. The central portion of each pixel electrode **161** is removed such that it has a ring shape. Alternatively, the pixel electrode **161** may not be overlapped with the first and second light interception patterns **1261** and **1262**. In this case, the distance between the pixel electrode **161** and the first and second light interception patterns **1261** and **1262** is established to be $2\ \mu\text{m}$ or less.

A passivation layer **170** is formed on the data line assembly, the pixel electrodes **161**, and the subsidiary gate pads **167**. The passivation layer **170** at the pad portions and the short circuit line portions are removed together with the gate insulating layer **130** such that the gate pads **123**, the gate connectors **1241**, the gate short circuit line **1242**, the data pads **165**, the data connectors **1661** and the data short circuit line **1662** are all exposed to the outside. At this time, the gate insulating layer **130** and the passivation layer **170** over the gate pads **123**, the gate connectors **1241** and the gate short circuit line **1242** are all removed, but the gate insulating layer **130** under the data pads **165**, the data connectors **1661** and the data short circuit line **1662** are not removed. The passivation layer **170** is formed with silicon nitride or acryl-based organic insulating material.

A method for fabricating the above-structured TFT array substrate will be explained with reference to FIGS. **13A** to **18B**.

As shown in FIGS. **13A** and **13B**, a metallic conductive layer with a thickness of 1000 to 3000 Å is deposited onto

a substrate **110** through sputtering, and patterned to thereby form a gate line assembly, a common electrode line assembly, subsidiary data lines **125**, and first and second light interception patterns **1261** and **1262**. The gate line assembly includes gate lines **121**, gate pads **123**, and a gate short circuit line **1242** connected to the gate pads **123** via connectors **1241**. Parts of the gate lines **121** functions as gate electrodes **122**. The common electrode line assembly includes upper and lower common signal lines **127** and **128** disposed between the neighboring gate lines **121**, and common electrodes **129** connected to the upper and lower common signal lines **127** and **128**.

Thereafter, as shown in FIGS. **14A** to **17**, an ohmic contact pattern **153**, a semiconductor pattern **141**, and contact holes **131**, **132** and **133** are formed.

First, as shown in FIGS. **14A** and **14B**, a gate insulating layer **130** with a thickness of 1500 to 5000 Å, a semiconductor layer **140** with a thickness of 500 to 2000 Å and an ohmic contact layer **150** with a thickness of 300 to 600 Å are sequentially deposited onto the substrate **110** through CVD. A photoresist film with third and fourth portions **191** and **192** in different thickness are then formed on the contact layer **150**. As in the first preferred embodiment, using a mask with films different in light transmission, or a mask with a slit or mosaic pattern, the third photoresist portion **191** for forming an ohmic contact pattern **153** and a semiconductor pattern **141** is set to be the thickest. And the fourth photoresist pattern **192** is set to be thinner than the third photoresist pattern **191**. The photoresist film placed over the area of contact holes **131**, **132** and **133** is entirely removed.

Thereafter, the fourth photoresist portion **192** and the underlying ohmic contact layer **150**, semiconductor layer **140** and gate insulating layer **130** are etched. At this time, the ohmic contact layer **150** and the semiconductor layer **140** for forming an ohmic contact pattern **153** and a semiconductor pattern **141** are left out, and the ohmic contact layer **150**, the semiconductor layer **140** and the gate insulating layer **130** for forming contact holes **131**, **132** and **133** are removed while exposing the underlying gate pads **123**, gate short circuit line **1242** and subsidiary data lines **125**. The remaining ohmic contact layer **150** and semiconductor layer **140** are all removed while leaving out the gate insulating layer **130**.

For this purpose, as shown in FIG. **15**, the ohmic contact layer **150**, the semiconductor layer **140** and the gate insulating layer **130** for forming the contact holes **131**, **132**, **133** are removed through dry etching or wet etching.

As shown in FIG. **16**, the fourth photoresist portion **192** is removed through ashing while exposing the underlying ohmic contact layer **150**. At this time, the third photoresist portion **191** is partially etched by a predetermined thickness.

As shown in FIG. **17**, the ohmic contact layer **150** and the semiconductor layer **140** are etched to form an ohmic contact pattern **153** and a semiconductor pattern **141**, and the remaining third photoresist portion **191** is removed.

As shown in FIGS. **18A** and **18B**, a metallic conductive layer with a thickness of 1500 to 3000 Å is deposited onto the substrate **110** through sputtering, and patterned to thereby form pixel electrodes **161**, a data line assembly, and subsidiary gate pads **167**. The data line assembly includes data lines **162**, drain electrodes **164**, data pads **165**, connectors **1661**, and a data short circuit line **1662**. Parts of the data lines **162** function as source electrodes **163**. Then, the exposed ohmic contact pattern **153** is etched to thereby complete ohmic contact patterns **151** and **152**. At this time, the pixel electrodes **161** are partially overlapped with the

13

upper and lower common signal lines **127** and **128**, and the first and second light interception patterns **1261** and **1262**. Each pixel electrode **161** has its center removed such that it has a ring shape. Alternatively, the pixel electrode **161** may be spaced apart from the first and second light interception patterns **1261** and **1262** with a distance of $2\ \mu\text{m}$ or less. The subsidiary gate pads **167** are to strengthen adhesion of the gate pads **123** to external circuits while protecting them. Such subsidiary gate pads are not necessarily required, but may be selectively adopted.

Finally, as shown in FIGS. **11** and **12**, silicon nitride is deposited onto the substrate **110** through CVD, or an organic insulating material is spin-coated onto the substrate **110** to thereby form a passivation layer **170** with a thickness of $2000\ \text{\AA}$ or more. Like the first preferred embodiment, the exposed passivation layer **170** and gate insulating layer **130** are etched after an assembly process or after sealing the liquid crystal injection hole such that the subsidiary gate pads **167**, the data pads **165**, the connectors **1241** and **1661** and the short circuit lines **1242** and **1662** are exposed to the outside.

In this preferred embodiment, contact holes are formed at the gate insulating layer during the step of forming the semiconductor pattern such that the gate line assembly and the data line assembly contact each other via the contact holes. Furthermore, the gate and data pads may be formed at the same plane as either the gate line assembly or the data line assembly with the same material, and connected to the relevant line assembly through contact holes.

On the other hand, a shadow frame may be used to simplify the processing steps. The shadow mask is used to prevent depositing the gate insulating layer or the semiconductor on the pad portions including the gate and the data pads to expose the pads.

Now, a structure of a TFT array substrate according to an embodiment of the present invention will be described with reference to the FIGS. **19** to **23**.

As shown in FIG. **19**, a plurality of panel areas is formed on an insulating plate **1**. For example, as shown in FIG. **19**, six panel areas **210**, **220**, **230**, **240**, **250** and **260** are formed on a glass plate **1**. When the substrates are TFT array substrates, the substrate areas **210**, **220**, **230**, **240**, **250** and **260** include display areas **211**, **221**, **231**, **241**, **251** and **261** having a plurality of pixels and peripheral areas **212**, **222**, **232**, **242**, **252** and **262** respectively. TFTs, wires including gate lines and data lines, pixel electrodes, and common electrodes are repeatedly arranged in a matrix shape in the display areas **211**, **221**, **231**, **241**, **251** and **261**. Pads to be connected to external circuits and electrostatic discharge protection circuits are provided in the peripheral areas **212**, **222**, **232**, **242**, **252** and **262**.

FIG. **20** is a layout view of one TFT array substrate area shown in FIG. **19** according to an embodiment of the present invention.

As shown in FIG. **20**, a number of a plurality of wires including pixel electrode line assembly **65** and **66**, gate lines **21**, data lines **61**, and common electrode line assembly **24** and **25** are formed in the display area surrounded by an imaginary line **150**. Gate pads **23** and data pads **64** respectively connected to the gate lines **21** and the data lines **61** are formed in the peripheral area.

FIG. **21** is a layout view of a TFT panel for an LCD according to a third embodiment of the present invention, and an enlarged view of a portion mainly including a pixel and pads of the FIG. **20**. FIGS. **22** and **23** are cross-sectional views respectively taken along the line XXII-XXII' and XXIII-XXIII' of the FIG. **21**.

14

As shown in FIGS. **21** to **23**, most of structure is the same as that of the first embodiment.

However, in this embodiment, the gate insulating layer **30** is removed in the peripheral areas, on which the gate pads **23** are formed, to expose the gate pads **23**, and the passivation layer is not formed.

Here, the common electrode line assembly **24** and **25** provides storage capacitance along with the pixel electrode line assembly **65** and **66** by overlapping each other. The ohmic contact pattern **51** reduces the contact resistance between the semiconductor pattern **41** and the corresponding data line assembly parts **61**, **62**, **63** and **64**, and has the same layout as the data line assembly parts **61**, **62**, **63** and **64**, and the pixel electrode line assembly **65** and **66**. In other words, a first ohmic contact portion **51** under the data line part has the same shape as the data line parts **61**, **62**, and **64**, a second ohmic contact portion **52** under the drain electrode part has the same shape as the drain electrode **63**, and the pixel electrode line assembly **65** and **66**. Also, the semiconductor pattern **41** has the same layout as the corresponding data line assembly **61**, **62**, **63** and **64**, and the pixel electrode line assembly **65** and **66**, and the corresponding ohmic contact pattern **51**, **52** except for the channel part C of the thin film transistor. In other words, the data line assembly **61**, **62**, and **63**, especially the source electrode **62** and the drain electrode **63** are separated from each other by the channel part C of thin film transistor and the portions **51** and **52** of ohmic contact layer pattern thereunder are also separated from each other, but the semiconductor portion **41** is not divided into two pieces so that it can traverse the channel of a thin film transistor.

In this embodiment, the semiconductor pattern **41** or the ohmic contact patterns **51** and **52** may be extended outside the data line assembly **61**, **62**, **63** and **64**, and the pixel electrode line assembly **65** and **66**.

On the other hand, a passivation layer may be formed on the data line assembly **61**, **62**, **63** and **64**, and the pixel electrode assembly **65** and **66**. The passivation layer may have contact holes exposing the data pads **64**, and the gate pad **23**, and can be made of an insulating material such as SiNx, acrylic organic material, other transparent photo-definable material, or other organic material. Furthermore, a redundant data line assembly electrically connected to the data line assembly may be formed on the passivation layer.

A manufacturing method for a thin film transistor array panel according to the third embodiment of the present invention will now be described with reference to the FIGS. **24A** to **35C** and FIGS. **19** to **23**.

At first, as shown in FIGS. **24A** to **24C**, a layer of conductor, such as a metal, is deposited on a substrate **10** by such methods as sputtering to a thickness of $1,000\ \text{\AA}$ to $3,000\ \text{\AA}$, and gate line assembly including a gate line **21**, a gate pad **23**, a gate electrode **22**, and a common electrode line assembly including a common electrode line **24** and common electrodes **25** are formed by dry or wet etching using a first mask.

Next, as shown in FIGS. **25A** and **25B**, a gate insulating layer **30**, a semiconductor layer **40**, and an ohmic contact layer **50** are sequentially deposited to thicknesses of $1,500\ \text{\AA}$ to $5,000\ \text{\AA}$, $500\ \text{\AA}$ to $2,000\ \text{\AA}$, and $300\ \text{\AA}$ to $600\ \text{\AA}$, respectively, by such methods as chemical vapor deposition (CVD). Then, a conductor layer **60**, such as a metal, is deposited to a thickness of $1,500\ \text{\AA}$ to $3,000\ \text{\AA}$ by such methods as sputtering and a photoresist layer **90** having a thickness of $1\ \mu\text{m}$ to $2\ \mu\text{m}$ is coated on the conductive layer **60**. Here, the gate insulating **30** is only deposited on the

portion except for the gate portion of the peripheral areas on which the gate pads **23** are formed, and the semiconductor layer **40**, the ohmic contact layer **50** or the conductor layer **60** may be selectively deposited such as the gate insulating layer **30**. For this deposition, a shadow frame having a deposition blocking area **200** on the portion corresponding to the gate portion of the peripheral areas is used, as shown in FIG. **26**. The deposition blocking area **200** is a portion on which a blocking layer to prevent thin films from being deposited, as a lined portion in FIG. **26**. Of course, a deposition blocking area may be extended on the portion corresponding to the whole peripheral areas including the data portion having data pads **64** that will be formed later, to prevent the gate insulating layer **30**, the semiconductor layer **40**, or the ohmic contact layer **50** from being selectively deposited.

Here, the gate insulating layer **30**, the semiconductor layer **40**, and the ohmic contact layer **50** are not deposited on the gate portion of the peripheral areas, but the semiconductor layer **40**, and the ohmic contact layer **50** may be deposited as shown in FIG. **27**. Of course, the conductor layer **60** may be not deposited on the gate pad portion by using the shadow frame **100**, not shown in drawings.

Thereafter, the photoresist layer **90** is exposed to light through a second mask and developed to form a photoresist pattern **91** and **92** as shown in FIGS. **28A** and **28B**. At this time, the first portion **92** of the photoresist pattern located between a source electrode **62** and a drain electrode **63**, i.e., a thin film transistor channel part C as shown in FIG. **24A**, is thinner than the second portion **91** of photoresist pattern located over the data wire portion A where a data wire **61**, **62**, **63** and **64** will be formed, and the third portion, the remaining portion of the photoresist pattern located at portion B, has almost no photoresist pattern left. The third portion may have a thickness depending on the etching method. For example, the third portion has substantially zero thickness when using a wet etch, but the third portion may have non-zero thickness when using a dry etch. At this time, the thickness ratio between the first portion **92** and the second portion **91** depends on the etch condition that will be described later. However, it is preferable that the thickness of the first portion **92** is equal to or less than half of that of the second portion **91**. Here, it is preferable that the second mask has a light transmission of 3% or less corresponding to the area of a data line assembly and a pixel electrode line assembly, a light transmission of 20–60%, more preferably 30–40%, corresponding to the TFT channel area, and a transmission of 90% or more. The thickness of the first portion **92** is in the range of 2,000–5,000 Å, more preferably 3,000–4,000 Å, and the thickness of the second portion **91** is in the range of 1.6 to 1.9 μm, in the case of using positive photoresist.

As shown in FIG. **28**, the first portion **92** is not etched out on the gate pad portion, because the gate pads **23** is to be exposed in the steps of forming the semiconductor pattern **41**, the data line assembly **61**, **62**, **63** and **64**, and the pixel electrode line assembly **65** and **66**. However, the photoresist may be completely removed. Nonetheless, it is preferable that the first portion **92** is not etched out on the gate pad portion to prevent the gate pads **23** from being damaged in later etch processes. Furthermore, as shown in FIG. **29**, a thicker photoresist pattern such as the second portion **91** may remain on the portion of the gate pad portion to form a pad buffer layer covering the gate pads **23** with the same layer as the data line assembly **61**, **62**, **63** and **64** without depositing the gate insulating layer **30**, the semiconductor layer **40**, and the ohmic contact layer **50**.

Furthermore, when depositing the semiconductor layer **40** on the gate pad portion of the peripheral areas as shown in FIG. **27**, the photoresist on the gate portion of the peripheral areas is removed to expose the gate pads **23**, as shown in FIG. **30**. On the other hand, when not depositing the conductor layer **60** on the gate pad portion by using the shadow frame, a photoresist pattern such as the second portion **91** having the thicker thickness may be remained on the gate pad portion, as shown in FIG. **31**.

There are methods controlling the amount of incident light by forming a pattern such as a slit or a lattice, which is smaller than the resolution of the exposure device, or by providing a partly-transparent layer on the mask to form the photoresist pattern **91** and **92** having the different thickness depending on the position. When manufacturing a mask using partly-transparent layer, a thickness of the partly-transparent layer may be controlled, or the partly-transparent layer having multi-layered structure made of a plurality of layers having a different transmittance may be used, to control the amount of incident light.

Another method to vary the thickness of the photoresist layer employs reflow. Here, a photoresist layer is exposed to light through a mask having substantially transparent portions and substantially opaque portions, respectively, to form a photoresist pattern having portions of zero and nonzero thicknesses. However, as described above, the portion of zero thickness may have a residual thickness of photoresist. The photoresist pattern is subject to reflow such that the thicker photoresist flows into the zero thickness portions to form a new photoresist pattern having a thinner thickness.

Referring back to FIGS. **28A** and **28B**, the photoresist pattern **91** and **92**, and the layers thereunder including the conductor layer **60**, the ohmic contact layer **50**, and the semiconductor layer **40** are then subject to an etching process. When this is done, there may be left a data line assembly and the layers thereunder at the data line assembly part A, and only the semiconductor layer on the channel part C. In addition three layers **60**, **50**, and **40** in the remaining part B are removed from the gate insulating layer **30**, and the gate pads **23** on the peripheral areas may be exposed.

As shown in FIGS. **32A** and **32B**, the ohmic contact layer **50** of the part B is exposed by removing the conductor layer **60** thereon. At this time, both wet and dry etch can be used, and it is preferable that the conductor layer **60** is etched but the photoresist layer **91** and **92** are not etched. However, since dry etch is hard to achieve this condition the photoresist pattern **91** and **92** may be also etched. In this case, the first portion **92** may be made thicker than in wet etch case so that the conductor layer **60** is not exposed.

The conductor layer **60** made of Mo or MoW alloy, Al or Al alloy, or Ta can be etched by dry or wet etch method. However, the conductor layer **60** made of Cr, is better etched by wet etch because Cr is not easily removed by dry etch. CeNH_3 is available as wet etchant for etching Cr conductor layer **60**. The mixed gas systems of CF_4 and HCl or CF_4 and O_2 is available for dry etching, a Mo or MoW conductor layer **60**. In this case, the etch rate of the latter system on the photoresist layer is similar to that of the conductor layer **60**.

Referring to FIGS. **32A** and **32B**, as a result, only the portions **67** of the conductor **60** under the photoresist **91** and **92** at the channel part C and the data wire part B for source/drain electrodes are left, and the remaining portion of the conductor layer **60** at part B is wholly removed to expose the ohmic contact layer **50** thereunder. At this time, the conductor pattern **67** has the same layout as the data line assembly parts **61**, **62**, **63** and the pixel electrode line

assembly **65** and **66** except that the source electrode **62** and the drain electrode **63** are connected to each other. When dry etch is used, the photoresist layer **91** and **92** is also etched to a certain thickness. At this time, the conductor pattern **67** covering the gate pads **23** may remain as shown in FIG. **33A** in the case of forming the photoresist pattern **91** as shown in FIG. **29**, and the semiconductor layer **40** and the ohmic contact layer **30** may remain as shown in FIG. **33B** in the case of removing the photoresist as shown in FIG. **30**.

Next, the exposed portions of the ohmic conductor layer **50** at part B and the semiconductor layer **40** thereunder of FIGS. **32A** and **32B** have been removed by dry etching along with first portion **92** of the photoresist layer as shown FIGS. **34A** and **34B**. The etch condition may be such that the photoresist pattern **91** and **92**, the ohmic contact layer **50**, and the semiconductor layer **40** are all etched (the semiconductor layer and the ohmic contact layer have almost the same etch rate), but the gate insulating layer **30** is not etched. It is preferable that the etch rates of the photoresist patterns **91** and **92** and the semiconductor layer **40** are almost the same. This occurs example with the mixed gas systems of SF₆ and HCl or SF₆ and O₂. When the etch rates of the photoresist patterns **91** and **92** and the semiconductor layer **40** are almost the same, the thickness of the first portion **92** may be equal to or less than the sum of the thicknesses of the semiconductor **40** and the ohmic contact layer **50**.

Then, as shown in FIGS. **34A** and **34B**, the conductor pattern **67** is exposed by removing the first portion **92** of the channel part C, the gate insulating layer **30** is exposed by removing the ohmic contact layer **50** and the semiconductor layer **40** of the part B, and the gate pad **23** is exposed. At the same time, the thickness of the second portion **91** over the data wire part A is reduced by etching. Furthermore, the completed semiconductor pattern **41** is obtained at this step. The reference numeral **57** represents the ohmic contact layer pattern under the conductor pattern **67** for the source/drain electrodes. Here, the thickness of the second portion **91** over the gate pad portion is reduced by etching as shown in FIGS. **33A** and **31** in case of remaining the second portion **91** as shown in FIGS. **33A** and **31**, and the gate pad **23** is exposed as shown in FIG. **35C** in the case of forming the semiconductor layer **40** and the ohmic contact layer **50** as shown in FIG. **33B**.

The remaining photoresist layer on the conductor pattern **67** is then removed by ashing or plasma etching.

Plasma gas or microwaves are used in the ashing step, and oxygen is an example of the compositions mainly used.

Next, as shown in **21** and **23** the conductor pattern **67** for source/drain electrodes at the channel part C and the ohmic contact layer pattern **57** for source/drain electrodes of FIG. **34A** are removed by etching. At this time, it is possible either to etch both the conductor pattern **67** and the ohmic contact layer **57** by a dry etching method, or to etch the conductor pattern **67** by a wet etching method and the ohmic contact layer **57** by a dry etching method. It is preferable in the former case that the etch conditions having a large etch selectivity between the conductor pattern **67** and the ohmic contact layer pattern **57** is employed. This is because if the etch selectivity is not large enough, it is hard to detect the end point of the etch and to control the thickness of the semiconductor pattern **41** around the channel part C. This can be achieved by using a mixed gas system of SF₆ and O₂ for example. When doing the wet etching and the dry etching sequentially, the lateral sides of the conductor pattern **67** subject to wet etching are also etched but those of the ohmic contact layer pattern **57** that is dry etched are hardly etched

at all. Thereby, the profile of these two patterns **67** and **57** makes a step like form. The mixed gas systems of CF₄ and O₂ are examples of an etch gas system for etching the ohmic contact layer pattern **57** and the semiconductor pattern **41**. The semiconductor pattern **41** may also be formed to have a uniform thickness by etching with the mixed gas system of CF₄ and O₂. At this time, the thickness of the semiconductor pattern **41** may be reduced and the second portion **91** of photoresist pattern is also etched to a certain thickness. The etch conditions may also be set not to etch the gate insulating layer **30** and the gate pad **23**, and it is preferable to make the photoresist pattern thick enough not to expose the data line assembly **61**, **62**, **63** and **64**.

As a result, the source electrode **62** and the drain electrode **63** are divided, and the complete data wire parts **61**, **62**, **63** and **64** and the completed contact layer pattern **51** and **52** thereunder are obtained.

Next, the remaining second portion **92** of the photoresist layer on the data line assembly is removed. However, the second portion **92** may be removed after removing the conductor pattern **67** for source/drain electrodes on the channel part C and before removing of the ohmic contact layer pattern **57** under the conductor pattern **67**.

In summary, this process can be done by using both wet etching and dry etching in turn, or by using only dry etching.

In the former case, the conductor layer of the part B is first removed by wet etching, and the ohmic contact layer and the semiconductor layer thereunder are removed by dry etching. At this time, the photoresist layer of the part C is consumed to a certain thickness, and the part C may have or may not have any residual photoresist, which substantially depends on the initial thickness of the photoresist layer of the part C. When the part C has residual photoresist, the residual photoresist is removed by ashing. Finally, the conductor layer of the part C is wet etched to separate the source and the drain electrodes, and the ohmic contact layer of the part C is removed by using dry etching.

In the latter case, the conductor layer, the ohmic contact layer and the semiconductor layer of the part B are removed by dry etching. As the former case, the part C may have or may not have residual photoresist, and the residual photoresist is removed by ashing when the part C has residual photoresist. Finally, the conductor layer of the part C is dry etched to separate the source and the drain electrodes, and the ohmic contact layer of the part C is removed by using dry etching.

Also, if the data line assembly is etched, the semiconductor pattern, the contact layer pattern and the data wire may be completed in one step. In other words, it is desirable that the photoresist pattern **92** and the contact layer **50** thereunder of the part C are dry etched, and the portion of the photoresist pattern **91** of the part A is dry etched during dry etching the conductor layer, the ohmic contact layer, and the semiconductor layer of the part B.

Since the latter process uses only one type of etching method, it is simpler but it is hard to achieve proper etching conditions. On the contrary, the former process has the advantage of ease of achieving proper etching condition, but it is more complicated.

In this embodiment according to the present invention, the semiconductor pattern **41** has the same layout as that of the data line assembly **61**, **62**, **63** and **64**, and the pixel electrode line assembly **65** and **66**, but the semiconductor pattern **41** may be extended outside the circumference of the data line assembly **61**, **62**, **63** and **64**, or the pixel electrode line assembly **65** and **66** by remaining the second portion **91** of the photoresist pattern at the circumference of the first portion **91** of the photoresist pattern.

Furthermore, a passivation layer covering the data line assembly **61**, **62**, **63** and **64**, the pixel electrode line assem-

bly **65** and **66**, and the semiconductor pattern **41** may be formed, and the shadow frame having the blocking deposition area may be used to prevent the passivation layer from being deposited on the gate pad and the data pad portions of the peripheral areas.

In this embodiment according to the present invention, because the shadow frame is used to prevent the gate insulating layer from being deposited on the peripheral area, the TFT array substrate for the LCD is manufactured by using two masks including one to form the gate line assembly and the pixel electrode line assembly, the other to form the data line assembly, the pixel electrode line assembly and the semiconductor pattern.

As described above, the pixel electrodes, the data line assembly and the semiconductor pattern are formed at only one photolithography process, and the shadow frame is used to prevent the gate insulating layer from being deposited on the peripheral area, thereby simplifying the processing steps and reducing the production cost. Furthermore, the subsidiary data lines are formed at the same plane as the gate line assembly with the same material, and the semiconductor pattern and the contact holes exposing the subsidiary data lines are formed in only one photolithography process, thereby preventing the data lines from being cut and simplifying the processing steps.

While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the art will appreciate that various modifications and substitutions can be made thereto without departing from the spirit and scope of the present invention as set forth in the appended claims.

What is claimed is:

1. A method for fabricating a thin film transistor array substrate for a liquid crystal display, comprising the steps of:

forming a gate line assembly and a common electrode line assembly on a first substrate, the gate line assembly comprising a plurality of gate lines and gate pads, the common electrode line assembly comprising common signal lines and common electrodes;

forming a gate insulating layer;

forming a semiconductor pattern;

forming an ohmic contact pattern;

forming a data line assembly and pixel electrodes, the data line assembly comprising a plurality of data lines, data pads, and source and drain electrodes, the pixel electrodes being connected to the drain electrodes while proceeding parallel to the common electrodes;

forming a passivation layer; and

etching the passivation layer and the gate insulating layer such that the gate pads and the data pads are exposed to the outside,

wherein the passivation layer and the gate insulating layer are etched after a second substrate is assembled to the first substrate, and the passivation layer and the gate insulating layer are exposed externally to the second substrate,

wherein the data line assembly, the pixel electrodes, the ohmic contact pattern and the semiconductor pattern are formed through a photolithography using one photoresist pattern of different thickness, and

wherein the photoresist pattern has a first portion placed between the source electrode and the drain electrode with a predetermined thickness, a second portion for forming the data line assembly and the pixel electrodes thicker than the first portion, and a third portion thinner than the first portion.

2. The method of claim 1, wherein the passivation layer and the gate insulating layer are exposed outside of the second substrate.

3. The method of claim 1, wherein the gate and the data pads is exposed after injecting liquid crystal molecules in-between the first substrate and the second substrate facing each other, and sealing the gap between the first substrate and second substrate.

4. The method of claim 1, wherein the photoresist pattern is formed using a mask with thin films of different light transmission.

5. The method of claim 4 wherein the mask comprises a thin film with a light transmission of 20 to 50% corresponding to the first portion of the photoresist pattern, and a thin film with a light transmission of 3% or less corresponding to the second portion of the photoresist pattern.

6. The method of claim 1, wherein the photoresist pattern is made using a mask with a minute pattern, the minute pattern of the mask corresponding to the area between the source electrode and the drain electrode while bearing an opening width smaller than the resolution of a light exposing device.

7. The method of claim 6 wherein the minute pattern is either a slit pattern or a mosaic pattern.

8. The method of claim 6, wherein the opening width of the minute pattern is $2\ \mu\text{m}$ or less.

9. A method for fabricating a thin film transistor array substrate for a liquid crystal display, comprising the steps of: forming a gate line assembly and a common electrode line assembly on a first substrate, the gate line assembly comprising a plurality of gate lines and gate pads, the common electrode line assembly comprising common signal lines and common electrodes;

forming a gate insulating layer;

forming a semiconductor pattern;

forming an ohmic contact pattern;

forming a data line assembly and pixel electrodes, the data line assembly comprising a plurality of data lines, data pads, and source and drain electrodes, the pixel electrodes being connected to the drain electrodes while proceeding parallel to the common electrodes;

forming a passivation layer; and

etching the passivation layer and the gate insulating layer such that the gate pads and the data pads are exposed to the outside,

wherein the passivation layer and the gate insulating layer are etched after a second substrate is assembled to the first substrate, and the passivation layer and the gate insulating layer are exposed externally to the second substrate, and

wherein subsidiary data lines are formed at the step of forming the gate line assembly, and first contact holes exposing the subsidiary data lines are formed at the step of forming the gate insulating layer, the steps of forming the ohmic contact pattern, the semiconductor pattern and the first contact holes being made through a photolithography using one photoresist pattern of different thickness, the photoresist pattern having a first portion corresponding to the ohmic contact pattern and the semiconductor pattern with a predetermined thickness, a second portion thicker than the first portion, and a third portion corresponding to the first contact holes and thinner than the first portion.

10. The method of claim 9, wherein the pixel electrodes are formed in a linear shape while proceeding parallel to the common electrodes.

11. The method of claim 10, further comprising the step of forming one or more light interception patterns to be placed at the same plane as the gate lines with the same material such that each light interception pattern is separated from the gate line and positioned close to the neighboring subsidiary data line while proceeding parallel to the subsidiary data line.

12. The method of claim 11, wherein the pixel electrodes are partially overlapped with the light interception patterns.

21

13. The method of claim **11**, wherein the pixel electrodes are spaced apart from the light interception patterns by a distance of $2\ \mu\text{m}$ or less.

14. The method of claim **9**, further comprising the steps of:
forming a gate short circuit line that is connected to the gate pads;

5

22

forming a second contact hole at the gate insulating layer that exposes the gate short circuit line; and
forming a data short circuit line that is connected to the data pads, and is connected to the gate short circuit line through the second contact hole.

* * * * *

专利名称(译)	用于液晶显示器的薄膜晶体管阵列基板及其制造方法		
公开(公告)号	US6678018	公开(公告)日	2004-01-13
申请号	US09/779705	申请日	2001-02-09
[标]申请(专利权)人(译)	PARK WOON YONG 金铉HWAN KI董铉		
申请(专利权)人(译)	PARK焕YONG KIM贤焕 KI董铉		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD.		
[标]发明人	PARK WOON YONG KIM HYEON HWAN KI DONG HYEON		
发明人	PARK, WOON-YONG KIM, HYEON-HWAN KI, DONG-HYEON		
IPC分类号	G02F1/1368 G02F1/13 H01L21/336 H01L21/02 H01L29/66 H01L29/786 G02F1/1343 G02F1/1362 G09F9/00 H01L21/84 H01L27/12 G02F1/136		
CPC分类号	G02F1/13458 G02F1/1368 H01L27/12 H01L29/66765 H01L29/78669 G02F1/134363 G02F2001/136231		
审查员(译)	KIM , 罗伯特H.		
助理审查员(译)	CHUNG , DAVID Y.		
优先权	1020000021693 2000-04-24 KR 1020000006273 2000-02-10 KR		
其他公开文献	US20020057393A1		
外部链接	Espacenet USPTO		

摘要(译)

一种制造用于液晶显示器的薄膜阵列基板的方法包括在第一基板上形成栅极线组件和公共电极线组件的步骤。栅极线组件包括多条栅极线和栅极焊盘，并且公共电极线组件包括公共信号线和公共电极。之后，在第一基板上形成栅极绝缘层，并在栅极绝缘层上形成半导体图案和欧姆接触图案。然后在第一基板上形成数据线组件和像素电极。数据线组件包括多条数据线，数据焊盘以及源极和漏极。像素电极连接到漏电极，同时平行于公共电极。在衬底上形成钝化层。蚀刻钝化层和栅极绝缘层，使得栅极焊盘和数据焊盘暴露于外部。此时，在组装工艺之后执行蚀刻，其中第二基板布置成面对第一基板并组装在一起，并且钝化层和栅极绝缘层暴露在第二基板的外部。

