

FIG. 2
Related Art




FIG. 3

Related Art




FIG. 4A

Related Art




FIG. 4B

Related Art




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 6G




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 7E




FIG. 7F




FIG. 7G




FIG. 8




FIG. 9A




FIG. 9B




FIG. 10




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 11D




FIG. 11E




FIG. 11F




FIG. 11G




FIG. 11H




FIG. 11I




FIG. 11J




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 12D




FIG. 12E




FIG. 12F




FIG. 12G




FIG. 12H




FIG. 12I





FIG. 12J



**ARRAY SUBSTRATE FOR IN-PLANE
SWITCHING MODE LIQUID CRYSTAL
DISPLAY DEVICE AND METHOD OF
FABRICATING THE SAME**

[0001] The present application claims the benefit of Korean Patent Application No. 2005-0133552 filed in Korea on Dec. 29, 2005, which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a liquid crystal display (LCD) device, and more particularly, to an array substrate for an in-plane switching (IPS) mode LCD device and method of fabricating the same that is capable of having high luminance and a wide viewing angle.

[0004] 2. Discussion of the Related Art

[0005] The liquid crystal molecules for an LCD device have orientation arrangement characteristics resulting from their thin and long shape. An arrangement direction of the liquid crystal molecules can be controlled by applying an electrical field to them. Thus, the LCD device displays images using a variation of transmittance of the liquid crystal molecules by controlling magnitudes of the electric field. The LCD device including a thin film transistor (TFT) as a switching element, referred to as an active matrix LCD (AM-LCD) device, has excellent high resolution characteristics and displaying characteristics for moving images.

[0006] A conventional LCD device includes a first substrate, a second substrate and a liquid crystal layer. The first substrate includes a pixel electrode, and the second substrate includes a color filter layer and a common electrode. The first and second substrates face each other, and the liquid crystal layer is interposed therebetween. The conventional LCD device displays images using a vertical electric field between the pixel and common electrodes. The LCD device using the vertical electric field has a high transmittance and a high aperture ratio. However, the LCD device has a narrow viewing angle, low contrast ratio, and other issues.

[0007] To resolve the above-mentioned problems, the IPS mode LCD device having a wide viewing angle may be used.

[0008] FIG. 1 is a schematic cross-sectional view of an IPS mode LCD device according to the related art. As shown in FIG. 1, the IPS mode LCD device includes first and second substrates 10 and 40 and a liquid crystal layer LC. The first and second substrates 10 and 40 face each other, and the liquid crystal layer LC is interposed therebetween. The first and second substrates 10 and 40 may be referred to as an array substrate and a color filter substrate, respectively.

[0009] A pixel region P is defined on the first substrate 10. A thin film transistor (TFT) T, a common electrode 30 and a pixel electrode 32 are formed on the first substrate 10 in the pixel region P. The TFT T includes a gate electrode 14 on the first substrate 10, a gate insulating layer 16 on the gate electrode 14, a semiconductor layer 18 on the gate insulating layer 16, and source and drain electrodes 20 and 22 on the semiconductor layer 18. The gate and source electrodes 14 and 20 extend from the gate and data lines 12 and 24, respectively, and the source and drain electrodes 20 and 22 are separated from each other. The common and pixel electrode 30 and 32 may be formed of a transparent con-

ductive material. The common and pixel electrode 30 and 32 are alternately arranged with and parallel to each other. The pixel electrode 32 is connected to the TFT T. The liquid crystal layer LC is driven by an electric field induced between the common and pixel electrodes 30 and 32.

[0010] Although not shown in FIG. 1, gate and data lines are formed on the first substrate 10 to define the pixel region P, and a common line is formed on the first substrate 10 to apply voltage into the common electrode 30.

[0011] The second substrate 40 includes a black matrix 42 and a color filter 44. The black matrix 42 corresponds to the gate line (not shown), the data line (not shown) and the TFT T. The color filter 44, which includes sub-color filters 44a and 44b, corresponds to the pixel region P. The color filter 44 includes one of red R, green G and blue (not shown) color.

[0012] FIG. 2 is a schematic plane view of an array substrate for an IPS mode LCD device according to the related art.

[0013] The gate and data lines 12 and 24 are formed on the first substrate 10 to define the pixel region P, and a common line 15 is parallel to and separated from the gate line 12. The TFT T is formed in the pixel region P to be connected to the gate and data lines 12 and 24. The TFT T includes the gate electrode 14, the gate insulating layer 16 (of FIG. 1), the semiconductor layer 18 and the source and drain electrodes 20 and 22. The gate and source electrodes 14 and 20 extend from the gate and data lines 12 and 24, respectively, and the source and drain electrodes 20 and 22 are separated from each other. Moreover, the common and pixel electrodes 30 and 32 are formed in the pixel region P. The pixel electrode 32 is connected to the TFT T and alternately arranged with the common electrode 30. The common electrode 30 extends from the common line 15 so as to be perpendicular to the common line 15. The common and pixel electrodes 30 and 32 are parallel to each other.

[0014] To improve luminance of images and aperture ratio, the pixel and common electrodes 32 and 30 are formed of the transparent conductive material. However, since the effective electric field, which drives the liquid crystal layer LC (of FIG. 1), is induced not on the pixel and common electrodes 32 and 30 but between the pixel and common electrode 32 and 30, there are problems of deficiency of luminance and aperture ratio.

[0015] To resolve these problems in the IPS mode LCD device, an advanced horizontal in-plane switching (AH-IPS) mode LCD device may be used. The pixel electrodes of the AH-IPS mode LCD device has a much narrower distance between them than the IPS mode LCD device, and the common electrode has a plate shape. The pixel electrodes are formed on the common electrode. The AH-IPS mode LCD device has a wide viewing angle in left and right sides and high contrast ratio. Moreover, there is no color shift.

[0016] FIG. 3 is a plane view of an array substrate for an AH-IPS mode LCD device according to the related art.

[0017] As shown in FIG. 3, the array substrate for the AH-IPS mode LCD device includes the gate and data lines 54 and 72, the TFT T, the common electrode 52 and the plurality of pixel electrodes 78 on a substrate 50. The gate and data lines 54 and 72 cross each other to define the pixel region P on the substrate 50. The TFT T is connected to the gate and data lines 54 and 72. The TFT T includes the gate electrode 56, the gate insulating layer (not shown), the semiconductor layer 62 and the source and drain electrodes

68 and **70**. The semiconductor layer **62** includes an active layer (not shown) and an ohmic contact layer (not shown). The gate and source electrodes **56** and **68** extend from the gate and data lines **54** and **72**, respectively, and the drain electrode **70** is separated from the source electrode **68**.

[0018] The common electrode **52** is plate shaped and is formed in an entire surface of the pixel region. The plurality of pixel electrodes **78** is formed on the common electrode **52**. The plurality of pixel electrodes **78** are bar shaped. The plurality of pixel electrodes **78** extend from first and second connection lines **78a** and **78b**. The plurality of pixel electrodes **78** are connected to one another by the first and second connection lines **78a** and **78b**. The plurality of pixel electrodes **78** are separated from one another in a center region of the pixel region P. The first connection line **78a** is connected to the drain electrode **70**, and the second connection line **78b** may overlap the gate line **54**.

[0019] The liquid crystal layer (not shown) is driven by the electric field between the common and pixel electrode **52** and **78**. Since the distance between the common and pixel electrodes **52** and **78** is much closer than the conventional IPS mode LCD device, the electric field effectively drives liquid crystal molecules of the liquid crystal layer (not shown) on the pixel electrode **78** such that the AH-IPS mode LCD device has higher luminance than the conventional IPS-mode LCD device.

[0020] FIGS. **4A** and **4B** are cross-sectional view taken along the lines IVa-IVa and IVb-IVb of FIG. **3**.

[0021] As shown in FIG. **4A**, the TFT T is formed in pixel region P on the substrate **50**. The TFT T includes the gate electrode **56** on the substrate **50**, the gate insulating layer **58** on the gate electrode **56**, the semiconductor layer **62**, which includes the active layer **62a** and the ohmic contact layer **62b**, on the gate insulating layer **58**, the source and drain electrodes **68** and **70** on the semiconductor layer **62**.

[0022] The common electrode **52** is formed of the transparent conductive material on the substrate **50**. An insulating layer **53** is interposed between the common electrode **52** and the gate electrode **56**. The first connection line **78a** is formed over the TFT T with the passivation layer **74** therebetween. The first connection line **78a** is connected to the drain electrode **68** through a drain contact hole **76** of the passivation layer **74**.

[0023] As shown in FIG. **4B**, the plurality of bar shaped pixel electrodes **78** correspond to the common electrode **52**. The plurality of pixel electrodes **78** extend from the first connection line **78a** (of FIG. **4A**) to be connected to one another. The data line **72** is formed on the gate insulating layer **58** and at both sides of the pixel region P.

[0024] The AH-IPS mode LCD device has the wide viewing angle and high contrast ratio. However, since the pixel electrodes **78** overlap the common electrode **52**, there are storage capacities generated between the pixel and common electrodes **78** and **52**. The storage capacities between the pixel and common electrodes **78** and **52** in the AH-IPS mode LCD device may be five times as much as the storage capacity in the conventional IPS-mode LCD device shown in FIGS. **1** and **2**. It requires that the TFT T in the AH-IPS mode LCD device has a greater size than the conventional IPS-mode LCD device shown in FIGS. **1** and **2** such that aperture ratio in the AH-IPS mode LCD device is reduced. Moreover, since the pixel electrodes are arranged to be

parallel to the data line **72** (of FIG. **3**), the viewing angle in upper and lower sides and a diagonal direction is deteriorated.

SUMMARY

[0025] Accordingly, the present invention is directed to an IPS mode LCD device that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

[0026] Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

[0027] An array substrate for an IPS mode LCD device comprises a substrate; a gate line along a first direction; a data line along a second direction; and a TFT connected to the gate and data lines. A common electrode having a plate shape is formed of a first transparent conductive material. A pixel electrode is formed of a second transparent conductive material on the common electrode and includes first and second portions and a plurality of third portions combining the first portion with the second portion. The first and second portions are parallel to the second direction and separated from each other, and the plurality of third portions are oblique to the first and second portions and separated from one another.

[0028] In another aspect of the present invention, a method of fabricating an array substrate for an IPS mode LCD device comprises forming a common electrode including a transparent conductive material and a plate shape on a substrate using a first mask. A gate line is formed along a first direction and a gate electrode is formed on the substrate having the common electrode, using a second mask. A gate insulating layer is formed on the common electrode, the gate line and the gate electrode. A semiconductor layer is formed on the gate insulating layer and corresponding to the gate electrode using a third mask. Source and drain electrodes and a data line are formed on the semiconductor layer and the gate insulating layer using a fourth mask. The source and drain electrodes are separated from each other, and the data line is arranged along a second direction; forming a passivation layer including a drain contact hole on the source and drain electrodes and the data line using a fifth mask. The drain contact hole exposes the drain electrode. A pixel electrode is formed connected to the drain electrode through the drain contact hole on the passivation layer using a sixth mask. The pixel electrode includes first and second portions and a plurality of third portions combining the first portion with the second portion. The first and second portions are parallel to the second direction and separated from each other. The plurality of third portions are oblique to the first and second portions and separated from one another.

[0029] In another aspect of the present invention, a method of fabricating an array substrate for an IPS mode LCD device comprises forming a gate line along a first direction, a gate electrode and a common electrode of a plate shape on a substrate using a first mask. A gate insulating layer is formed on the gate line, the gate electrode and the common electrode. A semiconductor layer is formed on the gate insulating layer and corresponding to the gate electrode

using a second mask. Source and drain electrodes and a data line are formed on the semiconductor layer and the gate insulating layer using a third mask. The source and drain electrodes are separated from each other, and the data line is arranged along a second direction. A passivation layer including a drain contact hole is formed on the source and drain electrodes and the data line using a fourth mask. The drain contact hole exposes the drain electrode. A pixel electrode is formed connected to the drain electrode through the drain contact hole on the passivation layer using a fifth mask. The pixel electrode includes first and second portions and a plurality of third portions combining the first portion with the second portion. The first and second portions are parallel to the second direction and separated from each other. The plurality of third portions are oblique to the first and second portions and separated from one another.

[0030] It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0031] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

[0032] FIG. 1 is a schematic cross-sectional view of an IPS mode LCD device according to the related art.

[0033] FIG. 2 is a schematic plane view of an array substrate for an IPS mode LCD device according to the related art.

[0034] FIG. 3 is a plane view of an array substrate for an AH-IPS mode LCD device according to the related art.

[0035] FIGS. 4A and 4B are cross-sectional view taken along the lines III-III and IV-IV of FIG. 3.

[0036] FIG. 5 is a plane view of an array substrate for an IPS-mode LCD device according to a first exemplary embodiment of the present invention.

[0037] FIGS. 6A to 6G are cross-sectional views showing a process of fabricating a portion taken along the line V-V of FIG. 5.

[0038] FIGS. 7A to 7G are cross-sectional views showing a process of fabricating a portion taken along the line VI-VI of FIG. 5.

[0039] FIG. 8 is a plane view of an array substrate for an IPS-mode LCD device according to a second exemplary embodiment of the present invention.

[0040] FIGS. 9A and 9B are cross-sectional views taken along the lines VII-VII and VIII-VIII, respectively.

[0041] FIG. 10 is a plane view of an array substrate for an IPS-mode LCD device according to a third exemplary embodiment of the present invention.

[0042] FIGS. 11A to 11J are cross-sectional views showing a process of fabricating a portion taken along the line IX-IX of FIG. 10.

[0043] FIGS. 12A to 12J are cross-sectional views showing a process of fabricating a portion taken along the line X-X of FIG. 10.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0044] Reference will now be made in detail to the preferred embodiments, examples of which are illustrated in the accompanying drawings.

[0045] FIG. 5 is a plane view of an array substrate for an IPS-mode LCD device according to a first exemplary embodiment of the present invention. The IPS-mode LCD device according to a first exemplary embodiment of the present invention includes an insulating layer of a low dielectric constant between the pixel and common electrodes to resolve the problem of storage capacity in the related art.

[0046] As shown in FIG. 5, the gate and data lines 104 and 120 are formed on the substrate 100. The gate and data lines 104 and 120 cross each other to define the pixel region P. The TFT T is connected to the gate and data lines 104 and 120. The TFT T includes the gate electrode 106, the semiconductor layer 112, the source electrode 116 and the drain electrode 118. The common electrode 102 and the pixel electrode 126 are formed on the substrate 100 in the pixel region P. The common and pixel electrode 102 and 126 are plate shaped and bar shaped, respectively. The pixel electrode 102 includes first and second portions 126a and 126b and a plurality of third portions 126c. The first and second portions 126a and 126b are substantially parallel to the data line 120. The first and second portions 126a and 126b are parallel to and separated from each other. The plurality of third portions 126c connect to the first and second portions 126a and 126b. The plurality of third portions 126c are parallel to one another and have an angle of 0 degree to 45 degree with respect to the gate line 104. In other words, the plurality of third portions 126c is oblique to the first and second portions 126a and 126b. The plurality of third portions 126c are arranged as closed to each other as possible so that the electric field between the common and pixel electrodes 102 and 126 drives the liquid crystal molecules on the pixel electrode 126. The third pixel electrode 126c in one pixel region P may be symmetric with the third pixel electrode 126c in another pixel region P which is next to the one pixel region P. The viewing angles in upper and lower sides and a diagonal direction are improved by the above mentioned structure.

[0047] First and second metal patterns 108a and 108b are formed on both ends of the common electrode 102. The first and second metal patterns 108a and 108b are parallel to the data line 120. In other words, the first and second metal patterns 108a and 108b are parallel to the first and second portions 126a and 126b. The first metal pattern 108a in one pixel region P and the second metal pattern 108b in another pixel region, which is next to the one pixel region P, are integrated each other. The resistance of the common electrode 102 is reduced by the first and second metal patterns 108a and 108b. Moreover, the first and second metal patterns 108a and 108b block leakage light. The liquid crystal molecules in a light leakage region D next to the common electrode 102 are irregularly arranged such that undesired images are displayed in the light leakage region D. The first and second metal patterns 108a and 108b is capable of preventing the above problem.

[0048] Moreover, a margin of forming a black matrix (not shown) on an upper substrate (not shown) is decreased due to the first and second metal patterns **108a** and **108b**. In more detail, when the black matrix (not shown) is formed to correspond to the light leakage region D, the margin is required for misalignment. The larger the margin, the less aperture ratio the device has. The first and second metal patterns **108a** and **108b** decrease the margin such that the aperture ratio is improved.

[0049] The gate insulating layer (not shown) between the common and pixel electrodes **102** and **126** has a low dielectric constant. The dielectric constant of the gate insulating layer (not shown) in the present invention may be about 3 to 4. The storage capacity between the common and pixel electrodes **102** and **126** is reduced by the gate insulating layer having the dielectric constant. Moreover, since the storage capacity between the common and pixel electrodes **102** and **126**, the size of the TFT T is reduced.

[0050] FIGS. 6A to 6G are cross-sectional views showing a process of fabricating a portion taken along the line V-V of FIG. 5, and FIGS. 7A to 7G are cross-sectional views showing a process of fabricating a portion taken along the line VI-VI of FIG. 5.

[0051] A first mask process is described in FIGS. 6A and 7A. The common electrode **102** is formed on the substrate **100** in the pixel region P by depositing and patterning a transparent conductive material using a first mask (not shown). The transparent conductive material includes one of indium-tin-oxide (ITO) and indium-zinc-oxide (IZO).

[0052] A second mask process is described in FIGS. 6B and 7B. The gate line **104** (of FIG. 5) is formed on the substrate **100** including the common electrode **102** by depositing and patterning a first metallic material using a second mask (not shown). The first metallic material includes at least one of aluminum (Al), aluminum alloy (AlNd), tungsten (W), copper (Cu), Molybdenum (Mo), Chromium (Cr), moly-tungsten (MoW). The gate line **104** (of FIG. 5) may function as the gate electrode **106**. The gate electrode **106** may extend from the gate line **104**. At the same time, the first and second metal patterns **108a** and **108b** are formed on both sides of the common electrode **102**. The first and second metal patterns **108a** and **108b** may be perpendicular to the gate line **104** (FIG. 5).

[0053] Next, as shown in FIGS. 6C and 7C, the gate insulating layer **110** is formed on the gate line **104** (FIG. 5), the gate electrode **106**, the common electrode **102** and the first and second metal patterns **108a** and **108b** by depositing an insulating material. The insulating material has the low dielectric constant between about 3 and about 4. For example, silicon oxide (SiO₂), benzocyclobutene (BCB) and acrylic resin may be used for the gate insulating layer **110**. Silicon oxide (SiO₂) has dielectric constant of about 3.4. The dielectric constant of the gate insulating layer may be less than 3. When the gate insulating layer has the dielectric constant between 3 and 4, the storage capacity between the common and pixel electrodes **102** and **126** has a quarter of the storage capacity of device in the related art. The LCD device in the related art includes the gate insulating layer of silicon nitride (SiN_x). Since the storage capacity of IPS mode LCD device according to the present invention is reduced, the TFT T is capable of having a small size and the aperture ratio is improved.

[0054] A third mask process is described in FIGS. 6D and 7D. As shown in FIGS. 6D and 7D, the semiconductor layer

112 including the active layer **112a** and the ohmic contact layer **112b** on the gate insulating layer **110** is formed by sequentially depositing and patterning intrinsic amorphous silicon (a-Si:H) and impurity-doped amorphous silicon (n+a-Si:H) using a third mask (not shown). The semiconductor layer **112** corresponds to the gate electrode **106**.

[0055] A fourth mask process is described in FIGS. 6E and 7E. As shown in FIGS. 6E and 7E, the source and drain electrodes **116** and **118**, which are separated from each other, are formed on the semiconductor layer **112** by depositing and patterning a second metallic material using a fourth mask (not shown). The second metallic material may include at least one of aluminum (Al), aluminum alloy (AlNd), tungsten (W), copper (Cu), Molybdenum (Mo), Chromium (Cr), moly-tungsten (MoW). At the same time, the data line **120** is formed on the gate insulating layer **110**. The data line **120** extends from the source electrode **116** and crosses the gate line **104** (of FIG. 5) to define the pixel region P.

[0056] A fifth mask process is described in FIGS. 6F and 7F. As shown in FIGS. 6F and 7F, the passivation layer **122**, which includes a drain contact hole **124**, is formed on the source and drain electrodes **116** and **118** and the data line **120** by depositing and patterning one of an inorganic insulating material and an organic insulating material using a fifth mask process. The inorganic insulating material and the organic insulating material include a low dielectric constant. The drain contact hole **124** exposes the drain electrode **118**.

[0057] A sixth mask process is described in FIGS. 6G and 7G. As shown in FIGS. 6G and 7G, a pixel electrode **126** is formed on the passivation layer **122** by depositing and patterning a transparent conductive material using a sixth mask (not shown). The transparent conductive material may include one of ITO and IZO. The pixel electrode **126** is connected to the drain electrode **118** through the drain contact hole **124**.

[0058] The pixel electrode **126** includes the first and second portions **126a** and **126b** and the plurality of third portions **126c**. The first and second portions **126a** and **126b** are parallel to the data line and separated from each other. In other words, the first and second portions **126a** and **126b** are perpendicular to the gate line **104** (FIG. 5). The plurality of third portions **126c** connect to the first and second portions **126a** and **126b**. The plurality of third portions **126c** are parallel to one another and have an angle of 0 degree to 45 degree with respect to the gate line **104**. In other words, the plurality of third portions **126c** is oblique to the first and second portions **126a** and **126b**. The third pixel electrode **126c** in one pixel region P may be symmetric with the third pixel electrode **126c** in another pixel region P which is next to the one pixel region P.

[0059] The array substrate for the IPS mode LCD device according to the first exemplary embodiment of the present invention is manufactured by the above-mentioned processes. Since the array substrate includes the gate insulating layer **110** of a low dielectric constant, the storage capacity between the common and pixel electrodes **102** and **126** is reduced. Since the TFT has a small size, the aperture ratio is improved. Moreover, since the pixel electrode **126** is parallel to and oblique to the data line **120**, the IPS mode LCD device has a wide viewing angle.

[0060] FIG. 8 is a plane view of an array substrate for an IPS-mode LCD device according to a second exemplary embodiment of the present invention. The array substrate according to the second exemplary embodiment includes a

metal pattern to block the light leakage region between the common electrode and data line.

[0061] As shown in FIG. 8, the gate and data lines 204 and 220, the TFT T, the common electrode 202, the first and second metal pattern 208a and 208b are formed on the substrate 200. The gate and data lines 204 and 220 cross each other such that the pixel region P is defined on the substrate 200. The TFT T is connected to the gate and data lines 204 and 220. The TFT T includes the gate electrode 206, the semiconductor layer 212, the source electrode 216 and the drain electrode 218. The common electrode 202 and the pixel electrode 226 are formed on the substrate 200 in the pixel region P. The common and pixel electrode 202 and 226 have the plate shape and the bar shape, respectively. The pixel electrode 202 includes first and second portions 226a and 226b and a plurality of third portions 226c. The first and second portions 226a and 226b are substantially parallel to the data line 220. The first and second portions 226a and 226b are parallel to and separated from each other. The plurality of third portions 226c connect to the first and second portions 226a and 226b. The plurality of third portions 226c are parallel to one another and have an angle of 0 degree to 45 degree with respect to the gate line 204. In other words, the plurality of third portions 226c are oblique to the first and second portions 226a and 226b. The plurality of third portions 226c are arranged as closed to each other as possible so that the electric field between the common and pixel electrodes 202 and 226 drives the liquid crystal molecules on the pixel electrode 226. The third pixel electrode 226c in one pixel region P may be symmetric with the third pixel electrode 226c in another pixel region P which is next to the one pixel region P. The viewing angles in upper and lower sides and a diagonal direction are improved by the above mentioned structure.

[0062] The first and second metal patterns 208a and 208b are formed in the light leakage region D. The light leakage region D corresponds to between the common electrode 202 and the data line 220. Each of the first and second metal patterns 208a and 208b overlaps the common electrode 202 and the data line 220 such that the light leakage region D is fully covered with the first and second metal patterns 208a and 208b. The first and second metal patterns 208a and 208b are parallel to the data line 220. In other words, the first and second metal patterns 208a and 208b are parallel to the first and second portions 226a and 226b. The first metal pattern 208a in one pixel region P and the second metal pattern 208b in another pixel region, which is next to the one pixel region P, are integrated each other. The resistance of the common electrode 202 is reduced by the first and second metal patterns 208a and 208b. Moreover, the first and second metal patterns 208a and 208b block leakage light in the light leakage region D such that the IPS-LCD device does not require the black matrix (not shown). Without the black matrix, the aperture ratio is improved.

[0063] Since the data line 220 overlaps the first and second metal patterns 208a and 208b, an organic insulating layer (not shown) is formed between the data line 220 and the first metal pattern 220a and between the data line 220 and the second metal pattern 220b to prevent a voltage in the first and second metal patterns 208a and 208b affecting the data line 220. The organic insulating layer (not shown) has a low dielectric constant.

[0064] FIGS. 9A and 9B are cross-sectional views taken along the lines VII-VII and VIII-VIII, respectively.

[0065] As shown in FIGS. 9A and 9B, the gate and data lines 204 (of FIG. 8) and 220 cross each other such that the pixel region P is defined on the substrate 200. The TFT T is connected to the gate and data lines 204 (of FIG. 8) and 220. The TFT T includes the gate electrode 206, the gate insulating layer 210 on the gate electrode 206, the semiconductor layer 212 on the gate insulating layer 210, the source electrode 216 and the drain electrode 218 on the semiconductor layer 212. The gate electrode 206 and the source electrode 216 extend from the gate line 204 (of FIG. 8) and the data line 220, respectively. The source and drain electrodes 216 and 218 are separated from each other. The semiconductor layer 212 includes the active layer 212a and the ohmic contact layer 212b.

[0066] The common electrode 202 of a transparent conductive material is formed on the substrate 200. The common electrode 202 is plate shaped. The pixel electrode 226, which includes the first and second portions 226a and 226b and the plurality of third portions 226c, is formed over the common electrode 202. The gate insulating layer 210 and the passivation layer 222 are sequentially disposed between the common and pixel electrodes 202 and 226.

[0067] Moreover, the first and second metal patterns 208a and 208b are formed the light leakage region D. As mentioned above, the light leakage region D corresponds to the region between the common electrode 202 and the data line 220. The first and second metal patterns 208a and 208b contacts the common electrode 202 and overlaps the data line 220. The leakage light in the light leakage region D is fully blocked by the first and second metal patterns 208a and 208b. To prevent the first and second metal patterns 208a and 208b affecting the data line 220, the gate insulating layer 210, which is disposed between the first metal pattern 208a and the data line 220 and between the second metal pattern 208b and the data line 220, is formed of an insulating material having a low dielectric constant less than 3. The insulating material may include one of BCB and acrylic resin.

[0068] The array substrate according to the second exemplary embodiment of the present invention is fabricated by a same process as described above with respect to the first embodiment.

[0069] FIG. 10 is a plane view of an array substrate for an IPS-mode LCD device according to a third exemplary embodiment of the present invention. The array substrate according to the third exemplary embodiment is fabricated by a process using fewer masks than the first and second exemplary embodiments. Moreover, a phenomenon of reverse taper, which occurs when laminated metal layers are simultaneously patterned, is prevented in the third exemplary embodiment.

[0070] As shown in FIG. 10, the gate and data lines 314 and 332 are aligned on the substrate 300. The gate and data lines 314 and 332 cross each other such that the pixel region P is defined on the substrate 300. The TFT T is connected to the gate and data lines 314 and 332. The TFT T includes the gate electrode 316, the semiconductor layer 324, the source electrode 328 and the drain electrode 330. The common electrode 318 and the pixel electrode 338 are formed on the substrate 300 in the pixel region P. The common and pixel electrode 318 and 338 are plate shaped and bar shaped, respectively. The pixel electrode 338 includes the first and second portions 338a and 338b and the plurality of third portions 338c. The first and second portions 338a and 338b

are substantially parallel to the data line 332. The first and second portions 338a and 338b are parallel to and separated from each other. The plurality of third portions 338c connect to the first and second portions 338a and 338b. The plurality of third portions 338c are parallel to one another and have an angle of 0 degree to 45 degree with respect to the gate line 314. In other words, the plurality of third portions 338c are oblique to the first and second portions 338a and 338b. The plurality of third portions 338c are arranged as close to each other as possible so that the electric field between the common and pixel electrodes 318 and 338 drives the liquid crystal molecules on the pixel electrode 338. The third pixel electrode 338c in one pixel region P may be symmetric with the third pixel electrode 338c in another pixel region P, which is next to the one pixel region P. The viewing angles in upper and lower sides and a diagonal direction are improved by the above mentioned structure.

[0071] The array substrate according to the third exemplary embodiment is fabricated by a fifth mask process by forming the common electrode 318, the gate line 314 and the gate electrode 316 using a same mask (not shown). At the same time, the first and second metal patterns 320a and 320b are formed at both ends of the common electrode 318 to reduce a resistance of the common electrode 318. The first metal pattern 320a in one pixel region P is integrated the second metal pattern 320b in another pixel region P, which is next to the one pixel region P, such that a common voltage is applied into the common electrode 318 in different pixel regions P. A fabricating process of the array substrate according to the third exemplary embodiment is described in FIGS. 11A to 11J and FIGS. 12A to 12J.

[0072] FIGS. 11A to 11J are cross-sectional views showing a process of fabricating a portion taken along the line IX-IX of FIG. 10, and FIGS. 12A to 12J are cross-sectional views showing a process of fabricating a portion taken along the line X-X of FIG. 10.

[0073] A first mask process is described by FIGS. 11A to 11F and FIGS. 12A to 12F.

[0074] As shown in FIGS. 11A and 12A, a transparent conductive material layer 302, a first metallic material layer 304 and a second metallic material layer 306 are formed on the substrate 300 by sequentially depositing a transparent conductive material, a first metallic material and a second metallic material. The transparent conductive material may include one of ITO and IZO. The first metallic material may be Mo. The second metallic material may be AlNd.

[0075] Next, as shown in FIGS. 11B and 12B, a photoresist (PR) layer 308 is formed on the second metallic material layer 306 by coating a PR. Then, a first mask M, which includes a transmissive area B1, a blocking area B2 and a half-transmissive area B3, is disposed over the PR layer 308. The half-transmissive area B3 has a transmittance less than the transmissive area B1 and greater than the blocking area B2. The half-transmissive area B3 may be formed of one of an opaque layer and a slit shape. When the PR layer 308 is exposed using the first mask M, the PR layer 308 corresponding to the half-transmissive area B3 is less exposed than the PR layer 308 corresponding to the transmissive area B1 and much exposed than the PR layer 308 corresponding to the blocking area B2. The blocking area B2 is disposed a region in which the gate electrode 316 (FIG. 10), the gate line 314 (FIG. 10) and the first and second metal patterns 320a (FIG. 10) and 320b (FIG. 10). Since the half-transmissive area B3 functions to prevent the phenomenon of

reverse taper in the gate line 314 (FIG. 10) and the first and second metal patterns 320a (FIG. 10) and 320b (FIG. 10), the half-transmissive area B3 is disposed at both ends of the blocking area B2. Moreover, the half-transmissive area B3 is disposed in a region, in which the common electrode 318 (FIG. 10) is to be formed.

[0076] Next, the PR layer 308 is exposed and developed using the first mask M.

[0077] As shown in FIGS. 11C and 12C, first and second PR patterns 310 and 312, which have different height, are formed on the second metallic material layer 306. The first and second PR patterns 310 and 312 correspond to the blocking and half-transmissive area B2 and B3, respectively. The first PR pattern 310 is higher than the second PR pattern 312. The PR layer 308 corresponding to the transmissive area B1 is perfectly removed such that the second metallic material layer 306 corresponding to the transmissive area B1 is exposed between the first and second PR patterns 310 and 312.

[0078] Next, the exposed second metallic material layer 306 is removed using a first etchant. Sequentially, the first metallic material layer 304 and the transparent conductive material layer 302 are removed using the first etchant.

[0079] Thus, as shown in FIGS. 11D and 12D, a transparent conductive material pattern M1, a first metallic material pattern M2 and a second metallic material pattern M3 are formed between the substrate 300 and the first PR pattern 310 and between the substrate 300 and the second PR pattern 312. The transparent conductive material pattern M1, the first metallic material pattern M2 and the second metallic material pattern M3 corresponding to end portions B of the second PR pattern 312 have a tapered side shape. In other words, the first metallic material pattern M2 extrudes from the second metallic material pattern M3, and the transparent conductive material pattern M1 extrudes from the first metallic material pattern M2.

[0080] Next, as shown in FIGS. 11E and 12E, the first and second PR patterns 310 and 312 are ashed such that the first PR pattern 310 is partially removed and the second PR pattern 312 is perfectly removed. As a result, the second metallic material pattern M3 corresponding to the second PR pattern 312 is exposed.

[0081] Next, as shown in FIGS. 11F and 12F, the exposed second metallic material pattern M3 and the first metallic material pattern M2 below the exposed second metallic material pattern M3 are removed using a second etchant. The second etchant is different from the first etchant such that the transparent conductive material pattern M1 is not removed. Moreover, the first metallic material pattern M2, which is formed of Mo, and the second metallic material pattern M3, which is formed of AlNd, has different etching ratio with regard to the second etchant. The first metallic material pattern M2 is much etched than the second metallic material pattern M3. However, since the first metallic material pattern M2 extrudes from the second metallic material pattern M3, the first and second metallic material patterns M2 and M3 may have a same end line.

[0082] When only one PR pattern is formed on the second metallic material layer M3 unlike the above-mentioned process, the transparent conductive material pattern M1 and the first and second metallic material patterns M2 and M3 have a same shape, not the tapered side shape. In this case, the first and second metallic material patterns M2 and M3 have the reverse tapered shape and are not on the same end

line. When an insulating layer is formed on the first and second metallic material patterns having the reverse tapered shape, the insulating layer has defects. When the insulating layer is patterned, an etchant used for patterning may contact the gate line below the insulating layer through the defects such that the gate line may be damaged.

[0083] Since the first and second metallic material patterns M2 and M3 have the same end line, not the reverse tapered shape, the array substrate according to the third exemplary embodiment do not have the above-mentioned problems.

[0084] The transparent conductive material pattern M1, which is not covered with the first metallic material pattern M2, functions as the common electrode 318. The gate electrode 316 has a triple-layered structure including the transparent conductive material pattern M1 and the first and second metallic material patterns M2 and M3. Moreover, the first and second metal patterns 320a and 320b form both ends of the common electrode 318. The first and second metal patterns 320a and 320b have double-layered structures. At the same time, the gate line 314 (FIG. 10) is formed on the substrate 300. The gate line 314 (FIG. 10) has the same structure as the gate electrode 316. Then, the first PR pattern 310 is removed.

[0085] A contact hole is formed at an end of the gate line by partially removing the gate line in first mask process. In this case, when the gate line has the reverse-tapered shape, there is a problem of contact another metal layer with the gate line because of the reverse-tapered shape. However, since the gate line in the present embodiment has the tapered shape, the array substrate according to the present embodiment does not have the above-mentioned problem.

[0086] A second mask process is described in FIGS. 11G and 12G. As shown in FIGS. 11G and 12G, the gate insulating layer 322 is formed on the gate electrode 316 and the common electrode 318 by depositing a first insulating material of low dielectric constant. The first insulating material may include silicon oxide (SiO₂).

[0087] Next, the semiconductor layer 324, which includes the active layer 324a and the ohmic contact layer 324b, is formed on the gate insulating layer 322 by sequentially depositing and patterning intrinsic amorphous silicon (a-Si:H) and impurity-doped amorphous silicon (n+a-Si:H). The active layer 324a and the ohmic contact layer 324b are formed of intrinsic amorphous silicon (a-Si:H) and impurity-doped amorphous silicon (n+a-Si:H), respectively.

[0088] A third mask process is described in FIGS. 11H and 12H. As shown in FIGS. 11H and 12H, the source and drain electrodes 328 and 330 and the data line 332 are formed on the gate insulating layer 322 and the semiconductor layer 324 by depositing and patterning a third metallic material. The third metallic material includes at least one of Al, AlN, Cr, Mo, MoW, W and Cu. The source and drain electrodes 328 and 330 are separated from each other, and the source electrode 328 extends from the data line 332. The data line 332 crosses the gate line 314 (FIG. 10) such that the pixel region P is defined.

[0089] A fourth mask process is described in FIGS. 11I and 12I. As shown in FIGS. 11I and 12I, the passivation layer 334, including a drain contact hole 336, is formed on the source and drain electrodes 328 and 330 and the data line 332 by depositing and patterning a second insulating material of low dielectric constant. The second insulating material may include SiO₂. The passivation layer 334 may be formed of

an organic insulating material. The drain contact hole 336 exposes the drain electrode 330.

[0090] A fifth mask process is described in FIGS. 11J and 12J. As shown in FIGS. 11J and 12J, the pixel electrode 338 is formed on the passivation layer 334 by depositing and patterning a transparent conductive material. The transparent conductive material includes one of ITO and IZO. The pixel electrode 338 is connected to the drain electrode 330 through the drain contact hole 336. The pixel electrode 338 includes the first and second portions 338a and 338b and the plurality of third portions 338c. The first and second portions 338a and 338b are parallel to the data line 332 and separated from each other. The plurality of third portions 338c combine the first portion 338a with the second portion 338b. The plurality of third portions 338c have an angle between 0 degree and 45 degrees with regard to the gate line 314 (of FIG. 10).

[0091] The array substrate according to the third exemplary embodiment is fabricated by the above-mentioned five mask process.

What is claimed is:

1. An array substrate for an IPS mode LCD device, comprising:
 - a substrate;
 - a gate line along a first direction;
 - a data line along a second direction;
 - a TFT connected to the gate and data lines;
 - a common electrode having a plate shape on the substrate and comprised of a first transparent conductive material; and
 - a pixel electrode comprised of a second transparent conductive material on the common electrode and including first and second portions and a plurality of third portions combining the first portion with the second portion, wherein the first and second portions are parallel to the second direction and separated from each other, and wherein the plurality of third portions are oblique to the first and second portions and separated from one another.
2. The substrate according to claim 1, further comprising an insulating layer between the common and pixel electrodes, wherein the insulating layer has a dielectric constant between about 3 and about 4.
3. The substrate according to claim 2, wherein the insulating layer includes one of SiO₂, benzocyclobutene (BCB) and acrylic resin.
4. The substrate according to claim 1, further comprising first and second metal patterns disposed between the common electrode and the data line.
5. The substrate according to claim 4, wherein the first and second metal patterns contact the common electrode.
6. The substrate according to claim 4, wherein the first and second metal patterns overlap the data line.
7. The substrate according to claim 4, wherein the first metal pattern in one pixel region is integrated with the second metal pattern in another pixel region.
8. The substrate according to claim 4, wherein the first and second metal patterns are on a same layer and comprised of a same material as the gate line.
9. The substrate according to claim 1, wherein the plurality of third portions have an angle between 0 degree and 45 degrees with regard to the first direction.

10. The substrate according to claim 1, wherein the first and second transparent conductive materials include one of ITO and IZO.

11. The substrate according to claim 1, wherein the gate line includes first, second and third layers.

12. The substrate according to claim 11, wherein the first layer is on a same layer and comprised of a same material as the common electrode, and the second and third layers include Mo and AlNd, respectively.

13. The substrate according to claim 12, further comprising first and second metal patterns each including fourth and fifth layers disposed between the common electrode and the data line, wherein the fourth layer is on a same layer and comprised of a same material as the second layer, and the fifth layer is on a same layer and comprised of a same material as the third layer.

14. A method of fabricating an array substrate for an IPS mode LCD device, comprising:

forming a common electrode including a transparent conductive material and a plate shape on a substrate, using a first mask;

forming a gate line along a first direction and a gate electrode on the substrate having the common electrode, using a second mask;

forming a gate insulating layer on the common electrode, the gate line and the gate electrode;

forming a semiconductor layer on the gate insulating layer and corresponding to the gate electrode, using a third mask;

forming source and drain electrodes and a data line on the semiconductor layer and the gate insulating layer, using a fourth mask, wherein the source and drain electrodes are separated from each other, and the data line is arranged along a second direction;

forming a passivation layer including a drain contact hole on the source and drain electrodes and the data line, using a fifth mask, the drain contact hole exposing the drain electrode; and

forming a pixel electrode connected to the drain electrode through the drain contact hole on the passivation layer, using a sixth mask, wherein the pixel electrode includes first and second portions and a plurality of third portions combining the first portion with the second portion, wherein the first and second portions are parallel to the second direction and separated from each other, and wherein the plurality of third portions are oblique to the first and second portions and separated from one another.

15. The method according to claim 14, wherein the gate insulating layer includes one of SiO₂, benzocyclobutene (BCB) and acrylic resin and has a dielectric constant between about 3 and about 4.

16. The method according to claim 14, further comprising forming first and second metal patterns between the common electrode and the data line.

17. The method according to claim 16, wherein the first and second metal patterns contact the common electrode and overlap the data line.

18. The method according to claim 16, wherein the first metal pattern in one pixel region is integrated with the second metal pattern in another pixel region.

19. The method according to claim 16, wherein the first and second metal patterns are simultaneously formed as the gate line.

20. The method according to claim 14, wherein the plurality of third portions have an angle between 0 degree and 45 degrees with regard to the first direction.

21. A method of fabricating an array substrate for an IPS mode LCD device, comprising:

forming a gate line along a first direction, a gate electrode and a common electrode of a plate shape on a substrate, using a first mask;

forming a gate insulating layer on the gate line, the gate electrode and the common electrode;

forming a semiconductor layer on the gate insulating layer and corresponding to the gate electrode, using a second mask;

forming source and drain electrodes and a data line on the semiconductor layer and the gate insulating layer, using a third mask, wherein the source and drain electrodes are separated from each other, and the data line is arranged along a second direction;

forming a passivation layer including a drain contact hole on the source and drain electrodes and the data line, using a fourth mask, the drain contact hole exposing the drain electrode; and

forming a pixel electrode connected to the drain electrode through the drain contact hole on the passivation layer, using a fifth mask, wherein the pixel electrode includes first and second portions and a plurality of third portions combining the first portion with the second portion, wherein the first and second portions are parallel to the second direction and separated from each other, and wherein the plurality of third portions are oblique to the first and second portions and separated from one another.

22. The method according to claim 21, wherein the step of forming the gate line, the gate electrode and the common electrode includes;

sequentially forming first, second and third metallic material layers on the substrate;

forming a PR layer on the third metallic material layer; disposing a mask including first, second and third areas over the PR layer, the third area having a transmittance between the first and second areas;

forming first, second and third PR patterns on the third metallic material layer by exposing and developing the PR layer using the mask, wherein the second PR pattern has a less height than the first PR pattern and a same height as the third PR pattern and is disposed both sides of the first PR pattern, and wherein the third metallic material layer corresponding to the first area is exposed between the second and third PR patterns;

forming first, second and third metallic material patterns on the substrate by sequentially removing the third, second and first metallic material layers exposed between the PR patterns;

exposing the third metallic material pattern by the first PR patterns by removing the second and third PR patterns; sequentially removing the third and second metallic material patterns exposed by the first PR pattern such that the first metallic material pattern is exposed; and

removing the first PR pattern, wherein the first, second and third metallic material patterns below the first PR patterns are defined as the

gate line and gate electrode, respectively, and the exposed first metallic material pattern is defined as the common electrode.

23. The method according to claim 22, wherein the third area includes one of an opaque layer and a slit layer.

24. The method according to claim 22, wherein the second and third PR patterns correspond to the third area.

25. The method according to claim 22, wherein the first metallic material layer includes one of ITO, IZO, and the second and third metallic material layers include Mo and AlNd, respectively.

26. The method according to claim 25, wherein the first, second and third metallic material patterns formed by sequentially removing the first, second and third metallic material layers have a tapered side shape.

27. The method according to claim 26, wherein the second and third metallic material patterns of the gate line and the gate electrode have substantially the same shape.

28. The method according to claim 21, further comprising simultaneously forming first and second metal patterns as the gate line, the gate electrode and the common electrode, wherein the first and second metal patterns are disposed at both ends of the common electrode.

29. The method according to claim 28, wherein the first and second metal patterns are aligned along the second direction.

30. The method according to claim 21, wherein the plurality of third portions have an angle between 0 degree and 45 degrees with regard to the first direction.

* * * * *

专利名称(译)	用于面内切换模式液晶显示装置的阵列基板及其制造方法		
公开(公告)号	US20070153204A1	公开(公告)日	2007-07-05
申请号	US11/644716	申请日	2006-12-22
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG 飞利浦LCD CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. LTD.		
[标]发明人	KIM DO SUNG AHN BYUNG CHUL		
发明人	KIM, DO-SUNG AHN, BYUNG-CHUL		
IPC分类号	G02F1/1343		
CPC分类号	G02F1/133345 G02F2001/13629 G02F2001/134372 G02F1/13439		
优先权	1020050133552 2005-12-29 KR		
其他公开文献	US7710526		
外部链接	Espacenet USPTO		

摘要(译)

用于IPS模式LCD装置的阵列基板包括基板;沿第一方向的栅极线;沿第二方向的数据线; TFT连接到栅极线 and 数据线;公共电极, 在基板上具有板状, 由第一透明导电材料形成;在公共电极上由第二透明导电材料形成并包括第一和第二部分的像素电极和将第一部分与第二部分组合的多个第三部分。第一和第二部分平行于第二方向并彼此分开, 并且多个第三部分相对于第一和第二部分倾斜并且彼此分开。

