



US007894032B2

(12) **United States Patent**
Ahn

(10) **Patent No.:** **US 7,894,032 B2**
(45) **Date of Patent:** ***Feb. 22, 2011**

(54) **LIQUID CRYSTAL DISPLAY DEVICE
HAVING PARTICULAR STRUCTURE FOR
DATA LINE, SOURCE ELECTRODE, DRAIN
ELECTRODE AND PIXEL ELECTRODE**

(75) Inventor: **Byung Chul Ahn**, Anyang-shi (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/654,263**

(22) Filed: **Dec. 15, 2009**

(65) **Prior Publication Data**

US 2010/0157233 A1 Jun. 24, 2010

Related U.S. Application Data

(62) Division of application No. 11/312,593, filed on Dec. 21, 2005, now Pat. No. 7,656,500.

(30) **Foreign Application Priority Data**

Dec. 24, 2004 (KR) 10-2004-0112577

(51) **Int. Cl.**

G02F 1/1343 (2006.01)

G02F 1/1339 (2006.01)

(52) **U.S. Cl.** **349/147; 349/38; 349/153;**
349/190; 349/141

(58) **Field of Classification Search** 349/147,
349/38, 153, 190, 141
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,338,989	B1 *	1/2002	Ahn et al.	438/158
7,348,198	B2 *	3/2008	Ahn	438/30
7,369,202	B2 *	5/2008	Ahn et al.	349/141
7,489,379	B2 *	2/2009	Ahn et al.	349/139
7,679,699	B2 *	3/2010	Ahn et al.	349/114

* cited by examiner

Primary Examiner—Mike Qi

(74) *Attorney, Agent, or Firm*—McKenna Long & Aldridge LLP

(57) **ABSTRACT**

A liquid crystal display device and a fabricating method having a simplified process are disclosed. The liquid crystal display device comprises, among other features, first and second substrates, a gate line crossing a data line with a gate insulating film therebetween to define a pixel area. A common line is provided on the substrate substantially parallel to the gate line, and a common electrode is extended from the common line into the pixel area. A pixel electrode is extended from a drain electrode into the pixel area to form a horizontal electric field with the common electrode. The data line, a source electrode, a drain electrode and the pixel electrode are formed of a first conductive layer group having at least double conductive layers, and are formed in an area to be sealed by a sealant upon joining the first and second substrates.

14 Claims, 22 Drawing Sheets




FIG. 1
RELATED ART




FIG. 2





FIG. 3






FIG. 4

FIG. 5




FIG. 6A




FIG. 6B




FIG. 7A




FIG. 7B




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 8.




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10C




FIG. 10D





FIG. 10E



LIQUID CRYSTAL DISPLAY DEVICE HAVING PARTICULAR STRUCTURE FOR DATA LINE, SOURCE ELECTRODE, DRAIN ELECTRODE AND PIXEL ELECTRODE

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a Divisional of application Ser. No. 11/312,593 filed Dec. 21, 2005 now U.S. Pat. No. 7,656,500, now allowed; which claims priority to Korean Patent Application No. 10-2004-0112577, filed Dec. 24, 2004 all of which are hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a liquid crystal display device using a horizontal electric field, and more particularly to a thin film transistor substrate of a horizontal electric field applying type and a fabricating method thereof that simplify a process.

2. Discussion of the Related Art

Generally, a liquid crystal display (LCD) controls light transmittance of a liquid crystal having a dielectric anisotropy using an electric field to display a picture. To this end, the LCD includes a liquid crystal display panel for displaying a picture by a liquid crystal cell matrix, and a driving circuit for driving the liquid crystal display panel.

In FIG. 1, a related art liquid crystal display panel is comprised of a color filter substrate 10 and a thin film transistor substrate 20 that are joined together with a liquid crystal 24 therebetween.

The color filter substrate 10 includes a black matrix 4, a color filter 6 and a common electrode 8 that are sequentially provided on an upper glass substrate 2. The black matrix 4 is provided in a matrix type on the upper glass substrate 2. The black matrix 4 divides an area of the upper glass substrate 2 into a plurality of cell areas to be provided with the color filter 6, and prevents a light interference between adjacent cells and an external light reflection. The color filter 6 is provided at the cell area divided by the black matrix 4 in such a manner to be divided into red (R), green (G) and blue (B) areas. Thus, transmitting red, green and blue lights. The common electrode 8 is formed of a transparent conductive layer formed entirely on the color filter 6, and supplies a common voltage Vcom that serves as a reference voltage upon driving of the liquid crystal 24. Further, an over-coat layer (not shown) for smoothing the color filter 6 may be provided between the color filter 6 and the common electrode 8.

The thin film transistor substrate 20 includes a thin film transistor 18 and a pixel electrode 22 provided for each cell area defined by a crossing of a gate line 14 and a data line 16 at a lower glass substrate 12. The thin film transistor 18 applies a data signal from the data line 16 to the pixel electrode 22, in response to a gate signal from the gate line 14. The pixel electrode 22, formed of a transparent conductive layer, supplies the data signal from the thin film transistor 18 to drive the liquid crystal 24.

The liquid crystal 24 having a dielectric anisotropy is rotated in accordance with an electric field formed by the data signal from the pixel electrode 22 and a common voltage Vcom from the common electrode 8 to control light transmittance, thereby implementing a gray scale level.

Further, a liquid crystal display panel includes a spacer (not shown) for uniformly maintaining a cell gap between the color filter substrate 10 and the thin film transistor substrate 20.

In the liquid crystal display panel, the color filter substrate 10 and the thin film transistor substrate 20 are formed by a plurality of mask processes. Herein, one mask process includes many processes such as thin film deposition (coating), cleaning, photolithography, etching, photo-resist stripping and inspection processes.

Particularly, because the thin film transistor substrate includes a semiconductor process and requires a plurality of mask processes, it has a complicated fabricating process which is a major factor in the increased manufacturing costs of the liquid crystal display panel. Therefore, a thin film transistor substrate has been developed to reduce the number of mask process from a five-round mask process that is a standard mask process.

Liquid crystal displays are largely classified into a vertical electric field applying type and a horizontal electric field applying type based upon with a direction of the electric field driving the liquid crystal.

The liquid crystal display of a vertical electric field applying type drives a liquid crystal in a twisted nematic (TN) mode with a vertical electric field formed between a pixel electrode and a common electrode arranged opposite to each other on the upper and lower substrates. The liquid crystal display of a vertical electric field applying type has an advantage of a large aperture ratio, while having a drawback of a narrow viewing angle of about 90°.

The liquid crystal display of a horizontal electric field applying type drives a liquid crystal in an in-plane switching (IPS) mode with a horizontal electric field between the pixel electrode and the common electrode arranged in parallel to each other on the lower substrate. The liquid crystal display of a horizontal electric field applying type has an advantage of a wide viewing angle of about 160°.

The thin film transistor substrate in the liquid crystal display of a horizontal electric field applying type also requires a plurality of mask processes which is a drawback of a complicated fabricating process. Therefore, in order to reduce the manufacturing costs, it is necessary to reduce the number of mask processes.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to a liquid crystal display device that substantially obviates one or more of the problems due to limitations and disadvantages of the related art. An advantage of the present invention is to provide a thin film transistor substrate of a horizontal electric field applying type and a fabricating method thereof that simplify a process.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. These and other advantages of the invention may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the invention, the liquid crystal display device according to one aspect of the present invention comprises first and second substrates; a gate line on the first substrate; a data line crossing the gate line with a gate insulating film therebetween to define a pixel area; a thin film transistor including a gate electrode connected to the gate

3

line, a source electrode connected to the data line, a drain electrode opposite the source electrode and a semiconductor pattern defining a channel between the source electrode and the drain electrode; a common line on the first substrate substantially parallel to the gate line; a common electrode extended from the common line into the pixel area; and a pixel electrode extended from the drain electrode into the pixel area to form a horizontal electric field with the common electrode, wherein the data line, the source electrode, the drain electrode and the pixel electrode are formed of a first conductive layer group having at least double conductive layers, and are formed in an area to be sealed by a sealant upon joining the first and second substrates.

In another embodiment, a method of fabricating a liquid crystal display device comprises a first mask process of forming a first mask pattern group including a gate line, a gate electrode connected to the gate line, a common line substantially parallel to the gate line and a common electrode connected to the common line on a first substrate; a second mask process of forming a gate insulating film on the first mask pattern group and forming a semiconductor pattern on the gate insulating film; and a third mask process of forming a third mask pattern group including a data line crossing the gate line and the common line, a source electrode connected to the data line, a drain electrode opposite the source electrode and a pixel electrode connected to the drain electrode from a first conductive layer group having at least double conductive layers on the gate insulating film, wherein the third mask pattern group is formed in an area to be sealed by a sealant upon joining the first substrate and a second substrate.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principals of the invention.

In the drawings:

FIG. 1 is a schematic perspective view showing a structure of a related art liquid crystal display panel;

FIG. 2 is a plan view showing a structure of a thin film transistor substrate of horizontal electric field applying type according to an embodiment of the present invention;

FIG. 3 is a sectional view of the thin film transistor substrate of a horizontal electric field applying type taken along III-III', IV-IV', V-V' and VI-VI' lines in FIG. 2;

FIG. 4 is a plan view showing a structure of a thin film transistor substrate of a horizontal electric field applying type according to the another embodiment of the present invention;

FIG. 5 is a sectional view showing a data pad area of a liquid crystal display panel employing the thin film transistor substrate of a horizontal electric field applying type shown in FIG. 3;

FIG. 6a and FIG. 6b are a plan view and a sectional view explaining a first mask process in a method of fabricating the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention, respectively;

FIG. 7a and FIG. 7b are a plan view and a sectional view explaining a second mask process in a method of fabricating

4

the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention, respectively;

FIG. 8a to FIG. 8f are sectional views more specifically explaining the second mask process;

FIG. 9a and FIG. 9b are a plan view and a sectional view explaining a third mask process in a method of fabricating the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention, respectively; and

FIG. 10a to FIG. 10e are sectional views more specifically explaining the third mask process.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

FIG. 2 is a plan view showing a structure of a thin film transistor substrate of a horizontal electric field applying type according to an embodiment of the present invention, and FIG. 3 is a section view of the thin film transistor substrate taken along III-III', IV-IV', V-V' and VI-VI' lines in FIG. 2.

Referring to FIG. 2 and FIG. 3, the thin film transistor substrate of a horizontal electric field applying type includes a gate line 102 and a data line 104 provided on a lower substrate 150 in such a manner to cross each other with a gate insulating film 152 therebetween and define a pixel area, a thin film transistor TFT connected to the gate line 102, the data line 104, a pixel electrode 118, the pixel electrode 118 and a common electrode 122 provided to form a horizontal electric field at said pixel area, a common line 120 connected to the common electrode 122, and a storage capacitor Cst provided at an overlapping portion between the common electrode 122 and a drain electrode 112. Further, the thin film transistor substrate includes a gate pad 124 connected to the gate line 102, a data pad 132 connected to the data line 104, and a common pad 140 connected to the common line 120.

The gate line 102 supplies a scanning signal from a gate driver (not shown), while the data line 104 supplies a video signal from a data driver (not shown). The gate line 102 and the data line 104 cross each other with the gate insulating film 152 therebetween to define the pixel area.

The gate line 102 is formed on the substrate 150 in a multiple-layer structure having at least double metal layers. For instance, as shown FIG. 3, the gate line 102 has a double-layer structure including a first conductive layer 101 employing a low-resistance metal such as Al and a second conductive layer 103 employing a metal capable of reducing a contact resistance against the transparent conductive layer such as Mo. The data line 104 is formed on the gate insulating film 152 in a multiple-layer structure in which at least double layers including the transparent conductive layer are built. For example, as shown FIG. 5, the data line 104 has a double-layer structure in which a third conductive layer 111 employing a transparent conductive layer or an opaque metal having a strong corrosion resistance and a high strength such as Ti or W, etc and a fourth conductive layer 113 employing a metal are formed.

The thin film transistor TFT allows a video signal applied to the data line 104 to be charged into the pixel electrode 118 and be maintained in response to a scanning signal applied to the gate line 102. To this end, the thin film transistor includes a gate electrode extended from the gate line 102, a source electrode 110 connected to the data line 104, a drain electrode 112 positioned opposite the source electrode 110 to be con-

5

nected to the pixel electrode **118**, an active layer **114** overlapping the gate line **102** with the gate insulating film **152** therebetween to provide a channel between the source electrode **110** and the drain electrode **112**, and an ohmic contact layer **116** formed on the active layer **114** in an area other than the channel portion to make an ohmic contact with the source electrode **110** and the drain electrode **112**. Herein, the source electrode **110** and the drain electrode **112** have a double-layer structure in which the third and fourth conductive layers **111** and **113** are formed on the gate insulating film **152** provided with the semiconductor pattern **115** along with the data line **104**.

The common line **120** and the common electrode **122** supply a reference voltage for driving the liquid crystal, that is, a common voltage to each pixel.

To this end, the common line **120** includes an internal common line **120A** substantially parallel to the gate line **102** at a display area, and an external common line **120B** commonly connected to the internal common line **120A** at a non-display area. The common electrode **122** is provided within the pixel area to be connected to the internal common line **120A**. More specifically, the common electrode **122** includes a horizontal part **122A** overlapping the drain electrode **112** adjacent the gate line **102**, and a finger part **122B** extended from the horizontal part **122A** into the pixel area to be connected to the internal common line **120A**. The common line **120** and the common electrode **122** have a double-layer structure in which the first conductive layer and second conductive layers **101** and **103** are formed on the substrate **150** along with the gate line **102**.

The storage capacitor **Cst** is provided such that the first horizontal part **122A** of the common electrode **122** overlaps with the drain electrode **112** with the gate insulating film **152** therebetween. Herein, the drain electrode **112** is extended from the overlapping portion between it and the thin film transistor TFT, that is, the gate line **102** in such a manner to overlap with the first horizontal part **122A** of the common electrode **122** as widely as possible. Thus, a capacitance value of the storage capacitor **Cst** is increased by the wide overlapping area between the common electrode **122** and the drain electrode **112**, so that the storage capacitor **Cst** allows a video signal charged in the pixel electrode **118** to be stably maintained until a next signal is charged.

The pixel electrode **118** is extended from the drain electrode **112** in such a manner to have a finger shape substantially parallel to the finger part **122B** of the common electrode **122**. An edge of the pixel electrode **118** is overlapped with the internal common line **120A**. The pixel electrode **118** has a double-layer structure in which the third conductive layer and fourth conductive layers **111** and **113** are formed on the gate insulating film **152** similar to the drain electrode **112**. Accordingly, if a video signal is applied, via the thin film transistor, to the pixel electrode **118**, then a horizontal electric field is formed between the pixel electrode **118** and the finger part **122B** of the common electrode **122** supplied with the common voltage. Liquid crystal molecules arranged in the horizontal direction between the thin film transistor array substrate and the color filter array substrate by such a horizontal electric field are rotated due to a dielectric anisotropy. Transmittance of a light transmitting in the pixel area is differentiated depending upon a rotation extent of the liquid crystal molecules, thereby implementing a gray level scale.

Further, as shown FIG. 4, the finger part **122B** of the common electrode **122** and the finger part **118B** of the pixel electrode **118** may be formed in a zigzag manner. In this case, an edge of the finger part **122B** of the common electrode **122** adjacent to the data line **104** can be formed substantially

6

parallel to the data line **104** or in a zigzag manner. Alternatively, the data line **104** may be formed in a zigzag manner along the finger part **122B** of the adjacent common electrode **122**.

The gate line **102** is connected, via the gate pad **124**, to the gate driver (not shown). The gate pad **124** consists of a lower gate pad electrode **126** extended from the gate line **102**, and an upper gate pad electrode **130** connected, via a first contact hole **128** passing through the gate insulating film **152**, to the lower gate pad electrode **126**.

The data line **104** is connected, via the data pad **132**, to a data driver (not shown). The data pad **132** consists of a lower data pad electrode **134** connected to a data link **135**, an upper data pad electrode **138** connected, via a second contact hole **136** passing through the gate insulating film **152**, to the lower data pad electrode **134**.

The common line **120** receives a reference voltage from a common voltage source (not shown) via the common pad **140**. The common pad **140** consists of a lower common pad electrode **142** extended from the external common line **120B**, and an upper common pad electrode **146** connected, via a third contact hole **144** passing through the gate insulating film **152**, to the lower common pad electrode **142**.

In such a thin film transistor substrate according to the embodiment of the present invention, the data pad **132** has the same structure as the gate pad **124** and the common pad **140**. More specifically, the lower gate pad electrode **126**, the lower common pad electrode **142**, the lower data pad electrode **134** and the data link **135** have a double-layer structure in which the first conductive layer and second conductive layers **101** and **103** are formed on the substrate **150** along with the gate line **102**. Also, the upper gate pad electrode **130**, the upper common pad electrode **146** and the upper data pad electrode **138** are formed on the gate insulating film **152** along with the data line **104**, and are formed of the third conductive layer **111** in which the fourth conductive layer **113** is removed, that is, a transparent conductive layer.

The data link **135** is extended from the lower data pad electrode **134** to thereby have a structure in which the first and second conductive layers **101** and **103** are formed. The second conductive layer **103** of the data link **135** is exposed through the fourth contact hole **148** to be connected to the third conductive layer **111** of the data line **104**. In this case, the third conductive layer **111** of the data line **104** may be integral to the upper data pad electrode **138**. The data line **104** is exposed due to an absence of the protective film. In order to prevent the fourth conductive layer **113** of the data line **104** from being exposed to the exterior thereof and oxidized, as shown FIG. 5, the fourth contact hole **148** is positioned within an area sealed by a sealant **200**. Thus, the fourth conductive layer **113** of the data line **104** positioned at the sealed area is protected by a lower alignment film **214** to be formed thereon.

Referring to FIG. 5, a thin film transistor substrate formed with the lower alignment film **214** and a color filter substrate **210** formed with an upper alignment film **212** are joined to each other by the sealant **200**, and a cell gap between the two substrates sealed by the sealant **200** is formed with a liquid crystal therebetween. In this case, the liquid crystal may be formed by a liquid crystal dropping method in which a liquid crystal layer is formed by dropping the liquid crystal on at least one substrate and then joining the substrates or a vacuum injection method in which two substrates are joined and then the liquid crystal is injected. The upper and lower alignment films **212** and **214** are formed with an organic insulating material at each picture display area of the two substrates. The sealant **200** is formed with being spaced in such a manner to be not in contact with the upper and lower alignment films

212 and **214** for the purpose of reinforcing an adhesive force. Thus, the data line **104**, the source electrode **110**, the drain electrode **112**, and the pixel electrode **118** provided at the thin film transistor substrate are positioned at an area sealed by the sealant **200**, so that it may be sufficiently protected by the lower alignment film **214** formed thereon as well as by the liquid crystal formed in the sealed area.

The thin film transistor substrate of a horizontal electric field applying type according to the first embodiment of the present invention having no protective film as described above is formed by the following three-round mask process.

FIG. **6a** and FIG. **6b** are a plan view and a sectional view explaining a first mask process, respectively, in a method of fabricating the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention.

A first mask pattern group including the gate line **102**, the lower gate pad electrode **126**, the common line **120**, the common electrode **122**, the lower common pad electrode **142**, the data link **135** and the lower data pad electrode are formed on the lower substrate **150** by the first mask process. Herein, the first mask pattern group has a multiple-layer structure in which at least two conductive layers are formed. For convenience, only a double-layer structure having the first and second conductive layers **101** and **103** will be explained.

More specifically, the first and second conductive layers **101** and **103** are disposed on the lower substrate **150** by a deposition technique such as the sputtering. The first conductive layer **101** and second conductive layers **103** may employ an Al-alloy such as Mo, Ti, Cu and AlNd, a Mo-alloy such as Al, Cr and MoW, or a metal material such as a Cu-alloy. For example, the first and second conductive layers **101** and **103** may employ a double-layer structure such as Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Cu/Mo, Mo/Al, Cu-alloy/Mo, Cu-alloy/Al, Cu-alloy/Mo-alloy, Cu-alloy/Al-alloy, Al/Mo-alloy, Mo-alloy/Al, Al-alloy/Mo-alloy, Mo-alloy/Al-alloy, Mo/Al-alloy. Alternatively, there may be a layered structure of at least triple layers such as Mo/Al(Nd)/Mo, Ti/Al(Nd)/Ti, Mo/Ti/Al(Nd). Next, a first photo-resist pattern is formed on the second conductive layer **101** by photolithography using a first mask. Then, portions of the first and second conductive layers **101** and **103** exposed through the first photo-resist pattern are etched by an etching process, thereby providing the first mask pattern group including a double-layer structure of the gate line **102**, the lower gate pad electrode **126**, the common line **120**, the common electrode **122**, the lower common pad electrode **142**, the data link **135** and the lower data pad electrode **134**.

FIG. **7a** and FIG. **7b** are a plan view and a section view explaining a second mask process in a method of fabricating the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention, respectively, and FIG. **8a** to FIG. **8f** are section views more specifically explaining the second mask process.

The gate insulating film **152** including first to fourth contact holes **128**, **136**, **144** and **148** and the semiconductor pattern **115** are formed on the lower substrate **150** provided with the first mask pattern group by the first mask process. The semiconductor pattern **115** and the contact holes **128**, **136**, **144** and **148** of the gate insulating film **152** are defined by a single mask process employing a diffractive exposure mask or a half tone mask. Hereinafter, a case where the half tone mask is used as a second mask will be described.

In FIG. **8a**, the gate insulating film **152**, an amorphous silicon layer **105** and an amorphous silicon layer **107** doped with an n⁺ or p⁺ impurity are sequentially disposed on the lower substrate **150** provided with the first mask pattern group

by a deposition technique such as the PECVD. The gate insulating film **152** is formed of an inorganic insulating material such as silicon oxide (SiO_x) or silicon nitride (SiN_x).

In FIG. **8b**, a second photo-resist pattern **168** having step coverage is formed by photolithography using a half tone mask. The half tone mask is comprised of a shielding part for shielding an ultraviolet ray, a half-tone transmitting part for partially transmitting the ultraviolet ray using a phase-shifting material, and a full transmitting part for fully transmitting the ultraviolet ray. The second photo-resist pattern **168** includes second photo-resist patterns **168A** and **168B** having a different thickness and an aperture part formed by photolithography using a half tone mask. In this case, the relatively thick second photo-resist pattern **168A** and is provided at a shielding area P1 of the second photo-resist overlapping with the shielding part of the half tone mask; the second photo-resist pattern **168B** is thinner than the second photo-resist pattern **168A** and is provided at a half tone exposure area P2 overlapping the half-tone transmitting part; and the aperture part is provided at an full exposure area P3 overlapping the full transmitting part.

In FIG. **8c**, the first to fourth contact holes **128**, **136**, **144** and **148** pass through the gate insulating film **152** from the amorphous silicon layer **105** doped with an n⁺ or p⁺ impurity **107** are formed by the etching process using the second photo-resist pattern **168** as a mask. The first contact hole **128** exposes the lower gate pad electrode **126**; the second contact hole **136** exposes the lower data pad electrode **134**; the third contact hole **144** exposes the lower common pad electrode **142**; and the fourth contact hole **148** exposes the data link **135**.

In FIG. **8d**, a thickness of the second photo-resist pattern **168A** is thinned while the second photo-resist pattern **168B** is removed by an ashing process using an oxygen (O₂) plasma.

In FIG. **8e**, the amorphous silicon doped with an n⁺ or p⁺ impurity **107** and the amorphous silicon layer **105** are patterned by the etching process using the ashed second photo-resist pattern **168A** as a mask to thereby provide the semiconductor pattern **115** including the active layer **114** and the ohmic contact layer **116**.

In FIG. **8f**, the second photo-resist pattern **168A** left on the semiconductor pattern **115** in FIG. **8e** is removed by a stripping process.

FIG. **9a** and FIG. **9b** are a plan view and a section view explaining a third mask process in a method of fabricating the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention, respectively, and FIG. **10a** to FIG. **10e** are section views more specifically explaining the third mask process.

A third mask pattern group including the data line **104**, the source electrode **110**, the drain electrode **112**, the pixel electrode **118**, the upper gate pad electrode **130**, the upper data pad electrode **138** and the upper common pad electrode **146** is formed on the gate insulating film **152** provided with the semiconductor pattern **115** by the third mask process. Herein, the third mask pattern group A including the data line **104**, the source electrode **110**, the drain electrode **112** and the pixel electrode **118** has a multiple-layer structure in which at least two conductive layers are formed. For convenience, only a double-layer structure having the third and fourth conductive layers **111** and **113** formed will be explained. The third mask pattern group B including the upper gate pad electrode **130**, the upper data pad electrode **138** and the upper common pad electrode **146** has a single-layer structure formed from the third conductive layer **111** of the third mask pattern group A. The third mask pattern group including the third mask pattern group A having such a double-layer structure and the third mask pattern group B having such a single-layer structure is

formed by the third mask process using a diffractive exposure mask or a half tone mask. Hereinafter, a case where the half tone mask is used as a third mask will be described.

In FIG. 10a, the third and fourth conductive layers **111** and **113** are sequentially formed on the gate insulating film **152** provided with the semiconductor pattern **115** by a deposition technique such as the sputtering. The third conductive layer **111** may be formed of a transparent conductive material such as ITO, TO, IZO or ITZO, or an opaque metal having a strong corrosion resistance and a high strength such as Ti or W. The fourth conductive layer **113** employs a single layer formed of a metal material such as Mo, Ti, Cu, AlNd, Al, Cr, a Mo-alloy, a Cu-alloy or an Al-alloy, or may have a layered structure of at least double layers such as Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Mo/Al(Nd)/Mo, Cu/Mo, Ti/Al(Nd)/Ti, Mo/Al, Mo/Ti/Al(Nd), Cu-alloy/Mo, Cu-alloy/Al, Cu-alloy/Mo-alloy, Cu-alloy/Al-alloy, Al/Mo-alloy, Mo-alloy/Al, Al-alloy/Mo-alloy, Mo-alloy/Al-alloy, Mo/Al-alloy.

In FIG. 10b, a third photo-resist pattern **182** having step coverage is formed by the photolithography using a half tone mask. The half tone mask is comprised of a shielding part for shielding an ultraviolet ray, a half-tone transmitting part for partially transmitting the ultraviolet ray using a phase-shifting material, and a full transmitting part for fully transmitting the ultraviolet ray. The third photo-resist pattern **182** includes third photo-resist patterns **182A** and **182B** having a different thickness and an aperture part formed by photolithography using a half tone mask. In this case, the relatively thick third photo-resist pattern **182A** is provided at a shielding area P1 of the third photo-resist overlapping with the shielding part of the half tone mask; the third photo-resist pattern **182B** is thinner than the third photo-resist pattern **182A** and is provided at a half tone exposure area P2 overlapping the half-tone transmitting part; and the aperture part is provided at an full exposure area P3 overlapping with the full transmitting part.

The fourth and third conductive layer **113** and **111** are etched by a different etchant, the third conductive layer **111** positioned at a portion lower than the upper fourth conductive layer **113** is over-etched to cause an under-cut area. Further, the ohmic contact layer **116** between the source electrode **110** and the drain electrode **112** is removed by an etching process using the source electrode **110** and the drain electrode **112** as a mask, for example, a dry-etching process, to thereby expose the active layer **114**. In this case, an edge of the separated ohmic contact layer **116** has a more protruded shape than the third conductive layer **111** edges of the source electrode **110** and the drain electrode **112**.

In FIG. 10d, a thickness of the third photo-resist pattern **182A** is thinned and the third photo-resist pattern **182B** is removed by an ashing process. Such a removal of the third photo-resist pattern **182B** exposes the fourth conductive layer **113** of the upper gate pad electrode **130**, the upper data pad electrode **138** and the upper common pad electrode **146**. Further, the edge of the ashed third photo-resist pattern **182A** is positioned at an inner side of the edge of the patterned fourth conductive layer **113**.

In FIG. 10e, the fourth conductive layer **113** of the upper gate pad electrode **130**, the upper data pad electrode **138** and the upper common pad electrode **146** are etched by the etching process using the ashed third photo-resist pattern **182A** as a mask to thereby provide the upper gate pad electrode **130**, the upper data pad electrode **138** and the upper common pad electrode **146** that have a single-layer structure of the third conductive layer **111**. In this case, each side of the fourth conductive layer **113** exposed through the edge of the third photo-resist pattern **182A** is again etched. Thus, the third and

fourth conductive layers **111** and **113** of the data line **104**, the source electrode **110**, the drain electrode **112** and the pixel electrode **118** have a constant step coverage having a stepwise shape. Further, the edge of the ohmic contact layer **116** at the channel portion of the thin film transistor TFT may be more protruded than those of the source electrode **110** and the drain electrode **112** to thereby provide the ohmic contact layer **118** and the third and fourth conductive layers **111** and **113** with step coverage taking a stepwise shape. And the third photo-resist pattern **182A** is removed by a stripping process.

The etching process of the third and fourth conductive layers **111** and **113** in the third mask process may be performed by wet-etching or dry-etching. But, the wet-etching is preferable.

As a result, the thin film transistor substrate of a horizontal electric field applying type according to the embodiment of the present invention has an exposed structure of the data line **104**, the source electrode **110**, and the pixel electrode **118** due to an absence of the protective film. However, all of these are positioned at an area sealed by the sealant, so that they may be sufficiently protected by the lower alignment film formed thereon as well as by the liquid crystal formed in the sealed area.

As described above, in the thin film transistor substrate of a horizontal electric field applying type according to the present invention, the semiconductor pattern and the contact holes are formed by utilizing the first half tone (or diffractive exposure) mask.

Moreover, in the thin film transistor substrate of a horizontal electric field applying type according to the present invention, a single-layer structure of upper pad electrodes are formed, along with a multiple-layer structure of other third mask pattern group, without any protective film with the aid of the second half tone (or diffractive exposure) mask.

Accordingly, in the thin film transistor substrate of a horizontal electric field applying type according to the present invention, the entire process can be simplified by the three-round mask process, so that it becomes possible to reduce the material costs and the equipment investment costs as well as to improve productivity.

Furthermore, the liquid crystal panel to which the thin film transistor substrate of a horizontal electric field applying type according to the present invention is applied, allows the data line, the source electrode, the drain electrode and the pixel electrode to be exposed due to an absence of the protective film to sufficiently protect the lower alignment film formed thereon or by the liquid crystal formed in the area sealed by the sealant. Also, the pads of the thin film transistor substrate have the same structure, and the data link connected to the data pad is connected, via the contact hole, to the data line within the area sealed by the sealant. Thus, it becomes possible to prevent an illumination problem, etc. caused by the absence of the protective film.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A liquid crystal display device, comprising:
 - first and second substrates;
 - a gate line on the first substrate;
 - a data line crossing the gate line with a gate insulating film therebetween to define a pixel area;

11

a thin film transistor including a gate electrode connected to the gate line, a source electrode connected to the data line, a drain electrode opposite the source electrode and a semiconductor pattern defining a channel between the source electrode and the drain electrode;

a common line on the first substrate substantially parallel to the gate line;

a common electrode extended from the common line into the pixel area; and

a pixel electrode extended from the drain electrode into the pixel area to form a horizontal electric field with the common electrode,

wherein the data line, the source electrode, the drain electrode and the pixel electrode are formed of a first conductive layer group having at least double conductive layers, and are formed in an area to be sealed by a sealant upon joining the first and second substrates.

2. The device as claimed in claim 1, further comprising: a storage capacitor provided such that the drain electrode overlaps a portion of the common electrode with the gate insulating film therebetween.

3. The device as claimed in claim 1, further comprising: a data link on the first substrate to be connected to the data line via a contact hole passing through the gate insulating film.

4. The device as claimed in claim 3, wherein the contact hole is formed in an area to be sealed by the sealant.

5. The device as claimed in claim 3, further comprising: an alignment film on the data line, the source electrode, the drain electrode and the pixel electrode.

6. The device as claimed in claim 5, wherein the contact hole is formed under the alignment film.

7. The device as claimed in claim 3, further comprising: a gate pad connected to the gate line; a data pad connected to the data link; and a common pad connected to the common line, wherein each of the gate pad, the data pad and the common pad includes:

12

a lower pad electrode on the first substrate;

a contact hole passing through the gate insulating film to expose the lower pad electrode; and

an upper pad electrode connected to the lower pad electrode via the contact hole and formed of at least one conductive layer of the first conductive layer group.

8. The device as claimed in claim 7, wherein the upper pad electrode of the data pad is integral to the at least one conductive layer of the data line.

9. The device as claimed in claim 1, wherein at least one conductive layer of the conductive layer group includes one of a transparent conductive layer, Ti and W.

10. The device as claimed in claim 1, wherein the semiconductor pattern is formed only at a position to be provided with the thin film transistor.

11. The device as claimed in claim 1, wherein the gate line, the gate electrode, the common line and the common electrode are formed of a second conductive layer group having at least double conductive layers.

12. The device as claimed in claim 11, wherein, a lowermost layer of the first conductive layer group includes a transparent conductive layer, and an uppermost layer of the second conductive layer group includes a metal having one of Mo and Mo-Alloy.

13. The device as claimed in claim 11, wherein the second conductive group has step coverage having a stepwise shape.

14. The device as claimed in claim 1, wherein the semiconductor pattern includes an active layer, and an ohmic contact layer connected between the source electrode and the active layer and between the drain electrode and the active layer, and

wherein the ohmic contact layer has portions on opposite sides of the channel, and an edge of the ohmic contact layer and edges of source electrode and the drain electrode have step coverage having a stepwise shape.

* * * * *

专利名称(译)	具有用于数据线，源电极，漏电极和像素电极的特定结构的液晶显示装置		
公开(公告)号	US7894032	公开(公告)日	2011-02-22
申请号	US12/654263	申请日	2009-12-15
[标]申请(专利权)人(译)	AHN BYUNG CHUL		
申请(专利权)人(译)	AHN BYUNG CHUL		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	AHN BYUNG CHUL		
发明人	AHN, BYUNG CHUL		
IPC分类号	G02F1/1343 G02F1/1339		
CPC分类号	G02F1/134363 G02F1/1362 G02F2001/13629		
优先权	1020040112577 2004-12-24 KR		
其他公开文献	US20100157233A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种液晶显示装置和具有简化工艺的制造方法。除了其他特征之外，液晶显示装置包括第一和第二基板，与数据线交叉的栅极线，其间具有栅极绝缘膜以限定像素区域。在基板上提供基本平行于栅极线的公共线，并且公共电极从公共线延伸到像素区域中。像素电极从漏电极延伸到像素区域中以与公共电极形成水平电场。数据线，源电极，漏电极和像素电极由具有至少双导电层的第一导电层组形成，并且在连接第一和第二基板时形成在要用密封剂密封的区域中。

