



US 20010013915A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2001/0013915 A1**
Song (43) **Pub. Date: Aug. 16, 2001**

(54) **IN-PLANE SWITCHING LCD PANEL**

(52) **U.S. Cl.** **349/141; 349/139; 349/123**

(76) **Inventor: In-Duk Song, Kumi-shi (KR)**

(57) **ABSTRACT**

Correspondence Address:
Song K. Jung, Esq.
LONG ALDRIDGE & NORMAN LLP
701 Pennsylvania Avenue, N.W.
Washington, DC 20004 (US)

An IPS-LCD panel includes first and second substrates, and a liquid crystal interposed therebetween. The first substrate includes common and pixel electrodes that are formed of a transparent conductive material. Because the common and pixel electrodes are transparent, aperture ratios of the inventive IPS-LCD panel are increased.

(21) **Appl. No.: 09/737,770**

(22) **Filed: Dec. 18, 2000**


(30) **Foreign Application Priority Data**

Dec. 16, 1999 (KR) 1999-58108

Publication Classification


(51) **Int. Cl.⁷ G02F 1/1337; G02F 1/1343**

Another IPS-LCD panel includes opaque pixel electrodes and transparent common electrodes. In forming the opaque pixel electrodes, a black matrix of the same material as the pixel electrodes is also formed on the first substrate. Because the inventive black matrix is much smaller than a conventional one, the aperture ratios of the second inventive IPS-LCD panel become higher.




(related art)

FIG. 1




(related art)


FIG. 2




(related art)
FIG. 3




(related art)
FIG. 4



(related art)
FIG. 5




(related art)
FIG. 6




(related art)

FIG. 7A



(related art)

FIG. 7B



(related art)
FIG. 8




FIG. 9




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16

IN-PLANE SWITCHING LCD PANEL

[0001] This application claims the benefit of Korean Patent Application No. 1999-58108, filed on Dec. 16, 1999, which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a liquid crystal display device, and more particularly to a liquid crystal display device implementing in-plane switching (IPS) where an electric field to be applied to liquid crystal is generated in a plane parallel to a substrate.

[0004] 2. Discussion of the Related Art

[0005] Recently, liquid crystal display (LCD) devices with light, thin, and low power consumption characteristics are used in office automation equipment and video units and the like. Driving methods for such LCDs typically include a twisted nematic (TN) mode and a super twisted nematic (STN) mode. Although TN-LCDs and STN-LCDs have been put to practical use, they have a drawback in that they have a very narrow viewing angle. In order to solve the problem of narrow viewing angle, IPS-LCD devices have been proposed. IPS-LCD devices typically include a lower substrate where a pixel electrode and a common electrode are disposed, an upper substrate having no electrode, and a liquid crystal interposed between the upper and lower substrates.

[0006] FIG. 1 is a cross-sectional view illustrating a conventional TN-LCD panel. As shown in FIG. 1, the liquid crystal display panel has lower and upper substrates 1a and 1b with a liquid crystal layer ("LC") interposed between the lower and upper substrates 1a and 1b. The lower substrate 1a has a thin film transistor ("TFT") as a switching element for changing orientation of the LC molecules. The TFT includes a pixel electrode 15 to apply a voltage to the LC layer according to signals from the TFT. The upper substrate 1b has a color filter 25 for implementing colors. There is a common electrode 14 on the color filter 25. The common electrode 14 serves as an electrode for applying a voltage to the LC layer. The pixel electrode 15 is arranged over a pixel portion "P", i.e., a display area. Further, to prevent leakage of the liquid crystal injected into the space between the two substrates 1a and 1b, the two substrates 1a and 1b are sealed by a sealant 6.

[0007] As described above, because the pixel and common electrodes 15 and 14 of the conventional TN-LCD panel are positioned on the lower and upper substrates 1a and 1b, respectively, the electric field induced therebetween is perpendicular to the lower and upper substrates 1a and 1b. Therefore, unlike the TN or STN-LCD panel, the IPS-LCD panel implements an electric field parallel to the substrates. A detailed explanation about operation modes of a typical IPS-LCD panel will be provided referring to FIGS. 2 to 6.

[0008] As shown in FIG. 2, lower and upper substrates 1a and 1b are spaced apart from each other, and a liquid crystal is interposed therebetween. The lower and upper substrates are called array and color filter substrates, respectively. Pixel and common electrodes 15 and 14 are disposed on the lower substrate 1a. The pixel and common electrodes 15 and 14 are parallel with and spaced apart from each other. A color filter

25 is disposed on a surface of the upper substrate 1b and opposes the lower substrate 1a. The pixel and common electrodes 15 and 14 apply an electric field "E" to the liquid crystal. The liquid crystal has a negative dielectric anisotropy, and thus it is aligned parallel with the electric field "E".

[0009] FIGS. 3 to 6 conceptually illustrate operation modes of a conventional IPS-LCD device. When there is no electric field between the pixel and the common electrodes 15 and 14, the long axes of the liquid crystal molecules maintain an angle from a line perpendicular to the parallel pixel and common electrodes 15 and 14. Herein, the angle is 45 degrees, for example.

[0010] On the contrary, when there is an electric field between the pixel and common electrodes 15 and 14, there is an in-plane electric field "E" parallel to the surface of the lower substrate 1a between the pixel and common electrodes 15 and 14. The in-plane electric field "E" is parallel to the surface of the lower substrate 1a because the pixel and common electrodes are formed on the lower substrate 1a. Accordingly, the liquid crystal molecules are twisted so as to align the long axes thereof with the direction of the electric field, thereby the liquid crystal molecules are aligned such that the long axes thereof are parallel with the line perpendicular to the pixel and common electrodes 15 and 14.

[0011] By the above-mentioned operation modes and with additional parts such as polarizers and alignment layers, the IPS-LCD device displays images. The IPS-LCD device has wide viewing angle and low color dispersion. The fabricating processes of this IPS-LCD device are simpler than other various LCD devices. But, because the pixel and common electrodes are disposed on the same plane of the lower substrate, the transmittance and aperture ratio are low.

[0012] For the sake of discussing the above-mentioned problem of the IPS-LCD device in detail, with reference to FIGS. 7A and 7B, the basic structure of the IPS-LCD device will be described in detail.

[0013] FIG. 7A is a plan view illustrating in detail the structure of one pixel region in the IPS-LCD device, specifically, a unit pixel region 10. In addition, a cross-sectional view taken along a line "B-B" in FIG. 7A is illustrated in FIG. 7B.

[0014] On the surface of the transparent substrate 1A adjacent to the liquid crystal layer, a scan signal line 2 made of, for example, aluminum (Al) is formed extending along the x-direction, as shown in FIG. 7A. In addition, a reference signal line 4, also known as a common line, is formed extending along the x-direction, close to the scan signal line 2 on the +y-direction side thereof. The reference signal line 4 is also made of, for example, Al. A region surrounded by the scan signal line 2, the reference signal line 4, and the video signal lines 3 constitutes a pixel region 10, as previously described.

[0015] In addition, the pixel region 10 includes a reference electrode 14 formed by the reference signal line 4, and another reference electrode 14 formed adjacent to the scan signal line 2. The pair of horizontally extending reference electrodes 14 are positioned adjacent to one of a pair of video signal lines 3 (on the right side of the figure), and are electrically connected to each other through a conductive layer 14A which is formed simultaneously with the reference electrodes 14.

[0016] In the structure described above, the reference electrodes 14 form a pair extending in the direction parallel to the scan signal line 2. Stated another way, the reference electrodes form a strip extending in a direction perpendicular to the video signal lines 3, later described.

[0017] A first insulating film 11 (see FIG. 7B) made of, for example, silicon nitride is formed on the surface of the lower substrate 1A on which the scan signal lines 2 are formed, overlying the scan signal line 2, the reference signal lines 4, and the reference electrodes 14. The first insulating film 11 functions as (i) an inter-layer insulating film for insulating the scan signal line 2 and the reference signal line 4 from the video signal lines 3, (ii) as a gate-insulating layer for a region in which a thin film transistor (TFT) is formed, and (iii) as a dielectric film for a region in which a capacitor Cstg is formed. The TFT includes a drain electrode 3A and a source electrode 15A. A semiconductor layer 12 for the TFT is formed near a cross point of the gate and data lines 2 and 3. A first polarization layer 18 is formed on the other surface of the lower substrate 1A.

[0018] On the first insulating film 11, a display electrode 15 is formed parallel with the reference electrode 14. One end portion of the display electrode 15 is electrically connected with the conductive layer 14A, and the other end portion thereof is electrically connected with the source electrode 15A. Still on the first insulating film 11, a first planar film 16 is formed to cover the display electrode 15. A first alignment film 17 is formed on the first planar film 16.

[0019] FIG. 7B illustrates a cross-sectional view of the upper substrate 1B on which a black matrix 300 is formed. A color filter 25 is formed to close an opening in the black matrix 300. Then, a second planar film 27 is formed to cover the color filter 25 and the black matrix 300. A second alignment layer 28 is formed on the surface of the second planar film 27 facing the liquid crystal layer.

[0020] The color filter 25 is formed to define three sub-pixel regions adjacent to and extending along the video signal line 3 and to position a red (R) filter, a green (G) filter, and a blue (B) filter, for example, from the top of the three sub-pixel regions. The three sub-pixel regions constitute one pixel region for color display.

[0021] A second polarization layer 29 is also arranged on the surface of the upper substrate 1B that is opposite to the surface of the upper substrate 1B adjacent to the liquid crystal layer, on which various films are formed as described above.

[0022] It will be understood that in FIG. 7B, a voltage applied between the reference electrodes 14 and the display electrode 15 causes an electric field E to be generated in the liquid crystal layer LC in parallel with the respective surfaces of the lower and upper substrates 1A, 1B. This is why the illustrated structure is referred to as the in plane switching, as mentioned above.

[0023] To improve the aperture ratio, the distance between the reference and display electrodes 14 and 15 should be enlarged. In that case, a driving voltage to induce the electric field between the reference and display electrodes 14 and 15 must be increased to maintain a normal display.

[0024] Further, since the low aperture ratio results in a low brightness quality of the liquid crystal display device, the

incident light from the back-light device must be brighter to compensate, which increases power consumption of the liquid crystal display device.

[0025] FIG. 8 shows an array substrate of another conventional IPS-LCD device.

[0026] As shown in FIG. 8, gate and common lines 50 and 54 are arranged transversely and parallel with each other. A data line 60 is arranged perpendicular to the gate and common lines 50 and 54. Gate electrode 52 and source electrode 62 are positioned near a cross point of the gate and data lines 50 and 60, and communicate with the gate line 50 and the data line 60, respectively. Herein, the source electrode 62 overlaps a portion of the gate electrode 52.

[0027] A plurality of common electrodes 54a are positioned spaced apart and perpendicular to the common line 54. The common electrodes 54a communicate with the common line 54. A first connecting line 66 communicates with the drain electrode 64, and a plurality of pixel electrodes 66a are positioned perpendicular to the first connecting line 66. First ends of the pixel electrodes 66a communicate with the first connecting line 66, and the second ends of pixel electrodes 66a communicate with a second connecting line 68 that is positioned over the common line 54. Accordingly, the common electrodes 54a and the pixel electrodes 66a are parallel with and spaced apart from each other in an alternating pattern.

[0028] Similarly to the array substrate of FIG. 7A, since the pixel and common electrodes 66a and 54a are formed on the same substrate, the aperture ratio is reduced. That is to say, the opaque pixel and common electrodes prevent incident light produced by a back light (not shown) from passing through pixel areas covered by the pixel and common electrodes. If distances between the common and pixel electrodes are enlarged to improve the aperture ratios, much stronger driving voltage must be generated between the electrodes to compensate for the loss of the electric fields due to the greater distance therebetween.

[0029] In addition, the intensity of the back light must be increased to compensate for the loss of the back light due to the decrease in the aperture ratios. Therefore, power consumption will be increased.

SUMMARY OF THE INVENTION

[0030] Accordingly, the present invention is directed to an IPS-LCD device that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

[0031] An object of the present invention is to provide an IPS-LCD device having a high aperture ratio.

[0032] In order to achieve the above object, the first preferred embodiment of the present invention provides an in-plane switching liquid crystal display device including a gate line on a first substrate; a data line on the first substrate, the data line being perpendicular to the gate line; a common line on the first substrate, the common line being parallel with the gate line and being formed of a metal; a pixel electrode and a common electrode on the first substrate, the pixel and common electrodes being formed of a transparent conductive material; and a liquid crystal layer between the first and second substrates.

[0033] The transparent conductive material includes indium tin oxide (ITO) or indium zinc oxide (IZO).

[0034] The device further includes an auxiliary common line on the first substrate, the auxiliary common line being connected with the common electrode. The auxiliary common line includes indium tin oxide (ITO) or indium zinc oxide (IZO).

[0035] The gate and common lines include a material selected from a group consisting of chromium (Cr), aluminum (Al), aluminum alloy (Al alloy), molybdenum (Mo), tantalum (Ta), tungsten (W), antimony (Sb), and an alloy thereof.

[0036] The device further includes a first alignment layer on the first substrate.

[0037] The first alignment layer is selected from a group consisting of polyimide and photo-alignment material.

[0038] The device further includes a thin film transistor at an intersection of the gate and data lines.

[0039] At least one of the pixel and common electrodes is on the same layer with the gate electrode.

[0040] The device further includes a gate-insulating layer over the pixel electrode.

[0041] The device further includes a passivation layer over the gate-insulating layer.

[0042] The common electrode is on the passivation layer.

[0043] The device further includes a black matrix on the passivation layer.

[0044] The black matrix includes the same material as the pixel electrodes.

[0045] It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWING

[0046] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

[0047] In the drawings:

[0048] FIG. 1 is a cross-sectional view illustrating a liquid crystal display device according to the related art;

[0049] FIGS. 2 to 6 are perspective views illustrating operation modes of the conventional IPS-LCD device;

[0050] FIG. 7A is a plane view illustrating an array substrate of the conventional IPS-LCD device;

[0051] FIG. 7B is a cross-sectional view taken along a line "B-B" in FIG. 7A;

[0052] FIG. 8 is a plane view of an array substrate of another conventional IPS-LCD device;

[0053] FIG. 9 is a plane view illustrating an array substrate of an IPS-LCD device according a first preferred embodiment of the present invention;

[0054] FIGS. 10A and 10B are different cross-sectional views for different embodiments of the present invention taken along a line "X-X" of FIG. 9;

[0055] FIGS. 11A and 11B are different cross-sectional views for different embodiments of the present invention taken along a line "XI-XI" of FIG. 9;

[0056] FIG. 12 is a cross-sectional view taken along a line "XII-XII" of FIG. 9,

[0057] FIG. 13 is a plane view of an auxiliary common line;

[0058] FIG. 14 is a plane view of an auxiliary gate line;

[0059] FIG. 15 is a plane view illustrating an array substrate of an IPS-LCD device according to a second preferred embodiment of the present invention; and

[0060] FIG. 16 is a cross-sectional view taken along a line "XVI-XVI" of FIG. 15.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0061] Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

[0062] First Preferred Embodiment

[0063] FIG. 9 is a plane view of an array substrate according to a first preferred embodiment of the present invention.

[0064] As shown in FIG. 9 and FIG. 10A, a gate line 100 is transversely disposed on a substrate 1. A common line 120 is spaced apart from the gate line 100 and disposed parallel with the gate line 100. A data line 200 that is spaced apart from each other is disposed across and perpendicular to the gate and the common lines 100 and 120.

[0065] Near an intersection of the gate and data lines 100 and 200, gate and source electrodes 110 and 210 are positioned and electrically connected with the gate and data lines 100 and 200, respectively. A drain electrode 220, including a drain contact hole 240, is spaced apart from the source electrode 210 and overlaps a portion of the gate electrode 110. The source electrode 210 also overlaps a portion of the gate electrode 110.

[0066] A first connecting line 320 electrically contacts the drain electrode 220 through the drain contact hole 240, and is disposed parallel with the gate line 100. A plurality of pixel electrodes 310 are disposed perpendicular to the first connecting line 320, and communicate with the first connecting line 320. Ends of the pixel electrodes 310 are connected with a second connecting line 330 over the common electrode 130.

[0067] A storage electrode 230 including a storage contact hole 250 is disposed over the common line 120, and electrically contacts the second connecting line 330 through the storage contact hole 250. Namely, each of the pixel electrodes 310 is electrically connected with the storage electrode 230.

[0068] A plurality of common electrodes **130** are disposed parallel with the pixel electrodes **310**, and electrically contact the common line **120**. Each common electrode **130** is spaced apart from the adjacent pixel electrodes **310**. One end of each of the common electrodes is electrically connected to one another.

[0069] The common line **120** and the gate and data lines **100** and **200** are an opaque metal, while the common and pixel electrodes **130** and **310** are a transparent conductive material. Preferably, the opaque metal is selected from a group consisting of chromium (Cr), aluminum (Al), aluminum alloy (Al alloy), molybdenum (Mo), tantalum (Ta), tungsten (W), and antimony (Sb), and an alloy thereof, while the transparent conductive material is indium tin oxide (ITO) or indium zinc oxide (IZO).

[0070] Now, referring to FIG. 10A, a fabricating process for the array substrate **1** shown in FIG. 9 is provided.

[0071] At first, the gate and common electrodes **110** and **130** are formed on the substrate **1**. The gate line **100** of FIG. 9 is formed with the gate electrode **110** in the same layer. Because the gate and common electrodes **110** and **130** are different materials, they are formed in different steps. After that, a gate-insulating layer **132** is formed on the substrate **1** to cover the gate and common electrodes **110** and **130**. Subsequently, an active layer **134** is formed on the gate-insulating layer **132**, particularly over the gate electrode **110**. The gate-insulating layer **132** is silicon nitride (SiN_x) or silicon oxide (SiO₂), while the active layer **134** includes an amorphous silicon layer (a-Si) and a doped amorphous silicon layer (n⁺a-Si, not shown).

[0072] The source and drain electrodes **210** and **220** are formed on the active layer **134**, and are made of the same material as the gate electrode **110**. Further, the source and drain electrodes **210** and **220** and the gate electrode **110** may be formed of different materials. At this point, the data lines **200** of FIG. 9 are formed together with the source electrode **210** such that the data lines **200** and the source electrode **210** are connected. Thereafter, a passivation layer **136** is deposited over the substrate **1** and patterned to form the drain contact hole **240** that exposes a portion of the drain electrode **220**.

[0073] Next, the pixel electrodes **310**, which contact the drain electrode **220** through the drain contact hole **240**, are formed on the passivation layer **136**. Subsequently, though not shown in FIG. 10A, an orientation film of polyimide or photoalignment material is formed on the pixel electrodes **310** and rubbed by a fabric or irradiated by light.

[0074] FIG. 10B shows a different fabricating process for the array substrate **1** of FIG. 9. As shown, the pixel electrodes **310** are formed on the gate-insulating layer **132** before the passivation layer **136** is formed. Thereafter, the passivation layer **136** is formed to cover the pixel electrodes **310**.

[0075] As described above, the IPS-LCD device according to the first preferred embodiment of the present invention employs a transparent conductive material for the common and pixel electrodes **130** and **310** such that light incident from a back-light (not shown) passes through the common and pixel electrodes **130** and **310** with a little or no reflection or absorption. Therefore, the aperture ratio problem of the conventional IPS-LCD device is reduced or eliminated. For

example, compared with the conventional IPS-LCD, the aperture ratio of the IPS-LCD device according to the first preferred embodiment increases by at least 10%.

[0076] Now, structures of other portions of the array substrate shown in FIG. 9 are described in detail with reference to FIGS. 11A, 11B, and 12.

[0077] FIGS. 11A and 11B show different structures of the common line **120** and the common electrode **130**.

[0078] In FIG. 11A, metal for the common line **120** is first formed on the substrate **1**, and then the transparent conductive material is formed on the substrate **1** to overlap a portion of the metal for the common line **120**. Namely, after the common line **120** is first formed on the substrate **1**, the common electrode **130** is later formed on the substrate **1** such that an end of the common electrode **130** overlaps a portion of the common line **120**.

[0079] On the contrary, as shown in FIG. 11B, if the common electrode **130** is first formed on the substrate **1**, the later formed common line **120** overlaps a portion of the common electrode **130**. Namely, the transparent conductive material for the common electrode **130** is first formed on the substrate **1**, and then the gate line **100** (see FIG. 9) and common lines **100** and **120** are formed on the substrate **1** to overlap a portion of the common electrode **130**.

[0080] FIG. 12 shows a storage capacitor including the storage electrode **230** of FIG. 9. As shown, the common line **120** is formed together with the gate line **100** of FIG. 9 on the substrate **1**. The gate-insulating layer **132** is then formed to cover the common line **120**. The common line **120** is made of the same material as the gate line **100** of FIG. 9. On the gate-insulating layer **132**, the storage electrode **230** is formed together with the source and drain electrodes **210** and **220** of FIG. 9, and thus all of them contain the same material.

[0081] The passivation layer **136** is formed on the storage electrode **230**. The storage contact hole **250** is formed in the passivation layer **136** such that a portion of the storage electrode **230** is exposed through a storage contact hole **250**. Thereafter, the pixel electrode **310** is formed on the passivation layer **136** and electrically connected with the storage electrode **230** through the storage contact hole **250**.

[0082] When the common line **120** and the common electrodes **130** have the structure shown in FIG. 11A, the common electrodes **130** preferably have the structure of FIG. 13. As shown in FIG. 13, an auxiliary common electrode **125** is formed of the same transparent conductive material as the common electrode **130** to cover the common line **120** and a common pad **126**. The common pad **126** is located at one end of the common line **120**. The plurality of common electrodes **130** communicate with the auxiliary common electrode **125**.

[0083] Further, as shown in FIG. 14, an auxiliary gate line **105** of the same transparent conductive material as the common electrodes **130** is preferably employed to cover the gate line **100** and a gate pad **106**, which is positioned at one end of the gate line **100**. The auxiliary common and gate lines, respectively, protect the common and gate lines from an etching solution in later processes.

[0084] In the first preferred embodiment, since the pixel and common electrodes **310** and **130** in the pixel region are

formed of the transparent conductive material and the gate, data, and common lines are formed of the metal, the aperture ratio is increased such that the brightness is improved.

[0085] Second Preferred Embodiment

[0086] The second preferred embodiment employs an opaque metal, instead of the ITO, for a pixel electrode. Further, in the second preferred embodiment, a black matrix is formed together with the pixel electrode.

[0087] As shown in **FIGS. 15 and 16**, the pixel electrodes **312** of the opaque metal are formed instead of the transparent pixel electrodes **310** of **FIG. 9**. The black matrix **150** of opaque material is formed on the passivation layer **136** to cover the active layer **134**. To form the pixel electrode **312** and the black matrix **150**, the opaque metal layer is deposited on the passivation layer **136** and patterned in the same process. The opaque metal layer is preferably chromium (Cr), which has a low light-reflectivity.

[0088] An IPS-LCD device according to the second preferred embodiment of the present invention preferably employs a normally black (NB) mode LC that displays dark when no electric field is applied to the LC.

[0089] Compared with the aperture ratio of a conventional IPS-LCD device employing a black matrix that is wider than the gate or data line, the aperture ratio of an IPS-LCD device employing the array substrate according to the second preferred embodiment of the present invention increases by more than 10%.

[0090] As described above, the preferred embodiment of the present invention has advantages of higher aperture ratio than the conventional one.

[0091] It will be apparent to those skilled in the art that various modifications and variation can be made in the method of manufacturing a thin film transistor of the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An in-plane switching liquid crystal display device comprising:

- a gate line on a first substrate;
- a data line on the first substrate, the data line being perpendicular to the gate line;
- a common line on the first substrate, the common line being parallel with the gate line and being formed of a metal;
- a pixel electrode and a common electrode on the first substrate, the pixel and common electrodes being formed of a transparent conductive material; and
- a liquid crystal layer between the first and second substrates.

2. The device of claim 1, wherein the transparent conductive material includes indium tin oxide (ITO).

3. The device of claim 1, wherein the transparent conductive material includes indium zinc oxide (IZO).

4. The device of claim 1, further comprising an auxiliary common line on the first substrate, the auxiliary common line being connected with the common electrode.

5. The device of claim 4, wherein the auxiliary common line includes indium tin oxide (ITO).

6. The device of claim 4, wherein the auxiliary common line includes indium zinc oxide (IZO).

7. The device of claim 1, wherein the gate and common lines include a material selected from a group consisting of chromium (Cr), aluminum (Al), aluminum alloy (Al alloy), molybdenum (Mo), tantalum (Ta), tungsten (W), antimony (Sb), and an alloy thereof.

8. The device of claim 1, further comprising a first alignment layer on the first substrate.

9. The device of claim 1, wherein the first alignment layer is selected from a group consisting of polyimide and photo-alignment material.

10. The device of claim 1, further comprising a thin film transistor at an intersection of the gate and data lines.

11. The device of claim 5, wherein at least one of the pixel and common electrodes is on the same layer with the gate electrode.

12. The device of claim 1, further comprising a gate-insulating layer over the pixel electrode.

13. The device of claim 12, further comprising a passivation layer over the gate-insulating layer.

14. The device of claim 13, wherein the common electrode is on the passivation layer.

15. The device of claim 13, further comprising a black matrix on the passivation layer.

16. The device of claim 15, wherein the black matrix includes the same material as the pixel electrodes.

17. An in-plane switching Liquid Crystal Display (LCD) device, comprising:

a first substrate and a second substrate

a gate line on the first substrate;

a metal common line on the first substrate, the common line parallel to the gate line.

a data line on the first substrate, the data line being perpendicular to the gate line;

a common electrode on the first substrate;

a thin film transistor having a gate electrode, a source electrode and a drain electrode formed on the first substrate;

liquid crystal interposed between the first and second substrates;

a pixel electrode contacting the drain electrode of the thin film transistor; and

wherein, the pixel and common electrodes are formed of a transparent conductive material.

18. The LCD device of claim 17, wherein a portion of the common line overlies a portion of the common electrode.

19. The LCD device of claim 17, wherein a portion of the common electrode overlies a portion of the common line.

20. The LCD device of claim 17, further comprising storage electrode.

21. The LCD device of claim 20, wherein the storage electrode contacts the pixel electrode through a storage contact hole.

22. The LCD device of claim 20, wherein the storage electrode is between the pixel electrode and the first substrate.

23. The LCD device of claim 17, further comprising an auxiliary common electrode covering the common line, wherein the common electrode is electrically connected to the auxiliary common electrode.

24. The LCD device of claim 23, wherein the auxiliary common electrode is formed of the same transparent material as the common electrode.

25. The device of claim 23, wherein the auxiliary common electrode includes indium tin oxide (ITO).

26. The device of claim 23, wherein the auxiliary common line includes indium zinc oxide (IZO).

27. The LCD device of claim 23, further comprising a common pad at an end of the common line.

28. The LCD device of claim 17, further comprising an auxiliary gate line and a gate pad covering the gate line and the gate pad.

29. The LCD device of claim 28, wherein the auxiliary gate line is formed of the same transparent conductive material as the common electrode.

30. The device of claim 28, wherein the auxiliary gate line includes indium tin oxide (ITO).

31. The device of claim 28, wherein the auxiliary gate line includes indium zinc oxide (IZO).

32. The LCD device of claim 17, further comprising a black matrix on the second substrate.

33. The LCD device of claim 17, wherein the transparent conductive material includes indium tin oxide (ITO).

34. The LCD device of claim 17, wherein the transparent conductive material includes indium zinc oxide (IZO).

35. An in-plane switching Liquid Crystal Display (LCD) device, comprising:

a first substrate and a second substrate

a gate line on the first substrate;

a metal common line on the first substrate, the common line parallel to the gate line.

a data line on the first substrate, the data line being perpendicular to the gate line;

a common electrode formed of a transparent conductive material on the first substrate;

a thin film transistor having a gate electrode, a source electrode and a drain electrode formed on the first substrate;

liquid crystal interposed between the first and second substrates; and

a pixel electrode formed of an opaque metal contacting the drain electrode of the thin film transistor.

36. The LCD device of claim 35, further comprising a black matrix formed of the same opaque metal as the pixel electrode.

37. The LCD device of claim 36, wherein the opaque metal is Cr.


39. The LCD device of claim 35, wherein the opaque metal is Cr.

* * * * *


专利名称(译)	面内切换LCD面板		
公开(公告)号	US20010013915A1	公开(公告)日	2001-08-16
申请号	US09/737770	申请日	2000-12-18
[标]申请(专利权)人(译)	宋DUK		
申请(专利权)人(译)	宋IN-DUK		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	SONG IN DUK		
发明人	SONG, IN-DUK		
IPC分类号	G02F1/1343 G02F1/1362 G02F1/1337		
CPC分类号	G02F1/134363 G02F1/136209		
优先权	1019990058108 1999-12-16 KR		
其他公开文献	US7916258		
外部链接	Espacenet USPTO		

摘要(译)

IPS-LCD面板包括第一和第二基板，以及插入其间的液晶。第一基板包括由透明导电材料形成的公共和像素电极。因为公共和像素电极是透明的，所以增加了本发明的IPS-LCD面板的孔径比。另一个IPS-LCD面板包括不透明像素电极和透明公共电极。在形成不透明像素电极时，在第一基板上也形成与像素电极相同材料的黑色矩阵。因为本发明的黑色矩阵比传统的黑色矩阵小得多，所以第二个发明的IPS-LCD面板的孔径比变得更高。



(related art)
FIG. 1



(related art)
FIG. 2