



US007471350B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 7,471,350 B2**
(45) **Date of Patent:** **Dec. 30, 2008**

(54) **ARRAY SUBSTRATE FOR LIQUID CRYSTAL DISPLAY AND FABRICATION METHOD THEREOF**

(75) Inventors: **Kyoung Mook Lee**, Seoul (KR); **Seung Hee Nam**, Gyeonggi-do (KR); **Jae Young Oh**, Gyeonggi-do (KR)

(73) Assignee: **LG. Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/663,774**

(22) Filed: **Sep. 17, 2003**

(65) **Prior Publication Data**

US 2004/0257487 A1 Dec. 23, 2004

(30) **Foreign Application Priority Data**

Jun. 20, 2003 (KR) 10-2003-0040394

(51) **Int. Cl.**

G02F 1/136 (2006.01)

G02F 1/1343 (2006.01)

(52) **U.S. Cl.** **349/43**; 349/139

(58) **Field of Classification Search** 349/42-43, 349/46, 47, 138-139; 438/30
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,303,074 A * 4/1994 Salisbury 349/55

5,856,854 A * 1/1999 Hyun 349/43
6,184,947 B1 * 2/2001 Ozaki et al. 349/42
6,215,541 B1 * 4/2001 Song et al. 349/141
6,256,077 B1 * 7/2001 Baek 349/43
6,307,216 B1 * 10/2001 Huh et al. 257/59
6,365,917 B1 * 4/2002 Yamazaki 257/72
6,461,899 B1 * 10/2002 Kitakado et al. 438/149
6,847,422 B2 * 1/2005 Zhang et al. 349/106

FOREIGN PATENT DOCUMENTS

WO WO 03/058332 A1 * 7/2003

* cited by examiner

Primary Examiner—Dung T. Nguyen

(74) Attorney, Agent, or Firm—McKenna Long & Aldridge LLP

(57) **ABSTRACT**

Disclosed is an array substrate for a liquid crystal display, including: a substrate; a gate line and a thin film transistor having a gate electrode, a source electrode, a drain electrode and an active layer formed over the substrate; an interlayer insulating layer formed on the thin film transistor; a first gate redundancy line formed on the interlayer insulating layer, and connected electrically with one of the gate electrode and the gate line through a first gate contact hole and formed of the same material as the source and drain electrodes; a passivation layer provided on the first gate redundancy line and the interlayer insulating layer; and a pixel electrode electrically connected with the drain electrode through the drain contact hole formed in the passivation layer.

27 Claims, 14 Drawing Sheets




Fig. 1A
Related Art




Fig. 1B
Related Art




Fig.2
Related Art




Fig. 3




Fig. 4A





Fig. 4B






Fig.5




Fig.6A




Fig.6B




Fig.6C




Fig.6D




Fig.7




Fig.8A




Fig.8B




Fig.9




Fig. 10A




Fig. 10B




Fig. 11A




Fig. 11B




Fig.11C





Fig.11D



ARRAY SUBSTRATE FOR LIQUID CRYSTAL DISPLAY AND FABRICATION METHOD THEREOF

This application claims the benefit of Korean Patent Application No. 2003-40394, filed on Jun. 20, 2003, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display, and more particularly, to an array substrate for a liquid crystal display and a fabrication method thereof.

2. Description of the Related Art

Recently, as modern society quickly changes in an information-oriented society, flat panel displays having many advantages such as slimmness, light weight, and low power consumption are widely used. Particularly, among the flat panel displays, liquid crystal displays (LCD) having superior color reproduction have been developed.

As known in the art, a liquid crystal display is formed by the steps of: arranging two substrates each having electrode formed on one surface thereof to face with each other; and injecting liquid crystal material between two substrates. In the liquid crystal display, images are displayed by rearranging liquid crystal molecules by an electric field generated by a voltage applied to two electrodes to vary light transmittance.

In the above liquid crystal display, a lower substrate is an array substrate including a thin film transistor for applying a signal to a pixel electrode and is formed by repeating a metallic film and insulating film forming step and a lithography step. Further, an upper substrate is a substrate including a color filter layer of three colors of red, green and blue sequentially arranged and is manufactured using a pigment dispersion method, a dyeing method, an electro deposition method, etc.

Generally, an active layer of the thin film transistor is formed of amorphous silicon (a-Si:H). This is because the amorphous silicon is easily fabricated in a large-sized structure, thereby resulting in a higher productivity, and the amorphous silicon can be deposited on the substrate at a lower temperature below 350° C., thereby permitting use of a lower price insulating substrate.

However, because a hydrogenated amorphous silicon is in disordered atomic arrangement due to a weak Si—Si bond and a dangling bond, when light is radiated on or an electric field is applied to the hydrogenated amorphous silicon, it is changed to be in a meta-stable state, so that when the amorphous silicon is used in the thin film transistor, questionable stability results.

In particular, the amorphous silicon has a disadvantage in which deterioration is caused by light radiation. Further, because a driving unit for a display pixel has an electric characteristic (low field effect mobility: 0.1~1.0 cm²/V·s) that causes the reliability to deteriorate, the amorphous silicon is difficult to use in a driving circuit.

Further, if a liquid crystal panel for the liquid crystal display increases in resolution, the pad pitch external to the substrate is narrowed for connecting a gate line and a data line of a thin film transistor substrate with a tape carrier package (TCP), so that TCP bonding itself becomes difficult.

However, because polycrystalline silicon has a field effect mobility larger than the amorphous silicon, the driving circuit can be formed directly on the substrate, which decreases the

manufacturing cost for a driving integrated circuit and simplifies the mounting structure of the driving IC.

Further, the above polycrystalline silicon has the advantages that the field effect mobility is one hundred to two hundreds times larger than that of the amorphous silicon, the response speed is fast, and the stability is excellent with respect to temperature and light. Furthermore, the polycrystalline silicon has the advantage that the driving circuit can be formed on the same substrate.

Various fabrication methods of polycrystalline silicon having the above advantages are known in the art. Typically, to form polycrystalline silicon, amorphous silicon is deposited through a plasma enhanced chemical vapor deposition or a low pressure chemical vapor deposition, and the deposited amorphous silicon is again crystallized.

As one method of forming polycrystalline silicon uses a laser annealing method in which the substrate is heated to a temperature of about 250° C. while an excimer laser radiates a thin amorphous silicon film to form the polycrystalline silicon. Another crystallizing method is a metal induced crystallization (MIC) method in which a metal deposited on the amorphous silicon is used as a seed to form the polycrystalline silicon. Another crystallizing method is a solid phase crystallization (SPC) method in which the amorphous silicon is heated for a long time at a high temperature to form the polycrystalline silicon, etc.

On the other hand, in order to provide a reliable thin film transistor, it is important to form a larger crystalline grain. One method for solving this is a single crystalline forming method (Robert S. Sposilli, M. A. Crowder, and James S. Im, Mat. Res. Soc. Symp. Proc. Vol. 452, 956~957, 1997) using a sequential lateral solidification (SLS) crystallization technique that uses the fact that the silicon crystalline grain grows up from a boundary surface between a liquid-phase silicon and a solid-phase silicon in a vertical direction.

In the SLS crystallization technique, the magnitude of the laser energy, and the range and the translation distance of the laser beam are properly controlled such that the silicon crystalline grain can be laterally grown-up by a predetermined length to allow the amorphous silicon to be crystallized as a single crystalline silicon.

Hereinafter, with reference to the attached drawings, a conventional array substrate and fabrication method thereof will be described including a polycrystalline silicon thin film transistor.

FIGS. 1A and 1B are sectional views respectively illustrating conventional top-gate type thin film transistors of a pixel and a driving circuit, and the pixel and the driving circuit all employ a top-gate type thin film transistor in which a gate electrode is positioned over a semiconductor layer.

First, in a pixel thin film transistor (I) of FIG. 1A, a buffer layer 114 is formed on a whole insulating substrate 100, a semiconductor layer 116 is formed on the buffer layer 114, and then a gate insulating layer 118 and a gate electrode 120 are sequentially formed on a central portion of the semiconductor layer 116.

Further, an interlayer insulating layer 124 having first and second semiconductor layer contact holes 122a and 122b formed therein is formed on the whole resultant substrate having the gate electrode 120. Additionally, source and drain electrodes 126 and 128 are formed to connect with the semiconductor layer 116 through the first and second semiconductor layer contact holes 122a and 122b.

Furthermore, a passivation layer 132 having a drain contact hole 130 formed therein is formed on the resultant substrate having the source and drain electrodes 126 and 128, and a

pixel electrode is formed on the passivation layer to connect with the drain electrode **128** through the drain contact hole **130**.

The semiconductor layer **116** includes an active layer **116a** formed in a region corresponding to the gate insulating layer **118**, and an N⁺ doped N-type impurity layer **116c** formed in a contact region with the source and drain electrodes **126** and **128**. In a junction portion between the source and drain electrodes **126**, **128** between the active layer **116a** and the N-type impurity layer **116c** and the gate electrode **120**, a lightly doped drain (LDD) layer **116b** is located.

The LDD layer **116b** is doped with a lower concentration for the purpose of dispersing hot carriers so as to prevent a leakage current from increasing and to minimize a current loss in an ON state.

In FIG. 1B, a complimentary metal-oxide-silicon (CMOS) thin film transistor includes a thin film transistor (II) having an N doped channel and a thin film transistor (III) having a P doped channel, and for description convenience, the same elements are numbered in a sequence of II and III.

As shown in FIG. 1B, an N-type semiconductor layer **140** and a P-type semiconductor layer **142** are formed on the insulating substrate **100** having the buffer layer **114** formed. Herein, the gate insulating layers **144a** and **144b** and the gate electrodes **146a** and **146b** are respectively formed on the N-type and P-type semiconductor layers **140** and **142**. Additionally, the interlayer insulating layer **124** having the semiconductor layer contact holes **147a**, **147b**, **147c** and **147d** formed therein is formed on the whole resultant substrate having the gate electrodes **146a** and **146b**.

Source and drain electrodes **150a**, **152a**, **150b** and **152b** are respectively formed on the interlayer insulating layer **124** to connect with the N-type and P-type semiconductor layers **140** and **142** through the semiconductor layer contact holes **147a**, **147b**, **147c** and **147d**, and the passivation layer **132** is formed on the whole resultant substrate having the source and drain electrodes **150a**, **152a**, **150b** and **152b**.

The N-type semiconductor layer **140** includes, as in the semiconductor layer **116** of FIG. 1A, an active layer **140a** formed in a contact region with the gate insulating layer **144a**, an N-type impurity layer **140c** formed in a region including a contact region with the source and drain electrodes **150a** and **152a**, and an LDD layer **140b** between the active layer **140a** and N-type impurity layer **140c**.

Hereinafter, a conventional fabrication method will be described for a general thin film transistor of the pixel and a CMOS thin film transistor of the driving circuit.

FIG. 2 is a process flow chart illustrating a conventional fabrication method of a top-gate type thin film transistor of FIGS. 1A and 1B, and this fabrication method includes a photolithography step (hereinafter, "masking process") using a photoresist (PR).

First, the insulating substrate is prepared, and the buffer layer is formed on the insulating substrate **S100**. For the material of the buffer layer, an inorganic insulating film such as a silicon nitride film (SiNx) or a silicon oxide film (SiOx) may be used.

Next, the active layer is formed on the buffer layer **S11**. In this step, the amorphous silicon (a-Si) layer is deposited to have a thickness of about 550 Å on the resultant substrate having the buffer layer formed, and then a dehydrogenation process is performed. Additionally, through a crystallization process, a crystalline silicon layer is formed such as a polycrystalline silicon layer or a single crystalline silicon layer, and then the crystalline silicon layer is used to form the active layer by a first masking process.

After that, the gate insulating layer and the gate electrode are formed **S120**. A silicon nitride film with a thickness of about 1000 Å and a molybdenum (Mo) film with a thickness of about 2000 Å are sequentially deposited on the resultant substrate having the active layer formed, and then through a second masking process, the gate insulating layer and the gate electrode are formed.

Next, a step is performed for completing the N-type semiconductor layer. That is, the N⁻ doped LDD layer is formed on the resultant substrate having the gate electrode, the gate insulating layer is formed, and then through a third masking process, the N⁺ doped N-type impurity layer is formed **S130**.

Next, the P⁺ doped P-type impurity layer is formed on the resultant substrate having the N-type impurity layer formed therein, through a fourth masking process **S140**.

Further, a step is performed for forming the interlayer insulating layer **S150**. The inorganic insulating film with a thickness of about 7000 Å may be silicon nitride or silicon oxide and is deposited on the resultant substrate having the P-type impurity layer formed, and then through a fifth masking process, the interlayer insulating layer having the semiconductor layer contact hole is formed.

Next, molybdenum (Mo) with a thickness of about 500 Å and aluminum neodymium (AlNd) with a thickness of about 3000 Å are sequentially deposited on the resultant substrate with the interlayer insulating layer, and then through a sixth masking process, a blanket etching is performed to form the source and drain electrode to connect with the impurity layer through the semiconductor layer contact hole **S160**.

Further, the silicon nitride film with a thickness of about 4000 Å is deposited to form the passivation layer on the resultant substrate with the source and drain electrodes, and then a hydrogenation heat-treatment process is performed. The hydrogenation heat-treatment process may be performed once using nitrogen (N₂) gas at a temperature of change about 380° C.

Next, through a seventh masking process, the drain contact hole is formed in the passivation layer **S170**.

Finally, the pixel electrode is formed on the passivation layer **S180**. In this step, a layer of Indium Tin Oxide (ITO) about 500 Å thick is deposited on the resultant substrate having the passivation layer formed, and then through an eighth masking process, the pixel electrode is formed to connect with the drain electrode through the drain contact hole.

One problem as the liquid crystal display increases size and increases in resolution, the length of the lines lengthen and a width thereof are narrowed thereby resulting in increasing a probability of a signal delay.

Accordingly, there remains a need to decrease the resistance of the lines using a low resistance material.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to a liquid crystal display and a fabrication method thereof that substantially obviates one or more problems due to limitations and disadvantages of the related art.

An advantage of the present invention is to provide an array substrate for a liquid crystal display and a fabrication method thereof in which a gate redundancy line is formed on a gate electrode and/or a gate line in a thin film transistor such that the resistance of the gate electrode and/or the gate line is decreased, and the gate electrode and gate line are prevented from being disconnected thereby being applicable to a large area liquid crystal display panel resulting in a better quality low resistance line that prevents signal delay.

5

Additional features and advantages of the invention will be set forth in part in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the invention, as embodied and broadly described herein, there is provided an array substrate for a liquid crystal display, the array substrate including: a substrate; a gate line and a thin film transistor having a gate electrode, a source electrode, a drain electrode and an active layer formed over the substrate; an interlayer insulating layer formed on the thin film transistor; a first gate redundancy line formed on the interlayer insulating layer, and connected electrically with one of the gate electrode and the gate line through a first gate contact hole and formed of the same material as the source and drain electrodes; a passivation layer provided on the first gate redundancy line and the interlayer insulating layer; and a pixel electrode electrically connected with the drain electrode through the drain contact hole formed in the passivation layer.

In another aspect of the present invention, there is provided an array substrate for a liquid crystal display, including: a substrate; a gate line and a thin film transistor having a gate electrode, a source electrode, a drain electrode and an active layer formed on the substrate; an interlayer insulating layer formed on the thin film transistor; a passivation layer formed on the interlayer insulating layer; a pixel electrode electrically connected with the drain electrode through a drain contact hole formed in the passivation layer; and a gate redundancy line formed on the passivation layer, and connected electrically with one of the gate electrode and the gate line through a gate contact hole and formed of the same material as the pixel electrode.

In another aspect of the present invention, there is provided a method for fabricating an array substrate for a liquid crystal display, the method including the steps of: forming a gate line and a gate electrode on a substrate; forming an interlayer insulating layer on the gate line and the gate electrode; forming a first gate redundancy line on the interlayer insulating layer and electrically connected with one of the gate electrode and the gate line through a first gate contact hole; forming a passivation layer on the first gate redundancy line and the interlayer insulating layer; and forming a drain contact hole in the passivation layer, and forming a pixel electrode connected electrically with the drain electrode through the drain contact hole.

In another aspect of the present invention, there is provided a method for fabricating an array substrate for a liquid crystal display, the method including the steps of: forming a gate line and a gate electrode on a substrate; forming an interlayer insulating layer on the gate line and the gate electrode; forming a passivation layer on the interlayer insulating layer; and forming a gate contact hole in the passivation layer, and forming a gate redundancy line connected electrically with one of the gate electrode and the gate line through the gate contact hole.

It is to be understood that both the foregoing general description and the following detailed description of the

6

present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principle of the invention.

In the drawings:

FIG. 1 is a sectional view respectively illustrating conventional top-gate type thin film transistors of a pixel part and a driving circuit part;

FIG. 2 is a process flow chart illustrating a conventional fabrication method of a top-gate type thin film transistor;

FIG. 3 is a sectional view respectively illustrating top-gate type thin film transistors of a pixel part and a driving circuit part according to a first embodiment of the present invention;

FIG. 4 is a view illustrating a sequence of a fabrication method of a top-gate type thin film transistor of FIG. 3;

FIG. 5 is a sectional view respectively illustrating top-gate type thin film transistors of a pixel part and a driving circuit part according to a second embodiment of the present invention;

FIG. 6 is a view illustrating a sequence of a fabrication method of a top-gate type thin film transistor of FIG. 5;

FIG. 7 is a schematic plane view illustrating a portion of a pixel region in an array substrate including a bottom-gate type thin film transistor according to a third embodiment of the present invention;

FIGS. 8A and 8B are respective sectional views, taken along lines I-I' and II-II' of FIG. 7;

FIG. 9 is a schematic plane view illustrating a portion of a pixel region in an array substrate including a bottom-gate type thin film transistor according to a fourth embodiment of the present invention;

FIGS. 10A and 10B are respective sectional views, taken along lines III-III' and IV-IV' of FIG. 9; and

FIGS. 11A to 11D are views illustrating various types of contact holes for forming a gate redundancy line on a gate electrode and a gate line according to other embodiments of the present invention.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, example of which are illustrated in the accompanying drawings.

FIG. 3 is a sectional view respectively illustrating top-gate type thin film transistors of a pixel and a driving circuit according to a first embodiment of the present invention. In FIG. 3, the pixel and the driving circuit all have a top-gate type thin film transistor in which a gate electrode is positioned on a semiconductor layer.

First, as shown in FIG. 3, in a pixel thin film transistor (IV), a buffer layer 214 is formed on a whole insulating substrate 200, a semiconductor layer 216 is formed on the buffer layer 214, and then a gate insulating layer 218 and a gate electrode 220 are sequentially formed on a central portion of the semiconductor layer 216.

Further, an interlayer insulating layer 224 having first and second semiconductor layer contact holes 222a and 222b and a gate contact hole 239 formed therein is formed on the resultant substrate to cover the gate electrode 220. Addition-

ally, source and drain electrodes **226** and **228** are formed to connect with the semiconductor layer **216** through the first and second semiconductor layer contact holes **222a** and **222b**.

Furthermore, a gate redundancy line **229** is formed to connect with the gate electrode **220** through the gate contact hole **239** formed in the interlayer insulating layer **224**. The gate redundancy line **229** is formed at the same time that the source and drain electrodes **226** and **228** are formed and with the same material.

Additionally, a passivation layer **232** having a drain contact hole **230** is formed on the resultant substrate having the source and drain electrodes **226** and **228** and the gate redundancy line **229**, and a pixel electrode **234** is formed on the passivation layer **232** to connect with the drain electrode **228** through the drain contact hole **230**.

The semiconductor layer **216** includes an active layer **216a** formed in a region corresponding to the gate insulating layer **218**, and an N⁺ doped N-type impurity layer **216c** formed in a contact region with the source and drain electrodes **226** and **228**. In a junction portion between the source and drain electrodes **226** and **228** between the active layer **216a** and the N-type impurity layer **216c** and the gate electrode **220**, a lightly doped drain (LDD) layer **216b** is formed.

The LDD layer **216b** is doped with a lower concentration for the purpose of dispersing hot carriers so as to prevent a leakage current from increasing and to minimize a current loss in an ON state.

Also, as shown in FIG. 3, in the array substrate for the liquid crystal display according to the present invention, the CMOS thin film transistor of the driving circuit includes a thin film transistor (V) having an N doped channel and a thin film transistor (VI) having a P doped channel.

As illustrated, an N-type semiconductor layer **240** and a P-type semiconductor layer **242** are formed on the insulating substrate **200** having the buffer layer **214** formed. The gate insulating layers **244a** and **244b** and the gate electrodes **246a** and **246b** are formed on the N-type and P-type semiconductor layers **240** and **242**. Additionally, the interlayer insulating layer **224** having the semiconductor layer contact holes **247a**, **247b**, **247c**, and **247d** and the gate contact holes **239a** and **239b** is formed on the whole resultant substrate having the gate electrodes **246a** and **246b**.

Source and drain electrodes **250a**, **252a**, **250b** and **252b** are respectively formed on the interlayer insulating layer **224** to connect with the N-type and P-type semiconductor layers **240** and **242** through the semiconductor layer contact holes **247a**, **247b**, **247c**, and **247d**. Additionally, gate redundancy lines **249a** and **249b** are formed to connect with the gate electrodes **246a** and **246b** through the gate contact holes **239a** and **239b**. Also, the passivation layer **232** is formed on the whole resultant substrate having the source and drain electrodes **250a**, **252a**, **250b** and **252b** and the gate redundancy lines **249a** and **249b**.

Herein, as in the semiconductor layer **216** of the pixel the N-type semiconductor layer **240** includes an active layer **240a** formed in a contact region with the gate insulating layer **244a**, an N-type impurity layer **240c** formed in a region including a contact region with the source and drain electrodes **250a** and **252a**, and an LDD layer **240b** between the active layer **240a** and N-type impurity layer **240c**.

Also, because the P-type semiconductor layer **242** uses a positively charged carrier, it has less carrier deterioration and a smaller leakage current than those of the N-type thin film transistor. Accordingly, the P-type semiconductor layer **242** is constructed to include a contact region with the gate insulating layer **244b** as the active layer **242a** and an external region

of the active layer **242a** as the P-type impurity layer **242b** without an individual LDD layer.

In the above description, the thin film transistor having an LDD layer formed is described, but in the thin film transistor also may be formed in an offset structure not the LDD layer.

Also, in the above description, it is described that the gate redundancy line is formed on the gate electrode, but the gate redundancy line may be formed on the gate line as well as the gate electrode.

Hereinafter, for an array substrate for the liquid crystal display according to the present invention, a fabrication method of the pixel thin film transistor will be described in detail.

FIGS. 4A to 4D are views illustrating a sequence of the fabrication method of the top-gate type thin film transistor according to a first embodiment of the present invention. This fabrication method includes a photolithography process using a photoresist (PR).

First, as shown in FIG. 4A, the buffer layer **214** is formed on the insulating substrate **200**. The buffer layer **214** material may be an inorganic insulating film such as a silicon nitride film (SiNx) or a silicon oxide film (SiOx).

Next, the semiconductor layer **216** is formed on the buffer layer **214**. In this step, the amorphous silicon (a-Si) is deposited with a thickness of about 550 Å on the resultant substrate having the buffer layer **214** formed, and then a dehydrogenation process is performed. Additionally, a crystallization process forms a crystalline silicon layer such as a polycrystalline silicon layer or a single crystalline silicon layer, and then the crystalline silicon layer is used to form the semiconductor layer **216** by a first masking process.

Further, the gate insulating layer **218** and the gate electrode **220** are sequentially formed.

A silicon nitride film or a silicon oxide film with a thickness of about 1000 Å is sequentially deposited to form the gate insulating layer **218** on the resultant substrate having the semiconductor layer **216**. Then, molybdenum (Mo) with a thickness of about 2000 Å is deposited and, the gate electrode **220** is formed by a second masking process.

Next, a step is performed for completing the N-type semiconductor layer. The N⁻ doped LDD layer **216b** is formed on the resultant substrate having the gate electrode **220** and the gate insulating layer **218**, and then through a third masking process, the N⁺ doped N-type impurity layer **216c** is formed.

Next, the P⁺ doped P-type impurity layer (not shown in the drawing, but used to form the driving circuit thin film transistor) is formed on the resultant substrate having the N-type impurity layer **216c** formed therein.

Further, a step is performed for forming the interlayer insulating layer **224**. The inorganic insulating film with a thickness of about 7000 Å may be silicon nitride or silicon oxide and is deposited on the resultant substrate.

Next, as shown in FIG. 4B, the semiconductor layer contact holes **222a** and **222b** and the gate contact hole **239** are formed in the interlayer insulating layer **224** using a fifth masking process.

Further, aluminum neodymium (AlNd) with a thickness of about 3000 Å and molybdenum (Mo) with a thickness of about 500 Å are deposited to form a metallic layer on the resultant substrate having the interlayer insulating layer **224** including the semiconductor layer contact holes **222a** and **222b** and the gate contact hole **239**. The metallic layer also may be formed to include Mo/Al/Mo, and also instead of aluminum, an aluminum alloy may be used.

Next, a blanket etching process is performed by a sixth masking process. Accordingly, as shown in FIG. 4C, the source and drain electrodes **226** and **228** are formed to con-

nect with the impurity layer through the semiconductor layer contact holes **222a** and **222b**. Additionally, the gate redundancy line **229** is formed of the same material as the source and drain electrodes **226** and **228**, to connect with the gate electrode **220** through the gate contact hole **239**.

Additionally, as shown in FIG. 4D, a silicon nitride film or silicon oxide film about 4000 Å thick is deposited to form the passivation layer **232** on the resultant substrate having the source and drain electrodes **226** and **228** and the gate redundancy line **229** formed.

Next, the hydrogenation heat-treatment step is performed. The hydrogenation heat-treatment step may be performed once at a temperature of about 380° C. using nitrogen (N₂) gas.

Next, through a seventh masking process, the drain contact hole **230** is formed in the passivation layer **232**, and the pixel electrode **234** is formed on the passivation layer **232**. In this step, ITO with a thickness of about 500 Å is deposited on the resultant substrate having the passivation layer **232** formed, by an eighth masking process, the pixel electrode **234** is formed to connect with the drain electrode **228** through the drain contact hole **230**.

Accordingly, the present invention may, by the gate redundancy line, lower the resistance of the gate electrode and the gate line and prevent the gate electrode and the gate line from being disconnected, thereby improving response speed and providing good image quality in the liquid crystal display.

FIG. 5 is a sectional view respectively illustrating the pixel thin film transistor (VII) and a driving circuit CMOS thin film transistor (VIII) and (IX) according to a second embodiment of the present invention. In FIG. 5, a pixel and a driving circuit all have a top-gate type thin film transistor in which a gate electrode is positioned on a semiconductor layer.

First, as shown in FIG. 5, in a pixel thin film transistor (VII), a buffer layer **314** is formed on a whole insulating substrate **300**, a semiconductor layer **316** is formed on the buffer layer **314**, and then a gate insulating layer **318** and a gate electrode **320** are sequentially formed on a central portion of the semiconductor layer **316**.

Further, an interlayer insulating layer **324** having first and second semiconductor layer contact holes **322a** and **322b** formed therein is formed on the resultant substrate having the gate electrode **320**. Additionally, source and drain electrodes **326** and **328** are formed to connect with the semiconductor layer **316** through the first and second semiconductor layer contact holes **322a** and **322b**.

Additionally, a passivation layer **332** having the drain contact hole **330** and the gate contact hole **339** therein is formed on the resultant substrate having the source and drain electrodes **326** and **328** and the gate electrode **320** formed. Also, a pixel electrode **334** is formed on the passivation layer **332** to connect with the drain electrode **328** through the drain contact hole **330**.

The passivation layer **332** and the interlayer insulating layer **324** formed on the gate electrode **320** are etched to form the gate contact hole **339**.

At the same time that the pixel electrode **334** is formed on the passivation layer **332**, a gate redundancy line **329** is formed of the same material. Accordingly, the gate redundancy line **329** is in contact with the gate electrode **320** through the gate contact hole **339**.

The semiconductor layer **316** includes an active layer **316a** in a region corresponding to the gate insulating layer **318**, and an N⁺ doped N-type impurity layer **316c** in a contact region with the source and drain electrodes **326** and **328**. In a junction portion between the source and drain electrodes **326** and

328 between the active layer **316a** and the N-type impurity layer **316c** and the gate electrode **320**, a lightly doped drain (LDD) layer **316b** is formed.

The LDD layer **316b** is doped with a lower concentration for the purpose of dispersing hot carriers so as to prevent a leakage current from increasing and to minimize a current loss in an ON state.

Also, as shown in FIG. 5, the CMOS thin film transistor of the driving circuit includes a thin film transistor (VIII) having an N doped channel and a thin film transistor (IX) having a P doped channel.

As illustrated, an N-type semiconductor layer **340** and a P-type semiconductor layer **342** are formed on the insulating substrate **300** having the buffer layer **314** formed. The gate insulating layers **344a** and **344b** and the gate electrodes **346a** and **346b** are respectively formed on the N-type and P-type semiconductor layers **340** and **342**. Additionally, the interlayer insulating layer **324** having the semiconductor layer contact holes **347a**, **347b**, **347c** and **347d** formed therein is formed on the whole resultant substrate having the gate electrodes **346a** and **346b**.

Source and drain electrodes **350a**, **352a**, **350b**, and **352b** are respectively formed on the interlayer insulating layer **324** to respectively connect with the N-type and P-type semiconductor layers **340** and **342** through the semiconductor layer contact holes **347a**, **347b**, **347c**, and **347d**. Additionally, the passivation layer **332** is formed on the resultant substrate having the source and drain electrodes **350a**, **352a**, **350b**, and **352b**.

Herein, the gate contact holes **339a** and **339b** passing through the passivation layer **332** and the interlayer insulating layer **324** are simultaneously formed when the drain contact hole **330** is formed in the pixel part thin film transistor. Also, when the pixel electrode **334** is formed in the pixel thin film transistor, the gate redundancy lines **349a** and **349b** are simultaneously formed of the same material.

As in the semiconductor layer **316** of the pixel part, the N-type semiconductor layer **340** includes an active layer **340a** formed in a contact region with the gate insulating layer **344a**, an N-type impurity layer **340c** formed in a region including a contact region with the source and drain electrodes **350a** and **352a**, and an LDD layer **340b** formed between the active layer **340a** and N-type impurity layer **340c**.

Also, because the P-type semiconductor layer **342** uses a positively charged carrier, it has less carrier deterioration and smaller leakage current than those of the N-type thin film transistor. Accordingly, the P-type semiconductor layer **342** is constructed to include a contact region with the gate insulating layer **344b** as the active layer **342a**, and an external region of the active layer **342a** as the P-type impurity layer **342b** without an individual LDD layer.

Hereinafter, for an array substrate for the liquid crystal display according to the present invention, the fabrication method of the pixel thin film transistor will be described in detail.

FIGS. 6A to 6D are views illustrating a sequence of the fabrication method of the top-gate type pixel thin film transistor according to a second embodiment of the present invention. This fabrication method includes a photolithography process using a photoresist (PR).

First, as shown in FIG. 6A, the buffer layer **314** is formed on the insulating substrate **300**. The buffer layer material may be an inorganic insulating film such as a silicon nitride film (SiNx) or a silicon oxide film (SiOx).

Next, the semiconductor layer **316** is formed on the buffer layer **314**. In this step, the amorphous silicon (a-Si) layer is deposited with a thickness of about 550 Å on the resultant

substrate having the buffer layer **314** formed, and then a dehydrogenation process is performed. Additionally, a crystallization process forms a crystalline silicon layer such as a polycrystalline silicon layer or a single crystalline silicon layer, and then the crystalline silicon layer is used to form the semiconductor layer **316** by a first masking process.

Further, the gate insulating layer **318** and the gate electrode **320** are sequentially formed.

A silicon nitride film or a silicon oxide film with a thickness of about 1000 Å is sequentially deposited to form the gate insulating layer **318** on the resultant substrate having the semiconductor layer **316**. Then molybdenum (Mo) with a thickness of about 2000 Å is deposited, and by a second masking process, the gate electrode **320** is formed.

Next, a step is performed for completing the N-type semiconductor layer **316**. The N⁻ doped LDD layer **316b** is formed on the resultant substrate having the gate electrode **320** and the gate insulating layer **318**, and then through a third masking process, the N⁺ doped N-type impurity layer **316c** is formed.

Next, the P⁺ doped P-type impurity layer (not shown) is formed on the resultant substrate having the N-type impurity layer **316c** formed therein.

Further, a step is performed for forming the interlayer insulating layer **324**. The inorganic insulating film with thickness of about 7000 Å may be silicon nitride or the silicon oxide and is deposited on the resultant substrate having the P-type impurity layer formed therein.

Next, as shown in FIG. 6B, the semiconductor layer contact holes **322a** and **322b** are formed in the interlayer insulating layer **324** using a fifth masking process.

Further, aluminum neodymium (AlNd) with a thickness of about 3000 Å and molybdenum (Mo) with a thickness of about 500 Å are deposited to form a metallic layer on the resultant substrate having the interlayer insulating layer **324** including the semiconductor layer contact holes **322a** and **322b**. The metallic layer also may be formed to include Mo/Al/Mo, and also instead of aluminum, an aluminum alloy may be used.

Next, a blanket etching process is performed by a sixth masking process. Accordingly, the source and drain electrodes **326** and **328** are formed to connect with the impurity layer **316c** through the semiconductor layer contact holes **322a** and **322b**.

Additionally, as shown in FIG. 6C, a silicon nitride film or silicon oxide film about 4000 Å thick is deposited to form the passivation layer **332** on the resultant substrate having the source and drain electrodes **326** and **328** formed.

Next, the hydrogenation heat-treatment step is performed. The hydrogenation heat-treatment step may be performed once at a temperature of about 380° C. using nitrogen (N₂) gas.

Next, through a seventh masking process, the drain contact hole **330** and the gate contact hole **339** are formed in the passivation layer **332**. The drain contact hole **330** and the gate contact hole **339** are simultaneously formed using one mask. The gate contact hole **339** is formed by etching the passivation layer **332** and the interlayer insulating layer **324** to expose an upper surface of the gate electrode **320**.

Finally, as shown in FIG. 6D, the pixel electrode **334** is formed on the passivation layer **332**. In this step, ITO with a thickness of about 500 Å is deposited on the resultant substrate having the passivation layer **332** formed, and the pixel electrode **334** is formed to connect with the drain electrode **328** through the drain contact hole **330** by an eighth masking process.

When the pixel electrode **334** is formed in the pixel thin film transistor, the gate redundancy line **329** is simultaneously formed of the same material. Accordingly, the gate redundancy line **329** is in contact with the gate electrode **320** through the gate contact hole **339**.

As described above, the present invention can, by the gate redundancy line, prevent the gate electrode and the gate line from being disconnected to thereby provide a good quality of image in the liquid crystal display. Additionally, in the above description, it is illustrated that the gate redundancy line is formed on the gate electrode, however the gate redundancy line may be formed on the gate line as well as the gate electrode.

On the other hand, the present invention is also applicable to a liquid crystal display including a bottom-gate type thin film transistor as well as the liquid crystal display including the top-gate type thin film transistor. With reference to the attached drawing, an array substrate including the bottom-gate type thin film transistor using the poly crystalline silicon, and a fabrication method thereof according to the present invention will be described in another embodiment.

FIG. 7 is a schematic plane view illustrating a portion of a pixel region in an array substrate including a bottom-gate type thin film transistor according to a third embodiment of the present invention.

As shown in FIG. 7, a matrix type of a pixel region is defined on a transparent substrate by a plurality of gate lines **411** arranged in parallel with one another and a plurality of data lines **412** arranged in parallel with one another substantially perpendicular to the gate lines **411**. Additionally, at a crossing point of two lines **411** and **412**, a thin film transistor including a semiconductor layer **416**, a gate electrode **420**, and source and drain electrodes **426** and **428** is provided. Also, a pixel electrode **434** is further provided to electrically connect to the thin film transistor.

The semiconductor layer **416** is electrically connected with the source and drain electrodes **426** and **428** by first and second semiconductor layer contact holes **422a** and **422b**. Further, the drain electrode **428** and the pixel electrode **434** are electrically connected with each other by the drain contact hole **430**.

Additionally, a gate redundancy line **429** is connected with the gate electrode **420** and the gate line **411** through the gate contact hole **439**. The gate redundancy line **429** is, at the time of forming the source and drain electrodes **426** and **428**, formed of the same material on the gate electrode **420** and the gate line **411**. The gate contact hole **439** formed on the gate electrode **420** is located in a region where the semiconductor layer **416** is not formed.

FIGS. 8A and 8B are respective sectional views, taken along lines I-I' and II-II' of FIG. 7, and schematically illustrate a portion of the pixel region in the array substrate including the bottom-gate type thin film transistor according to the present invention.

As shown in FIG. 8A taken along line I-I' of FIG. 7, a buffer layer **414** is formed on a whole insulating substrate **400**, and a gate electrode **420** is formed on the buffer layer **414**. Further, a gate insulating layer **418** is formed covering the resultant substrate having the gate electrode **420**, and a semiconductor layer **416** is formed on the gate insulating layer **418**.

An interlayer insulating layer **424** is further formed having first and second semiconductor contact holes **422a** and **422b** therein and covering the resultant substrate having the semiconductor layer **416**. Also, source and drain electrodes **426** and **428** are formed to respectively connect with the semiconductor layer **416** through the first and second semiconductor layer contact holes **422a** and **422b**.

On the other hand, in the present invention, when the first and second semiconductor layer contact holes **422a** and **422b** are formed, the gate contact hole (not shown in FIG. 8A, but referring to a reference numeral **439** of FIG. 8B) is simultaneously formed in the interlayer insulating layer **424**.

Additionally, a passivation layer **432** having the drain contact hole **430** therein is formed on the resultant substrate having the source and drain electrodes **426** and **428**. Also, the pixel electrode **434** is formed on the passivation layer **432** to connect with the drain electrode **428** through the drain contact hole **430**.

In the meanwhile, as shown in FIG. 8B taken along line II-II' of FIG. 7, the buffer layer **414** is formed on the whole insulating substrate **400**, and the gate electrode **420** is formed on the buffer layer **414**.

Further, the gate insulating layer **418** is formed on the resultant substrate having the gate electrode **420**, and the interlayer insulating layer **424** is formed on the resultant substrate having the gate insulating layer **418**.

Additionally, the gate redundancy line **429** is formed to connect with the gate electrode **420** through the gate contact hole **439** formed in the interlayer insulating layer **424** and the gate insulating layer **418**. The gate redundancy line **429** is formed at the same time as the source and drain electrodes and of the same material.

Accordingly, the present invention can, by the gate redundancy line, lower the resistance of the gate electrode and the gate line and prevent the gate electrode and the gate line from being disconnected, thereby improving the response speed and image quality of the liquid crystal display. The fabrication method of the liquid crystal display including the bottom-gate type thin film transistor according to the present invention is similar with those of the first and second embodiments.

FIG. 9 is a schematic plane view illustrating a portion of the pixel region in an array substrate including a bottom-gate type thin film transistor according to a fourth embodiment of the present invention.

As shown in FIG. 9, a matrix type of a pixel region is defined on a transparent substrate by a plurality of gate lines **511** arranged in parallel with one another and a plurality of data lines **512** arranged in parallel with one another substantially perpendicular to the gate line **511**. Additionally, at a crossing point of two lines **511** and **512**, a thin film transistor including a semiconductor layer **516**, a gate electrode **520**, and source and drain electrodes **526** and **528** is provided. Also, a pixel electrode **534** is further provided to electrically connect to the thin film transistor.

The source and drain electrodes **526** and **528** are electrically connected with the semiconductor layer **516** through first and second semiconductor layer contact holes **522a** and **522b**, and the drain electrode **528** and the pixel electrode **534** are electrically connected with each other by the drain contact hole **530**.

Additionally, a gate redundancy line **529** is connected with the gate electrode **520** and the gate line **511** through the gate contact hole **539**. The gate redundancy line **529** is, at the same time of forming the pixel electrode **534**, formed of the same material. The gate contact hole **539** formed on the gate electrode **520** is located in a region where the semiconductor layer **516** is not formed.

FIGS. 10A and 10B are respective sectional views taken along lines III-III' and IV-IV' of FIG. 9, and schematically illustrate a portion of a pixel region in an array substrate including the bottom-gate type thin film transistor according to the present invention.

As shown in FIG. 10A taken along line III-III' of FIG. 9, a buffer layer **514** is formed on a whole insulating substrate

500, and a gate electrode **520** is formed on the buffer layer **514**. Further, a gate insulating layer **518** is formed covering the resultant substrate having the gate electrode **520**, and a semiconductor layer **516** is formed on the gate insulating layer **518**.

An interlayer insulating layer **524** is further formed having first and second semiconductor contact holes **522a** and **522b** and covering the resultant substrate having the semiconductor layer **516**. Also, source and drain electrodes **526** and **528** are formed to respectively connect with the semiconductor layer **516** through the first and second semiconductor layer contact holes **522a** and **522b**.

Additionally, a passivation layer **532** including the drain contact hole **530** is formed on the resultant substrate having the source and drain electrodes **526** and **528**. Also, the pixel electrode **534** is formed on the passivation layer **532** to connect with the drain electrode **528** through the drain contact hole **530**. The drain contact hole **530** and the gate contact hole (not shown in FIG. 10A, but referring to a reference numeral **539** of FIG. 10B) are simultaneously formed using one mask.

Additionally, as shown in FIG. 10B taken along line IV-IV' of FIG. 9, the buffer layer **514** is formed on the whole insulating substrate **500**, and the gate electrode **520** is formed on the buffer layer **514**.

Further, the gate insulating layer **518** is formed on the resultant substrate having the gate electrode **520**, and the interlayer insulating layer **524** is formed on the gate insulating layer **518**. Also, the passivation layer **532** is formed on the interlayer insulating layer **524**.

Additionally, the gate redundancy line **529** is formed to connect with the gate electrode **520** through the gate contact hole **539** formed passing through the passivation layer **532**, the interlayer insulating layer **524** and the gate insulating layer **518**. The gate redundancy line **529** is formed at the same time as the pixel electrode and formed of the same material.

Accordingly, the present invention can, by the gate redundancy line, prevent the gate electrode and the gate line from being disconnected thereby providing improved image quality in the liquid crystal display. The fabrication method of the liquid crystal display including the bottom-gate type thin film transistor according to the present invention is similar with those of the first and second embodiments.

Further, in the above-described embodiments according to the present invention, the method is described in which, when the source and drain electrodes are formed, the same material is used to form the gate redundancy line, or when the pixel electrode is formed, the same material is used to form the gate redundancy line. However, in the present invention, a dual gate redundancy line can be formed in which, when the source and drain electrodes are formed, a first gate redundancy line is formed, and when the pixel electrode is formed, a second gate redundancy line is overlapped to be formed on the first gate redundancy line.

Also, as shown in FIGS. 11A to 11D, in the array substrate for the liquid crystal display according to the present invention, various types of contact holes may be realized which are provided on the gate electrode and/or the gate line and on which the gate redundancy line is formed.

In other words, as shown in FIG. 11A, the contact hole **639** for connection of a gate redundancy line **629** may be formed only on a gate electrode **620**. Additionally, as shown in FIG. 11B, the contact hole **639** for connection of the gate redundancy line **629** may be formed only on the gate line **611**. Further, as shown in FIG. 11C, the contact hole **639** for connection of the gate redundancy line **629** may also be formed all on the gate electrode **620** and the gate line **611**.

15

Furthermore, as shown in FIG. 11D, the contact holes 639 for connection of the gate redundancy line 629 may be formed in not all gate redundancy line 629 forming regions, but only in partial regions.

The above various types of contact holes may be applied to all of the top-gate type liquid crystal displays and the bottom-gate type liquid crystal displays. Here, numerals 612 and 626 and 628 respectively designate the data line, the source electrode and the drain electrode.

As described above, in the present invention, when the source and drain electrode or the pixel electrode, the gate redundancy line is formed so as to further form a second metallic film on the gate metal. Accordingly, the present invention may lower the resistance of the gate electrode and the gate line and prevent the gate electrode and the gate line from being disconnected, thereby improving the response speed and the image quality of the liquid crystal display.

Further, the present invention has an advantage of, when the source and drain electrode or the pixel electrode are simultaneously formed, the gate redundancy line is formed thereby increasing a manufacturing efficiency by reducing the number of individual masking processes needed.

It will be apparent to those skilled in the art that various modifications and variation can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An array substrate for a liquid crystal display, the array substrate comprising:

- a substrate;
- a plurality of gate lines and a plurality of thin film transistors each having a gate electrode, a source electrode, a drain electrode and an active layer formed over the substrate;
- an interlayer insulating layer formed on the thin film transistors;
- a first gate redundancy line internal to the display formed on the interlayer insulating layer, and connected electrically with just one of the gate electrodes, one of the gate lines, and both gate electrode and gate line through a first gate contact hole and formed of the same material as one of the source and drain electrodes;
- a passivation layer provided on the first gate redundancy line and the interlayer insulating layer;
- a pixel electrode electrically connected with the drain electrode through the drain contact hole formed in the passivation; and
- a second gate redundancy line internal to the display formed on the passivation layer, and connected electrically with the first gate redundancy line through a second gate contact hole.

2. The array substrate according to claim 1, wherein the thin film transistor is a top-gate thin film transistor.

3. The array substrate according to claim 2, wherein the first gate contact hole is formed passing through the interlayer insulating layer.

4. The array substrate according to claim 1, wherein the thin film transistor is a bottom-gate thin film transistor.

5. The array substrate according to claim 4, wherein the first gate contact hole is formed passing through the gate insulating layer and the interlayer insulating layer.

6. The array substrate according to claim 1, wherein the second redundancy line is formed of the same material as the pixel electrode.

16

7. The array substrate according to claim 1, wherein the first gate redundancy line electrically connects with a gate line through a second gate contact hole.

8. An array substrate for a liquid crystal display, the array substrate comprising:

- a substrate;
- a plurality of gate lines and a plurality of thin film transistors each having a gate electrode, a source electrode, a drain electrode and an active layer formed on the substrate;
- an interlayer insulating layer formed on the thin film transistors;
- a passivation layer formed on the interlayer insulating layer;
- a pixel electrode electrically connected with the drain electrode through a drain contact hole formed in the passivation layer; and
- a gate redundancy line internal to the display formed on the passivation layer, and connected electrically with just one of the gate electrodes, the gate lines, and both gate electrode and gate line through a gate contact hole and formed of the same material as the pixel electrode, wherein the gate contact hole is formed passing through the interlayer insulating layer and passivation layer.

9. The array substrate according to claim 8, wherein the thin film transistor is a top-gate thin film transistor.

10. The array substrate according to claim 8, wherein the thin film transistor is a bottom-gate thin film transistor.

11. The array substrate according to claim 10, wherein the gate contact hole is formed passing through the gate insulating layer, the interlayer insulating layer, and the passivation layer.

12. The array substrate according to claim 8, wherein the gate redundancy line electrically connects with a gate line through a second gate contact hole.

13. A method of fabricating an array substrate for a liquid crystal display, the method comprising:

- forming a plurality of gate lines and gate electrodes on a substrate;
- forming an interlayer insulating layer on the gate lines and the gate electrodes;
- forming a plurality of thin film transistors with the gate electrodes, source electrodes, drain electrodes, and active layers;
- forming a first gate redundancy line internal to the display on the interlayer insulating layer electrically connected with just one of the gate electrodes, the gate lines, and both the gate electrode and gate line through a first gate contact hole;
- forming a passivation layer on the first gate redundancy line and the interlayer insulating layer;
- forming a drain contact hole in the passivation layer, and forming a pixel electrode connected electrically with the drain electrode through the drain contact hole; and
- forming a second gate redundancy line internal to the display on the passivation layer connected electrically with the first gate redundancy line through a second gate contact hole.

14. The fabrication method according to claim 13, wherein the first gate redundancy line is formed with the same process and of the same material as one of the source electrode and drain electrode.

15. The fabrication method according to claim 13, wherein the thin film transistor having the gate electrode and the source electrode, and the drain electrode is formed in a top-gate manner.

17

16. The fabrication method according to claim 15, wherein the first gate contact hole is formed passing through the interlayer insulating layer.

17. The fabrication method according to claim 13, wherein thin film transistor having the gate electrode and the source electrode, and the drain electrode is formed in a bottom-gate manner.

18. The fabrication method according to claim 17, including forming a gate insulating layer between the gate electrode and the active layer, wherein the first gate contact hole is formed passing through the gate insulating layer and the interlayer insulating layer.

19. The fabrication method according to claim 13, wherein the second gate redundancy line is formed in the same process and of the same material as the pixel electrode.

20. The fabrication method according to claim 13, wherein the second gate contact hole is formed passing through the passivation layer on the first gate redundancy line.

21. The fabrication method according to claim 13, further comprising forming a second gate contact hole wherein the first gate redundancy line electrically connects with the gate line through the second gate contact hole.

22. A method of fabricating an array substrate for a liquid crystal display, the method comprising:

forming a plurality of gate lines and gate electrodes on a substrate;

forming an interlayer insulating layer on the gate line and the gate electrode;

18

forming a plurality of thin film transistors with gate electrodes, source electrodes, drain electrodes, and active layers;

forming a passivation layer on the interlayer insulating layer and the thin film transistors; and

forming a gate contact hole in the passivation layer, and forming a gate redundancy line internal to the display connected electrically with just one of the gate electrodes, the gate lines, and both gate electrode and gate line through the gate contact hole,

wherein the gate redundancy line is formed with the same process and the same material as the pixel electrode.

23. The fabrication method according to claim 22, wherein the thin film transistor is formed in a top-gate manner.

24. The fabrication method according to claim 23, wherein the gate contact hole is formed passing through the interlayer insulating layer and passivation layer.

25. The fabrication method according to claim 22, wherein the thin film transistor is formed in a bottom-gate manner.

26. The fabrication method according to claim 25, including forming a gate insulating layer between the gate electrode and the active layer, wherein the gate contact hole is formed passing through the gate insulating layer, the interlayer insulating layer, gate insulating layer and the passivation layer.

27. The fabrication method according to claim 22, further comprising forming a second gate contact hole in the passivation layer and interlayer insulating layer wherein the gate redundancy line electrically connects with the gate line through a second gate contact hole.

* * * * *

专利名称(译)	用于液晶显示器的阵列基板及其制造方法		
公开(公告)号	US7471350	公开(公告)日	2008-12-30
申请号	US10/663774	申请日	2003-09-17
[标]申请(专利权)人(译)	LEE KYOUNG MOOK NAM HEE SEUNG OH JAE YOUNG		
申请(专利权)人(译)	LEE KYOUNG MOOK NAM HEE SEUNG OH JAE YOUNG		
当前申请(专利权)人(译)	LG.显示CO. , LTD.		
[标]发明人	LEE KYOUNG MOOK NAM SEUNG HEE OH JAE YOUNG		
发明人	LEE, KYOUNG MOOK NAM, SEUNG HEE OH, JAE YOUNG		
IPC分类号	G02F1/136 G02F1/1343 G02F1/1362		
CPC分类号	G02F1/136286 G02F1/136227 G02F1/136277		
审查员(译)	NGUYEN , 龚便T.		
优先权	1020030040394 2003-06-20 KR		
其他公开文献	US20040257487A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种用于液晶显示器的阵列基板，包括：基板；栅极线和薄膜晶体管，具有在基板上形成的栅电极，源电极，漏电极和有源层；形成在薄膜晶体管上的层间绝缘层；第一栅极冗余线，形成在层间绝缘层上，并通过第一栅极接触孔与栅极和栅极线之一电连接，并由与源极和漏极相同的材料形成；钝化层设置在第一栅极冗余线和层间绝缘层上；像素电极通过形成在钝化层中的漏极接触孔与漏极电连接。

