



US 20070070279A1

(19) **United States**(12) **Patent Application Publication**
Sugiyama et al.(10) **Pub. No.: US 2007/0070279 A1**(43) **Pub. Date: Mar. 29, 2007**(54) **LIQUID CRYSTAL DISPLAY DEVICE**(52) **U.S. Cl. 349/139**(75) Inventors: **Hiroki Sugiyama**, Tottori-shi (JP);
Shinichiro Nomura, Tottori-shi (JP);
Takayuki Kato, Tottori-shi (JP);
Satoshi Morita, Tottori-shi (JP)(57) **ABSTRACT**Correspondence Address:
**WESTERMAN, HATTORI, DANIELS &
ADRIAN, LLP**
1250 CONNECTICUT AVENUE, NW
SUITE 700
WASHINGTON, DC 20036 (US)(73) Assignee: **SANYO EPSON IMAGING DEVICES
CORP.**, Tokyo (JP)(21) Appl. No.: **11/523,629**(22) Filed: **Sep. 20, 2006**(30) **Foreign Application Priority Data**Sep. 26, 2005 (JP) 2005-278287
Apr. 28, 2006 (JP) 2006-124918**Publication Classification**(51) **Int. Cl.**
G02F 1/1343 (2006.01)

A liquid crystal display device of the present invention comprises an array substrate **11** equipped with signal lines **33** and scan lines **32** deployed in a matrix arrangement, thin film transistors (TFTs) **34** provided near the intersections of the signal lines **33** and scan lines **32**, and pixel electrodes **40** of which one is provided in each of the pixel domains delimited by the signal lines **33** and scan lines **32**; a color filter substrate **12** on which are formed color filters **22R** to **22B** and common electrodes **23**; and a liquid crystal layer **13** placed between said two substrates; wherein the pixel electrodes **40** are positioned so as not to overlap the signal lines **33**, or not to overlap the scan lines **32**, or not to overlap either, when viewed from above, and below the spaces between adjacent pixel electrodes **40**, resin black matrices **45** are deployed so as to overlap the pixel electrodes **40** when viewed from above. These features allow a liquid crystal display device to be provided that can prevent light leakage from the peripheral portions of the scan lines and signal lines, as well as curb display defects such as crosstalk, and that additionally achieves efficient power consumption.


10A

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9








Fig. 10





Fig. 12



LIQUID CRYSTAL DISPLAY DEVICE

FIELD OF THE INVENTION

[0001] The present invention relates to a liquid crystal display device. In particular it relates to a liquid crystal display device in which the electrostatic capacitance generated between the scan lines and signal lines on the one hand, and the pixel electrodes and common electrodes on the other, is reduced, so that display faults are prevented and power consumption is lowered.

BACKGROUND OF THE INVENTION

[0002] Over recent times the use of liquid crystal display devices has spread rapidly not only in information and telecommunications equipment but in electronic equipment in general. Since these liquid crystal display devices do not themselves emit light, most such devices in use are of the transmissive type that has a backlight provided at the back of a substrate.

[0003] An ordinary transmissive liquid crystal display device of the related art will now be described with reference to FIGS. 5 and 6. FIG. 5 is a schematic plan view showing in close-up a single pixel portion of the related art liquid crystal display device as seen through the color filter substrate, while FIG. 6 is a cross-sectional view on line VI-VI in FIG. 5.

[0004] The related art liquid crystal display device 10A of FIGS. 5 and 6 is composed of an array substrate 11, a color filter substrate 12, and a liquid crystal layer 13 provided between those two substrates. The array substrate 11 comprises: a transparent substrate 31 of glass or similar; multiple scan lines 32 and signal lines 33 that are constituted of conductive substances and are arranged in grid form on the surface of the transparent substrate 31; thin film transistors ("TFTs" below) 34 that are provided close to the intersections of the scan lines 32 and signal lines 33 and serve as switching elements; multiple storage capacitor electrodes 36 that are constituted of a conductive substance and are provided between the scan lines 32 so as to be almost parallel with the scan lines 32; a gate insulator 37 that covers the scan lines 32 and the storage capacitor electrodes 36 and is constituted of inorganic insulator; a protective insulator 38 that covers the signal lines 33 and the TFTs 34 and is constituted of inorganic insulator; an interlayer 39 that is provided over the protective insulator 38 and is constituted of organic insulation film; and pixel electrodes 40 constituted of indium tin oxide (ITO) or similar, which are provided over the interlayer 39, and each of which is positioned so as to cover one of the domains corresponding to one pixel that are enclosed by the scan lines 32 and signal lines 33.

[0005] The TFTs 34 are each composed of: a source electrode S that branches off from a signal line 33; a gate electrode G that branches off from a scan line 32; a drain electrode D that is connected to the pixel electrode 40; and a silicon layer 35 that is constituted of polysilicon (p-Si), amorphous silicon (a-Si) or the like. The pixel electrode 40 is connected to the drain electrode D via a contact hole 41 provided in the interlayer 39 located over the storage capacitor electrode 36.

[0006] The color filter substrate 12 comprises: a transparent substrate 21 constituted of glass or similar; black matri-

ces (not shown in the drawings) that are constituted of chromium metal or similar and are formed as a grid on the surface of the transparent substrate 21; color filters 22R, 22G, 22B constituted of red (R), green (G) and blue (B) etc., each of which is provided in one of the domains delimited by the black matrices; and common electrodes 23 that are constituted of ITO or the like and provided over the color filters 22R, 22G, 22B. To manufacture the liquid crystal display device 10A, the two substrates 11 and 12 are positioned with their surfaces opposing each other, their like outer edges are stuck together by means of seal material (not shown in the drawings), spacers 14 are placed in the resulting interior space, and such space is filled with liquid crystal, thus forming a liquid crystal layer.

[0007] Such a liquid crystal display device is for example set forth in Japanese Laid-Open Patent Publication 2001-188256, which includes techniques for rendering the device's aperture ratio higher. One such technique that has long been publicly known, called "field shield pixel" (FSP) or similar term, enlarges the pixel electrode domains in order to raise the aperture ratio, and involves covering the TFTs over with an organic insulative film and flattening the entire surface prior to formation of the pixel electrodes.

[0008] FIG. 7 is a cross section on the line VII-VII in FIG. 5. As FIG. 7 shows, in a related art liquid crystal display device 10A the side and end portions of the pixel electrodes 40, each of which covers a domain corresponding to one pixel, are formed so as to overlap the scan lines 32 and signal lines 33 as viewed from above. The purpose of such overlapping of the pixel electrodes 40 with the scan lines 32 and signal lines 33 is to prevent light leakage from such join portions; more precisely, to prevent light leakage from occurring when light from the backlight of the liquid crystal display device 10A passes through the liquid crystal layer at the portions where the orientation of the crystals is disturbed due to the application of voltage at the pixel electrodes' edges. The scan lines 32 and signal lines 33 normally have an identical width L_1 which is approximately 8 μm , while the width L_2 of the overlaps with the pixel electrodes 40 is approximately 2 μm in each case.

[0009] However, if the pixel electrodes are formed over the scan lines and signal lines, certain electrostatic capacitances C_{sd} , C_{gd} will be present between the scan lines 32 and signal lines 33 on the one hand and the pixel electrodes 40 on the other, as shown in FIG. 7. If such electrostatic capacitances C_{sd} , C_{gd} exceed a certain level, crosstalk will occur in the display screen when the liquid crystal display device 10A is driven. Crosstalk is particularly liable to occur around black displays which are displayed on a white background. The occurrence mechanism of such crosstalk is thought to be due to reasons such as described below. Namely, FIG. 8 shows a screen in which crosstalk has occurred, in a liquid crystal display device 10A such as shown in FIGS. 5 to 7. In FIG. 8 a black screen is displayed on a white background, with a point within the white background domain being labeled "X" and points within the domains above and below the black screen, that is, lying on the signal lines, labeled "Y". The voltage waveforms at such points X and Y are shown in FIG. 9.

[0010] As FIG. 9 shows, when a signal is applied to the gate electrode of a TFT, the TFT is driven and writing into the pixel electrode begins. When this happens, the potential

of the pixel electrode is maintained for a certain period by the capacitance of the auxiliary electrode (refer to FIG. 9A). The potential for the white display that is written into the pixel electrode during the write period rises and falls together with the amplitude of the opposing electrode potential V_{com} throughout the hold period (refer to FIG. 9B). Observing the waveforms of the voltages applied in this state to the signal lines and pixel electrodes at points X and Y, it can be seen that voltage for the white display is continuously applied to the signal lines at the point X portion up until the next write period comes, and that the potential of the pixel electrodes at such point X portion rises and falls with the same amplitude up until the next write period comes (refer to FIGS. 9C and 9D).

[0011] If, mid-way through such process, voltage for a black display is applied to the signal lines at the point Y portion, the amplitude of the pixel electrode's potential at the Y point portion will vary, and will continue to do so for as long as such voltage is applied to such signal lines (refer to FIG. 9E). As a result, the effective value of the voltage applied to the liquid crystals will differ at points X and Y, giving rise to a difference ΔV which will manifest as a difference in brightness and cause crosstalk to occur (refer to FIG. 9F).

[0012] Thus, in a related art liquid crystal display device 10A such as described above there is the problem that crosstalk occurs as a result of the electrostatic capacitance C_{gd} that arises between the scan lines 32 and pixel electrodes 40 and the electrostatic capacitance C_{sd} that arises between the signal lines 33 and pixel electrodes 40. To resolve this problem, one can increase the capacitance of the capacitor that is constituted by the portion of overlap between the storage capacitor electrode 36 and the drain electrode D of the TFT 34, in other words the storage capacitor that serves as signal hold capacitance for activation of the active matrix, thereby permitting the electrostatic capacitances C_{gd} and C_{sd} to be ignored. But in order to increase the storage capacitor it will be necessary to enlarge the area of the storage capacitor electrode 36, which will give rise to the further problem of a fall in the aperture ratio of each pixel, since the storage capacitor electrode 36 is composed of a light-blocking conductive substance.

[0013] Furthermore, in the related art liquid crystal display device 10A there is also formed an electrostatic capacitance C_{sc} between the signal lines 33 of the array substrate 11 and the common electrodes 23 of the color filter substrate 12 when the array substrate 11 and the color filter substrate 12 are superposed on each other. Likewise, an electrostatic capacitance is formed between the scan lines 32 and the common electrodes 23. Terming such capacitance C_{gc} , the equivalent circuits for a single pixel of the liquid crystal display device 10A may be represented as in FIG. 10.

[0014] As FIG. 10 shows, the electrostatic capacitances C_{sc} and C_{gc} exert an adverse effect on the opposing electrode potential V_{com} . More specifically, there exists the problem that electrical power is consumed by these electrostatic capacitances C_{sc} and C_{gc} , with the result that the power consumption of the liquid crystal display device 10A increases.

[0015] Moreover, the TFTs used in the liquid crystal display device have the property that when light is shone on them a faint electric current flows through them. When

generated, such faint current causes hindrance of the TFT ON/OFF control. In the related art liquid crystal display devices therefore, black matrices for preventing extraneous light from being shone onto the TFTs are deployed over the color filter substrate so as to overlap the TFTs when viewed from above, with the purpose of preventing light leakage to the TFTs. By such means it is possible to curb to a certain extent the shining of extraneous light onto the TFT, but the fact that black matrices are provided over the color filter substrate means that relatively wide gaps are formed between that substrate and the TFTs, with the result that entry of extraneous light from oblique directions cannot be prevented. A further problem is that light from the backlight will shine onto the black matrices, constituted of chromium metal or the like, where some of such light will be reflected and shone onto the TFTs, resulting in light leakage to the TFTs.

SUMMARY OF THE INVENTION

[0016] In view of the foregoing problems, the present inventors conducted many and various investigations into liquid crystal display devices that could prevent light leakage and flicker at the peripheral portions of the scan lines and signal lines, as well as curb to a good degree the generation of electrostatic capacitance between the signal and scan lines and the pixel electrodes; as a result they arrived at the present invention when they discovered that by forming over the signal lines and scan lines resin black matrices that are broader than the signal lines and scan lines it is possible to eliminate the occurrence of light leakage without making the pixel electrodes overlap the scan lines and signal lines, and furthermore the implementation of light blockage between the pixels via the scan lines and signal lines will not be necessary, so that the scan lines and signal lines can be made narrower, which will curb the electrostatic capacitance that arises between the scan and signal lines and the common electrodes.

[0017] Thus the purpose of the present invention is to provide a liquid crystal display device that can prevent light leakage from the peripheral portions of the scan lines and signal lines, as well as curb display defects such as crosstalk, and that additionally achieves efficient power consumption.

[0018] In order to resolve the aforementioned problems, a first mode of the present invention is a liquid crystal display device having:

[0019] a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors provided near the intersections of said signal lines and scan lines, and pixel electrodes of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;

[0020] a second substrate on which are formed color filters and common electrodes;

[0021] and

[0022] a liquid crystal layer placed between said two substrates;

[0023] and with the features that said pixel electrodes are positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said

pixel electrodes, resin black matrices are deployed so as to overlap said pixel electrodes when viewed from above.

[0024] Another feature of the liquid crystal display device of the aforementioned first mode is that the width of said signal lines or said scan lines, or both, is 3 to 5 μm , and the width of said resin black matrices 6 to 10 μm .

[0025] A further feature of the liquid crystal display device of the aforementioned first mode is that said resin black matrices are embedded in an interlayer that is provided above said signal lines and scan lines and below the spaces between said pixel electrodes.

[0026] A still further feature of the liquid crystal display device of the aforementioned first mode is that said resin black matrices are also provided over said thin film transistors.

[0027] A yet further feature of the liquid crystal display device of the aforementioned first mode is that an interlayer is provided below said pixel electrodes, and a reflective film is provided in at least part of the space between said pixel electrodes and said interlayer.

[0028] A second mode of the present invention is a liquid crystal display device having:

[0029] a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors provided near the intersections of said signal lines and scan lines, and pixel electrodes of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;

[0030] a second substrate on which are formed color filters and common electrodes;

[0031] and

[0032] a liquid crystal layer placed between said two substrates;

[0033] and with the features that said pixel electrodes are positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said pixel electrodes, insulative light-blocking members are deployed so as to overlap said pixel electrodes when viewed from above.

[0034] Another feature of the liquid crystal display device of the aforementioned second mode is that said light-blocking members are also provided over said thin film transistors.

[0035] A further feature of the liquid crystal display device of the aforementioned second mode is that black matrices are formed on said color filter substrate so as to correspond to said pixel domains.

[0036] A still further feature of the liquid crystal display device of the aforementioned second mode is that said insulative light-blocking members are composed of material that is different from that of said color filter substrate's black matrices.

[0037] A third mode of the present invention is a liquid crystal display device having:

[0038] a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors

provided near the intersections of said signal lines and scan lines, an interlayer that covers said thin film transistors, and pixel electrodes which lie over said interlayer and of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;

[0039] a second substrate on which are formed color filters and common electrodes;

[0040] and

[0041] a liquid crystal layer placed between said two substrates;

[0042] and with the features that said pixel electrodes are positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said pixel electrodes, insulative light-blocking members are provided so as to extend from the edges of said signal lines or scan lines to the edges of said pixel electrodes.

[0043] Another feature of the liquid crystal display device of the aforementioned third mode is that said light-blocking members are also provided over said thin film transistors.

[0044] A further feature of the liquid crystal display device of the aforementioned third mode is that black matrices are formed on said color filter substrate so as to correspond to said pixel domains.

[0045] A still further feature of the liquid crystal display device of the aforementioned third mode is that said insulative light-blocking members are composed of material that is different from that of said color filter substrate's black matrices.

[0046] Thanks to possessing the structure above, the present invention yields outstanding effects that will now be described. Namely, although according to each of the modes of the present invention the pixel electrodes are positioned so as not to overlap the signal lines and scan lines, there will occur no light leakage between the pixel electrodes since resin black matrices or insulative light-blocking members are formed below the spaces between the adjacent pixel electrodes so as to overlap the pixel electrodes. That is, whereas in the related art liquid crystal display devices the signal lines and pixel electrodes are made to overlap so that light will not leak at the peripheral portions of the signal lines, etc., and light is thereby prevented from being reflected by the disturbed-orientation liquid crystals that occur at the end portions of the pixel electrodes, in the present invention the light-blocking is satisfactorily effected by means of resin black matrices or insulative light-blocking members instead of the signal lines and scan lines, so that there is no need to form the pixel electrodes so as to overlap the signal lines and scan lines viewed from above. By such means it is possible to curb electrostatic capacitance to a good degree, in particular the electrostatic capacitance C_{sd} that arises between the pixel electrodes and the signal lines, which is the electrostatic capacitance that causes crosstalk to occur. As a result, crosstalk and other display defects can be curbed without enlarging the area of the storage capacitor electrodes which constitute the storage capacitor that serves as signal hold capacitance. Further, the fact that such electrostatic capacitance can be curbed means that the electrical power that such electrostatic capacitance consumes can also be curbed, so that a liquid crystal display device with

reduced power consumption can be provided. The fact that various signals are applied to the signal lines means that the electrostatic capacitance C_{sd} arising between the signal lines and the pixel electrodes will tend to be greater than that arising between the scan lines and the pixel electrodes. Therefore, the resin black matrices should be provided over the signal lines at least. This is because the scan lines are solely for supplying ON/OFF signals to the TFTs and therefore have capacitance that is not particularly large. If however the resin black matrices are also provided over the scan lines, then display defects will not arise there either, and moreover it will be possible to reduce electrostatic capacitance between the scan lines and pixel electrodes and between the scan lines and common electrodes, thus permitting realization of a liquid crystal display device with even lower power consumption.

[0047] In the aforementioned first mode the signal lines and scan lines, which in the related art required a width of 8 μm in order to assure light blockage, no longer need to be light-blocking, and consequently may be made narrower, with a width of 3 to 5 μm , preferably 4 μm . As an inevitable result, the electrostatic capacitance occurring between such narrowed signal and scan lines on the one hand and the common electrodes on the other will be lessened, which will enable realization of a liquid crystal display device with even higher-efficiency power consumption. Further, the signal lines' and scan lines' role of blocking light between the pixel electrodes is taken over by the resin black matrices, whose width will be from 6 to 10 μm , preferably 8 μm identical with the width of the related art signal and scan lines, so that there will be no risk of the light blockage being inferior to the related art level.

[0048] In the aforementioned first mode the fact that the resin black matrices are embedded inside the interlayer permits the thickness of the interlayer to be the same as in the related art, so that there is no risk that the liquid crystal display device itself will be thick. Further, being thus surrounded with organic or inorganic insulative film, the resin black matrices will not be subject to any adverse electrical charge effects from the various lines.

[0049] In each of the aforementioned modes the provision of resin black matrices or light-blocking members between the pixel electrodes curbs light leakage, etc., on the wiring lines, and if resin black matrices or light-blocking members are also provided on the TFTs, then light leakage to the TFTs can also be reliably prevented. More precisely, the distance between the black matrices and the TFTs will be extremely small compared to when the black matrices are provided over the color filter substrate as in the related art; hence there will be almost no entry of extraneous light from oblique directions, and almost no light from the backlight will be shone onto the TFTs via reflection at the resin black matrices. This will make it possible to curb the occurrence of flicker to a good degree. The resin black matrices or light-blocking members provided over the TFTs can use the same materials as the resin black matrices or light-blocking members described earlier, and in that case will preferably be formed in the same process as the resin black matrices or light-blocking members provided between the pixel electrodes, since this will obviate an increase in manufacturing processes.

[0050] The liquid crystal display device of the aforementioned first mode is not limited to being of the transmissive

type; it could for example be a semitransmissive liquid crystal display device if a reflective film is formed over the light-blocking portions, where the storage capacitor electrode and TFT, etc., are formed, within each pixel domain, or it could be a reflective liquid crystal display device if a reflective film is formed over the whole of each pixel domain. In any of these cases the liquid crystal display device that is provided will have high-efficiency power consumption and curbed display defects, thanks to possessing the foregoing structure.

BRIEF DESCRIPTION OF THE DRAWINGS

[0051] FIG. 1 is a schematic plan view illustrating in close-up a single pixel portion of the liquid crystal display device of an embodiment of the present invention as seen through the color filter substrate.

[0052] FIG. 2 is a cross-sectional view along line II-II in FIG. 1.

[0053] FIG. 3 is a cross-sectional view along line III-III in FIG. 1.

[0054] FIG. 4 is a cross-sectional view along line IV-IV in FIG. 1.

[0055] FIG. 5 is a schematic plan view illustrating in close-up a single pixel portion of a related art liquid crystal display device as seen through the color filter substrate.

[0056] FIG. 6 is a cross-sectional view along line VI-VI in FIG. 5.

[0057] FIG. 7 is a cross-sectional view along line VII-VII in FIG. 5.

[0058] FIG. 8 illustrates a screen in which crosstalk has occurred.

[0059] FIG. 9 is a set of graphs illustrating the voltage waveforms at various points in a liquid crystal display device when crosstalk occurs.

[0060] FIG. 10 is a diagram illustrating the equivalent circuits of a single pixel portion of a related art liquid crystal display device.

[0061] FIG. 11 is a schematic plan view illustrating in close-up a single pixel portion of the liquid crystal display device of another embodiment of the present invention as seen through the color filter substrate.

[0062] FIG. 12A is a cross-sectional view along line XII-XII in FIG. 11, and FIG. 12B is a cross-sectional view through a related art liquid crystal display device.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0063] Preferred embodiments of the present invention will now be described with reference to the drawings. It should however be understood that the embodiments below represent merely illustrative instances of liquid crystal display devices for realizing the technical thought of the present invention; these embodiments are not intended to limit the present invention to these particular liquid crystal display devices. Adaptations could yield other embodiments equally valid within the scope of the claims.

Embodiment 1

[0064] FIG. 1 is a schematic plan view illustrating in close-up a single pixel portion of the liquid crystal display device of an embodiment of the present invention as seen through the color filter substrate; FIG. 2 is a cross-sectional view along line II-II in FIG. 1; FIG. 3 is a cross-sectional view along line III-III in FIG. 1; and FIG. 4 is a cross-sectional view along line IV-IV in FIG. 1. Those parts of the liquid crystal display device 10 described below that are structurally similar to the corresponding parts of the related art liquid crystal display device 10A are assigned the same reference numerals.

[0065] As shown in FIGS. 1 and 2, a liquid crystal display device 10 of the present invention is composed of an array substrate 11, a color filter substrate 12, and a liquid crystal layer 13 provided between those two substrates. The array substrate 11 comprises:

[0066] a transparent substrate 31 of glass or similar;

[0067] multiple scan lines 32 and signal lines 33 that are constituted of a conducting substance and are arranged in grid form on the surface of the transparent substrate 31;

[0068] TFTs 34 that are provided close to the intersections of the scan lines 32 and signal lines 33 and serve as switching elements;

[0069] multiple storage capacitor electrodes 36 that are constituted of a conductive substance and are provided between the scan lines 32 so as to be almost parallel with the scan lines 32;

[0070] a gate insulator 37 that is constituted of inorganic insulator and covers the scan lines 32 and the storage capacitor electrodes 36;

[0071] a protective insulator 38 that is constituted of inorganic insulator and covers the signal lines 33 and the TFTs 34;

[0072] an interlayer 39 that is constituted of organic insulation film and is provided over the protective insulator 38;

[0073] pixel electrodes 40 constituted of ITO or similar which are provided over the interlayer 39, and each of which is positioned so as to cover one of the domains corresponding to one pixel that are enclosed by the scan lines 32 and signal lines 33; and

[0074] resin black matrices 45, 46 that are embedded into the interlayer 39 over the scan lines 32 and signal lines 33.

[0075] The TFTs 34 are each composed of:

[0076] a source electrode S that branches off from a signal line 33;

[0077] a gate electrode G that branches off from a scan line 32;

[0078] a drain electrode D that is connected to a pixel electrode 40; and

[0079] a silicon layer 35 that is constituted of polysilicon (p-Si), amorphous silicon (a-Si) or the like;

[0080] the pixel electrode 40 being connected to the drain electrode D via a contact hole 41 provided in the interlayer 39 located over the storage capacitor electrode 36.

[0081] In FIG. 1 the hatched portions are the resin black matrices 45, 46, which are constituted of resin material possessing light-blocking ability and are formed in grids so as to align with the scan lines 32 and signal lines 33, the signal line resin black matrix 45 being formed over the signal lines 33 and the scan line resin black matrix 46 being formed over the scan lines 32. In the present embodiment the widths of the scan lines 32 and signal lines 33 are equal, which means that the resin black matrices 45, 46 will also have equal width, preferably 6 to 10 μm , more preferably 8 μm , while the width of the scan lines 32 and signal lines 33 will preferably be 3 to 5 μm , more preferably 4 μm .

[0082] The color filter substrate 12 is composed of: a transparent substrate 21 constituted of glass or similar; black matrices (not shown in the drawings) that are constituted of chromium metal or similar and are formed in a grid on the surface of the transparent substrate 21; color filters 22R, 22G, 22B constituted of red (R), green (G) and blue (B) etc., each of which is provided in one of the domains delimited by the black matrices; and common electrodes 23 that are constituted of ITO or the like and provided over the color filters 22R, 22G, 22B. To manufacture the liquid crystal display device 10, the two substrates 11 and 12 are positioned with their surfaces opposing each other, their like outer edges are stuck together by means of seal material (not shown in the drawings), spacers 14 are placed in the resulting interior space, and such space is filled with liquid crystal, thus forming a liquid crystal layer.

[0083] Next, the manufacturing process for the array substrate 11 of the liquid crystal display device 10 of the present invention will be described.

[0084] First of all, a film of a conductive substance constituted of aluminum, molybdenum, chromium or an alloy of these is formed with a particular thickness on the transparent substrate 31. Then by means of patterning using a publicly-known photolithographic method, parts of such film are etched away so as to form multiple scan lines 32 of width 4 μm that extend in the horizontal direction, and storage capacitor electrodes 36 in between the multiple scan lines 32. These storage capacitor electrodes 36 are of what is called the Cs On Common type, whereby adjacent electrodes are linked by narrow linking wires.

[0085] Next, a gate insulator 37 of a particular thickness is formed so as to cover the transparent substrate 31, on which the scan lines 32 and storage capacitor electrodes 36 were formed in the above process. For this gate insulator 37, a transparent resin material constituted of silicon nitride or similar will be used. Then a semiconductor layer of for example a-Si is formed over the gate insulator 37. Following that, the a-Si layer is etched away, leaving portions that will cover the gate electrodes G to be projected from the scanning lines 32, and thus is formed a silicon layer 35 that will serve as part of the TFTs 34. Next, using methods similar to the foregoing, there are formed multiple signal lines 33 of width 4 μm in a direction orthogonal to the scan lines 32, source electrodes S that project from the signal lines 33 and are connected to the silicon layer 35, and drain electrodes D which cover over the storage capacitor electrodes 36 and of which one edge is connected to the silicon layer 35. As a result, TFTs 34 that will serve as switching elements are formed close to the intersections of the transparent substrate 31's scan lines 32 and signal lines 33. Further, a protective

insulator **38** for surface stabilization, around 0.1 to 0.5 μm thick and constituted of inorganic insulative material, is formed over the transparent substrate **31** so as to cover the various wiring lines, by means of the CVD method.

[0086] Next, resin black matrices **45, 46** are formed above the scan lines **32** and signal lines **33** so as to cover the scan lines **32** and signal lines **33**. The resin black matrices **45, 46** have a width of 8 μm and are formed so that the scan lines **32** and signal lines **33**, being located below the resin black matrices **45, 46**, will be invisible from above (refer to FIGS. 3 and 4).

[0087] Following the above, an interlayer **39**, constituted of organic insulative material, for flattening the surface of the array substrate **11** is formed over the whole surface of that substrate by means of the spin coating method. The interlayer **39** is roughly 2.0 to 3.0 μm thick at the thickest places. In this forming stage, the interlayer **39** is formed so that the resin black matrices **45, 46** become embedded in the interior thereof. Furthermore, in the portions of the interlayer **39** that are located above the storage capacitor electrodes **36** there are provided contact holes **41** for electrically connecting the pixel electrodes **40** to be described later to the drain electrodes **D**. The position of these holes is not limited to being above the storage capacitor electrodes **36**. However, when the array substrate **11** and the color filter substrate **12** are stuck together to produce the liquid crystal display device **10**, the distance between the two substrates will be different at the portions where the contact holes **41** are formed from what it is at the other portions, and this poses hazard of unevenness in the display quality. Accordingly, the holes will preferably be provided over the storage capacitor electrodes **36**, which are of a light-blocking material.

[0088] Next, a pixel electrode **40** constituted of, for example, ITO is formed in each of the pixel domains enclosed by the scan lines **32** and signal lines **33**. The outer edges of each pixel electrode **40** are positioned so as not to overlap the adjacent scan lines **32** or signal lines **33** when viewed from above, and moreover so as to lie over the resin black matrices **45, 46**. With the foregoing processes, manufacture of the array substrate **11** is complete.

[0089] Thus, according to the liquid crystal display device **10** of the present invention, thanks to the fact that the outer edges of the pixel electrodes **40** are formed so as to overlap the resin black matrices **45, 46**, without overlapping the scan lines **32** and signal lines **33** viewed from above, good light-blocking ability can be secured from the resin black matrices **45, 46**, and the capacitance of the electrostatic capacitors that are produced between the scan lines **32** and signal lines **33** on the one hand, and the pixel electrodes on the other, can be lessened.

[0090] In addition, the scan lines **32** and signal lines **33** can be formed without consideration for light-blocking ability, and therefore can be of smaller width, for example 4 μm , instead of the 8 μm or so in the related art. Because of this it is also possible to reduce the capacitance of the electrostatic capacitors C_{sc} , C_{gc} (refer to FIG. 10) which take as electrodes the scan lines **32**, signal lines **33**, and common electrodes **23**. Thus, the electrical power that such electrostatic capacitance would otherwise consume will be saved, and the liquid crystal display device **10** will operate with highly efficient power consumption.

[0091] Moreover, although in the foregoing embodiment the resin black matrices are provided only between adjacent

pixel electrodes, or more precisely, above the signal lines and scan lines, it will be preferable to provide resin black matrices over the TFTs as well, since this will permit the occurrence of flicker due to light leakage to the TFTs to be curbed to a good degree. Where it is desired also to provide resin black matrices over the TFTs in this way, such should be provided simultaneously with the process that forms the resin black matrices over the signal lines and scan lines. This point will be discussed in more detail under embodiment 2.

Embodiment 2

[0092] FIG. 11 is a schematic plan view illustrating in close-up a single pixel portion of the liquid crystal display device of another embodiment of the present invention as seen through the color filter substrate, while FIG. 12A is a cross-sectional view through the liquid crystal display device of such embodiment of the present invention. Items in embodiment 2 that are the same as those in embodiment 1 are assigned the identical reference numerals. FIG. 11 This cross-sectional view represents a cross-section through the position of a signal line **33** and the position of a TFT **34**, being cut along the line XII-XII in FIG. 11. 12B provides, for the purpose of comparison with embodiment 2, a cross-sectional view through a related art liquid crystal display device at similar positions to those of FIG. 12A.

[0093] In embodiment 2, as in embodiment 1, the signal lines **33** and pixel electrodes **40** are deployed so as not to overlap each other when viewed from above, and below the pixel electrodes **40** there are provided insulative light-blocking members **48** extending from the edges of the signal lines **33** to the edges of the pixel electrodes **40**. Whereas the black matrices **50** on the color filter substrate **12** side were not shown in the drawings for embodiment 1, the drawings for embodiment 2 show such black matrices **50**, which are formed so as to overlap the scan lines **32** and signal lines **33** when viewed from above.

[0094] The insulative light-blocking members **48** might be items similar to the resin black matrices **45** of embodiment 1, and it would be permissible for the insulant to be of a substance such as oxide provided that such had light-blocking ability. But in consideration of the manufacturing and processing aspects, these items will preferably be made of resin.

[0095] Specifically, the insulative light-blocking members **48** will be of an ordinary resin material into which carbon particles coated with acrylic are mixed. Being insulative, these members will preferably have rather high resistance, specifically of $10^{13}\Omega\cdot\text{cm}$ or higher. The members' permittivity will preferably be low; for the sake of reducing unneeded capacitance the permittivity will preferably be no more than 14 F/m, or more preferably, no more than 10 F/m.

[0096] The insulative light-blocking members **48** and the color filter substrate **12** side black matrices **50** are both required to be light-blocking, but are composed of differing materials. The insulative light-blocking members **48** will preferably have light-blocking ability that is as great as possible, but need not necessarily have light-blocking ability on a par with the color filter substrate **12** side black matrices **50**. Normally it will be only or mainly the light-blocking ability of the color filter substrate **12** side black matrices **50** that needs to be considered, as these matrices will be provided more on the transparent substrate **21** side than the

common electrodes **23**, which are formed densely over the entire substrate. Thus, the black matrices **50** will generally be formed by applying a film of chromium metal or similar using the sputtering method. Despite being extremely thin at around 500 Å, these black matrices **50** have extremely great light-blocking ability and thereby prevent, etc., mixing of adjacent hues. The insulative light-blocking members **48**, on the other hand, are located between the signal lines **33** and pixel electrodes **40**, and as previously mentioned, will preferably have not only light-blocking ability but also high resistance together with low permittivity. Thus, for these members the characteristics of their material are more important than for the black matrices **50**, and it will be permissible for the light-blocking ability of such material to be inferior to that of the black matrices **50**.

[0097] As in embodiment 1, the light-blocking members **48** are formed via the spin coating method and patterned into a particular shape. More specifically, in the related art panel shown in FIG. 12B for reference, the light-blocking members **48** are provided not only at the portions where the signal lines and pixel electrodes overlap, but also at the portions above the signal lines **33**. Thus, with the present embodiment there is a drastic reduction in the capacitance that was inevitably generated in the related art at the portions where the signal lines and pixel electrodes overlapped in order to block light, and light leakage near the edge portions of the pixel electrodes, which in the related art was prevented by means of the overlapping between the signal lines and pixel electrodes, can be prevented by means of the light-blocking members **48**.

[0098] Being constituted of resin, the light-blocking members **48** can easily be formed so as to be thick. With a thickness of approximately 1.0 to 1.5 µm, it will be possible also to block effectively the light from the backlight that incidents from oblique directions. Then it will be possible to form the pixel electrodes **40** over the interlayer **39**, which will be formed with a thickness of approximately 2.0 to 3.0 µm so as to cover the thickly-formed light-blocking members **48** and also to render flat the surface of the array substrate **12**, by means of which an increase can be effected in the aperture ratio. Particularly if the light-blocking members **48** are formed to be thick on the array substrate **12** side, it will be possible to block effectively on the array substrate **12** side the oblique-direction light from the backlight and hence there will be little need for concern about light leakage from the backlight on the array substrate **12** side. Neither will there be need for concern about backlight light leakage from the array substrate **12** side as regards the color filter substrate **11** side black matrices **50**. This means that those black matrices **50** can be made thin, with the result that a further improvement in the aperture ratio can be effected.

[0099] According to the above description the light-blocking members **48** are covered over by the interlayer **39**, but alternatively pixel electrodes might be formed over the light-blocking members **48**, instead of providing the interlayer **39** here. However, the interlayer **39**, which is constituted of organic insulation film, has permittivity ϵ of around 4 F/m, whereas the light-blocking members **48** have permittivity that is higher than this. Consequently the structure whereby the light-blocking members **48** are covered over by the interlayer **39** will be more preferable in order to effect a reduction, albeit small, in the unneeded capacitance.

[0100] In embodiment 2, light-blocking members **49** are provided over the TFTs **34**. These light-blocking members **49** are provided using the same materials and in the same process as the light-blocking members **48**. By thus providing light-blocking members **49** over the TFTs also, extraneous light incidenting from oblique directions (indicated by arrows in the drawings) can be blocked by the light-blocking members **49**, as can light from the backlight that is reflected by the color filter substrate **12** side black matrices **50**, which are constituted of chromium metal or the like. Thus, none of such light will be shone onto the TFTs **34**, and light leakage to the TFTs can be prevented. Furthermore, whereas with the related art it was to a certain extent necessary to form the color filter substrate **12** side black matrices **50** so as to cover the TFTs **34** with a fairly broad margin in order to block extraneous light from oblique directions, in embodiment 2 there is no such necessity thanks to the light-blocking members **49**. This means that the color filter substrate **12** side black matrices **50** can be formed to have the same width as the TFTs **34**, or alternatively, the black matrices **50** over the TFTs **34** can be omitted. In either case it will be possible to raise the aperture ratio of the liquid crystal display device **10**.

[0101] The light-blocking members **48** that cover the signal lines **33** are shown in the drawings as being formed in a trapezoidal shape, but nevertheless are not limited to such a shape. The light-blocking members **48** might be formed to extend from the edges of the signal lines **33** to the edges of the pixel electrodes **40**, or a light blocking member **48** might be deployed from one edge of a signal line **33** to a pixel electrode **40**, and separately another light blocking member **48** be deployed from the other edge of the signal line **33** to the pixel electrode **40**, that is, light blocking members **48** might be provided separately on either side of each signal line **33**.

[0102] In order to make the liquid crystal display device **10** of the present invention into a semitransmissive rather than a transmissive one, all that need be done is to form minute concavo-convexities on the surface of the interlayer **39**, except in the places where such film is formed over the apertural portions of the pixel domains, and to form in between such concavo-convex portions and the pixel electrodes **40** a reflective film constituted of a light reflecting material. Where it is desired to turn such liquid crystal display device into a reflective one, it will suffice to form a reflective film over the entire area between the interlayer **39** and the pixel electrodes **40**.

1. A liquid crystal display device comprising:

- a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors provided near the intersections of said signal lines and scan lines, and pixel electrodes of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;
- a second substrate on which are formed color filters and common electrodes; and
- a liquid crystal layer placed between said two substrates; said pixel electrodes being positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said pixel electrodes, resin

black matrices being deployed so as to overlap said pixel electrodes when viewed from above.

2. The liquid crystal display device according to claim 1, wherein the width of said signal lines or said scan lines, or both, is 3 to 5 μm , and the width of said resin black matrices 6 to 10 μm .

3. The liquid crystal display device according to claim 1, wherein said resin black matrices are embedded in an interlayer that is provided above said signal lines and scan lines and below the spaces between said pixel electrodes.

4. The liquid crystal display device according to claim 1, wherein said resin black matrices are also provided over said thin film transistors.

5. The liquid crystal display device according to claim 1, wherein an interlayer is provided below said pixel electrodes, and a reflective film is provided in at least part of the space between said pixel electrodes and said interlayer.

6. A liquid crystal display device comprising:

a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors provided near the intersections of said signal lines and scan lines, and pixel electrodes of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;

a second substrate on which are formed color filters and common electrodes; and

a liquid crystal layer placed between said two substrates; said pixel electrodes being positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said pixel electrodes, insulative light-blocking members being deployed so as to overlap said pixel electrodes when viewed from above.

7. The liquid crystal display device according to claim 6, wherein said light-blocking members are also provided over said thin film transistors.

8. The liquid crystal display device according to claim 6, wherein black matrices are formed on said color filter substrate so as to correspond to said pixel domains.

9. The liquid crystal display device according to claim 8, wherein said insulative light-blocking members are composed of material that is different from that of said color filter substrate's black matrices.

10. A liquid crystal display device comprising:

a first substrate equipped with signal lines and scan lines deployed in a matrix arrangement, thin film transistors provided near the intersections of said signal lines and scan lines, an interlayer that covers said thin film transistors, and pixel electrodes which lie over said interlayer and of which one is provided in each of the pixel domains delimited by said signal lines and scan lines;

a second substrate on which are formed color filters and common electrodes; and

a liquid crystal layer placed between said two substrates;

said pixel electrodes being positioned so as not to overlap said signal lines, or not to overlap said scan lines, or not to overlap either, when viewed from above; and below the spaces between adjacent said pixel electrodes, insulative light-blocking members being provided so as to extend from the edges of said signal lines or scan lines to the edges of said pixel electrodes.

11. The liquid crystal display device according to claim 10, wherein said light-blocking members are also provided over said thin film transistors.

12. The liquid crystal display device according to claim 10, wherein black matrices are formed on said color filter substrate so as to correspond to said pixel domains.

13. The liquid crystal display device according to claim 12, wherein said insulative light-blocking members are composed of material that is different from that of said color filter substrate's black matrices.

* * * * *

专利名称(译)	液晶显示装置		
公开(公告)号	US20070070279A1	公开(公告)日	2007-03-29
申请号	US11/523629	申请日	2006-09-20
申请(专利权)人(译)	三洋爱普生影像设备CORP.		
当前申请(专利权)人(译)	日本展示WEST INC.		
[标]发明人	SUGIYAMA HIROKI NOMURA SHINICHIRO KATO TAKAYUKI MORITA SATOSHI		
发明人	SUGIYAMA, HIROKI NOMURA, SHINICHIRO KATO, TAKAYUKI MORITA, SATOSHI		
IPC分类号	G02F1/1343		
CPC分类号	G02F1/134336 G02F1/133514 G02F2001/13606 G02F1/136209		
优先权	2005278287 2005-09-26 JP 2006124918 2006-04-28 JP		
其他公开文献	US8553182		
外部链接	Espacenet USPTO		

摘要(译)

本发明的液晶显示装置包括阵列基板11，其配备有以矩阵排列展开的信号线33和扫描线32，设置在信号线33和扫描线32的交叉点附近的薄膜晶体管（TFT）34，像素电极40，其中一个设置在由信号线33和扫描线32界定的每个像素域中；滤色器基板12上形成有滤色器22R至22B和公共电极23；以及放置在所述两个基板之间的液晶层13；其中，像素电极40定位成不与信号线33重叠，或者不与扫描线32重叠，或者当从上方观察时，并且在相邻像素电极40之间的空间下方，树脂黑矩阵中不重叠。当从上方观察时，配置图45所示的像素电极40以与像素电极40重叠。这些特征允许提供液晶显示装置，其可以防止光从扫描线和信号线的外围部分泄漏，以及抑制诸如串扰的显示缺陷，并且另外实现有效的功耗。

