



US 20030142259A1

(19) **United States**

(12) **Patent Application Publication**

Asai et al.

(10) **Pub. No.: US 2003/0142259 A1**

(43) **Pub. Date: Jul. 31, 2003**

(54) **LATERAL ELECTRIC FIELD LIQUID CRYSTAL DISPLAY DEVICE**

(30) **Foreign Application Priority Data**

Jan. 30, 2002 (JP) 21184/2002

(75) Inventors: **Takuya Asai**, Tokyo (JP); **Syouichi Kuroha**, Tokyo (JP); **Takeshi Sasaki**, Tokyo (JP)

Publication Classification

(51) **Int. Cl.⁷** **G02F 1/1343**

(52) **U.S. Cl.** **349/141**

(57) **ABSTRACT**

In a lateral electric field liquid crystal display device, a major electrode portion for generating a lateral electric field is formed using a layer different from a layer on which other electrodes and lines are formed. In this case, the major portion is formed to have a thickness of $\frac{1}{20}$ to $\frac{1}{3}$ of the thickness of each of the other electrodes and lines. Thus, flatness of a base film of an alignment layer is significantly improved, also alignment layer material can be coated and formed with high flatness on the base film, and rubbing of the alignment layer material can be performed uniformly for the overall substrate surface.

Correspondence Address:
McGinn & Gibb, PLLC,
Suite 200
8321 Old Courthouse Road
Vienna, VA 22182-3817 (US)

(73) Assignee: **NEC Corporation**, Tokyo (JP)

(21) Appl. No.: **10/353,023**

(22) Filed: **Jan. 29, 2003**




FIG. 1
(PRIOR ART)




FIG. 2
(PRIOR ART)




FIG. 3





FIG. 4



LATERAL ELECTRIC FIELD LIQUID CRYSTAL DISPLAY DEVICE

BACKGROUND OF THE INVENTION

[0001] 1. Field of the Invention

[0002] The present invention relates to a lateral electric field liquid crystal display device. More specifically, the present invention relates to an electrode structure of an active element substrate.

[0003] 2. Description of the Related Art

[0004] In general, a lateral electric field liquid crystal display device is constructed such that a pixel electrode and a common electrode are provided on the same, substrate, and an electric field is applied therebetween. Each pixel electrode is connected to an active element, such as a thin-film transistor (TFT), to constitute an active matrix substrate (TFT substrate). Liquid crystal is filled between the TFT substrate and an opposing substrate. In this lateral electric field liquid crystal display device, since the liquid crystal is controlled by the electric field applied parallel to a substrate surface, a wide viewing angle can be obtained.

[0005] The TFT substrate of the type described above will be explained with reference to **FIGS. 1 and 2**. **FIG. 1** is a plan view of one pixel of the TFT substrate of the conventional liquid crystal display device as viewed from the side of liquid crystal. **FIG. 2** is a cross-sectional view taken along the line X-X' of **FIG. 1**.

[0006] A scanning line **103**, a gate electrode **102** connected to the scanning line **103**, a common line **104**, and a common electrode **105** extending as a part of the common line **104** are formed of a metal film in the same layer on a transparent insulation substrate **101** formed of, for example, glass. A gate insulating film **106** is formed over these lines and electrodes. The common electrode **105** is partially formed parallel to a pixel electrode described below. Subsequently, a semiconductor island **107** is formed on the gate insulating film **106**. Thereafter, a signal line **110**, source/drain electrodes **108** and **109** of a TFT, both of which are partially formed on the semiconductor island **107** to be connected thereto, and a pixel electrode **111** connected to the source/drain electrode **109** are formed using the same metal film as that used to form the source/drain electrode. Note that both the pixel electrode **111** and the previously formed common electrode **105** are partially formed in parallel with each other. In addition, an interlayer insulating film **112** and an alignment layer **113** are formed in such a manner as to cover the semiconductor island **107**, the source/drain electrodes **108** and **109**, and the pixel electrode **111**. In this manner, formation of TFT substrate **300** is completed. Note that a storage capacitor is formed where the pixel electrode **111** and the common line **104** overlap each other (an overlap portion **122** indicated as a cross-hatched portion).

[0007] Light shielding film **152** is formed on the transparent insulation substrate **151** to partition pixels on the TFT substrate **300** and cover the semiconductor island **107**. An insulating film **153** and an alignment layer **154** are formed to cover the light shielding films **152**, thereby constituting an opposing substrate **400**.

[0008] Liquid crystal **127** is filled between the TFT substrate **300** and the opposing substrate **400** thus to form a

liquid crystal display device. In **FIG. 2**, a polarizer and the like are not shown for simplification.

[0009] It should be noted that the scanning line **103**, the common line **104** and the signal line **110** are formed to have enough thickness to reduce resistance values thereof. Since the common line **104** and the common electrode **105** are formed together with the scanning line **103**, all of which have the same thickness. Consequently, as shown in **FIG. 2**, the interlayer insulating film **112** covering these electrodes and lines is formed with large variation in a height of step. In this case, when an alignment layer material coated having large height of step on the interlayer insulating film **112** is subjected to a rubbing process, the material cannot be rubbed uniformly over the TFT substrate. As a consequence, the alignment layer **113** is formed unevenly due to nonuniformity of rubbing, thereby making the liquid crystal display device have nonuniformity of display.

SUMMARY OF THE INVENTION

[0010] An object of the present invention is therefore to provide a lateral electric field liquid crystal display device configured to have an insulating film formed below an alignment layer and with reduced height of its steps in order to perform rubbing uniformly over the alignment layer.

[0011] According to the present invention, there is provided a lateral electric field liquid crystal display device including a TFT substrate, an opposing substrate and a liquid crystal layer sandwiched between the TFT substrate and the opposing substrate, in which the TFT substrate includes a signal line, a common line, a pixel electrode and a common electrode. The liquid crystal display device thus configured is characterized in that the pixel electrode is partially formed in a layer different from and above the signal line and the common line, the common electrode is formed in the layer, and the common electrode and a portion of the pixel electrode formed in the layer is formed thinner than the signal line and the common line.

[0012] The liquid crystal display device thus configured is further characterized in that the pixel electrode further comprises an auxiliary capacitive electrode formed in the same layer as that used for the signal line and formed to overlap the common line.

[0013] The liquid crystal display device thus configured is further characterized in that the portion of the pixel electrode is connected to a drain electrode of a thin film transistor (TFT) through a contact hole and the common electrode is connected to the common line through a contact hole.

[0014] The liquid crystal display device thus configured is still further characterized in that the TFT substrate further includes a transparent substrate, a scanning line formed on the transparent substrate, a gate insulating film formed on the transparent substrate to cover the scanning line, a semiconductor layer formed on the gate insulating film, a first interlayer insulating film formed on the gate insulating film to cover the semiconductor film, a second insulating film formed on the first insulating film, and an alignment layer formed on the second insulating film. The above-described liquid crystal display device is further constructed such that the common line is formed on the transparent substrate together with the scanning line, the signal line is formed between the gate insulating film and the first interlayer

insulating film and is connected to one end of the semiconductor film, the pixel electrode includes a lower-layer pixel electrode formed on the gate insulating film together with the signal line and connected to the other end of the semiconductor film, the common electrode is formed between the first interlayer insulating film and the second interlayer insulating film and connected to the common line, the pixel electrode further includes an upper-layer pixel electrode formed on the first interlayer insulating film together with the common electrode and connected to the lower-layer pixel electrode, and the upper-layer pixel electrode is thinner than the signal line and the common line.

[0015] The liquid crystal display device thus constructed is further characterized in that a thickness of each of the common electrode and the upper-layer pixel electrode is in a range of twentieth to third of a thickness of each of the signal line and the common line.

[0016] Therefore, flatness of an underlying film for an alignment layer is significantly improved and a material for the alignment layer also can be formed with high flatness on the underlying film, and further, rubbing of the material for the alignment layer can therefore be performed uniformly over the substrate. Consequently, the uniformly rubbed alignment layer is obtained and the liquid crystal display device is able to significantly reduce display failure due to unevenness of rubbing.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] In the accompanying drawings:

[0018] **FIG. 1** is a plan view of one pixel portion of a TFT substrate of a conventional liquid crystal display device;

[0019] **FIG. 2** is a cross-sectional view taken along the line X-X' of **FIG. 1**;

[0020] **FIG. 3** is a plan view of one pixel portion of a TFT substrate of a liquid crystal display device according to the present invention; and

[0021] **FIG. 4** is a cross-sectional view taken along the line X-X' of **FIG. 3**.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0022] Hereinbelow, an embodiment of a liquid crystal display device according to the present invention will be described with reference to **FIGS. 3 and 4**.

[0023] A metal film (of Cr, Al, or Ta, or an alloy of the foregoing metals) having a thickness of 200 to 500 nm is patterned on a transparent insulation substrate **1** formed of, for example, glass in order to simultaneously form a scanning line **3**, a gate electrode **2** connected to the scanning line **3**, and a common line **4**. Thereafter, a gate insulating film **6** (such as an SiNx film having a thickness of 400 to 600 nm) is formed over the substrate. Then, a semiconductor island **7** (of, for example, amorphous silicon or polysilicon) is formed on the gate insulating film **6**. Thereafter, a metal film (of Cr, Al, or Ta, or an alloy of the foregoing metals) having a thickness of 200 to 500 nm is deposited and then patterned in order to form a signal line **10**, source/drain electrodes **8**, **9**, and a first pixel electrode **11** (lower layer pixel electrode) connected to the source/drain electrode **9**. As shown in **FIG. 3**, the first pixel electrode **11** is formed to include a capaci-

tive electrode **22** overlapping the common line **4** in addition to electrodes parallel to later formed common electrodes **5**. The common line **4** and the capacitive electrode **22** form an auxiliary capacitor. Thus, the lower-layer pixel electrode also serves as a capacitive storage electrode.

[0024] A first interlayer insulating film **12** of, for example, SiNx, having a thickness of 200 to 400 nm is deposited over the substrate to cover the semiconductor island **7**, the source/drain electrodes **8**, **9**, the signal line **10**, and the first pixel electrode **11**. Subsequently, a contact hole **31** for common electrode and a contact hole **32** for pixel electrode are formed in the insulating film so that portions of the insulating film positioned above the common line **4** and the source/drain electrode **9** are opened.

[0025] A metal film (of Cr, Al, or Ta, or an alloy of the foregoing metals) having a thickness of 20 to 120 nm is deposited as a film thinner than the signal line **10** over the first interlayer insulating film **12**, preferably to a thickness of twentieth to third of the thickness of the signal line **10**, and then patterned to form the common electrodes **5** connected to the common line **4** through the contact hole **31** for common electrode and a second pixel electrode **25** (upper-layer pixel electrode) connected to the source/drain electrode **9** through the contact hole **32** for pixel electrode. In this case, a lower limit of the thickness of the common electrodes **5** and the second pixel electrode **25** is based on a desired ratio of resistance of the common electrode (and the upper-layer pixel electrode) to resistance of the common line (and the signal line). An upper limit of the thickness thereof is based on a desired height of the step formed by the insulating film below the alignment layer. The common electrodes **5** and the second pixel electrode **25** are formed in parallel with each other and, in addition, the common electrodes **5** and the first pixel electrode **11** are formed in parallel with each other. Furthermore, the second pixel electrode **25** is formed so as not to overlap the first pixel electrode **11**.

[0026] A second interlayer insulating film **26** made of, for example, SiNx and having a thickness of 600 to 800 nm is deposited over the substrate to cover the common electrodes **5** and the second pixel electrode **25**. Subsequently, a material for an alignment layer is coated thereon to a thickness of 80 to 120 nm and then rubbed to form an alignment layer **13**. In this manner, formation of TFT substrate **100** is completed.

[0027] An opposing substrate **200** disposed opposite the TFT substrate **100** is generally formed in the following manner.

[0028] First, a light shielding film **52** is formed on a transparent insulation substrate **51** so that the film partitions the individual pixels of the TFT substrate **100** and corresponds to the semiconductor island **7**. Then, an insulating film **53** and an alignment layer **54** are formed over the substrate to cover the light shielding film **52**.

[0029] Liquid crystal **27** is filled between thus formed TFT substrate **100** and opposing substrate **200** to provide a liquid crystal display device. In **FIG. 4**, a polarizer, etc., are not shown for simplicity.

[0030] As described above, the second pixel electrode **25**, the common electrodes **5**, etc. are formed in the layer different from the layer used for the signal line **10** and the common line **4** that allow a large amount of current. Thus,

the thickness of the metal film constituting the second pixel electrode **25** and the common electrodes **5** can be determined independently of the thickness of the signal line, the common line, etc. Consequently, the metal film constituting the pixel electrode and the common electrode can be formed to a thickness thinner than the signal line, the common line, etc., thereby allowing reduction of height of steps formed by the surface of the second interlayer insulating film **26** located on the metal film.

[0031] As described above, one set of the common electrodes **5** and the second pixel electrode **25** for generating the lateral electric field is formed of the metal film having a thickness of 20 to 120 nm, which thickness is significantly smaller than that of the conventional metal film, i.e., 200 to 500 nm, and in addition, has thereunder no lines and electrodes that produce height of steps, thereby allowing the second interlayer insulating film **26** to significantly reduce height of its steps, which height is significantly smaller than that observed in the conventional case.

[0032] As for the other set of the common electrodes **5** and the first pixel electrode **11** for generating the lateral field, the first pixel electrode **11** is still thick, i.e., 200 to 500 nm. However, since the first interlayer insulating film **12** and the second interlayer insulating film **26** are formed over the substrate to cover the other set of the electrodes, height of steps formed below the alignment layer **13** is significantly smaller than that observed in the conventional structure. Accordingly, a material for the alignment layer is formed with high flatness on the second interlayer insulating film **26** and the material can be uniformly rubbed in a subsequent step, thereby allowing uniformity of the alignment layer **13** over the substrate.

[0033] The liquid crystal display device including the above-described uniform alignment layers exhibits noticeable advantages, particularly, when the display device is used as a liquid crystal display device performing monochromatic display. In this case, the contrast obtained by dividing the white luminance by the black luminance has been proven to increase 1.5 times that observed using the liquid crystal display apparatus having the structure shown in **FIGS. 1 and 2**.

[0034] In the embodiment, although the second interlayer insulating film is formed thicker than the first interlayer insulating film, the second interlayer insulating film may be formed thinner than the above-described thickness depending on a contrast allowed in a liquid crystal display device. In addition, the second interlayer insulating film may be formed using an organic film instead of the inorganic film, allowing the second interlayer insulating film to be thinner than the first interlayer insulating film.

[0035] The present embodiment has been described with reference to the example including the storage electrode. However, even in the structure including no storage electrode, it is apparent that equivalent advantages can be obtained by providing pixel electrodes and common electrodes in a layer different from those for the signal and common lines.

[0036] As described above, according to the liquid crystal display device of the present invention, the major electrodes for generating the lateral electric field are formed in a layer different from layers for other electrodes and lines, and

further, formed thinner than the other electrodes and lines. Therefore, flatness of an underlying film for an alignment layer is significantly improved and a material for the alignment layer also can be formed with high flatness on the underlying film, and further, rubbing of the alignment layer material can therefore be performed uniformly over the substrate. Consequently, the uniformly rubbed alignment layer is obtained and the liquid crystal display device is able to significantly enhance its contrast.

What is claimed is:

1. A lateral electric field liquid crystal display device comprising:

a TFT substrate provided with a signal line, a common line, a pixel electrode and a common electrode, said pixel electrode being partially formed in a layer different from and above said signal line and said common line, said common electrode being formed in said layer; said common electrode and a portion of said pixel electrode formed in said layer being formed thinner than said signal line and said common line;

an opposing substrate; and

a liquid crystal layer sandwiched between said TFT substrate and said opposing substrate,

said TFT substrate including.

2. The lateral electric field liquid crystal display device according to claim 1, wherein the pixel electrode further comprises an auxiliary capacitive electrode formed in the same layer as that used for said signal line and formed to overlap said common line.

3. The lateral electric field liquid crystal display device according to claim 1, wherein said portion of said pixel electrode is connected to a drain electrode of a thin film transistor (TFT) through a contact hole and said common electrode is connected to said common line through a contact hole.

4. A lateral electric field liquid crystal display device according to claim 1, wherein said TFT substrate further comprises:

a transparent substrate;

a scanning line formed on said transparent substrate;

a gate insulating film formed on said transparent substrate to cover said scanning line;

a semiconductor layer formed on said gate insulating film;

a first interlayer insulating film formed on said gate insulating film to cover said semiconductor film;

a second insulating film formed on said first insulating film; and

an alignment layer formed on said second insulating film,

and wherein said common line is formed on said transparent substrate together with said scanning line, and wherein said signal line is formed between said gate insulating film and said first interlayer insulating film and is connected to one end of said semiconductor film, and wherein said pixel electrode includes a lower-layer pixel electrode formed on said gate insulating film together with said signal line and connected to the other end of said semiconductor film, and wherein said common electrode is formed between said first inter-

layer insulating film and said second interlayer insulating film and connected to said common line, and wherein said pixel electrode further includes an upper-layer pixel electrode formed on said first interlayer insulating film together with said common electrode and connected to said lower-layer pixel electrode, and wherein said upper-layer pixel electrode is thinner than said signal line and said common line.

5. The lateral electric field liquid crystal display device according to claim 4, wherein a thickness of each of said common electrode and said upper-layer pixel electrode is in a range of twentieth to third of a thickness of each of said signal line and said common line.

6. The lateral electric field liquid crystal display device according to claim 4, wherein a voltage is applied between said common electrode and said upper-layer pixel electrode

and between said common electrode and said lower-layer pixel electrode to make liquid crystal molecules of said liquid crystal layer rotate within a plane parallel to said transparent substrate.

7. The lateral electric field liquid crystal display device according to claim 4, wherein a portion of said lower-layer pixel electrode is an auxiliary capacitive electrode.

8. The lateral electric field liquid crystal display device according to claim 1, wherein a portion of said pixel electrode formed in said layer is connected to a source/drain electrode of a thin film transistor through a contact hole and said common electrode is connected to said common line through a contact hole.

* * * * *

专利名称(译)	横向电场液晶显示装置		
公开(公告)号	US20030142259A1	公开(公告)日	2003-07-31
申请号	US10/353023	申请日	2003-01-29
申请(专利权)人(译)	NEC公司		
当前申请(专利权)人(译)	NLT科技有限公司.		
[标]发明人	ASAI TAKUYA KUROHA SYOICHI SASAKI TAKESHI		
发明人	ASAI, TAKUYA KUROHA, SYOICHI SASAKI, TAKESHI		
IPC分类号	G02F1/1368 G02F1/1333 G02F1/1343 G09F9/30 G09F9/35 H01L29/786		
CPC分类号	G02F1/134363 G02F2201/48		
优先权	2002021184 2002-01-30 JP		
其他公开文献	US6888601		
外部链接	Espacenet USPTO		

摘要(译)

在横向电场液晶显示装置中，使用与形成其他电极和线的层不同的层形成用于产生横向电场的主电极部分。在这种情况下，主要部分形成为具有每个其他电极和线的厚度的1/20至1/3的厚度。因此，取向层的基膜的平坦度显著提高，并且也可以在基膜上以高平坦度涂覆和形成取向层材料，并且可以对整个基板表面均匀地进行取向层材料的摩擦。

