



US008013969B2

(12) **United States Patent**  
**Ahn et al.**

(10) **Patent No.:** **US 8,013,969 B2**  
(45) **Date of Patent:** **Sep. 6, 2011**

(54) **LIQUID CRYSTAL DISPLAY DEVICE  
COMPRISING A PROTECTIVE FILM SO  
THAT THE PROTECTIVE FILM BORDERS  
WITH ONE END OF A TRANSPARENT  
CONDUCTIVE PATTERN**

(75) Inventors: **Byung Chul Ahn**, Anyang-si (KR); **Joo Soo Lim**, Gumi-si (KR); **Byung Ho Park**, Pohang-si (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **12/787,713**

(22) Filed: **May 26, 2010**

(65) **Prior Publication Data**  
US 2010/0231820 A1 Sep. 16, 2010

**Related U.S. Application Data**  
(62) Division of application No. 11/168,314, filed on Jun. 29, 2005, now Pat. No. 7,751,011.

(30) **Foreign Application Priority Data**  
Dec. 24, 2004 (KR) ..... 10-2004-0112584

(51) **Int. Cl.**  
**G02F 1/1343** (2006.01)  
**G02F 1/1333** (2006.01)

(52) **U.S. Cl.** ..... **349/141**; 349/138

(58) **Field of Classification Search** ..... 349/141,  
349/138

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,542,960 A	9/1985	Yang
4,685,195 A	8/1987	Szydlo et al.
5,162,933 A	11/1992	Kakuda et al.
5,317,433 A	5/1994	Miyawaki
5,339,181 A	8/1994	Kim et al.
5,462,887 A	10/1995	Gluck
5,668,379 A	9/1997	Ono et al.
5,731,856 A	3/1998	Kim et al.

(Continued)

FOREIGN PATENT DOCUMENTS

CN	1512253	7/2004
----	---------	--------

(Continued)

*Primary Examiner* — Mark A Robinson


*Assistant Examiner* — Charles Chang

(74) *Attorney, Agent, or Firm* — McKenna Long & Aldridge LLP

(57) **ABSTRACT**

A thin film transistor substrate for applying a horizontal electric field and a fabricating method thereof for simplifying a process are disclosed. In a liquid crystal display device according to the present invention, a gate line on a substrate; a data line crossing the gate line having a gate insulating film there between to define a pixel area; a thin film transistor including a gate electrode, a source electrode, a drain electrode and a semiconductor layer to define a channel between the source electrode and the drain electrode; a common line on the substrate; a common electrode in the pixel area; and a pixel electrode in the pixel area to form a horizontal electrode field with the common electrode, wherein the data line, the source electrode and the drain electrode have an opaque conductive pattern and a transparent conductive pattern, the pixel electrode is formed by an extension of the transparent conductive pattern of the drain electrode, and a protective film borders with the transparent conductive pattern and in the remaining area thereof.

**11 Claims, 21 Drawing Sheets**



U.S. PATENT DOCUMENTS

5,771,083	A	6/1998	Fujihara et al.	
5,793,460	A	8/1998	Yang	
5,847,781	A	12/1998	Ono et al.	
5,959,708	A	9/1999	Lee et al.	
6,215,542	B1	4/2001	Lee et al.	
6,233,034	B1	5/2001	Lee et al.	
6,256,081	B1	7/2001	Lee et al.	
6,281,953	B1	8/2001	Lee et al.	
6,285,428	B1	9/2001	Kim et al.	
6,319,760	B1	11/2001	Lee et al.	
6,351,300	B1	2/2002	Park et al.	
6,362,032	B1	3/2002	Kim et al.	
6,362,858	B1	3/2002	Jeon et al.	
6,388,726	B1	5/2002	Kim et al.	
6,404,470	B1	6/2002	Kim et al.	
6,429,918	B1	8/2002	Choi et al.	
6,449,026	B1	9/2002	Min et al.	
6,456,351	B1	9/2002	Kim et al.	
6,462,800	B1	10/2002	Kim et al.	
6,512,503	B1	1/2003	Kim et al.	
6,545,293	B2*	4/2003	Wong	257/59
6,562,645	B2	5/2003	Sung et al.	
6,580,487	B1	6/2003	Kim et al.	
6,583,842	B2	6/2003	Hong et al.	
6,678,027	B2	1/2004	Park et al.	
6,741,311	B1	5/2004	Hong et al.	
7,060,541	B2	6/2006	Lee et al.	
2001/0005238	A1*	6/2001	Yun et al.	349/43
2001/0005251	A1	6/2001	Kim et al.	
2001/0005597	A1	6/2001	Shin et al.	
2001/0006765	A1	7/2001	Lee et al.	
2001/0007779	A1	7/2001	Lee et al.	
2001/0010576	A1	8/2001	Lee et al.	


2001/0038370	A1	11/2001	Yeung	
2001/0048500	A1	12/2001	Lim et al.	
2001/0048501	A1	12/2001	Kim et al.	
2002/0008828	A1	1/2002	Park et al.	
2002/0041354	A1	4/2002	Noh et al.	
2002/0044248	A1	4/2002	Park et al.	
2002/0067453	A1	6/2002	Kim et al.	
2002/0067454	A1	6/2002	Hong et al.	
2002/0089630	A1	7/2002	Liu et al.	
2002/0163604	A1	11/2002	Kim et al.	
2002/0180920	A1	12/2002	Noh et al.	
2003/0076469	A1	4/2003	Liu	
2003/0098939	A1	5/2003	Min et al.	
2003/0117558	A1	6/2003	Kim et al.	
2003/0160921	A1	8/2003	Nakashima et al.	
2003/0197181	A1*	10/2003	Yun	257/72
2003/0202140	A1	10/2003	Liu	
2004/0197966	A1	10/2004	Cho et al.	
2005/0030451	A1	2/2005	Liu	
2005/0046775	A1	3/2005	Lee et al.	
2005/0062923	A1	3/2005	Lyu et al.	
2005/0068483	A1	3/2005	Lee et al.	

FOREIGN PATENT DOCUMENTS

CN	1550857	12/2004
JP	2000-066240	3/2000
JP	2001-250958	9/2001
JP	2003-337349	11/2003
KR	10-1998-0085147	12/1998
KR	10-1999-0031218	5/1999
KR	10-2000-0050883	8/2000
KR	10-2003-0082651	10/2003

\* cited by examiner

FIG. 1  
RELATED ART






FIG. 2






FIG. 4





FIG. 5A

FIG. 5B






FIG. 6A

FIG. 6B




FIG. 7A




FIG. 7B




FIG. 7C







FIG. 7E





FIG. 7F






FIG. 8A

FIG. 8B




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D





FIG. 9E



**LIQUID CRYSTAL DISPLAY DEVICE  
COMPRISING A PROTECTIVE FILM SO  
THAT THE PROTECTIVE FILM BORDERS  
WITH ONE END OF A TRANSPARENT  
CONDUCTIVE PATTERN**

This is a divisional application of U.S. patent application Ser. No. 11/168,314, filed on Jun. 29, 2005 now U.S. Pat. No. 7,751,011, which claims the benefit of Korean Patent Application No. P2004-112584, filed in Korea on Dec. 24, 2004, all of which are hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a liquid crystal display using a horizontal electric field, and more particularly to a thin film transistor substrate and a fabricating method thereof that are adaptive for simplifying a process.

2. Description of the Related Art

Generally, a liquid crystal display (LCD) controls light transmittance of a liquid crystal having a dielectric anisotropy using an electric field to thereby display a picture. To this end, the LCD includes a liquid crystal display panel for displaying a picture by a liquid crystal cell matrix, and a driving circuit for driving the liquid crystal display panel.

Referring to FIG. 1, a related art liquid crystal display panel is comprised of a color filter substrate **10** and a thin film transistor substrate **20** that are joined to each other with having a liquid crystal **24** there between.

The color filter substrate **10** includes a black matrix **4**, a color filter **6** and a common electrode **8** that are sequentially provided on an upper glass substrate **2**. The black matrix **4** is provided in a matrix type on the upper glass substrate **2**. The black matrix **4** divides an area of the upper glass substrate **2** into a plurality of cell areas to be provided with the color filter **6**, and prevents a light interference between adjacent cells and an external light reflection. The color filter **6** is provided at the cell area divided by the black matrix **4** in such a manner to be divided into red(R), green(G) and blue(B) ones, thereby transmitting red, green and blue lights. The common electrode **8** is formed from a transparent conductive layer entirely coated onto the color filter **6**, and supplies a common voltage  $V_{com}$  that serves as a reference voltage upon driving of the liquid crystal **24**. Further, an over-coated layer (not illustrated) for smoothing the color filter **6** may be provided between the color filter **6** and the common electrode **8**.

The thin film transistor substrate **20** includes a thin film transistor **18** and a pixel electrode **22** provided for each cell area defined by a crossing between a gate line **14** and a data line **16** at a lower glass substrate **12**. The thin film transistor **18** applies a data signal from the data line **16** to the pixel electrode **22** in response to a gate signal from the gate line **14**. The pixel electrode **22** formed from a transparent conductive layer supplies a data signal from the thin film transistor **18** to drive the liquid crystal **24**.

The liquid crystal **24** having a dielectric anisotropy is rotated in accordance with an electric field formed by a data signal from the pixel electrode **22** and a common voltage  $V_{com}$  from the common electrode **8** to control light transmittance, thereby implementing a gray scale level.

Further, the liquid crystal display panel includes a spacer (not illustrated) for constantly keeping a cell gap between the color filter substrate **10** and the thin film transistor substrate **20**.

In such a liquid crystal display panel, the color filter substrate **10** and the thin film transistor substrate **20** are formed by a plurality of mask processes. Herein, one mask process includes a lot of processes such as thin film deposition (coating), cleaning, photolithography, etching, photo-resist stripping and inspection processes, etc.

Particularly, because the thin film transistor substrate includes the semiconductor process and requires the plurality of mask processes, it has a complicate fabricating process to act as a major factor in the manufacturing cost rise of the liquid crystal display panel. Therefore, the thin film transistor substrate has been developed toward a reduction in the number of mask process.

Meanwhile, the liquid crystal displays are largely classified into a vertical electric field applying type and a horizontal electric field applying type depending upon with a direction of the electric field driving the liquid crystal.

The liquid crystal display of vertical electric field applying type drives a liquid crystal in a twisted nematic (TN) mode with a vertical electric field formed between a pixel electrode and a common electrode arranged in opposition to each other on the upper and lower substrate. The liquid crystal display of vertical electric field applying type has an advantage of a large aperture ratio while having a drawback of a narrow viewing angle about  $90^\circ$ .

The liquid crystal display of horizontal electric field applying type drives a liquid crystal in an in plane switching (IPS) mode with a horizontal electric field between the pixel electrode and the common electrode arranged in parallel to each other on the lower substrate. The liquid crystal display of horizontal electric field applying type has an advantage of a wide viewing angle about  $160^\circ$ .

The thin film transistor substrate in the liquid crystal display of horizontal electric field applying type also requires a plurality of mask process thereby complicating the fabricating process. Therefore, in order to reduce the manufacturing cost, it is necessary to reduce the number of mask processes.

SUMMARY OF THE INVENTION

Accordingly, it is an advantage of the present invention to provide a thin film transistor substrate of horizontal electric field applying type and a fabricating method thereof that are adaptive for simplifying a process.

In order to achieve these and other advantages of the invention, a liquid crystal display device according to one aspect of the present invention comprises a gate line on a substrate; a data line crossing the gate line having a gate insulating film there between to define a pixel area; a thin film transistor including a gate electrode, a source electrode, a drain electrode and a semiconductor layer for defining a channel between the source electrode and the drain electrode; a common line on the substrate; a common electrode in the pixel area; and a pixel electrode in the pixel area to form a horizontal electrode field with the common electrode, wherein the data line, the source electrode and the drain electrode have an opaque conductive pattern and a transparent conductive pattern, the pixel electrode is formed by an extension of the transparent conductive pattern of the drain electrode, and a protective film borders with the transparent conductive pattern and in the remaining area thereof.

A method of fabricating a liquid crystal display device according to another aspect of the present invention comprises a first mask process of forming a first mask pattern group including a gate line, a gate electrode, a common line and a common electrode on a substrate; a second mask process of forming a gate insulating film on the first mask pattern

group and a semiconductor pattern and an opaque conductive pattern on the gate insulating film; and a third mask process of forming a transparent conductive pattern on the opaque conductive pattern and forming a protective film having a border with the transparent conductive pattern, wherein a data line crossing the gate line, a source electrode and a drain electrode are formed of a double-layer structure having the opaque conductive pattern and the transparent conductive pattern, and a pixel electrode is extended from the transparent conductive pattern of the drain electrode to form a horizontal electric field with the common electrode.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

In the drawings:

FIG. 1 is a schematic perspective view illustrating a structure of a related art liquid crystal display panel;

FIG. 2 is a plan view illustrating a structure of a thin film transistor substrate of horizontal electric field applying type according to an embodiment of the present invention;

FIG. 3 is a section view of the thin film transistor substrate taken along the III-III', IV-IV' and V-V' lines in FIG. 2;

FIG. 4 is a plan view illustrating a structure of a thin film transistor substrate of horizontal electric field applying type according to another embodiment of the present invention;

FIG. 5A and FIG. 5B are a plan view and a section view illustrating a first mask process in a method of fabricating the thin film transistor substrate of horizontal electric field applying type according to the embodiment of the present invention, respectively;

FIG. 6A and FIG. 6B are a plan view and a section view illustrating a second mask process in a method of fabricating the thin film transistor substrate horizontal electric field applying type according to the embodiment of the present invention, respectively;

FIG. 7A to FIG. 7F are section views for specifically explaining the second mask process;

FIG. 8A and FIG. 8B are a plan view and a section view illustrating a third mask process in a method of fabricating the thin film transistor substrate horizontal electric field applying type according to the embodiment of the present invention, respectively; and

FIG. 9A to FIG. 9E are section views for specifically explaining the third mask process.

#### DETAILED DESCRIPTION OF THE EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

Hereinafter, exemplary embodiments of the present invention will be described in detail with reference to FIGS. 2 to 9E.

FIG. 2 is a plan view illustrating a structure of a thin film transistor substrate of horizontal electric field applying type according to an embodiment of the present invention, and

FIG. 3 is a section view of the thin film transistor substrate taken along the III-III', IV-IV' and V-V' lines in FIG. 2.

Referring to FIG. 2 and FIG. 3, the thin film transistor substrate includes a gate line 102 and a data line 104 provided on a lower substrate 150 in such a manner to cross each other with having a gate insulating film 144 there between and define a pixel area, a thin film transistor TFT connected to the gate line 102 and the data line 104, a pixel electrode 118 and a common electrode 122 provided to form a horizontal electric field at said pixel area, a common line 120 connected to the common electrode 122, and a storage capacitor Cst provided at an overlapping portion between the pixel electrode 118 and a drain electrode 122. Further, the thin film transistor substrate includes pads 124 connected to the gate line 102, the data line 104 and the common line 120.

The gate line 102 supplies a scanning signal from a gate driver (not illustrated) while the data line 104 supplies a video signal from a data driver (not illustrated). The gate line 102 and the data line 104 cross each other with having a gate insulating film 152 there between to define the pixel area.

The gate line 102 is formed on the substrate 150 in a multiple-layer structure having at least double gate metal layers built. For instance, as illustrated in FIG. 3, the gate line 102 has a double-layer structure in which first and second gate metal layers 101 and 103 are built. The data line 104 is formed on the gate insulating film 152 in a multiple-layer structure having at least double layers including a transparent conductive layer. For instance, as illustrated in FIG. 3, the data line 104 has a double-layer structure in which a source/drain metal pattern 111 and a transparent conductive pattern 113 are built. Herein, the transparent conductive pattern 113 is provided in such a manner to capture the source/drain metal pattern 111, thereby preventing an illumination problem caused by an exposure of the source/drain metal pattern 111.

The thin film transistor TFT allows a pixel signal on the data line 104 to be charged into the pixel electrode 118 and stored in response to a scanning signal from the gate line 102. To this end, the thin film transistor TFT includes a gate electrode included in the gate line 102, a source electrode 110 connected to the data line 104, a drain electrode 112 positioned in opposition to the source electrode 110 to be connected to the pixel electrode 118, and a semiconductor pattern 115 overlapping with the gate line 102 with having the gate insulating film 152 there between to define a channel between the source electrode 110 and the drain electrode 112. Herein, the source electrode 110 and the drain electrode 112 have a double-layer structure in which the source/drain metal pattern 111 and the transparent conductive pattern 113 are built. The semiconductor pattern 115 includes an active layer 114 forming a channel between the source electrode 110 and the drain electrode 112, and an ohmic contact layer 116 formed on the active layer 114 other than the channel portion to make an ohmic contact with the source electrode 110 and the drain electrode 112.

The common line 120 and the common electrode 122 supply a reference voltage for driving the liquid crystal, that is, a common voltage to each pixel. The common line 120 and the common electrode 122 have a double-layer structure in which the first and second gate metal layers 101 and 103 are built.

The common line 120 includes an internal common line 120A provided in parallel to the gate line 102 at a display area, and an external common line 120B commonly connected to the internal common line 120A at a non-display area.

The common electrode 122 is provided within the pixel area to be connected to the internal common line 120A. More specifically, the common electrode 122 includes a horizontal part 122A overlapping with the drain electrode 112 adja-

cently with the gate line 102, and a finger part 122B extended from the horizontal part 122A into the pixel area to be connected to the internal common line 120A.

The pixel electrode 118 is provided such that the transparent conductive pattern 113 of the drain electrode 112 is extended to form a horizontal electric field along with the common electrode 122. More specifically, the pixel electrode 118 includes a horizontal part 118a overlapping with the horizontal part 122A of the common electrode 122 with having the gate insulating film 152 there between, and a finger part 118B extended from the horizontal part 118A in such a manner to have a finger shape parallel to the finger part 122B of the common electrode 122. Herein, the finger part 118A of the pixel electrode 118 overlaps with a portion of the internal common line 120A. The pixel electrode 118 is formed of the transparent conductive pattern 113, so that it may contribute to an aperture ratio. If a video signal is applied, via the thin film transistor TFT, to the pixel electrode 118, then a horizontal electric field is formed between the pixel electrode 118 and the finger part 122B of the common electrode 122 supplied with the common voltage. Liquid crystal molecules arranged in the horizontal direction between the thin film transistor array substrate and the color filter array substrate by such a horizontal electric field is rotated due to a dielectric anisotropy. Transmittance of a light transmitting the pixel area is differentiated depending upon a rotation extent of the liquid crystal molecules, thereby implementing a gray level scale.

Further, the finger part 122B of the common electrode 122 and the pixel electrode 118 can be formed in a zigzag shape as illustrated in FIG. 4. In this case, the edge being adjacent to the data line 104 at the finger part 122B of the common electrode 122 can be formed in parallel to the data line 104, or may be formed in a zigzag shape. Alternatively, the data line 104 may be formed in a zigzag shape along the finger part 122B of the adjacent common electrode 122.

The storage capacitor Cst is provided such that the first horizontal part 122A of the common electrode 122 overlaps with the horizontal part 118A of the pixel electrode 118 with having the gate insulating film 152 there between. Herein, the first horizontal part 118A of the pixel electrode 118 is provided in such a manner to be extended from the transparent conductive pattern 113 of the drain electrode 112 and overlap with the first horizontal part 122A of the common electrode 122 as widely as possible. Thus, a capacitance value of the storage capacitor Cst is increased by the wide overlapping area between the common electrode 122 and the pixel electrode 118, so that the storage capacitor Cst allows a video signal charged in the pixel electrode 118 to be stably maintained until the next signal is charged.

The gate line 102, the data line 104 and the common line 120 receive the corresponding driving signal, via the pad 124 connected to each of them, from the driving circuit. The pads 124 have the same structure. More specifically, the pad 124 includes a lower pad electrode 126, and an upper pad electrode 130 connected, via a first contact hole 128 passing through the gate insulating film 152, to the lower pad electrode 126. Herein, the lower pad electrode 126 has a double-layer structure in which the first and second gate metal layers 101 and 103 are built like the gate line 102 and the common line 120, whereas the upper pad electrode 130 has the transparent conductive pattern 113.

Thus, each of the gate line 102 and the common line 120 is connected, via the lower pad electrode 126 provided on the substrate 150 in the same structure, to the corresponding pad 124. On the other hand, the data line 104 provided on the gate insulating film 152 is connected, via a contact electrode 160, to a data link 135 extended from the corresponding lower pad

electrode 126. Herein, the contact electrode 160 is extended such that the transparent conductive pattern 113 of the data line 104 overlaps with the data link 135. The contact electrode 160 is connected, via a second contact hole 148 passing through the gate insulating film 152, to the data link 135. The contact electrode 160 is extended along the data link 135 to be integral to the corresponding upper pad electrode 130.

The protective film 154 includes the pixel electrode 118, the upper pad electrode 130 and the contact electrode 160. The protective film 154 borders with the transparent conductive patterns 113 included in the data line 104, the source electrode 110 and the drain electrode 122. This is because the protective film 154 is formed in a state in which the photoresist pattern used upon formation of the transparent conductive pattern 113 is left and then is patterned by lifting-off the photo-resist pattern.

Accordingly, the thin film transistor substrate of horizontal electric field applying type according to the embodiment of the present invention having the above-mentioned structure is formed by the following three-round mask process.

FIG. 5A and FIG. 5B are a plan view and a section view illustrating a first mask process, respectively, in a method of fabricating the thin film transistor substrate of horizontal electric field applying type according to the embodiment of the present invention.

A first mask pattern group including the gate line 102, the lower pad electrode 126, the data link 135, the common line 120 and the common electrode 122 is formed on the lower substrate 150 by the first mask process. Such a first mask pattern group has a multiple-layer structure in which at least two conductive layers are built. But, the sake of explanation, there will be described only a double-layer structure having the first and second gate metal layers 101 and 103 built.

More specifically, the first and second gate metal layers 101 and 103 are formed on the lower substrate 150 by a deposition technique such as the sputtering, etc. Each of the first and second gate metal layers 101 and 103 is made from a metal material such as Mo, Ti, Cu, Al, Cr, a Mo alloy, a Cu alloy or an Al alloy, etc. For example, a layer built structure of the first and second gate metal layers 101 and 103 employs Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Cu/Mo, Mo/Al, Cu-alloy/Mo, Cu-alloy/Al, Cu-alloy/Mo-alloy, Cu-alloy/Al-alloy, Al/Mo alloy, Mo-alloy/Al, Al-alloy/Mo-alloy, Mo-alloy/Al-alloy or Mo/Al alloy, etc. Alternatively, it may employ a triple-layer built structure such as Ti/Al(Nd)/Ti or Mo/Ti/Al(Nd), etc.

Then, the first and second gate metal layers 101 and 103 are patterned by the photolithography and the etching process using a first mask to thereby provide the first mask pattern group including the gate line 102, the lower pad electrode 126, the data link 135, the common line 120 and the common electrode 122 each of which takes a double-layer structure.

FIG. 6A and FIG. 6B are a plan view and a section view illustrating a second mask process in a method of fabricating the thin film transistor substrate of horizontal electric field applying type according to the embodiment of the present invention, respectively, and FIG. 7A to FIG. 7F are section views for specifically explaining the second mask process.

The gate insulating film 152 having the first and second contact holes 124 and 128, the semiconductor pattern 115 and the source/drain pattern 111 are formed on the lower substrate 150 provided with the first mask pattern group by the second mask process. These are formed by a single mask process employing a diffractive exposure mask or a half tone mask. Hereinafter, a case where the half tone mask is used as a second mask will be described.

Referring to FIG. 7A, the gate insulating film **152**, an amorphous silicon layer **105**, an amorphous silicon layer **107** doped with an  $n^+$  or  $p^+$  impurity and a source/drain metal layer **109** are sequentially formed on the lower substrate **155** provided with the first mask pattern group by a deposition technique such as the PECVD, etc. Herein, the gate insulating film **152** is formed of an inorganic insulating material such as silicon nitride ( $\text{SiN}_x$ ) or silicon oxide ( $\text{SiO}_x$ ). The source/drain metal layer **109** employs a single layer formed of a metal material such as Mo, Ti, Cu, AlNd, Al, Cr, a Mo alloy, a Cu alloy or an Al alloy, etc., or employs a layer built structure of at least double layers such as Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Mo/Al(Nd)/Mo, Cu/Mo, Ti/Al(Nd)/Ti, Mo/Al, Mo/Ti/Al(Nd), Cu-alloy/Mo, Cu-alloy/Al, Cu-alloy/Mo-alloy, Cu-alloy/Al-alloy, Al/Mo alloy, Mo-alloy/Al, Al-alloy/Mo-alloy, Mo-alloy/Al-alloy, Mo/Al alloy, Cu/Mo alloy or Cu/Mo(Ti), etc.

Referring to FIG. 7B, a first photo-resist pattern **168** having step coverage is formed by the photolithography using the half tone mask. The half tone mask is comprised of a shielding part for shielding an ultraviolet ray, a half-tone transmitting part for partially transmitting the ultraviolet ray using a phase-shifting material, and a full transmitting part for fully transmitting the ultraviolet ray. The first photo-resist pattern **168** having a different thickness of photo-resist patterns **168A** and **168B** provided by the photolithography using the half tone mask; and the aperture part is provided. The relatively thick photo-resist pattern **168A** is provided at a shielding area **P1** of the first photo-resist overlapping with the shielding part of the half tone mask; the photo-resist pattern **168B** thinner than the photo-resist pattern **168A** is provided at a half-tone exposure part **P2** overlapping with the half-tone transmitting part; and the aperture part is provided at a full exposure area **P3** overlapping with the full transmitting part.

Referring to FIG. 7C, the first and second contact holes **124** and **148** passing through an area extended from the source/drain metal layer **109** until the gate insulating film **144** are formed by the etching process using a second photo-resist pattern **168** as a mask. The first contact hole **128** exposes the lower pad electrode **126**, whereas the second contact hole **148** exposes the data link **135**.

Referring to FIG. 7D, a thickness of the photo-resist pattern **168A** is thinned and the photo-resist pattern **168B** is removed by the ashing process using oxygen ( $\text{O}_2$ ) plasma.

Referring to FIG. 7E, the source/drain metal layer **109**, the amorphous silicon layer **107** doped with an impurity and the amorphous silicon layer **105** are patterned by the etching process using the ashed photo-resist pattern **168A** as a mask, thereby providing the semiconductor pattern **115** having the active layer **114** and the ohmic contact layer **116** and the source/drain metal pattern **111** overlapped thereon.

Referring to FIG. 7F, the photo-resist pattern **168A** left on the source/drain metal pattern **111** in FIG. 7E is removed by the stripping process.

Otherwise, a process of forming the first and second contact holes **128** and **148** and the semiconductor pattern **115** including the active layer **114** and the ohmic contact layer **116** using the first photo-resist pattern **168** as a mask may be replaced by a single of process.

FIG. 8A and FIG. 8B are a plan view and a section view illustrating a third mask process in a method of fabricating the thin film transistor substrate of horizontal electric field applying type according to the embodiment of the present invention, respectively, and FIG. 9A to FIG. 9E are section views for specifically explaining the third mask process.

A transparent conductive pattern **113** covering the source/drain metal pattern **111** and the protective film **154** making a

border with the transparent conductive pattern **113** are formed by the third mask process. Thus, the data line **104**, the source electrode **110** and drain electrode **112** having a double-layer structure in which the source/drain metal pattern **111** and the transparent conductive pattern **113** are built are provided and, at the same time, the pixel electrode **118**, the upper pad electrode **130** and the contact electrode **160** having a single-layer structure of the transparent conductive pattern **113** are provided.

More specifically, as illustrated in FIG. 9A, a transparent conductive layer **117** is formed on the gate insulating film **152** provided with the source/drain metal pattern **111**. The transparent conductive layer **117** is formed from ITO, TO, IZO or ITZO, etc.

Referring to FIG. 9B, a photo-resist pattern **182** is formed on the transparent conductive layer **117** by the photolithography using a third mask.

Referring to FIG. 9C, the transparent conductive layer **117** is patterned by an etching process using the photo-resist pattern **182** as a mask, that is, a wet etching process to thereby provide the transparent conductive pattern **113** capturing the source/drain metal pattern **111**. At this time, the transparent conductive pattern **113** is opened at a portion to be provided with the channel of the thin film transistor TFT. Thus, the exposed source/drain metal pattern **111** and the ohmic contact layer **116** under it are removed by an etching process using the transparent conductive pattern **113** as a mask, that is, a dry etching process, thereby allowing the active layer **114** to have an exposed structure. As a result, the data line **104**, the source electrode **110** and the drain electrode **112** having a double-layer structure are provided. Further, the pixel electrode **118** extended from the transparent conductive pattern **113** of the drain electrode **112** and the contact electrode **160** extended from the transparent conductive pattern **133** of the data line **104** are provided and, at the same time, the upper pad electrode **130** connected to the lower pad electrode **126** is provided. The transparent conductive pattern **113** is over-etched in comparison with the photo-resist pattern **182**.

Referring to FIG. 9D, the protective film **154** covering the photo-resist pattern **182** is entirely formed. In this case, the protective film **154** provided at the substrate in which the photo-resist pattern **182** does not exist has a structure opened with respect to the protective film **154** provided at the photo-resist pattern **182** by a spaced distance between the edge of the photo-resist pattern **182** and the edge of the transparent conductive pattern **113**. Thus, an infiltration of a stripper into a portion between the photo-resist pattern **182** and the transparent conductive pattern **113** is facilitated at the next lift-off process, thereby improving lift-off efficiency. The protective film **154** is formed from an inorganic insulating material like the gate insulating film **144**. Such a protective film **154** is formed by a deposition technique such as the PECVD or the sputtering, etc. But, it is desirable that the protective film **154** is formed by the sputtering in order to prevent a hardness of the photo-resist pattern **182** at a high temperature. Alternatively, the protective film **154** may be formed from an organic insulating material such as an acrylic organic compound, BCB or PFCB, etc.

Referring to FIG. 9E, the photo-resist pattern **182** illustrated in FIG. 9D and the protective film **154** provided thereon are removed by the lift-off process to thereby pattern the protective film **154**. The patterned protective film **154** makes a border with the transparent conductive pattern **113**. In other words, the protective film **154** making a border with the transparent conductive pattern **113** is left at the remaining area other than an area provided with the transparent conductive pattern **113**.

Accordingly, a channel length L of the thin film transistor TFT is determined by the transparent conductive pattern 113. Furthermore, a smoothing is possible in accordance with a thickness of the transparent conductive pattern 113, so that it becomes possible to prevent a rubbing badness upon an alignment treatment process such as the rubbing, etc. after forming the alignment film.

As described above, according to the present invention, the semiconductor pattern and the source/drain metal pattern, along with the contact hole, are formed by utilizing a half tone (or diffractive exposure) mask in the second mask process.

Also, according to the present invention, the transparent conductive pattern is formed and the protective film is patterned by lifting off the photo-resist pattern used upon formation of the transparent conductive pattern in the third mask process. Such transparent conductive pattern and protective film protects the metal layer at the lower portion thereof, thereby preventing an illumination problem.

As a result, according to the present invention, a process can be simplified by the three-round mask process, so that it becomes possible to reduce the material cost and the equipment investment cost, etc. as well as to improve the productivity.

Furthermore, according to the present invention, the pixel electrode is formed from the transparent conductive pattern, so that it becomes possible to improve an aperture ratio.

Although the present invention has been explained by the embodiments illustrated in the drawings described above, it should be understood to the ordinary skilled person in the art that the invention is not limited to the embodiments, but rather that various changes or modifications thereof are possible without departing from the spirit of the invention. Accordingly, the scope of the invention shall be determined only by the appended claims and their equivalents.

What is claimed is:

1. A liquid crystal display device, comprising:

- a gate line on a substrate;
  - a data line crossing the gate line having a gate insulating film therebetween to define a pixel area;
  - a thin film transistor including a gate electrode, a source electrode, a drain electrode and a semiconductor layer to define a channel between the source electrode and the drain electrode;
  - a common line on the substrate;
  - a common electrode in the pixel area; and
  - a pixel electrode in the pixel area to form a horizontal electrode field with the common electrode,
- wherein the data line, the source electrode and the drain electrode have an opaque conductive pattern and a transparent conductive pattern, the pixel electrode is formed by an extension of the transparent conductive pattern of the drain electrode, and one end of a protective film borders with an end of the transparent conductive pattern

at an area in which the end of the transparent conductive pattern is overlapped with the common line.

2. The liquid crystal display device as claimed in claim 1, further comprising:

- a storage capacitor provided such that the pixel electrode overlaps with a portion of the common electrode having the gate insulating film therebetween.

3. The liquid crystal display device as claimed in claim 1, wherein the gate line, the gate electrode, the common line and the common electrode includes one of a single-layer structure formed of one of Mo, Ti, Cu, AlNd, Al, Cr, a Mo alloy, a Cu alloy and an Al alloy, and a multiple-layer structure having at least two layers thereof.

4. The liquid crystal display device as claimed in claim 1, further comprising:

- a pad connected to the gate line, the common line and the data line, wherein the pad includes:
  - a lower pad electrode on the substrate with the gate line and the common line;
  - a contact hole passing through the gate insulating film to expose the lower pad electrode; and
  - an upper pad electrode connected to the lower data pad electrode via said contact hole and formed of the transparent conductive pattern.

5. The liquid crystal display device as claimed in claim 4, further comprising:

- a data link extended from the lower pad electrode of the data pad;
- a second contact hole passing through the gate insulating film to expose the data link; and
- a contact electrode extended from the transparent conductive pattern of the data line to be connected to the data link via the second contact hole.

6. The liquid crystal display device as claimed in claim 5, wherein the contact electrode is integral to the upper pad electrode.

7. The liquid crystal display device as claimed in claim 5, wherein the transparent conductive pattern encloses the opaque conductive pattern.

8. The liquid crystal display device as claimed in claim 1, wherein the opaque conductive pattern includes one of a single-layer structure formed of one of Mo, Ti, Cu, AlNd, Al, Cr, a Mo alloy, a Cu alloy and an Al alloy, and a multiple-layer structure having at least two layers thereof.

9. The liquid crystal display device as claimed in claim 5, wherein the upper pad electrode and the contact electrode borders with the protective film.

10. The liquid crystal display device as claimed in claim 1, wherein the common line is parallel to the gate line.

11. The liquid crystal display device as claimed in claim 1, wherein the pixel electrode extends from the drain electrode.

专利名称(译)	液晶显示装置包括保护膜，使得保护膜与透明导电图案的一端邻接		
公开(公告)号	<a href="#">US8013969</a>	公开(公告)日	2011-09-06
申请号	US12/787713	申请日	2010-05-26
[标]申请(专利权)人(译)	AHN BYUNG CHUL LIM JOO SOO 朴炳鎬		
申请(专利权)人(译)	AHN BYUNG CHUL LIM JOO SOO 朴炳鎬		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	AHN BYUNG CHUL LIM JOO SOO PARK BYUNG HO		
发明人	AHN, BYUNG CHUL LIM, JOO SOO PARK, BYUNG HO		
IPC分类号	G02F1/1343 G02F1/1333		
CPC分类号	G02F1/1362 G02F1/134363 G02F2001/136295		
助理审查员(译)	常, CHARLES		
优先权	1020040112584 2004-12-24 KR		
其他公开文献	US20100231820A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

公开了一种用于施加水平电场的薄膜晶体管基板及其制造方法，以简化工艺。在根据本发明的液晶显示装置中，基板上的栅极线；与栅极线交叉的数据线之间具有栅极绝缘膜以限定像素区域；薄膜晶体管，包括栅电极，源电极，漏电极和半导体层，以限定源电极和漏电极之间的沟道；基板上的公共线；像素区域中的公共电极；像素区域中的像素电极与公共电极形成水平电极场，其中数据线，源电极和漏电极具有不透明导电图案和透明导电图案，像素电极由延伸形成漏电极的透明导电图案和保护膜与透明导电图案相邻并在其余区域中。

