



US006819375B2

(12) **United States Patent**
Wachi

(10) **Patent No.:** **US 6,819,375 B2**
(45) **Date of Patent:** **Nov. 16, 2004**

(54) **COLOR FILTER HAVING SURFACE PROFILE FOR LIQUID CRYSTAL ALIGNMENT, LIQUID CRYSTAL DISPLAY PANEL, AND METHOD OF PRODUCING**

5,831,704 A * 11/1998 Yamada et al. 349/124
6,573,959 B1 * 6/2003 Molsen 349/113
6,654,090 B1 * 11/2003 Kim et al. 349/129

(75) Inventor: **Reiko Wachi, Matsumoto (JP)**
(73) Assignee: **Seiko Epson Corporation (JP)**
(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

FOREIGN PATENT DOCUMENTS

JP	5-45653	2/1993
JP	5-61049	3/1993
JP	6-34975	2/1994
JP	6-214234	8/1994
JP	7-199193	8/1995
JP	8-262445	10/1996
JP	2001-154198	6/2001
JP	2001-154199	6/2001

(21) Appl. No.: **10/345,110**
(22) Filed: **Jan. 15, 2003**

* cited by examiner

(65) **Prior Publication Data**
US 2003/0147027 A1 Aug. 7, 2003

Primary Examiner—Tarifur R. Chowdhury
Assistant Examiner—Andrew Schechter
(74) *Attorney, Agent, or Firm*—Harness, Dickey & Pierce, P.L.C.

(30) **Foreign Application Priority Data**
Jan. 15, 2002 (JP) 2002-006541
Nov. 27, 2002 (JP) 2002-343962


(51) **Int. Cl.**⁷ **G02F 1/1337; G02F 1/1335**
(52) **U.S. Cl.** **349/106; 349/129; 349/191**
(58) **Field of Search** **349/106, 129, 349/191**

(57) **ABSTRACT**

A color filter is provided on the surface of a substrate that opposes liquid crystals. The color filter has a surface profile defining the state of alignment of the liquid crystals. More specifically, the color filter has a plurality of alignment control protrusions whose top portions extend in one direction. A thin alignment film is formed so as to cover the color filter having such a surface profile.

(56) **References Cited**
U.S. PATENT DOCUMENTS
5,818,560 A * 10/1998 Kouno et al. 349/129

15 Claims, 16 Drawing Sheets







FIG. 1

FIG. 2






FIG. 3




FIG. 6




FIG. 7





FIG. 8

FIG. 9






FIG. 10




FIG. 11




FIG. 12

FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21





FIG. 22



**COLOR FILTER HAVING SURFACE
PROFILE FOR LIQUID CRYSTAL
ALIGNMENT, LIQUID CRYSTAL DISPLAY
PANEL, AND METHOD OF PRODUCING**

BACKGROUND OF THE INVENTION

1. Technical Field of the Invention

The present invention relates to a color filter substrate and a method of producing the same, a liquid crystal display panel using the color filter substrate, and an electronic apparatus.

2. Description of the Related Art

A liquid crystal display panel comprises a pair of substrates bonded together with a sealant, and liquid crystals sealed between both of the substrates. In order to define an alignment state of the liquid crystals when a voltage is not applied thereto, in general, the liquid crystal display panel is formed so that alignment films that are formed on the surfaces of the respective substrates opposing the liquid crystals using polyimide or the like are rubbed. The rubbing is an operation that is carried out on the surfaces of the alignment films in a certain direction with a rubbing cloth (buff cloth) wound upon a roller.

However, dust that is produced when the surfaces of the alignment films are rubbed with a rubbing cloth adheres to a display area, so that a reduction in the display quality, such as an uneven display, results. In addition, the surface states of the rubbed alignment films are determined by various conditions associated with rubbing, such as the strength or force with which the tip of the rubbing cloth contacts the surfaces of the alignment films, the material of the rubbing cloth, or how fast the alignment films are rubbed with the rubbing cloth. However, these conditions have many uncertainties, so that many of them are difficult to control qualitatively. For this reason, it becomes difficult to form alignment films of desired qualities, and therefore the yield of liquid crystal display panels is reduced. Further, when a liquid crystal display panel comprising a switching element such as a TFD (thin film diode) element or a TFT (thin film transistor) element is used, these switching elements may break due to static electricity that is produced when the alignment films are rubbed with a rubbing cloth. Accordingly, since various problems arise due to rubbing, there is a need for a technology for defining the state of alignment of liquid crystals without rubbing alignment films.

The present invention has been achieved in view of the above-described circumstances, and has as one object the provision of a color filter substrate which makes it possible to restrict the occurrence of problems caused by rubbing an alignment film, a method of producing the color filter substrate, a liquid crystal display panel using the color filter substrate, and an electronic apparatus.

SUMMARY OF THE INVENTION

To overcome the above-described problems, according to the present invention, there is provided a color filter substrate comprising one of a pair of substrates for sandwiching liquid crystals and color filters, the color filters are disposed on the surface of the one substrate that faces the liquid crystals, the color filters transmit light of a particular wavelength and have surface profiles defining a state of alignment of the liquid crystals.

With such a color filter substrate, since the surface profile of each color filter defines the state of alignment of the liquid

crystals, it is not necessary to rub an alignment film for defining the state of alignment of the liquid crystals. Therefore, the occurrence of the various problems caused by rubbing an alignment film, such as the adherence of dust that is produced as the alignment film is rubbed or electrostatic damage to a switching element, is eliminated, so that a high yield of color filter substrates can be maintained.

The surface of each color filter may have a profile defined by a plurality of alignment control protrusions whose top portions extend in one direction. By using this structure, it is possible to align (in parallel) liquid crystal molecules to which a voltage is not applied so that the long axes thereof are disposed along the aforementioned one direction. Alternatively, the surface of each color filter may have a profile defined by an alignment control protrusion having a plurality of surfaces that are inclined with respect to the surface of the one substrate and protruding towards a side away from the one substrate at an intersection line of each surface. By using this structure, it is possible to align (vertically) liquid crystal molecules to which a voltage is not applied so that the long axes thereof face a direction perpendicular to the inclined surfaces. The surface of each color filter may have a curved profile protruding towards a side away from the one substrate to similarly achieve vertical alignment.

According to another aspect of the present invention, there is provided a liquid crystal display panel comprising liquid crystals between a pair of opposing substrates, and color filters which are disposed on the surface of one of the pair of substrates that faces the liquid crystals. The color filters transmit light of a particular wavelength and have surface profiles defining a state of alignment of the liquid crystals.

In this liquid crystal display panel, since the surface profile of each color filter can define the alignment state of the liquid crystals, as in the color filter substrate described above, the occurrence of the various problems caused by rubbing an alignment film can be eliminated. In the liquid crystal display panel, the surface of each color filter may have a profile defined by a plurality of alignment control protrusions whose top portions extend in one direction; or the surface of each color filter may have a profile defined by an alignment control protrusion having a plurality of surfaces that are inclined with respect to the surface of the one substrate and protrude towards a side away from the one substrate at an intersection line of each surface; or the surface of each color filter may have a curved profile protruding towards a side away from the one substrate. In other words, the surface profile of each color filter may be selected so that the long axes of the molecules of the liquid crystals are substantially parallel, that is, so that they are aligned in parallel (or homogeneously) with respect to the surface of one of the substrates, or so that the long axes of the liquid crystal molecules are inclined, that is, so that they are aligned vertically (or homeotropically) with respect to the surface of one of the substrates. The state of alignment of the liquid crystals is not limited to these, so that the liquid crystal molecules may be aligned in other ways. In other words, the surface profile of each color filter is not limited to the above-described profiles, so that the liquid crystal molecules can be aligned in other desired directions as appropriate.

According to another aspect of the present invention, there is provided an electronic apparatus comprising the above-described liquid crystal display panel. As mentioned above, according to the liquid crystal display panel of the present invention, it is possible to eliminate a reduction in

the yield of color filter substrates, so that the cost of producing the electronic apparatus that incorporates the liquid crystal display panel can be reduced. Examples of such an electronic apparatus include a personal computer and a cellular phone.

According to another aspect of the present invention, there is provided a method of producing a color filter substrate including one of a pair of substrates for sandwiching liquid crystals and color filters which transmit light of a particular wavelength. The method comprises a first step of forming a resin layer on the surface of the one substrate that faces the liquid crystals, and a second step of selectively removing portions of the resin layer in order to form the color filters having surface profiles that define a direction of alignment of the liquid crystals.

According to this method, since color filters having surface profiles defining the direction of alignment of the liquid crystals are formed, it is not necessary to rub an alignment film. Therefore, it is possible to eliminate the occurrence of the various problems caused by the rubbing. In addition, since profiles for defining the direction of alignment of the liquid crystals are provided at the same time that the color filters are formed, the production process is simplified and production cost is reduced compared to the case where a member for defining the direction of alignment of the liquid crystals is formed separately from the color filter.

The second step may comprise removing a plurality of linear areas at a surface of the resin layer over a portion of the resin layer in the thickness direction thereof. Alternatively, the second step may comprise removing a portion of the resin layer with successively varying depths in accordance with locations of a surface of the resin layer. The portion of the resin layer that is removed is not limited to the aforementioned portions, so that a portion of the resin layer that is removed may be selected in accordance with the desired alignment state of the liquid crystal molecules as appropriate.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a sectional view of the structure of a liquid crystal display panel of a first embodiment of the present invention.

FIG. 2 is a perspective view of the structure of a portion of the liquid crystal display panel.

FIG. 3 is a sectional view showing in enlarged form color filters of the liquid crystal display panel.

FIG. 4 is a perspective view of the structure of the color filters of the liquid crystal display panel.

FIG. 5 is a sectional view showing in a further enlarged form one of the color filters of the liquid crystal display panel.

FIG. 6 is a sectional view illustrating a method of producing the liquid crystal display panel.

FIG. 7 is a sectional view illustrating the method of producing the liquid crystal display panel.

FIG. 8 is an enlarged view of color filters of a liquid crystal display panel of a second embodiment of the present invention.

FIG. 9 is a perspective view of the structure of the color filters of the liquid crystal display panel.

FIG. 10 is a sectional view illustrating a method of producing the liquid crystal display panel.

FIG. 11 is a sectional view illustrating the method of producing the liquid crystal display panel.

FIG. 12 is a sectional view of the structure of a modification of the liquid crystal display panel of the present invention.

FIG. 13 shows the structure of a modification of the color filter used in the present invention from three sides thereof.

FIG. 14 shows the structure of a modification of the color filter used in the present invention from three sides thereof.

FIG. 15 shows the structure of a modification of the color filter used in the present invention from three sides thereof.

FIG. 16 is a perspective view of the structure of a modification of the color filter used in the present invention.

FIG. 17 is a sectional view of the structure of a modification of the liquid crystal display panel of the present invention.

FIG. 18 is a graph showing the relationship between the height of an alignment control protrusion and the transmittance ratio in the modification.

FIG. 19 is a graph showing the relationship between the distance of the alignment control protrusion and the transmittance ratio in the modification.

FIG. 20 is a perspective view of the structure of a modification of the liquid crystal display panel of the present invention.

FIG. 21 is a perspective view of the structure of a personal computer that is an example of an electronic apparatus to which the liquid crystal display panel of the present invention is applied.

FIG. 22 is a perspective view of the structure of a cellular phone that is an example of an electronic apparatus to which the liquid crystal display panel of the present invention is applied.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hereunder, a description of various embodiments of the present invention will be given with reference to the drawings. The embodiments are some forms of the present invention, and do not limit the scope of the invention, so that any modifications may be made within the scope of the present invention. In each of the figures below, in order to illustrate each layer and each member with recognizable sizes, the scales of each layer and each member are different.

A: First Embodiment

First, the form in which the present invention is applied to an active matrix liquid crystal display panel will be described. Hereunder, the case where a TFD (thin film diode) element, which is a two-terminal switching element, is used as a switching element will be used as an example. A liquid crystal display panel that is described below is what is called a transreflective liquid crystal display panel which can perform a display operation both by reflecting outside light, such as sunlight or illumination light inside a room, and by transmitting irradiation light from a backlight unit.

A-1: Structure of Liquid Crystal Display Panel

FIG. 1 is a sectional view of the structure of the liquid crystal display panel of the embodiment. As shown in FIG. 1, a liquid crystal display panel 1 comprises a first substrate 10 and a second substrate 20 that oppose each other and that are bonded with a sealant 30, and liquid crystals 40 that are sealed in an area surrounded by both of the substrates and the sealant 30. Hereunder, as shown in FIG. 1, the side of the first substrate 10 opposite the liquid crystals 40 is indicated as "viewer side." In other words, the "viewer side" means the side where a viewer views a display of the liquid crystal

display panel **1**. On the other hand, the side of the second substrate **20** opposite the liquid crystals **40** is indicated as “back side.”

The first substrate **10** and the second substrate **20** are light-transmissive plate-shaped members formed of, for example, glass, quartz, or plastic. Polarizers **101** and **201** for polarizing incident light are bonded to the outer sides (sides opposite to the liquid crystals **40**) of the respective first substrate **10** and the second substrate **20**. Similarly, retardation films **102** and **202** for compensating for interference color are bonded to the outer sides of the respective first substrate **10** and the second substrate **20**. Although, a backlight unit (illuminator) is actually disposed at the back side of the liquid crystal display panel **1**, it is not shown in FIG. **1**.

FIG. **2** is a perspective view showing in enlarged form the main portion of the liquid crystal display panel **1**. The sectional view taken along line I—I in FIG. **2** corresponds to FIG. **1**. For simplification, in FIG. **2**, the polarizers **101** and **201**, the retardation films **102** and **202**, etc., are not shown. As shown in FIGS. **1** and **2**, a plurality of pixel electrodes **11**, disposed in a matrix, and a plurality of scanning lines **12**, extending in one direction (in direction Y in FIG. **2**) in the gaps between the pixel electrodes **11**, are formed on the inside surface of the first substrate **10**. Each pixel electrode **11** is a substantially rectangular electrode formed of, for example, a transparent conductive material such as ITO (indium tin oxide).

As shown in FIG. **2**, each pixel electrode **11** and a scanning line **12** adjacent to the pixel electrode **11** are connected together through a TFD element **13**. Each TFD element **13** is a two-terminal switching element having a nonlinear current-voltage characteristic. As shown in FIG. **1**, the surface of the first substrate **10** having the pixel electrodes **11**, the scanning lines **12**, and the TFD elements **13** formed thereon is covered with an alignment film **14** (not shown in FIG. **2**). The alignment film **14** is a thin organic film, such as a polyimide film, and is rubbed for defining the state of alignment of the liquid crystals **40** when a voltage is not applied thereto.

On the other hand, as shown in FIG. **1**, a reflective layer **21**, light-shielding layers **22**, color filters **23** (**23R**, **23G**, and **23B**), data lines **24**, and an alignment film **25** are formed on the inside surface (that is, the surface at the side of the liquid crystals **40**) of the second substrate **20** in that order as viewed from the side of the second substrate **20**. As shown in FIG. **2**, the data lines **24** are stripe-shaped electrodes formed of transparent conductive materials such as ITO, and are formed above the surfaces of the color filters **23** and light-shielding layers **22**. The data lines **24** extend in a direction in which they intersect the scanning lines **12** (in a direction X shown in FIG. **2**), and oppose the pixel electrodes **11** arranged in rows on the first substrate **10**. In such a structure, the direction of alignment of the liquid crystals **40** that are sandwiched by the first substrate **10** and the second substrate **20** changes by application of a voltage between the pixel electrodes **11** and the data lines **24** opposing the pixel electrodes **11**. In other words, as shown in FIG. **2**, the areas where the pixel electrodes **11** and the respective data lines **24** oppose are disposed in a matrix, and function as sub-pixels **7**. In other words, the sub-pixels **7** are the smallest unit areas where the direction of alignment of the liquid crystals changes in accordance with the application of voltage.

As shown in FIG. **1**, the surfaces of the color filters **23** and light-shielding layers **22** where the data lines **24** are formed

are covered with the alignment film **25**. The alignment film **25** is the same as the alignment film **14** in that it is a thin organic film formed of polyimide or the like, but differs from it in that it is not rubbed.

The reflective layer **21** is formed of, for example, a single metal, such as aluminum or silver, or an alloy containing any one of these metals as a main component, and is a thin film that has light reflectivity. Light (such as illumination light inside a room or sunlight) incident upon the liquid crystal display panel **1** from the viewer side is reflected at the surface of the reflective layer **21**. The light exits from the reflective layer **21** and is viewed by a viewer, so that the liquid crystal display panel **1** performs a displaying operation by reflection. The inside surface of the second substrate **20** is made rough (not shown), so that the surface of the reflective layer **21** has a scattering structure in correspondence with this rough surface.

As shown in FIGS. **1** and **2**, light-transmissive sections **211** are provided at the portions of the reflective layer **21** near the central portions of the respective sub-pixels **7**. The light-transmissive sections **211** are openings for transmitting light incident upon the liquid crystal display panel **1** from the back surface side thereof towards the viewer side. In other words, illumination light from the backlight unit exits towards the viewer side through the light-transmissive sections **211** of the reflective layer **21**. The light is viewed by a viewer, so that the liquid crystal display panel **1** performs a display operation by transmission.

The light-shielding layers **22** are formed in the form of a lattice so as to overlap the gaps between the sub-pixels **7** disposed in a matrix (that is, the areas other than the areas where the pixel electrodes **11** and the respective data lines **24** oppose each other), and have the role of shielding the gaps between the sub-pixels **7** from light. The light-shielding layers **22** are formed of a resin material containing black coloring material, such as carbon black or a pigment, or a metal such as chromium (Cr).

The color filters **23** are resin layers formed in correspondence with the respective sub-pixels **7**, and are colored red (R), green (G), or blue (B) with a dye or a pigment. In other words, the color filters **23** of the respective colors selectively transmit light having wavelengths of the respective colors. By the three types of sub-pixels **7R**, **7G**, and **7B** corresponding to the color filters **23** of the respective three colors, red, green, and blue, one pixel (dot), which is the smallest unit of display, is formed. In the embodiment, as shown in FIG. **2**, the case using a structure in which color filters **23** of the same color are disposed over a plurality of sub-pixels **7** that form rows in the direction of extension of the scanning lines **12** (that is, what is called a stripe arrangement) is taken as an example.

FIG. **3** is a sectional view showing in enlarged form each element on the second substrate **20**, and FIG. **4** is a perspective view of the structures of the color filters **23**. The sectional view from line III—III in FIG. **4** corresponds to FIG. **3**. In these figures, an element that is associated with one pixel formed by three sub-pixels **7** corresponding to the three colors, red, green, and blue, is shown.

As shown in FIG. **3**, protrusions **231** (hereinafter referred to as “alignment control protrusions”) are formed at the surfaces of the color filters **23** of the respective colors. As shown in FIG. **4**, the alignment control protrusions **231** have profiles in which top portions **233** appear as protruding portions extending in the direction Y when viewed from other portions of the surfaces of the color filters **23**. In other words, it can be said that grooves **232** that are lower than the

top portions **233** of the alignment control protrusions **231** extend in one direction at portions of the surfaces of the color filters **23** other than where the alignment control protrusions **231** are formed. The heights of the top portions **233** of the respective alignment control protrusions **231** when viewed from the bottoms of the respective grooves **232** are each on the order of $1\ \mu\text{m}$, and the distances between the alignment control protrusions **231** (that is, the widths of the grooves **232**) are each on the order of $20\ \mu\text{m}$.

As shown in FIG. 3, the data lines **24** and the alignment films **25** are formed as thin films on the surfaces of the color filters **23** where the alignment control protrusions **231** are formed. Therefore, protrusions that correspond with the alignment control protrusions **231** (or depressions that correspond with the grooves **232**) are formed at the surface of the alignment film **25**. As a result, the long axes of the molecules of the liquid crystals **40** near the alignment film **25** are aligned along the protrusions and depressions extending along the surface of the alignment film **25**. In other words, when a voltage is not applied to the liquid crystals **40**, the long axes of the liquid crystals **40** are aligned homogeneously along the extending direction of the alignment control protrusions **231**, or parallel to the surface of the second substrate **20**.

Accordingly, in the embodiment, since the surfaces of the color filters **23** have profiles that allow the state of alignment of the liquid crystals to be defined, it is not necessary to rub the alignment film **25**. Therefore, various problems caused by rubbing the alignment film **25**, such as the adherence of dust or production of static electricity, can be effectively restricted.

The action of defining the direction of alignment of liquid crystal molecules **41** (hereinafter referred to as the "alignment control action") increases with the increasing area of contact of the liquid crystals **40** with the alignment film **25**. Therefore, it is desirable to select the distances between adjacent alignment control protrusions **231** (the widths of the grooves **232**) and the sizes of the alignment control protrusions **231** at the surfaces of the color filters **23** as follows.

First, it is desirable for a width W of each alignment control protrusion **231** shown in FIG. 5 to be small. More specifically, if the width of each alignment control protrusion **231** is less than about of $10\ \mu\text{m}$, a proper alignment control action for providing a displayed image with sufficient contrast is realized. It is presently difficult to make the width of each alignment control protrusion **231** smaller than $1\ \mu\text{m}$ due to manufacturing technological reasons. Therefore, it is desirable for the width W of each alignment control protrusion **231** to be from $1\ \mu\text{m}$ to $10\ \mu\text{m}$ inclusive.

Next, it is desirable for a height H of each alignment control protrusion **231** shown in FIG. 5 to be large. However, the height H of each alignment control protrusion **231** cannot be made larger than a cell gap (the thickness of the layer of the liquid crystals **40**). In general, the thickness of the cell gap is on the order of from $3\ \mu\text{m}$ to $5\ \mu\text{m}$ inclusive, so that it is desirable for each height H to be less than about $3\ \mu\text{m}$. However, when the height H of each alignment control protrusion **231** is made too small, stepped portions (heights H) formed by the grooves **232** and the top portions **233** are leveled by the data lines **24** and the alignment film **25**, which are formed on the color filters **23**, so that an alignment control action may not occur. Therefore, it is desirable for each height H to be larger than the sum total of the thickness of the data line **24** and the thickness of the alignment film **25**. In general, the thickness of each data line

24 is on the order of $0.1\ \mu\text{m}$, and the thickness of the alignment film **25** is on the order of $0.05\ \mu\text{m}$. Therefore, if each height H is on the order of $1\ \mu\text{m}$, which is sufficiently larger than the sum total ($0.15\ \mu\text{m}$) of the thickness of the data line **24** and the alignment film **25**, a sufficient alignment control action occurs. Accordingly, it is desirable for the height H of each alignment control protrusion **231** to be from $1\ \mu\text{m}$ to $3\ \mu\text{m}$ inclusive.

It is desirable that a distance D (see FIG. 5) between adjacent alignment control protrusions **231** be small. More specifically, if each distance D is less than about $70\ \mu\text{m}$, a proper alignment control action for providing a display image with sufficient contrast is realized. On the other hand, if each distance D is made too small, the surface of the alignment film **25** is subjected to a leveling operation without the data lines **24** and the alignment film **25** entering the stepped portions formed by the grooves **232** and the top portions **233**, so that a desired alignment control action may not occur. To prevent this, it is desirable for each distance D to be greater than twice the sum total of the thickness of the data line **24** and the thickness of the alignment film **25**. For example, in the case where the sum total of the thickness of a data line **24** and the thickness of the alignment film **25** is on the order of $0.15\ \mu\text{m}$, when each distance D is on the order of $3\ \mu\text{m}$, a sufficient alignment control action occurs. Accordingly, it is desirable for each distance D between adjacent alignment control protrusions **231** to be from $3\ \mu\text{m}$ to $70\ \mu\text{m}$ inclusive.

A-2: Method of Producing Liquid Crystal Display Panel

Next, a method of producing the liquid crystal display panel **1** of the above embodiment will be described with reference to FIGS. 6 and 7. However, since each element on the first substrate **10** can be produced using various known technologies, the method of producing these elements will not be described. Hereunder, the method of producing each element on the second substrate **20** will be primarily described.

A thin metallic film having light reflectivity is formed so as to cover the entire surface of the second substrate **20** facing the first substrate **10** by sputtering. Then, by patterning the thin film by photolithography and etching, as in Step a in FIG. 6, a reflective layer **21** having light-transmissive sections **211** formed in correspondence with respective sub-pixels is formed. In order to form the surface of the reflective layer **21** with a scattering structure, it is desirable to roughen the surface of the second substrate **20** prior to forming the reflective layer **21**. Alternatively, it is possible to form a resin layer covering the surface of the second substrate **20** prior to forming the reflective layer **21** and to roughen the surface of the resin layer.

Next, a thin chromium (Cr) film is formed by sputtering so as to cover the second substrate **20** having the reflective layer **21** formed thereon. Thereafter, by patterning the thin film by photolithography and etching, as in Step b in FIG. 6, light-shielding layers **22** that are arranged in the form of a lattice as a result of overlapping the gaps between the respective sub-pixels **7** are formed. Here, although the light-shielding layers **22** are formed of chromium, they may be formed of resin materials that have been colored black by, for example, carbon black. Alternatively, the light-shielding layers **22** may be formed by stacking color filters **23R**, **23G**, and **23B** of three colors, which are formed in a later step, at the gaps between the respective sub-pixels **7**.

Next, as described in detail below, the color filters **23R**, **23G**, and **23B** of the corresponding three colors, red, green, and blue, are successively formed onto the surface of the

second substrate **20**. Here, although the red color filter **23R**, the green color filter **23G**, and the blue color filter **23B** are successively formed in that order, the order in which the color filters **23** of the respective colors are formed is not limited to this.

As in Step c shown in FIG. 6, first, a resin layer **61** is formed so as to cover the entire surface of the second substrate **20**. The resin layer **61** is formed of a resin material, such as acrylic resin or epoxy resin, that is colored red by a pigment and to a thickness on the order of $2\ \mu\text{m}$. Here, the resin layer **61** is formed of a negative resin material that hardens when it reacts to light as it is exposed. Next, as in Step d shown in FIG. 6, the resin layer **61** is irradiated with ultraviolet light through a mask **62**. As shown in FIG. 6, a light-transmissive section **621** transmitting ultraviolet light is formed in the mask **62** so as to overlap the area of the resin layer **61** where the red color filter **23R** is to be formed (that is, the area of the resin layer **61** corresponding to a sub-pixel **7R**). The other portions of the mask **62** intercept ultraviolet light heading towards the areas of the resin layer **61** where the green and blue color filters **23G** and **23B** are to be formed and the light-shielding layers **22**. The amount of exposure to the area of the resin layer **61** where the red color filter **23R** is to be formed is adjusted so that only a portion of the resin layer **61** in the thickness direction (having a thickness on the order of $1\ \mu\text{m}$) is hardened by reacting to light, that is, so that not all of the portions of the resin layer **61** in the thickness direction are hardened. In FIG. 6, the portion of the resin layer **61** that is hardened by the exposure step is hatched.

Next, as in Step e shown in FIG. 7, the resin layer **61** is irradiated with ultraviolet light through a mask **63** that is different from the mask **62**. As shown in FIG. 7, light-transmissive sections **631** are formed in the mask **63** so as to overlap the areas where the alignment control protrusions **231** are to be formed in the area where the red color filter **23R** is to be formed. In other words, the areas other than where the alignment control protrusions **231** are to be formed in the area where the red color filter **23R** is to be formed, the areas where the green and blue color filters **23G** and **23B** are to be formed, and the areas where the light-shielding layers **22** are formed are not irradiated with ultraviolet light. As shown by hatching in FIG. 7, in the exposure step, the amount of exposure is adjusted so that the portion that hardens by reacting to light reaches the surface of the resin layer **61**.

Next, the resin layer **61** is developed, and is removed while leaving the portion thereof that has been hardened by the exposure. As in Step f shown in FIG. 7, by the developing step, the portions of the resin layer **61** other than where the red sub-pixel **7R** is formed are removed, and a plurality of linear portions at the surface of the portion of the resin layer **61** corresponding to where the red sub-pixel **7R** is formed (the portions corresponding to where the grooves **232** are formed) are removed over a portion of the resin layer **61** in the thickness direction. As a result, the red color filter **23R** having the plurality of alignment control protrusions **231** whose top portions extend in one direction is formed.

Thereafter, the green and blue color filters **23G** and **23B** are successively formed by the same procedure used to form the red color filter **23R** as illustrated in Steps c and d in FIG. 6 and Steps e and f in FIG. 7. In other words, first, a resin layer corresponding to each color is formed over the entire surface of the second substrate **20**. Second, a portion of the area in the thickness direction where the color filter **23** of the corresponding color is to be formed is hardened. Third, areas where the alignment control protrusions **231** are formed in the area where the color filter **23** is to be formed are

hardened. Fourth, the resin layer is developed. By repeating these steps, the three types of color filters, the red, green, and blue color filters **23R**, **23G**, and **23B** are formed as in Step g shown in FIG. 7.

Here, although the color filters **23** are formed of negative resin materials, they may be formed of positive resin materials that soften by reacting to light as they are exposed. In this case, the exposure illustrated in Step d shown in FIG. 6 is carried out using a mask having the light-transmissive sections **621** and the other portions of the mask **62** reversed, and the exposure illustrated in Step e shown in FIG. 7 is carried out using a mask having the light-transmissive sections **631** and the other portions of the mask **63** reversed.

Next, a thin film formed of ITO is formed so as to cover the color filters **23** and the light-shielding layers **22**. After forming data lines **24** by patterning the thin film, an alignment film **25** is formed so as to cover these data lines **24** (see FIG. 3). As mentioned above, the alignment film **25** is not rubbed.

The above-described method is the method of producing each element on the second substrate **20**. Thereafter, the second substrate **20** that has been subjected to the above-described method and the first substrate **10** having formed thereon the pixel electrodes **11**, the scanning lines **12**, the TFD elements **13**, and the alignment film **14** are bonded together with the sealant **30** with their electrode surfaces opposing each other. By sealing the liquid crystals **40** in the area that is surrounded by both substrates and the sealant **30**, and bonding the retardation films **102** and **202** and the polarizers **101** and **102**, the liquid crystal display panel **1** shown in FIG. 1 is produced.

In this manner, according to the method of producing the liquid crystal display panel of the embodiment, it is not necessary to rub the alignment film **25** on the second substrate **20**, so that it is possible to prevent the occurrence of the various problems caused by rubbing the alignment film **25**, such as a reduction in yield, adherence of dust that is produced as the alignment film is rubbed or damage to the TFD elements **13** due to production of static electricity.

In order for the surface profile of the alignment film **25** to define the state of alignment of the liquid crystals **40** without rubbing it, the following method may be carried out. Protrusions are formed on the color filters **23** and the light-shielding layers **22** using, for example, another piece of resin material that is different from those used to form the color filters **23** and the light-shielding layers **22**, and the alignment film **25** is formed so as to cover the protrusions. However, in order to form the protrusions, the step of forming the resin layer using a resin material and the step of forming the protrusions by selectively removing portions of the resin layer are required.

In contrast to this, according to the method of producing the liquid crystal display panel of the embodiment, the alignment control protrusions **231** for defining the state of alignment of the liquid crystals **40** are formed at the same time that the color filters **23** are formed. Therefore, compared to the case where the alignment control protrusions **231** are formed independently of the color filters **23**, the production process can be simplified, so that production costs can be reduced.

B: Second Embodiment

B-1: Structure of Liquid Crystal Display Panel

Next, a description of a liquid crystal display panel of a second embodiment of the present invention will be given. Apart from the profiles of the color filters, the liquid crystal display panel of the second embodiment has the same

structure as the liquid crystal display panel **1** of the first embodiment shown in FIG. **1**. Therefore, hereunder, only the profiles of the color filters of the liquid crystal display panel of the second embodiment will be described, and the other structural features will not be described below. In the figures

illustrated below, component parts of the liquid crystal display panel of the second embodiment corresponding to those of the liquid crystal display panel of the first embodiment are given the same reference numerals.

FIG. **8** is a sectional view showing in enlarged form each element on a second substrate **20** of the liquid crystal display panel of the second embodiment, and corresponds to FIG. **3** illustrating the first embodiment. FIG. **9** is a perspective view of the structure of the color filters corresponding to one pixel, and corresponds to FIG. **4** illustrating the first embodiment. FIG. **8** is a sectional view from line VIII—VIII in FIG. **9**.

As shown in FIGS. **8** and **9**, color filters **26** (**26R**, **26G** and **26B**) used in the second embodiment each have an alignment control protrusion **261** whose top portion extends in a direction **Y**. In other words, each alignment control protrusion **261** has two surfaces **262** and **263** that are inclined with respect to the surface of the second substrate **20**. An intersection line **264** extending in the direction **Y** is formed at the surfaces **262** and **263**, and each alignment control protrusion **261** is such as to protrude towards the viewer at the intersection line **264**. In other words, looking at the cross section of the color filters **26**, as shown in FIG. **8**, it can be said that each color filter **26** is substantially pentagonal in cross section having one of the apices protruding towards the viewer.

As shown in FIG. **8**, data lines **24** and an alignment film **25** are formed as thin films on the surfaces of the color filters **26** having the respective alignment control protrusions **261**. Therefore, protrusions that are in correspondence with the alignment control protrusions **261** are formed at the surface of the alignment film **25**. As a result, as shown by broken lines in FIG. **8**, the long axes of molecules **41** of liquid crystals **40** near the alignment film **25** are disposed in an upstanding state in directions that are perpendicular to the inclined surfaces **262** and **263** of each alignment control protrusion **261**, respectively. In other words, when a voltage is not applied to the liquid crystals **40**, the liquid crystals **40** are disposed homeotropically, that is, the long axes of the liquid crystals **40** are tilted (vertically) with respect to the surface of the second substrate **20**.

In the second embodiment, as in the first embodiment, the color filters **26** have surface profiles that can define the state of alignment of the liquid crystals **40**, so that it is not necessary to rub the alignment film **25**. Therefore, it is possible to prevent the occurrence of the various problems caused by rubbing the alignment film **25**.

B-2: Method of Producing the Color Filters **26**

Next, a method of producing the liquid crystal display panel of the second embodiment will be described. However, apart from the steps of producing the color filters **26**, the method of producing the liquid crystal display panel of the second embodiment is the same as the method of producing the liquid crystal display panel of the first embodiment, so that only the method of producing the color filters **26** will be described. As a result, the method of producing the other component parts will not be described below.

First, after forming a reflective layer **21** and light-shielding layers **22** onto the second substrate **20** by Steps a and b shown in FIG. **6**, a resin layer **61** that has been colored

red is formed so as to cover the entire surface of the second substrate **20** as in Step a shown in FIG. **10**. Next, as in Step b shown in FIG. **10**, the resin layer **61** is irradiated with ultraviolet light through a mask **62**. As in the first embodiment, a light-transmissive section **621** is formed in a portion of the mask **62** so as to overlap an area of the resin layer **61** where the red color filter **26R** is to be formed. Ultraviolet light traveling towards the other portions is intercepted. The amount of exposure to the area of the resin layer **61** where the red color filter **26R** is to be formed is adjusted so that only a portion of the resin layer **61** in the thickness direction (having a thickness of the order of $1\ \mu\text{m}$) is hardened by reacting to light. In FIG. **10**, the portion of the resin layer **61** that is hardened by the exposure step is hatched.

Next, as in Step c shown in FIG. **10**, the resin layer **61** is irradiated with ultraviolet light through a mask **64** that is different from the mask **62**. As shown in FIG. **10**, a light-transmissive section **641** transmitting ultraviolet light is provided in the area of the resin layer **61** where the red color filter **26R** is formed. However, the optical density of the light-transmissive section **641** is a minimum at a location thereof overlapping the top portion of the alignment control protrusion **261** in the area where the red color filter **26R** is formed, with the optical density becoming progressively smaller with increasing distance from this location towards the edges of the color filter **26**. Therefore, the exposure amount of ultraviolet light to the area of the resin layer **61** where the red color filter **26R** is to be formed becomes a maximum at a location corresponding to the top portion of the alignment control protrusion **261**, and becomes progressively smaller with increasing distance from this location. Due to the exposure light, as shown by hatching in Step c shown in FIG. **10**, the triangular portion of the resin layer **61** corresponding to the alignment control protrusion **261** is hardened.

Next, the resin layer **61** is developed, and is removed while leaving the portion thereof that has been hardened by the exposure. As shown in Step d shown in FIG. **11**, by the developing step, the portions of the resin layer **61** other than where a red sub-pixel **7R** is formed are removed, and portions of the red sub-pixel element **7R** are removed with progressively varying depths in accordance with the locations of the surface of the resin layer **61**. As a result, the red color filter **26R** having a substantially triangular cross-section alignment control protrusion **261** is produced.

Thereafter, the green color filter **26G** and the blue color filter **26B** are successively formed by the same procedure as that used to form the red color filter **26R** as illustrated in Steps a and b in FIG. **10** and Step d in FIG. **11**. As a result, as in Step e shown in FIG. **11**, the color filters **26R**, **26G**, and **26B** having the respective alignment control protrusions **261** for the three colors, red, green, and blue, are produced. Next, by the same procedures as those in the first embodiment, data lines **24** and an alignment film **25** are formed on the surfaces of the color filters **26** and the light-shielding layers **22**.

In this way, according to the second embodiment, it is not necessary to rub the alignment film **25** on the second substrate **20**, so that it is possible to prevent the occurrence of various problems caused by rubbing the alignment film **25** as in the first embodiment. Therefore, compared to the case where the protrusions for controlling the alignment of the liquid crystals **40** are formed independently of the color filters **26**, the production process can be simplified, so that production costs can be reduced.

C: Modification

Although the present invention is described with reference to embodiments, the above-described embodiments are used merely for illustrative purposes, so that the embodiments may be variously modified without departing from the gist of the present invention. Examples of the modifications are given below.

C-1: First Modification

In each of the above-described embodiments, a structure having color filters and light-shielding layers provided on the second substrate **20** disposed at the back side of the liquid crystal display panel is taken as an example. However, the color filters and light-shielding layers may be formed on the first substrate **10** disposed at the viewer side. FIG. **12** is a sectional view of the structure of a first modification of the liquid crystal display panel.

As shown in FIG. **12**, in a liquid crystal display panel **1'**, light-shielding layers **16** and color filters **17** are formed on the surface of a first substrate **10** disposed at the viewer side. The color filters **17** each have an alignment control protrusion for defining the state of alignment of liquid crystals **40** when a voltage is not applied thereto. In other words, the color filters **17** have the same profiles as either the color filters **23** shown in FIGS. **3** and **4** or the color filters **26** shown in FIGS. **8** and **9**. Pixel electrodes **11**, scanning lines **12**, TFD elements **13**, and an alignment film **14** are formed at the surfaces of the color filters **17** and the light-shielding layers **16**. Depressions and protrusions that correspond with the alignment control protrusions at the surfaces of the color filters **17** are formed at the surface of the alignment film **14**. The state of alignment of the liquid crystals **40** is defined by the protrusions and depressions, so that it is not necessary to rub the alignment film **14**.

On the other hand, a reflective layer **21** that is provided on the inside surface of the second substrate **20** is covered by an insulating layer **27** formed of, for example, a resin material. Data lines **24** and an alignment layer **25** are provided on the surface of the insulating layer **27**. The alignment film **25** is rubbed for defining the state of alignment of the liquid crystals **40**.

Accordingly, even if the color filters **17** and light-shielding layers **16** are provided on the first substrate **10** disposed at the viewer side, the same advantages as those of the first and second embodiments are provided. The color filter substrate of the present invention means the substrate where the color filters are provided regardless of whether it is disposed at the viewer side or the back side of the liquid crystal display panel.

C-2: Second Modification

In the first embodiment, the structure in which stripe-shaped alignment control protrusions **231** are provided at the surfaces of the color filters **23** and the liquid crystals are homogeneously aligned is taken as an example. In the second embodiment, the structure in which triangular cross section alignment control protrusions **261** are provided at the surfaces of the color filters **26** and the liquid crystals are aligned vertically is taken as an example. However, the surface profiles of the color filters (that is, the profiles of the alignment control protrusions) and the state of alignment of the liquid crystals are not limited thereto. In other words, the state of alignment of the liquid crystals may be different from those mentioned above, and it is desirable for the surface profiles of the color filters to be selected in accordance with the desired state of alignment. For example, in order to align the liquid crystals **40** vertically as in the second embodiment, the color filters **26** may have the

profiles shown in FIGS. **13** to **15**. In FIGS. **13** to **15**, only the color filter **26** corresponding to one sub-pixel **7** is shown. The color filter **26** shown in FIG. **13** has an alignment control protrusion **261a** having a substantially quadrangular pyramidal profile defined by four planes that are inclined with respect to the plate face of the second substrate **20**. The color filter **26** shown in FIG. **14** is formed by four planes that are inclined with respect to the plate face of the second substrate **20**, and has an alignment control protrusion **261b** where two of the planes intersect at a straight line. As shown by broken lines in FIGS. **13** and **14**, it is possible to align liquid crystal molecules **41** substantially perpendicular to each of the four planes forming the alignment control protrusion **261a** of the color filter **26** shown in FIG. **13** or the alignment control protrusion **261b** of the color filter **26** shown in FIG. **14**. On the other hand, as shown in FIG. **15**, an alignment control protrusion **261c** having a curved portion that protrudes in a direction opposite to the second substrate **20** may be used.

As shown in FIG. **16**, a structure having an alignment control protrusion **261d** provided on a portion of each color filter **26** in the widthwise direction may be used. Each color filter **26** shown in FIG. **16** has a planar portion **265** extending parallel to the plate face of the second substrate **20** in addition to an alignment control protrusion **261** similar to that used in the second embodiment having inclined surfaces **262** and **263**. In this structure, the liquid crystal molecules **41** are aligned in a direction perpendicular to the inclined surfaces **262** and **263** of each alignment control protrusion **261d**.

Although, in each of the embodiments and modifications, the structure in which the alignment film **14** on the first substrate **10** is rubbed is used, as shown in FIG. **17**, an alignment control protrusion **117** similar to the alignment control protrusion **261d** (**261**, or **261a** to **261c**) of each color filter **26** may also be provided on the first substrate **10**. More specifically, the alignment control protrusion **117** is formed of a resin material, such as acrylic resin or epoxy resin, by the same production process as that used in the first embodiment or the second embodiment. According to this structure, the direction of alignment of the liquid crystal molecules **41** near the first substrate **10** is determined by the alignment control protrusion **117**, so that it is not necessary to rub the alignment film **14**.

In the structure having the alignment control protrusion **117** provided on the first substrate **10**, as shown in FIG. **17**, the top portion of the alignment control protrusion **117** and the top portion of an alignment control protrusion **261d** on the second substrate **20** may be such as not to overlap each other as viewed from a direction perpendicular to the plate face. More specifically, the alignment control protrusion **117** on the first substrate **10** is made to oppose a planar portion **265** of a color filter **26** on the one hand, and the alignment control protrusion **261d** on the second substrate **20** is made to oppose the area of the first substrate **10** where the alignment control protrusion **117** is not provided so that the alignment control protrusion **117** is offset from the alignment control protrusion **261d**.

As in the second embodiment and as shown in FIGS. **13** to **16**, in the structure comprising alignment control protrusions **261** (including alignment control protrusions **261a**, **261b**, and **261c**) that have inclined surfaces with respect to the second substrate **20**, it is desirable to select the height of each alignment control protrusion **261** as follows. Here, FIG. **18** is a graph showing the relationship between a height **H** of each alignment control protrusion **261** shown in FIG. **17** and the transmittance ratio of the liquid crystal display

panel. FIG. 18 shows the transmittance ratio characteristics when voltages having three different values are applied to the liquid crystals 40. As is clear from FIG. 18, the transmittance ratio of the liquid crystal display panel increases as the height H of each alignment control protrusion 261 increases. Therefore, in the structure comprising alignment control protrusions 261 having inclined surfaces with respect to the second substrate 20, it is desirable for the height H of each alignment control protrusion 261 to be large. However, it is necessary to make the height H smaller than a cell gap.

When the structure shown in FIG. 17 is used, it is desirable to select a distance D between an alignment control protrusion 117 on the first substrate 10 and an alignment control protrusion 261 on the second substrate 20 as follows. FIG. 19 is a graph showing the relationship between the distance D and the transmittance ratio of the liquid crystal display panel. Like FIG. 18, FIG. 19 shows the characteristics when voltages having three different values are applied to the liquid crystals 40. As shown in FIG. 19, when the distance D is approximately equal to or less than 30 μm , the transmittance ratio increases as the distance D increases. On the other hand, when the distance D exceeds a value of approximately 30 μm , the transmittance ratio becomes substantially constant regardless of the distance D. Therefore, in order to maintain both the transmittance ratio and the liquid crystal alignment action at a high level, it is desirable for the distance D to be on the order of from 20 μm to 40 μm , and, more desirably, on the order of 30 μm .

C-3: Third Modification

On the other hand, it is desirable to properly select the direction in which the alignment film 14 on the first substrate 10 is rubbed so that the liquid crystals 40 are aligned in the desired direction due to its relationship with the extending direction of each alignment control protrusion 231 (or 261). For example, the alignment film 14 may be rubbed in a direction that is substantially parallel to the extending direction of each alignment control protrusion 231 or 261, or at a certain angle from the direction of extension of each alignment control protrusion 231 or 261. As in the second embodiment, when the liquid crystals 40 (liquid crystal molecules 41) are aligned vertically, it is not necessary to rub the alignment film 14.

C-4: Fourth Modification

Although, in each embodiment and each modification, a transmissive liquid crystal display panel which performs a display operation both by transmission and reflection using a reflective layer 21 having light-transmissive sections 211 is taken as an example, the present invention may be applied to a reflective liquid crystal display panel which performs a displaying operation only by reflection using a reflective layer not having light-transmissive sections 211 or to a transmissive liquid crystal display panel which does not have a reflective layer 21 and which performs a displaying operation only by transmission. In addition, although, in each embodiment and each modification, the case where a stripe arrangement in which color filters of the same color form a row is taken as an example, other arrangements, such as a mosaic arrangement or a delta arrangement, may be used for the arrangement of the color filters. The present invention is also applicable to a liquid crystal display panel using a three-terminal switching element that is typified by a TFT (thin film transistor) element, and to a passive matrix liquid crystal display panel not including a switching element. In this way, the present invention is applicable to any substrate or any liquid crystal display panel as long as they

are a color filter substrate having color filters formed thereon and a liquid crystal display panel using the color filter substrate, respectively, regardless of whether other structural elements are used.

The present invention is also applicable to an IPS (in plane switching) liquid crystal display panel. FIG. 20 is a perspective view showing part of the structure of this type of liquid crystal display panel when the present invention is applied thereto. As shown in FIG. 20, a color filter 23 has a surface profile for homogeneously aligning liquid crystal molecules 41. More specifically, a plurality of alignment control protrusions 231 extending in one direction are provided at the surface of the color filter 23. As shown by hatching in FIG. 20, a pixel electrode 281 and a common electrode 282 are provided on the surface of the color filter 23. The pixel electrode 281 and the common electrode 282 are substantially linear electrodes extending in a direction that is perpendicular to the direction of extension of the alignment control protrusions 231. The surface of the color filter 23 having these electrodes formed thereon is covered by an alignment film 25. On the other hand, although an alignment film is provided on the surface of a first substrate (not shown) opposing a second substrate 20, an electrode is not provided on the first substrate. In this structure, when a voltage is not applied between the pixel electrode 281 and the common electrode 282, as shown by broken lines in FIG. 20, the long axes of the liquid crystal molecules 41 align in a direction that is substantially perpendicular to the extending direction of the alignment control protrusions 231. On the other hand, when a transverse (horizontal) electrical field is produced between the pixel electrode 281 and the common electrode 282 as a result of application of a voltage therebetween, the liquid crystal molecules 41 rotate along the direction of the electrical field in a plane that is parallel to the plate face of the second substrate 20. Even in this structure, the same advantages as those that are provided by each of the above-described embodiments are provided.

D: Electronic Apparatus

Next, an electronic apparatus using the liquid crystal display panel of the present invention will be described.

D-1: Mobile Computer

First, an example in which the liquid crystal display panel of the present invention is applied to a display section of a portable personal computer (what is called a notebook personal computer) will be described. FIG. 21 is a perspective view of the structure of the personal computer. As shown in FIG. 21, a personal computer 91 comprises a body 912 having a keyboard 911 and a display section 913 to which the liquid crystal display panel of the present invention is applied.

D-2: Cellular Phone

Next, an example in which the liquid crystal display panel of the present invention is applied to a display section of a cellular phone will be described. FIG. 22 is a perspective view of the structure of the cellular phone. As shown in FIG. 22, a cellular phone 92 comprises, in addition to a plurality of operating buttons 921, an earpiece 922, a mouthpiece 923, and a display section 924 to which the liquid crystal display panel of the present invention is applied.

Examples of electronic apparatus to which the liquid crystal display panel of the present invention is applicable include, in addition to the personal computer shown in FIG. 21 and the cellular phone shown in FIG. 22, a liquid crystal television, a viewfinder/monitor-direct-viewing-type video tape recorder, a car navigation system, a pager, an electronic notebook, a calculator, a word processor, a work station, a television phone, a POS terminal, and a digital still camera.

Advantages

As described above, according to the present invention, it is possible to eliminate the occurrence of problems caused by rubbing an alignment film.

The entire disclosure of Japanese Patent Application Nos. 2002-006541 filed Jan. 15, 2002 and 2002-343962 filed Nov. 27, 2002 are incorporated by reference herein.

What is claimed is:

1. A color filter substrate comprising:

one of a pair of substrates for sandwiching liquid crystals; and

color filters disposed on a surface of the one substrate that faces the liquid crystals, the color filters transmitting light of a particular wavelength and having surface profiles defining a state of alignment of the liquid crystals,

wherein the surface profile of each color filter is defined by a plurality of alignment control protrusions having top portions that extend in a common direction.

2. The color filter substrate according to claim 1, wherein the alignment control protrusions have planar flat top portions that extend in the common direction.

3. The color filter substrate according to claim 1, wherein the alignment control protrusions each have a substantially prismatic shape with a linear upper edge that extends in the common direction.

4. The color filter substrate according to claim 1, wherein each alignment control protrusion includes inclined surfaces that join at upper edges to form linear top portions that extend in the common direction.

5. A liquid crystal display panel comprising:

liquid crystals between a pair of opposing substrates; and color filters disposed on a surface of one of the pair of substrates that faces the liquid crystals, the color filters transmitting light of a particular wavelength and having surface profiles defining a state of alignment of the liquid crystals,

wherein the surface profile of each color filter is defined by a plurality of alignment control protrusions having top portions that extend in a common direction.

6. The liquid crystal display panel according to claim 5, further comprising:

an electrode disposed on a surface of each color filter for applying a voltage to the liquid crystals; and

an alignment film covering the surface of each color filter having the electrode provided thereon;

wherein a distance between adjacent alignment control protrusions is greater than twice a sum total of a thickness of each electrode and a thickness of the alignment film.

7. The liquid crystal display panel according to claim 5, further comprising:

an electrode disposed on a surface of each color filter for applying a voltage to the liquid crystals; and

an alignment film covering the surface of each color filter having the electrode provided thereon;

wherein a height of each alignment control protrusion is greater than a sum total of a thickness of each electrode and a thickness of the alignment film.

8. A method of producing a color filter substrate including one of a pair of substrates for sandwiching liquid crystals and color filters which transmit light of a particular wavelength, the method comprising:

a first step of forming a resin layer on a surface of the one substrate that faces the liquid crystals; and

a second step of selectively removing portions of the resin layer to form the color filters having surface profiles that define a direction of alignment of the liquid crystals;

wherein the surface profile of each color filter is defined by a plurality of alignment control protrusions having top portions that extend in a common direction.

9. The method of producing a color filter substrate according to claim 8, wherein the second step further comprises removing a plurality of linear areas in a thickness direction from a surface of the resin layer.

10. The method of producing a color filter substrate according to claim 8, wherein the second step further comprises removing a portion of the resin layer in successively varying depth steps at locations along a surface of the resin layer.

11. A color filter substrate comprising:

one of a pair of substrates for sandwiching liquid crystals; and

color filters disposed on a surface of the one substrate that faces the liquid crystals, the color filters transmitting light of a particular wavelength and having surface profiles defining a state of alignment of the liquid crystals,

wherein the surface profile of each color filter further comprises a curved profile which protrudes away from the one substrate.

12. A liquid crystal display panel comprising:

liquid crystals between a pair of opposing substrates; and color filters disposed on a surface of one of the pair of substrates that faces the liquid crystals, the color filters transmitting light of a particular wavelength and having surface profiles defining a state of alignment of the liquid crystals,

wherein the surface profile of each color filter further comprises a curved profile that protrudes away from the one substrate.

13. A method of producing a color filter substrate including one of a pair of substrates for sandwiching liquid crystals and color filters which transmit light of a particular wavelength, the method comprising:

a first step of forming a resin layer on a surface of the one substrate that faces the liquid crystals; and

a second step of selectively removing portions of the resin layer to form the color filters having surface profiles that define a direction of alignment of the liquid crystals;

wherein the surface profile of each color filter further comprises a curved profile which protrudes away from the one substrate.

14. The method of producing a color filter substrate according to claim 13, wherein the second step further comprises removing a plurality of linear areas in a thickness direction from a surface of the resin layer.

15. The method of producing a color filter substrate according to claim 13, wherein the second step further comprises removing a portion of the resin layer in successively varying depth steps at locations along a surface of the resin layer.

专利名称(译)	具有用于液晶取向的表面轮廓的滤色器，液晶显示板和制造方法		
公开(公告)号	US6819375	公开(公告)日	2004-11-16
申请号	US10/345110	申请日	2003-01-15
[标]申请(专利权)人(译)	和知REIKO		
申请(专利权)人(译)	和知REIKO		
当前申请(专利权)人(译)	SEIKO EPSON CORPORATION		
[标]发明人	WACHI REIKO		
发明人	WACHI, REIKO		
IPC分类号	G02F1/1335 G02F1/1337 G02F1/13 G02B5/20 G02F1/133		
CPC分类号	G02F1/133514 G02F1/1337 G02F2001/133776 G02F1/133555		
优先权	2002006541 2002-01-15 JP 2002343962 2002-11-27 JP		
其他公开文献	US20030147027A1		
外部链接	Espacenet USPTO		

摘要(译)

滤色器设置在与液晶相对的基板表面上。滤色器具有限定液晶取向状态的表面轮廓。更具体地，滤色器具有多个对准控制突起，其顶部在一个方向上延伸。形成薄的配向膜以覆盖具有这种表面轮廓的滤色器。

