



US007439586B2

(12) **United States Patent**
Jung et al.

(10) **Patent No.:** **US 7,439,586 B2**
(45) **Date of Patent:** **Oct. 21, 2008**

(54) **LIQUID CRYSTAL DISPLAY DEVICE AND
FABRICATING METHOD THEREOF**

(75) Inventors: **Tae Young Jung**, Gumi-si (KR); **Ji No
Lee**, Goyang-si (KR); **Hee Young
Kwack**, Seoul (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 426 days.

(21) Appl. No.: **11/143,681**

(22) Filed: **Jun. 3, 2005**

(65) **Prior Publication Data**

US 2005/0269638 A1 Dec. 8, 2005

(30) **Foreign Application Priority Data**

Jun. 5, 2004 (KR) 10-2004-0041137

(51) **Int. Cl.**
G02F 1/1339 (2006.01)

(52) **U.S. Cl.** **257/347; 257/59; 257/72;**
257/48

(58) **Field of Classification Search** 257/347,
257/59, 72, 48
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,653,864 A * 3/1987 Baron et al. 349/156

5,162,933 A 11/1992 Kakuda et al.
5,317,433 A 5/1994 Miyawaki et al.
5,339,181 A 8/1994 Kim et al.
5,462,887 A 10/1995 Glück
5,668,379 A 9/1997 Ono et al.
5,731,856 A 3/1998 Kim et al.
5,764,324 A * 6/1998 Lu et al. 349/113
5,771,083 A 6/1998 Fujihara et al.
5,793,460 A 8/1998 Yang
5,838,414 A * 11/1998 Lee 349/157
5,847,781 A 12/1998 Ono et al.
6,424,401 B1 * 7/2002 Kang et al. 349/153
6,690,445 B2 * 2/2004 Matsumoto 349/155
6,967,703 B2 * 11/2005 Nam et al. 349/153
7,084,849 B2 * 8/2006 Noguchi et al. 345/96

* cited by examiner

Primary Examiner—Eugene Lee

(74) *Attorney, Agent, or Firm*—McKenna Long & Aldridge
LLP

(57) **ABSTRACT**

A base thin film transistor (TFT) substrate includes a substrate, array areas on the substrate; at least one dummy area on the substrate and between the array areas; an insulating film on the substrate; at least one aperture through the insulating film and arranged within the at least one dummy area; and at least one post arranged within the at least one aperture.

7 Claims, 20 Drawing Sheets





FIG. 1
RELATED ART




FIG. 2
RELATED ART




FIG. 3A
RELATED ART




FIG. 3B
RELATED ART




FIG. 3C
RELATED ART




FIG. 3D
RELATED ART




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 5C






FIG. 6



300

FIG. 7






FIG. 8

FIG. 9

300




FIG. 10A




FIG. 10B




FIG. 10C





FIG. 10D



LIQUID CRYSTAL DISPLAY DEVICE AND FABRICATING METHOD THEREOF

This application claims the benefit of Korean Patent Application No. P2004-041137, filed on Jun. 5, 2004, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The principles of the present invention generally relate to thin film transistor (TFT) substrates of display devices and their methods of fabrication. More particularly, the principles of the present invention relate to a base TFT substrate and a simplified method of fabricating the same.

2. Discussion of the Related Art

Generally, LCD devices display pictures by controlling light transmittance characteristics of liquid crystal material via selectively applied electric fields. To this end, LCD devices typically include an LCD panel and driving circuits for driving the LCD panel.

The LCD panel has a plurality of liquid crystal cells arranged in a matrix pattern and generally includes a TFT substrate and a color filter substrate bonded to and spaced apart from the TFT substrates, thereby defining a cell gap between the two substrates. Liquid crystal material is provided within the cell gap as are spacers for maintaining cell gap uniformity.

The TFT substrate includes gate lines, data lines crossing the gate lines to define pixel areas, switching devices (i.e., TFTs) at crossings of the gate and data lines, pixel electrodes formed within the pixel areas and connected to corresponding TFTs, and an alignment film over the pixel electrodes. Each of the gate and data lines include pad portions that are electrically connected to predetermined driving circuits. Accordingly, the gate and data lines receive scanning and pixel signals, respectively, from the driving circuits via corresponding pad portions. In response to scanning signals applied to the gate lines, corresponding TFTs switch pixel signals, transmitted by corresponding data lines, to corresponding pixel electrodes.

The color filter substrate includes a plurality of color filters individually aligned over corresponding pixel electrodes, a black matrix between adjacent color filters for and reflecting external light, a common electrode for applying a reference voltage to a subsequently provided liquid crystal layer, and an alignment film over the common electrode.

After the aforementioned TFT array and color filter substrates are prepared, they are bonded together via a sealant material to form a cell gap, liquid crystal material is injected through an injection hole within the sealant material and into the cell gap to form the liquid crystal layer. Subsequently, the injection hole is subsequently sealed and fabrication of the LCD panel is complete.

The process used to fabricate the TFT array substrate described above is complicated and relatively expensive because it involves a number of semiconductor processing techniques that require a plurality of mask processes. It is generally known that a single mask process requires many sub-processes such as thin film deposition, cleaning, photolithography, etching, photo-resist stripping, inspection, etc. To reduce the complexity and cost associated with fabricating TFT array substrates, procedures have been developed to minimize the number masking process required. Accord-

ingly, a four-mask process has been developed that removes the necessity of a mask process from a standard five-mask process.

FIG. 1 illustrates a plan view of a TFT array substrate of an LCD device, fabricated using a related art four-mask process. FIG. 2 illustrates a sectional view of the TFT array substrate taken along the I-I' line shown in FIG. 1.

Referring to FIGS. 1 and 2, the TFT array substrate includes gate lines 2 and data lines 4 formed so as to cross each other on a lower substrate 42 to define a plurality of pixel areas, a gate insulating film 44 between the gate and data lines 2 and 4, a TFT 6 provided each crossing of the gate and data lines 2 and 4, and a pixel electrode 18 provided at each pixel area. The TFT array substrate further includes a storage capacitor 20 provided at a region where each pixel electrode 18 and a previous gate line 2 overlap, a gate pad 26 connected to each gate line 2, and a data pad 34 connected to each data line 4.

Each TFT 6 allows a pixel signal transmitted by a corresponding data line 4 to be charged and maintained within a corresponding pixel electrode 18 in response to a scanning signal transmitted by a corresponding gate line 2. To this end, each TFT 6 includes a gate electrode 8 connected to a corresponding gate line 2, a source electrode 10 connected to a corresponding data line 4, a drain electrode 12 connected to a corresponding pixel electrode 18, and an active layer 14 overlapping the gate electrode 8 and defining a channel between the source electrode 10 and the drain electrode 12.

The active layer 14 is overlapped by the source and drain electrodes 10 and 12 of each TFT 6, the data lines 4, as well as a lower data pad electrode 36 and an upper storage electrode 22. An ohmic contact layer 48 is formed on the active layer 14 and ohmically contacts the data line 4, the source electrode 10, the drain electrode 12, the lower data pad electrode 36, and the upper storage electrode 22.

Each pixel electrode 18 is connected to a drain electrode 12 of a corresponding TFT 6 via a first contact hole 16 formed through a passivation film 50. During operation, a potential difference is generated between the pixel electrode 18 and a common electrode supported by a color filter substrate (not shown). In the presence of an electric field generated by the potential difference, molecules within the liquid crystal material (which have a particular dielectric anisotropy), rotate to align themselves vertically between the TFT array and color filter substrates. The magnitude of the applied electric field determines the extent of rotation of the liquid crystal molecules. Accordingly, various gray scale levels of light emitted by a light source (not shown) may be transmitted by a pixel area by varying the magnitude of the applied electric field.

Each storage capacitor 20 associated with a pixel area includes a previous gate line 2, an upper storage electrode 22 overlapping with the previous gate line 2 and separated from the previous gate line 2 by the gate insulating film 44, the active layer 14, and the ohmic contact layer 48. A pixel electrode 18 is connected to the upper storage electrode 22 via a second contact hole 24 formed through the passivation film 50. Constructed as described above, the storage capacitor 20 allows pixel signals charged within the pixel electrode 18 to be uniformly maintained until a next pixel signal is charged at the pixel electrode 18.

Each gate line 2 is connected to a gate driver (not shown) via a corresponding gate pad 26. Accordingly, each gate pad 26 consists of a lower gate pad electrode 28 and an upper gate pad electrode 32. The lower gate pad electrode 28 is an extension of the gate line 2 and is connected to the upper gate pad electrode 32 via a third contact hole 30 formed through the gate insulating film 44 and the passivation film 50.

Each data line **4** is connected to a data driver (not shown) via a corresponding data pad **34**. Accordingly, each data pad **34** consists of a lower data pad electrode **36** and an upper data pad electrode **40**. The lower data pad electrode **36** is an extension of the data line **4** and is connected to the upper data pad electrode **40** via a fourth contact hole **38** formed through the passivation film **50**.

Having described the TFT array substrate above, a method of fabricating the TFT array substrate according to the related art four-mask process will now be described in greater detail with reference to FIGS. 3A to 3D.

Referring to FIG. 3A, a gate metal pattern, including the gate line **2**, the gate electrode **8**, the lower gate pad electrode **28**, is formed on the lower substrate **42** in a first mask process.

Specifically, a gate metal layer is formed over the entire surface of the lower substrate **42** via a deposition technique such as sputtering. The gate metal layer may have a single- or double-layered metal structure including chromium (Cr), molybdenum (Mo), an aluminum (Al) group metal, etc. After being deposited, the gate metal layer is patterned using photolithography and etching techniques in conjunction with a first mask pattern to provide the aforementioned gate metal pattern.

Referring next to FIG. 3B, a gate insulating film **44** is coated over the entire surface of the lower substrate **42** and on the gate metal pattern. In a second mask process, a semiconductor pattern and a data metal pattern are provided on the gate insulating film **44**. The semiconductor pattern consists of the active layer **14** and the ohmic contact layer **48**. The data metal pattern consists of the data line **4**, the source electrode **10**, the drain electrode **12**, the lower data pad electrode **36**, and the upper storage electrode **22**.

Specifically, the gate insulating film **44**, a first and a second semiconductor layer, and a data metal layer are sequentially formed over the surface of the lower substrate **42** and on the gate metal pattern by deposition techniques such as plasma enhanced chemical vapor deposition (PECVD) and sputtering. The gate insulating film **44** typically includes an inorganic insulating material such as silicon nitride (SiN_x) or silicon oxide (SiO_x). The active layer **14** is formed from the first semiconductor layer and typically includes undoped amorphous silicon. The ohmic contact layer **48** is formed from the second semiconductor layer and typically includes an n^+ amorphous silicon layer. The data metal layer typically includes a material such as molybdenum (Mo), titanium (Ti), and tantalum (Ta).

After depositing the data metal layer, a photo-resist film (not shown) is formed and is photolithographically patterned using a second mask pattern. Specifically, the second mask pattern is provided as a diffractive exposure mask having a diffractive exposure region corresponding to a channel of a subsequently formed TFT. Upon exposure through the second mask pattern and development, a photo-resist pattern is created wherein a portion of the photo-resist film remaining in a region corresponding to the channel has a lower height relative to portions of the photo-resist film remaining in regions outside the channel.

Subsequently, the photo-resist pattern is used as a mask to pattern the data metal layer in a wet etching process, thereby forming the aforementioned data metal pattern, wherein the source and drain electrodes **10** and **12** are connected to each other in a region corresponding to the channel of the subsequently formed TFT **6**. Next, the photo-resist pattern is used as a mask to sequentially pattern the first and second semiconductor layers in a dry etching process and form the aforementioned semiconductor pattern.

After the semiconductor pattern is formed, the portion of the photo-resist having the relatively lower height is removed from the region corresponding to the channel in an ashing process. Upon performing the ashing process, the relatively thicker portions of the photo-resist in regions outside the channel region are thinned but, nevertheless, remain. Using the remaining photo-resist pattern as a mask, the portion of the data metal layer and the ohmic contact layer **48** arranged in the channel region are then etched in a dry etching process. As a result, the active layer **14** within the channel region is exposed, the source electrode **10** is disconnected from the drain electrode **12**, and the remaining photo-resist pattern is removed in a stripping process.

Referring next to FIG. 3C, the passivation film **50** is coated over the entire surface of the lower substrate **42**, and on the gate insulating film **44**, the data metal pattern, and the active layer **14**. In a third mask process, the first to fourth contact holes **16**, **24**, **30**, and **38**, respectively, are formed.

Specifically, the passivation film **50** is formed over the surface of the lower substrate **42**, and on the gate insulating film **44**, the data metal pattern, and the active layer **14** via a deposition technique such as PECVD. The passivation film **50** typically includes an inorganic insulating material such as SiN_x or SiO_x , or an organic material having a small dielectric constant such as an acrylic organic compound, benzocyclobutene (BCB) or perfluorocyclobutane (PFCB). The passivation film **50** is then patterned via an overlaying third mask pattern using photolithography and etching processes to thereby define the first to fourth contact holes **16**, **24**, **30** and **38**.

The first contact hole **16** is formed through the passivation film **50** to expose the drain electrode **12**, the second contact hole **24** is formed through the passivation film **50** to expose the upper storage electrode **22**, the third contact hole **30** is formed through the passivation film **50** and the gate insulating film **44** to expose the lower gate pad electrode **28**, and the fourth contact hole **38** is formed through the passivation film **50** to expose the lower data pad electrode **36**.

Referring next to FIG. 3D, a transparent conductive pattern including the pixel electrode **18**, the upper gate pad electrode **32**, and the upper data pad electrode **40** are formed on the passivation film **50** in a fourth mask process.

Specifically, a transparent conductive material is coated over the entire surface of the passivation film **50** and within the first to fourth contact holes **16**, **24**, **30**, and **38** via a deposition technique such as sputtering. The transparent conductive material typically includes indium-tin-oxide (ITO). In a fourth mask process, the transparent conductive material is patterned using photolithographic and etching techniques using a fourth mask pattern to thereby form the aforementioned transparent conductive pattern.

Accordingly, the pixel electrode **18** is electrically connected to the drain electrode **12** via the first contact hole **16** while also being electrically connected to the upper storage electrode **22**, via the second contact hole **24**. The upper gate pad electrode **32** is electrically connected to the lower gate pad electrode **28** via the third contact hole **30** and the upper data pad electrode **40** is electrically connected to the lower data pad electrode **48** via the fourth contact hole **38**.

While the TFT array substrate described above may be formed using a four-mask process that is advantageous over previously known five-mask processes, the four-mask process can still be undesirably complicated and, therefore, costly. Accordingly, it would be beneficial to fabricate a TFT array substrate according to a less complex, and therefore less costly, process.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to a liquid crystal display device and a method of fabricating the same that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

An advantage of the present invention provides a base TFT substrate and a method of fabricating the same in which the efficiency of a lift-off process is improved.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. These and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, an LCD device may, for example, include a substrate; a plurality array areas on the substrate; at least one dummy area on the substrate and between the plurality of array areas; an insulating film on the substrate; at least one aperture through the insulating film and arranged within the at least one dummy area; and at least one post arranged within the at least one aperture.

In another aspect of the present invention, a method of fabricating a display device may, for example, include forming a plurality array areas on a first substrate, wherein the plurality of array areas are separated by at least one dummy area; forming an insulating film on the first substrate; forming at least one aperture through a portion of the insulating film arranged within the at least one dummy area; and forming at least one post arranged within the at least one aperture.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

In the drawings:

FIG. 1 illustrates a plan view of a thin film transistor (TFT) array substrate, fabricated using a related art four-mask process;

FIG. 2 illustrates a sectional view of the TFT array substrate taken along line I-I' shown in FIG. 1;

FIGS. 3A to 3D illustrate a method of fabricating the TFT array substrate shown in FIG. 2;

FIGS. 4A and 4B illustrate sectional views of display and non-display areas, respectively, resulting from the application of a third mask process used to fabricate a TFT substrate;

FIGS. 5A to 5D illustrate sectional views specifically explaining the third mask process shown in FIGS. 4A and 4B;

FIG. 6 illustrates a plan view of a base TFT array substrate bonded to a base color filter substrate according to a first embodiment of the present invention;

FIG. 7 illustrates a sectional view of the bonded base TFT array and color filter substrates, taken along the line II-II' as shown in FIG. 6;

FIG. 8 illustrates a plan view of a base TFT array substrate bonded to a base color filter substrate according to a second embodiment of the present invention;

FIG. 9 illustrates a sectional diagram illustrating the initial panel shown in FIG. 8, taken along the line III-III' as shown in FIG. 8; and

FIGS. 10A to 10D illustrate sectional diagrams specifically explaining a third mask process of the thin film transistor substrate shown in FIG. 9.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

Co-pending U.S. patent application Ser. No. 10/969,869, the disclosure of which is hereby incorporated by reference for all purposes as if fully set forth herein, can be understood to disclose a method of fabricating a TFT according to a three-mask process.

In the third mask process of the three-mask process disclosed in the co-pending application, a transparent conductive film is coated over the entire surface of a photo-resist pattern that has been used to form various contact holes within passivation and gate insulating films. Subsequently, the photo-resist pattern is removed according to a lift-off process and, as a result, the transparent conductive film is also patterned. Although not shown, stripper penetration paths can be provided between and over wirings (e.g., gate lines, data lines, power transmission lines, signal transmission lines, etc.) to facilitate penetration of a stripper solution into the photo-resist pattern, over which the transparent conductive film is coated, and increase the efficiency of the lift-off process. When the stripper solution infiltrates the photo-resist pattern through the stripper penetration paths, removal (i.e., lift-off) of the photo-resist pattern from the passivation film may be facilitated.

FIGS. 4A and 4B illustrate sectional views of display and non-display areas, respectively, of a TFT substrate resulting from the application of the third mask process of the aforementioned three-mask process.

Referring to FIG. 4A, the display area of a related art TFT substrate, fabricated in a manner similar to the three-mask process disclosed in U.S. patent application Ser. No. 10/969,869, includes a TFT 106 and a pixel electrode 118 disposed within a pixel area defined by the crossing of gate and data lines 102 and 104, respectively. The TFT substrate also includes a storage capacitor 120.

The TFT 106 includes a gate electrode 108 connected to a gate line 102, a source electrode 110 connected to a data line 104, a drain electrode 112 opposing the source electrode 110 and connected to the pixel electrode 118, an active layer 114 overlapping the gate electrode 108 and a portion of a gate insulating film 144 to form a channel between the source and drain electrodes 110 and 112, and an ohmic contact layer 146 between the source and drain electrodes 110 and 112 and the active layer 114.

A pixel hole 160 is aligned within the pixel area and is formed through a passivation film 150 and the gate insulating film 144. The pixel electrode 118 is disposed within the pixel hole 160 and contacts a side surface of the drain electrode 112 that is exposed by the pixel hole 160.

The storage capacitor 120 includes first and second upper storage electrodes 122 and 125, respectively, which overlap a previous gate line 102 and are separated from the previous gate line 102 by the gate insulating film 144 and the ohmic contact and active layers 1146 and 114. A first sidewall of the first upper storage electrode 122 contacts the pixel electrode 118 and the second upper storage electrode 125 is formed

within a first contact hole **124** formed through the ohmic contact layer **146**, the active layer **114**, and the first storage upper electrode **122**. Moreover, the second upper storage electrode **125** contacts a second sidewall of the first upper storage electrode **122**.

Referring to FIG. **4B**, the non-display area of the related art TFT substrate, fabricated in a manner similar to the three-mask process disclosed in U.S. patent application Ser. No. 10/969,869, includes a plurality of line-on-glass (LOG) signal lines **210** that transmit power and gate control signals from a data tape carrier package (TCP), on which a data driver is mounted, to a gate TCP, on which a gate driver is mounted. Further, stripper penetration paths herein provided as first and second groups of slits **213** and **215**, respectively, within the passivation and gate insulating films **150** and **144**, respectively, are formed over and between LOG signal lines **210**, respectively. Moreover, first and second groups of dummy transparent conductive patterns **214** and **216**, respectively, remain after performing the aforementioned lift-off process.

FIGS. **5A** to **5D** illustrate sectional views specifically explaining the third mask process shown in FIGS. **4A** and **4B**.

Referring to FIG. **5A**, the aforementioned third mask process generally begins with the sequential formation of the passivation film **150** and a photo-resist film over the entire surface of the substrate **142**, and on the gate insulating film **144**, a previously formed gate metal pattern, and previously formed semiconductor and data metal patterns. Generally, the gate metal pattern includes the gate line **102**, the gate electrode **108**, and the LOG signal lines **210** and is formed in a first mask process. Moreover, the semiconductor pattern includes the active layer **114** and the ohmic contact layer **146** while the data metal pattern includes the data line **104**, the source electrode **110**, the drain electrode **112**, and the first upper storage electrode **122**, wherein both the semiconductor and data metal patterns are formed in a second mask process. Using a third mask (not shown), the photo-resist film is patterned to form a photo-resist pattern **152**.

Subsequently, and as shown in FIG. **5B**, the pixel hole **160** and first and second groups of slits **213** and **215** are variously formed within the passivation and/or gate insulating films **150** and **144** and the first contact hole **124** is formed through the passivation film **150** and the semiconductor pattern in an etching process using the photo-resist pattern **152** as a mask. During the etching process, the passivation film **150** is over-etched and, as a result, portions of the photo-resist pattern **152** that surround the pixel and first contact holes **160** and **124** and the first and second groups of slits **213** and **215**.

Referring to FIG. **5C**, a transparent conductive film **154** is deposited via a deposition process such as sputtering over the photo-resist pattern **152**, within the pixel and first contact holes **160** and **124**, respectively, and within the first and second groups of slits **213** and **215**, respectively. Subsequent to removing the photo-resist pattern **152** according to a lift-off process, the pixel electrode **118**, the second storage upper electrode **125**, and the first and second groups of dummy transparent conductive patterns **214**, **216** are simultaneously formed as shown in FIG. **5D**.

Referring back to FIG. **5C**, the stripper penetration path is generally present at regions "A", as illustrated at an interface of the photo-resist pattern **152** and sidewalls of the passivation film **150** that define the pixel and first contact holes **160** and **124** and the first and second groups of slits **213** and **215** due to the generally protruded shape of portions of the photo-resist pattern **152** that surround the pixel and first contact holes **160** and **124** and the first and second groups of slits **213** and **215**. Specifically, due to the nature of the sputtering process, the transparent conductive film **154** is not coated

onto the lower portions of the photo-resist pattern **152** having the generally protruded shape. As a result, a stripper solution may penetrate into the photo-resist pattern **152** more easily where the transparent conductive film **154** is absent, thereby increasing the efficiency with which the photo-resist pattern is removed both in the display area and in the non-display area of the TFT array substrate.

To increase the efficiency with which TFT array substrates are fabricated, multiple TFT array substrates may be fabricated on a single base substrate and may then be separated from each other to form the TFT array substrates shown in FIGS. **4A** and **4B**, wherein the substrate **142** constitutes a portion of the original base substrate. Individual TFT array substrates are separated from each other within the base substrate by dummy areas. Accordingly, dummy areas are provided between non-display regions of adjacently formed TFT array substrates. While stripper penetration paths facilitate removal of the photo-resist pattern formed over display and non-display areas of individual TFT array substrates as they are formed on the base substrate, stripper penetration paths are not formed in the dummy areas of the base substrate. Accordingly, portions of the photo-resist film may remain over the dummy areas and decrease the efficiency with which subsequent processes (e.g., bonding processes) are performed across the entire base substrate.

FIG. **6** illustrates a plan view of a base TFT array substrate bonded to a base color filter substrate according to a first embodiment of the present invention. FIG. **7** illustrates a sectional view of the bonded base TFT array and color filter substrates, taken along the line II-II' as shown in FIG. **6**.

Referring to FIGS. **6** and **7**, a plurality of unit LCD panels **302** may be provided within a bonded substrate assembly **300** comprising a base TFT array substrate **310** bonded to a base color filter substrate **320**. For example, the base TFT substrate **310** may include a plurality of TFT arrays and the base color filter substrate **320** may include a plurality of color filter arrays. When the base TFT array and color filter substrates **310** and **320** are aligned, they may be bonded together to form a plurality of unit LCD panels **302**. In one aspect of the present invention, each unit LCD panel **302** may, for example, include a display area and a non-display area (herein collectively referred to as an array area). In another aspect of the present invention, the display area of each unit LCD panel may for example, include the structures formed as discussed and illustrated in FIGS. **4A** to **5D**. In still another aspect of the present invention, the non-display area of each unit LCD panel may for example, include the structures formed as discussed and illustrated in FIGS. **4B** to **5D**.

According to principles of the present invention, the base TFT array and color filter substrates **310** and **320** may be bonded together via sealant material. In one aspect of the present invention, main sealant patterns **304** may be provided around at least a portion of the display area of each unit LCD panel **302**. In another aspect of the present invention, dummy sealant patterns **306** may be provided in dummy areas between array areas of adjacent unit LCD panels **302** and may function to maintain uniformity of the cell gap within each of the unit LCD panels **302**. In still another aspect of the present invention, spacers **322** may be provided within the display areas of the unit LCD panels **302** to further maintain uniformity of the cell gap within each of the unit LCD panels **302**.

According to principles of the present invention, the base TFT substrate **310** may be exemplarily formed according to the three-mask process described above with respect to FIGS. **5A** to **5D** and may thus incorporate a lift-off technique to simultaneously pattern a transparent conductive film and remove a photo-resist pattern. In one aspect of the invention,

apertures **318** may be formed through portions of the passivation and gate insulating films **316** and **314**, respectively, to create the aforementioned stripper penetration paths. In another aspect of the invention, the apertures **318** may be formed within the aforementioned dummy areas between array areas of adjacent unit LCD panels. In still another aspect of the present invention, the apertures **318** may be formed simultaneously with the formation of the various pixel and contact holes formed at the display and non-display areas of each unit LCD panel **302**. Due to presence of apertures **318**, the aforementioned third mask process may be efficiently completed across the entire base TFT array substrate **310**.

According to principles of the present invention, a transparent conductive film may be coated over the photo-resist pattern that is used in the aforementioned third mask process to form the apertures **318**. Accordingly, after the photo-resist pattern is removed via the lift-off process, a dummy transparent conductive pattern **330** remains within the apertures **318** and contacts a lower substrate **312** of the base TFT array substrate **310**.

According to principles of the present invention, the main and dummy sealant patterns **304** and **306** have substantially the same thickness. In one aspect of the present invention, the main and dummy sealant patterns **304** and **306** may both be formed on the base TFT array substrate **310** or on the base color filter substrate **320**. In another aspect of the present invention, one of the main and dummy sealant patterns **304** and **306** may be formed on one of the base TFT array substrate **310** and the base color filter substrate **320** while the other of the main and dummy sealant patterns **304** and **306** are formed on the other of the base TFT array substrate **310** and the base color filter substrate **320**.

Regardless of which substrate the main and dummy sealant patterns **304** and **306** are formed on, the dummy sealant patterns **306** are aligned with the apertures **318** formed in the passivation and gate insulating films **316** and **314**. Accordingly, a step difference may potentially occur between the main and dummy sealant patterns **304** and **306**. When a step difference does occur, excessive pressure may be applied to the main sealant pattern **304** when the base TFT array substrate **310** is bonded to the color filter substrate **320**, particularly if the bonding is carried out at an elevated temperature (e.g., in a hot-pressing process). Moreover, the base TFT array and/or base color filter substrates **310** and **320** may become deflected, thereby increasing or decreasing the cell gap of the display area surrounded by the main sealant pattern **304** or even cause the cell gap to be non-uniform.

To prevent the occurrence of such potential disadvantages, and with reference to FIGS. **8** and **9**, a base TFT array substrate **310'** may be fabricated similarly to the base TFT array substrate **310** discussed above with respect to FIGS. **6** and **7** but may be fabricated to further include support posts **340** that support the dummy sealant patterns **306**.

For example, the base TFT substrate **310'** may be exemplarily formed according to the three-mask process described above that incorporates a lift-off technique to simultaneously pattern a transparent conductive film and remove a photo-resist pattern. In one aspect of the invention, apertures **338** may be formed through portions of the passivation and gate insulating films **316** and **314**, respectively, to create the aforementioned stripper penetration paths. In another aspect of the invention, the apertures **338** may be formed within the aforementioned dummy areas between array areas of adjacent unit LCD panels **302**. In still another aspect of the present invention, the apertures **338** may be formed simultaneously with the formation of the various pixel and contact holes formed at the display and non-display areas of each unit LCD panel **302**.

Thus, the apertures **338** may facilitate completion of the aforementioned third mask process across the entire base TFT array substrate **310'**.

According to principles of the present invention, the base TFT array substrate **310'** may further include at least one of support post **340** arranged within the apertures **338**, and a plurality of holes **341** formed within the support post **340**. In one aspect of the present invention, the support post **340** and the holes **341** may be formed simultaneously with the formation of the apertures **338**. In another aspect of the present invention, the support post **340** may contact a lower surface of dummy sealant pattern **306**. In still another aspect of the present invention, a width of each hole **341** may be less than a width of the dummy sealant pattern **306**.

As similarly discussed above with respect to FIGS. **6** and **7**, the main and dummy sealant patterns **304** and **306** may have substantially the same thickness. In one aspect of the present invention, the main and dummy sealant patterns **304** and **306** may both be formed on the base TFT array substrate **310** or on the base color filter substrate **320**. In another aspect of the present invention, one of the main and dummy sealant patterns **304** and **306** may be formed on one of the base TFT array substrate **310'** and the base color filter substrate **320** while the other of the main and dummy sealant patterns **304** and **306** are formed on the other of the base TFT array substrate **310'** and the base color filter substrate **320**.

Regardless of which substrate the main and dummy sealant patterns **304** and **306** are formed on, the dummy sealant patterns **306** may be aligned with the support post **340** arranged within the apertures **338** that are formed in the passivation and gate insulating films **316** and **314**, respectively. Accordingly, the dummy sealant patterns **306** may be supported by portions of the passivation and gate insulating films **316** and **314** of the support post **340** such that substantially no step difference occurs between the main and dummy sealant patterns **304** and **306**. As a result, the uniformity of the cell gap between the base TFT array and color filter substrates **310'** and **320** may be substantially maintained due to the support of the dummy sealant **306** by the support post **340**.

Having described the TFT array substrate **310'** with respect to FIGS. **8** and **9**, a method of its fabrication according to principles of the present invention will now be described in greater detail with reference to FIGS. **10A** to **10D**.

Referring to FIG. **10A**, a passivation film **316** may be formed over the entire surface of the gate insulating film **314** via a deposition technique such as PECVD, spin coating, or the like. A photo-resist film may then be formed over the entire surface of the passivation film **316** and may be photolithographically patterned using a third mask pattern. Using the third mask pattern, the photo-resist film may be selectively exposed to, for example, ultraviolet (UV) light, thereby creating a photo-resist pattern **352** having open portions aligned over regions where apertures **338** and holes **341** will subsequently be formed.

Referring to FIG. **10B**, the passivation film **316** and the gate insulating film **314** may be patterned via an etching process using the photo-resist pattern **352** as a mask to form the apertures **338** and the holes **341**.

Referring to FIG. **10C**, a transparent conductive material **354** may be formed over the photo-resist pattern **352** and on the topography formed below (e.g., on the sidewalls of the passivation and gate insulating films **316** and **314**, respectively, that define the apertures **338** and the holes **341** within the support post **340**). As shown, the transparent conductive material **354** may be formed such that substantially no material is formed on the lower portions of the protruded edge regions of the photo-resist pattern **352**, thereby improving the

11

efficiency of a subsequent lift-off process. In one aspect of the present invention, the transparent conductive material **354** may be formed via a deposition technique such as sputtering, or the like. In another aspect of the present invention, the transparent conductive material **354** may, for example, include a material such as ITO, TO, IZO, indium oxide (IO), or the like, or combinations thereof.

Referring to FIG. **10D**, the photo-resist pattern **352** and portions of the transparent conductive material **354** formed thereon may be simultaneously removed in a lift-off process, thereby forming a transparent conductive patterns **330** within the apertures **338** and the holes **341**. Accordingly, transparent conductive patterns **330** contact the sidewalls of the passivation and gate insulating films **316** and **314** that define the apertures **338** and the holes **341**.

Subsequently, and with reference to FIG. **9**, the base TFT array substrate **310'** shown in FIG. **10D** may be bonded to a base color filter substrate **320**. According to principles of the present invention, the base TFT array and color filter substrates **310'** and **320** may be bonded together via main and dummy sealant patterns **304** and **306**. In one aspect of the present invention, the main and dummy sealant patterns **304** and **306** may have substantially the same thickness. In another aspect of the present invention, the main and dummy sealant patterns **304** and **306** may both be formed on the base TFT array substrate **310'** or on the base color filter substrate **320**. In another aspect of the present invention, one of the main and dummy sealant patterns **304** and **306** may be formed on one of the base TFT array substrate **310** and the base color filter substrate **320** while the other of the main and dummy sealant patterns **304** and **306** are formed on the other of the base TFT array substrate **310** and the base color filter substrate **320**.

As described above, the principles of the present invention provide a base TFT substrate and a method of fabricating the same wherein, for example, apertures are formed through portions of the passivation and gate insulating films arranged within dummy areas between array areas of adjacent LCD panels that are, in turn, formed in a pair of bonded base substrates. By providing such apertures, stripper penetration paths may be arranged within the dummy areas to facilitate completion of a mask process across the entire base TFT array substrate in which a photo-resist pattern is removed while a conductive film is simultaneously patterned.

As additionally discussed above, the principles of the present invention may provide a plurality of posts arranged

12

within the apertures and aligned, for example, with at least a portion of a subsequently provided dummy seal pattern. By providing such posts, a step difference between main and dummy sealant patterns may be substantially eliminated, thereby ensuring a substantially uniform cell gap between the bonded base TFT array and color filter substrates.

It will be apparent to those skilled in the art that various modifications and variation can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A base thin film transistor (TFT) array substrate, comprising:

a substrate;
a plurality of array areas on the substrate;
at least one dummy area on the substrate and between the plurality of array areas;
an insulating film on the substrate;
at least one aperture through the insulating film and arranged within the at least one dummy area; and
at least one post arranged within the at least one aperture, wherein the at least one aperture includes a plurality of holes.

2. The base TFT array substrate of claim 1, wherein the at least one post comprises insulating material.

3. The base TFT array substrate of claim 2, wherein the at least one post includes:

a gate insulating film; and
a passivation film.

4. The base TFT array substrate of claim 1, further comprising a dummy sealant pattern on the at least one post.

5. The base TFT array substrate of claim 1, further comprising a transparent conductive material formed within the plurality of holes and the aperture.

6. The base TFT array substrate of claim 1, wherein a width of each hole is less than a width of the dummy sealant pattern formable over the at least one aperture.

7. The base TFT array substrate of claim 1, further comprising a plurality of TFTs within each array area.

* * * * *

专利名称(译)	液晶显示装置及其制造方法		
公开(公告)号	US7439586	公开(公告)日	2008-10-21
申请号	US11/143681	申请日	2005-06-03
[标]申请(专利权)人(译)	JUNG TAEŷ 李积ŷ KWACK HEEŷ		
申请(专利权)人(译)	JUNG TAEŷ 李积ŷ KWACK HEEŷ		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	JUNG TAE YOUNG LEE JI NO KWACK HEE YOUNG		
发明人	JUNG, TAE YOUNG LEE, JI NO KWACK, HEE YOUNG		
IPC分类号	G02F1/1339 G02F1/1368 G02F1/1333 G02F1/136 G09G3/36 H01L21/336 H01L29/786		
CPC分类号	G02F1/1368 G02F2001/133388 G02F2001/136231		
审查员(译)	LEE , EUGENE		
优先权	1020040041137 2004-06-05 KR		
其他公开文献	US20050269638A1		
外部链接	Espacenet USPTO		

摘要(译)

基底薄膜晶体管 (TFT) 基板包括基板 , 基板上的阵列区域;至少一个虚设区域位于基板上和阵列区域之间;基板上的绝缘膜;至少一个孔穿过绝缘膜并设置在至少一个虚设区域内;至少一个柱设置在至少一个孔内。

