



US008294855B2

(12) **United States Patent**
Lim et al.

(10) **Patent No.:** **US 8,294,855 B2**
(45) **Date of Patent:** **Oct. 23, 2012**

(54) **METHOD OF FABRICATING A LIQUID CRYSTAL DISPLAY DEVICE**

(75) Inventors: **Joo Soo Lim**, Gumi-si (KR); **Woong Sik Kim**, Seongnam-si (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 42 days.

5,339,181 A	8/1994	Kim et al.	
5,462,887 A	10/1995	Glück	
5,668,379 A	9/1997	Ono et al.	
5,731,856 A	3/1998	Kim et al.	
5,771,083 A	6/1998	Fujihara et al.	
5,793,460 A	8/1998	Yang	
5,847,781 A	12/1998	Ono et al.	
6,100,954 A	8/2000	Kim et al.	
2002/0033918 A1	3/2002	Shigeno et al.	349/114
2003/0086046 A1*	5/2003	You	349/149
2003/0160921 A1*	8/2003	Nakashima et al.	349/113
2003/0197181 A1*	10/2003	Yun	257/72

(Continued)

(21) Appl. No.: **12/458,456**

(22) Filed: **Jul. 13, 2009**

(65) **Prior Publication Data**

US 2009/0275155 A1 Nov. 5, 2009

Related U.S. Application Data

(62) Division of application No. 11/168,315, filed on Jun. 29, 2005, now Pat. No. 7,626,669.

(30) **Foreign Application Priority Data**

Dec. 4, 2004 (KR) 10-2004-0101554

(51) **Int. Cl.**

G02F 1/1335 (2006.01)
G02F 1/1345 (2006.01)
G02F 1/13 (2006.01)

(52) **U.S. Cl.** 349/114; 349/152; 349/187

(58) **Field of Classification Search** 349/114, 349/149, 153, 152, 187

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,162,933 A 11/1992 Kakuda et al.
5,317,433 A 5/1994 Miyawaki et al.

FOREIGN PATENT DOCUMENTS

CN 1385743 A 12/2002

(Continued)


Primary Examiner — Jessica M Merlin

(74) *Attorney, Agent, or Firm* — McKenna Long & Aldridge, LLP

(57) **ABSTRACT**

The present invention relates to a transfective thin film transistor substrate and method of fabricating the same that is adaptive for simplifying its process. The liquid crystal display device includes: first and second substrates; a gate line on the first substrate; a gate insulating film on the first substrate; a data line crossing the gate line to define a pixel area; a thin film transistor connected to the gate line and the data line; an organic insulating film on the gate line, the data line and the thin film transistor, and having a transmission hole in the pixel area; a pixel electrode on the organic insulating film of the pixel area via the transmission hole and connected to the thin film transistor; and a reflective electrode on the pixel electrode having a same edge part as the pixel electrode or an edge part located at inner side from an edge part of the pixel electrode and exposing the pixel electrode of the transmission hole.

14 Claims, 31 Drawing Sheets



US 8,294,855 B2

Page 2

U.S. PATENT DOCUMENTS

2004/0051823 A1* 3/2004 Choi 349/43
2004/0085488 A1 5/2004 Cho et al. 349/40
2004/0201803 A1 10/2004 Yang
2004/0207795 A1* 10/2004 Sakai et al. 349/149

FOREIGN PATENT DOCUMENTS

CN 1395140 A 2/2003

CN 1397829 2/2003
CN 1538227 A 10/2004
JP 2003-131246 A 5/2003
JP 2003-248232 9/2003
JP 2004-294807 10/2004
JP 2004-318073 11/2004
TW 567369 A 6/1991

* cited by examiner

FIG. 1
RELATED ART




FIG. 3A





FIG. 3B







FIG. 4A

FIG. 4B







FIG. 5A

FIG. 5B







FIG. 6A

FIG. 6B







FIG. 7A

FIG. 7B






FIG. 8A

FIG. 8B




FIG. 8C




FIG. 8D




FIG. 8F




FIG. 10




FIG. 11A




FIG. 11B




FIG. 12A




FIG. 12B




FIG. 13A




FIG. 13B




FIG. 14A




FIG. 14B




FIG. 15A





FIG. 15B



METHOD OF FABRICATING A LIQUID CRYSTAL DISPLAY DEVICE

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a Divisional of application Ser. No. 11/168,315 filed Jun. 29, 2005 now U.S. Pat. No. 7,626,669, now allowed, which claims priority to Korean Patent Application No. 10-2004-101554, filed Dec. 4, 2004 all of which are hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a transfective thin film transistor substrate of a liquid crystal display device. More particularly, the present invention relates to a transfective thin film transistor substrate and method of fabricating the same that is adaptive for simplifying a manufacturing process.

2. Description of the Related Art

A liquid crystal display device controls the light transmissivity of liquid crystal, which has dielectric anisotropy, by use of an electric field, thereby displaying a picture. The liquid crystal display device includes a liquid crystal display panel to display a picture through a liquid crystal cell matrix, and a drive circuit to drive the liquid crystal display panel.

In FIG. 1, a related art liquid crystal display panel includes a color filter substrate **10** and a thin film transistor substrate **20** which are bonded to each other and have a liquid crystal material **24** therebetween.

The color filter substrate **10** includes a black matrix **4**, a color filter **6** and a common electrode **8** which are sequentially formed on an upper glass substrate **2**. The black matrix **4** is formed on the upper glass substrate **2** in a matrix shape. The black matrix **4** divides the area of the upper glass substrate **2** into a plurality of cell areas in which a color filter **6** is to be formed, and prevents an optical interference and external light reflection between the adjacent cells. The color filter **6** is formed and divided into red R, green G, blue B in the cell area divided by the black matrix **4** to transmit red, green and blue lights respectively. The common electrode **8** supplies a common voltage V_{com} to a transparent conductive layer, which is spread over the entire surface of the color filter **6**, wherein the common voltage V_{com} becomes a reference when driving the liquid crystal material **24**. And, to flatten the color filter **6**, an overcoat layer (not shown) is additionally formed between the color filter **6** and the common electrode **8**.

The thin film transistor substrate **20** includes a thin film transistor **18** and a pixel electrode **22**, wherein the thin film transistor **18** is formed in each cell area defined by a crossing of a gate line **14** and a data line **16** in a lower glass substrate **12**. The thin film transistor **18** supplies a data signal from the data line **16** to the pixel electrode **22** in response to a gate signal from the gate line **14**. The pixel electrode **22** formed of a transparent conductive layer supplies the data signal from the thin film transistor **18** to drive the liquid crystal material **24**.

The liquid crystal material **24** having dielectric anisotropy rotates along the electric field formed by the common voltage V_{com} of the common electrode **8** and the data signal of the pixel electrode **22** to control the light transmissivity, thereby making the gray level realized.

And, the liquid crystal display panel further includes a spacer (not shown) to fixedly maintain the cell gap between the color filter substrate **10** and the thin film transistor substrate **20**.

The color filter substrate **10** and the thin film transistor substrate **20** of the liquid crystal display panel are formed using a plurality of mask processes. One mask process includes a plurality of processes such as a thin film deposition (coating) process, a cleaning process, a photolithography process (hereinafter, referred to as a photo process), an etching process, a photo-resist peeling process, an inspection process and so on. Especially, the thin film transistor substrate includes a semiconductor process and requires a plurality of mask processes. Thus, the manufacturing process is complicated so that it becomes a material cause for the increase of the liquid crystal display panel manufacturing cost.

The liquid crystal display device is generally classified into a transmissive type that a picture is displayed by use of the light being incident from a backlight unit, a reflective type that a picture is displayed by reflecting an external light such as a natural light, and a transfective type using an advantage of both the transmissive type and the reflective type.

There is a problem that the power consumption of a backlight unit is high in the transmissive type and the reflective type depends on the external light so as not to be able to display the picture in a dark environment. On the other hand, the transfective liquid crystal display device operates in the reflective mode if the external light is sufficient and in the transmissive mode if the external light is not sufficient. Thus, it might be able to reduce the power consumption more than the transmissive liquid crystal display device and it is not restricted by the external light, which is different from the reflective liquid crystal display device.

To this end, the transfective liquid crystal display panel includes each pixel having a reflection area and a transmission area. Accordingly, a reflection electrode, formed in the reflection area, and an insulating film for making light paths in both the reflection area and the transmission area are the same should be further added in a transfective thin film transistor, as compared to the thin film transistor array shown in FIG. 1. As a result, since the number of mask processes would be increased, there is a problem that the manufacturing process of the related art transfective thin film transistor substrate is complex.

SUMMARY OF THE INVENTION

Accordingly, the present invention provides a transfective thin film transistor substrate and method of fabricating the same.

In order to achieve these and other features of the invention, a liquid crystal display device according to present invention includes: first and second substrates; a gate line on the first substrate; a gate insulating film on the first substrate; a data line crossing the gate line to define a pixel area; a thin film transistor connected to the gate line and the data line; an organic insulating film on the gate line, the data line and the thin film transistor, and having a transmission hole in the pixel area; a pixel electrode on the organic insulating film of the pixel area via the transmission hole and connected to the thin film transistor; and a reflective electrode on the pixel electrode having a same edge part as the pixel electrode or an edge part located at inner side from an edge part of the pixel electrode and exposing the pixel electrode of the transmission hole.

In another aspect of the invention, a method of fabricating a liquid crystal display device according to the present inven-

tion includes: providing first and second substrates; forming a gate line on the first substrate using a first mask; forming a gate insulating film on the first substrate, a semiconductor pattern on the gate insulating film, a data line crossing the gate line to define a pixel area on the semiconductor pattern, a source electrode, and a drain electrode using a second mask; forming an organic insulating film on the data line, the source electrode and the drain electrode and forming a transmission hole passing through the organic insulating film using a third mask; and forming a pixel electrode connected to the drain electrode, passing through the organic insulating film and the transmission hole and forming a reflective electrode exposing the pixel electrode of the transmission hole on the pixel electrode using a fourth mask.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other features of the invention will be apparent from the following detailed description of the embodiments of the present invention with reference to the accompanying drawings, in which:

FIG. 1 is a perspective view illustrating a structure of a related art liquid crystal display panel;

FIG. 2 is a plan view partially illustrating a part of a transfective thin film transistor substrate according to an embodiment of the present invention;

FIGS. 3A and 3B are sectional views illustrating the transfective thin film transistor substrate taken along the line II-II', III-III', IV-IV' shown in FIG. 2;

FIGS. 4A and 4B are a plan view and a sectional view describing a first mask process of the transfective thin film transistor substrate according to the embodiment of the present invention;

FIGS. 5A and 5B are a plan view and a sectional view describing a second mask process of the transfective thin film transistor substrate according to the embodiment of the present invention;

FIGS. 6A and 6B are a plan view and a sectional view describing a third mask process of the transfective thin film transistor substrate according to the embodiment of the present invention;

FIGS. 7A and 7B are a plan view and a sectional view describing a fourth mask process of the transfective thin film transistor substrate according to the embodiment of the present invention;

FIGS. 8A to 8F are sectional views for illustrating the fourth mask process according to the present invention using a half-tone mask;

FIG. 9 is a sectional view for illustrating the use of a partial exposure mask in the fourth mask process of the present invention;

FIG. 10 is a plan view briefly illustrating the transfective thin film transistor substrate according to the embodiment of the present invention, with a surrounding part centered;

FIGS. 11A to 11C are a plan view and sectional view specifically illustrating a contact area of a data link and a data line shown in FIG. 10;

FIGS. 12A and 12B are a plan view and a sectional view describing a first mask process of the transfective thin film transistor substrate shown in FIGS. 11A and 11B;

FIGS. 13A and 13B are a plan view and a sectional view describing a second mask process of the transfective thin film transistor substrate in FIGS. 11A and 11B;

FIGS. 14A and 14B are a plan view and a sectional view describing a third mask process of the transfective thin film transistor substrate in FIGS. 11A and 11B; and

FIGS. 15A and 15B are a plan view and a sectional view describing a fourth mask process of the transfective thin film transistor substrate in FIGS. 10A and 10B.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

Hereinafter, the embodiments of the present invention will be described in detail with reference to FIGS. 2 to 15B.

FIG. 2 is a plan view illustrating a transfective thin film transistor substrate according to the first embodiment of the present invention, and FIGS. 3A and 3B are sectional views illustrating the transfective thin film transistor substrate taken along the lines II-II', III-III', IV-IV' shown in FIG. 2.

In FIGS. 2 and 3, the transfective thin film transistor substrate includes: a gate line **102** and a data line **104** that define a pixel area on a lower substrate **142** by crossing each other with a gate insulating film **144** therebetween; a thin film transistor **106** connected to the gate line **102** and the data line **104**; a pixel electrode **118** formed at each pixel area and connected to the thin film transistor **106**; and a reflection electrode **156** formed to overlap the pixel electrode **118** at a reflection area of each pixel. Accordingly, each pixel area is divided into a reflection area, having the reflection electrode **156** and the pixel electrode **118**, and a transmission area, having the pixel electrode **118** exposed through an open part.

The thin film transistor **106** responds to the scan signal of the gate line **102** to maintain a pixel signal supplied to the data line **104**. For this, the thin film transistor **106** includes the gate line **102**, a source electrode **110** connected to the data line **104**, a drain electrode **112** that faces the source electrode **110** and is connected to the pixel electrode **118**, an active layer **116** which overlaps the gate line **102** with the gate insulating film **144** to form a channel between the source electrode **110** and the drain electrode **112**, and an ohmic contact layer **146** making an ohmic contact with the active layer **116**, the source electrode **110** and the drain electrode **112** except a channel part.

And, a semiconductor pattern **148** including the active layer **116** and the ohmic contact layer **146** is formed to overlap the data line **104**.

The pixel electrode **118** is formed at each pixel area defined by the crossing of the gate line **102** and the data line **104**. More specifically, the pixel electrode **118** is formed on an organic insulating film **154** of each pixel area to pass through a drain contact hole **114** passing through the organic insulating film **154** and the passivation film **150** and a transmission hole **170** passing through from the organic insulating film **154** and the gate insulating film **144**. Accordingly, the pixel electrode **118** is connected to the drain electrode **112** via the drain contact hole **114** and is connected to the substrate **142** via the transmission hole **170**. Further, the pixel electrode **118** is overlapped by the reflection electrode **156** formed on the pixel electrode **118** in the reflection area, and is exposed via an open part of the reflection electrode **156** to transmit light in the transmission area. The pixel electrode **118** generates a potential difference with the common electrode of the color filter substrate (not shown) by the pixel signal supplied through the thin film transistor **106**. The liquid crystal material having dielectric anisotropy rotates by this potential difference to control the transmissivity of the light which goes through the liquid crystal layer of each of the reflection area and the transmission area, thus the brightness becomes different in accordance with the video signal.

The reflection electrode **156** is formed at the reflection area of each pixel to reflect an external light. More specifically, the reflection electrode **156** defines the transmission area by exposing the pixel electrode **118** formed in the transmission hole **170** and defines the reflection area by overlapping the remaining part of the pixel electrode **118**, in which the remaining part of the pixel electrode **118** surrounds the transmission area. And, the reflection electrode **156** is formed to be separated from the reflection electrode **156** of an adjacent pixel on the signal line such as the data line **104** and the gate line **102**. In this arrangement, the reflection electrode **156** has an edge part identical to that of the pixel electrode **118**, or has an edge part located at a slightly inner side from the edge part of the pixel electrode **118**. The reflection electrode **156** has an embossing shape along the surface of the organic insulating film **154** together with the pixel electrode **118**, thus its reflection efficiency increases due to its dispersion effect.

Herein, the transmission hole **170** is formed to pass through a relatively thick organic insulating film **154**, a passivation film **150** and the gate insulating film **144** under the organic insulating film **154**. Accordingly, the length of the light path that runs through the liquid crystal layer becomes the same at the reflection area and the transmission area. Thus, the transmission efficiency of the reflection mode and the transmission mode becomes the same.

The thin film transistor substrate of the present invention further includes a storage capacitor **120** connected to the drain electrode **112** in order to stably maintain a video signal supplied to the pixel electrode **118**. An enlarged drain electrode **112** overlaps the storage line **122** substantially parallel to the gate line **102** with the gate insulating film **144** therebetween to form the storage capacitor **120**. Accordingly, the semiconductor pattern **148** is further overlapped under the drain electrode **112** overlapping the storage line **122**. And, the pixel electrode **118** is connected to the drain electrode **112** via the contact hole **114** on the storage line **122**.

The gate line **102** is connected to a gate driver (not shown) through the gate pad **126**. The gate pad **126** includes a lower gate pad electrode **128** extended from the gate line **102** and an upper gate pad electrode **132** connected to the lower gate pad electrode **128** via a first contact hole **130** passing from the organic insulating film **154** to the gate insulating film **144**.

The data line **104** is connected to a data driver (not shown) through the data pad **134**. The data pad **134** is formed with the structure like the gate pad **126** described above. More specifically, the data pad **134** includes a lower data pad electrode **136** formed on the substrate **142** and an upper data pad electrode **140** connected to the lower data pad electrode **136** via a second contact hole **138** passing from the organic insulating film **154** to the gate insulating film **144**. The lower data pad electrode **136** of the data pad **134** is connected to the data line **104**, formed together with the semiconductor pattern **148** on the gate insulating film **144**, through a separate contact electrode (not shown).

Herein, the passivation film **150** shown in FIG. 3A can be omitted as shown in FIG. 3B.

The thin film transistor according to the embodiment of the present invention with such a composition is formed by the following four mask processes.

FIGS. 4A and 4B are a plan view and a sectional view explaining a first mask process of fabricating method of the thin film transistor substrate according to the embodiment of the present invention.

A gate pattern is formed by a first mask process, wherein the gate pattern includes the gate line **102**, the storage line

122, the lower gate pad electrode **128** connected to the gate line **102**, and the lower data pad electrode **136**, on the lower substrate **142**.

More specifically, a gate metal layer is formed by a deposition method such as sputtering. The gate metal layer is formed in a single layer structure of, for example, Mo, Cu, Al, Ti, Cr, Mo alloy, Al alloy such as AlNd, or Cu alloy. Or, the gate metal layer may be formed in a structure having a plurality of layers more than a double structure such as Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Mo/Al(Nd)Mo, Cu/Mo, Ti/Al(Nd)/Ti, Mo/Al, Mo/Ti/Al(Nd), Cu alloy/Mo, Cu alloy/Al, Cu alloy/Mo alloy, Cu alloy/Al alloy, Al/Mo alloy, Mo alloy/Al, Al alloy/Mo alloy, Mo alloy/Al alloy. Subsequently, the gate metal layer is patterned by a photolithography process using the first mask and an etching process, to thereby form a gate metal pattern including the gate line **102**, the storage electrode **122**, the lower gate pad electrode **128**, and the lower data pad electrode **136**.

FIGS. 5A and 5B are a plan view and a sectional view illustrating a second mask process of the transfective thin film transistor substrate according to the embodiment of the present invention.

The gate insulating film **144** is formed on the lower substrate **142** where the gate metal pattern is formed. And, a source/drain pattern including the data line **104**, the source electrode **110** and the drain electrode **112**, and a semiconductor pattern **148** including the active layer **116** and the ohmic contact layer **146** that overlap along the rear surface of the source/drain pattern are formed on the gate insulating film **144** by a second mask process. The semiconductor pattern **148** and the source/drain pattern are formed by one mask process using a diffractive exposure mask or a half-tone mask. Hereinafter, for example, an example using the diffractive exposure mask will be described as follows.

Specifically, the gate insulating film **144**, an amorphous silicon layer, an amorphous silicon layer doped with impurities n+ or p+, and a source/drain metal layer are sequentially formed on the lower substrate **142** where the gate pattern is formed. For example, the gate insulating film **144**, the amorphous silicon layer, the amorphous silicon layer doped with impurities are formed by PECVD, and the source/drain metal layer is formed by sputtering. The gate insulating film **144** may be formed of inorganic insulating material such as silicon oxide SiO_x, silicon nitride SiN_x, and the source/drain metal layer is formed in a single structure of Mo, Cu, Al, Ti, Cr, Mo alloy, Al alloy such as AlNd, or Cu alloy. Or, the gate insulating film **144** may be formed as a structure having a plurality of layer, for example, structure more than a double structure such as Al/Cr, Al/Mo, Al(Nd)/Al, Al(Nd)/Cr, Mo/Al(Nd)Mo, Cu/Mo, Ti/Al(Nd)/Ti, Mo/Al, Mo/Ti/Al(Nd), Cu alloy/Mo, Cu alloy/Al, Cu alloy/Mo alloy, Cu alloy/Al alloy, Al/Mo alloy, Mo alloy/Al, Al alloy/Mo alloy, Mo alloy/Al alloy.

And a photo-resist pattern having a stepped difference is formed on the source/drain metal layer by a photolithography process using a diffractive exposure mask. The photo-resist pattern has a relatively thicker thickness at an area where the semiconductor pattern and the source/drain pattern should be formed and a relatively thinner thickness at an area where the channel of the thin film transistor is formed.

A source/drain metal pattern and the semiconductor pattern thereunder are formed by an etching process using the photo-resist pattern having the stepped difference. Herein, the source/drain pattern includes the data line **104**, and the drain electrode **112** integrated with the source electrode **110**.

And then, the thin part of the photo-resist pattern is removed and the thick part of the photo-resist pattern

becomes thinner, by an ashing process. By an etching process using the ashed/photo-resist pattern, the source electrode **110** is separated from the drain electrode **112**, and the ohmic contact layer **146** under the source electrode **110** and the drain electrode **112** is eliminated. Subsequently, the photo-resist pattern remaining on the source/drain metal pattern is removed by a strip process.

FIGS. **6A** and **6B** are a plan view and a sectional view illustrating a third mask process of the transfective thin film transistor substrate according to the embodiment of the present invention.

The passivation film **150** and the organic insulating film/**154**, which cover the source/drain metal pattern, are formed, and the transmission hole **170**, the drain contact hole **114**, the first contact hole **130** and the second contact hole **138**, passing through the passivation film **150** and the organic film **154**, are formed, by use of the third mask process. Herein, the passivation film **150** can be omitted.

Specifically, passivation film **150** is formed by the deposition method such PECVD on the gate insulating film **144** where the source/drain metal pattern is formed. The passivation film **150** is formed of an inorganic insulating material similar to the gate insulating film **144**.

Subsequently, the organic insulating film **154**, having an embossing surface at the reflection area and having the transmission hole **170**, the drain contact hole **114**, the first contact hole **130** and the second contact hole **138**, are formed on the passivation film **150** by coating a photosensitive organic material such as acrylic resin by use of a spin coating method. And then, the organic insulating film **154** is patterned by the photolithography process using the third mask, thereby forming the transmission hole **170**, the drain contact hole **114**, the first contact hole **130** and the second contact hole **138** which pass through the organic film **154** and correspond to the transmission part of the third mask. Further, the third mask has a structure where a shielding part and a diffractive exposure part (or a transfective part) repeat at the rest area except for the transmission part. The organic insulating film **154** in correspondence to the above repeat structure is patterned to have a structure that a shielding area (projected part) and a diffractive exposure area (groove part), having a stepped difference at the reflection area, are repeated. Subsequently, the organic insulating film **154** where the projected part and the groove part are repeated is cured so that the surface of the organic insulating film **154** has the embossing shape.

The passivation film **150** and the gate insulating film **144** under the organic film **154** are patterned by using the organic insulating film **154** as a mask, so that the transmission hole **170**, the first contact hole **130** and the second contact hole **138** are extended to pass through the gate insulating film **144**, and the drain contact hole **114** is extended to pass through the passivation film **150**.

FIGS. **7A** and **7B** are a plan view and a sectional view illustrating a fourth mask process of the transfective thin film transistor substrate according to the embodiment of the present invention, and FIGS. **8A** to **8F** are sectional views for specifically explaining the fourth mask process according to the present invention using a half-tone mask.

A transparent conductive pattern, including the pixel electrode **118**, the upper gate pad electrode **132** and the upper data pad electrode **140**, and a reflection electrode **156** are formed on the organic insulating film **154** having the embossing shape, by use of the fourth mask process. The transparent

conductive pattern and the reflection electrode **156** are formed by a diffractive exposure mask, a half-tone mask, and a partial transmission mask.

In FIG. **8A**, a transparent conductive film **117** and a reflection metal layer **155** to cover the organic insulating film **154** are deposited by a deposition method such as sputtering. The transparent conductive film **117** may be formed of ITO, TO, IZO, ITZO and the like, and the reflection metal layer **155** may be formed of a metal having a high reflexivity like Al and AlNd. The transparent conductive film **117** may be formed in a double layered structure such as AlNd/Mo and the like. Subsequently, a photo-resist **239** is applied to the reflection metal layer **155**, and then, is exposed by a photolithography process using a half-tone mask **230** and developed, to thereby form a photo-resist pattern **240** having a stepped difference as shown in FIG. **8B**.

Specifically, the half-tone mask **230** includes a quartz substrate **232**, and a half-tone transmission layer **236** and a shielding layer **234** formed on the quartz substrate **232**. The shielding layer **234** is formed of a metal such as Cr and CrOx, and the half-tone transmission layer **236** is formed of MoSiX. Herein, a shielding part **P1**, where the half-tone transmission layer **236** and the shielding part **234** overlap, intercepts ultra violet UV light. Thus, a first photo-resist pattern **240B** remains at an area, where both the reflection metal layer **155** and the transparent conductive film **117** should be existed, as shown in FIG. **8B**. A partial transmission part **P2**, where the half-tone transmission layer **236** is located, partially transmits the ultra violet UV light. Thus, a second photo-resist pattern **240B** remains that is thinner than the first photo-resist pattern **240A** where only transparent conductive film **117** should be existed. And, a full transmission part **P3**, where the quartz substrate **232** is exposed, transmits the entire ultra violet UV light, so that a photo-resist pattern **240** does not exist at an area, where both the reflection metal layer **155** and the transparent conductive film **117** should be removed, as shown in FIG. **8B**.

In FIG. **8C**, the reflection metal layer **155** and the transparent conductive film **117** are patterned by an etching process using the photo-resist pattern **240** as a mask, e.g., by a wet etching process, to thereby form a transparent conductive pattern including the pixel electrode **118**, the upper gate pad electrode **132** and the upper data pad electrode **140**, and a reflection electrode **156**, overlapping the pixel electrode. Herein, the pixel electrode **118** and the reflection electrode **156** have the same edge part. The pixel electrode **118** and the reflection electrode **156** are formed to overlap the organic insulating film **154** which passes through the transmission hole **170** at the pixel area. And the pixel electrode **118** and the reflection electrode **156** are connected to the drain electrode **112** which passing through the drain contact hole **114**. Since the surface of the organic insulating film **154** has an embossing shape, the pixel electrode **118** and the reflection electrode **156** formed on the organic insulating film **154** have an embossing shape. The upper gate pad electrode **132** and the upper data pad electrode **140** are respectively connected to the lower gate pad electrode **128** and the lower data pad electrode **136** via the first and the second contact holes **130** and **138**.

In FIG. **8D**, a thickness of the first photo-resist pattern **240A**, and the second photo-resist pattern **240B** is removed, by an ashing process.

In FIG. **8E**, the exposed reflection electrode **156** is etched by a wet etching process using the ashed first photo-resist pattern **240A** as a mask, to thereby expose the pixel electrode **118** in the transmission hole **170**, the upper gate pad electrode **132**, and the upper data pad electrode **140**. At this time, the edge part of the reflection electrode **156** on the pixel electrode

118 is exposed to be etched along the ashed first photo-resist pattern **240A**. Accordingly, the edge part of the reflection electrode **156** may be located at inner side from the edge part of the pixel electrode **118**.

In FIG. **8F**, the first photo-resist pattern **240A** left on the reflection electrode **156** in FIG. **8E** is removed by a strip process.

The photo-resist pattern **240** including the first and the second photo-resist patterns **240A** and **240B**, having thicknesses different from each other, as shown in FIG. **8B** may be formed by an exposure method, which continually use two masks, i.e., a partial exposure mask, using under exposure as shown in FIG. **9**.

In FIG. **9**, a first partial exposure mask **250** includes a quartz substrate **252** and a shielding layer **254** partially formed on the quartz substrate **252**. A second partial exposure mask **260** includes a quartz substrate **262** and a shielding layer **264** partially formed on the quartz substrate **262**. A photo-resist **239** is continually exposed twice by sequentially using the first and the second partial exposure masks **250** and **260**. Accordingly, a developer reaction amount of the photo-resist **239** is differentiated by a sum of exposure amount of two times, to thereby form a first and a second photo-resist pattern **240A** and **240B**, which have thicknesses different from each other.

Specifically, a shielding part P1, where shielding layers **254** and **264** of the first and the second partial exposure masks **250** and **260** are located, entirely intercepts ultra violet UV light in exposure of two times, to thereby remain the first photo-resist pattern **240A** at an area, where both the reflection metal layer **155** and the transparent conductive film **117**, as shown in FIG. **8B**. A partial transmission part P2, where only shielding layer **254** of the first partial exposure mask **250** is located, transmits only a second ultra violet UV light in exposure of two times, to thereby remain the second photo-resist pattern **240B** thinner than the first photo-resist pattern **240A** at an area, where only the transparent conductive film **117** exists, as shown in FIG. **8B**. And, a full transmission part P3, where the quartz substrates **252** and **262** of the first and the second exposure masks **250** and **260** are located, transmits the entire ultra violet UV light in exposure of two times, so that a photo-resist pattern **240** does not exist at an area, where both the reflection metal layer **155** and the transparent conductive film **117** should be removed, as shown in FIG. **8B**.

Accordingly, the method of fabricating the transfective thin film transistor substrate according to the embodiment of the present invention is possible to simplify processes by performing four mask processes.

FIG. **10** is a plan view briefly illustrating the transfective thin film transistor substrate according to the present invention, with a surrounding part.

The transfective thin film transistor substrate **100** shown in FIG. **10** includes a contact electrode **160** in order to connect the data pad **134** formed in the same layer as the gate pad **126** to the data line **104**. In other words, the contact electrode **160** connects a data link **135** extended from the data pad **134**, to the data line **104**. Herein, the contact electrode **160** is formed of the same metal layer as the pixel electrode **118** formed at an active area **182**, is formed of the same reflection metal layer as the reflection electrode **156**, or may be formed in a double layered structure in which the transparent conductive film and the reflection metal layer are stacked. Herein, if the contact electrode **160** is formed of the reflection metal layer to be exposed to an exterior, then there occurs a problem that the contact electrode **160** is corroded. Thus, it is located at an area which is sealed by a sealant **180**, i.e., between the sealant **180** and an active area **182**. Accordingly, it is possible to prevent the corrosion of the contact electrode **160**.

FIG. **11A** is an enlarged plan view illustrating a contact area of the data line **104** and a data link **135**, FIGS. **11B** and **11C** are sectional views illustrating the contact area taken along the line V-V'.

In FIGS. **11A** and **11B**, the data link **135** is adjacent to the data line **104** or overlapped with the data line **104**. Herein, the data line **104** is extended from the data pad **134**, i.e., the lower data pad electrode **136** and is located at the area which is to be sealed by the sealant **180**.

A third contact hole **162** passes through the organic insulating film **154** to the gate insulating film **144** to expose the data link **135**, and a fourth contact hole **164** passes through the organic insulating film **154** and the passivation film **150** to expose the data line **104**.

The contact electrode **160** includes a first contact electrode **166** formed of the transparent conductive film similar to the upper data pad electrode **140** and a second contact electrode **168** formed of the reflection metal layer to capture the first contact electrode **166**. Differently from this, the contact electrode **160** can be formed of only the first contact electrode **166**, or can be formed of only the second contact electrode **168**. The contact electrode **160** connects the data link **135** to the data line **104** via the third and the fourth contact hole **162** and **164**.

The passivation film **150** shown in FIG. **11B** can be omitted as shown in FIG. **11C**.

The surrounding part of the transfective thin film transistor, i.e., the contact area of both the data line **104** and the data link **135**, is formed by performing the fourth mask process as described above. This will be described with reference to FIGS. **12A** to **15B**.

In FIGS. **12A** and **12B**, a gate metal pattern is formed on the lower substrate **142** by a first mask process, wherein the gate metal pattern includes the data link **135** along with the lower data pad electrode **136**. The first mask process is the same as described in FIGS. **4A** and **4B**.

In FIGS. **13A** and **13B**, a gate insulating film **144** is formed by a second mask process, and a semiconductor pattern **148**, including an active layer **116** and an ohmic contact layer **146**, and a data line **104** are stacked on the gate insulating film **144**. The second mask process is the same as described in FIGS. **5A** and **5B**.

In FIGS. **14A** and **14B**, a passivation film **150** and an organic insulating film **154** are formed, and third and fourth contact holes **162** and **164**, that passing through the passivation film **150** and the organic insulating film **154** are formed, by use of a third mask process. The third contact hole **162** passes through the organic insulating film **154** to the gate insulating film **144** to expose the data link **135**, and the fourth contact hole **164** passes through the organic insulating film **154** and the passivation film **150** to expose the data line **104**. Herein, the passivation film **150** can be omitted. The third mask process is the same as described in FIGS. **6A** and **6B**.

In FIGS. **15A** and **15B**, the contact electrode **160**, having the first and the second contact electrodes **166** and **168**, is formed together with the upper data pad electrode **140**, by use of a fourth mask process. The contact electrode **160** passes through the first and the second contact holes **162** and **164** to connect the data link **135** with the data line **104**. The first contact electrode **166** is formed of the same transparent conductive film as the upper data pad electrode **140**, and the second contact electrode **168** is formed of the same reflection metal layer as the above-mentioned reflection electrode **156**. The contact electrode **160** is formed to correspond to the first photo-resist pattern **240A** of the shielding part P1 as shown in FIG. **8B**. At this time, the second contact electrode **168** is the same edge part as the first electrode **166** or has an edge part at an inner side from that of the first electrode **166**.

Differently from this, the contact electrode **160** can be formed of only the first contact electrode **166**, i.e., the transparent conductive film. In this case, the contact electrode **160**

is formed to correspond to the second photo-resist pattern 240B of the partial transmission part P2 as shown in FIG. 8B.

As described above, in the transreflective thin film transistor substrate and the method of fabricating method according to the present invention, the organic insulating film is patterned and a plurality of contact holes is formed by one mask process. Further, the transparent conductive pattern, having the pixel electrode, and the reflection electrode are formed by another mask process. Thus, it is possible to simplify processes by performing four mask processes.

In addition, in the transreflective thin film transistor substrate and the method of fabricating method according to the present invention, the data link and the data line, formed respectively on different layers, are connected together by the contact electrode including at least one of the transparent conductive film and the reflection metal layer. In this arrangement, the contact electrode is formed in the area to be sealed by the sealant, thus it is possible to prevent the corrosion problem caused by the exposure of the contact electrode formed of the reflection metal layer.

It will be apparent to those skilled in the art that various modifications and variation can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A method of fabricating a liquid crystal display device, comprising:
 - providing first and second substrates;
 - forming a gate line on the first substrate, a lower gate pad electrode connected to the gate line, a lower data pad electrode, and a data link extended from the lower data pad electrode, using a first mask during a first mask process;
 - forming a gate insulating film on the first substrate, a semiconductor pattern on the gate insulating film, a data line crossing the gate line to define a pixel area on the semiconductor pattern, a source electrode, and a drain electrode using a second mask during a second mask process;
 - forming an organic insulating film on the data line, the source electrode and the drain electrode and forming a transmission hole passing through the organic insulating film, a gate pad contact hole exposing the lower gate pad electrode, a data pad contact hole exposing the lower data pad electrode, and a plurality of contact holes exposing the data link and the data line, using a third mask during a third mask process; and
 - forming a pixel electrode connected to the drain electrode, passing through the organic insulating film and the transmission hole, forming a reflective electrode on the pixel electrode in a reflective area of the pixel and exposing the pixel electrode in the transmission hole, forming an upper gate pad electrode connected to the lower gate pad electrode via the gate pad contact hole, forming an upper data pad electrode connected to the lower data pad electrode via the data pad contact hole, and forming a contact electrode connected to the data link and the data line through the plurality of contact holes, using a fourth mask during a fourth mask process, in which the contact electrode includes a transparent conductive film same as the pixel electrode and a reflective metal layer same as the reflective electrode,
 wherein the fourth mask process further comprises:
 - forming a transparent conductive film and a reflective metal layer on the organic insulating film;

forming first and second photo-resist patterns on the reflective metal layer using the fourth mask, wherein the first photo-resist pattern is thicker than that of the second photo-resist pattern;

- 5 patterning the transparent conductive film and the reflective metal layer by an etching using the first and the second photo-resist patterns as a mask to form a transparent conductive pattern and a reflective electrode, wherein the transparent conductive pattern has the pixel electrode, the upper pad electrode and the contact electrode, and the reflective electrode has an edge part same as the transparent conductive pattern;
- 10 removing the second photo-resist pattern and thinning the first photo-resist pattern;
- removing the reflective electrode in the transmission hole and on the upper pad electrode by an etching using the first photo-resist pattern as a mask; and
- 15 removing the first photo-resist pattern.

2. The method according to claim 1, wherein: the first mask process further includes forming a storage line substantially parallel to the gate line on the first substrate; and

the second mask process further includes forming a storage capacitor overlapping the storage line with the gate insulating film therebetween by extending the drain electrode and the semiconductor pattern.

3. The method according to claim 1, wherein the contact electrode is located at an area to be sealed by a sealant.

4. The method according to claim 1, wherein the reflective electrode is connected to the pixel electrode and encloses a lateral surface of the transmission hole.

5. The method according to claim 1, wherein the first and the second photo-resist patterns are formed by a photolithography process using one of a diffractive exposure mask, a half-tone mask, and a partial exposure mask.

6. The method according to claim 5, wherein the photolithography process has two exposure processes using first and second partial exposure masks in a case of the partial exposure mask.

7. The method according to claim 5, wherein the first photo-resist pattern corresponds to a shielding layer in the first and the second partial exposure masks, and the second photo-resist pattern corresponds to a shielding layer in the first partial exposure mask.

8. The method according to claim 1, wherein the third mask process further comprises forming a passivation film under the organic insulating film.

9. The method according to claim 8, wherein the passivation film is formed of an inorganic insulating material.

10. The method according to claim 8, wherein the transmission hole passes through the organic insulating film to the gate insulating film.

11. The method according to claim 1, wherein the transmission hole passes through the organic insulating film to the gate insulating film.

12. The method according to claim 1, wherein the third mask process further comprises forming a drain contact hole passing through the organic insulating film to expose the drain electrode, wherein the pixel electrode is connected to the drain electrode via the drain contact hole.

13. The method according to claim 1, wherein the reflective electrode and the pixel electrode overlap at least one of the gate line and the data line.

14. The method according to claim 1, wherein the pixel electrode has a different edge from an edge part of the reflective electrode.

* * * * *

专利名称(译)	制造液晶显示装置的方法		
公开(公告)号	US8294855	公开(公告)日	2012-10-23
申请号	US12/458456	申请日	2009-07-13
[标]申请(专利权)人(译)	LIM JOO SOO KIM WOONG SIK		
申请(专利权)人(译)	LIM JOO SOO KIM WOONG SIK		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	LIM JOO SOO KIM WOONG SIK		
发明人	LIM, JOO SOO KIM, WOONG SIK		
IPC分类号	G02F1/1335 G02F1/1345 G02F1/13		
CPC分类号	G02F1/133555 G02F1/13458 G02F1/136227		
优先权	1020040101554 2004-12-04 KR		
其他公开文献	US20090275155A1		
外部链接	Espacenet USPTO		

摘要(译)

本发明涉及透反射薄膜晶体管基板及其制造方法，其适于简化其工艺。液晶显示装置包括：第一和第二基板；第一基板上的栅极线；第一基板上的栅极绝缘膜；与栅极线交叉的数据线以定义像素区域；薄膜晶体管连接到栅极线 and 数据线；栅极线，数据线和薄膜晶体管上的有机绝缘膜，在像素区域具有透射孔；像素区域的有机绝缘膜上的像素电极通过传输孔并连接到薄膜晶体管；像素电极上的反射电极，具有与像素电极相同的边缘部分或位于像素电极的边缘部分的内侧并暴露透射孔的像素电极的边缘部分。

