



US006559920B1

(12) **United States Patent**
Ahn et al.

(10) **Patent No.:** **US 6,559,920 B1**
(45) **Date of Patent:** **May 6, 2003**

(54) **LIQUID CRYSTAL DISPLAY DEVICE AND METHOD OF MANUFACTURING THE SAME**

(75) Inventors: **Byung-Chul Ahn**, Kyoungsangbuk-do (KR); **Soon-Sung Yoo**, Kyoungsangbuk-do (KR); **Yong-Wan Kim**, Kyoungsangnam-do (KR)

(73) Assignee: **L G. Philips LCD Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 104 days.

(21) Appl. No.: **09/694,285**

(22) Filed: **Oct. 24, 2000**

(30) **Foreign Application Priority Data**

Oct. 25, 1999 (KR) 99-46345

(51) **Int. Cl.**⁷ **G02F 1/1343; G02F 1/136**

(52) **U.S. Cl.** **349/187; 349/44**

(58) **Field of Search** **349/44, 110, 111, 349/43, 187**

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,778,560 A * 10/1988 Takeda et al. 257/350
6,043,511 A * 3/2000 Kim 257/57
6,256,077 B1 * 7/2001 Baek 257/59

* cited by examiner

Primary Examiner—Robert H. Kim


Assistant Examiner—P. R. Akkapeddi


(74) *Attorney, Agent, or Firm*—Birch, Stewart, Kolasch & Birch, LLP

(57) **ABSTRACT**

The present invention discloses a method of manufacturing a liquid crystal display device, including: providing a substrate; depositing sequentially a first metal layer and a first insulating layer on the substrate; patterning the first metal layer and the first insulating layer using a first mask to form a gate line and a first gate insulating layer; depositing sequentially a second gate insulating layer, a pure semiconductor layer, a doped semiconductor layer and a second metal layer over the whole substrate; patterning the second metal layer using a second mask to form a data line, source and drain electrodes, a capacitor electrode, the capacitor electrode overlapping a portion of the gate line; etching the doped semiconductor layer between the source and drain electrodes to form a channel region; depositing a third insulating layer over the whole substrate; patterning the third insulating layer using a third mask to form a passivation film, the passivation film having a smaller width than the data line and covering the source and drain electrodes and exposing a portion of the drain electrode and the capacitor electrode; depositing a transparent conductive material layer over the whole substrate; and patterning the transparent conductive material layer using a fourth mask to pixel electrode, the pixel electrode contacting the drain electrode.


4 Claims, 9 Drawing Sheets






(related art)

FIG. 1




(related art)

FIG. 2




(related art)

FIG. 3A




(related art)

FIG. 3B




(related art)

FIG. 3C



(related art)

FIG. 3D



(related art)

FIG. 3E




FIG. 4




FIG. 5A




FIG. 5B





FIG. 5C




FIG. 5D




FIG. 6




FIG. 7

LIQUID CRYSTAL DISPLAY DEVICE AND METHOD OF MANUFACTURING THE SAME

CROSS REFERENCE

This application claims the benefit of Korean Patent Application No. 1999-46345, filed on Oct. 25, 1999, under 35 U.S.C. § 119, the entirety of which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display device, and more particularly, to a liquid crystal display (LCD) device and a method of manufacturing the same.

2. Description of Related Art

FIG. 1 is a cross sectional view illustrating a typical LCD device. As shown in FIG. 1, the LCD device includes lower and upper substrates 2 and 4 with a liquid crystal layer 10 interposed therebetween. The lower substrate 2 has a thin film transistor "S" (TFT) as a switching element and a pixel electrode 14, and the upper substrate 4 has a color filter 8 and a common electrode 12. The pixel electrode 14 is formed over a pixel region "P" serves to apply a voltage to the liquid crystal layer 10 along with the common electrode 12, and the color filter 8 serves to implement natural colors. A sealant 6 seals an edge of the lower and upper substrate 2 and 4 to prevent a leakage of the liquid crystal.

FIG. 2 is a plan view illustrating the lower array substrate of the typical LCD device. As shown in FIG. 2, the lower array substrate 2 includes gate lines 22 arranged in a transverse direction and data lines 24 arranged in a longitudinal direction perpendicular to the gate lines 22. The TFTs "S" are arranged near a crossing point of the gate and data lines 22 and 24. The pixel electrodes 14 are arranged on a region defined by the gate and data lines 22 and 24. Each of the TFT "S" includes a gate electrode 26, a source electrode 28 and the drain electrode 30. The gate electrode 26 extends from the gate line 22, and the source electrode 28 extends from the data line 24. The drain electrode 30 is electrically connected with the pixel electrode 14 through a drain contact hole 30'. Data and gate pads 21 and 23 are arranged at terminal portions of the gate and data lines 22 and 24, respectively. Storage capacitors "Cst" are formed over a portion of the gate line 22.

A process for manufacturing the LCD device described above is very complex. Especially, the lower array substrate is manufactured through several mask processes. The process of manufacturing the lower array substrate is explained below with reference with FIGS. 3A to 3E.

FIGS. 3A to 3E are cross sectional views taken long lines A—A and B—B of FIG. 2, respectively. First, as shown in FIG. 3A, a metal layer is deposited on a substrate 1 using a sputtering technique after removing alien substances and organic materials and cleaning the substrate to enforce an adhesion between the substrate 1 and the metal layer. Thereafter, the metal layer is patterned into a gate line 22 including a gate electrode 26 using a first mask. The gate line 22 is made of a low resistive material such as aluminum or molybdenum to lower a RC delay. Pure aluminum is a bad corrosion resistance and may cause a line defect due to a hillock in a subsequent process. Therefore, an aluminum alloy or a two or three-layered aluminum is usually used. A portion of the gate line 22 serves as a first capacitor electrode.

As shown in FIG. 31B, a gate insulating layer 50 is deposited on the exposed surface of the substrate 1 while covering the gate line 22 and the gate electrode 26. The gate insulating layer 50 has a thickness of 3000 Å and is usually made of SiNx or SiOx. A pure amorphous silicon layer 52 and a doped amorphous silicon layer 54 are sequentially deposited on the gate insulating layer 50. Then, the amorphous silicon layer 52 and the doped amorphous silicon layer 54 are patterned into an active layer 55 and a semiconductor island 53. The doped amorphous silicon layer 54 is called an ohmic contact layer and serves to reduce a contact resistance between the active layer 55 and a metal layer that will be formed in later process.

Subsequently, as shown in FIG. 3C, a metal layer is deposited on the semiconductor layers 53 and 55 and is patterned into source and drain electrodes 28 and 30 using a third mask. The source and drain electrode 53 and 55 are usually made of chromium or chromium alloy. At the same time as the source and drain electrodes 28 and 30, the data lines 24 are formed. A second capacitor electrode 58 is formed on the gate insulating layer 50 and overlaps a portion of the gate line 22 in order to form a storage capacitor. In other words, using the third mask, the data line 24, the source and drain electrodes 28 and 30, and the second capacitor electrode 58 are formed. Using the source and drain electrodes 28 and 30 as a mask, a portion of the ohmic contact layer 54 over the gate electrode 26 is etched. If the portion of the ohmic contact layer 54 over the gate electrode 26 is not etched, it brings about bad electrical characteristics and a bad performance of the TFT "S". Etching the portion of the ohmic contact layer 54 over the gate electrode 26 requires special attention. It is because the etching uniformity directly affects electrical characteristics of the TFT.

As shown in FIG. 3D, a passivation film 56 is formed over the substrate 1 using the fourth mask in order to protect the active layer 55. The passivation film 56 may affect electrical characteristics of the TFT due to an unstable energy state of the active layer 55 and alien substances generated during the etching process, and therefore it is usually made of an inorganic material such as SiNx and SiO₂ or an organic material such as benzocyclobutene (BCB). The passivation film 56 also requires a high light transmittance, a high humidity resistance and a high durability. The passivation film 56 includes two contact hole: the drain contact hole 30' and a capacitor contact hole 58'.

Therefore, as shown in FIG. 3E, a transparent conducting oxide layer is deposited on the passivation film 56 and is patterned into the pixel electrode 14 using a fifth mask. The pixel electrode 14 is usually made of indium tin oxide (ITO). The pixel electrode 14 is electrically connected with the drain electrode 30 through the drain contact hole 30' and with the second capacitor electrode 58 through the capacitor contact hole 58'.

The process for manufacturing the conventional LCD device described above includes at least five masks. Further, when the gate electrode is made of aluminum, at least two masks are required to overcome an occurrence of the hillock that may be generated on the surface of the aluminum layer. Therefore, manufacturing the TFT array substrate basically requires five or six masks. Such a mask process includes various processes such as a cleaning, a depositing, a baking, an etching and the like. Therefore, even a reduction of one mask causes a short processing time, a low production cost and a high manufacturing yield.

For the foregoing reasons, there is a need for a liquid crystal display device manufactured by the mask process decreased in number.

SUMMARY OF THE INVENTION

To overcome the problems described above, preferred embodiments of the present invention provide a liquid crystal display device manufactured the mask process decreased in number and a method of manufacturing the same.

Preferred embodiments of the present invention further provide the liquid crystal display device having a short processing time and a high manufacturing yield.

In order to achieve the above object, the preferred embodiment of the present invention A method of manufacturing a liquid crystal display device, including: providing a substrate; depositing sequentially a first metal layer and a first insulating layer on the substrate; patterning the first metal layer and the first insulating layer using a first mask to form a gate line and a first gate insulating layer; depositing sequentially a second gate insulating layer, a pure semiconductor layer, a doped semiconductor layer and a second metal layer over the whole substrate; patterning the second metal layer using a second mask to form a data line, source and drain electrodes, a capacitor electrode, the capacitor electrode overlapping a portion of the gate line; etching the doped semiconductor layer between the source and drain electrodes to form a channel region; depositing a third insulating layer over the whole substrate; patterning the third insulating layer using a third mask to form a passivation film, the passivation film having a smaller width than the data line and covering the source and drain electrodes and exposing a portion of the drain electrode and the capacitor electrode; depositing a transparent conductive material layer over the whole substrate; and patterning the transparent conductive material layer using a fourth mask to pixel electrode, the pixel electrode contacting the drain electrode.

The gate line includes a gate pad formed at its terminal portion, the gate pad including at least one pad contact hole. The method further includes forming gate pad electrode using the fourth mask, the gate pad electrode contacting the gate pad through at least one pad contact hole. A crossing portion between the gate line and data line is insulated by the second insulating layer, the pure semiconductor layer and the doped semiconductor layer.

The preferred embodiment of the present invention further provides a liquid crystal display device, including: a substrate; a thin film transistor formed on the substrate, including: a gate line having a gate electrode; first and second insulating layers; an active layer; and source and drain electrodes; a pixel electrode overlapping a portion of the gate lines and contacting the drain electrode; and a storage capacitor including: a portion of the gate line as a first electrode; a second electrode overlapping the portion of the gate line; and the first and second insulating layers, the pure semiconductor layer and the doped semiconductor layer interposed between the gate line and the pixel electrode as a dielectric layer.

The LCD device according to the preferred embodiment of the present invention has the following advantages. First, since the LCD device can be manufactured using only four masks, the processing time becomes decreased and the manufacturing yield is high. Further, since the process is reduced in number, the production cost is low. Since the gate pads include a plurality of the pad contact holes, a contact resistance between the pixel electrode and the gate pad becomes lowered due to the side contact.

BRIEF DESCRIPTION OF THE DRAWINGS

For a more complete understanding of the present invention and the advantages thereof, reference is now made to

the following descriptions taken in conjunction with the accompanying drawings, in which like reference numerals denote like parts, and in which:

FIG. 1 is a cross sectional view illustrating a typical liquid crystal display (LCD) device;

FIG. 2 is a plan view illustrating an array substrate of the typical LCD device,

FIGS. 3A to 3E are cross sectional views taken along lines A—A and B—B of FIG. 2;

FIG. 4 is a plan view illustrating an array substrate of an LCD device according to a preferred embodiment of the present invention;

FIGS. 5A to 5D are plan views and cross sectional views taken along lines □—□ of FIG. 4;

FIG. 6 is a cross sectional view taken along line □—□ of FIG. 5D, and

FIG. 7 is a cross sectional view taken along line □—□ of FIG. 5D.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Reference will now be made in detail to the preferred embodiment of the present invention, example of which is illustrated in the accompanying drawings.

FIG. 4 is a plan view illustrating a lower array substrate of a liquid crystal display (LCD) device according to the preferred embodiment of the present invention. As shown in FIG. 4, gate lines **102** are arranged in a transverse direction and data lines **120** are arranged in a longitudinal direction perpendicular to the gate lines **102**. The TFTs are arranged near a crossing point of the gate and data lines **102** and **120**. The pixel electrodes **118** are arranged on a region defined by the gate and data lines **102** and **120**. Each of the TFT includes a gate electrode **101**, a source electrode **112** and the drain electrode **114**. The gate electrode **101** extends from the gate line **102**, and the source electrode **112** extends from the data line **114**. The drain electrode **114** is electrically connected with the pixel electrode **118** through a drain contact hole **116**. Data and gate pads **106** and **124** are arranged at terminal portions of the gate and data lines **102** and **120**, respectively. Storage capacitors are formed over a portion of the gate line **102**.

A process for manufacturing the LCD device according to the preferred embodiment of the present invention is explained below with reference with FIGS. 5A to 3D.

FIGS. 5A to 5D are plan views and cross sectional views taken long lines □—□ of FIG. 4. First, as shown in FIG. 5A, a first metal layer and a first insulating layer are sequentially deposited on a substrate **1** and is patterned into the gate line **102** and a gate insulating layer **200** using a first mask. The gate line **102** includes the gate electrode **101**. In FIG. 5A, the gate electrode **101** seems like a portion of the gate line **102**, but the gate electrode **101** may extend from the gate line **102**. The gate line **102** is made of aluminum, chromium, molybdenum or aluminum alloy, for example, having the dual-layered structure of AlNd/Mo. The gate pads **106** are formed at a terminal portion of the gate lines **102**. Preferably, the gate pads **106** include a plurality of pad contact holes **108**. Through the pad contact hole **108**, the gate pad **106** is electrically connected with the transparent conductive electrode that will be formed in subsequent process. When the gate pad **106** includes a plurality of the pad contact holes **108**, a contact resistance between the gate pad **106** and the transparent conductive electrode becomes lowered.

Subsequently, as shown in FIG. 5B, a semiconductor layer **202** and a second metal layer are sequentially deposited on

the gate insulating layer **200** and are patterned into source and drain electrodes **112** and **114**, a capacitor electrode **150** using a second mask. Thereafter, using the source and drain electrodes **112** and **114** as a mask, a portion of the semiconductor layer **202** is etched. The semiconductor layer **202**, even though not shown, includes a doped semiconductor layer and a pure semiconductor layer. In other words, excluding a portion of the semiconductor layer **202** under the patterned second metal layer, the rest portion of the semiconductor layer **202** is etched in order to decrease a leakage current. A second insulating layer **201** is formed on the gate insulating layer **200**. The reason is to prevent a possible line short at a step portion "T" between the gate line **102** and the data line **120**.

Then, as shown in FIG. 5C, a third insulating layer is deposited over the whole substrate **1** and is patterned into a passivation film **122** using a third mask. At this point, the semiconductor layer **202** and the second insulating layer **201** excluding a portion under the patterned passivation film **122** are etched at the same time. The gate line **102** including the gate pad **106** is protected by the gate insulating layer **200**. The passivation film **122** includes a capacitor contact hole **204** and a drain contact hole **116**. The capacitor contact hole **204** is formed over the capacitor electrode **150**, and the drain contact hole **116** is formed over the drain electrode **114**.

Finally, as shown in FIG. 5D, a transparent conductive material layer is deposited on the passivation film **122** and is patterned into the pixel electrode **118** using a fourth mask. The pixel electrode **118** is electrically connected with the drain electrode **114** through the drain contact hole **116** and with the capacitor electrode **150** through the capacitor contact hole **203**, respectively. A gate pad electrode **107** is formed over the gate pad **106** for a side-contact with the gate pad **106**.

FIG. 6 is a cross sectional view taken along line □—□ of FIG. 5D, illustrating the data pad. As shown in FIG. 6, the semiconductor layer **202** is formed over the substrate **1**. The data pad **105** is patterned on the semiconductor layer **202**, the passivation film **122** overlaps both end portions of the data pad **105**. A data pad electrode **109** covers the passivation film **122** to electrically contact the data pad **105**. At this point, the gate and data pad electrodes **107** and **109** substantially contact with the external drive circuit (not shown).

FIG. 7 is a cross sectional view taken along line □—□ of FIG. 5D, illustrating the storage capacitor. As shown in FIG. 7, the storage capacitor includes the gate line **102** as a first capacitor electrode and the capacitor electrode **150** as a second capacitor electrode. The gate insulating layer **200** and second insulating layer **201** are used as a dielectric layer. The pixel electrode **118** serves as an electrode for withdrawing charges and is electrically connected with the capacitor electrode **150**.

As described above, a crossing portion between the gate line and the data line is insulated by the second insulating layer. When the gate lines are formed using the first mask, the gate pad contact hole is formed. Further, since the gate pads include a plurality of the pad contact holes, a contact resistance between the pixel electrode and the gate pad becomes lowered due to the side contact.

The LCD device according to the preferred embodiment of the present invention has the following advantages. First, since the LCD device can be manufactured using only four masks, the processing time becomes decreased and the manufacturing yield is high. Further, since the process is reduced in number, the production cost is low. Since the gate pads include a plurality of the pad contact holes, a contact resistance between the pixel electrode and the gate pad becomes lowered due to the side contact.

While the invention has been particularly shown and described with reference to preferred embodiments thereof, it will be understood by those skilled in the art that the foregoing and other changes in form and details may be made therein without departing from the spirit and scope of the invention.

What is claimed is:

1. A method of manufacturing a liquid crystal display device, comprising:

- providing a substrate;
- depositing sequentially a first metal layer and a first insulating layer on the substrate;
- patterning the first metal layer and the first insulating layer together using a first mask to form a gate line and a first gate insulating layer;
- depositing sequentially a second gate insulating layer, a pure semiconductor layer, a doped semiconductor layer and a second metal layer over the whole substrate;
- patterning the second metal layer using a second mask to form a data line, source and drain electrodes, a capacitor electrode, the capacitor electrode overlapping a portion of the gate line;
- etching the doped semiconductor layer between the source and drain electrodes to form a channel region;
- depositing a third insulating layer over the whole substrate;
- patterning the third insulating layer using a third mask to form a passivation film, the passivation film having a smaller width than the data line and covering the source and drain electrodes and exposing a portion of the drain electrode and the capacitor electrode;
- depositing a transparent conductive material layer over the whole substrate; and
- patterning the transparent conductive material layer using a fourth mask to pixel electrode, the pixel electrode contacting the drain electrode.

2. The method of claim 1, wherein the gate line includes a gate pad formed at its terminal portion, the gate pad including at least one pad contact hole.

3. The method of claim 1, further comprising, forming gate pad electrode using the fourth mask, the gate pad electrode contacting the gate pad through at least one pad contact hole.

4. The method of claim 1, wherein a crossing portion between the gate line and data line is insulated by the second insulating layer, the pure semiconductor layer and the doped semiconductor layer.

* * * * *

专利名称(译)	液晶显示装置及其制造方法		
公开(公告)号	US6559920	公开(公告)日	2003-05-06
申请号	US09/694285	申请日	2000-10-24
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	大号G.飞利浦液晶CO., LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO., LTD.		
[标]发明人	AHN BYUNG CHUL YOO SOON SUNG KIM YONG WAN		
发明人	AHN, BYUNG-CHUL YOO, SOON-SUNG KIM, YONG-WAN		
IPC分类号	G02F1/13 G02F1/1362 G02F1/136 G02F1/1343		
CPC分类号	G02F1/13458 G02F1/136227 G02F1/136213		
审查员(译)	KIM, 罗伯特H.		
优先权	1019990046345 1999-10-25 KR		
外部链接	Espacenet USPTO		

摘要(译)

本发明公开了一种制造液晶显示装置的方法，包括：提供基板；在基板上依次沉积第一金属层和第一绝缘层；使用第一掩模图案化第一金属层和第一绝缘层，以形成栅极线和第一栅极绝缘层；在整个衬底上依次沉积第二栅极绝缘层，纯半导体层，掺杂半导体层和第二金属层；使用第二掩模图案化第二金属层以形成数据线，源极和漏极，电容器电极，电容器电极与栅极线的一部分重叠；蚀刻源极和漏极之间的掺杂半导体层以形成沟道区；在整个衬底上沉积第三绝缘层；使用第三掩模图案化第三绝缘层以形成钝化膜，钝化膜具有比数据线小的宽度并覆盖源电极和漏电极并暴露漏电极和电容器电极的一部分；在整个衬底上沉积透明导电材料层；使用第四掩模对像素电极图案化透明导电材料层，像素电极与漏电极接触。

