



US006703173B2

(12) **United States Patent**  
**Lu et al.**

(10) **Patent No.:** **US 6,703,173 B2**  
(45) **Date of Patent:** **Mar. 9, 2004**

(54) **COLOR FILTERS FOR LIQUID CRYSTAL DISPLAY PANELS AND METHOD OF PRODUCING THE SAME**

(75) Inventors: **Chun Fu Lu**, Hsinchu (TW); **Fanny Shieh**, Hsinchu (TW); **Chin-Tai Chen**, Kaohsiung (TW)

(73) Assignee: **Industrial Technology Research Institute**, Hsinchu (TW)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/098,855**

(22) Filed: **Mar. 13, 2002**

(65) **Prior Publication Data**

US 2003/0099887 A1 May 29, 2003

(30) **Foreign Application Priority Data**

Nov. 23, 2001 (TW) ..... 90129105 A

(51) **Int. Cl.**<sup>7</sup> ..... **G02B 5/20; G02F 1/1335**

(52) **U.S. Cl.** ..... **430/7**

(58) **Field of Search** ..... 430/7; 349/106; 358/891

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

5,641,595 A \* 6/1997 Hsieh et al. .... 430/7

**FOREIGN PATENT DOCUMENTS**

JP 1-229205 A \* 9/1989

JP 4-158303 A \* 6/1992

JP 7-239468 A \* 9/1995

\* cited by examiner


*Primary Examiner*—John A. McPherson

(74) *Attorney, Agent, or Firm*—Merchant & Gould P.C.

(57) **ABSTRACT**

A color filter for liquid crystal display panels. The filter includes a transparent substrate with a metal layer formed thereon, and a first color layer, a second colour layer and a third color layer are integrally formed with the same metal layer. The invention also provides a method for producing the color filter described above. The method applies the theory of oxidizing metal layers by repeatedly exposing and oxidizing to form a color filter having multiple integrally formed colors. Depending on requirements, the color filter of the invention also includes the black matrix that is often included in liquid crystal display panels.

**31 Claims, 7 Drawing Sheets**






FIG. 1a ( PRIOR ART )




FIG. 1b ( PRIOR ART )




FIG. 1c ( PRIOR ART )



FIG. 2a



FIG. 2b




FIG. 2c




FIG. 2d




FIG. 2e




FIG. 2f




FIG. 2g




FIG. 2h




FIG. 3a




FIG. 3b




FIG. 3c




FIG. 3d




FIG. 3e




FIG. 3f




FIG. 4a




FIG. 4b




FIG. 4c




FIG. 4d




FIG. 4e




FIG. 4f




FIG. 4g




FIG. 4h

# COLOR FILTERS FOR LIQUID CRYSTAL DISPLAY PANELS AND METHOD OF PRODUCING THE SAME

## BACKGROUND OF THE INVENTION

### 1. Field of the Invention

The present invention relates to a color filter for liquid crystal display (LCD) panels, in particular, a color filter with integrally formed multicolor layer and a method of producing the same.

### 2. Description of the Prior Art

In general, conventional methods for producing color filters for LCD panels utilize various mechanisms to coat three primary colors (red, green and blue) onto predetermined positions of a substrate, followed by separation, filtration and the addition of adhesive. Examples of such methods includes printing, electro-deposition method, colorant dispersion, dyeing, ink-jet etc. The above-mentioned methods and their disadvantages are further discussed as follows:

- (1) Printing method: Three primary colors are sequentially printed onto a substrate using a screen board. However it is difficult to control the positions of colors and the uniformity of the thickness of various colors.
- (2) Electro-deposition method: Ground colorants are sequentially electro-deposited to predetermined positions by electrical-ionic dispersing agent. But, patterns of colors are limited due to the thickness of colorant affected by difficulty in controlling the uniformity of current.
- (3) Colorant dispersion method: Non-ionic surfactant is used as dispersion agent for high molecular colorant to make a colored photosensitive agent. A substrate coated with the photosensitive agent is then subjected to photolithography to obtain expected colored areas. However, three courses of lithography are required, thereby increasing production costs.
- (4) Dyeing method: A substrate coated with a dyeable photosensitive agent is exposed to obtain partitioned areas, followed by localized coloring to obtain expected color areas. However, this method exhibits reliability problems, such as deficiency of chemical resistance, heat resistance and litho-resistance.
- (5) Ink-jet method: Shown in FIGS. 1a-1c, where **104** represents a substrate, **103** represents black matrix, **102** represents an ink-absorbing layer, and **101a-101c** represent ink in different colors. In FIG. 1a, a substrate **104** is prepared for ink-jetting; and contact of ink with the substrate is shown in FIG. 1b. FIG. 1c illustrates the completion of colored substrate. In this method, a substrate is firstly coated with an ink-absorbing layer, followed by another smooth coating of photoresist agent in thick-film. Next, the substrate is subjected to photolithography to attain partitioned areas, followed by ink-jetting to obtain expected colored areas. In this method, three primary colors (red, green, blue) are printed onto the substrate simultaneously, thus the process time and costs for material are more economical than the colorant dyeing method. However, high molecular material is required as adhesion promoter or dispersion agent, which is mostly deficient in resistance to chemicals, heat and light.

In addition, in the above-mentioned methods, three colors are formed in repeated steps. Hence, gaps easily occur

between different colors. Also, the thickness of colors is difficult to control. Consequently, there are problems in product quality.

## SUMMARY OF THE INVENTION

In order to overcome the above problems, an object of the invention is to provide a color filter for LCD panels, in which the multicolor layer of the color filter is formed directly from the oxidization of a metal layer on the substrate, without high molecular material, such as dispersion agent, adhesion agent, and color-absorbing layer. As a result, deficiency in resistance to chemicals, heat and light is avoided.

It is another object of the invention to provide a color filter with high rate of windows, good reliability, and high resolution.

Another object of the invention is to provide a method to produce a color filter that causes less pollution and is low in production costs.

In order to achieve the above objects, there is provided a color filter for LCD panels, comprising a transparent substrate; and a metal layer formed on the substrate, wherein the metal layer contains integrally formed first color layer, second colour layer and third color layer.

Based on this invention, a method for producing a color filter with integrally formed multicolor layer is carried out by repeatedly exposing a transparent substrate coated with a metal layer with the aid of a photoresist layer to form different colors in the metal layer. The pattern of the photoresist layer is predetermined so that the different color layers are formed in the required positions. In the case where black matrix is necessary, it can be easily attained by further exposing the metal layer with another photoresist layer having the pattern of black matrix.

The present invention will become more fully understood from the detailed description given hereinbelow and the accompanying drawings, given by way of illustration only and thus not intended to be limitative of the present invention.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1a-1c illustrate the process of producing a color filter by conventional ink-jet method.

FIGS. 2a-2h illustrate the process according to the 1<sup>st</sup> Embodiment of the invention to produce a color filter without black matrix.

FIGS. 3a-3f illustrate the process according to the 1<sup>st</sup> Embodiment of the invention to produce a color filter with black matrix.

FIGS. 4a-4h illustrate the process according to the 2<sup>nd</sup> Embodiment of the invention to produce a color filter.

## DETAILED DESCRIPTION OF THE INVENTION

According to the invention, a color filter for liquid crystal display panels comprises a transparent substrate and a metal layer formed on the substrate, wherein a first color layer, a second color layer and a third color layer are integrally formed with the metal layer. In addition, black matrix can also be added in the positions between different colour layers with extra steps.

A method for producing a color filter for liquid crystal display panels comprises providing a transparent substrate, and forming a metal layer on the substrate, oxidizing the

metal layer to form a first color layer, forming a positive photoresist layer on the first color layer, exposing selectively to form a completely exposed area, a partially exposed area and an unexposed area on the positive photoresist layer, entirely oxidizing the metal layer, removing the partially exposed area by entirely exposing and oxidizing again to form a second color layer from the first color layer corresponding to the partially exposed area of the positive photoresist layer and to form a third color layer in the metal layer corresponding to the completely exposed area of the positive photoresist layer, and removing the positive photoresist layer.

In the case where it is necessary to form black matrix, the above method further comprises the steps of: forming a photoresist layer on the first color layer, the second color layer and the third color layer, exposing selectively to form black matrix in the photoresist layer corresponding to the positions between different color layers, oxidizing integrally to form fourth color layers in the metal layer between different color layers, and removing the photoresist layer.

According to another embodiment of the invention, the method for producing a color filter for liquid crystal display panels comprising providing a transparent substrate, and forming a metal layer on the substrate, oxidizing the metal layer to form a first color layer, forming a positive photoresist layer on the first color layer, exposing selectively to form a completely exposed area, partially exposed area and unexposed area on the positive photoresist layer, entirely oxidizing the metal layer, removing the partially exposed area and exposing entirely again to form a second color layer from the first color layer corresponding to the partially exposed area of the positive photoresist layer and to form a third color layer in the metal layer corresponding to the completely exposed area of the positive photoresist layer, and removing the positive photoresist layer.

To form black matrix in the color filter, the following steps can be further performed: forming a photoresist layer on the first color layer, the second color layer and the third color layer; exposing selectively to form black matrix in the photoresist layer corresponding to the positions between different color layers; oxidizing integrally to form fourth color layers in the metal layer between different color layers; and removing the photoresist layer.

According to another embodiment of the invention, a method for producing a color filter for liquid crystal display panels comprises providing a transparent substrate, and forming a metal layer on the substrate, oxidizing the metal layer integrally to form a first color layer, forming a positive photoresist layer on the first color layer, exposing selectively to form a complete exposed area, a first exposed area, a second exposed area and unexposed area on the positive photoresist layer, wherein the exposure dose of the first exposed area is greater than that of the second exposed area, oxidizing the metal layer integrally, removing the first exposed area and reoxidizing, removing the second exposed area and reoxidizing to form a fourth color layer on the first color layer corresponding to the complete exposed area, a third color layer on the first color layer corresponding to the first exposed area and a second color layer on the first color layer corresponding to the second exposed area, and removing the remaining positive photoresist layer.

The preferable transparent substrate in this invention is glass or polymer, and metal layer is preferably Cr, Cu, Al, Fe or Ni, with a thickness of 60–5000 Å.

The method for producing a color filter for liquid crystal display panels of the invention mainly uses oxidation of

metal to form different colors. Using oxidation of chromic acid as an example, blue, green, red and black are obtained based on the length of the reaction time of chromium in chromic acid.

According to the invention, colors of the color filter can also be achieved by other means, such as laser or high temperature oxidation, where the affect of the uniformity of current density on patterns can be avoided. In addition, the use of color photoresist agent is economized.

Furthermore, since the color layer of the color filter of the invention is oxidized directly from metal, there are no problems such as color mixing or leakage of light. Consequently, the optical quality of the color filter is greatly improved. In comparison to conventional processes, the invention provides a method that is superior in quality and production costs.

#### PREFERRED EMBODIMENTS

##### 1<sup>st</sup> Embodiment

FIGS. 2a–2f illustrate the process according to the 1<sup>st</sup> Embodiment of the invention to produce a color filter without black matrix. First, in FIG. 2a, a transparent substrate **100** is provided, followed by forming a Cr layer **110α** by physical vapor deposition (PVD) on the substrate **100**, as shown in FIG. 2b. Next, the Cr layer is completely oxidized to form a first color layer **110** (blue).

The formation of metal layer by PVD can be replaced with chemical vapor deposition (CVD) as well. The thickness of the Cr layer is at least a layer of Cr atom or Cr-containing alloy, within the range of 60–5000 Å. The transparent substrate is glass or polymer. As for the Cr layer, other metals such as Cu, Al, Fe and Ni are applicable as well. The oxidation step is performed by a strong acid, such as chromic acid, sulfuric acid, nitric acid or combinations thereof. A combination of chromic acid and sulfuric acid is used in this embodiment.

Then, in FIG. 2c, a positive photoresist layer **120** is formed on the first color layer **110**. The positive photoresist layer is novolak resin, diazo compound or combinations thereof. In this embodiment, a commonly used photoresist agent containing novolak resin is used.

Next, a mask **150** with predetermined pattern is used for photolithography, as shown in FIG. 2d. The pattern of the mask is designed so that it contains three areas with different exposure (including a complete exposed area **130α**, partially exposed area **125α** and unexposed area **132**). Suitable developing solution contains sodium carbonate, sodium hydrogencarbonate, sodium silicate, sodium hydroxide, potassium hydroxide and tetraalkyl amine compounds and combinations thereof. Sodium hydrogencarbonate is used in this embodiment.

After the above photolithography steps, a complete exposed area **130**, partially exposed area **125** and unexposed area **120** are formed. Next, strong acid completes oxidization. At this time, the first color layer corresponding to the completely exposed area **130** is oxidized twice to form a third color layer **135**, as shown in FIG. 2e.

Then, the partially exposed area **125** of the positive photoresist layer is removed to reveal the first color layer corresponding to the partially exposed area, as shown in FIG. 2f. Strong acid is used again to complete oxidization. At this time, the first color layer corresponding to the partially exposed area is twice oxidized to form a second color layer **140** (green) and the third color layer **136** is oxidized three times to become red. The first color layer **110** located at both ends remain blue, shown in FIG. 2g. Three color layers are simultaneously obtained by the above

5

repeated oxidation steps. Finally, the remaining positive photoresist layer **120** is removed to obtain a color filter with integrally formed three color layers: first color layer **110**, second color layer **140** and third color layer **136**.

The color filter obtained is then subjected to further steps to form black matrix. FIGS. **3a–3f** illustrates the process to produce a color filter with black matrix, and FIG. **3a** shows a transparent substrate **100** with three color layers **110**, **136** and **140** formed on the surface.

In FIG. **3b**, an overall photoresist layer **160** is formed on the color layer. Next, a mask is used for photolithography. The mask has unexposed area **165** and complete exposed area **170a**, as shown in FIG. **3c**, where the complete exposed area is located between different color layers **110**, **136** and **140**. After photolithography, complete exposed areas **170** are formed on the photoresist layer **160**, as shown in FIG. **3d**. In this step, either positive or negative photoresist layer is applicable.

Oxidation with strong acid is then repeated to form black matrix **180** between different color layers **110**, **136** and **140**, as shown in FIG. **3e**. Finally, a color filter with black matrix, shown in FIG. **3f**, is obtained by removing the remaining photoresist layer **160**.

*2<sup>nd</sup> Embodiment*

FIGS. **4a–4h** illustrate the process according to the *2<sup>nd</sup>* Embodiment of the invention to produce a color filter. In this embodiment, details such as the thickness of the metal layer and the formation method thereof, developing solution and photoresist material are the same as those of the *1<sup>st</sup>* Embodiment.

Firstly, in FIGS. **4a** and **4b**, a Cr layer was completely oxidized to form a first color layer **310** (blue) and a positive photoresist layer **320** is sequentially formed on a transparent substrate **300**.

Then, as shown in FIG. **4c**, a mask is used for photolithography. The pattern of the mask includes four areas of different exposures (completely exposed area **335a**, a first partially exposed area **325a**, a second partially exposed area **330a** and an unexposed area **320a**), where the exposure of the first partially exposed area is greater than that of the second partially exposed area. An alkali solution of sodium hydrogencarbonate is used as the developing solution.

After the above photolithography steps, a complete exposed area **335**, a first partially exposed area **325**, a second partially exposed area **330** and an unexposed area **320** are formed on the positive photoresist layer. Next, as shown in FIG. **4d**, overall oxidation is performed, so that an area of the first color layer corresponding to the complete exposed area **335** is twice oxidized to form a fourth color layer **341**, leaving the areas **350**, **360** not oxidized.

Next, the first partially exposed area **325** of the positive photoresist layer is removed to reveal the first color layer **350** corresponding to the first partially exposed area **325**, shown in FIG. **4e**. Again, an overall oxidation is performed so that the first color layer **350** corresponding to the first partially exposed area **325** is twice oxidized to form a third color layer **351**, and the fourth color layer **342** is oxidized three times, shown in FIG. **4f**. At this time, the first color layer **360** remains covered by the second partially exposed area **331**.

Then, as shown in FIG. **4g**, the second partially exposed area **331** is removed, followed by an overall oxidation. At this time, the first color layer corresponding to the second partially exposed area **331** is oxidized twice to form a second color layer **361** (green), the third color layer is oxidized three times to become red, the fourth color layer **343** is oxidized four times to become black, and the first color layer **310** at

6

both ends remain blue. Four colors are obtained after the steps repeated above. Finally, as shown in FIG. **4h**, the remaining positive photoresist layer **320** is removed to obtain a color filter with four color layers (the first color **310**, the fourth color layer **340**, the third color layer **352** and the second color layer **361** formed integrally. The fourth color layer is the black matrix.

It is observed from the embodiments that different colors of the color filter of the invention are formed directly from the oxidation of metal. Since different colors are formed integrally, there is no mixing or disconnection of colors. The fourth color layer described in this invention refers to the black matrix, which is often required in a color filter for liquid crystal display panels. When necessary, a coating for protection can be applied to protect against pollution or stop further oxidation.

Though the oxidation is done by strong acid in the embodiments, high temperature or laser are also applicable to provide necessary energy. In particular, laser exhibits the ability to reduce the partitions needed for lithography.

The foregoing description of the preferred embodiments of this invention has been presented for purposes of illustration and description. Obvious modifications or variations are possible in light of the above teaching. The embodiments were chosen and described to provide the best illustration of the principles of this invention and its practical application to thereby enable those skilled in the art to utilize the invention in various embodiments and with various modifications as are suited to the particular use contemplated. All such modifications and variations are within the scope of the present invention as determined by the appended claims when interpreted in accordance with the breadth to which they are fairly, legally, and equitably entitled.

What is claimed is:

**1.** A method for producing a color filter for liquid crystal display panels, comprising:

providing a transparent substrate, and forming a metal layer on the substrate;

oxidizing the metal layer to form a first color layer;

forming a positive photoresist layer on the first color layer;

exposing selectively to form a completely exposed area, partially exposed area and unexposed area on the positive photoresist layer;

entirely oxidizing the metal layer;

removing the partially exposed area and oxidizing entirely again to form a second color layer from the first color layer corresponding to the partially exposed area of the positive photoresist layer and to form a third color layer in the metal layer corresponding to the completely exposed area of the positive photoresist layer; and removing the positive photoresist layer.

**2.** The method as claimed in claim **1**, wherein the transparent substrate is glass or polymer.

**3.** The method as claimed in claim **1**, wherein the metal is Cr, Cu, Al, Fe or Ni.

**4.** The method as claimed in claim **1**, wherein the thickness of the metal layer is 60–5000 Å.

**5.** The method as claimed in claim **1**, wherein the positive photoresist layer is novolak resin, diazo compound or combinations thereof.

**6.** The method as claimed in claim **1**, wherein a solution used for developing contains sodium carbonate, sodium hydrogencarbonate, sodium silicate, sodium hydroxide, potassium hydroxide and tetraalkyl amine compounds and combinations thereof.

7

7. The method as claimed in claim 1, wherein the oxidizing step is carried out by strong acids.

8. The method as claimed in claim 7, wherein the strong acids are chromic acid, sulfuric acid, nitric acid and combinations thereof.

9. The method as claimed in claim 1, wherein the oxidizing step is carried out by laser or high temperature.

10. The method as claimed in claim 1, wherein the metal layer is formed by physical vapor deposition (PVD) or chemical vapor deposition (CVD).

11. The method as claimed in claim 1, further comprising: forming a photoresist layer on the first color layer, the second color layer and the third color layer;

exposing selectively to form black matrix in the photoresist layer corresponding to the positions between different color layers;

oxidizing integrally to form fourth color layers in the metal layer between different color layers; and

removing the photoresist layer.

12. The method as claimed in claim 11, wherein the transparent substrate is glass or polymer.

13. The method as claimed in claim 11, wherein the metal is Cr, Cu, Al, Fe or Ni.

14. The method as claimed in claim 11, wherein the thickness of the metal layer is 60–5000 Å.

15. The method as claimed in claim 11, wherein the positive photoresist layer is novolak resin, diazo compound or combinations thereof.

16. The method as claimed in claim 11, wherein a solution used for developing contains sodium carbonate, sodium hydrogencarbonate, sodium silicate, sodium hydroxide, potassium hydroxide and tetraalkkyl amine compounds and combinations thereof.

17. The method as claimed in claim 11, wherein the oxidizing step is carried out by strong acids.

18. The method as claimed in claim 17, wherein the strong acids are chromic acid, sulfuric acid, nitric acid and combinations thereof.

19. The method as claimed in claim 11, wherein the oxidizing step is carried out by laser or high temperature.

20. The method as claimed in claim 11, wherein the metal layer is formed by physical vapor deposition (PVD) or chemical vapor deposition (CVD).

21. A method for producing a color filter for liquid crystal display panels, comprising:

providing a transparent substrate, and forming a metal layer on the substrate;

8

oxidizing the metal layer integrally to form a first color layer;

forming a positive photoresist layer on the first color layer;

5 exposing selectively to form a complete exposed area, a first exposed area, a second exposed area and unexposed area on the positive photoresist layer, wherein the exposure of the first exposed area is greater than that of the second exposed area;

oxidizing the metal layer integrally;

removing the first exposed area and reoxidizing;

removing the second exposed area and reoxidizing to form a fourth color layer on the first color layer corresponding to the complete exposed area, a third color layer on the first color layer corresponding to the first exposed area and a second color layer on the first color layer corresponding to the second exposed area;

removing the remaining positive photoresist layer.

22. The method as claimed in claim 21, wherein the transparent substrate is glass or polymer.

23. The method as claimed in claim 21, wherein the metal is Cr, Cu, Al, Fe or Ni.

24. The method as claimed in claim 21, wherein the thickness of the metal layer is 60–5000 Å.

25. The method as claimed in claim 21, wherein the positive photoresist layer is novolak resin, diazo compound or combinations thereof.

26. The method as claimed in claim 21, wherein a solution used for developing contains sodium carbonate, sodium hydrogencarbonate, sodium silicate, sodium hydroxide, potassium hydroxide and tetraalkkyl amine compounds and combinations thereof.

27. The method as claimed in claim 21, wherein the oxidizing step is carried out by strong acids.

28. The method as claimed in claim 21, wherein the strong acids are chromic acid, sulfuric acid, nitric acid and combinations thereof.

29. The method as claimed in claim 21, wherein the oxidizing step is carried out by laser or high temperature.

30. The method as claimed in claim 21, wherein the metal layer is formed by physical vapor deposition (PVD) or chemical vapor deposition (CVD).

31. The method as claimed in claim 21, wherein the fourth color layer is black matrix.

\* \* \* \* \*

专利名称(译)	用于液晶显示板的滤色器及其制造方法		
公开(公告)号	<a href="#">US6703173</a>	公开(公告)日	2004-03-09
申请号	US10/098855	申请日	2002-03-13
[标]申请(专利权)人(译)	鲁俊富 SHIEH FANNY 陈钱大		
申请(专利权)人(译)	鲁俊富 SHIEH FANNY 陈展泰		
当前申请(专利权)人(译)	工业技术研究院		
[标]发明人	LU CHUN FU SHIEH FANNY CHEN CHIN TAI		
发明人	LU, CHUN FU SHIEH, FANNY CHEN, CHIN-TAI		
IPC分类号	G02F1/13 G02F1/1335 G02B5/20 G02B5/00 G02F1/133		
CPC分类号	G02B5/201 G02F1/133514 G02F1/133516		
代理机构(译)	商户德律P.C.		
审查员(译)	MCPHERSON, JOHN A.		
优先权	090129105 2001-11-23 TW		
其他公开文献	US20030099887A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

一种用于液晶显示板的滤色器。滤光器包括透明基板，其上形成有金属层，第一颜色层，第二颜色层和第三颜色层与相同的金属层一体形成。本发明还提供了一种制造上述滤色器的方法。该方法应用通过重复曝光和氧化来氧化金属层的理论，以形成具有多种整体形成的颜色的滤色器。根据需要，本发明的滤色器还包括通常包括在液晶显示板中的黑色矩阵。

