



US 20020149733A1

(19) **United States**

(12) **Patent Application Publication**

**Lyu et al.**

(10) **Pub. No.: US 2002/0149733 A1**

(43) **Pub. Date: Oct. 17, 2002**

(54) **LIQUID CRYSTAL DISPLAY DEVICE  
HAVING WIDE VIEWING ANGLE AND  
IMPROVED CONTRAST RATIO**

(76) Inventors: **Jae-Jin Lyu**, Kyungki-do (KR); **Hea-Ri Lee**, Seoul (KR); **Kyeong-Hyeon Kim**, Kyungki-do (KR); **Jian-Min Chen**, Kyungki-do (KR)

Correspondence Address:  
**MYERS BIGEL SIBLEY & SAJOVEC**  
**PO BOX 37428**  
**RALEIGH, NC 27627 (US)**

(21) Appl. No.: **10/114,718**

(22) Filed: **Apr. 1, 2002**

#### Related U.S. Application Data

(62) Division of application No. 09/087,628, filed on May 29, 1998.

#### Foreign Application Priority Data

May 29, 1997 (KR) ..... 97-21709  
Jun. 27, 1997 (KR) ..... 97-28480

#### Publication Classification

(51) **Int. Cl.<sup>7</sup>** ..... **G02F 1/1339**  
(52) **U.S. Cl.** ..... **349/155**

(57)

#### ABSTRACT

A liquid crystal display comprises two parallel spaced substrates and a liquid crystal layer with negative dielectric anisotropy interposed between the substrates. The ratio  $d/p$ , the cell gap  $d$  between the substrates to the pitch  $p$  of the liquid crystal layer, is equal to or less than 0.3, and the retardation value  $\Delta n^*d$  may be in the range of 0.25-0.4. In absence of electric field, the liquid crystal molecules are arranged vertically to the substrates, and when the sufficient electric field is applied, the liquid crystal molecules are parallel to the substrates and twisted by 90° from one substrate to the other.

To the outer surface of a liquid crystal cell having a liquid crystal material with a negative dielectric anisotropy, a combination of a-plate, c-plate or biaxial compensation films is attached. The direction having the largest refractive index of the a-plate or the biaxial film is parallel or perpendicular to the polarizing direction of adjacent polarizer. The difference between the summation of the retardation  $(n_x - n_z)^*d$  of the a-plate, the c-plate and the biaxial films and the polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation due to birefringence of the liquid crystal cell. The retardation  $(n_x - n_z)^*d$  of the a-plate or the biaxial film is 0-100 nm.  $n_x$ ,  $n_y$  and  $n_z$  are the refractive indices of the x, y and z axes respectively when the z axis is perpendicular to the surface of the liquid crystal cell, the x axis is in the surface of the liquid crystal cell and having the largest refractive index of the a-plate or the biaxial film and the y axis is in same plane as the x axis and perpendicular to the x axis, and  $d$  is the thickness of the film.




FIG.1A




FIG.1B




FIG.2







FIG.3




**FIG.4A**



**FIG.4B**



**FIG.4C**



**FIG.6A**






FIG.5



**FIG. 6B**



**FIG. 8A**






FIG.7



**FIG. 8B**



**FIG. 8C**




FIG.9




FIG.10




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 11D




FIG.12A




FIG.12B




FIG. 12C




FIG. 12D




FIG.13




FIG.14




FIG. 15




FIG. 16




FIG.17




FIG.18




FIG.19




FIG.20




FIG.21




FIG.22




FIG.23




FIG.28A




FIG.24




FIG.25




FIG.26




FIG.27




FIG.28B




FIG.28C




FIG.29A




FIG.29B




FIG.29C




FIG.29D




FIG.30





FIG.31



## LIQUID CRYSTAL DISPLAY DEVICE HAVING WIDE VIEWING ANGLE AND IMPROVED CONTRAST RATIO

### BACKGROUND OF THE INVENTION

[0001] (a) Field of the Invention

[0002] The present invention relates to liquid crystal displays using vertical alignment and compensation films.

[0003] (b) Description of the Related Art

[0004] A liquid crystal display has two substrates opposite each other and a liquid crystal layer interposed between the substrates. If the electric field is applied to the liquid crystal layer, the liquid crystal molecules changes their orientations to control the transmittance of the incident light.

[0005] A twisted nematic (TN) liquid crystal display includes a couple of transparent substrates having transparent electrodes thereon, a liquid crystal layer interposed between the substrates, and a couple of polarizers which are attached to the outer surfaces of the substrates. In off state, i.e., in absence of the electric field, the molecular axes of the liquid crystal molecules are aligned parallel to the substrates and twisted spirally by a constant pitch from one substrate to the other substrate, and the director of the liquid crystal layer varies continuously.

[0006] However, the contrast ratio of the conventional TN mode liquid crystal display, especially in normally black mode, may not be so high because the incident light is not fully blocked in absence of the electric field.

[0007] To solve this problem, a vertically aligned twisted nematic (VATN) mode liquid crystal display is proposed in the U.S. Pat. No. 5,477,358, "CHIRAL NEMATIC LIQUID CRYSTAL DISPLAY WITH HOMEOTROPIC ALIGNMENT AND NEGATIVE DIELECTRIC ANISOTROPY", whose patentee is Case Western Reserve University and in "Eurodisplay '93", pp. 158-159 by Takahashi et al.

[0008] On the contrary to the TN mode, the alignment of the liquid crystal molecules of the VATN mode liquid crystal display in off state is similar to that of the TN mode in on state, that is, the liquid crystal molecules align perpendicular to the substrates. In the on state, the molecular axes of the liquid crystal molecules are aligned parallel to the substrates and twisted spirally by a constant pitch from one substrate to the other substrate, and the director of the liquid crystal layer varies continuously.

[0009] In case of VATN mode liquid crystal display in normally black mode, sufficient darkness in off state because the molecular axes of the liquid crystal molecules are aligned vertically to the substrate when the electric field is applied.

[0010] The display characteristics of VATN may become better by optimizing the parameters such as the ratio d/p of the cell gap d to the pitch p of the liquid crystal layer, the difference of refractive indices  $\Delta n$  between in both directions and the retardation value  $\Delta n^*d$ .

[0011] In the mean time, because of the refractive anisotropy of the liquid crystal material, the retardation value  $\Delta n^*d$  changes as the viewing direction, thereby causing the difference of the intensity and the characteristics of light.

Therefore, TN displays have the change in contrast ratio, color shift, gray inversion, etc. according to the viewing angle.

[0012] TN LCDs with compensation film are developed to compensate the difference of retardation in liquid crystal layer. However, the film compensated TN LCDs still have problems such as inharmony of the display characteristics and gray inversion.

### SUMMARY OF THE INVENTION

[0013] It is therefore an object of the present invention to provide optimized cell parameters such as d/p,  $\Delta n$  and  $\Delta n^*d$  to improve the optical characteristics of LCDs.

[0014] It is another object of the present invention to widen the viewing angle of liquid crystal displays.

[0015] It is another object of the present invention to increase the contrast ratio of liquid crystal displays.

[0016] These and other objects, features and advantages are provided, according to the present invention, by a liquid crystal display comprising two parallel spaced substrates and a liquid crystal layer with negative dielectric anisotropy injected between two substrates wherein the ratio d/p, the cell gap d between two substrates to the pitch p of the liquid crystal layer, may be equal to or less than 0.3.

[0017] The liquid crystal layer is made of a chiral nematic liquid crystal or a nematic liquid crystal with 0.01-1.0 wt % of chiral dopant.

[0018] On two substrates, alignment layers are formed to align the liquid crystal molecules vertically to the substrates. The alignment layers may or may not be rubbed.

[0019] The refractive anisotropy  $\Delta n$  may be 0/065-0.123, the cell gap d between two substrates may be 3.0-6.0  $\mu\text{m}$  and the retardation value  $\Delta n^*d$  may be 0.25-0.4.

[0020] When the electric field is not applied, the liquid crystal molecules are arranged vertically to the substrates, and when the sufficient electric field is applied, the liquid crystal molecules are parallel to the substrates and twisted by 90° from one substrate to the other.

[0021] These and other objects, features and advantages are also provided, according to the present invention, by a liquid crystal display comprising a liquid crystal cell having a liquid crystal material with a negative dielectric anisotropy, and a combination of a-plate, c-plate or biaxial compensation films attached to the outer surface of the liquid crystal cell.

[0022] The slow axis which is the direction having the largest refractive index of a-plate or biaxial compensation film may be parallel or perpendicular to the transmission axis of adjacent polarizer.

[0023] The difference between the summation of the retardation  $(n_{xa}-n_{za})*d_B$  of the a-plate compensation film, the retardation  $(n_{xc}-n_{zc})*d_c$  of the c-plate compensation film, the retardation  $(n_{xb}-n_{zb})*d_b$  of the biaxial compensation film and the retardation of the polarizers, and the retardation of the liquid crystal cell may be equal to or less than 15% of the retardation of the liquid crystal cell. The retardation  $(n_x - n_{ya})*d_B$  of the a-plate compensation film or the retardation  $(n_{xb} - n_{yb})*d_b$  of the biaxial compensation film may be 0-100

nm. Here,  $n_x$ ,  $n_y$  and  $n_z$  are the refractive indices of the x, y and z axes respectively when z axis is the direction perpendicular to the surface of the liquid crystal cell, x axis is in the surface of the liquid crystal cell and having the largest refractive index of the a-plate or the biaxial compensation film and y axis is in the surface of the liquid crystal cell and perpendicular to the x axis, and d is the thickness of the liquid crystal cell.

#### BRIEF DESCRIPTION OF THE DRAWINGS

[0024] **FIGS. 1A and 1B** are schematic diagrams of the alignment of liquid crystal molecules of a VATN liquid crystal display respectively in black state and white state according to an embodiment of the present invention.

[0025] **FIG. 2** is a sectional view of a VATN liquid crystal cell according to the present invention.

[0026] **FIG. 3** is a graph showing transmittance T as a function of voltage V applied to the liquid crystal cell for various d/p in the Experiment 1.

[0027] **FIGS. 4A, 4B and 4C** show the viewing angle characteristics for various d/p in the Experiment 1.

[0028] **FIG. 5** is a graph showing transmittance T as a function of voltage V applied to the liquid crystal cell for various d/p in the Experiment 2.

[0029] **FIGS. 6A and 6B** show the viewing angle characteristics for various d/p in the Experiment 2.

[0030] **FIG. 7** is a graph showing transmittance T as a function of voltage V applied to the liquid crystal cell for various d/p in the Experiment 3.

[0031] **FIGS. 8A, 8B and 8C** show the viewing angle characteristics for various d/p in the Experiment 3.

[0032] **FIG. 9** is a graph of the viewing angle in the 45° diagonal direction as a function of the retardation value.

[0033] **FIG. 10** illustrates the relation between the cell gap and the response time.

[0034] **FIGS. 11A-20** show the structures of the liquid crystal display according to the first to the sixteenth embodiments respectively.

[0035] **FIG. 21** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_x - n_y)^*d$  for the LCD according to the tenth embodiment of the present invention shown in **FIG. 14**.

[0036] **FIG. 22** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_{xb} - n_{yb})^*d_b$  for the LCD according to the tenth embodiment of the present invention shown in **FIG. 15**.

[0037] **FIG. 23** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_{xb} - n_{yb})^*d_b$  for the LCD according to the thirteenth embodiment of the present invention shown in **FIG. 17**.

[0038] **FIG. 24** shows the viewing angle characteristics of the VATN LCD according to the eleventh embodiment.

[0039] **FIG. 25** shows the viewing angle characteristics of the VATN LCD according to the thirteenth embodiment.

[0040] **FIG. 26** shows the 3-D luminance of the VATN LCD according to the eleventh embodiment.

[0041] **FIG. 27** shows the 3-D luminance of the VATN LCD according to the thirteenth embodiment.

[0042] **FIGS. 28A-28C** show the 8 gray scale performance of the VATN LCD according to the thirteenth embodiment.

[0043] **FIGS. 29A-29D** show the 8 gray scale performance of the 2-D VATN LCD having the structure of the thirteenth embodiment.

[0044] **FIG. 30** shows the viewing angle characteristics of the 2-D VATN LCD having the structure of the tenth embodiment.

[0045] **FIG. 31** shows the viewing angle characteristics of the VATN LCD having the structure of the eleventh embodiment.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0046] The present invention will now be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the present invention are shown. This invention may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. In the drawings, the thickness of layers and regions are exaggerated for clarity.

[0047] **FIGS. 1A and 1B** are schematic diagrams of the alignment of liquid crystal molecules of a VATN liquid crystal display respectively in black state and white state according to an embodiment of the present invention. **FIG. 2** shows the structure of a VATN liquid crystal display according to an embodiment of the present invention.

[0048] As shown in **FIGS. 1A and 1B**, two transparent insulating substrates **1** and **2** are opposite and spaced apart from each other, and transparent electrodes **12** and **120** made of a transparent conductive material such as ITO (indium tin oxide). Alignment layers **14** and **140** are formed on the inner surfaces of the substrates **1** and **2**. Between two substrates **1** and **2**, a liquid crystal material layer **100** made of a chiral nematic liquid crystal having negative dielectric anisotropy or a nematic liquid crystal material doped with chiral dopant of 0.01-0.3 wt % is interposed. The ratio d/p, the cell gap d between the substrates **1** and **2** divided by the pitch p of the liquid crystal layer **100**, is preferably equal to or less than 0.3, and the retardation value  $\Delta n^*d$  is preferably in the range of 0.25-0.4. On the outer surfaces of two substrates **1** and **2**, a polarizer **13** and an analyzer **130**, which polarize the rays incident on the liquid crystal material layer **100** and the rays out of the liquid crystal material layer **100** respectively, are attached. The polarizing direction of the polarizer **13** attached to the lower substrate **1** is perpendicular to that of the analyzer **130** attached to the upper substrate **2**. Alignment layers **14** and **15** may be rubbed or not.

[0049] **FIG. 1A** shows the off state that the electric field is not applied, where the molecular axes of the liquid crystal

molecules **3** in the liquid crystal layer **100** are aligned perpendicular to the surface of the substrates **1** and **2** by the aligning force of the alignment layers **14** and **15**.

[0050] The polarized light by the polarizer **13** passes through the liquid crystal layer **100** without changing its polarization. Then, the light is blocked by the analyzer **130** to make a black state.

[0051] FIG. 1B shows the on state that the sufficient electric field is applied to the liquid crystal layer by the electrodes **4** and **5**, where the liquid crystal molecules **3** in the liquid crystal layer **100** are twisted spirally by 90° from the lower substrate **1** to the upper substrate **2** and the director of the liquid crystal layer varies continuously. Near the inner surfaces of two substrates **1** and **2**, the aligning force of the alignment layers **14** and **15** is larger than the force due to the applied electric field, and thus the liquid crystal molecules stay vertically aligned.

[0052] The polarized light by the polarizer **13** passes through the liquid crystal layer **100**, and its polarization is rotated by 90° according to the variation of the director of the liquid crystal layer. Accordingly the light passes through the analyzer **130** to make a white state.

[0053] Next, the experiments according to the present invention will be described.

[0054] FIG. 2 is a sectional view of a VATN liquid crystal cell according to the present invention.

[0055] As shown in FIG. 2, a liquid crystal layer **100** is interposed between two parallel substrates **1** and **2** spaced apart from each other. Spacers **200** are mixed with the liquid crystal layer **100** to sustain the gap between the substrates **1** and **2**. On the inner surfaces of the substrates **1** and **2** near the edge of the substrates **1** and **2**, a sealant **300** is formed to prevent the liquid crystal material from flowing out of the cell.

#### [0056] Experiment 1

[0057] In this experiment, JALS204, JALS572 (Japan Synthetic Rubber Co.) or SE-1211 (Nissan Chemical Co.) which are used for homeotropic alignment layers were used as an alignment layer. Plastic spacers having 4.5  $\mu\text{m}$  diameter were included in the sealant **300**, and the diameter of spacers spread on the substrate **1** or **2** to maintain the cell gap was 4.5  $\mu\text{m}$ . Liquid crystal material, which is filled in the gap between the substrates, was a twisted nematic liquid crystal material with negative dielectric anisotropy and doped with a dopant MLC 6247 (Merck Co.). The refractive anisotropy  $\Delta n$  of the liquid crystal was 0.085, the dielectric anisotropy  $\Delta \epsilon_{\text{was}}$  4.5, the elastic constant  $K_{11}$  was 15.4 pN,  $K_{22}$  was 5.8 pN and  $K_{33}$  was 17.4 pN, and the viscosity was 30 mm<sup>2</sup>/s. The cell gap  $d$  varies from 3  $\mu\text{m}$  to 6  $\mu\text{m}$ , and the pitch  $p$  is adjusted by varying the amount of the added dopant.

[0058] FIG. 3 is a graph showing transmittance  $T$  as a function of voltage  $V$  applied to the liquid crystal cell for various  $d/p$ , and FIGS. 4A, 4B and 4C show the viewing angle characteristics for various  $d/p$  in the Experiment 1.

[0059] As shown in FIG. 3, the transmittance  $T$  increases as  $d/p$  decreases. When  $d/p$  is 0.57, the transmittance is less than 10%. However, if  $d/p$  is 0.1 or 0.3, the transmittance has relatively high value more than 18%. The voltage difference between the electrodes is in the range of 0-10 V.

[0060] As a result, the transmittance  $T$  increases as  $d/p$  decreases, and the transmittance is high when the  $d/p$  is less than 0.3.

[0061] When  $d/p$  is 0.5, the viewing angles in up, down, left and right directions are about 40° and those in diagonal directions are less than 90° partly as shown in FIG. 4C. However, as shown in FIGS. 4A and 4B, when  $d/p$  is 0.1 or 0.3, the viewing angles in up, down, left and right directions are larger than 40° and those in diagonal directions are more than 90°.

#### [0062] Experiment 2

[0063] In this experiment, the structure of liquid crystal cell was the same as in the first experiment except the alignment layers. In Experiment 2, an alignment layer **14** was rubbed in the direction of 45° polar angle. As a result of the rubbing, the liquid crystal molecules were tilted by about 1° with respect to the perpendicular direction to the substrate.

[0064] FIG. 5 is a graph showing transmittance  $T$  as a function of voltage  $V$  applied to the liquid crystal cell for various  $d/p$ , and FIGS. 6A and 6B show the viewing angle characteristics for various  $d/p$  in the Experiment 2.

[0065] As shown in FIG. 5, when  $d/p$  is 0.5, the transmittance is less than 10% for the sufficient applied voltage. However, when  $d/p$  is 0.1, the transmittance increases to more than 10% as the voltage increases and when  $d/p$  is 0.3, the transmittance is over 20%. The voltage difference between the electrodes is in the range of 0-5 V.

[0066] FIGS. 6A and 6B show the viewing angle characteristics. When  $d/p$  is 0.5, as shown in FIG. 6B, the viewing angles in up and down directions are more than 90° but those in left and right directions are less than 90°. However, as shown in FIG. 6A, in the case that  $d/p$  is 0.3, all the viewing angles in up, down, left and right directions are over 90°.

#### [0067] Experiment 3

[0068] In this experiment, the structure of the liquid crystal cell was the same as in the first experiment except the alignment layers. In Experiment 3, two alignment layers **14** and **15** were rubbed in the direction of 0° polar angle and 90° polar angle respectively, therefore the rubbing directions of two alignment layers **14** and **15** are perpendicular to each other.

[0069] FIG. 7 is a graph showing transmittance  $T$  as a function of voltage  $V$  applied to the liquid crystal cell for various  $d/p$ , and FIGS. 8A, 8B and 8C show the viewing angle characteristics for various  $d/p$  in the Experiment 3.

[0070] As shown in FIGS. 7 and 8A-8C, the transmittance  $T$  decreases as  $d/p$  increases, and thus the contrast ratio decreases and the viewing angle characteristics become worse.

[0071] As shown in FIG. 7, when  $d/p$  is 0.5, the transmittance is less than 10% for the sufficient applied voltage. However, when  $d/p$  is 0.3, the transmittance increases to more than 25% as the voltage increases, and when  $d/p$  is 0.1, the transmittance is over 35%. The voltage difference between the electrodes is in the range of 0-5 V. As shown in FIGS. 8A and 8C, when  $d/p$  is 0.1 or 0.5, the viewing angles in up, down, left and right directions are larger than 90°.

However, as shown in **FIG. 8B**, when  $d/p$  is 0.3, the viewing angles in up, down, left and right directions are about  $90^\circ$ .

[0072] Experiment 4

[0073] In this experiment, the dependency of the viewing angle characteristics in diagonal directions on the retardation value  $\Delta n_d$  was tested. As in Experiment 3, all the alignment layers **14** and **15** were rubbed.  $\Delta n$  varies in the range of 0.065-0.123 and the cell gap  $d$  varies in the range of 3.0-6.1  $\mu\text{m}$  to vary the retardation value  $\Delta n_d$  in the range of 0.3-0.6.

[0074] **FIG. 9** is a graph of the viewing angle in the  $45^\circ$  diagonal direction as a function of the retardation value.

[0075] As shown in **FIG. 9**, the retardation value  $\Delta n_d$  is preferably equal to or less than 0.4 to get a wide viewing angle over  $140^\circ$ .

[0076] Experiment 5

[0077] In this experiment, the dependency of the response time on the cell gap and  $d/p$  was measured. Two test cells were used having the cell gap of 4.0  $\mu\text{m}$  and 4.5  $\mu\text{m}$  respectively, and  $d/p$  varied in the range of 0.1-0.5 by adjusting the amount of the added dopant. Other conditions were the same as in Experiment 4.

[0078] **FIG. 10** is a graph of the response time as a function of the cell gap and  $d/p$ .

[0079] As shown in **FIG. 10**, the response time is shorter as the cell gap and  $d/p$  is smaller. If the cell gap is narrow, the electric field is stronger than when the cell gap is small, and, therefore, the liquid crystal molecules respond faster. The response time increases as  $d/p$  increases because the viscosity of the liquid crystal material increases as the density of dopant increases.

[0080] Now, film-compensated VATN liquid crystal displays according to the embodiments of the present invention will be described in detail. FIGS. **11A-20** show the structures of VATN liquid crystal displays according to the embodiments.

[0081] A VATN liquid crystal display according to the first embodiment of the present invention is shown in **FIG. 11A**.

[0082] A liquid crystal cell **50** having a liquid crystal material with negative dielectric anisotropy such as that as shown in **FIG. 1A** is prepared. A polarizer **10** is attached on the outer surface of rear side of the liquid crystal cell **50**. On the outer surface of the front side of the liquid crystal cell **50** an a-plate compensation film **20**, a c-plate compensation film **30** and another polarizer **11** are attached in sequence. The buffing direction of an alignment layer (such as **14** in **FIG. 1A**) on the inner surface of the front side of the liquid crystal cell **50** up-right. The solid arrow indicates the buffing direction of the alignment layer the front side of the liquid crystal cell. On the contrary, the buffing direction of an alignment layer (such as **15** in **FIG. 1A**) on the inner surface of the rear side of the liquid crystal cell **50** is down-right. The dotted arrow indicates the buffing direction of the alignment layer on the rear side of the liquid crystal cell. In the first embodiment of the present invention, the liquid crystal cell operates in "e" mode that the polarizing directions of the polarizers **10** and **11** represented by bidirectional arrows are parallel to the buffing directions of the neighboring alignment layers.

[0083] An a-plate compensation film has the refractive indices  $n_x$ ,  $n_y$  and  $n_z$  satisfying the relation  $n_x > n_y = n_z$ , and a c-plate compensation has the refractive indices satisfying the relation  $n_x = n_y > n_z$ , where  $n_x$ ,  $n_y$  and  $n_z$  are respectively the refractive indices in the x-direction, y-direction and z-direction when the z-direction is perpendicular to the surface of the liquid crystal cell **50**, and the x-axis and y-axis spans a plane parallel to the surface of the liquid crystal cell **50**.

[0084] The x-axis of the a-plate compensation film, which has a largest refractive index (slow axis), may match with or be perpendicular to the polarizing direction of its neighboring polarizer. If not, the light leakage may be generated to reduce the contrast ratio. In the case that the liquid crystal display shown in **FIG. 11A**, the x-axis of the a-plate compensation film **20** is in the up-right direction and parallel to the polarizing direction of the polarizer **11**. The solid bidirectional arrow drawn on the a-plate compensation film **20** indicates the direction of the x-axis of the a-plate compensation film **20**.

[0085] According to the second embodiment, as shown in **FIG. 11B**, the positions of a-plate and c-plate compensation films are exchanged. On the rear side of the liquid crystal cell **50**, a polarizer **10** is attached. An a-plate compensation film **20**, a c-plate compensation film **30** and a polarizer **11** is attached on the front side of the liquid crystal cell **50** in sequence. The buffing directions of the alignment layer, the polarizing directions of the polarizer **10** and **11** and the x-axis of the a-plate compensation film **20** are similar to those of the first embodiment.

[0086] Liquid crystal displays according to the third and the fourth embodiments are shown in **FIGS. 11C and 11D** respectively, where the compensation films **20** and **30** are inserted between the rear polarizer **10** and the liquid crystal cell **50**. According to the third embodiment, a c-plate compensation film **30**, an a-plate compensation film **20** and a polarizer **10** are attached in sequence on the rear side of the liquid crystal cell **50** (**FIG. 11C**). In the fourth embodiment, the positions of the c-plate compensation film **30** and the a-plate compensation film **20** are opposite to those in the third embodiment (**FIG. 11D**). The buffing directions of the alignment layers and the polarizing directions of the polarizers **10** and **11** are similar to those of the first embodiment. The x-axis of the a-plate compensation film **20** is matched with the polarizing direction of the rear polarizer **10** neighboring to the a-plate compensation film **20**.

[0087] FIGS. **12A-12D** illustrate liquid crystal displays according to the fifth to the eighth embodiment, and the liquid crystal displays operate in "o" mode. Arrangements of a liquid crystal cell **50**, polarizers **10** and **11**, an a-plate compensation film **20** and a c-plate compensation film **30** are substantially the same as those of the liquid crystal displays shown in **FIGS. 11A-11D**. The difference is that the liquid crystal displays operate in "o" mode, that is, the buffing directions of alignment layers are perpendicular to the polarizing directions of the neighboring polarizers, and that the buffing directions of the alignment layers are perpendicular to x-axis of the a-plate compensation films.

[0088] **FIG. 13** illustrates a liquid crystal display according to the ninth embodiment. The liquid crystal display has another c-plate compensation film **31** inserted between the liquid crystal cell **50** and the rear polarizer **10** in the first embodiment. The liquid crystal display according to the

tenth embodiment, as shown in **FIG. 14**, has another a-plate compensation film **21** inserted between the c-plate compensation film **31** and the rear polarizer **10** in the ninth embodiment, and the x-axis of the a-plate film **21** is parallel to the polarizing direction of the rear polarizer **10**.

**[0089]** A liquid crystal display according to the eleventh embodiment is shown in **FIG. 15**. A rear polarizer **10** is attached to the rear side of a liquid crystal cell **50** having a liquid crystal material with negative dielectric anisotropy. On the opposite side of the liquid crystal cell, a biaxial compensation film **40** is interposed between the liquid crystal cell **50** and a front polarizer **11**. The biaxial compensation film has the refractive indices satisfying the relation that  $n_x > n_y > n_z$ . As in the embodiments described above, the x-axis of the biaxial compensation film may be parallel or perpendicular to the polarizing direction of its neighboring polarizer. It may operate in "e" mode or "o" mode.

**[0090]** According to the twelfth embodiment; a biaxial compensation film **40** is interposed between a rear polarizer **10** and the rear side of a liquid crystal cell **50**, and a front polarizer **11** is attached directly on the front side of the liquid crystal cell **50**, as shown in **FIG. 16**. As in the embodiments described above, the x-axis of the biaxial compensation film may be parallel or perpendicular to the polarizing direction of its neighboring polarizer. It may operate in "e" mode or "o" mode.

**[0091]** As shown in **FIG. 17**, according to the thirteenth embodiment, two biaxial compensation films **40** and **41** are inserted between respective polarizers **10** and **11** and the front and rear side of a liquid crystal cell **50**, respectively. As in the embodiments described above, the x-axis of the biaxial compensation film may be parallel or perpendicular to the polarizing direction of its neighboring polarizer. It may operate in "e" mode or "o" mode.

**[0092]** A liquid crystal display according to the fourteenth embodiment is shown in **FIG. 18**. A rear polarizer **10** is attached to the rear side of a liquid crystal cell **50** having a liquid crystal material with negative dielectric anisotropy. On the opposite side of the liquid crystal cell, a biaxial compensation film **40** and a c-plate compensation film **30** are inserted between the liquid crystal cell **50** and a front polarizer **11**. The x-axis of the biaxial compensation film **40** is parallel to the polarizing direction of its neighboring polarizer **11**. The liquid crystal cell operates in "e" mode that the polarizing directions are parallel to the buffering directions of the neighboring alignment layers in this embodiment. The position of the biaxial compensation film **40** and the c-plate compensation film **30** may be exchanged, and they may be inserted between a rear polarizer **10** and the liquid crystal cell **50**.

**[0093]** Another c-plate compensation film **31** may be added between the rear polarizer **10** and the liquid crystal cell of the fourteenth embodiment, according the fifteenth embodiment as shown in **FIG. 19**. A c-plate compensation film and a biaxial compensation film may be added to the LCD of fourteenth embodiment as in the sixteenth embodiment (**FIG. 20**). The x-axis of the biaxial compensation film may be perpendicular to the polarizing direction of the neighboring polarizer, and the liquid crystal display may operate in "o" mode.

**[0094]** In the meantime, the contrast ratio CR for the VATN LCD is defined as follows:

$$CR = (luminance)_{ON} / (luminance)_{OFF}$$

**[0095]** That is, the contrast ratio in normally black mode is the value that  $(luminance)_{ON}$ , which is the luminance at the state that the voltage is applied (on state), divided by  $(luminance)_{OFF}$ , which is the luminance at the state that the voltage is not applied (off state). The contrast ratio may be drastically improved if somehow the luminance in off state is further reduced.

**[0096]** The viewing angle characteristics and gray scale performance of the film compensated VATN LCD according to the present invention were calculated by optical simulation program. The geometrical structure and relevant parameters used in the simulation are summarized in Table 1. It was assumed that the polarizer itself gives retardation of -60 nm.

TABLE 1

The parameters of VATN cells for optical simulations		
Elastic constant (pN)	$K_1$	16.6
	$K_2$	6.5
	$K_3$	18.5
Relative dielectric constant	$\epsilon_{\parallel}$	3.5
	$\epsilon_{\perp}$	7.7
Refractive index	$\bar{n}_e$	1.5584
	$\bar{n}_o$	1.4757
Pretilt angle	$\theta_D$	89°
Twist angle	$\Phi_{TN}$	90°
Cell gap (μm)	$d$	4.0
Cell gap divided by Pitch	$d/p$	0.1
Off state voltage (V)	$V_{off}$	0
On state voltage (V)	$V_{on}$	5
Buffing direction	front	45° or 225°
	back	315° or 135°

**[0097]** The net retardation value due to all retardation films (including the polarizers),  $(n_x - n_z) * d$ , is preferably equal to that of the liquid crystal cell birefringence. In our case, the liquid crystal cell birefringence was around 320 nm. However, the biaxiality of the compensation films may be optimized in the individual case.

**[0098]** **FIG. 21** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_x - n_y) * d$  for the LCD according to the tenth embodiment of the present invention shown in **FIG. 14**.

**[0099]** Referring to **FIG. 14**, the structure of the VATN LCD according to the tenth embodiment of the present invention is more fully described. A liquid crystal cell **50** has a liquid crystal material with negative dielectric anisotropy. On the front side of the liquid crystal cell **50**, a c-plate compensation film **30** and an a-plate compensation film **20** is attached in sequence and a polarizer **11** is attached thereto. On the rear side of the liquid crystal cell **50**, a c-plate compensation film **31** and an a-plate compensation film **11** is attached in sequence, and a polarizer **11** is also attached thereto. The polarizing directions of the polarizers **10** and **11** are parallel to the buffering direction of their neighboring alignment layers of the liquid crystal cell **50**. That is, the liquid crystal cell operates in "e" mode. The orientation of x-axis (slow axis) of a-plate compensation film **20** and **21** matches with the polarizing direction of its neighboring polarizer.

**[0100]** The optimum retardation value  $(n_{xa}-n_{ya})*d_a$  of the a-plate compensation film is around 20 nm as shown in graph of **FIG. 21** where  $n_{xa}$  and  $n_{ya}$  are respectively the refractive indices along the x-axis and the y-axis of the a-plate compensation films, and  $d_B$  is the thickness of the a-plate compensation film. The maximum contrast ratio is 140:1 in up 60° direction.

**[0101]** **FIG. 22** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_{xb}-n_{yb})*d_b$  for the LCD according to the tenth embodiment of the present invention shown in **FIG. 15** where  $n_{xb}$  and  $n_{yb}$  are respectively the refractive indices along the x-axis and the y-axis of the biaxial compensation films, and  $d_b$  is the thickness of the biaxial compensation film. The optimum retardation value  $(n_{xb}-n_{yb})*d_b$  of the biaxial compensation film is around 50 nm as shown in **FIG. 22**.

**[0102]** If a biaxial compensation film is used as in the eleventh embodiment of the present invention, the contrast ratio may be more improved. As shown in **FIG. 22**, the contrast ratio is over 175:1 in up 60° direction. The contrast ratio in left and right 60° directions are about 250:1 and 175:1, respectively.

**[0103]** **FIG. 23** is a graph showing the contrast ratios in right, up, left and bottom 60° directions as a function of the retardation value  $(n_{xb}-n_{yb})*d_b$  for the LCD according to the thirteenth embodiment of the present invention shown in **FIG. 17**.

**[0104]** Referring to **FIG. 17**, the structure of the VATN LCD according to the thirteenth embodiment of the present invention is described in detail. A liquid crystal cell **50** has a liquid crystal material with negative dielectric anisotropy. Both on the front and rear side of the liquid crystal cell **50**, two biaxial compensation films **40** and **41** and two polarizers **11** and **10** are attached respectively. The liquid crystal cell operates in “e” mode that the polarizing directions of the polarizers **10** and **11** are parallel to the buffering directions of their neighboring alignment layers of the liquid crystal cell **50**. The orientation of x-axis (slow axis) of biaxial compensation film **40** and **41** matches with the polarizing direction of its neighboring polarizer.

**[0105]** The optimum retardation value  $(n_{xb}-n_{yb})*d_b$  of the biaxial compensation film is around 40 nm as shown in **FIG. 23**. The contrast ratio is as good as in the eleventh embodiment of the present invention.

**[0106]** The contrast ratio in up 60° direction is about 200:1, and the contrast ratios in left and right 60° directions are over 250:1.

**[0107]** In the tenth embodiment of the present invention, if the retardation value  $(n_{xc}-n_{zc})*d_c$  of the c-plate compensation films **30** and **31** is 100 nm, the net retardation value of all retardation films (including the polarizers),  $(n_x-n_z)*d$ , is 360 nm because the retardation value of the a-plate compensation film is 20 nm and the retardation value of the polarizer is 60 nm. This value is nearly equal to the liquid crystal cell birefringence.

**[0108]** In the eleventh embodiment of the present invention, if the retardation value  $(n_{xb}-n_{zb})*d_b$  of the biaxial compensation films **40** is 200 nm, the total retardation value

of all retardation films,  $(n_x-n_z)*d$ , is 320 nm. This value is equal to the liquid crystal cell birefringence.

**[0109]** In the thirteenth embodiment of the present invention, if the retardation value  $(n_{xb}-n_{zb})*d_b$  of the biaxial compensation films **40** and **41** is 100 nm, the net retardation value of all retardation,  $(n_x-n_z)*d$ , is 320 nm as in the eleventh embodiment of the present invention.

**[0110]** As shown in the above, if the difference between the net retardation value of all retardation,  $(n_x-n_z)*d$ , and the liquid crystal cell birefringence is relatively small, the viewing characteristics are much improved. The difference is preferably equal to or less than 15% of the liquid crystal cell birefringence.

**[0111]** **FIGS. 24 and 25** show the viewing angle characteristics of the film compensated VATN LCDs according to the eleventh and thirteenth embodiments of the present invention, respectively. The viewing angle characteristics are dramatically improved compared with the cases that the compensation film is not used and that c-plate compensation films are used.

**[0112]** **FIGS. 26 and 27** show the 3-dimensional luminance distributions of the film compensated VATN LCDs according to the eleventh and thirteenth embodiments of the present invention, respectively. A VATN LCD in off state has the intrinsic light leakage in 45° direction relative to the polarizing direction. The c-plate compensation film with optimum value may reduce the light leakage by 10 times. The optimum black states of the VATN LCDs may be achieved by using the biaxial compensation films according to embodiments of the present invention. It results in the extremely high contrast ratio.

**[0113]** The eight gray scale performance of the VATN LCD according to the thirteenth embodiment using the optimum biaxial compensation film is calculated, and the calculated result is shown in **FIGS. 28A-28C**. **FIG. 28A** is the graph of the luminance as a function of the azimuthal angle in the plane making 45° relative to the polarizing directions. **FIG. 28B** is the graph of the luminance as a function of the azimuthal angle in the vertical plane to the polarizing direction, and **FIG. 28C** is the graph of the luminance as a function of the azimuthal angle in the horizontal plane to the polarizing direction. Although the contrast of the display gets improved a lot in these compensation modes, the gray scale performances are not so good enough.

**[0114]** If the compensation configurations according to the embodiments of the present invention are adapted to 2-domain VATN LCD, the gray scale performance gets greatly improved. **FIGS. 29A-29D** show the gray scale performance of 2-D VATN LCD having the compensation configuration according to the thirteenth embodiment of the present invention. **FIG. 29A** is the graph of the luminance as a function of the azimuthal angle in the horizontal plane to the polarizing direction. **FIG. 29B** is the graph of the luminance as a function of the azimuthal angle in the vertical plane to the polarizing direction, and **FIGS. 29C and 29D** are respectively the graph of the luminance as a function of the azimuthal angle in the planes making 45° and 135° relative to the polarizing direction.

**[0115]** **FIGS. 30 and 31** show the gray scale performances of 2-D VATN LCDs having the compensation configurations

according to the tenth and the eleventh embodiments of the present invention, respectively.

**[0116]** All compensation configurations shown in FIGS. 11A-20 can be used for 2-D or multi-domain VATN LCDs as long as the buffing directions match with the x-axis (slow axis) of the biaxial or the a-plate compensation film.

**[0117]** Moreover, the film compensated VATN LCDs according to the present invention may be adapted to ECB (electrically controlled birefringence) VATN LCDs, fringe controlled multi-domain VATN LCDs. IPS (in-plane switching) mode VATN LCDs, etc.

**[0118]** In the drawings and specification, there have been disclosed typical preferred embodiments of the invention and, although specific terms are employed, they are used in a generic and descriptive sense only and not for purposes of limitation, the scope of the invention being set forth in the following claims.

What is claimed is:

1. A liquid crystal display comprising:
  - two spaced apart substrates, each substrate having an electrode; and
  - a liquid crystal layer with negative dielectric anisotropy which is interposed between the two substrates and homeotropically aligned;
  - wherein cell gap between the substrates divided by pitch of the liquid crystal layer is equal to or less than 0.3.
2. The liquid crystal display of claim 1, wherein the liquid crystal layer comprises a chiral nematic liquid crystal material.
3. The liquid crystal display of claim 1, wherein the liquid crystal layer comprises a nematic liquid crystal material including chiral dopant of 0.01-1.0 wt %.
4. The liquid crystal display of claim 1, further comprising two alignment layers which are formed on inner surfaces of the substrates respectively and align the liquid crystal layer homeotropically.
5. The liquid crystal display of claim 4, wherein the alignment layers are not rubbed.
6. The liquid crystal display of claim 4, wherein one of the alignment layers is rubbed.
7. The liquid crystal display of claim 4, wherein both the alignment layers are rubbed.
8. The liquid crystal display of claim 1, wherein the refractive anisotropy of the liquid crystal layer is in the range of 0.065-0.123.
9. The liquid crystal display of claim 8, wherein the cell gap between the substrates is in the range of 3.0-6.0  $\mu\text{m}$ .
10. The liquid crystal display of claim 9, wherein the dielectric anisotropy multiplied by the cell gap is equal to or less than 0.4.
11. The liquid crystal display of claim 1, further comprising two polarizers which are attached to the outer surfaces of the substrates respectively and have polarizing directions perpendicular to each other.
12. A liquid crystal display comprising:
  - a vertically aligned liquid crystal cell having a first and a second surfaces opposite each other and having a liquid crystal material with negative dielectric anisotropy;
  - a first and a second polarizers attached to the first and the second surfaces of the liquid crystal cell respectively; and
  - a first a-plate compensation film and a first c-plate compensation film disposed between the first surface of the liquid crystal cell and the first polarizer,
 wherein a direction having a largest refractive index in the first a-plate compensation film is parallel or perpendicular to the polarizing direction of the first polarizer.
13. The liquid crystal display of claim 12, wherein the difference between the summation of the retardation  $(n_{xa1} - n_{za1}) * d_{a1}$  of the first a-plate compensation film, the retardation  $(n_{xc1} - n_{zc1}) * d_{c1}$  of the first c-plate compensation film and the retardation of the first and the second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,
  - where a z-axis is perpendicular to the first surface of the liquid crystal cell, an x-axis is the same direction as the direction having a largest refractive index in the first a-plate compensation film,  $n_{xa1}$ ,  $n_{za1}$ ,  $n_{xc1}$  and  $n_{zc1}$  are respectively the refractive indices along the x-axis and the z-axis of the first a-plate and of the first c-plate compensation films, and  $d_{a1}$  and  $d_{c1}$  are the thickness of the first a-plate and the first c-plate compensation films respectively.
14. The liquid crystal display of claim 13, wherein the retardation value  $(n_{xa1} - n_{ya1}) * d_{a1}$  of the first a-plate compensation film is in the range of 0-100 nm,
  - where a y-axis is in the first surface of the liquid crystal cell and perpendicular to the x-axis, and  $n_{ya1}$  is the refractive index of the first a-plate compensation film along the y-axis.
15. The liquid crystal display of claim 14, wherein the liquid crystal cell comprises:
  - a pair of transparent substrates;
  - homeotropic alignment layers which are formed on the substrates and divided into two regions whose buffing directions are different; and
  - a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.
16. The liquid crystal display of claim 15, wherein the buffing direction of the alignment layer adjacent to the first a-plate compensation film matches with the direction having the largest refractive index of the first a-plate compensation film.
17. The liquid crystal display of claim 12, further comprising a second c-plate compensation film attached to the second surface of the liquid crystal cell.
18. The liquid crystal display of claim 17, wherein the difference between the summation of the retardation  $(n_{xa1} - n_{za1}) * d_{a1}$  of the first a-plate compensation film, the retardation  $(n_{xc1} - n_{zc1}) * d_{c1}$  of the first c-plate compensation film, the retardation  $(n_{xc2} - n_{zc2}) * d_{c2}$  of the second c-plate compensation film and the retardation of the first and the second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the direction having a largest refractive index in the first a-plate compensation film,  $n_{xa1}$ ,  $n_{za1}$ ,  $n_{xc1}$ ,  $n_{zc1}$ ,  $n_{xc2}$  and  $n_{zc2}$  are respectively the refractive indices along the x-axis and the z-axis of the first a-plate, the first c-plate and the second c-plate compensation film, and  $d_{a1}$ ,  $d_{c1}$  and  $d_{c1}$  are the thickness of the first a-plate, the first c-plate and the second c-plate compensation films respectively.

**19.** The liquid crystal display of claim 18, wherein the retardation value  $(n_{xa1}-n_{ya1})^*d_{a1}$  of the first a-plate compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane and perpendicular to the x-axis,  $n_{ya1}$  is the refractive index of the first a-plate compensation film along the y-axis.

**20.** The liquid crystal display of claim 19, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers which are formed on the substrates and divided into two regions whose buffering directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**21.** The liquid crystal display of claim 20, wherein the buffering direction of the alignment layer adjacent to the first a-plate compensation film matches with the direction having the largest refractive index of the first a-plate compensation film.

**22.** The liquid crystal display of claim 17, further comprising a second c-plate compensation film attached to the second c-plate compensation film.

**23.** The liquid crystal display of claim 22, wherein the direction having a largest refractive index in the second a-plate compensation film is parallel or perpendicular to the polarizing direction of the second polarizer.

**24.** The liquid crystal display of claim 23, wherein the difference between the summation of the retardation  $(n_{xa1}-n_{za1})^*d_{a1}$  of the first a-plate compensation film, the retardation  $(n_{xa2}-n_{za2})^*d_{a2}$  of the second a-plate compensation film, the retardation  $(n_{xc1}-n_{zc1})^*d_{c1}$  of the first c-plate compensation film, the retardation  $(n_{xc2}-n_{zc2})^*d_{c2}$  of the second c-plate compensation film and the retardation of the first and second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the direction having a largest refractive index in the first or the second a-plate compensation film,  $n_{xa1}$ ,  $n_{za1}$ ,  $n_{xa2}$ ,  $n_{za2}$ ,  $n_{xc1}$ ,  $n_{zc1}$ ,  $n_{xc2}$  and  $n_{zc2}$  are respectively the refractive indices along the x-axis and the z-axis of the first a-plate, the second a-plate, the first c-plate and the second c-plate compensation film, and  $d_{a1}$ ,  $d_{a2}$ ,  $d_{c1}$  and  $d_{c1}$  are the thickness of the first a-plate, the second a-plate, the first c-plate and the second c-plate compensation films respectively.

**25.** The liquid crystal display of claim 24, wherein the summation of the retardation value  $(n_{xa1}-n_{ya1})^*d_{a1}$  of the first a-plate compensation film and the retardation value  $(n_{xa2}-n_{ya2})^*d_{a2}$  of the second a-plate compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane and perpendicular to the x-axis,  $n_{ya1}$  and  $n_{ya2}$  are the refractive indices of the first and the second a-plate compensation film along the y-axis.

**26.** The liquid crystal display of claim 25, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers which are formed on the substrates and divided into two regions whose buffering directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**27.** The liquid crystal display of claim 26, wherein the buffering directions of the alignment layers adjacent to the first and the second a-plate compensation films match with the directions having the largest refractive index of the first and the second a-plate compensation films.

**28.** A liquid crystal display comprising:

a vertically aligned liquid crystal cell having a first surface and a second surface opposite each other and having a liquid crystal material with negative dielectric anisotropy;

a first and a second polarizers attached to the first and the second surfaces of the liquid crystal cell respectively; and

a first biaxial compensation film and a first c-plate compensation film disposed between the first surface of the liquid crystal cell and the first polarizer,

wherein a direction having a largest refractive index in the first biaxial compensation film is parallel or perpendicular to the polarizing direction of the first polarizer.

**29.** The liquid crystal display of claim 28, wherein the difference between the summation of the retardation  $(n_{xb1}-n_{zb1})^*d_{b1}$  of the first biaxial compensation film, the retardation  $(n_{xc1}-n_{zc1})^*d_{c1}$  of the first c-plate compensation film and the retardation of the first and the second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the same direction as the direction having a largest refractive index in the first biaxial compensation film,  $n_{xb1}$ ,  $n_{zb1}$ ,  $n_{xc1}$  and  $n_{zc1}$  are respectively the refractive indices along the x-axis and the z-axis of the first biaxial and the first c-plate compensation film, and  $d_{b1}$  and  $d_{c1}$  are the thickness of the first biaxial and the first c-plate compensation films respectively.

**30.** The liquid crystal display of claim 29, wherein the retardation value  $(n_{xb1}-n_{yb1})^*d_{b1}$  of the first biaxial compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane and perpendicular to the x-axis,  $n_{yb1}$  is the refractive index of the first biaxial compensation film along the y-axis.

**31.** The liquid crystal display of claim 30, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers which are formed on the substrates and divided into two regions whose buffing directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**32.** The liquid crystal display of claim 31, wherein the buffing direction of the alignment layer adjacent to the first biaxial compensation film matches with the direction having the largest refractive index of the first biaxial compensation film.

**33.** The liquid crystal display of claim 28, further comprising a second c-plate compensation film attached to the second surface of the liquid crystal cell.

**34.** The liquid crystal display of claim 33, wherein the difference between the summation of the retardation  $(n_{xb1} - n_{zb1}) * d_{b1}$  of the first biaxial compensation film, the retardation  $(n_{xc1} - n_{zc1}) * d_{c1}$  of the first c-plate compensation film, the retardation  $(n_{xc2} - n_{zc2}) * d_{c2}$  of the second c-plate compensation film and the retardation of the first and the second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the direction having a largest refractive index in the first biaxial compensation film,  $n_{xb1}$ ,  $n_{zb1}$ ,  $n_{xc1}$ ,  $n_{zc1}$ ,  $n_{xc2}$  and  $n_{zc2}$  are respectively the refractive indices along the x-axis and the z-axis of the first biaxial, the first c-plate and the second c-plate compensation film, and  $d_{b1}$ ,  $d_{c1}$  and  $d_{c2}$  are the thickness of the first biaxial, the first c-plate and the second c-plate compensation films respectively.

**35.** The liquid crystal display of claim 34, wherein the retardation value  $(n_{xb1} - n_{yb1}) * d_{b1}$  of the first biaxial compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane and perpendicular to the x-axis,  $n_{yb1}$  is the refractive index of the first biaxial compensation film along the y-axis.

**36.** The liquid crystal display of claim 35, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers formed on the substrates and divided into two regions whose buffing directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**37.** The liquid crystal display of claim 36, wherein the buffing direction of the alignment layer adjacent to the first biaxial compensation film matches with the direction having the largest refractive index of the first biaxial compensation film.

**38.** The liquid crystal display of claim 28, further comprising a second biaxial compensation film attached to the second c-plate compensation film.

**39.** The liquid crystal display of claim 38, wherein the direction having a largest refractive index in the second

biaxial compensation film is parallel or perpendicular to the polarizing direction of the second polarizer.

**40.** The liquid crystal display of claim 39, wherein the difference between the summation of the retardation  $(n_{xb1} - n_{zb1}) * d_{b1}$  of the first biaxial compensation film, the retardation  $(n_{xb2} - n_{zb2}) * d_{b2}$  of the second biaxial compensation film, the retardation  $(n_{xc1} - n_{zc1}) * d_{c1}$  of the first c-plate compensation film, the retardation  $(n_{xc2} - n_{zc2}) * d_{c2}$  of the second c-plate compensation film and the retardation of the first and the second polarizers, and the retardation due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the direction having a largest refractive index in the first or the second biaxial compensation film,  $n_{xb1}$ ,  $n_{zb1}$ ,  $n_{xb2}$ ,  $n_{zb2}$ ,  $n_{xc1}$ ,  $n_{zc1}$ ,  $n_{xc2}$  and  $n_{zc2}$  are respectively the refractive indices along the x-axis and the z-axis of the first biaxial, the second biaxial, the first c-plate and the second c-plate compensation film, and  $d_{b1}$ ,  $d_{b2}$ ,  $d_{c1}$  and  $d_{c2}$  are the thickness of the first biaxial, the second biaxial, the first c-plate and the second plate compensation films respectively.

**41.** The liquid crystal display of claim 40, wherein the summation of the retardation value  $(n_{xb1} - n_{yb1}) * d_{b1}$  of the first biaxial compensation film and the retardation value  $(n_{xb2} - n_{yb2}) * d_{b2}$  of the second biaxial compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane and perpendicular to the x-axis,  $n_{yb1}$ ,  $n_{yb2}$  are the refractive indices of the first biaxial and the second biaxial compensation films along the y-axis.

**42.** The liquid crystal display of claim 41, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers formed on the substrates and divided into two regions whose buffing directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**43.** The liquid crystal display of claim 42, wherein the buffing directions of the alignment layers adjacent to the first and the second biaxial compensation films match with the directions having the largest refractive index of the first and the second biaxial compensation films.

**44.** A liquid crystal display comprising:

a vertically aligned liquid crystal cell having a first and a second surfaces opposite each other and having a liquid crystal material with negative dielectric anisotropy;

a first and a second polarizers attached to the first and the second surfaces of the liquid crystal cell respectively;

a first biaxial compensation film disposed between the first surface of the liquid crystal cell and the first polarizer; and

wherein a direction having a largest refractive index in the first biaxial compensation film is parallel or perpendicular to the polarizing direction axis of the first polarizer.

**45.** The liquid crystal display of claim 44, wherein the difference between the summation of the retardation value of the first biaxial compensation film,  $(n_{xb1}-n_{zb1})*d_{b1}$  and the first and the second polarizers, and the retardation value due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the same direction as the direction having a largest refractive index in the first biaxial compensation film,  $n_{xb1}$  and  $n_{zb1}$  are respectively the refractive indices along the x-axis and the z-axis of the first biaxial compensation film, and  $d_{b1}$  is the thickness of the first biaxial compensation film.

**46.** The liquid crystal display of claim 45, wherein the retardation value  $(n_{xb1}-n_{yb1})*d_{b1}$  of the first biaxial compensation film is in the range of 0-100 nm,

where a y-axis is in the first plane of the liquid crystal cell and perpendicular to the x-axis,  $n_{yb1}$  is the refractive index of the first biaxial compensation film along the y-axis.

**47.** The liquid crystal display of claim 46, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers which are formed on the substrates and divided into two regions whose buffing directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**48.** The liquid crystal display of claim 47, wherein the buffing direction of the alignment layer adjacent to the first biaxial compensation film matches with the direction having the largest refractive index of the first biaxial compensation film.

**49.** The liquid crystal display of claim 44, further comprising a second biaxial compensation film attached to the second surface of the liquid crystal cell.

**50.** The liquid crystal display of claim 49, wherein the direction having a largest refractive index in the second biaxial compensation film is parallel or perpendicular to the polarizing direction of the second polarizer.

**51.** The liquid crystal display of claim 50, wherein the difference between the summation of the retardation value of the first biaxial compensation film,  $(n_{xb1}-n_{zb1})*d_{b1}$ , the retardation value of the second biaxial compensation film,  $(n_{xb2}-n_{zb2})*d_{b2}$  and the first and the second polarizers, and the retardation value due to birefringence of the liquid crystal cell is equal to or less than 15% of the retardation value due to birefringence of the liquid crystal cell,

where a z-axis is perpendicular to the first plane of the liquid crystal cell, a x-axis is the direction having a largest refractive index in the first biaxial or the second biaxial compensation film,  $n_{xb1}$ ,  $n_{zb1}$ ,  $n_{xb2}$  and  $n_{zb2}$  are respectively the refractive indices along the x-axis and the z-axis of the first and the second biaxial compensation films, and  $d_{b1}$  and  $d_2$  are the thickness of the first and the second biaxial compensation films respectively.

**52.** The liquid crystal display of claim 51, wherein the summation of the retardation value  $(n_{xb1}-n_{yb1})*d_{b1}$  of the first biaxial compensation film and the retardation value  $(n_{xb2}-n_{yb2})*d_{b2}$  of the second biaxial compensation film is in the range of 0-100 nm ,

where a y-axis is in the first plane of the liquid crystal cell and perpendicular to the x-axis,  $n_{yb1}$  and  $n_{yb2}$  are the refractive indices of the first and the second biaxial compensation films along the y-axis.

**53.** The liquid crystal display of claim 52, wherein the liquid crystal cell comprises:

a pair of transparent substrates;

homeotropic alignment layers formed on the substrates and divided into two regions whose buffing directions are different; and

a liquid crystal material with negative dielectric anisotropy interposed between the alignment layers.

**54.** The liquid crystal display of claim 53, wherein the buffing directions of the alignment layers adjacent to the first and the second biaxial compensation films match with the directions having the largest refractive index of the first and the second biaxial compensation films.

\* \* \* \* \*

专利名称(译)	液晶显示装置具有宽视角和改善的对比度		
公开(公告)号	<a href="#">US20020149733A1</a>	公开(公告)日	2002-10-17
申请号	US10/114718	申请日	2002-04-01
[标]申请(专利权)人(译)	LYU JAE金 LEE HEA RI KIM KYEONG铉 陈健MIN		
申请(专利权)人(译)	LYU JAE-JIN 李HEA-RI KIM KYEONG铉 陈建民		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LYU JAE JIN LEE HEA RI KIM KYEONG HYEON CHEN JIAN MIN		
发明人	LYU, JAE-JIN LEE, HEA-RI KIM, KYEONG-HYEON CHEN, JIAN-MIN		
IPC分类号	G02F1/13 G02F1/1335 G02F1/13363 G02F1/139 G02F1/1339		
CPC分类号	G02F1/133634 G02F1/1393 G02F1/1337 G02F2001/13712 G02F2001/133742 G02F1/13363 G02F1/1396		
优先权	1019970021709 1997-05-29 KR 1019970028480 1997-06-27 KR		
其他公开文献	US6646701		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

## 摘要(译)

液晶显示器包括两个平行间隔的基板和介于基板之间的具有负介电各向异性的液晶层。d / p, 基板之间的单元间隙d与液晶层的间距p的比率d / p等于或小于0.3, 并且延迟值 $\Delta D^* d$ 可以在0.25-0.4的范围内。在没有电场的情况下, 液晶分子垂直于基板排列, 并且当施加足够的电场时, 液晶分子平行于基板并从一个基板扭转90°到另一个基板。在具有负介电各向异性的液晶材料的液晶单元的外表面上, 附着a-板, c-板或双轴补偿膜的组合。具有最大折射率的方向a板或双轴膜与相邻偏振器的偏振方向平行或垂直。a-板, c-板和双轴膜与偏振器的延迟 $(nx-nz)^* d$ 的总和与液晶单元的双折射引起的延迟之差等于或小于由于液晶单元的双折射导致的延迟的15%。a-板或双轴膜的延迟 $(nx-nz)^* d$ 为0-100nm。当z轴垂直于液晶单元的表面时, nx, ny和nz分别是x, y和z轴的折射率, x轴在液晶单元的表面中并且具有最大的折射率a板或双轴膜的折射率与y轴在与x轴相同的平面上并垂直于x轴, d是厚度电影。

