



US008893618B2

(12) **United States Patent**
Yoo et al.

(10) **Patent No.:** **US 8,893,618 B2**
(45) **Date of Patent:** **Nov. 25, 2014**

(54) **PATTERNING METHOD AND METHOD FOR
MANUFACTURING LIQUID CRYSTAL
DISPLAY DEVICE USING THE SAME**

(75) Inventors: **Hong Suk Yoo**, Gunpo-si (KR); **Chul
Ho Kim**, Incheon-si (KR); **Jung Jae
Lee**, Gwacheon-si (KR); **Tae Young Oh**,
Anyang-si (KR); **Choon Ho Park**,
Anyang-si (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 676 days.

(21) Appl. No.: **11/477,439**

(22) Filed: **Jun. 30, 2006**

(65) **Prior Publication Data**

US 2007/0157841 A1 Jul. 12, 2007

(30) **Foreign Application Priority Data**

Dec. 29, 2005 (KR) 10-2005-0134118

(51) **Int. Cl.**

B41F 9/01 (2006.01)
H05K 3/12 (2006.01)
G02B 5/20 (2006.01)
G02B 5/22 (2006.01)
G02F 1/1335 (2006.01)
H05K 3/20 (2006.01)

(52) **U.S. Cl.**

CPC **H05K 3/1275** (2013.01); **G02B 5/201**
(2013.01); **G02B 5/223** (2013.01); **G02F**
1/133516 (2013.01); **H05K 3/207** (2013.01);
G02F 1/133512 (2013.01); **H05K 3/125**
(2013.01); **H05K 2203/0113** (2013.01); **H05K**
2203/013 (2013.01); **H05K 2203/0143**
(2013.01); **H05K 2203/0534** (2013.01); **H05K**
2203/1173 (2013.01)

USPC **101/492**; 101/170; 347/103

(58) **Field of Classification Search**

CPC **G02F 1/133516**; **H05K 3/125**; **H05K**
3/1275; **H05K 2203/013**; **H05K 2203/0534**

USPC 101/327, 368, 463.1, 170, 491, 492;
349/187

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,635,006	A *	6/1997	Watanabe et al.	156/240
6,234,608	B1 *	5/2001	Genovese et al.	347/54
6,358,602	B1 *	3/2002	Horiuchi et al.	428/323
6,690,448	B2 *	2/2004	Kawase et al.	349/187
7,015,503	B2 *	3/2006	Seki et al.	257/40
2003/0047535	A1 *	3/2003	Schueller et al.	216/41
2003/0124865	A1	7/2003	Baek et al.	

(Continued)

FOREIGN PATENT DOCUMENTS

CN	1258428	A	6/2000
CN	1508598	A	6/2004

(Continued)

Primary Examiner — Jill Culler


Assistant Examiner — Justin Olamit

(74) *Attorney, Agent, or Firm* — McKenna Long & Aldridge
LLP

(57) **ABSTRACT**

A patterning method and a method for manufacturing an LCD device using the same are disclosed. The patterning method includes preparing a printing plate having concave and convex portions; coating a pattern material in the concave portion of the printing plate; rolling a printing roller on the printing plate to print the pattern material of the concave portion on the printing roller; and rolling the printing roller on a substrate to print the pattern material of the printing roller on the substrate.

6 Claims, 6 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2004/0119935 A1 6/2004 Baek et al.
 2004/0126678 A1 7/2004 Bael et al.
 2004/0127135 A1* 7/2004 Baek et al. 445/24
 2004/0201048 A1* 10/2004 Seki et al. 257/294
 2005/0042320 A1 2/2005 Hasei
 2006/0054086 A1* 3/2006 Takamura 118/708
 2006/0068319 A1* 3/2006 Andriessen et al. 430/270.1
 2006/0090660 A1* 5/2006 Oh 101/375

FOREIGN PATENT DOCUMENTS

CN 1573493 A 2/2005
 CN 1693955 A 9/2005

JP 6-186416 A 7/1994
 JP 06-302598 10/1994
 JP 10-095178 4/1996
 JP 2000-335073 A 12/2000
 JP 2001-286813 A 10/2001
 JP 2002-189121 A 7/2002
 JP 2003-195024 7/2003
 JP 2004-029831 A 1/2004
 JP 2004-212814 A 7/2004
 JP 2004-212925 A 7/2004
 JP 2005-043678 2/2005
 JP 2005-115000 4/2005
 KR 10-2001-0012686 A 2/2001
 KR 10-2004-0059101 A 7/2004
 WO WO 2007/120877 A2 10/2007

* cited by examiner

FIG. 1A
Related Art




FIG. 1B
Related Art




FIG. 1C
Related Art




FIG. 2A
Related Art




FIG. 2B
Related Art




FIG. 2C
Related Art




FIG. 2D
Related Art




FIG. 3A



FIG. 3B



FIG. 3C




FIG. 3D




FIG. 4A




FIG. 4B



FIG. 4C




FIG. 4D




FIG. 5A




FIG. 5B




FIG. 5C



FIG. 5D






FIG. 6A**FIG. 6B**

PATTERNING METHOD AND METHOD FOR MANUFACTURING LIQUID CRYSTAL DISPLAY DEVICE USING THE SAME

This application claims the benefit of Korean Patent Application No. P2005-134118, filed on Dec. 29, 2005, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to liquid crystal display (LCD) devices, and more particularly, to a patterning method for an LCD device.

2. Discussion of the Related Art

Among various ultra-thin flat type display devices, which include a display screen having a thickness of no more than several centimeters, liquid crystal display (LCD) devices are widely used for notebook computers, monitors, aircraft, etc. because they have advantages such as low power consumption and portability.

An LCD device includes lower and upper substrates facing each other at a predetermined interval therebetween, and a liquid crystal layer formed between the lower and upper substrates.

The lower substrate includes a gate line, a data line, and a thin film transistor. The gate line is formed perpendicular to the data line to define a unit pixel region. The thin film transistor is formed adjacent to a crossing of the gate and data lines and serves as a switching device. A pixel electrode is connected to the thin film transistor.

The upper substrate includes a black matrix layer for shielding the gate line, the data line and the thin film transistor from light, a color filter layer formed on the black matrix layer, and a common electrode formed on the color filter layer.

The above-described LCD device includes various elements formed by repeated steps. Photolithography may be used to form the elements in various shapes.

A patterning method using a photolithographic process of the related art will be described with reference to FIGS. 1A to 1C.

FIGS. 1A to 1C are cross sectional views illustrating a patterning method using a photolithography of the related art.

As shown in FIG. 1A, a pattern material layer **20** is formed on a substrate **10**, and a layer of photoresist **21** is formed on the pattern material layer **20**.

As shown in FIG. 1B, a mask **30** with a predetermined pattern is positioned above the photoresist layer **21**, and then light is provided to the substrate **10** by an exposure apparatus.

As shown in FIG. 1C, the photoresist layer **21** is patterned using a development process. The pattern material layer **20** is etched using the patterned photoresist layer **21** as a mask, to obtain a desired pattern **20a**.

The above photolithographic process uses a photoresist layer and a mask with the predetermined pattern that increases the manufacturing cost for an LCD device. In addition, photolithography requires exposure and development, which are complicated processes that increase the manufacturing time of LCD devices.

To overcome these problems associated with photolithography, new patterning methods has been developed using a printing method using a printing roller.

A patterning method using a printing roller according to the related art will be described with reference to the FIGS. 2A to 2D.

FIGS. 2A to 2D are cross sectional views illustrating a process for forming a pattern material layer on a substrate with a printing roller according to the related art.

As shown in FIG. 2A, a pattern material **20** is coated onto a printing plate **40** having recesses and lands.

As shown in FIG. 2B, a blade **35** is used to remove pattern material **20b** from the surface of the printing plate **40**, leaving pattern material **20a** in the recesses of the printing plate **40**.

As shown in FIG. 2C, a printing roller **50** is rolled across the printing plate **40**. The pattern material **20a** remaining in the recesses is printed onto the printing roller **50**, forming a predetermined pattern on the printing roller **50**.

Referring to FIG. 2D, by rolling the printing roller **50** having the pattern material **20a** coated thereonto on a substrate **10**, the pattern material **20a** of the printing roller **50** is printed onto the substrate **10**.

The patterning method using the printing roller and the printing plate does not require a mask having a predetermined pattern, and does not require exposure or development processes, thereby decreasing the manufacturing cost and time.

However, the patterning method using the printing roller according to the related art has the following disadvantages.

In the patterning method using the printing roller and the printing plate according to the related art, as shown in FIG. 2B, the pattern material **20** is coated onto the printing plate **40**, and the pattern material **20b** is removed from the surface of the printing plate using a blade **35** to leave the pattern material only in the recesses of the printing plate **40**. The removal of pattern material **20b** from the surface of the printing plate may be incomplete, leaving residue in the portions of the printing plate other than the recesses. The pattern material left in the recesses may be non-uniform. Further, applying the pattern material **20b** to the printing plate and then removing portions of the pattern material from the printing plate increases manufacturing cost due to the waste of pattern material.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to a patterning method and a method for manufacturing a liquid crystal display (LCD) device using the same that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

An advantage of the present invention is to provide a patterning method and a method for manufacturing an LCD device using the same, to improve the preciseness of printing, and to reduce cost and waste of material.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, a patterning method includes: preparing a printing plate having recesses and lands; dropping a pattern material in the recesses of the printing plate; rolling a printing roller on the printing plate to print the pattern material in the recesses onto the printing roller; and rolling the printing roller on a substrate to print the pattern material on the printing roller onto the substrate.

In another aspect of the present invention, a method for manufacturing an LCD device includes: preparing first and second printing plates having concave and convex portions; coating a black matrix material in the concave portion of the

first printing plate; rolling a first printing roller on the first printing plate to print the black matrix material on the first printing roller; forming a black matrix layer on a substrate by rolling the first printing roller on the substrate to print the black matrix material on the substrate; coating a color filter material in the concave portion of the second printing plate; rolling a second printing roller on the second printing plate to print the color filter material of the concave portion on the second printing roller; and forming a color filter layer on the substrate including the black matrix layer by rolling the second printing roller on the substrate including the black matrix layer to print the color filter material on the substrate including black matrix layer.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention. In the drawings:

FIGS. 1A, 1B, and 1C are cross sectional views illustrating a patterning method using a photolithography of the related art;

FIGS. 2A, 2B, 2C, and 2D are cross sectional views illustrating a patterning method using a printing roller according to the related art;

FIGS. 3A, 3B, 3C, and 3D are cross sectional views illustrating a patterning method according to the first embodiment of the present invention;

FIGS. 4A, 4B, 4C, and 4D are cross sectional views illustrating a patterning method according to the second embodiment of the present invention; and

FIGS. 5A, 5B, 5C, and 5D are cross sectional views illustrating a method for manufacturing an LCD device according to the present invention; and FIGS. 6A and 6B are cross sectional view illustrating another method for manufacturing an LCD device according to the present invention.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

Reference will now be made in detail to embodiments of the present invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

Hereinafter, a patterning method and a method for manufacturing an LCD device according to the present invention will be described with reference to the FIGS. 3A to 3D.

FIGS. 3A to 3D are cross sectional views illustrating a patterning method according to a first embodiment of the present invention.

In the patterning method according to the first embodiment of the present invention, a predetermined material layer is formed on a predetermined portion of a substrate excluding a pattern area, and a hydrophobic material is coated on a surface of the predetermined material layer. A pattern material layer is formed on the substrate excluding the predetermined material layer using an ink-jet method, whereby the pattern mate-

rial layer is printed on a printing roller. For example, the predetermined material layer may be formed of a black matrix layer.

As shown in FIG. 3A, the black matrix layer **230** is formed on a hydrophilic substrate **100** excluding the pattern area. The black matrix layer **230** may be formed using photolithography.

As shown in FIG. 3B, a hydrophobic treatment is applied to the surface of the black matrix layer **230**, to thereby form a hydrophobic layer **260** to form a printing plate having the black matrix layer **230** and the hydrophobic layer **260** is prepared.

The pattern material layer is a hydrophilic material. That is, if the hydrophobic layer **260** were not formed on the surface of the black matrix layer **230**, the pattern material layer would permeate into the black matrix layer **230**, and the printed pattern material would not be precisely formed for printing the pattern material on the printing roller. Forming the hydrophobic layer **260** on the surface of the black matrix layer **230** prevents the permeation of the pattern material layer into the black matrix layer.

As shown in FIG. 3C, a pattern material is dropped onto the substrate **100** corresponding to the pattern area, that is, the portion of the substrate having no black matrix layer **230**, using a precision nozzle **600**.

After dropping an appropriate amount of the pattern material as shown in FIG. 3D, the pattern material is printed on the printing roller by rolling the printing roller on the printing plate. The pattern material is then printed onto a substrate for an LCD device by rolling the printing roller on an LCD substrate.

By forming the pattern using an ink-jet method employing a precision nozzle, it is possible to decrease the consumption of pattern material.

In the above description of the embodiment illustrated in FIGS. 3A to 3D, the predetermined material layer **230** is described as being a hydrophilic, black matrix pattern material, while the pattern material is described as also hydrophilic. However, the predetermined material and the pattern material may have other combinations of hydrophobic and hydrophilic properties. When the predetermined material layer **230** and the pattern material have opposite properties, for example, when the predetermined material layer is hydrophobic while the pattern material is hydrophilic is hydrophilic, the hydrophobic layer **260** may be omitted. However, when the pattern material and the predetermined material layer have the same property, that is when both are either hydrophobic or hydrophilic, the layer **260** is chosen to have the opposite property from the pattern material and the predetermined material. For example, when the pattern material and the predetermined material **230** are both hydrophobic, the hydrophobic layer **260** described above is replaced with a hydrophilic layer.

Alternatively, a recess may be formed in a glass substrate without forming a black-matrix layer, and a pattern material may be dropped in the recess of the glass substrate to form a desired pattern. This method will be explained in detail with reference to FIGS. 4A to 4D.

FIGS. 4A to 4D are cross sectional views of illustrating a patterning method according to a second embodiment of the present invention.

As shown in FIG. 4A, a printing plate **400** having recesses **430** and lands **460** is prepared. The printing plate **400** may be formed from a glass, organic or inorganic material.

The bottom of a recess **430** formed in the printing plate **400** may be hydrophilic. By forming printing plate **400** of material having a strong hydrophilic property, performing an addi-

tional hydrophilic treatment to the bottom of the recess **430** of the printing plate **400** may be avoided. However, if the printing plate **400** is formed of a hydroxyl-based or carbonyl-based organic material, a hydrophilic treatment using oxygen plasma may be applied to the bottom of a recess **430** of the printing plate **400**.

When the bottom of the recesses **430** of the printing plate **400** have a strong hydrophilic property, the pattern material effectively spreads over the bottom of the recesses **430**.

The printing plate **400** has lands **460** to which a hydrophobic treatment may be applied. Alternatively, the printing plate **400** may be formed of a material having a strong hydrophilic property. When the lands **460** of the printing plate **400** have a strong hydrophobic property, coating of the pattern material onto the upper surface of the lands **460** may be prevented.

The hydrophobic treatment may include treating the lands **460** of the printing plate **400** with fluoric carbon CF_4 plasma.

The pattern material is dropped into a recess of the printing plate using at least one precision nozzle **600**. When using one precision nozzle **600**, the precision nozzle **600** is moved to each recess **430**. When using a plurality of precision nozzles, it is possible to decrease the process time by reducing or eliminating motion of the precision nozzles **600**.

The pattern material is dropped only in the recesses **430** and coats only the recesses of the printing plate **400**. Accordingly, a residue may be avoided reducing material costs and manufacturing costs.

The printing plate **400** can be reused reducing the processes used for forming a complicated pattern.

After dropping the appropriate amount of pattern material **200a** in a recess **430** using the precision nozzle **600** as shown in FIG. **4B**, a printing roller **500** is rolled on the printing plate **400**, as shown in FIG. **4C**. The pattern material **200a** from the recess **430** of the printing plate **400** is printed on the surface of the printing roller **500**, whereby the pattern material **200a** having the predetermined pattern is formed on the printing roller **500**.

A blanket **550** of Si-based resin is formed on the surface of the printing roller **500**. The blanket **550** of Si-based resin has elasticity to decrease friction between the printing roller **500** and the printing plate **400**, and between the printing roller **500** and a substrate **100**.

As shown in FIG. **4D**, by rolling the printing roller **500** on the substrate **100**, the pattern material **200a** is printed on the substrate **100**, forming the pattern material **200a** in the predetermined pattern on the substrate **100**.

In the above description of the embodiment illustrated in FIGS. **4A** to **4D**, the pattern material is described as being hydrophilic, while the lands of the printing plate are hydrophobic and the recesses of the printing plate are hydrophilic. Alternatively, a hydrophobic pattern material may be used in which case the lands of the printing plate are hydrophilic, and the recesses of the printing plate are hydrophobic. If the printing plate is made of a hydrophobic material, the lands of the printing plate may be made hydrophilic by treatment such as a treatment with an oxygen plasma. If the printing plate is made of a hydrophilic material, the recesses of the printing plate may be made hydrophobic by treatment such as a treatment with a fluoric carbon plasma.

In the above-described embodiment, the pattern material is prevented from coating the lands of the printing plate by controlling a hydrophobic or hydrophilic property of the lands to be opposite that of the pattern material. Alternatively, the depth of the pattern material in the recesses may be controlled during dropping of the pattern material to prevent coating of the lands of the printing plate, as illustrated in FIGS. **6A** and **6B**. The printing plate **400** has a recess depth

measured from the bottom of a recess **430** adjacent to the surface of an adjacent land **460**. When dropping the pattern material into the recess **430** using the precision nozzle **600**, the precision nozzle is controlled to form a height of pattern material in the recess based on the feature to be printed. As shown in FIGS. **6A** and **6B**, the height of the printed material in the recess is less than the height of the recess depth, leaving a recess gap having an effective height measured from the surface of the printed material in the recess **430** to the surface of an adjacent land **460** for preventing coating of the lands with pattern material. The effective height of the gap may be equal or greater than the height of the printed material in the recess in which case the depth of the recess is at least twice the height of the pattern material in the recess. For example, when forming a color filter, the precision nozzle may be controlled to form a height of color filter material in the recess of about $3\ \mu\text{m}$. The recess depth of the printing plate may be $6\ \mu\text{m}$ or greater leaving an effective recess gap of at least $3\ \mu\text{m}$. The depth of the recess may be limited to $30\ \mu\text{m}$.

The above-described patterning method may be applied in a manufacturing process for an LCD device. In particular, the above patterning method may be used in forming a black matrix layer and a color filter layer of an LCD device.

FIGS. **5A** to **5D** are cross sectional views of illustrating a method for manufacturing an LCD device according to the present invention.

As shown in FIG. **5A**, a black matrix layer **270** is formed on a first substrate **130**. That is, as shown in FIGS. **3C**, **4A** and **4B**, a black matrix material is formed in the recesses **430** of the printing plate **400** by using the precision nozzle **600**. As described above, the printing roller **500** is rolled on the printing plate **400** and the black matrix material formed in the recesses **430** of the printing plate **400** is printed on the surface of the printing roller **500**. The printing roller **500** is then rolled on the first substrate **130**, printing the black matrix material onto the first substrate **130** to form the black matrix layer **270**.

R, G, and B color filter materials are formed in respective recesses **430** of a second printing plate **400** using the precision nozzle **600**. As shown in FIG. **5B**, respective color filter layer patterns **280** are formed in corresponding recesses of the first substrate **130** having the black matrix layer **270**, by rolling a second roller **500** on the second printing plate **400** and then rolling the second printing roller **500** on the first substrate **130**.

As shown in FIG. **5C**, a second substrate **160** having a thin film transistor array substrate is prepared.

Although not shown, a process for preparing the second substrate **160** includes forming gate and data lines crossing each other to define a pixel region, forming a thin film transistor formed adjacent to a crossing of the gate and data lines, forming a passivation layer on an entire surface including the thin film transistor, and forming a pixel electrode connected to a drain electrode of the thin film transistor.

As shown in FIG. **5D**, the first and second substrates **130** and **160** are bonded to each other, and a liquid crystal layer **700** is formed between the first and second substrates **130** and **160**.

The liquid crystal layer **700** may be formed using a dispensing method or an injection method.

When using the dispensing method, a sealant having no inlet is formed on any one of the first and second substrates **130** and **160**, liquid crystal is dispensed on any one of the first and second substrates **130** and **160**, and the two substrates are bonded to each other.

When using the injection method, after forming a sealant having an inlet on any one of the first and second substrates

7

130 and 160, liquid crystal is injected into a space between the first and second substrates 130 and 160 by capillary phenomenon and pressure difference.

As mentioned above, the patterning method and the method for manufacturing the LCD device according to embodiments of the present invention have the following advantages.

By preparing a printing plate having a recesses and coating the pattern material in the recesses of the printing plate using a precision nozzle, it is possible to reduce defects during printing. In addition, coating the pattern material only in the recesses of the printing plate decreases manufacturing cost by decreasing consumption of the pattern material.

It will be apparent to those skilled in the art that various modifications and variation can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalent.

What is claimed is:

1. A method for manufacturing an LCD device comprising:
preparing a first substrate and a second substrate;
forming a pattern on the first substrate; and
forming a liquid crystal layer between the first and second substrates,
wherein forming a pattern on the first substrate comprises:
preparing a printing plate having recesses and lands;
dropping a pattern material into the recesses of the printing plate using at least one precision nozzle to form the pattern material in the recesses of the printing plate,

8

stopping said dropping a pattern material into the recesses before a height of the pattern material formed in each recess reaches one-half a depth of the recess in order to prevent coating of lands of the printing plate,

rolling a printing roller on the printing plate to print the pattern material in a recess of the printing plate onto the printing roller, wherein the printing roller comprises a blanket of Si-based resin, having elasticity, adhered to a surface thereof; and

rolling the printing roller on the first substrate to print the pattern material on the printing roller onto the first substrate.

2. The method for manufacturing an LCD device of claim 1, wherein the pattern material is one of a black matrix material and a color filter material.

3. The method for manufacturing an LCD device of claim 1, wherein preparing the printing plate having recesses and lands comprises:

forming a predetermined material layer on the printing plate corresponding to the lands.

4. The method for manufacturing an LCD device of claim 3, wherein the predetermined material layer includes a black matrix layer.

5. The method for manufacturing an LCD device of claim 1, wherein the process of preparing the printing plate having recesses and lands comprises forming grooves in the printing plate corresponding to the recesses.

6. The patterning method of claim 5, wherein the process of preparing the printing plate having recesses and lands further comprises forming a predetermined material layer on the printing plate corresponding to the lands.

* * * * *

专利名称(译)	图案化方法和使用该方法制造液晶显示装置的方法		
公开(公告)号	US8893618	公开(公告)日	2014-11-25
申请号	US11/477439	申请日	2006-06-30
[标]申请(专利权)人(译)	侑香小号 KIM CHUL ^ h 李正Ĵ OH TAEÿ PARK CHOON ^ h		
申请(专利权)人(译)	侑香小号 KIM CHUL ^ h 李正Ĵ OH TAEÿ PARK CHOON ^ h		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	YOO HONG SUK KIM CHUL HO LEE JUNG JAE OH TAE YOUNG PARK CHOON HO		
发明人	YOO, HONG SUK KIM, CHUL HO LEE, JUNG JAE OH, TAE YOUNG PARK, CHOON HO		
IPC分类号	G02F1/1335 B41N1/12 B41M1/10 B41M1/34 B41F17/14 B41F9/01 H05K3/12 G02B5/22 H05K3/20 G02B5/20 B41F3/20 G03F1/92		
CPC分类号	H05K2203/1173 G02B5/201 H05K3/207 H05K2203/0113 H05K3/1275 G02B5/223 G02F1/133516 H05K2203/0143 H05K2203/0534 G02F1/133512 H05K2203/013 H05K3/125 B41M5/0256 B41M1/04 B41F3/36 B41M3/003 B41M1/02 B41F17/00 B41F31/08 B41M1/10 B41M1/26 B41M1/34 G02F1/13 G02F1/1333		
优先权	1020050134118 2005-12-29 KR		
其他公开文献	US20070157841A1		
外部链接	Espacenet USPTO		

摘要(译)

公开了一种图案化方法和使用该图案化方法制造LCD装置的方法。图案化方法包括制备具有凹凸部分的印刷版;在印刷版的凹部涂覆图案材料;在印刷版上滚动印刷辊, 在印刷辊上印刷凹部的图案材料;并且将印刷辊在基板上滚动以在基板上印刷印刷辊的图案材料。

