



US007889296B2

(12) **United States Patent**
Ohmuro et al.

(10) **Patent No.:** **US 7,889,296 B2**
(45) **Date of Patent:** **Feb. 15, 2011**

(54) **LIQUID CRYSTAL DISPLAY DEVICE AND
MANUFACTURING METHOD FOR THE
SAME**

(75) Inventors: **Katsufumi Ohmuro**, Kawasaki (JP);
Norio Sugiura, Kawasaki (JP);
Kunihiro Tashiro, Kawasaki (JP);
Yoshio Koike, Kawasaki (JP)

(73) Assignee: **Sharp Kabushiki Kaisha**, Osaka (JP)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 1030 days.

(21) Appl. No.: **11/708,796**

(22) Filed: **Feb. 21, 2007**

(65) **Prior Publication Data**

US 2007/0146594 A1 Jun. 28, 2007

Related U.S. Application Data

(62) Division of application No. 10/701,305, filed on Nov.
4, 2003, now Pat. No. 7,209,107.

(30) **Foreign Application Priority Data**

Nov. 6, 2002 (JP) 2002-323073
Nov. 29, 2002 (JP) 2002-347077

(51) **Int. Cl.**
G02F 1/1335 (2006.01)

(52) **U.S. Cl.** 349/114; 349/106; 349/113

(58) **Field of Classification Search** 349/106,
349/113, 114, 129
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,712,874 A * 12/1987 Sekimura et al. 349/106
5,177,627 A * 1/1993 Ishiwata et al. 349/162
5,418,635 A 5/1995 Mitsui et al.
5,708,486 A 1/1998 Miyawaki et al.

5,724,111 A 3/1998 Mizobata et al.
5,753,937 A 5/1998 Shimomaki et al.
5,847,789 A 12/1998 Nakamura et al.
5,850,274 A * 12/1998 Shin et al. 349/129
5,872,611 A 2/1999 Hirata et al.
6,124,909 A 9/2000 Miyashita et al.

(Continued)

FOREIGN PATENT DOCUMENTS

JP 5-232465 9/1993

(Continued)

Primary Examiner—David Nelms


Assistant Examiner—David Y Chung

(74) *Attorney, Agent, or Firm*—Greer, Burns & Crain, Ltd

(57) **ABSTRACT**

On a glass substrate, gate bus lines, data bus lines, and TFTs are formed. Then, on the substrate, an insulating film, covering the gate bus lines, data bus lines and TFTs, is formed, and a positive type photoresist film is further formed thereon. Next, through exposure and development processes, the resist film is divided for each picture element and subjected to ultraviolet ray irradiation to harden only a surface layer thereof. Then, the resist film is subjected to heat treatment to form thereon wrinkle-form surface ruggedness of a uniform pattern, which is determined depending on the size of the resist film. Subsequently, reflection electrodes are formed on the resist film. The reflection electrodes are formed to overlap the gate bus line, data bus line and TFTs, and the regions between the adjacent reflection electrodes serve as light transmission regions.

10 Claims, 35 Drawing Sheets



US 7,889,296 B2

Page 2

U.S. PATENT DOCUMENTS

6,169,593	B1	1/2001	Kanaya et al.	
6,195,140	B1	2/2001	Kubo et al.	
6,452,653	B1	9/2002	Yamanaka et al.	
6,476,889	B2	11/2002	Urabe et al.	
6,850,298	B2	2/2005	Fujimori et al.	
6,853,421	B2	2/2005	Sakamoto et al.	
7,075,603	B2	7/2006	Ihida et al.	
2001/0033350	A1 *	10/2001	Kobayashi et al.	349/106
2002/0075441	A1	6/2002	Fujimori et al.	
2002/0140886	A1	10/2002	Sugiura et al.	
2002/0149728	A1 *	10/2002	Ogishima et al.	349/129
2003/0128317	A1	7/2003	Ohmuro et al.	

2004/0218120 A1 11/2004 Ikeno et al.

FOREIGN PATENT DOCUMENTS

JP	7-333598	12/1995
JP	8-338993	12/1996
JP	10-307205	11/1998
JP	11-2811	1/1999
JP	11-281972	10/1999
JP	11-305248	11/1999
JP	2001-166289	6/2001
JP	2002-221716	8/2002
JP	2002-296585	10/2002
JP	2003-202594	7/2003

* cited by examiner

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D




FIG. 9E




FIG. 9F




FIG. 9G




FIG. 9H




FIG. 9I




FIG. 9J




FIG. 9K




FIG. 9L




FIG. 9M




FIG. 10




FIG. 11

REFLECTION/TRANSMISSION CHARACTERISTICS (180ppi)




FIG. 12

AFM IMAGE OF THE REFLECTION ELECTRODES




FIG. 13A




FIG. 13B




FIG. 13C




FIG. 14




FIG. 15




FIG. 16A




FIG. 16B




FIG. 16C





FIG. 17






FIG. 20




FIG. 21A




FIG. 21B




FIG. 22A




FIG. 22B




FIG. 24A




FIG. 24B




FIG. 25




FIG. 26A




FIG. 26B




FIG. 27A





FIG. 27B






FIG. 29





FIG. 30



LIQUID CRYSTAL DISPLAY DEVICE AND MANUFACTURING METHOD FOR THE SAME

This is a divisional of application Ser. No. 10/701,305, filed 5
Nov. 4, 2003 now U.S. Pat. No. 7,209,107.

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is based upon and claims priority of Japa-
nese Patent Applications No. 2002-347077, filed on Nov. 29,
2002, and No. 2002-323073, filed on Nov. 6, 2002, the con-
tents being incorporated herein by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display 20
device having a reflection electrode and a manufacturing
method for the same and, more particularly, to a liquid crystal
display device applicable to a transmissive type liquid crystal
display device which can be used as a reflection type liquid
crystal display device in the environment of a bright ambient,
and can be used as a transmission type liquid crystal display
device by switching on a backlight in the environment of a
dark ambient, and a manufacturing method for the same.

2. Description of the Prior Art

A liquid crystal display device is thin and lightweight
compared with a CRT (Cathode Ray Tube), having an advan- 30
tage that it can be driven with a lower voltage with low power
consumption. The liquid crystal display device is used for
various electronic devices such as a TV set, a notebook type
personal computer, a desktop type personal computer, a PDA
(Personal Digital Assistance), and a cellular telephone. Espe- 35
cially, an active matrix type liquid crystal display device
provided with a TFT (Thin-film transistor) as a switching
element for each sub-pixel (hereafter, referred to as a picture
element in this invention) shows an excellent display charac-
teristic comparable to the CRT, with its high driving capabil- 40
ity. Therefore, the active matrix type liquid crystal display
device has been extensively used for the fields where conven-
tionally the CRT is used, such as a desktop type personal
computer and a TV set.

Generally, the liquid crystal display device has a structure 45
in which liquid crystal is enclosed between two transparent
substrates. A picture element electrode, the TFT and the like
are formed for each picture element on one of the two trans-
parent substrates, and color filters disposed opposingly to the
picture element electrode and a common electrode that is 50
common to each picture element are formed on the other
substrate. Hereafter, the substrate having the picture element
electrode and the TFT formed thereon is referred to as a TFT
substrate, and the substrate arranged opposingly to the TFT
substrate is referred to as a counter substrate. Note that one 55
pixel is formed of three picture elements (sub-pixels) of red
(R), green (G) and blue (B).

The liquid crystal display device includes a transmission
type liquid crystal display device and a reflection type liquid
crystal display device. The transmission type liquid crystal
display device displays images by controlling the light quan- 60
tity of transmitted rays of light for each picture element, while
the reflection type liquid crystal display device displays
images by controlling the light quantity of reflected rays of
light for each picture element. The transmission type liquid
crystal display device requires an exclusive light source 65
called a backlight. Meanwhile, in the reflection type liquid

crystal display device, an ambient condition of light (natural
light or lamplight) is used as a light source. Therefore, the
reflection type liquid crystal display device has a merit of
consuming much less power compared with the transmission
type liquid crystal display device. In addition, the reflection
type liquid crystal display device is more excellent in visibil-
ity outdoors than the transmission type liquid crystal display
device. Hereafter, the picture element electrode of the reflec-
tion type liquid crystal display device is also referred to as a
reflection electrode.

For example, Japanese Patent Laid-Open No. Hei
08-338993 discloses a reflection type liquid crystal display
device in which a TN (twisted nematic) type liquid crystal is
used and an alignment film is subjected to rubbing treatment
to make the liquid crystal twist align. Moreover, Japanese
Patent Laid-Open No. Hei 05-232465 discloses a liquid crys- 15
tal display device whose reflection electrode is provided with
ruggedness by using a photolithography method. In this way,
by providing the surface of the reflection electrode with rug-
gedness, it is avoided that the visibility is greatly changed
depending on a position where a panel is observed, by irregu-
lar reflection of light.

However, the process for forming ruggedness on the sur-
face of the reflection electrode is complicated in the above-
described method. Hereupon, the present inventors provide a
method for forming a reflection electrode provided with rug- 25
gedness on the surface thereof by using a positive type pho-
toresist (for example, Japanese Patent Laid-Opens No. 2002-
221716 and No. 2002-296585). In this method, the step to
harden only a surface layer is carried out by subjecting the
photoresist to ultraviolet ray irradiation and followed by heat
treatment. Fine ruggedness is thus formed on the surface of
the resist film. Then, by forming the reflection electrode on
the resist film, the reflection electrode having surface rugged- 35
ness can be easily formed.

Incidentally, in the reflection type liquid crystal display
device, since an ambient condition of light (natural light or
lamplight) is used as a light source, the visibility is greatly
changed depending on the ambient condition of light. That is,
when its neighborhood is bright, the visibility of the reflection
type liquid crystal display device is satisfactory. However,
when its neighborhood is dark, the visibility thereof is
extremely decreased. In order to overcome such a disadvan-
tage, the reflection type liquid crystal display device having a
light source (front light unit) on a front panel surface, is
proposed. However, the reflection type liquid crystal display
device with this structure is formed so that the light reflected
by the reflection electrode may be transmitted through the
front light unit, where the reflective light is reduced. There- 45
fore, such a reflection type liquid crystal display device poses
a problem that contrast of an image is lowered and sufficient
visibility is not obtained compared with the reflection type
liquid crystal display device without any front light unit.

Japanese Patent Laid-Open No. Hei 07-333598 discloses a
liquid crystal display device (hereafter, referred to as a trans-
flective type liquid crystal display device) that can be used as
a reflection type liquid crystal display device when its neigh-
borhood is bright, and as a transmission type liquid crystal
display device by switching on a backlight when its neigh-
borhood is dark. This is realized by forming a reflection
electrode of a metal thin film for semi-transmitting light.
However, in this type of transmissive type liquid crystal dis-
play device, when used as a transmission type liquid crystal
display device, light absorption by the metal thin film is
increased. Therefore, the utilization efficiency of light is bad,
involving a problem that satisfactory visibility cannot be
obtained unless a backlight having large luminance is used. Al

(aluminum) film having a thickness of about 30 nm is used as the metal thin film for semi-transmitting light. However, in the case of a large-sized liquid crystal display device, it is extremely difficult to form an Al thin film having a uniform thickness over the entire surface of a panel.

Japanese Patent Laid-Open No. Hei 11-281972 discloses a transreflective type liquid crystal display device in which the central part of a reflection electrode is opened to form a transmission region through which light is transmitted, and in the transmission region, a transparent electrode such as an ITO (Indium-Tin Oxide) is formed.

FIG. 1 is a schematic diagram showing an example of the TFT substrate of a conventional transreflective type liquid crystal display device with the above structure.

On the TFT substrate, a plurality of gate bus lines **71** disposed so as to be parallel to each other, and a plurality of data bus lines **72** so as to be orthogonal to the gate bus lines **71**, are formed. In the vicinity of each area where the gate bus line **71** and the data bus line **72** intersect with each other, a TFT **73** is formed. Moreover, in each rectangular region partitioned by the gate bus lines **71** and the data bus lines **72**, a reflection electrode **74** made of a metal film for reflecting light such as Al (aluminum) is formed. In the central part of the reflection electrode **74**, an opening part **74a** for transmitting light is formed, and in the opening part **74a**, a transparent electrode **75** made of a transparent electric conductor such as ITO is formed.

The gate bus lines **71**, the data bus lines **72**, and the TFTs **73** are covered with an insulating flattening film; the reflection electrodes **74** are formed on the flattening film; and the transparent electrodes **75** are formed under the flattening film. When direct contact of the Al constituting the reflection electrodes **74** and the ITO constituting the transparent electrodes **75** occurs, corrosion is caused due to a battery effect. For this reason, the reflection electrodes **74** and the transparent electrodes **75** are electrically connected via a barrier metal such as Ti (titanium).

In the liquid crystal display device with the above structure, scanning signals are sequentially supplied to a plurality of the gate bus lines **71**, and display signals are supplied to each of the data bus lines **72** when displaying an image. Then, the TFTs **73** connected to the gate bus lines **71** supplied with the scanning signals become in ON states, and the display signals are written in the reflection electrodes **74** and the transparent electrodes **75** via the TFTs **73**, whereby the orientation of liquid crystal molecules between the reflection electrodes **74** and the counter substrate, as well as the transparent electrodes **75** and the counter substrate, are changed. Consequently, the light quantity of the reflective light or the transmitted light is also changed. By controlling the light quantity of the reflective light or the transmitted light for each picture element, a desired image is displayed on the liquid crystal display device.

According to the transreflective type liquid crystal display device, comparatively satisfactory visibility is secured in any case of using it as the reflection type display device or as the transmission type display device.

However, in the transreflective type liquid crystal display device disclosed in Japanese Patent Laid-Open No. Hei 11-281972, the transparent electrodes made of ITO and the barrier metal are required to be formed in addition to the reflection electrodes made of Al. Accordingly, there arises a problem that many processes are required, involving an increase in product costs.

Furthermore, in this transreflective type liquid crystal display device, if the transmission region is enlarged, the reflection region is reduced. Transmission and reflection characteristics

are thus defined by a trade-off relation. In a liquid crystal display device with high resolution, the area of one picture element is small. Therefore, it is difficult to obtain a satisfactory liquid crystal display device in reflection characteristics as well as in transmission characteristics.

Further, in the reflection region, incident light is transmitted through CF (color filter) layers two times and emitted to a display screen side. Meanwhile, in the transmission region, incident light is transmitted through the CF layers only once and emitted to the display screen side. For this reason, chromaticity irregularity is generated between the cases of using the transreflective type liquid crystal display device as a reflection type liquid crystal display device (hereafter, referred to as a reflection mode) and as a transmission type liquid crystal display device (hereafter, referred to as a transmission mode).

When the color purity of the CF layers is adjusted so that a bright display can be obtained when displaying in the reflection mode, the color purity in the transmission mode is deteriorated, resulting in a display in light colors. Conversely, when the color purity of the CF layers is adjusted so that satisfactory color rang can be obtained when displaying in the transmission mode, reflected light is lowered when displaying in the reflection mode, resulting in an extremely dark display.

In order to overcome the above-described problems, a structure of the liquid crystal display device is conventionally known, in which the color purity of the CF layers is made to be different between the reflection regions and the transmission regions (for example, Japanese Patent Laid-Open No. Hei 11-2811). In this structure, for example, the CF layers are not formed in the reflection regions, but formed in the transmission regions only. Accordingly, when displaying in the transmission mode, a display with high color purity can be obtained, and when displaying in the reflection mode, a display with high luminance, in achromatic colors though, can be obtained. However, this structure involves a problem that display quality is greatly changed when the reflection mode and the transmission mode are switched with each other. Moreover, in the reflection mode, a full-color display cannot be provided, involving a problem that a transmittable information quantity for users via the display screen is reduced and good display quality cannot be obtained.

In order to overcome the above-described problems, another structure of the liquid crystal display device is conventionally known, in which color purity is made to be different between the reflection regions and the transmission regions (for example, Japanese Patent Laid-Opens No. Hei 11-305248 and No. 2001-166289). However, in this structure, while the chromaticity irregularity between the transmission mode and the reflection mode can be reduced, reflection characteristics and transmission characteristics are still defined by a trade-off relation. Therefore, it is difficult to improve both of the reflection characteristics and the transmission characteristics, raising a problem that utilization efficiency of light is degraded.

Also, there is provided a reflection type liquid crystal display device in which the color purity of the CF layers is made to be different for each picture element region (for example, Japanese Patent Laid-Open No. Hei 10-307205). In this structure, a display is produced using picture elements of six colors in total including three colors of red (R), green (G) and blue (B) with the addition of complementary colors thereof of cyan (C), magenta (M) and yellow (Y), thereby enlarging the range for color reproduction. However, an increase in a drive circuit leads to an increase in the manufacturing costs, and therefore the liquid crystal display device provided with the picture

elements of six colors may not be practical. In addition, the above structure is not applicable to the transfective type liquid crystal display device.

The transfective type liquid crystal display device that improves the transmission characteristics without decreasing the reflection characteristics, is proposed in Japanese Patent Laid-Open No. 2003-202594 filed by the present applicant. This transfective type liquid crystal display device will be explained with reference to FIGS. 2 to 5. FIG. 2 shows a structure of the TFT substrates of the transfective type liquid crystal display device, and FIG. 3 shows a sectional structure of the transfective type liquid crystal device taken along the line I-I of FIG. 2. As shown in FIGS. 2 and 3, reflection electrodes 110 are formed so as to cover gate bus lines 104, data bus lines 106, and TFTs 108. The regions where the reflection electrodes 110 are formed serve as reflection regions R and R'. The regions surrounding the reflection electrodes 110 serve as transmission regions T and T'. The liquid crystal in the transmission regions T and T' are driven similarly to the liquid crystal in the reflection regions R and R' by an oblique electric field between the reflection electrodes 110 and a common electrode 130.

In this structure, the regions used neither as the reflection regions nor as the transmission regions in the conventional liquid crystal display device, are used as the transmission regions T and T'. Moreover, the areas of the gate bus lines 104, the data bus lines 106, and the TFTs 108 which are exposed in the transmission regions T and T', are decreased to a large extent. Therefore, the areas of the transmission regions T and T' can be enlarged without decreasing the areas of the reflection regions R and R'. Accordingly, the transmission characteristics can be improved without decreasing the reflection characteristics, and good display characteristics can be obtained in both of the reflection mode and the transmission mode.

FIG. 4 shows another structure of the transfective type liquid crystal display device. As shown in FIG. 4, the reflection electrodes 110 are formed in regions surrounded by the gate bus lines 104 and the data bus lines 106. The regions where the reflection electrodes 110 are formed serve as reflection regions. The reflection electrodes 110 have opening parts 150a to 150e formed therein. The opening parts 150a to 150e are opened to be formed into various shapes such as a slit-like shape and a circular or polygonal hole-like shape. The regions where the opening parts 150a to 150e are formed serve as transmission regions.

FIG. 5 shows further another structure of the transfective type liquid crystal display device. As shown in FIG. 5, the reflection electrodes 110 are formed so as to cover the gate bus lines 104, data bus lines 106, and the TFTs 108. The regions where the reflection electrodes 110 are formed serve as reflection regions. The reflection electrodes 110 have opening parts 150f to 150k formed therein which are opened to be formed into a slit-like shape, a circular or polygonal hole-like shape and the like. The regions where the opening parts 150f to 150k are formed and the regions between the adjacent reflection electrodes 110 serve as transmission regions.

In the structures shown in FIGS. 4 and 5, transparent electrodes such as ITO are not formed in the transmission regions. Therefore, the transparent electrodes and a barrier metal layer are not required to be formed therein. Moreover, for example, by forming the opening parts 150a to 150k into a shape enabling the orientation control of a liquid crystal having negative dielectric anisotropy, rubbing treatment for an oriented film can be eliminated. Accordingly, a manufacturing process of the liquid crystal display device is simplified and manufacturing costs are reduced.

As described above, according to the transfective type liquid crystal display devices as shown in FIGS. 2 to 5, the transmission characteristics can be enhanced without decreasing the reflection characteristics. At the same time, the manufacturing process can be simplified and the manufacturing costs can be reduced. However, this transfective type liquid crystal display device still has such problems as will be described below. FIG. 6 shows a schematic sectional structure of three picture elements of the liquid crystal display device taken along the line II-II of FIG. 4. As shown in FIG. 6, a light beam t of the transmission light emitted from a backlight unit (not shown) to be emitted to a display screen side, and a light beam r of the reflection light incident from the display screen side and reflected by the reflection electrode 110 to be emitted to the display screen side, pass along different light paths. That is, the light beam t of the transmission light is transmitted through the CF layer R only once. On the other hand, the light beam r of the reflection light is transmitted through the CF layer R twice. Therefore, there arises a problem that color purity is made to be different between the transmission mode display and the reflection mode display, thereby degrading display quality.

Moreover, in order to obviate the occurrence of difference in color purity between the transmission mode display and the reflection mode display, it is conventionally known that the film thickness of the CF layers in the transmission regions is made twice as thick as CF layers in the reflection regions. However, in this structure, alignment margins for tolerating alignment deviation generated when aligning a TFT substrate 102 having the reflection electrodes 110 formed thereon with a counter substrate 114 having the CF layers formed thereon, cannot be secured. For this reason, there arises a problem that when the alignment deviation is generated, color purity is made to be different between the transmission mode display and the reflection mode display, thereby degrading the display quality.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a liquid crystal display device of those with high resolution, excellent in reflection characteristics compared with a conventional one, and a manufacturing method for the same.

Another object of the present invention is to provide a transfective type liquid crystal display device which can be manufactured more easily than a conventional one and is good in reflection characteristics and transmission characteristics, and a manufacturing method for the same.

Further another object of the present invention is to provide a liquid crystal display device having good display quality.

The above-described problems are solved by a liquid crystal display device constituted by enclosing liquid crystal between a pair of substrates. The liquid crystal display device includes, on one of the pair of substrates, gate bus lines supplied with scanning signals; data bus lines supplied with display signals; thin-film transistors having gate electrodes electrically connected to the gate bus lines and drain electrodes electrically connected to the data bus lines; a resin film divided for each picture element and having wrinkle-form surface ruggedness; reflection electrodes formed on the resin film, having fine surface ruggedness following the surface ruggedness of the resin film, and electrically connected to source electrodes of the thin-film transistors.

In the present invention, the resin film having the wrinkle-form rugged surface formed thereon is divided for each picture element. As disclosed in Japanese Patent Laid-Open No. 2002-221716, if the surface of a resin film is hardened, and

followed by heat treatment, fine wrinkle-form surface ruggedness can be formed. It is confirmed, according to experiments by the present inventors, that a wrinkle-form rugged pattern formed on the surface of the resist film is not uniform when the resist film is large in size, while a uniform wrinkle-form rugged pattern is formed in accordance with the size of the resist film when the size of the resist film is reduced.

In order to obtain such an effect, a picture element is preferably set to the size corresponding to 110 to 850 ppi (pixel per inch). When the size of a picture element is large, a slit is formed on the resist film and the reflection electrode to divide the resist film and the reflection electrode for one picture element into a plurality of regions. The similar effects can be thus obtained. Accordingly, if the sizes of the resist film and the reflection electrode are determined beforehand and a rugged pattern is formed so that light incident to a liquid crystal panel from the upside may be reflected in the direction of a normal line of a panel surface, utilization efficiency of light is improved and visibility is improved.

Note that in order to obtain good reflection characteristics, a flattened area where the average angle of the surface of the reflection electrode is 5° or less is preferably set to 50% or more. In addition, when the resist film is divided by the slit into the plurality of regions, the length of the short side of each divided region is preferably set to 5 μm or more in order to obtain surface ruggedness of a uniform pattern on the resist film.

In addition, when the resist film and the reflection electrodes are formed so that the gate bus lines, data bus lines, and the thin-film transistors may be overlapped one another, the regions between the adjacent reflection electrodes can be set as light transmission regions through which light is transmitted, thereby realizing the transmissive type liquid crystal display device. In this case, liquid crystal molecules in the light transmission regions are driven by an electric field transversely leaked from the reflection electrodes.

The above-described problems are solved by a liquid crystal display device constituted by enclosing liquid crystal between a pair of substrates, including, on one of the pair of substrates, gate bus lines supplied with scanning signals; data bus lines supplied with display signals; thin-film transistors having gate electrodes and drain electrodes, the gate electrodes being electrically connected to the gate bus lines and the drain electrodes being electrically connected to the data bus lines; a resin film divided for each picture element and disposed on upper part of the gate bus lines, the data bus lines, and the thin-film transistors; and reflection electrodes formed on the resin film and electrically connected to source electrodes of the thin-film transistors.

In the present invention, the resin film, which is divided for each picture element, and the reflection electrodes are formed so as to overlap the gate bus lines, data bus lines, and thin-film transistors. In this case, the regions between the adjacent reflection electrodes serve as light transmission regions through which light is transmitted. Accordingly, compared with a method of creating the light transmission regions by forming opening parts in the reflection electrodes, the areas of the light transmission regions can be increased even though the areas of the reflection electrodes are the same.

The above problems are solved by a manufacturing method for a liquid crystal display device including the steps of: forming on a first substrate gate bus lines supplied with scanning signals, data bus lines supplied with display signals, and thin-film transistors having gate electrodes connected to the gate bus line and drain electrodes connected to the data bus line; forming a photoresist film on upper part of the gate bus lines, the data bus lines, and the thin-film transistors; dividing

the photoresist film for each picture element, and exposing and developing photoresist to form opening parts at positions corresponding to source electrodes of the thin-film transistors; hardening only a surface layer of the photoresist film; subjecting the photoresist film to heat treatment to form wrinkle-form surface ruggedness; forming on the photoresist film reflection electrodes electrically connected to the source electrodes of the thin-film transistors via the opening parts; and arranging opposingly the first substrate and a second substrate provided with an electrode made of a transparent conductive film, and enclosing liquid crystal therebetween.

According to the present invention, the photoresist film is divided for each picture element and followed by heat treatment, thereby forming surface ruggedness. In this case, it is confirmed in experiments by the present inventors that a uniform rugged pattern can be formed in accordance with the size of the photoresist film. Therefore, while considering conditions of actually using the liquid crystal display device, if the size of the resist film is set, to form a rugged pattern, so that light incident to a liquid crystal panel from the upside can be reflected in the direction of a normal line of a panel surface, utilization efficiency of light is improved and visibility is improved.

The above-described problems are solved by a manufacturing method for the liquid crystal display device, including the steps of: forming on a first substrate gate bus lines supplied with scanning signals, data bus lines supplied with display signals, and thin-film transistors having gate electrodes connected to the gate bus lines and drain electrodes connected to the data bus lines; forming a photoresist film on upper part of the gate bus lines, the data bus lines, and the thin-film transistors; dividing the photoresist film for each reflection electrode forming region overlapping with the gate bus line, the data bus line and the thin-film transistor, and exposing and developing photoresist to form opening parts at positions corresponding to source electrodes of the thin-film transistors; forming on the photoresist film reflection electrodes electrically connected to the source electrodes of the thin-film transistors via the opening parts; and arranging opposingly the first substrate and a second substrate provided with an electrode made of a transparent conductive film, and enclosing liquid crystal therebetween.

In the present invention, the resist film and the reflection electrodes are divided for each picture element so as to overlap the gate bus lines, data bus lines, and the thin-film transistors. In this case, the regions between the adjacent reflection electrodes serve as light transmission regions through which light is transmitted. Compared with a method of creating the light transmission regions by forming opening parts in the reflection electrodes, the areas of the light transmission regions can be increased even though the areas of the reflection electrodes are the same.

The above-described problems are solved by a liquid crystal display device including: a pair of substrates opposingly arranged; a liquid crystal enclosed between the pair of substrates; a plurality of picture element regions, each including a reflection region having a reflection electrode formed on one of the pair of substrates and reflecting light incident from the other substrate, and a transmission region for transmitting light incident from the one substrate, the transmission region being a region of a circumference or an opening part of the reflection electrode; and wavelength selecting layers, each formed in the transmission region, extending up to part of the reflection region, and selecting and transmitting light having a predetermined wavelength.

In the present invention, the wavelength selecting layers extend up to part of the reflection regions, and therefore when

displaying in the reflection mode, the light that is transmitted though the wavelength selecting layers twice and the light that is not transmitted through the reflection selecting layers are mixed, thereby providing a high luminance display. Moreover, the area ratio of the regions for forming the wavelength selecting layers of the reflection regions to the entire reflection regions is adjusted, thereby making the color purity of the reflection mode display closer to the color purity of the transmission mode display. Thus, the transreflective type liquid crystal display device with good display quality can be obtained.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic diagram showing an example of a TFT substrate of a conventional transreflective type liquid crystal display device.

FIG. 2 is a plan view showing a structure of another conventional transreflective type liquid crystal display device.

FIG. 3 is a sectional view taken along the line I-I of FIG. 2.

FIG. 4 is a plan view showing a structure of further another conventional transreflective type liquid crystal display device.

FIG. 5 is a plan view showing a structure of still another conventional transreflective type liquid crystal display device.

FIG. 6 is a sectional view explaining about a problem of a conventional liquid crystal display device.

FIG. 7 is a plan view showing a liquid crystal display device according to a first embodiment of the present invention.

FIG. 8 is a schematic sectional view taken along the line III-III of FIG. 7.

FIGS. 9A to 9M are schematic sectional views showing a manufacturing method for a TFT substrate of the liquid crystal display device according to the first embodiment of the present invention in a process order.

FIG. 10 is a view showing relations of transmissive aperture ratio and effective reflection area ratio to resolution, between a conventional transreflective type liquid crystal display device and the transreflective type liquid crystal display device of the first embodiment.

FIG. 11 is a view showing microscopic images obtained by checking a reflection state and a transmission state when applied voltages are 0V and 2.3 V, in the liquid crystal display device manufactured according to the first embodiment.

FIG. 12 is a view showing an AFM image of a reflection electrode of the liquid crystal display device according to the first embodiment.

FIGS. 13A to 13C are plan views showing a transreflective type liquid crystal display device according to a second embodiment of the present invention.

FIG. 14 is a view showing relations of transmissive aperture ratio and effective reflection area ratio to resolution, between a conventional transreflective type liquid crystal display device and the transreflective type liquid crystal display device of the second embodiment.

FIG. 15 is a view showing microscopic images obtained by checking a display state when applied voltages are 0V and 2.3 V, in the liquid crystal display device manufactured according to the second embodiment.

FIGS. 16A to 16C are plan views showing a transreflective type liquid crystal display device according to a third embodiment of the present invention.

FIG. 17 is a view showing microscopic images obtained by checking a display state when applied voltages are 0V and 2.3 V, in the liquid crystal display device manufactured according to the third embodiment.

FIG. 18 is an outline structure of a liquid crystal display device according to a first basic structure of a fourth embodiment of the present invention.

FIG. 19 is a sectional view showing a schematic structure of the liquid crystal display device according to the first basic structure of the fourth embodiment of the present invention.

FIG. 20 is a sectional view showing a schematic structure of a liquid crystal display device according to a second basic structure of the fourth embodiment of the present invention.

FIGS. 21A and 21B are sectional views showing a schematic structure of a liquid crystal display device according to a third basic structure of the fourth embodiment of the present invention.

FIGS. 22A and 22B are sectional views showing schematic structures of a liquid crystal display device according to a fourth basic structure of the fourth embodiment of the present invention.

FIG. 23 is a sectional view showing a schematic structure of the liquid crystal display device according to the fourth basic structure of the fourth embodiment of the present invention.

FIGS. 24A and 24B are views showing a structure of a liquid crystal display device according to example 1 of the fourth embodiment of the present invention.

FIG. 25 is an x-y chromaticity chart of the liquid crystal display device according to example 1 of the fourth embodiment of the present invention.

FIGS. 26A and 26B are views showing a structure of a liquid crystal display device according to example 2 of the fourth embodiment of the present invention.

FIGS. 27A and 27B are views showing a structure of a liquid crystal display device according to example 3 of the fourth embodiment of the present invention.

FIGS. 28A and 28B are views showing a structure of a liquid crystal display device according to example 4 of the fourth embodiment of the present invention.

FIG. 29 is a view showing a structure of a liquid crystal display device according to a fifth embodiment of the present invention.

FIG. 30 is a view showing a modified example of the structure of the liquid crystal display device according to the fifth embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hereafter, preferred embodiments of the present invention will be explained with reference to the accompanying drawings.

First Embodiment

FIG. 7 is a plan view showing a liquid crystal display device of a first embodiment of the present invention, and FIG. 8 is a schematic sectional view taken along the line III-III of FIG. 7. Note that this embodiment shows an example in which the present invention is applied to a transreflective type liquid crystal display device using a VA (vertically aligned) type liquid crystal.

As shown in FIG. 8, the liquid crystal display device of this embodiment is constituted including a TFT substrate 10 and a counter substrate 30, and a vertically aligned nematic liquid crystal 40. The TFT substrate 10 and the counter substrate 30 face each other, and the vertically aligned nematic liquid crystal 40 is enclosed between these substrates. Polarizing plates (linear polarizing plate or circular polarizing plate having the linear polarized light + $\pi/4$ phase difference com-

bined) 38 and 39 are arranged under the TFT substrate 10 and on the counter substrate 30, respectively. In addition, a light source (backlight: not shown) is disposed below the TFT substrate 10.

As shown in FIGS. 7 and 8, the TFT substrate 10 is constituted including a glass substrate 11, gate bus lines 12a formed on the glass substrate 11, storage capacitor bus lines 12b, data bus lines 17a, storage capacitor electrodes 17b, TFTs 7 and reflection electrodes 20a and the like. The gate bus lines 12a and the storage capacitor bus lines 12b horizontally extend, and the data bus lines 17a vertically extend. The gate bus lines 12a and the storage capacitor bus lines 12b are covered with a gate insulating film 13 and electrically disconnected from the data bus lines 17a by this gate insulating film 13.

In the vicinity of each portion where the gate bus line 12a and the data bus line 17a intersect with each other, the TFT 7 is formed. This TFT 7 is constituted by using a silicon film (amorphous silicon film or polysilicon film) 14 formed on the gate insulating film 13 as an operating layer, and using part of the gate bus line 12a as a gate electrode. A channel protection film 15a made of SiN is formed on the channel region of this TFT 7. A drain electrode 17d and a source electrode 17s are respectively formed on both sides of the channel protection film 15a. These drain electrode 17d and source electrode 17s are electrically connected to the silicon film 14 via an n⁺ type amorphous silicon film 16, which is an ohmic contact layer. Moreover, the drain electrode 17d is electrically connected to the data bus line 17a, and the source electrode 17s is electrically connected to the reflection electrode 20a.

Further, the storage capacitor electrodes 17b are formed above the storage capacitor bus lines 12b via the gate insulating film 13.

The TFTs 7 and the storage capacitor electrodes 17b are covered with a final protection film (not shown) made of SiN or the like, and a resist film 19 having a finely rugged surface is formed thereon. The reflection electrodes 20a made of Al or the like are formed on the resist film 19. The reflection electrode 20a is electrically connected to the source electrode 17s of the TFT 7 and the storage capacitor electrode 17b via contact holes 18a and 18b formed on the final protection film and the resist film 19. Moreover, a rugged pattern following that of the resist film 19 is formed on the surface of the reflection electrode 20a.

In this embodiment, the resist film 19 is formed only below the reflection electrode 20a. In addition, the resolution of the liquid crystal display device of this embodiment is 110 to 850 ppi, and the size of the reflection electrode 20a is set according to the resolution. Further, in this embodiment, as shown in FIG. 7, the reflection electrode 20a is formed so as to overlap the gate bus line 12a, the storage capacitor bus line 12b, the data bus line 17a and the TFT 7, and the region between the adjacent reflection electrodes 20a serves as a transmission region through which light is transmitted is formed.

An alignment layer 21 made of polyimide or the like is formed on the reflection electrode 20a. In this embodiment, the surface of the alignment layer 21 is not subjected to rubbing treatment. However, the rubbing treatment may be applied thereto.

Meanwhile, the counter substrate 30 is constituted including a glass substrate 31, color filters 32 formed on one face side (lower side in FIG. 8) of the glass substrate 31, and a common electrode 33. The color filters 32 have three colors of red (R), green (G) and blue (B), and the color filter 32 of one of the colors is arranged in one picture element.

The common electrode 33 is formed under the color filters 32, and an alignment layer 34 made of polyimide or the like is

formed under the common electrode 33. The surface of the alignment layer 34 is subjected to rubbing treatment which decides orientation direction of liquid crystal molecules when no electric field is applied thereto.

The TFT substrate 10 and counter substrate 30 are arranged interposing spacers (not shown) for maintaining a constant interval therebetween, and joined by a sealing material (not shown) coated onto the outside of a display region.

In the liquid crystal display device of this embodiment, positions of the gate bus lines 12a and the data bus lines 17a are different from those in a conventional transmissive type liquid crystal display device. Regions contributing neither to the reflection characteristics nor the transmission characteristics in the conventional liquid crystal display device, that is, the regions between the adjacent reflection electrodes are used as transmission regions in this embodiment. The liquid crystal molecules in these regions are driven by an electric field transversely leaked from the reflection electrodes 20a.

Moreover, in this embodiment, the resist film 19 is divided for each picture element. On the surface of this resist film 19, wrinkle-form ruggedness is provided by hardening and subjecting to heat treatment only a surface layer of the resist film 19, as will be described later. It is confirmed, according to experiments by the present inventors, that a wrinkle-form rugged pattern formed on the surface of the resist film is not uniform when the resist film is large in size, while a uniform wrinkle-form rugged pattern is formed in accordance with the size of the resist film when the size of the resist film is made small. Accordingly, with considering conditions in actually using the liquid crystal display device, the size of the resist film is set, to form a rugged pattern, so that light incident to a liquid crystal panel from the upside can be reflected in the direction of a normal line of a panel surface. Thus, the utilization efficiency of light is improved and visibility is improved.

Although it is not proven why the rugged pattern is uniformized when the size of the resist film is made small, the reason is estimated as follows. That is, when the resist film is large in size, a portion generating ruggedness by heat treatment is not fixed. Moreover, the ruggedness is independently generated at a plurality of portions. Therefore, the rugged pattern is not uniform. However, when the size of the resist film is small, the largest working portion of stress is periodically generated in accordance with the size of the resist film. Therefore, the rugged pattern becomes uniform in accordance with the size of the resist film. In order to obtain the above effects, it is necessary to set one picture element electrode 20a to a size corresponding to the resolution of 110 to 850 ppi.

Note that the rugged pattern formed on the resist film also relates to the film thickness of the resist film. In addition, in order to efficiently reflect the light incident from the upside of the liquid crystal display device in the direction of a normal line of a panel surface, a flattened area (area where the average angle of inclination is 5° or less) in a surface of the reflection electrode is preferably set to 50% or more.

Hereafter, a manufacturing method for the liquid crystal display device of this embodiment will be explained.

FIGS. 9A to 9M are schematic sectional views showing a manufacturing method for the TFT substrate of the liquid crystal display device of this embodiment in a process order. First, as shown in FIG. 9A, a metal film 12 is formed on the glass substrate 11 by sputtering, and a resist film 41 of a predetermined pattern is formed thereon using photoresist.

13

Next, as shown in FIG. 9B, the metal film 12 is etched using the resist film 41 as a mask to form the gate bus lines 12a and storage capacitor bus lines 12b. Thereafter, the resist film 41 is removed.

Next, as shown in FIG. 9C, the gate insulating film 13 is formed on the entire upper surface of the glass substrate 11 by a plasma CVD method. Further, the amorphous silicon film 14 to be the operating layer of the TFT, and a SiN (silicon nitride) film 15 to be the channel protection film are sequentially formed thereon.

Thereafter, a positive type photoresist film is formed on the SiN film 15. Then, the photoresist film is exposed to light from the rearside of the glass substrate 11, and further exposed from the frontside of the glass substrate 11 via a predetermined exposure mask. Thereafter, the photoresist film is subjected to a development process to form a resist film 42 covering channel protection film forming regions above the gate bus lines 12a.

Next, as shown in FIG. 9D, the SiN film 15 is etched using the resist film 42 as a mask to form the channel protection films 15a. Thereafter, the resist film 42 is removed.

Next, as shown in FIG. 9E, the n⁺ type amorphous silicon film 16 to be the ohmic contact layer is formed on the entire upper surface of the glass substrate 11. Thereafter, a metal film 17 to be the data bus lines, the source electrodes and the drain electrodes are formed by a PVD (Physical Vapor Deposition) method. Then, a resist film 45 of a predetermined pattern is formed on the metal film 17 using photoresist.

Next, as shown in FIG. 9F, the metal film 17, the n⁺ type amorphous silicon film 16 and the silicon film 14 are etched to secure the shape of the silicon film 14 to be the operating layer of the TFT 7. Simultaneously, the data bus lines 17a, the source electrodes 17s, the drain electrodes 17d, and the storage capacitor electrodes 17b are formed. At this time, part of the silicon film 14 intended to be a channel of the TFTs 7 is protected by the protection films 15a. Thereafter, the resist film 45 is removed.

Next, as shown in FIG. 9G, the final protection film 18 is formed on the entire upper surface of the glass substrate 11 using, for example, SiN. Then, a resist film 46 having contact hole forming parts opened thereon is formed on the final protection film 18.

Next, as shown in FIG. 9H, the final protection film 18 is etched using the resist film 46 as a mask to form contact holes 18a and 18b reaching the source electrode 17s and the storage capacitor electrode 17b, respectively. Thereafter, the resist film 46 is removed.

Next, as shown in FIG. 9I, the positive type photoresist film 19 is formed on the entire upper surface of the glass substrate 11, which is then subjected to exposure and development processes to form opening parts where the contact holes 18a and 18b are exposed and to divide the resist film 19 for each picture element. Subsequently, post-baking at a temperature of 130 to 145° C., the surface layer of the resist film 19 is further irradiated with a UV ray (ultraviolet ray) to crosslink the polymers in the surface layer. Next when baking at a temperature of 200° C. or more, since thermal deformation characteristics (coefficient of thermal expansion or of thermal shrinkage) between the surface layer (crosslinked part) and the deep part thereof (not crosslinked part) of the resist film 19 are different, fine wrinkle-form ruggedness is generated, as shown in FIG. 9J, on the surface of the resist film 19. In this case, as described before, the resist film 19 is divided into small regions for each picture element in this embodiment, and therefore the rugged pattern formed on the resist film 19 is ununiformalized D

14

Note that in this embodiment, only the surface layer of the resist film 19 is hardened by UV irradiation. However, inner stresses in the thickness direction of the resist film may be changed by irradiation of heat, plasma, UV, or ion beam.

Next, as shown in FIG. 9K, the entire upper surface of the glass substrate 11 is subjected to sputtering with Al to form a metal film 20. On the surface of the metal film 20 on the resist film 19, fine ruggedness is formed following that of the resist film 19. This metal film 20 is electrically connected to the source electrodes 17s and the storage capacitor electrodes 17b via contact holes 18a and 18b. Thereafter, a resist film 48 is formed in a predetermined pattern to secure the shapes of the reflection electrodes.

Subsequently, as shown in FIG. 9L, the metal film 20 is etched using the resist film 48 as a mask to form a reflection electrode 20a for each picture element. Thereafter, as shown in FIG. 9M, the resist film 48 is removed. Then, an alignment layer (not shown) made of polyimide and the like is formed on the entire upper surface of the glass substrate 11. In this way, the reflection electrodes 20a having finely rugged surfaces is formed.

Hereafter, a manufacturing method of the counter substrate 30 will be explained. First, a red color-photosensitive resin, a green color-photosensitive resin, and a blue color-photosensitive resin are used to form the color filters 32 on one face (on the lower face in FIG. 8) of the glass substrate 31.

Next, ITO is sputtered onto the color filters 32 to form the transparent common electrode 33. Then, the alignment layer 34 made of polyimide is formed on the common electrode 33, thereby completing the counter substrate 30.

Next, the spacers (not shown) are arranged for maintaining a constant interval between the TFT substrate 10 and the counter substrate 30, and the liquid crystal 40 is enclosed between the TFT substrate 10 and the counter substrate 30 using a vacuum injection method or a dropping injection method. In this way, the transmissive type liquid crystal display device as shown in FIGS. 7 and 8 is completed.

FIG. 10 is a view showing relations of transmissive aperture ratio and effective reflection area ratio to resolution, between the conventional transmissive type liquid crystal display device shown in FIG. 1 and the transmissive type liquid crystal display device of this embodiment, with the resolution (ppi) as the abscissa and with transmissive aperture ratio (left axis) and effective reflection area ratio (right axis) as the ordinate. Herein, in the conventional liquid crystal display device, the transmissive aperture ratio is fixed to be 14% regardless of the resolution. In addition, an inter-picture element interval is set to 8 f μ m, a width of the data bus lines is set to 5 f μ m, a width of the storage capacitor bus lines is set to 12 f μ m, and a width of the gate bus lines is set to 10 f μ m.

As shown in this FIG. 10, in the conventional liquid crystal display device, the effective reflection area ratio is about 74% when the resolution is 125 ppi, and as the resolution is higher, the effective reflection area ratio is decreased. Meanwhile, in the liquid crystal display device of this embodiment, the transmissive aperture ratio is about 14% and the effective reflection area ratio is about 85% when the resolution is 125 ppi, and thereby it is clarified that the effective reflection area ratio is large compared with the conventional example. Moreover, in this embodiment, when the resolution is about 180 ppi, the transmissive aperture ratio is about 18%, and the effective reflection area ratio is about 78%. In order to recognize small characters described in catalogues or the like, the resolution of 180 ppi or more is required. That is, from FIG. 10, it is found that the liquid crystal display device of this embodiment is good in reflection characteristics and trans-

15

mission characteristics, and excellent in visibility, even though having high resolution of about 180 ppi.

FIG. 11 shows microscopic images obtained by checking a reflection state and a transmission state at displaying when applied voltages are 0V and 2.3V, in the liquid crystal display device manufactured according to this embodiment. Herein, the resolution of this liquid crystal display device corresponds to 180 ppi, and a cell gap is 3 μm , and an n-type nematic liquid crystal is enclosed between the TFT substrate and the counter substrate after the vertical alignment of these substrates is subjected to rubbing treatment. A design values of a photo-mask used for manufacturing the liquid crystal display device is also shown in FIG. 11. Moreover, FIG. 12 shows an AFM (Atomic Force Microscope) image of the reflection electrodes of the liquid crystal display device. It is found from FIG. 11 that good characteristics can be obtained in any case of using the liquid crystal display device as a reflection type liquid crystal display device and as a transmission type liquid crystal display device.

Second Embodiment

FIG. 13A is a plan view showing a transfective type liquid crystal display device of a second embodiment of the present invention. This embodiment is different from the first embodiment in that the reflection electrode is provided with slits. The other structure is basically the same as that of the first embodiment, and therefore overlapping explanation will be omitted.

In this embodiment, as shown in FIG. 13A, a plurality of slits 52 are provided on a reflection electrode 51 and a resist film disposed thereunder, in parallel to the gate bus line 12a. That is, by these slits 52, the resist film is divided into a plurality of regions in one picture element.

As described before, a rugged pattern formed on the resist film is determined depending on the size of the resist film. Like this embodiment, by providing the slits 52 on the reflection electrode 51 and the resist film thereunder, a desired rugged pattern can be formed on the reflection electrode 51 even when the reflection electrode 51 is large in size. In addition, slit 52 portions serve as transmission regions, thereby heightening the transmissive aperture ratio. Slits 53 or 54 having the shapes as shown in FIGS. 13B and 13C, respectively, may also be formed according to a desired rugged pattern. In order to surely form ruggedness of a uniform pattern, any short side of the regions divided by the slits 52, 53 and 54 is preferably 5 μm .

FIG. 14 is a view showing relations of transmissive aperture ratio and effective reflection area ratio to resolution, between the conventional transfective type liquid crystal display device shown in FIG. 1 and the transfective type liquid crystal display device of this embodiment, with the resolution (ppi) as the abscissa and with transmissive aperture ratio (left axis) and effective reflection area ratio (right axis) as the ordinate. Herein, in the conventional liquid crystal display device, the transmissive aperture ratio is fixed to be 14% regardless of the resolution. In addition, an inter-pixel interval is set to 8 μm , a width of the data bus lines is set to 5 μm , a width of the storage capacitor bus lines is set to 12 μm , and a width of the gate bus lines is set to 10 μm .

As clarified from the FIG. 14, in this embodiment, ruggedness can be formed in a desired pattern even in the reflection type liquid crystal display device with a resolution of 125 ppi or less, and therefore the transfective type liquid crystal display device having high utilization efficiency of light is achieved.

16

FIG. 15 shows microscopic images obtained by checking a display state at displaying when applied voltages are 0V and 2.3V, in the liquid crystal display device manufactured according to this embodiment. Designed values of a photo-mask used for manufacturing the liquid crystal display device is also shown in FIG. 15. It is found from the FIG. 15 that uniform rugged patterns are formed for each picture element.

Third Embodiment

FIG. 16A is a plan view showing a transfective type liquid crystal display device of a third embodiment of the present invention. Note that this embodiment is different from the first embodiment in that the reflection electrode is not provided with a rugged surface, and the reflection electrode is provided with slits. The other structure is basically the same as that of the first embodiment, and therefore overlapping explanation will be omitted.

In this embodiment, as shown in FIG. 16A, a reflection electrode 61 is provided with slits 62, and slit 62 portions serve as transmission regions. Slits 63 and 64 in the shapes as shown in FIGS. 16B and 16C, respectively, may also be provided. However, the shapes of the slits are preferably common to each picture element. Moreover, any short side of the regions divided by the slits is preferably 5 μm or more.

In this embodiment, the reflection electrode 61 is formed so as to overlap the gate bus line 12a, the data bus line 17a, and the TFT 7. Moreover, the region between the adjacent reflection electrodes 61 serves as a light transmission region. Further, the reflection electrode 61 is provided with the slits 62 so as to serve as a light transmission region. Accordingly, in the liquid crystal display device of this embodiment, the transmissive aperture ratio is high compared with the conventional one, thereby improving the reflection characteristics as well as the transmission characteristics.

FIG. 17 shows microscopic images obtained by checking a display state at displaying when applied voltages are 0V and 2.3V, in the liquid crystal display device manufactured according to this embodiment. Design values of a photomask used in manufacturing the liquid crystal is also shown in FIG. 17. From the FIG. 17, according to this embodiment, it is found that the reflection type liquid crystal display device having high utilization efficiency of light and good visibility even when the resolution is 125 ppi or less, can be achieved.

Note that in any of the above first to third embodiments, explanation was given to the case of applying the present invention to the vertically aligned (VA) type liquid crystal display device. However, the application of the present invention is not thereby limited to the vertically aligned type liquid crystal display device. The present invention can also be applied to a horizontally aligned type liquid crystal display device, a hybrid alignment type liquid crystal display device and the like.

Fourth Embodiment

A liquid crystal display device according to a fourth embodiment of the present invention will be explained with reference to FIGS. 18 to 28. First, a first basic structure of the present invention, which is a presupposition of this embodiment, will be explained by use of FIGS. 18 to 28. FIG. 18 shows an outline structure of a liquid crystal display device according to this basic structure. As shown in FIG. 18, for example, the VA (Vertically Aligned) type liquid crystal display device has a structure in which a TFT substrate 202 and a counter substrate 204 are opposingly aligned with each other, and a liquid crystal 206 (not shown in FIG. 18) is

enclosed therebetween. The TFT substrate **202** has a picture element electrode, a TFT and the like formed thereon for each picture element region, and the counter substrate **204** has a CF (color filter) layer and the like formed thereon. The liquid crystal **206** has a negative dielectric anisotropy. On the oppos-

ing surfaces of the both substrates **202** and **204**, a vertically aligned film is formed for aligning liquid crystal molecules, for example, in the vertical direction to the surfaces of the substrates.

On the TFT substrate **202**, a gate bus line drive circuit **280** and a data bus line drive circuit **282** are provided. The gate bus line drive circuit **280** has a driver IC mounted thereon for driving a plurality of gate bus lines, and the data bus line drive circuit **282** has a driver IC mounted thereon for driving a plurality of data bus lines. Both of the drive circuits **280** and **282** are adapted to output scanning signals and display signals to the predetermined gate bus lines or data bus lines based on predetermined signals outputted from a control circuit **284**.

On the surface opposite to the element forming surface of the TFT substrate **202**, a polarizing plate **287** is stuck. On the other surface of the polarizing plate **287** on the opposite side to the TFT substrate **202**, for example, a backlight unit **288** including a linear primary light source and a surface light guide plate, is disposed. Meanwhile, on the other surface of the counter substrate **204** on the opposite side to the resin CF layer forming surface, a polarizing plate **286** is stuck. A linearly polarizing plate or the combination of a linearly polarizing plate and a $\frac{1}{4}$ -wavelength plate is used for the light polarizing plates **286** and **287**.

FIG. **19** shows a schematic sectional structure of three picture elements of the liquid crystal display device according to this basic structure. As shown in FIG. **19**, data bus lines **214**, extending in the vertical direction to the paper surface, are formed on a glass substrate **210** of the TFT substrate **202**. A flattening film **232** is formed on the data bus lines **214**. Note that an insulating film formed on the lower layer of the data bus line **214** is not shown. Reflection electrodes **216** are formed on the flattening film **232**. Ruggedness is formed on the surfaces of the reflection electrodes **216** so as to improve light reflection characteristics. The regions where the reflection electrodes **216** are formed to serve as reflection regions **R1**. In the reflection electrodes **216**, opening parts are formed. The regions where the opening parts are formed serve as transmission regions **T1**. The reflection region **R1** and the transmission region **T1** constitute a picture element region **P**. Note that the surface of the reflection electrode **216** is formed into a mirror plane, and a forward scattering film may be arranged on the display screen side.

On a glass substrate **211** of the counter substrate **204**, CF layers **R**, **G** and **B**, obtained by mixing a pigment or a dye with a transparent resin, are formed. Each layer of the CF layers **R**, **G**, and **B** is formed by a multilayered dielectric film, and functions as a wavelength selecting layer for selecting and transmitting the light of **R**, **G** or **B**, respectively. The CF layers **R**, **G**, and **B** are formed in the transmission regions **T1** of the picture elements **P**, extending up to a part of the reflection regions **R1**. The CF layers **R**, **G**, and **B** have the same color purity in the part of the reflection regions **R1** and in the transmission regions **T1**.

In this basic structure, the CF layers are formed in the part of the reflection regions **R1**, and in a reflection mode display, the light transmitting the CF layers twice and the light not transmitting the CF layers are mixed. Therefore, a display with high luminance can be obtained, and if the area ratio of the region of the reflection regions **R1** where the CF layers are formed to the entire reflection regions **R1** is adjusted, color purity at the time of displaying in the reflection mode can be

close to the color purity at the time of displaying in the transmission mode. Accordingly, the transfective type liquid crystal display device having good display quality can be achieved.

Moreover, in this basic structure, even though alignment deviation occurs between the TFT substrate **202** and the counter substrate **204**, if the area ratio of the region of the reflection regions **R1** where the CF layers are formed to the entire reflection regions **R1** is not changed, display characteristics at the time of displaying in the reflection mode are not changed. Moreover, if the area ratio of the region of the transmission regions **T1** where the CF layers are formed to the entire transmission regions **T1** (100% in this basic structure) is not changed, display characteristics at the time of displaying in the transmission mode is not changed. The CF layers are formed substantially around the transmission regions **T1** in a width larger than the width of the transmission regions **T1**, to prevent the above-described area ratio from changing even when the alignment deviation occurs. Therefore, sufficient alignment margins can be secured, thereby preventing the degradation in the display quality due to the alignment deviation.

Next, a liquid crystal display device according to a second basic structure of the present invention will be explained by use of FIG. **20**. FIG. **20** shows a schematic sectional structure of three picture elements of the liquid crystal display device according to this basic structure. As shown in FIG. **20**, the counter substrate **204** has CF layers **C** (cyan), **M** (magenta), and **Y** (yellow), which are complementary colors of **R**, **G** and **B**, for transmitting the light of the wavelengths of **C**, **M** and **Y**. Each color of **R**, **G** and **B** is displayed by the combinations of each color of **C**, **M** and **Y**.

The reflection electrodes **216** are formed so as to cover the data bus lines **214**. The regions where the reflection electrodes **216** are formed serve as reflection regions **R1**. In the reflection electrodes **216**, opening parts are formed. The regions where the opening parts are formed serve as transmission regions **T1**. Moreover, in this structure, the region from an edge of each reflection electrode **216** to substantially the central part of a gap region between the adjacent reflection electrodes **216**, is used as a transmission region **T2**. The reflection region **R1** and the transmission regions **T1** and **T2** constitute a picture element region **P**. The liquid crystal **206** in the transmission regions **T1** and **T2** is driven similarly to the liquid crystal **206** in the reflection regions **R1** in the same picture element regions **P**, by an oblique electric field between the reflection electrodes **216** and a common electrode (not shown).

Each layer of the CF layers **C**, **M**, and **Y** is formed in the transmission region **T1**, extending up to part of the reflection region **R1**. Moreover, in the transmission regions **T1** on the CF layers **C**, **M** and **Y**, the CF layers of different colors are laminated, extending up to both sides of the reflection regions **R1**. That is, layered parts where any two layers of the CF layers **C**, **M**, **Y** are laminated are formed in part of the reflection regions **R1** and the transmission regions **T1** of the picture element regions **P**. In the remaining regions of the reflection regions, single layer parts of only one layer of the CF layers **C**, **M** and **Y**, are formed. In the transmission region **T1** of a picture element displaying **R** (RED), two layers of the CF layers **M** and **Y** are sequentially laminated. In the transmission region **T1** of a picture element displaying **G** (GREEN), two layers of the CF layers **Y** and **C** are sequentially laminated. In the transmission region **T1** of a picture element displaying **B** (BLUE), two layers of the CF layers **C** and **M** are sequentially laminated. Note that the order of laminating the CF layers is not limited to the orders as described above.

Moreover, in the reflection regions R1 of a picture element displaying R, the CF layers M and Y are formed with almost the same areas. In the reflection regions R1 of a picture element displaying G, the CF layers Y and C are formed with almost the same areas. In the reflection regions R1 of a picture element displaying B, the CF layers C and M are formed with almost the same areas.

In this basic structure, single layers of the CF layers C, M and Y are formed in part of the reflection regions R1. For example, in a picture element displaying G, when displaying in the reflection mode, the light transmitted through a single layer part including the CF layer C, and the light transmitted through a single layer part including the CF layer Y, are mixed. The CF layer C absorbs the wavelength of R, and therefore the light transmitted through the CF layer C has the wavelengths of B and G. Moreover, the CF layer Y absorbs the wavelength of B, and therefore the light transmitted through the CF layer Y has the wavelengths of R and G. For this reason, the mixed light has a peak at the wavelength of G to be viewed by an observer of the display screen as a light of almost green. Meanwhile, when displaying in the transmission mode, the light transmitted through the layered part where the CF layers C and Y are laminated, has the wavelength of G.

Herein, the mixed light when displaying G in the reflection mode also has the wavelengths of R and B. Therefore, chromaticity deviation occurs between a reflection mode display of G and a transmission mode display of G. Therefore, layered parts with the same structure as that of the transmission regions T1 are arranged in part of the reflection regions R1. The area ratio of the region of the reflection regions R1 where the layered parts are arranged to the entire reflection regions R1 is adjusted, thereby making the color purity of the reflection mode display closer to the color purity of the transmission mode display. Thus, the transfective type liquid crystal display device with good display quality can be obtained.

Further, in this structure similarly to the first basic structure, even though alignment deviation occurs between the TFT substrate 202 and the counter substrate 204, if the area ratio of the region of the reflection regions R1 where the layered parts are arranged to the entire reflection regions R1 does not change, display characteristics in the reflection mode are not changed. Moreover, if the area ratio of the region of the transmission regions T1 where the layered parts are arranged to the entire transmission regions T1 (100% in this basic structure) does not change, display characteristics in the transmission mode are not changed. The layered parts are formed substantially around the transmission regions T1, in a width larger than the width of the transmission region T1, to prevent the above-described area ratio from changing even when alignment deviation occurs. Therefore, sufficient alignment margins can be secured, thereby preventing the degradation in the display quality due to the alignment deviation.

Next, a liquid crystal display device according to a third basic structure of the present invention will be explained with reference to FIGS. 21A and 21B. FIG. 21A shows a schematic sectional structure of the liquid crystal display device according to this basic structure. As shown in FIG. 21A, the CF layers R, G and B of the counter substrate 204 are formed in part of the reflection regions R1 and in the transmission regions T1 of the picture element regions. On the entire surface of the substrate on the CF layers R, G, and B, a flattening film 233 for flattening the ruggedness on the surface of the counter substrate 204, is formed. With this structure, turbulence of orientation of the liquid crystal 206 caused by the

ruggedness on the surface of the substrate can be suppressed, thereby improving orientation stability of the liquid crystal 206.

FIG. 21B shows another example of the schematic sectional structure of the liquid crystal display device according to this basic structure. As shown in FIG. 21B, on the counter substrate 204, layered parts including the laminates of the CF layers C, M and Y are formed in a part of the reflection regions R1 and in the transmission regions T1. Single layer parts of the CF layers C, M, and Y are formed in the transmission regions T1. On the entire surface of the substrate on the CF layers C, M and Y, the flattening film 233 for flattening the ruggedness on the surface of the counter substrate 204 is formed. With this structure, turbulence of the orientation of the liquid crystal 206 caused by the ruggedness on the surface of the substrate can be suppressed, thereby improving orientation stability of the liquid crystal 206.

Next, a liquid crystal display device according to a fourth basic structure of the present invention will be explained by use of FIGS. 22A and 22B. FIG. 22A shows a schematic sectional structure of the liquid crystal display device according to this basic structure. As shown in FIG. 22A, on the CF layers R, G, and B of the counter substrate 204, and in the regions other than the transmission regions T1, the flattening film 233 is formed. A cell thickness dt in the transmission regions T1 where no flattening film 233 is formed is about 1 to 2.3 times (preferably about 1.7 to 2.3 times) a cell thickness dr in the reflection regions R1 where the flattening film 233 is formed. When displaying in the transmission mode, the light incident from a backlight unit side passes the liquid crystal 206 only once to emit toward a display screen side. On the other hand, when displaying in the reflection mode, the light incident from the display screen side passes the liquid crystal 206, is reflected by the reflection electrodes 216, and passes the liquid crystal 206 again to be emit toward the display screen side. Specifically, in this basic structure, the cell thickness dt in the transmission regions T1 is made almost twice the cell thickness dr in the reflection regions R1. Accordingly, a substantial retardation ($\Delta n \cdot d$) generated in the liquid crystal 206 in the transmission mode display is made nearly the same as that generated in the reflection mode display. Therefore, according to this basic structure, almost the same display characteristics between both the modes of transmission and reflection can be obtained. Note that in this basic structure, by forming the flattening film 233 on the CF substrate 204 in the region other than the transmission regions T1, the cell thickness dt in the transmission regions T1 and the cell thickness dr in the reflection regions R1 are made different. However, using the flattening film 232 on the TFT substrate 202, the cell thicknesses dt and dr may be made different.

FIG. 22B shows another example of the schematic sectional structure of the liquid crystal display device according to this basic structure. As shown in FIG. 22B, on the CF layers C, M and Y of the counter substrate 204 and in the region other than the transmission regions T1, the flattening film 233 is formed. The cell thickness dt in the transmission regions T1 where no flattening film 233 is formed is about 1 to 2.3 times (preferably about 1.7 to 2.3 times) the cell thickness dr in the reflection regions R1 where the flattening film 233 is formed. According to this example also, almost the same display characteristics can be obtained in both the modes of transmission and reflection.

FIG. 23 shows further another example of the schematic sectional structure of the liquid crystal display device according to this basic structure. As shown in FIG. 23, on the CF layers C, M and Y of the counter substrate 204 and in the region other than the transmission regions T1 and T2, the

flattening film **233** is formed. A cell thickness $dt1$ in the transmission regions **T1** where no flattening film **233** is formed and a cell thickness $dt2$ in the transmission regions **T2** are about 1 to 2.3 times (preferably about 1.7 to 2.3 times) the cell thickness dr in the reflection regions **R1** where the flattening film **233** is formed. According to this example also, almost the same display characteristics can be obtained in both the modes of transmission and reflection.

Next, a liquid crystal display device according to example 1 of this embodiment will be explained by use of FIGS. **24A** and **24B**. FIG. **24A** shows a structure of the liquid crystal display device according to example 1, and FIG. **24B** shows an outline sectional structure of the liquid crystal display device taken along the line IV-IV of FIG. **24A**. As shown in FIGS. **24A** and **24B**, on the TFT substrate **202** of the liquid crystal display device, a plurality of gate bus lines **212** extending in right and left directions of FIG. **24A** in parallel with each other, are formed. In addition, on the TFT substrate **202**, a plurality of data bus lines **214**, intersecting the gate bus lines **212** via an insulating film (not shown), and extending in the vertical direction of FIG. **24A** in parallel with each other, are formed. In the vicinity of each intersection position of the gate bus line **212** and the data bus line **214**, a TFT **220** is formed. The TFT **220** has a working semiconductor film (not shown) made of a-Si (amorphous silicon) for example. On the working semiconductor film, a channel protection film (not shown) is formed. On the channel protection film, a drain electrode **221** led out from the adjacent data bus line **214**, and a source electrode **222** are formed so as to face each other interposing a predetermined gap therebetween. In this structure, the gate bus lines **212** directly under the channel protection film is adapted to function as a gate electrode of the TFT **220**.

In the regions surrounded by the gate bus lines **212** and the data bus lines **214**, the reflection electrodes **216** made of Al etc., are formed. The regions where the reflection electrodes **216** are formed serve as reflection regions. The reflection electrodes **216** are electrically connected to the source electrodes **222** via contact holes **224**. Parts of the reflection electrodes **216** are opened and transparent electrodes **217** made of ITO etc., are formed therein. The regions where the transparent electrodes **217** are formed serve as transmission regions. The reflection regions and the transmission regions constitute picture element regions. The reflection electrode **216** and the transparent electrode **217** in one picture element are electrically connected via a barrier metal layer **250**.

Further, on the TFT substrate **202**, storage capacitor bus lines **218**, crossing the picture element regions, are formed in parallel to the gate bus lines **212**. On the storage capacitor bus lines **218**, a storage capacitor electrode **219** is formed for each picture element region. The storage capacitor electrodes **219** are electrically connected to the reflection electrodes **216** via contact holes **226**.

On the glass substrate **211** of the CF substrate (counter substrate) **204**, any of the CF layers R, G and B for an LCD monitor is formed in part of the reflection regions and in the transmission regions. The CF layers R, G and B are formed with such a film thickness that good color purity can be obtained in the transmission mode display. A flattening film **233** is formed on the entire surface of the substrate on the CF layers R, G and B. A common electrode **252** is formed on the entire surface of the substrate on the flattening film **233**.

FIG. **25** is an x-y chromaticity chart of the liquid crystal display device of this example 1. A solid line a in the chart shows a color reproducing range (an ideal value) in the reflection mode of the liquid crystal display device in which the area ratio of the region of the reflection regions where the CF

layers are formed to the entire reflection regions is 90%. Similarly, a solid line b shows a color reproducing range of the liquid crystal display device having the above-described area ratio of 80% in the reflection mode, a solid line c shows a color reproducing range of the liquid crystal display device having the area ratio of 70% in the reflection mode, and a solid line d shows a color reproducing range of the liquid crystal display device having the above-described area ratio of 50% in the reflection mode. A broken line e shows a color reproducing range (an ideal value) of a conventional reflection type liquid crystal display device in which CF layers having the film thickness of 0.75 μm are used. As shown in FIG. **25**, according to example 1, by setting the above-described area ratio to 70% to 90%, a reflection mode display, in which the color reproducing range is wider than that of the conventional reflection type liquid crystal display device, can be obtained. In addition, since the CF layers for an LCD monitor are used in example 1, the same color reproducing range as that of the LCD monitor can be obtained in the transmission mode.

In example 1, similarly to the first basic structure, the CF layers are formed in part of the reflection regions, and in a reflection mode display, the light transmitted through the CF layers twice and the light not transmitted through the CF layers are mixed. Therefore, a display with high luminance can be obtained. Moreover, the area ratio of the region of the reflection regions where the CF layers are formed to the entire reflection regions is adjusted, thereby making the color purity in the reflection mode display closer to the color purity in the transmission mode display. Thus, the transreflective type liquid crystal display device with good display quality can be obtained.

Moreover, in example 1, similarly to the first basic structure, even though alignment deviation occurs between the TFT substrate **202** and the counter substrate **204**, if the area ratio of the region of the reflection regions where the CF layers are formed to the entire reflection regions is not changed, display characteristics in the reflection mode are not changed. Moreover, if the area ratio of the region of the transmission regions where the CF layers are formed to the entire transmission regions (100% in example 1) is not changed, display characteristics in the transmission mode are not changed. The CF layers are formed in a width wider than that of the transmission regions to prevent the above-described area ratio from changing even when the alignment deviation is generated. Therefore, sufficient alignment margins can be secured, thereby preventing the degradation in the display quality due to the alignment deviation.

Further, in example 1, the reflection electrodes **216** are formed so as to cover the TFTs **220** for driving the adjacent picture elements located on the lower side in FIG. **24A** and the gate bus lines **212**. Therefore, when a predetermined potential is written in the reflection electrodes **216**, voltage is not applied to the gate bus line **212** on the lower side of the reflection electrodes **216**. Instead, the voltage is applied to the adjacent gate bus line **212** on the upper side of the reflection electrodes **216**. Accordingly, a picture element potential is not affected by an electric field of the gate bus lines **212**, and therefore the occurrence of a flicker and a luminance inclination can be prevented.

In example 1, the reflection electrodes **216** are formed so as to cover the TFTs **220** for driving the adjacent picture elements on the lower side, and the gate bus lines **212**. However, the reflection electrodes **216** may be formed in the regions surrounded by the gate bus lines **212** and the data bus lines **214**. By applying example 1 to the structure of the conven-

23

tional liquid crystal display device shown in FIG. 1, the liquid crystal display device with good display quality can be obtained.

Next, a liquid crystal display device according to example 2 of this embodiment will be explained by use of FIGS. 26A and 26B. FIG. 26A shows a structure of the liquid crystal display device according to this example, and FIG. 26B shows an outline sectional structure of the liquid crystal display device taken along the line V-V of FIG. 26A. As shown in FIGS. 26A and 26B, the reflection electrodes 216 are formed so as to cover the data bus lines 214, the TFTs 220 for driving the adjacent picture elements located on the lower side in FIG. 26A, and the gate bus lines 212. The regions where the reflection electrodes 216 are formed serve as reflection regions. The regions between the adjacent reflection electrodes 216 are used as transmission regions. The liquid crystal 206 in the transmission regions is driven similarly to the liquid crystal 206 in the reflection regions, by an oblique electric field between the reflection electrodes 216 and a common electrode (not shown). In part of the reflection regions and in the transmission regions on the counter substrate 204, any one of the CF layers R, G and B is formed for each picture element. In the example 2 also, the effects similar to those in example 1 can be obtained. In addition, by applying example 2 to the structure of the conventional liquid crystal display device shown in FIGS. 2 and 3, the liquid crystal display device with good display quality can be obtained.

Next, a liquid crystal display device according to example 3 of this embodiment will be explained by use of FIGS. 27A and 27B. FIG. 27A shows a structure of the liquid crystal display device according to example 3, and FIG. 27B shows an outline sectional structure of the liquid crystal display device taken along the line VI-VI of FIG. 27A. As shown in FIGS. 27A and 27B, in the reflection electrodes 216, opening parts 260a to 260c opened in various shapes are formed. For example, in the reflection electrode 216 for the left picture element of three picture elements shown in FIG. 27A, a plurality of diamond-shaped opening parts 260a are formed. Moreover, a plurality of rectangular opening parts 260b having long sides almost in parallel to the extending direction of the gate bus lines 212, are formed in the reflection electrode 216 for the middle picture element of the three picture elements. In the reflection electrode 216 for the right picture element, a plurality of rectangular opening parts 260c having long sides almost in parallel to the extending direction of the data bus lines 214, are formed. The regions where the reflection electrodes 216 are formed serve as reflection regions, and the regions where the opening parts 260a to 260c are formed serve as transmission regions. The liquid crystal 206 in the transmission regions is driven similarly to the liquid crystal 206 in the reflection regions, by an oblique electric field between the reflection electrodes 216 and a common electrode (not shown).

In part of the reflection regions and in the transmission regions on the counter substrate 204, any one of the CF layers R, G and B is formed for each picture element. The reflection electrodes 216 are formed so as to cover the TFTs 220 for driving the adjacent picture elements located on the lower side in FIG. 27A and the gate bus lines 212. According to example 3, the effects similar to those in example 1 and example 2 can be obtained.

In example 3, the reflection electrodes 216 are formed so as to cover the TFTs 220 for driving the adjacent picture elements located on the lower side and the gate bus lines 212. However, the reflection electrodes 216 may be formed in the regions surrounded by the gate bus lines 212 and the data bus

24

lines 214. By applying example 3 to the structure of the conventional liquid crystal display device shown in FIG. 4, the liquid crystal display device with good display quality can be obtained.

Next, a liquid crystal display device according to example 4 of this embodiment will be explained by use of FIGS. 28A and 28B. FIG. 28A shows a structure of the liquid crystal display device according to example 4, and FIG. 28B shows an outline sectional structure of the liquid crystal display device taken along the line VII-VII of FIG. 28A. As shown in FIGS. 28A and 28B, the reflection electrodes 216 are formed so as to cover the gate bus lines 212, the data bus lines 214, and the TFTs 220. In the reflection electrodes 216, a plurality of opening parts 260 opened in a nearly elliptical shape are formed. The regions where the opening parts 260 are formed serve as transmission regions T1. The regions where the reflection electrodes 216 are formed serve as reflection regions. Moreover, the regions where the opening parts 260 are formed and the regions between the adjacent reflection electrodes 216 serve as transmission regions. The liquid crystal 206 in the transmission regions is driven similarly to the liquid crystal 206 in the reflection regions, by an oblique electric field between the reflection electrodes 216 and a common electrode (not shown).

The counter substrate 204 have the CF layers C, M and Y for transmitting the light having the wavelengths of C, M and Y which are complementary colors of R, G and B. The CF layers C, M, and Y constitute layered parts where two layers are laminated, in part of the reflection regions and in the transmission regions. Moreover, the CF layers C, M, and Y constitute single layer parts having only one layer in the other regions. In the transmission region of a picture element displaying R, two layers of the CF layers M and Y are laminated. In the transmission region of a picture element displaying G, two layers of the CF layers Y and C are laminated. In the transmission region of a picture element displaying B, two layers of the CF layers C and M are laminated. On the CF layers C, M, and Y, the flattening film 233 is formed. According to the example 4, the effects similar to those in example 1 to example 3 can be obtained. In addition, since the flattening film 233 is formed on the CF layers C, M, and Y, orientation stability of the liquid crystal 206 can be improved similarly to the third basic structure. Moreover, by applying example 4 to the structure of the conventional liquid crystal display device shown in FIG. 5, the liquid crystal display device with good display quality can be obtained.

As described above, according to this embodiment, the liquid crystal display device having high utilization efficiency of light and good display quality can be achieved at low cost.

Fifth Embodiment

Next, a liquid crystal display device according to the fifth embodiment of the present invention will be explained by use of FIGS. 29 and 30. FIG. 29 shows a structure of the liquid crystal display device according to this embodiment. Note that constituent components functioning similarly to those of the liquid crystal display device according to the fourth embodiment are designated by the same numerals and symbols, and explanation thereof is omitted. As shown in FIG. 29, the reflection electrodes 216a to 216e constituting the reflection regions of the transfective type liquid crystal display device are formed in the regions partitioned by the gate bus lines 212 and the data bus lines 214. In the reflection electrodes 216a, 216b, 216d, and 216e, opening parts 260a, 260b, 260d, and 260e, opened in various shapes such as a slit-like shape and a circular hole-like shape, are respectively formed.

Further, in the peripheral parts of the reflection electrodes **216a** to **216e**, notched parts **260a'** to **260e'**, cut into various shapes such as a slit-like shape and a circular or polygonal hole-like shape, are respectively formed.

For example, in the reflection electrode **216a**, one slit-shaped opening part **260a** extending almost in parallel to the long sides of the reflection electrode **216a**, and slit-shaped notched parts **260a'** cut inside from the two opposing long sides of the reflection electrode **216a** and extending obliquely to both the long sides, are formed. In the reflection electrode **216b**, a plurality of slit-shaped opening parts **260b** extending almost in parallel to the short sides of the reflection electrode **216b**, and a plurality of slit-shaped notched parts **260b'** cut inside from both the long sides of the reflection electrode **216b** and extending almost in parallel to the short sides of the reflection electrode **216b**, are formed. In the reflection electrode **216c**, a plurality of wedge-like notched parts **260c'** cut from both the long sides of the reflection electrode **216c** and extending almost in parallel to the short sides of the reflection electrode **216c**, are mutually adjacently formed. In the reflection electrode **216d**, a plurality of circular opening parts **260d**, and a plurality of circular notched parts **260d'** cut from both the short sides and both the long sides of the reflection electrode **216d**, are formed. In the reflection electrode **216e**, one slit-shaped opening part **260e** extending almost in parallel to the long sides of the reflection electrode **216e**, and a plurality of wedge-like notched parts **260e'** cut from both the long sides of the reflection electrode **216e** and extending almost in parallel to the short sides of the reflection electrode **216e**, are formed.

The regions where the reflection electrodes **216a** to **216e** are formed serve as reflection regions. The regions where the opening parts **260a**, **260b**, **260d**, and **260e** are formed, and the regions where the notched parts **260a'** to **260e'** of the peripheral parts of the reflection electrodes **216a** to **216e** serve as transmission regions. No transparent electrodes are formed in the opening parts **260a**, **260b**, **260d**, and **260e**, and in the notched parts **260a'** to **260e'**. Liquid crystal molecules in the transmission regions are driven almost similarly to the liquid crystal molecules in the reflection regions of the same picture element, by an oblique electric field between end portions of the reflection electrodes **216a** to **216e** and a common electrode **252** (not shown in FIG. 29) on a counter substrates **204** side.

In FIG. 29, the opening parts **260a**, **260b**, **260d**, and **260e** and the notched parts **260a'** to **260e'** are formed in different shapes for each picture element. However, all of the opening parts **260a**, **260b**, **260d**, and **260e** and the notched parts **260a'** to **260e'** may be formed in the same shapes for each picture element. In addition, each opening part **260a**, **260b**, **260d**, and **260e** and each notched part **260a'** to **260e'** may have a shape to restrict the alignment of the liquid crystal molecules. With this structure, in the liquid crystal display device of VA mode in which the liquid crystal molecules are aligned almost perpendicular to the substrates, alignment division dispensing with rubbing treatment of an alignment layer is enabled. Note that although rubbing treatment is required, this embodiment is applicable to the liquid crystal display devices of TN mode in which a horizontally aligned layer is used, and of HAN (Hybrid Aligned Nematic) mode in which horizontally aligned layer and vertically aligned layer are used. According to this embodiment, good transmission characteristics can be obtained compared with the conventional transmissive type liquid crystal display device shown in FIG. 4.

FIG. 30 shows a modified example of the structure of the liquid crystal display device according to this embodiment. As shown in FIG. 30, reflection electrodes **216f** to **216k** are

formed at intersection positions of both bus lines **212** and **214** and on the upper layer of the TFTs **220**. Moreover, in the reflection electrodes **216f** to **216k**, various-shaped opening parts **260i** and notched parts **260f'** to **260k'** are formed.

For example, in the reflection electrode **216f**, a plurality of the notched parts **260f'** cut from both the long sides and one of the short sides of the reflection electrode **216f** and extending obliquely to the long sides of the reflection electrode **216f**, are formed. In the reflection electrode **216g**, a plurality of the triangular notched parts **260g'** cut from both the long sides of the reflection electrode **216g** are formed. In the reflection electrode **216h**, a plurality of the wedge-like notched parts **260h'** cut from both the long sides of the reflection electrode **216h** and extending in parallel to the short sides of the reflection electrode **216h** are mutually adjacently formed. In the reflection electrode **216i**, a plurality of the hexagonal opening parts **260i** and a plurality of the hexagonal notched parts **260i'** cut from both the long sides of the reflection electrode **216i**, are formed. In the reflection electrode **216j**, a plurality of the slit-shaped notched parts **260j'** cut from the short sides of the reflection electrode **216j** and extending almost in parallel to the long sides of the reflection electrode **216j**, are formed. In the reflection electrode **216k**, a plurality of the slit-shaped notched parts **260k'** cut from both the long sides of the reflection electrode **216k** and extending almost in parallel to the short sides of the reflection electrode **216k**, are formed. Tip end portions of the notched parts **260k'** are formed into arcuate roundness.

The regions where the reflection electrodes **216f** to **216k** are formed serve as reflection regions. The regions where the opening parts **260i** are formed, the regions where the notched parts **260f'** to **260k'** of the peripheral parts of the reflection electrodes **216f** to **216k** are formed, and the regions around the reflection electrodes **216f** to **216k**, serve as transmission regions. According to this modified example, good transmission characteristics can be obtained compared with the conventional transmissive type liquid crystal display device shown in FIG. 5.

The present invention is not limited to the above-described fourth to fifth embodiments and can be variously modified.

For example, in the above embodiments, the bottom gate type substrate for a liquid crystal display device was exemplified. However, the present invention is not limited thereto and applicable also to a top gate type substrate for a liquid crystal display device.

Moreover, in the above fourth to fifth embodiments, the channel protection film type substrate for a liquid crystal display device was exemplified. However, the present invention is not limited thereto and applicable also to a channel etch type substrate for a liquid crystal display device.

Further, in the above fourth to fifth embodiments, the active matrix type liquid crystal display device was exemplified. However, the present invention is not limited thereto and applicable also to a simple matrix type liquid crystal display device.

Furthermore, in the above fourth to fifth embodiments, the liquid crystal display device having the CF layers formed on the counter substrate **204** oppositely arranged to the TFT substrate **202**, was exemplified. However, the present invention is not limited thereto and applicable also to a liquid crystal display device having a so-called CF-on-TFT structure, in which the CF layers are formed on the TFT substrate **202**.

Further, in the above fourth to fifth embodiments, the liquid crystal display device of VA mode was exemplified. However, the present invention is not limited thereto and applicable also

27

to other liquid crystal display devices of MVA (Multi-domain Vertical Alignment) mode, TN mode, HAN mode and the like.

In addition, in the above fourth to fifth embodiments, the CF layers were exemplified as wavelength selecting layers. However, the present invention is not limited thereto, and a cholesteric liquid crystal or the like in which the light of a specific wavelength is selectively reflected, may be used as a wavelength selecting layer.

The present invention is applicable to a MVA (Multi-domain Vertical Alignment) type liquid crystal display. In this case, a slit functions as a structure for a multi-domain. When voltage is impressed, the liquid crystal molecules of the both side of a slit incline in the different direction. Thereby, a multi-domain is attained. It is not necessary to rubbing, which can simplify the fabrication process.

What is claimed is:

1. A liquid crystal display device, comprising:
a pair of substrates opposingly arranged;
a liquid crystal enclosed between the pair of substrates;
a plurality of picture element regions, each including a reflection region having a reflection electrode formed on one of the pair of substrates and reflecting light incident from a side of the other substrate, and a transmission region transmitting light incident from a side of the one substrate, the transmission region being a region of a circumference part of the reflection electrode; and
wavelength selecting layers, each formed in the transmission region on the other substrate, extending up to part of the reflection region, and selecting and transmitting light having a predetermined wavelength.
2. The liquid crystal display device according to claim 1, further comprising second wavelength selecting layers, each formed in the transmission region on the first wavelength selecting layer and extending up to a part or whole of the transmission region.
3. The liquid crystal display device according to claim 2, wherein the wavelength selecting layers and the second wavelength selecting layers transmit lights having different wavelengths from each other.

28

4. The liquid crystal display device according to claim 1, wherein the wavelength selecting layers are color filter layers obtained by mixing a pigment or a dye with a transparent resin.

5. The liquid crystal display device according to claim 1, further comprising a flattening film formed on the wavelength selecting layers to flatten a surface of the substrate.

6. The liquid crystal display device according to claim 1, wherein the transmission region has a cell thickness thicker than a cell thickness in the reflection region.

7. The liquid crystal display device according to claim 6, wherein the transmission region has the cell thickness nearly twice the cell thickness in the reflection region.

8. The liquid crystal display device according to claim 1, wherein the reflection electrodes are formed at positions overlapping with the gate bus lines, the data bus lines, and the thin-film transistors.

9. The liquid crystal display device according to claim 1, wherein a structure for multi-domain is formed at least on one of the substrates.

10. A liquid crystal display device, comprising:

- a pair of substrates opposingly arranged;
 - a liquid crystal enclosed between the pair of substrates;
 - a plurality of picture element regions, each including a reflection region having a reflection electrode formed on one of the pair of substrates and reflecting light incident from a side of the other substrate, and a transmission region transmitting light incident from a side of the one substrate, the transmission region being a region of an opening part of the reflection electrode; and
 - wavelength selecting layers, each formed in the transmission region on the other substrate, extending up to part of the reflection region, and selecting and transmitting light having a predetermined wavelength,
- wherein a transparent electrode, which is electrically connected to the reflection electrode, is not formed in the transmission region on the one substrate.

* * * * *

专利名称(译)	液晶显示装置及其制造方法		
公开(公告)号	US7889296	公开(公告)日	2011-02-15
申请号	US11/708796	申请日	2007-02-21
[标]申请(专利权)人(译)	OHMURO KATSUFUMI 杉浦NORIO 田代国广 小池YOSHIO		
申请(专利权)人(译)	OHMURO KATSUFUMI 杉浦NORIO 田代国广 小池YOSHIO		
当前申请(专利权)人(译)	夏普株式会社		
[标]发明人	OHMURO KATSUFUMI SUGIURA NORIO TASHIRO KUNIHIRO KOIKE YOSHIO		
发明人	OHMURO, KATSUFUMI SUGIURA, NORIO TASHIRO, KUNIHIRO KOIKE, YOSHIO		
IPC分类号	G02F1/1335 G09G3/36		
CPC分类号	G02F1/133371 G02F1/133514 G02F1/133553 G02F1/133555 G02F1/133707 G02F1/133753 G02F1/1393 G02F2203/09		
审查员(译)	内尔姆斯, DAVID		
优先权	2002323073 2002-11-06 JP 2002347077 2002-11-29 JP		
其他公开文献	US20070146594A1		
外部链接	Espacenet USPTO		

摘要(译)

在玻璃基板上,形成栅极总线,数据总线和TFT。然后,在基板上,形成覆盖栅极总线,数据总线和TFT的绝缘膜,并在其上进一步形成正型光致抗蚀剂膜。接下来,通过曝光和显影工艺,对每个像素分割抗蚀剂膜并进行紫外线照射以仅硬化其表面层。然后,对抗蚀剂膜进行热处理,在其上形成均匀图案的皱纹状表面粗糙度,这取决于抗蚀剂膜的尺寸。随后,在抗蚀剂膜上形成反射电极。形成反射电极以与栅极总线,数据总线和TFT重叠,并且相邻反射电极之间的区域用作光透射区域。

