



US010564467B2

(12) **United States Patent**  
**Kang et al.**

(10) **Patent No.:** **US 10,564,467 B2**  
(45) **Date of Patent:** **Feb. 18, 2020**

(54) **LIQUID CRYSTAL DISPLAY DEVICE AND  
METHOD FOR DRIVING THE SAME**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin-si  
(KR)

(72) Inventors: **Jong Hyuk Kang**, Suwon-si (KR);  
**Hyun Min Cho**, Seoul (KR); **Jae  
Byung Park**, Seoul (KR); **Jae Woong  
Kang**, Jeonju-si (KR); **Dae Hyun Kim**,  
Hwaseong-si (KR); **Suk Sun Lee**,  
Yongin-si (KR); **Joo Yeol Lee**, Seoul  
(KR); **Hyun Deok Im**, Seoul (KR);  
**Sung-Jin Hong**, Hwaseong-si (KR)

(73) Assignee: **Samsung Display Co., Ltd.**, Yongin-si  
(KR)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 4 days.

(21) Appl. No.: **14/993,743**

(22) Filed: **Jan. 12, 2016**

(65) **Prior Publication Data**

US 2016/0320664 A1 Nov. 3, 2016

(30) **Foreign Application Priority Data**

Apr. 30, 2015 (KR) ..... 10-2015-0062037

(51) **Int. Cl.**  
**G02F 1/1335** (2006.01)

(52) **U.S. Cl.**  
CPC .. **G02F 1/133528** (2013.01); **G02F 1/133621**  
(2013.01)

(58) **Field of Classification Search**  
CPC ..... G02F 1/133528; G02F 1/1368; G02F  
1/133621; G02F 1/133512;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,471,969 B2 6/2013 Banin et al.  
8,760,605 B2 6/2014 Cho et al.  
(Continued)

FOREIGN PATENT DOCUMENTS

KR 1020130047198 5/2013  
KR 1020130047199 5/2013  
(Continued)

OTHER PUBLICATIONS

Bruhn, et al., "Controlled fabrication of individual silicon quantum  
rods yielding high intensity, polarized light emission", Nanotech-  
nology, Nov. 19, 2009, pp. 1-5, 20, 505301, IOP Publishing Ltd,  
UK.

(Continued)

*Primary Examiner* — Paisley L Wilson


*Assistant Examiner* — Mariam Qureshi

(74) *Attorney, Agent, or Firm* — H.C. Park & Associates,  
PLC

(57) **ABSTRACT**

A liquid crystal display device which may prevent a color  
mixing phenomenon and a driving method thereof, the  
liquid crystal display device including a first substrate and a  
second substrate facing each other; a thin film transistor  
disposed inside the first substrate; a color conversion layer  
disposed inside the second substrate and including a plural-  
ity of quantum rods; a liquid crystal layer disposed between  
the first substrate and the second substrate; a first polarizer  
disposed outside the first substrate; and a second polarizer  
disposed outside the second substrate.

**13 Claims, 23 Drawing Sheets**



(58) **Field of Classification Search**

CPC ..... G02F 2001/133614; G02F 2001/133531;  
G02F 1/13394; G02F 2001/13398; G02F  
1/133553

See application file for complete search history.

2016/0223863 A1\* 8/2016 Mizunuma ..... G02F 1/133617  
2016/0223870 A1\* 8/2016 Miki ..... G02F 1/133617  
2016/0266450 A1\* 9/2016 Kim ..... G02F 1/133514  
2017/0108726 A1\* 4/2017 Yanai ..... G02F 1/13362

(56)

**References Cited**

## U.S. PATENT DOCUMENTS

8,902,384 B2 12/2014 Jeon et al.  
2013/0107170 A1 5/2013 Gee et al.  
2013/0135558 A1\* 5/2013 Kim ..... G02F 1/133528  
349/62  
2013/0242228 A1\* 9/2013 Park ..... G02F 1/133617  
349/61  
2013/0335799 A1\* 12/2013 Yoon ..... G02B 26/02  
359/227  
2014/0160408 A1 6/2014 Cho et al.  
2016/0070136 A1\* 3/2016 Jang ..... G02F 1/133514  
349/61  
2016/0091757 A1\* 3/2016 Miki ..... G02F 1/133617  
349/42

## FOREIGN PATENT DOCUMENTS

KR 1020130059222 6/2013  
KR 1020130140462 12/2013  
KR 101347896 1/2014  
KR 1020140000735 1/2014  
KR 1020140074495 6/2014  
WO 2010095140 8/2010

## OTHER PUBLICATIONS

Hu et al., "Linearly Polarized Emission from Colloidal Semicon-  
ductor Quantum Rods", Science, Jun. 15, 2001, pp. 2060-2063, vol.  
292, American Association for the Advancement of Science, Wash-  
ington DC, USA.

\* cited by examiner

FIG. 1






FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8






FIG. 9




240a } 240  
240b }

FIG. 10




240a } 240  
240b }

FIG. 11



240a } 240  
240b }

FIG. 12



240a } 240  
240b }



FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22





FIG. 23



# LIQUID CRYSTAL DISPLAY DEVICE AND METHOD FOR DRIVING THE SAME

## CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority from and the benefit of Korean Patent Application No. 10-2015-0062037, filed on Apr. 30, 2015, which is hereby incorporated by reference for all purposes as if fully set forth herein.

## BACKGROUND

### Field

Exemplary embodiments relate to a liquid crystal display device and a driving method thereof and, more particularly, to a liquid crystal display device which may prevent a color mixing phenomenon and a driving method thereof.

### Discussion of the Background

A liquid crystal display device, which is one of the most common types of flat panel displays currently in use, includes two sheets of display panels with field generating electrodes, such as a pixel electrode and a common electrode, formed thereon, and a liquid crystal layer interposed therebetween. An electric field is generated in a liquid crystal layer by applying a voltage to the field generating electrodes, and the orientation of liquid crystal molecules in the liquid crystal layer is determined by the generated electric field, thereby controlling polarization of incident light so as to display images.

Two sheets of display panels which form the liquid crystal display device may be configured by a thin film transistor display panel and an opposing display panel. In the thin film transistor display panel, a gate line that transmits a gate signal and a data line that transmits a data signal may be formed to intersect each other. The thin film transistor display panel also includes a thin film transistor connected to the gate line and the data line, and a pixel electrode connected to the thin film transistor. In the opposing display panel, a light blocking member, a color filter, and a common electrode may be formed. In some cases, the light blocking member, the color filter, and the common electrode may be formed in the thin film transistor display panel.

Recently, a liquid crystal display device having a structure which uses a quantum material to convert a color of light emitted from a light source, thereby omitting any need for a color filter, has been developed. However, a liquid crystal display device having such a structure suffers from a problem of a color mixing phenomenon, which results from the relatively long distance between a liquid crystal layer and a color conversion layer.

The above information disclosed in this Background section is only for enhancement of understanding of the background of the inventive concept, and, therefore, it may contain information that does not form the prior art that is already known in this country to a person of ordinary skill in the art.

## SUMMARY

Exemplary embodiments provide a liquid crystal display device which may prevent a color mixing phenomenon and a driving method thereof.

Additional aspects will be set forth in the detailed description which follows, and, in part, will be apparent from the disclosure, or may be learned by practice of the inventive concept.

An exemplary embodiment of the present invention discloses a liquid crystal display device including a first substrate and a second substrate facing each other; a thin film transistor disposed inside the first substrate; a color conversion layer disposed inside the second substrate and including a plurality of quantum rods; a liquid crystal layer disposed between the first substrate and the second substrate; a first polarizer disposed outside the first substrate; and a second polarizer disposed outside the second substrate.

An exemplary embodiment of the present invention also discloses a driving method of a liquid crystal display device including: providing light to a first polarizer of the liquid crystal display device; applying a voltage to a liquid crystal layer to control a polarization direction of light which passes through the first polarizer; adjusting a quantity of light which passes through the liquid crystal layer while passing through a color conversion layer including a plurality of quantum rods; and passing the light which passes through the color conversion layer through the second polarization layer.

The foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the claimed subject matter.

## BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the inventive concept, and are incorporated in and constitute a part of this specification, illustrate exemplary embodiments of the inventive concept, and, together with the description, serve to explain principles of the inventive concept.

FIG. 1 is a perspective view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 2 is a cross-sectional view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 3 is a view illustrating a polarization characteristic of a quantum dot.

FIG. 4 is a view illustrating a polarization characteristic of a quantum rod.

FIG. 5 is a cross-sectional view illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

FIGS. 6 to 13 are cross-sectional views of a process of a manufacturing method of a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 14 is a cross-sectional view schematically illustrating a liquid crystal display device according to a first comparative example.

FIG. 15 is a cross-sectional view schematically illustrating a liquid crystal display device according to a second comparative example.

FIG. 16 is a cross-sectional view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 17 is a result of simulation of color reproducibility according to an exemplary embodiment of the present invention.

FIG. 18 is a view illustrating a polarization direction of light which passes through each constituent element of a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 19 is a graph illustrating absorbance and light emittance in accordance with an angle formed by a polarization direction of incident light and an alignment direction of a quantum rod.

FIG. 20, FIG. 21, and FIG. 22 are views illustrating a polarization direction of light which passes through each constituent element of a liquid crystal display device according to an exemplary embodiment of the present invention.

FIG. 23 is a graph illustrating luminance in accordance with a polarization angle of liquid crystal.

#### DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various exemplary embodiments. It is apparent, however, that various exemplary embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various exemplary embodiments.

In the accompanying figures, the size and relative sizes of layers, films, panels, regions, etc., may be exaggerated for clarity and descriptive purposes. Also, like reference numerals denote like elements.

When an element or layer is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. For the purposes of this disclosure, “at least one of X, Y, and Z” and “at least one selected from the group consisting of X, Y, and Z” may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, XYY, YZ, and ZZ. Like numbers refer to like elements throughout. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

Although the terms first, second, etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are used to distinguish one element, component, region, layer, and/or section from another element, component, region, layer, and/or section. Thus, a first element, component, region, layer, and/or section discussed below could be termed a second element, component, region, layer, and/or section without departing from the teachings of the present disclosure.

Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper,” and the like, may be used herein for descriptive purposes, and, thereby, to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the

apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. Moreover, the terms “comprises,” “comprising,” “includes,” and/or “including,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

Various exemplary embodiments are described herein with reference to sectional illustrations that are schematic illustrations of idealized exemplary embodiments and/or intermediate structures. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, exemplary embodiments disclosed herein should not be construed as limited to the particular illustrated shapes of regions, but are to include deviations in shapes that result from, for instance, manufacturing. For example, an implanted region illustrated as a rectangle will, typically, have rounded or curved features and/or a gradient of implant concentration at its edges rather than a binary change from implanted to non-implanted region. Likewise, a buried region formed by implantation may result in some implantation in the region between the buried region and the surface through which the implantation takes place. Thus, the regions illustrated in the drawings are schematic in nature and their shapes are not intended to illustrate the actual shape of a region of a device and are not intended to be limiting.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

FIG. 1 is a perspective view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention, and FIG. 2 is a cross-sectional view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention. FIGS. 1 and 2 illustrate polarization states of light which passes through individual layers.

As illustrated in FIGS. 1 and 2, a liquid crystal display device according to an exemplary embodiment of the present invention includes a thin film transistor array panel 100 and an opposing display panel 200 which face each other, and a liquid crystal layer 3 is disposed between the thin film transistor array panel 100 and the opposing display panel 200.

The thin film transistor array panel 100 includes a first substrate 110 and a thin film transistor layer 120 disposed on the first substrate 110. The thin film transistor layer 120 is simplified and specific constituent elements will be described below. A first polarizer 12 is disposed outside the thin film transistor array panel 100.

The opposing display panel 200 includes a second substrate 210 and a color conversion layer 240 disposed on the

second substrate **210**. A second polarizer **22** is disposed outside the opposing display panel **200**.

The first polarizer **12** and the second polarizer **22** have a transmissive axis and an absorption axis. For light that is incident onto the first polarizer **12** and the second polarizer **22**, a light component which is parallel to a transmissive axis passes therethrough, and a light component that is parallel to an absorption axis does not pass therethrough. The transmissive axis of the first polarizer **12** is perpendicular to the transmissive axis of the second polarizer **22**.

The color conversion layer **240** includes a first color conversion layer **240a**, which includes a plurality of first quantum rods **250a**, and a second color conversion layer **240b**, which includes a plurality of second quantum rods **250b**. The first quantum rod **250a** and the second quantum rod **250b** are formed of a quantum material having a nano-size rod shape. The quantum material may change a wavelength of light. The first quantum rod **250a** is formed of a material which converts the incident light into red light, and the second quantum rod **250b** is formed of a material which converts the incident light into green light. The first quantum rod **250a** and the second quantum rod **250b** have predetermined directivities. The first quantum rod **250a** and the second quantum rod **250b** are arranged in a predetermined direction, and a rod shaped length direction is referred to as an "arrangement direction".

The first substrate **110** and the second substrate **210** include a first color pixel area PX(R), a second color pixel area PX(G), and a third color pixel area PX(B). The first color conversion layer **240a** is disposed in the first color pixel area PX(R), and the light which is incident onto the first color conversion layer **240a** is converted into red light and escapes the first color conversion layer **240a**. The second color conversion layer **240b** is disposed in the second color pixel area PX(G), and the light which is incident onto the second color conversion layer **240b** is converted into green light and escapes the second color conversion layer **240b**. A transparent photo resist **242** is disposed on the third color pixel area PX(B). The transparent photo resist **242** is transparent and light which is incident onto the transparent photo resist **242** escapes the transparent photo resist. The transparent photo resist **242** is disposed on the same layer as the first color conversion layer **240a** and the second color conversion layer **240b**.

Partitions **260** are formed between the first color conversion layer **240a** and the second color conversion layer **240b**, between the second color conversion layer **240b** and the transparent photo resist **242**, and between the transparent photo resist **242** and the first color conversion layer **240a**. That is, the partitions **260** are disposed at boundaries between the pixel areas PX(R), PX(G), and PX(B).

The first blue light blocking filter **230a** and the second blue light blocking filter **230b** are disposed on the second substrate **210**. The first blue light blocking filter **230a** is disposed in the first color pixel area PX(R) and between the second substrate **210** and the first color conversion layer **240a**. The second blue light blocking filter **230b** is disposed in the second color pixel area PX(G) and between the second substrate **210** and the second color conversion layer **240b**. The first blue light blocking filter **230a** and the second blue light blocking filter **230b** block the blue light by absorbing or reflecting the blue light component so that the block light component does not pass therethrough. The first blue light blocking filter **230a** passes the red light and blocks the blue light. The second blue light blocking filter **230b** passes the green light and blocks the blue light.

A blue band pass filter **267** is formed on the first color conversion layer **240a**, the second color conversion layer **240b**, and the transparent photo resist **242**. The blue band pass filter **267** is formed in the first color pixel area PX(R), the second color pixel area PX(G), and the third color pixel area PX(B). The blue band pass filter **267** is disposed between the first color conversion layer **240a** and the liquid crystal layer **3**, between the second color conversion layer **240b** and the liquid crystal layer **3**, and between the transparent photo resist **242** and the liquid crystal layer **3**. The blue band pass filter **267** is a filter which passes the blue light as it is.

The liquid crystal display device further includes a light source **500**, and light emitted from the light source **500** passes through the first polarizer **12** to be incident onto the first substrate **110**. The light source **500** may emit blue light and, for example, may be formed of a blue light emitting diode (LED).

Hereinafter, a polarization state of light which passes through the liquid crystal display device according to exemplary embodiments of the present invention will be described.

The light emitted from the light source **500** is non-polarized light and includes both a component which vibrates in a horizontal direction a component which vibrates in a vertical direction. Two components of the light are represented by a dotted line and a solid line in FIG. 1, and represented by an arrow in a horizontal direction and an arrow in a direction extending outward from the sheet in FIG. 2.

The non-polarized light provided from the light source **500** is changed into a polarized light while passing through the first polarizer **12**. A component which vibrates in a direction parallel to the transmissive axis of the first polarizer **12** passes through the first polarizer and a component which vibrates in a direction perpendicular to the transmissive axis is blocked. The transmissive axis of the first polarizer **12** may be in a vertical direction, and the component which vibrates in a horizontal direction is blocked and the component which vibrates in a vertical direction passes therethrough.

A polarization direction of the light which passes through the first polarizer **12** is changed while passing through the liquid crystal layer **3**. In this case, a variation of the polarization direction may be adjusted by adjusting a voltage which is applied to the liquid crystal layer **3**. FIGS. 1 and 2 illustrate that the polarization direction is changed by 90 degrees. Accordingly, when the light that is incident onto the liquid crystal layer **3** is formed of only a component which vibrates in the vertical direction, the light which passes through the liquid crystal layer **3** may be formed of a component which vibrates in the horizontal direction.

A wavelength of the light that passes through the liquid crystal layer **3** is changed while the light passes through the color conversion layer **240**. A blue light component of the light that passes through the first color conversion layer **240a** is changed into a red light component by the first quantum rod **250a**. A blue light component of the light that passes through the second color conversion layer **240b** is changed into a green light component by the second quantum rod **250b**. That is, the red light component is emitted from the first color pixel area PX(R) and the green light component is emitted from the second color pixel area PX(G). Because the transparent photo resist is formed in the third color pixel area PX(B) instead of the color conversion layer **240**, the blue light component passes therethrough without changing the wavelength of the light.

The light that passes through the first color conversion layer **240a** is mostly formed of the red light component, but may partially include the blue light component. When the blue light component passes therethrough as it is, not only red but also blue is disposed in the red pixel area PX(R). In this case, even though a user does not want to display blue, blue may be displayed. In the exemplary embodiment of the present invention, the first blue light blocking filter **230a** blocks the blue light component which passes through the first color conversion layer **240a**. The first blue light blocking filter **230a** absorbs or reflects the blue light component.

The light which passes through the second color conversion layer **240b** may be mostly formed of a green light component, but may partially include the blue light component. When the blue light component passes therethrough, not only green but also blue is disposed in the red pixel area PX(G). In this case, even though the user does not want to display blue, blue may be displayed. In the exemplary embodiment of the present invention, the second blue light blocking filter **230b** blocks the blue light component which passes through the second color conversion layer **240b**.

A propagation direction of some of the red light component whose wavelength is changed while passing through the first color conversion layer **240a** is changed so that some of the red light component may reach the blue band pass filter **267**. Further, a propagation direction of some of the green light component whose wavelength is changed while passing through the second color conversion layer **240b** is changed so that some of the green light component may reach the blue band pass filter **267**. In this case, the blue band pass filter **267** passes only the blue light component and reflects the red light component and the green light component to get out of the first color conversion layer **240a** and the second color conversion layer **240b**. The blue light component that is reflected by the first blue light blocking filter **230a** and the second blue light blocking filter **230b** may pass through the blue band pass filter **267**.

Of the light which passes through the first color conversion layer **240a**, the second color conversion layer **240b**, and the transparent photo resist **242**, only a component which vibrates in a direction parallel to the transmissive axis of the second polarizer **22** passes therethrough while passing through the second polarizer **22**. The transmissive axis of the second polarizer **22** is perpendicular to the transmissive axis of the first polarizer **12**. Therefore, the transmissive axis of the second polarizer **22** may be formed in a horizontal direction while a component which vibrates in a vertical direction is blocked, and a component which vibrates in a horizontal direction passes therethrough. In FIGS. 1 and 2, the light which passes through the liquid crystal layer **3** is formed of the component which vibrates in the horizontal direction so as to entirely pass through the second polarizer **22**.

Finally, the red light component is emitted from the first color pixel area PX(R), the green light component is emitted from the second color pixel area PX(G), and the blue light component is emitted from the third color pixel area PX(B), and a quantity of light is adjusted to display a screen.

Hereinafter, a quantum dot DQ and a polarization characteristic of a quantum rod QR will be described with reference to FIGS. 3 and 4.

FIG. 3 is a view illustrating a polarization characteristic of a quantum dot and FIG. 4 is a view illustrating a polarization characteristic of a quantum rod.

A quantum dot QD is a particle formed by several hundred to several thousands of atoms and refers to a semiconductor crystal obtained by composing the quantum in the unit of

nanometers (nm). The light that is incident onto the quantum dot QD is changed into light having a different wavelength and then emitted. According to a principle of the quantum dot QD, when energy, such as ultraviolet radiation, is applied to electrons in the semiconductor material made by quantum, the electrons repeatedly jump to a high energy level by a quantum jump and then drop to a low energy level by emitting the energy. The energy emitted has various wavelengths in accordance with a size of a quantum dot. When a region of the wavelength (energy) is a visible band region (380 nm to 800 nm), various visible colors are emitted at a wavelength in the form of energy. In the case of the quantum dot QD, as illustrated in FIG. 3, even though the incident light is polarized light, the emitted light is formed of non-polarized light.

The quantum rod QR has a characteristic which changes a wavelength of light, similarly to the quantum dot QD. However, the quantum rod QR has directivity, which is different from the quantum dot QD. As described above, the quantum rod QR has a rod shape, and a plurality of quantum rods may be arranged in a predetermined direction. In the case of the quantum rod QR, as illustrated in FIG. 4, the emitted light is formed of polarized light. In this case, the quantity of passing light varies depending on an angle formed by the polarization direction of the incident light and an arrangement direction of the quantum rod QR. As an angle formed by the polarization direction of the incident light and an arrangement direction of the quantum rod QR approaches zero, the quantity of passing light is increased and, as the angle approaches 90 degrees, the quantity of passing light is reduced.

For comparison, it is assumed that in the liquid crystal display device according to the exemplary embodiment of the present invention, the quantum dot QD is included in the color conversion layer **240** instead of the quantum rod QR. In such a comparative example, regardless of the polarization direction of the light which passes through the liquid crystal layer, the light which passes through the color conversion layer is formed of non-polarized light, and the quantity of light is the same as in the exemplary embodiment. Accordingly, transmittance may be adjusted for every pixel, and the second polarizer needs to be disposed between the liquid crystal layer and the color conversion layer in order to control the transmittance for every pixel. However, when the second polarizer is disposed between the liquid crystal layer and the color conversion layer, a distance between the liquid crystal layer and the color conversion layer is increased, and the light which passes through the pixel affects adjacent pixels, which may undesirably cause a color mixing phenomenon. For example, most of light which passes through the liquid crystal layer in the first color pixel area passes through the first color conversion layer to display red, but the remaining light component escapes through the second color pixel area or the third color pixel area, which are adjacent to the first color pixel area, and displays green or blue.

In the liquid crystal display device according to the exemplary embodiment of the present invention, a quantity of light which passes through the color conversion layer **240** may be adjusted in accordance with a polarization direction of light which passes through the liquid crystal layer **3**. Accordingly, the second polarizer **22** may be disposed outside the second substrate **210** and, thus, the distance between the liquid crystal layer **3** and the color conversion layer **240** may be reduced as compared with the comparative example. Therefore, a color mixing phenomenon may be prevented.

Hereinafter, a structure of the liquid crystal display device according to an exemplary embodiment of the present invention will be further described with reference to FIG. 5.

FIG. 5 is a cross-sectional view illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

As illustrated in FIG. 5, a liquid crystal display device according to an exemplary embodiment of the present invention includes a thin film transistor array panel **100** and an opposing display panel **200** which face each other, and a liquid crystal layer **3** is disposed between the thin film transistor array panel **100** and the opposing display panel **200**.

First, the thin film transistor array panel **100** will be described.

The gate electrode **124** is disposed on a first substrate **110** which is formed of a material such as transparent glass or plastic. Even though not illustrated, a gate line is formed on the first substrate **110** and the gate electrode **124** is connected to the gate line. A gate voltage is applied to the gate line and the gate voltage is transmitted to the gate electrode **124**.

A gate insulating layer **140** is formed on the gate electrode **124**. The gate insulating layer **140** may be formed of an inorganic insulating material, such as silicon nitride (SiN<sub>x</sub>) or silicon oxide (SiO<sub>x</sub>). Further, the gate insulating layer **140** may be formed as either a single layer or a multilayer.

A semiconductor **154** is formed on the gate insulating layer **140**. The semiconductor **154** may be formed on the gate electrode **124**. In some cases, the semiconductor **154** may be disposed below the data line **171**. The semiconductor **154** may be formed of amorphous silicon, polycrystalline silicon, or metal oxide.

An ohmic contact member (not illustrated) may be further formed on the semiconductor **154**. The ohmic contact may be formed of a material, such as n+ hydrogenated amorphous silicon, in which silicide or n-type impurity is doped at a high concentration.

A source electrode **173** and a drain electrode **175** are formed on the semiconductor **154**. The source electrode **173** and the drain electrode **175** are spaced apart from each other. Even though not illustrated, a data line is formed on the semiconductor **154** and the gate insulating layer **140** and the source electrode **173** is connected to the data line. A data signal is applied to the data line and the data signal is transmitted to the source electrode **173**.

The gate electrode **124**, the source electrode **173**, and the drain electrode **175** form a thin film transistor TFT together with the semiconductor **154**. The thin film transistor may serve as a switching element which transmits the data voltage which is applied to the data line. A channel of the thin film transistor is formed in the semiconductor between the source electrode **173** and the drain electrode **175**. When a gate-on voltage is applied to the gate electrode **124**, the thin film transistor is turned on and the data voltage which is applied to the source electrode **173** is transmitted to the drain electrode **175**.

A passivation layer **180** is formed on the source electrode **173**, the drain electrode **175**, and the semiconductor **154**. The passivation layer **180** may be formed of an organic insulating material or an inorganic insulating material, and may be formed as either a single layer or a multilayer.

A contact hole **185** is formed in the passivation layer **180**, and the contact hole **185** exposes at least a part of the drain electrode **175**.

A pixel electrode **191** is formed on the passivation layer **180**, and the pixel electrode **191** is connected to the drain electrode **175** through the contact hole **185**. The pixel

electrode **191** may be formed of transparent metal oxide, such as indium tin oxide (ITO) or indium zinc oxide (IZO).

A first polarizer **12** is disposed below the first substrate **110**. The first polarizer **12** may be attached to the outside of the first substrate **110**.

Next, the opposing display panel **200** will be described.

A light blocking member **220** is formed on the second substrate **210** which is formed of a material such as transparent glass or plastic. The first substrate **110** and the second substrate **210** face each other and, in this case, an inner surface of the first substrate **110** is considered as an upper surface and an outer surface thereof is considered as a lower surface, and an inner surface of the second substrate **210** is considered as an upper surface and an outer surface thereof is considered as a lower surface. Accordingly, in FIG. 5, it is described that the light blocking member **220** is disposed on the second substrate **210**.

Each of the first substrate **110** and the second substrate **210** includes a first color pixel area PX(R), a second color pixel area PX(G), and a third color pixel area PX(B). The light blocking members **220** are disposed at boundaries between the pixel areas PX(R), PX(G), and PX(B). That is, the light blocking member **220** may be disposed at a boundary between the first color pixel area PX(R) and the second color pixel area PX(G), at a boundary between the second color pixel area PX(G) and the third color pixel area PX(B), and a boundary between the third color pixel area PX(B) and the first color pixel area PX(R). Further, the light blocking member **220** is disposed so as to overlap the thin film transistor.

The light blocking member **220** is formed of a material which may block the light and prevents light leakage. The light blocking member prevents light leakage at the boundary between the pixel areas PX(R), PX(G), and PX(B) and in a portion where the thin film transistor is formed.

A first blue light blocking filter **230a** and a second blue light blocking filter **230b** are formed on the second substrate **210**. The first blue light blocking filter **230a** is disposed in the first color pixel area PX(R) and the second blue light blocking filter **230b** is formed in the second color pixel area PX(G). The light blocking member **220** is disposed between the first blue light blocking filter **230a** and the second blue light blocking filter **230b**.

The first blue light blocking filter **230a** and the second blue light blocking filter **230b** may absorb or reflect the blue light to block the blue light. The first blue light blocking filter **230a** and the second blue light blocking filter **230b** may be omitted if necessary.

A first color conversion layer **240a** is formed on the first blue light blocking filter **230a**. The first color conversion layer **240a** is disposed in the first color pixel area PX(R). The first color conversion layer **240a** includes a plurality of first quantum rods **250a** and the plurality of first quantum rods **250a** is arranged in a predetermined direction. The first quantum rod **250a** may convert the wavelength of the incident light into a red wavelength.

The second color conversion layer **240b** is formed on the second blue light blocking filter **230b**. The second color conversion layer **240b** is disposed in the second color pixel area PX(G). The second color conversion layer **240b** includes a plurality of second quantum rods **250b** and the plurality of second quantum rods **250b** is arranged in a predetermined direction. The second quantum rod **250b** may convert a wavelength of the incident light into a green wavelength.

The transparent photo resist **242** is formed on the second substrate **210**. The transparent photo resist **242** is disposed in

the third color pixel area PX(B). The transparent photo resist **242** passes light having all wavelengths. Therefore, when the blue light component is provided from the light source, the blue light component passes through the transparent photo resist **242**. The transparent photo resist **242** may be omitted if necessary.

Partitions **260** are formed at a side of the first color conversion layer **240a**, a side of the second color conversion layer **240b**, and a side of the transparent photo resist **242**. That is, the partitions **260** are disposed at boundaries of the pixel areas PX(R), PX(G), and PX(B). The partitions **260** may be disposed between the first color conversion layer **240a** and the second color conversion layer **240b**, between the second color conversion layer **240b** and the transparent photo resist **242**, and between the transparent photo resist **242** and the first color conversion layer **240a**.

A planarization layer **265** is formed on the first color conversion layer **240a**, the second color conversion layer **240b**, and the transparent photo resist **242**. The planarization layer **265** is disposed in an empty space between the partitions to planarize an upper surface. The planarization layer **265** may be omitted if necessary.

A blue band pass filter **267** is formed on the planarization layer **265**. The blue band pass filter **267** may pass the blue light component as it is. The blue band pass filter **267** may be omitted if necessary.

A common electrode **270** is formed on the blue band pass filter **267**. The common electrode **270** is formed on the entire second substrate **210**. The common electrode **270** may be formed of transparent metal oxide such as indium tin oxide (ITO), indium zinc oxide (IZO). A predetermined voltage may be applied to the common electrode **270**.

When the data voltage is applied to the pixel electrode **191** and a predetermined voltage is applied to the common electrode **270**, an electric field is formed between the pixel electrode **191** and the common electrode **270**. Accordingly, an electric field is generated in the liquid crystal layer **3** disposed between the pixel electrode **191** and the common electrode **270**, and an orientation of liquid crystal molecule **31** in the liquid crystal layer **3** may be determined in accordance with the data voltage. A polarization direction of the light which passes through the liquid crystal layer **3** is determined in accordance with the determined direction of the liquid crystal molecule **31** and, thus, luminance of the each pixel area PX(R), PX(G), and PX(B) is determined.

A second polarizer **22** is disposed below the second substrate **210**. The second polarizer **22** is attached to the outside of the second substrate **210**. A transmissive axis of the second polarizer **22** is perpendicular to a transmissive axis of the first polarizer **12**. Further, the arrangement direction of the first quantum rod **250a** and the second quantum rod **250b** is parallel to the transmissive axis of the second polarizer **22**. Accordingly, the arrangement direction of the first quantum rod **250a** and the second quantum rod **250b** is perpendicular to the transmissive axis of the first polarizer **12**.

Hereinafter, a manufacturing method of a liquid crystal display device according to an exemplary embodiment of the present invention will be described with reference to FIGS. 6 to 13.

FIGS. 6 to 13 are cross-sectional views of a process of a manufacturing method of a liquid crystal display device according to an exemplary embodiment of the present invention.

First, as illustrated in FIG. 6, a gate electrode **124** is formed on a first substrate **110** which is formed of glass or plastic.

A gate insulating layer **140** is formed on the gate electrode **124** using an inorganic insulating material such as silicon nitride ( $\text{SiN}_x$ ) or silicon oxide ( $\text{SiO}_x$ ). The gate insulating layer **140** may be formed as either a single layer or a multilayer.

A semiconductor material, such as amorphous silicon, polycrystalline silicon, or a metal oxide, is deposited on the gate insulating layer **140** and then patterned to form a semiconductor **154**. The semiconductor **154** may be formed to be disposed on the gate electrode **124**.

After depositing and patterning a metal material on the semiconductor **154** and the gate insulating layer **140**, a source electrode **173** and a drain electrode **175**, which are spaced apart from each other are formed. The metal material may be formed as either a single layer or a multilayer.

After continuously depositing the semiconductor material and the metal material, the semiconductor material and the metal material are simultaneously patterned to form the semiconductor **154**, the source electrode **173**, and the drain electrode **175**.

The gate electrode **124**, the source electrode **173**, and the drain electrode **175** form a thin film transistor TFT together with the semiconductor **154**. The thin film transistor may serve as a switching element which transmits the data voltage. In this case, a channel of the switching element is formed in the semiconductor **154** between the source electrode **173** and the drain electrode **175**.

A passivation layer **180** is formed on an exposed portion of the source electrode **173**, the drain electrode **175**, and the semiconductor **154**. The passivation layer **180** may be formed of either an organic insulating material or an inorganic insulating material, and as either a single layer or a multilayer.

The passivation layer **180** is patterned to form a contact hole **185** to expose at least a part of the drain electrode **175**.

Transparent metal oxide, such as indium tin oxide (ITO), and indium zinc oxide (IZO), is deposited on the passivation layer **180** and then patterned to form a pixel electrode **191**.

As illustrated in FIG. 7, a light shielding material is formed on the second substrate **210** which is formed of glass or plastic and then patterned to form a light blocking member **220**. The light blocking member **220** is formed to be disposed at boundaries of the pixel areas PX(R), PX(G), and PX(B).

As illustrated in FIG. 8, a blue light blocking material is formed on the second substrate **210** and the light blocking member **220**, and then patterned to form a first blue light blocking filter **230a** and a second blue light blocking filter **230b**. The first blue light blocking filter **230a** and the second blue light blocking filter **230b** may be formed by the same process using the same material, or by different processes using different materials.

As illustrated in FIG. 9, a first color conversion layer **240a** is formed on the first blue light blocking filter **230a**. The first color conversion layer **240a** is patterned to be disposed in the first color pixel area PX(R), and the first color conversion layer **240a** includes first quantum rods **250a** which are arranged in a predetermined direction.

A second color conversion layer **240b** is formed on the second blue light blocking filter **230b**. The second color conversion layer **240b** is patterned to be disposed in the second color pixel area PX(G) and the second color conversion layer **240b** includes second quantum rods **250b** which are arranged in a predetermined direction.

A transparent photo resist **242** is formed on the second substrate **210**. The transparent photo resist **242** is patterned to be disposed in the third color pixel area PX(B).

13

The first color conversion layer **240a**, the second color conversion layer **240b**, and the transparent photo resist **242** are patterned to have substantially the same height. The transparent photo resist **242** is formed to prevent a height difference between the pixel areas PX(R), PX(G), and PX(B).

As illustrated in FIG. **10**, partitions **260** are formed at the sides of the first color conversion layer **240a**, the sides of the second color conversion layer **240b**, and the sides of the transparent photo resist **242a** using a reflective material and a light shielding material.

As illustrated in FIG. **11**, a planarization layer **265** is formed on the first color conversion layer **240a**, the second color conversion layer **240b**, and the transparent photo resist **242**.

As illustrated in FIG. **12**, a transparent metal oxide, such as indium tin oxide (ITO) or indium zinc oxide (IZO), is deposited on the planarization layer **265** to form a common electrode **270**.

As illustrated in FIG. **13**, the first substrate **110** and the second substrate **210** are bonded to each other, and a liquid crystal material is injected between the first substrate **110** and the second substrate **210** to form a liquid crystal layer **3**.

Hereinafter, a color mixture preventing effect according to an exemplary embodiment of the present invention will be described with reference to FIGS. **14** to **16**.

FIG. **14** is a cross-sectional view schematically illustrating a liquid crystal display device according to a first comparative example, FIG. **15** is a cross-sectional view schematically illustrating a liquid crystal display device according to a second comparative example, and FIG. **16** is a cross-sectional view schematically illustrating a liquid crystal display device according to an exemplary embodiment of the present invention.

As illustrated in FIG. **14**, in a liquid crystal display device according to a first comparative example, a liquid crystal layer **3** is disposed between the first substrate **110** and the second substrate **210**, and a color conversion layer **240** is formed on a separate third substrate **310**. A first polarizer **12** is located outside the first substrate **110** and a second polarizer **22** is located outside the second substrate **210**. Accordingly, the second substrate **210** and the second polarizer **22** are disposed between the liquid crystal layer **3** and the color conversion layer **240**. Generally, a thickness of the substrate is approximately 100  $\mu\text{m}$  and a thickness of the second polarizer **22** is approximately 60  $\mu\text{m}$ . Therefore, a distance  $d$  between the liquid crystal layer **3** and the color conversion layer **240** is approximately 160  $\mu\text{m}$ . In this case, when a width of the light blocking member **220**, which is disposed between adjacent color conversion layers **240**, is approximately 30  $\mu\text{m}$ , an incident angle  $\theta$  at which the color mixture occurs is approximately 10.4 degrees. That is, in the liquid crystal display device according to the first comparative example, when the incident angle  $\theta$  of light which passes through the liquid crystal layer **3** is approximately 10.4 degrees or greater, the color mixture may occur.

As illustrated in FIG. **15**, in a liquid crystal display device according to a second comparative example, a liquid crystal layer **3** is disposed on the first substrate **110** and an overcoat **290** is formed so as to cover the liquid crystal layer **3**. A first polarizer **12** is disposed outside the first substrate **110** and a second polarizer **22** is disposed on the overcoat **290**. A color conversion layer **240** is disposed between the second polarizer **22** and the second substrate **210**. Accordingly, the overcoat **290** and the second polarizer **22** are disposed between the liquid crystal layer **3** and the color conversion layer **240**. A thickness of the overcoat **290** may be approxi-

14

mately 10  $\mu\text{m}$ , and a thickness of the second polarizer **22** may be approximately 60  $\mu\text{m}$ . Therefore, a distance  $d$  between the liquid crystal layer **3** and the color conversion layer **240** is approximately 70  $\mu\text{m}$ , which is reduced as compared with the distance in the first comparative example. In this case, when a width of the light blocking member **220**, which is disposed between adjacent color conversion layers **240**, is approximately 30  $\mu\text{m}$ , an incident angle  $\theta$  at which the color mixture occurs is approximately 22.3 degrees. That is, in the liquid crystal according to the second comparative example, when the incident angle  $\theta$  of light which passes through the liquid crystal layer **3** is approximately 22.3 degrees or greater, the color mixture may occur. Therefore, the possibility of color mixture in the liquid crystal display device according to the second comparative example is lower than that of the first comparative example.

As illustrated in FIG. **16**, in the liquid crystal display device according to an exemplary embodiment of the present invention, the liquid crystal layer **3** and the color conversion layer **240** are disposed between the first substrate **110** and the second substrate **210**. A first polarizer **12** is disposed outside the first substrate **110**, and a second polarizer **22** is disposed outside the second substrate **210**. In the present exemplary embodiment, the second polarizer **22** is disposed outside the second substrate **210**, which differs from the first comparative example and the second comparative example. Therefore, it is assumed that there is almost no interval between the liquid crystal layer **3** and the color conversion layer **240**. In this case, when a width of the light blocking member **220** which is disposed between adjacent color conversion layers **240** is approximately 30  $\mu\text{m}$ , an incident angle  $\theta$  at which the color mixture occurs is approximately 84.3 degrees. That is, in the liquid crystal display device according to an exemplary embodiment of the present invention, when the incident angle  $\theta$  of light which passes through the liquid crystal layer **3** is approximately 84.3 degrees or larger, the color mixture may occur. Therefore, the possibility of color mixture in the liquid crystal display device according to the exemplary embodiment of the present invention is much lower than either the first comparative example or the second comparative example.

Hereinafter, color reproducibility of a liquid crystal display device according to an exemplary embodiment of the present invention will be described.

FIG. **17** is a result of simulation of color reproducibility according to an exemplary embodiment of the present invention. For comparison, color reproducibility of a liquid crystal display device which uses a quantum dot QD instead of the quantum rod QR and color reproducibility of a general liquid crystal display device sRGB, which does not use a quantum material, are displayed.

As illustrated in FIG. **17**, the liquid crystal display device that uses a quantum dot QD may reproduce a broader range of colors than the general liquid crystal display device sRGB. Color reproducibility of the liquid crystal display device using the quantum dot QD is approximately 110% of color reproducibility of the general liquid crystal display device sRGB. Further, the liquid crystal display device that uses a quantum rod QR may reproduce a broader range of colors than the liquid crystal display device sRGB, which uses a quantum dot QD. Color reproducibility of the liquid crystal display device using the quantum rod QR is approximately 119% of the color reproducibility of the general liquid crystal display device sRGB. That is, the liquid crystal

display device according to an exemplary embodiment of the present invention provides higher color reproducibility using the quantum rod QR.

Hereinafter, a driving method of a liquid crystal display device according to an exemplary embodiment of the present invention will be described with reference to FIG. 18.

FIG. 18 is a view illustrating a polarization direction of light which passes through each constituent element of a liquid crystal display device according to an exemplary embodiment of the present invention. FIG. 18 illustrates a first color pixel area in which red is displayed and a driving method which will be described below is also applied to the second color pixel area in which green is displayed.

First, a light source 500 provides light to a first polarizer 12. The light provided by the light source 500 is non-polarized light and formed of a blue light component.

The light provided from the light source is changed into a polarized light while passing through the first polarizer 12. Of light provided from the light source, a component which vibrates in a direction parallel to the transmissive axis of the first polarizer 12 passes through the first polarizer, and a component which vibrates in a direction perpendicular to the transmissive axis is blocked.

A polarization direction of the light which passes through the first polarizer 12 is changed while passing through the liquid crystal layer 3. As described above, in the liquid crystal layer 3, a direction of the liquid crystal molecules is determined in accordance with a strength of an electric field formed between the pixel electrode and the common electrode and, thus, a polarization direction of the light which passes through the liquid crystal layer 3 is determined. That is, a voltage is applied to the liquid crystal layer 3 to control the polarization direction of the light which passes through the first polarizer 12.

The quantity of light which passes through the liquid crystal layer 3 is adjusted while the light passes through the color conversion layer 240. An adjustment method of a quantity of light will be described with reference to FIG. 19.

FIG. 19 is a graph illustrating absorptance and light emittance in accordance with an angle formed by a polarization direction of incident light and an alignment direction of a quantum rod.

As illustrated in FIG. 19, when an angle formed by a polarization direction of the light that is incident onto the quantum rod and an arrangement direction of the quantum rod is zero degree or 180 degrees, the absorptance and the light emittance are maximized. Further, when an angle formed by a polarization direction of the light that is incident onto the quantum rod and an arrangement direction of the quantum rod is 90 degrees, the absorptance and light emittance are minimized.

Therefore, the quantity of light that passes through the color conversion layer 240 is determined by an angle formed by a polarization direction of the light that passes through the liquid crystal layer 3 and the arrangement direction of the quantum rod included in the color conversion layer 240. The arrangement direction of the quantum rod is formed in a direction that is parallel to the transmissive axis of the second polarizer 22.

Referring to FIG. 18 again, since the angle formed by a polarization direction of the light that passes through the liquid crystal layer 3 and the arrangement direction of the quantum rod is greater than zero degrees, the quantity of light is reduced while passing through the color conversion layer 240. In this case, the light that passes through the liquid crystal layer 3 is a blue light component, and most of the blue light component is changed into a red component. In

this case, some of blue light components passes through the color conversion layer 240, but the blue light component is blocked by the blue light blocking filter (not illustrated) such that only the red color component passes therethrough.

The light which passes through the color conversion layer 240 passes through the second polarizer 22 and shows a predetermined luminance.

Hereinafter, a method of representing gray scales will be described with reference to FIGS. 20 to 22.

FIGS. 20 to 22 are views illustrating a polarization direction of light which passes through each constituent element of a liquid crystal display device according to an exemplary embodiment of the present invention. FIG. 20 illustrates a maximum gray scale, FIG. 21 illustrates an intermediate gray scale, and FIG. 22 illustrates a minimum gray scale.

As illustrated in FIG. 20, a predetermined electric field is generated in the liquid crystal layer 3 so that the polarization direction of the light is controlled to rotate by approximately 90 degrees while passing through the liquid crystal layer 3.

The polarization direction of the light that passes through the liquid crystal layer 3 is parallel to the arrangement direction of the quantum rod of the color conversion layer 240, so that most of the light passes through the color conversion layer 240, and the highest luminance may be obtained. By doing this, a maximum gray scale, that is, white may be displayed.

As illustrated in FIG. 21, a predetermined electric field is generated in the liquid crystal layer 3 so that the polarization direction of the light is controlled to rotate by approximately 45 degrees while passing through the liquid crystal layer 3.

The polarization direction of the light that passes through the liquid crystal layer 3 and the arrangement direction of the quantum rod of the color conversion layer 240 form an angle of approximately 45 degrees, so that some of light passes through the color conversion layer 240 and the remaining light does not pass through the color conversion layer 240 and blocked. Thus, an intermediate gray scale may be displayed.

As illustrated in FIG. 22, the electric field is not formed on the liquid crystal layer 3 so that the polarization direction of the light is controlled so as not to be changed while passing through the liquid crystal layer 3.

The polarization direction of the light that passes through the liquid crystal layer 3 and the arrangement direction of the quantum rod of the color conversion layer 240 form an angle of 90 degrees so that most of the light does not pass through the color conversion layer 240 to be blocked. By doing this, a minimum gray scale, that is, black may be displayed.

Hereinafter, a relationship between a rotational angle of the polarization direction and luminance of the light which passes through the liquid crystal layer will be described with reference to FIG. 23.

FIG. 23 is a graph illustrating luminance in accordance with a polarization angle of liquid crystal. A polarization angle of the liquid crystal refers to an angle at which a polarization direction of light which passes through a liquid crystal layer rotates. FIG. 23 also illustrates a graph representing a luminance in accordance with a polarization angle of the liquid crystal display device according to a comparative example. In the comparative example, a general crystal display does not use the quantum material.

A gray scale in the liquid crystal display device according to an exemplary embodiment of the present invention will be determined by Equation 1.

[Equation 1]

$$G=A \cos^4(P_0)+C \cos^2(P_0)+D \cos(P_0)+E$$

(G: gray scale,  $P_0$ : angle of polarization of liquid crystal)

As illustrated in FIG. 23, the change of luminance in accordance with polarization angle of the liquid crystal in the liquid crystal display device according to the exemplary embodiment of the present invention is different from the change of luminance in accordance with the polarization angle of the liquid crystal in the liquid crystal display device according to the comparative examples.

In the liquid crystal display device according to exemplary embodiments of the present invention as described above, a distance between a liquid crystal layer and a color conversion layer is minimized to prevent the color mixing phenomenon.

Although certain exemplary embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concept is not limited to such embodiments, but rather to the broader scope of the presented claims and various obvious modifications and equivalent arrangements.

What is claimed is:

1. A liquid crystal display device, comprising:

a first substrate and a second substrate facing each other, each of the first substrate and the second substrate comprising a first color pixel area, a second color pixel area, and a third color pixel area;

a thin film transistor disposed inside the first substrate;

a color conversion layer disposed inside the second substrate, the color conversion layer comprising:

a first color conversion layer disposed in the first color pixel area and configured to change incident light into a red light component and comprising a first quantum rod;

a second color conversion layer disposed in the second color pixel area and configured to change incident light into a green light component and comprising a second quantum rod; and

a transparent photo resist disposed in the third color pixel area;

a liquid crystal layer disposed between the first substrate and the second substrate;

a blue band pass filter disposed between the color conversion layer and the liquid crystal layer;

a planarization layer disposed between the color conversion layer and the liquid crystal layer;

a first polarizer disposed at an outside of the first substrate;

a second polarizer disposed at an outside of the second substrate;

a first blue light blocking filter disposed between the second substrate and the first color conversion layer;

a second blue light blocking filter disposed between the second substrate and the second color conversion layer; and

a light blocking member disposed at boundaries between the first color pixel area, the second color pixel area, and the third color pixel area,

wherein:

the light blocking member is arranged to extend between the first blue light blocking filter and the second blue light blocking filter;

light emitted from the first color pixel area passes through the liquid crystal layer, the first quantum rod, the second substrate, and the second polarizer in this order;

light emitted from the second color pixel area passes through the liquid crystal layer, the second quantum rod, the second substrate, and the second polarizer;

light emitted from the third color pixel area passes through the liquid crystal layer, the transparent photo resist, the second substrate, and the second polarizer in this order;

in the first and second color pixel areas, an arrangement direction of the first and the second quantum rods and a transmissive axis of the second polarizer are parallel to each other;

the light emitted in the third color pixel area does not pass through quantum rods;

the planarization layer is disposed in a space between the first color conversion layer, the second color conversion layer, and the transparent photoresist;

a plurality of partitions are disposed at sides of the first color conversion layer, the second color conversion layer, and the transparent photo resist, the partitions comprising a reflective material and a light shielding material;

a plurality of the blue band pass filters are disposed in the first color pixel area, the second color pixel area, and the third color pixel area; and

the plurality of the blue band pass filters disposed in the first color pixel area, the second color pixel area, and the third color pixel area are spaced apart from each other.

2. The liquid crystal display device of claim 1, wherein the transparent photo resist is disposed on the same layer as the first color conversion layer and the second color conversion layer.

3. The liquid crystal display device of claim 2, wherein the transparent photo resist is thicker than the first color conversion layer and the second color conversion layer.

4. The liquid crystal display device of claim 1, further comprising a blue band pass filter disposed between the color conversion layer and the liquid crystal layer.

5. The liquid crystal display device of claim 4, wherein the blue band pass filter is disposed in the first color pixel area, the second color pixel area, and the third color pixel area.

6. The liquid crystal display device of claim 1, further comprising a light source configured to provide a blue light component to the first substrate.

7. A driving method of a liquid crystal display device, the liquid crystal display device including a first substrate and a second substrate facing each other, each of the first substrate and the second substrate comprising a first color pixel area, a second color pixel area, and a third color pixel area, the method comprising:

providing light to a first polarizer of the liquid crystal display device;

applying a voltage to a liquid crystal layer to control a polarization direction of light which passes through the first polarizer;

adjusting a quantity of light which passes through the liquid crystal layer while passing through a color conversion layer disposed in the second substrate, the color conversion layer comprising:

a first color conversion layer disposed in the first color pixel area and configured to change incident light into a red light component and comprising a first quantum rod;

19

a second color conversion layer disposed in the second color pixel area and configured to change incident light into a green light component and comprising a second quantum rod; and  
 a transparent photo resist disposed in the third color pixel area; and  
 passing the light which passes through the color conversion layer through a second polarization layer, wherein:  
 a first blue light blocking filter is formed between the second substrate and the first color conversion layer;  
 a second blue light blocking filter is formed between the second substrate and the second color conversion layer;  
 a light blocking member is formed at boundaries between the first color pixel area, the second color pixel area, and the third color pixel area, the light blocking member being arranged to extend between the first blue light blocking filter and the second blue light blocking filter;  
 light emitted from the first color pixel area passes through the liquid crystal layer, the first quantum rod, the second substrate, and the second polarizer in this order;  
 light emitted from the second color pixel area passes through the liquid crystal layer, the second quantum rod, the second substrate, and the second polarizer;  
 light emitted from the third color pixel area passes through the liquid crystal layer, the transparent photo resist, the second substrate, and the second polarizer in this order;  
 in the first and second color pixel areas, an arrangement direction of the first and the second quantum rods and a transmissive axis of the second polarizer are parallel to each other, and the light emitted in the third color pixel area does not pass through quantum rods;  
 the liquid crystal display device further comprises a planarization layer disposed between the color conversion layer and the liquid crystal layer;  
 a blue band pass filter is disposed between the color conversion layer and the liquid crystal layer;  
 the planarization layer is disposed in a space between the first color conversion layer, the second color conversion layer, and the transparent photoresist;  
 a plurality of partitions are disposed at sides of the first color conversion layer, the second color conversion

20

layer, and the transparent photo resist, the partitions comprising a reflective material and a light shielding material;  
 a plurality of the blue band pass filters are disposed in the first color pixel area, the second color pixel area, and the third color pixel area; and  
 the plurality of the blue band pass filters disposed in the first color pixel area, the second color pixel area, and the third color pixel area are spaced apart from each other.  
 8. The driving method of claim 7, wherein:  
 as an angle formed by the polarization direction of light which passes through the liquid crystal layer and an arrangement direction of the quantum rod approaches zero, the quantity of light which passes through the color conversion layer is increased; and  
 as an angle formed by the polarization direction of light which passes through the liquid crystal layer and the arrangement direction of the quantum rod approaches 90 degrees, the quantity of light which passes through the color conversion layer is reduced.  
 9. The driving method of claim 7, wherein the quantum rods are arranged in a predetermined direction, and the arrangement direction of the quantum rods is parallel to the transmissive axis of the second polarizer.  
 10. The driving method of claim 7, wherein the light provided to the first polarizer is a blue light component.  
 11. The driving method of claim 10, wherein a blue light component which is not changed into a red light component among the light which passes through the first color conversion layer is blocked by the first blue light blocking filter.  
 12. The driving method of claim 10, wherein a blue light component which is not changed into a green light component among the light which passes through the second color conversion layer is blocked by the second blue light blocking filter.  
 13. The driving method of claim 7, wherein:  
 the transparent photo resist is disposed on the same layer as the first color conversion layer and the second color conversion layer; and  
 the transparent photo resist is thicker than the first color conversion layer and the second color conversion layer.

\* \* \* \* \*

|                |                                                                                                                                                             |         |            |
|----------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 液晶显示装置及其驱动方法                                                                                                                                                |         |            |
| 公开(公告)号        | <a href="#">US10564467</a>                                                                                                                                  | 公开(公告)日 | 2020-02-18 |
| 申请号            | US14/993743                                                                                                                                                 | 申请日     | 2016-01-12 |
| [标]申请(专利权)人(译) | 三星显示有限公司                                                                                                                                                    |         |            |
| 申请(专利权)人(译)    | 三星DISPLAY CO. , LTD.                                                                                                                                        |         |            |
| 当前申请(专利权)人(译)  | 三星DISPLAY CO. , LTD.                                                                                                                                        |         |            |
| [标]发明人         | KANG JONG HYUK<br>CHO HYUN MIN<br>PARK JAE BYUNG<br>KANG JAE WOONG<br>KIM DAE HYUN<br>LEE SUK SUN<br>LEE JOO YEOL<br>IM HYUN DEOK<br>HONG SUNG JIN          |         |            |
| 发明人            | KANG, JONG HYUK<br>CHO, HYUN MIN<br>PARK, JAE BYUNG<br>KANG, JAE WOONG<br>KIM, DAE HYUN<br>LEE, SUK SUN<br>LEE, JOO YEOL<br>IM, HYUN DEOK<br>HONG, SUNG-JIN |         |            |
| IPC分类号         | G02F1/1335                                                                                                                                                  |         |            |
| CPC分类号         | G02F1/133528 G02F1/133621 G02F1/133514 G02F1/133533 G02F1/1336 G02F2001/133614 G02F1/133617 G02F2202/36                                                     |         |            |
| 优先权            | 1020150062037 2015-04-30 KR                                                                                                                                 |         |            |
| 其他公开文献         | US20160320664A1                                                                                                                                             |         |            |
| 外部链接           | <a href="#">Espacenet</a>                                                                                                                                   |         |            |

#### 摘要(译)

一种可防止颜色混合现象的液晶显示装置及其驱动方法，该液晶显示装置包括彼此面对的第一基板和第二基板；薄膜晶体管设置在第一基板内部；色彩转换层，设置在第二基板的内部并包括多个量子棒。液晶层，设置在第一基板和第二基板之间。第一偏振器，设置在第一基板的外侧；第二偏振器，设置在第二基板的外侧。

