



US008446537B2

(12) **United States Patent**
Yamazaki et al.

(10) **Patent No.:** **US 8,446,537 B2**
(45) **Date of Patent:** **May 21, 2013**

(54) **LIQUID CRYSTAL DISPLAY DEVICE
HAVING RESIN LAYER CONTACTS A
TRANSPARENT CONDUCTIVE FILM**

(75) Inventors: **Shunpei Yamazaki**, Tokyo (JP); **Takeshi Nishi**, Kanagawa (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi-shi, Kanagawa-ken (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/345,816**

(22) Filed: **Jan. 9, 2012**

(65) **Prior Publication Data**

US 2012/0176560 A1 Jul. 12, 2012

Related U.S. Application Data

(63) Continuation of application No. 12/966,022, filed on Dec. 13, 2010, now Pat. No. 8,094,254, which is a continuation of application No. 12/498,679, filed on Jul. 7, 2009, now Pat. No. 7,852,421, which is a continuation of application No. 11/116,376, filed on Apr. 28, 2005, now Pat. No. 7,557,873, which is a continuation of application No. 09/443,678, filed on Nov. 18, 1999, now Pat. No. 6,900,855, which is a continuation of application No. 08/728,406, filed on Oct. 9, 1996, now Pat. No. 6,175,395.

(30) **Foreign Application Priority Data**

Oct. 12, 1995 (JP) 7-290373

(51) **Int. Cl.**

G02F 1/136 (2006.01)

G02F 1/1345 (2006.01)

G02F 1/1333 (2006.01)

(52) **U.S. Cl.**

USPC **349/44**; 349/42; 349/110; 349/149

(58) **Field of Classification Search**

USPC 349/42-44, 110, 149
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,408,836 A	10/1983	Kikuno
4,636,038 A	1/1987	Kitahara et al.
4,682,075 A	7/1987	Nelson et al.
4,832,457 A	5/1989	Saitoh et al.
4,846,556 A	7/1989	Haneda
4,874,227 A	10/1989	Matsukawa et al.
4,906,071 A	3/1990	Takahara et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP	0614108 A1	9/1994
JP	03-004214 A	1/1991

(Continued)


Primary Examiner — Huyen Ngo

(74) *Attorney, Agent, or Firm* — Fish & Richardson P.C.

(57) **ABSTRACT**

In an active matrix type liquid crystal display device, a plurality of pixels connected to thin film transistors (TFTs) are arranged in an active matrix form in a pixel portion, and driven by a driver circuit portion. The pixel portion and the driver circuit portion are formed on one of a pair of insulating substrates. A liquid crystal material is interposed between the insulating substrates. A black matrix material made of an organic resin is formed over the one insulating substrate in which the driver circuit portion has been formed. An flat film is formed on the black matrix material.

24 Claims, 12 Drawing Sheets



U.S. PATENT DOCUMENTS






4,934,791 A 6/1990 Shimizu et al.
 5,019,550 A 5/1991 Suzuki et al.
 5,032,531 A 7/1991 Tsutsui et al.
 5,055,899 A 10/1991 Wakai et al.
 5,106,197 A 4/1992 Ohuchida et al.
 5,121,237 A 6/1992 Ikeda et al.
 5,124,823 A 6/1992 Kawasaki et al.
 5,148,301 A 9/1992 Sawatsubashi et al.
 5,150,232 A 9/1992 Gunkima et al.
 5,164,853 A 11/1992 Shimazaki
 5,200,846 A 4/1993 Hiroki et al.
 5,200,847 A 4/1993 Mawatari et al.
 5,250,931 A 10/1993 Misawa et al.
 5,260,815 A 11/1993 Takizawa
 5,287,205 A 2/1994 Yamazaki et al.
 5,323,205 A 6/1994 Matsubara et al.
 5,345,324 A 9/1994 Koseki et al.
 5,414,547 A 5/1995 Matsuo et al.
 5,418,094 A 5/1995 Sato et al.
 5,453,858 A 9/1995 Yamazaki
 5,501,900 A 3/1996 Harada et al.
 5,512,215 A 4/1996 Tachizono et al.
 5,512,225 A 4/1996 Fukushi
 5,550,066 A 8/1996 Tang et al.
 5,568,288 A 10/1996 Yamazaki et al.
 5,568,291 A 10/1996 Murata et al.
 5,583,675 A 12/1996 Yamada et al.
 5,608,557 A 3/1997 Wu
 5,615,030 A 3/1997 Harada et al.
 5,625,473 A 4/1997 Kondo et al.
 5,631,753 A 5/1997 Hamaguchi et al.
 5,644,370 A 7/1997 Miyawaki et al.
 5,650,664 A 7/1997 Sakamoto

5,673,127 A 9/1997 Takahara et al.
 5,677,380 A 10/1997 Matsumura et al.
 5,684,553 A 11/1997 Fukuchi
 5,710,606 A 1/1998 Nakajima et al.
 5,739,880 A 4/1998 Suzuki et al.
 5,777,701 A 7/1998 Zhang
 5,777,702 A 7/1998 Wakagi et al.
 5,784,189 A 7/1998 Bozler et al.
 5,786,042 A 7/1998 Inoue et al.
 5,789,762 A 8/1998 Koyama et al.
 5,790,220 A 8/1998 Sakamoto et al.
 5,797,055 A 8/1998 Matsubara et al.
 5,814,529 A 9/1998 Zhang
 5,815,226 A 9/1998 Yamazaki et al.
 5,880,799 A 3/1999 Inoue et al.
 5,886,365 A 3/1999 Kouchi et al.
 5,933,205 A 8/1999 Yamazaki et al.
 5,963,278 A 10/1999 Yamazaki et al.
 6,175,395 B1 1/2001 Yamazaki et al.
 6,587,169 B1 7/2003 Yamazaki et al.
 2002/0051106 A1* 5/2002 Nagashima et al. 349/110
 2004/0125279 A1* 7/2004 Lee et al. 349/110
 2004/0263722 A1* 12/2004 Oh et al. 349/106

FOREIGN PATENT DOCUMENTS

JP 03-198030 A 8/1991
 JP 06-003659 A 1/1994
 JP 07-128685 A 5/1995
 JP 07-181461 A 7/1995
 KR 1993-0003266 B1 2/1993
 KR 1994-0022155 A 10/1994
 KR 1996-0029817 A 8/1996

* cited by examiner






FIG. 2A




FIG. 2B




FIG. 3A











FIG. 3B



399 ← | → 400




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E








FIG. 5F






FIG. 7




FIG. 8




FIG. 9A




FIG. 9B






FIG. 10



Overlap of ITO and
Black Matrix 7 μ m

FIG. 11A
(Prior Art)



Overlap of ITO and
Black Matrix 2 μ m

FIG. 11B




FIG. 12

LIQUID CRYSTAL DISPLAY DEVICE HAVING RESIN LAYER CONTACTS A TRANSPARENT CONDUCTIVE FILM

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. application Ser. No. 12/966,022, filed Dec. 13, 2010, not allowed, which is a continuation of U.S. application Ser. No. 12/498,679, filed Jul. 7, 2009, now U.S. Pat. No. 7,852,421, which is a continuation of U.S. application Ser. No. 11/116,376, filed Apr. 28, 2005, now U.S. Pat. No. 7,557,873, which is a continuation of U.S. application Ser. No. 09/443,678, filed Nov. 18, 1999, now U.S. Pat. No. 6,900,855, which is a continuation of U.S. application Ser. No. 08/728,406, filed Oct. 9, 1996, now U.S. Pat. No. 6,175,395, which claims the benefit of a foreign priority application filed in Japan as Serial No. 07-290373 on Oct. 12, 1995, all of which are incorporated by reference.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to an active matrix liquid crystal display device.

2. Description of Related Art

Active matrix liquid crystal display devices are known as being effective for high-quality display. They are constructed such that thin-film transistors are formed on a transparent substrate (usually a glass or quartz substrate) for respective pixels. Each thin-film transistor controls charge that enters or exits from an electrode (pixel electrode) of the associated pixel. The active matrix liquid crystal display devices require circuits (peripheral circuits) for driving the thin-film transistors for the respective pixels. In general, the peripheral circuits are constructed as an external IC circuit called a driver IC.

In an advanced version, the peripheral circuits formed by using thin-film transistors are integrated on the substrate. Providing a unified structure in which the pixel region and the peripheral circuit regions are integrated on the same substrate, this configuration facilitates the use of a liquid crystal panel.

As an example of application of the above liquid crystal panel, a projection-type liquid crystal display apparatus will be described below.

A first method of performing color display is to form color filters of R (red), G (green), and B (blue) in a liquid crystal panel. A second method is to prepare a plurality of panels and combine images formed by those panels. In recent years, with an increasing need for large screen display, the second method is used more frequently to implement a projection-type display apparatus, because in the first method the substrate size needs to be increased and hence it is difficult to manufacture a panel. The second method is disclosed in Japanese Utility Model Laid-Open No. 51-111580.

In the second method, to combine images, the consistency of optical axes is important. Conventionally, liquid crystal panels are arranged independently and the modulating of optical axes is performed by adjusting the position and orientation of each panel in a subtle manner. However, this is not preferable because it causes a cost increase and complicates the structure of the apparatus. There is known a further technique in which the same images are superimposed on each other to increase the screen size or the brightness. However, this technique has a problem of cost increase because it complicates the apparatus structure.

To solve the above problems, attempts have been made to integrate the three panels into a single panel. In this case, it is basically sufficient to generate a set of images corresponding to three colors of R, G and B. The brightness can be increased by generating two or more sets of images corresponding to R, G and B.

In this type of configuration, in forming peripheral driver circuit regions, it has been attempted to locate peripheral circuits that should be integrated at a high density at positions as close to the center of a substrate as possible, to increase a final production yield.

However, the above conventional liquid crystal display devices have two problems described below.

The first problem is as follows. A black matrix which is made of a reflective metal such as Cr and occupies a large area of a display screen is formed on the inside surface of an upper transparent glass substrate that is located on the display screen side. External light is reflected by the black matrix and comes out of the display screen. This lowers the contrast of a displayed image and hence makes it less visible, that is, lowers the display quality.

The second problem relates to a case where a black matrix is formed on an opposed substrate. In this case, as shown in FIG. 11A, a black matrix 1 is so formed as to overlap with ITO pixel electrodes 2 by 5-7 μm in consideration of the bonding accuracy of the TFT substrate and the opposed substrate. Thus, the size of opening portions is restricted. In this case, to increase the brightness of the display device, it is necessary to employ a brighter back light, resulting in an increase in power consumption.

FIG. 11A shows how the black matrix 1 on the opposed substrate and the ITO pixel electrodes 2 overlap with each other. Reference numerals 3-5 denote a signal line, a TFT, and a scanning line, respectively.

SUMMARY OF THE INVENTION

To solve the above two problems, an object of the present invention is to form a black matrix on TFTs of a driver circuit. This configuration has an advantage that the overlapping width can be reduced to about 2 μm because of improved bonding accuracy that is obtained by forming the black matrix and the ITO pixel electrodes on the same substrate.

This advantage will be described with reference to FIG. 11B. FIG. 11B shows how they overlap with each other in a case where the black matrix 1 is formed on the TFT substrate. While in the former case (FIG. 11A) the aperture ratio is about 15% (overlapping width: 7 μm), in the latter case (FIG. 11B) it is greatly increased to about 40% (overlapping width: 2 μm).

On the other hand, in the above-mentioned configuration in which the opposed substrate is made large enough to be opposed to the driver circuits and the driver circuits are provided in the liquid crystal region, the driver circuit regions and the pixel region come close to each other, which requires light shielding even in the driver circuit regions.

Where the black matrix for light shielding of the pixel region is formed on the substrate on which TFTs are formed and is also used for light shielding of the driver circuits to satisfy the above requirement, there has occurred a problem that the capacitance of an interlayer insulating film between TFTs of the driver circuits and the black matrix is not negligible though the shielding itself does not cause any problem.

If the interlayer insulating film is a 3,000-Å-thick silicon nitride film, it has a unit area capacitance of 2.50×10^{-16} F/ μm^2 . For example, if a clock line or the like of a driver circuit has a wiring line of 100 μm in width and 50,000 μm in

length, a capacitance formed by this wiring line of the driver circuit and the black matrix amounts to 1.25×10^{-9} F. In this case, if it is assumed that the wiring line of the driver circuit has a sheet resistance of $0.2 \Omega/\mu\text{m}^2$, its delay time amounts to 1.25×10^{-7} sec, which will cause a problem when the wiring line is driven at several megahertz. The circuit characteristics are more important in the driver circuits than in the pixel TFTs. Therefore, it is necessary to reduce the capacitance of the interlayer insulating film formed between TFTs of the driver circuits and the black matrix.

It is practiced to form only a black matrix 16 for a pixel region 14 on a TFT substrate 11 so as to be adjacent to ITO electrodes 17 and form a black matrix 18 for driver circuit regions 13 on an opposed substrate 12, as shown in FIG. 12. However, although this configuration increases the aperture ratio, the number of manufacturing steps increases because of the need of forming the black matrix 16 and 18 on both of the TFT substrate 11 and the opposed substrate 12. In FIG. 12, reference numerals 15 and 19 respectively denote an aluminum wiring line and color filters of R, G and B.

It is now desired to provide a liquid crystal display device which enables light shielding of driver circuit regions without increasing the number of manufacturing steps.

Another object of the invention is to prevent a capacitance from occurring in an interlayer insulating film formed between TFTs of a driver circuit and a black matrix, to reduce, in turn, the delay time of the driver circuit, to thereby produce high-resolution images.

To attain the above objects, according to the invention, there is provided an active matrix liquid crystal display device comprising: a first insulating substrate comprising: a pixel region in which a plurality of pixels having respective thin-film transistors are arranged in matrix form; a driver circuit region for driving the pixel region, the driver circuit region being provided on the same surface as the pixel region and having thin-film transistors; and a black matrix formed over the driver circuit region; a second insulating substrate opposed to the first insulating substrate; and a liquid crystal material interposed between the first and second insulating substrates.

There is also provided an active matrix liquid crystal display device comprising: a first insulating substrate comprising: a pixel region in which a plurality of pixels having respective thin-film transistors are arranged in matrix form and a planation film is formed; a driver circuit region for driving the pixel region, the driver circuit region being provided on the same surface as the pixel region and having thin-film transistors; and a black matrix formed over the first insulating substrate a second insulating substrate opposed to the first insulating substrate; and a liquid crystal material interposed between the first and second insulating substrates.

Further, there is provided a liquid crystal display device comprising: a pair of transparent substrates; a liquid crystal interposed between the pair of transparent substrates; 2n liquid crystal panels that are constituted by using the pair of transparent substrates, where n is a natural number, the 2n liquid crystal panels comprising: active matrix pixel regions; driver circuits arranged around the pixel regions; and a black matrix formed over the first insulating substrate; and means for combining images produced by the 2n liquid crystal panels.

Still further, there is provided a liquid crystal display device comprising: a pair of transparent substrates; a liquid crystal interposed between the pair of transparent substrates; 2n liquid crystal panels that are constituted by using the pair of transparent substrates, where n is a natural number, the 2n liquid crystal panels comprising: active matrix pixel regions

each having a planation film; driver circuits arranged around the pixel regions, one side of each of the driver circuits being adjacent to one of the pixel regions, and the other side being adjacent to the other pixel regions or the other driver circuits; and a black matrix formed over the first insulating substrate; and means for combining images produced by the 2n liquid crystal panels.

In the invention, the insulating substrate means a substrate made of a transparent material that has a certain level of strength with respect to external force, for instance, an inorganic material such as glass or quartz.

Where thin-film transistors (hereinafter called TFTs) are formed on a substrate, it is preferred to use a no-alkali glass substrate or a quartz substrate. Where it is intended to reduce the weight of a liquid crystal panel, there may be used a film that is low in birefringence, such as PES (polyethylene sulfide).

A TFT that is formed for each pixel or a peripheral driver circuit may be of a type in which the active layer is made of amorphous silicon or polysilicon.

An ITO (alloy of indium oxide and tin) transparent electrodes are formed on a substrate as electrodes for driving a liquid crystal material. In view of the heat resistance, it is desired to form a black matrix after formation of the ITO electrodes.

To prevent contrast reduction due to irregular reflection within the liquid crystal display device, the black matrix used in the invention may be of a type in which a black material is dispersed in a transparent material. Examples of the transparent material are inorganic materials such as glass and quartz and organic materials such as resin. From the viewpoint of easiness of manufacture, resin materials such as acrylic materials are preferred.

Examples of the black material are carbon black and a pigment. For examples, there may be used organic pigments of phthalocyanine pigments, quinacridon pigments, isoin-dolinone pigments, azo pigments, anthraquinone pigments, and dioxazine pigments.

Another method of forming the black matrix is to photosensitize a natural polymeric material such as gelatin, or a synthetic polymeric material such as polyvinyl alcohol, or polyvinyl pyrrolidone acrylic resin by a bichromate, then form a fine pattern by a photolithographic process, and finally dye it with an acid dye or a reactive dye.

A further method is to disperse a pigment such as carbon in a photosensitive resin such as a PVA resin, an acrylic resin, or a polyimide resin, and then form a fine pattern by a photolithographic process.

Among the above processes, the method of dispersing carbon black in an acrylic resin is preferred because it can reduce the resistance and form a thin film.

The method of dispersing a black material in a resin material may be selected properly in accordance with the black material used, from a stirring method using a stirrer, a ball mill method, three-roll method, etc. The dispersiveness of the black material can be improved by adding a small amount of dispersing agent such as a surfactant during a dispersing operation. To stabilize the dispersion and form a thin black matrix layer, it is desired that the average particle diameter of the black material be about $0.1 \mu\text{m}$. If the average particle diameter is larger than this value, there may occur color unevenness and hence the black matrix does not accomplish the intended function.

A black matrix can be formed on a TFT substrate in a manner similar to the manner of forming a resist pattern by an ordinary photolithographic method. That is, an organic solution in which a black material is dispersed is applied to a TFT

substrate by spin coating or printing, then patterned by a known photographic method, and finally subjected to post-baking of about 200° C.

The second insulating substrate that is opposed to the substrate on which TFTs are formed made of the same material as the latter. In addition to a transparent electrode, a member such as color filters, a black matrix, and/or a planation film may be formed on the opposed substrate when necessary. Where color filters are formed, first a black matrix is formed on the substrate, then color filters are formed, a planation film is then formed to flatten the uneven surface, and finally a transparent electrode layer is formed.

The liquid crystal material may be a nematic, cholesteric, or smectic material, or a dispersive liquid crystal in which one of those materials is dispersed in a transparent resin material. In particular, because the dispersive liquid crystal does not require the use of a polarizing plate, it can provide a bright panel.

Where a nematic, cholesteric, or smectic liquid crystal material is used, an orientation treatment is performed on one or both of the opposed surface of the pair of substrates to orient the liquid crystal material in a certain direction. The orientation treatment is actually a rubbing treatment in which the substrate surface is rubbed with a cloth or the like directly or through a thin film of an organic or inorganic material formed on one or both of the substrates.

The substrates that have been subjected to the orientation treatment are so disposed that the orientation-treated surfaces or the surfaces on which TFTs, transparent electrodes, etc. are formed are opposed to each other, and a liquid crystal material is interposed between the opposed substrates. Spacers or the like are distributed between the pair of substrates to provide a constant substrate gap. Spacers having a diameter of 1-10 μm are used. The pair of substrate are fixed to each other with an epoxy adhesive, for instance. The adhesive is applied to a circumferential portion of the substrates so as to surround the pixel region and the peripheral driver circuit regions.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1A-1G are sectional views showing a low-temperature polysilicon process according to a first embodiment of the present invention;

FIGS. 2A and 2B show a general configuration of an integrated active matrix panel according to a second embodiment of the invention;

FIGS. 3A and 3B show a general configuration of an integrated active matrix panel according to a third embodiment of the invention;

FIGS. 4A-4G are sectional views showing a low-temperature polysilicon process according to the third embodiment of the invention;

FIGS. 5A-5F and FIGS. 6A-6D show a manufacturing process of an active matrix liquid crystal display device according to a fourth embodiment of the invention;

FIG. 7 is a sectional view taken along line A-A in FIG. 6C;

FIG. 8 is a circuit diagram showing part of an active matrix circuit according to the fourth embodiment of the invention;

FIGS. 9A and 9B show the shape of a wiring line according to a fifth embodiment of the invention;

FIG. 10 shows a liquid crystal display device having a planation film according to a sixth embodiment of the invention;

FIGS. 11A and 11B show examples of active matrix liquid crystal display devices; and

FIG. 12 shows another example of an active matrix liquid crystal display device.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In the following, there are described manufacturing methods of a substrate of a liquid crystal display device using an active matrix circuit according to the present invention.

Embodiment 1

Referring to FIGS. 1A-1G, a description is made of a manufacturing process of a monolithic active matrix circuit according to a first embodiment of the invention. This is a low-temperature polysilicon process. In FIGS. 1A-1G, the left side shows a manufacturing process of TFTs **99** of a driver circuit and the right side shows a manufacturing process of a TFT **100** of an active matrix circuit.

First, a silicon oxide film of 1,000-3,000 Å in thickness, i.e., an undercoat oxide film **102** is formed on a glass substrate **101** (first insulating substrate) by sputtering or plasma CVD in an oxygen atmosphere.

Then, an amorphous silicon film having a thickness of 300-1,500 Å, preferably 500-1,000 Å, is formed by plasma CVD or LPCVD, and crystallized or improved in crystallinity by thermal annealing at a temperature not lower than 500° C., preferably 500-600° C. Optical annealing (for instance, laser annealing) may be performed after the thermal annealing to further improve the crystallinity. Further, as described in Japanese Patent Laid-Open No. 6-244103 and 6-244104, an element (catalyst element) such as nickel for accelerating crystallization of silicon may be added in the crystallization step by thermal annealing.

Next, the silicon film is etched into island-like active layers **103** (for a P-channel TFT) and **104** (for an N-channel TFT) of TFTs **99** of a driver circuit and an island-like active layer **105** of a TFT (pixel TFT) **100** of a matrix circuit. A silicon oxide gate insulating film **106** of 500-2,000 Å in thickness is then formed by sputtering in an oxygen atmosphere. Alternatively, it may be formed by plasma CVD. In this case, favorable results are obtained by using material gases of dinitrogen monoxide (N_2O) or oxygen (O_2), and monosilane (SiH_4).

Thereafter, an aluminum film of 2,000-6,000 Å in thickness is formed on the entire substrate surface by sputtering. To prevent occurrence of hillocks in a subsequent heating process, the aluminum film may contain silicon, scandium, palladium, or the like. Gate electrodes **107-109** are formed by etching the aluminum film. (FIG. 1A)

The aluminum gate electrodes **107-109** are then anodized. As a result, the surfaces of the gate electrodes **107-109** are formed with aluminum oxide layers **110-112**, which serve as insulating layers. (FIG. 1B)

Next, a photoresist mask **113** is so formed as to cover the active layer **103** which constitutes the P-channel TFT of the TFTs **99**. Phosphorus ions are then implanted at a dose of 1×10^{12} to 5×10^{13} atoms/cm² through ion doping by using a doping gas of phosphine. As a result, strong N-type regions (sources and drains) **114** and **115** are formed. (FIG. 1C)

Next, a photoresist mask **116** is so formed as to cover the active layer **104** which constitutes the N-channel TFT of the TFTs **99** and the active layer **105** which constitutes the pixel TFT. Boron ions are implanted at a dose of 5×10^{14} to 8×10^{15} atoms/cm² through ion doping by using a doping gas of diborane (B_2H_6). As a result strong P-type regions **117** (source and drain) are formed. That is, the strong N-type regions (sources and drains) **114** and **115** and the strong P-type regions (source and drain) **117** are formed by the above doping. (FIG. 1D)

Thereafter, thermal annealing is performed at 450-850° C. for 0.5-3 hours to repair damage by the doping, activate the doped impurities, and restore the crystallinity of silicon. A silicon oxide film of 3,000-6,000 Å in thickness as an interlayer insulating film **118** is then formed over the entire surface through plasma CVD. Alternatively, a silicon nitride film or a multi-layer film of a silicon oxide film and a silicon nitride film may be formed. Contact holes for the sources and drains are formed by etching the interlayer insulating film **118** through wet etching or dry etching.

Then, an aluminum film or a titanium/aluminum multi-layer film of 2,000-6,000 Å in thickness is formed through sputtering. By etching this film, electrodes/wiring lines **119-121** of the TFTs **99** of the driver circuit and electrodes/wiring lines **122** and **123** of the pixel TFT **100** are formed. (FIG. 1E) Further, a silicon nitride film **124** of 1,000-3,000 Å in thickness as a passivation film is formed through plasma etching and then etched to form a contact hole that reaches the electrode **123** of the pixel TFT **100**. Next, an ITO (indium tin oxide) film of 500-1,500 Å in thickness is formed through sputtering and then etched to form a pixel electrode **125**. Further, a 2,000-Å-thick silicon nitride film is formed through plasma CVD and then etched to become an interlayer film **126**. (FIG. 1F)

Next, a black matrix **127** made of a resin material is formed in regions excluding the pixel electrodes **125**, that is, formed on the TFTs **99** of the driver circuit and on wiring line regions including the pixel TFTs **100**. The black matrix **127** is formed by applying, by spin coating or printing, a solution in which carbon black having an average particle diameter of 1,000 Å is dispersed in an acrylic resin material. After pre-baking is performed at 100° C. for 2 min, the film is patterned by a known photolithography technique to form a black matrix **127** on all the wiring lines and the TFTs **99** and **100** except only the pixel electrodes **125**. (FIG. 1G) This patterning is performed by applying stronger ultraviolet light (more than 20 mW/cm²) than in ordinary patterning, so that the patterning time is insufficient to allow reaction with oxygen. An oxygen shielding film of PVA (polyvinyl alcohol), for instance, may be formed after the application of the black matrix. The reason for the shielding from oxygen is that the existence of oxygen cause the resin material to react with it and the quality of a resulting film is thereby lowered.

The development is performed by using a developing liquid in which TMAH is dissolved in water at 2.36 wt %. As a result, the 1-μm-thick black matrix **127** was formed on the peripheral driver circuit **99** the pixel TFT **100**, and the gate/source wiring lines. The aperture ratio of the pixel region is 60%.

A liquid crystal panel is formed by bonding the thus-formed TFT substrate to an opposed substrate. The substrate gap is made uniform over the entire panel by interposing 5-μm-diameter spherical spacers between the two substrates. To bond and fix the two substrate to each other, they are sealed with an epoxy adhesive with a pattern that surrounds the pixel region and the peripheral driver circuit regions. After the two substrates are cut into a given shape, a liquid crystal material is injected between the two substrates.

In the liquid crystal display device, since the black matrix is made of a resin material, the interlayer insulating film between the TFTs of the driver circuits and the black matrix has a capacitance is negligibly small.

Although in this embodiment the part of the black matrix formed on the pixel TFTs is made of a resin material, it may be also made of chromium. However, where the black matrix on the driver circuits and that on the pixel TFTs are formed

with different materials, the number of manufacturing steps is increased. It is also possible to form no black matrix on the pixel TFTs.

Embodiment 2

This embodiment is directed to the configuration of an integrated liquid crystal panel which is formed according to the manufacturing method of the first embodiment and in which its panels are unified. FIGS. 2A and 2B show a general configuration of an integrated liquid crystal panel according to this embodiment.

FIG. 2A is a plan view of the integrated liquid crystal panel and shows a general configuration of a substrate on which TFTs are formed. FIG. 2B is a sectional view taken along line A-A' in FIG. 2A. FIGS. 2A and 2B show a state in which the resin black matrix **127** of the first embodiment is formed in peripheral driver circuits **201**, **202** and **209-211**.

In the peripheral driver circuits, because of a high degree of integration, such defects as reduce the production yield occur at a high possibility. According to an empirical rule in forming an integrated circuit, the yield is lower in a peripheral portion of a substrate than in its central portion. This is considered due to various factors such as substrate distortion that is more remarkable in a peripheral portion, existence of dust that is higher in probability in a peripheral portion, and a mask registration error.

The reduction in yield due to such various factors becomes more remarkable as the degree of integration of a circuit increases. Therefore, to increase the yield of the entire device, it is effective to form highly integrated circuits in a central portion of a substrate, if possible.

The liquid crystal panel of FIGS. 2A and 2B is characterized in that a first set of panels **203-205** for formation of a color image (R, and B) and a second set of panels **206-208** for formation of another color image (R', G' and B') are integrated, and that peripheral driver circuits **201**, **202** and **209-211** are commonly used for those panels for each of horizontal scanning and vertical scanning.

Embodiment 3

This embodiment is directed to a case where a planation film is provided on a substrate according to the second embodiment on which TFTs are formed. That is, a planation film **428** is provided in a pixel region and regions where a black matrix is formed.

FIGS. 3A and 3B show this embodiment in which the same reference numerals as in the second embodiment denote the same parts.

First, a substrate according to the second embodiment formed with TFTs are produced according to the manufacturing method of the first embodiment. FIGS. 4A-4G show a specific manufacturing process.

First, a silicon oxide film of 1,000-3,000 Å in thickness, i.e., an undercoat oxide film **402** is formed on a glass substrate **401** (first insulating substrate) through sputtering or plasma CVD in an oxygen atmosphere.

Then, an amorphous silicon film having a thickness of 300-1,500 Å, preferably 500-1,000 Å, is formed by plasma CVD or LPCVD, and crystallized or improved in crystallinity by thermal annealing at a temperature not lower than 500° C., preferably 500-600° C. Optical annealing (for instance, laser annealing) may be performed after the thermal annealing to further improve the crystallinity. Further, as described in Japanese Patent Laid-Open No. 6-244103 and 6-244104, an element (catalyst element) such as nickel for accelerating crystallization of silicon may be added in the crystallization step by thermal annealing.

Next, the silicon film is etched into island-like active layers **403** (for a P-channel TFT) and **404** (for an N-channel TFT) of

TFTs **399** of a driver circuit and an island-like active layer **405** of a TFT (pixel TFT) **400** of a matrix circuit. A silicon oxide gate insulating film **406** of 500-2,000 Å in thickness is then formed through sputtering in an oxygen atmosphere. Alternatively, it may be formed by plasma CVD. In this case, favorable results are obtained by using material gases of dinitrogen monoxide (N₂O) or oxygen (O₂), and monosilane (SiH₄).

Thereafter, an aluminum film of 2,000-6,000 Å in thickness is formed on the entire substrate surface by sputtering. To prevent occurrence of hillocks in a subsequent heating process, the aluminum film may contain silicon, scandium, palladium, or the like. Gate electrodes **407-409** were formed by etching the aluminum film, (FIG. 4A)

The aluminum gate electrodes **407-409** are then anodized. As a result, the surfaces of the gate electrodes **407-409** are formed with aluminum oxide layers **410-412**, which serve as insulating layers. (FIG. 4B)

Next, a photoresist mask **413** is so formed as to cover the active layer **403** which constitutes the P-channel TFT of the TFTs **399**. Phosphorus ions are then implanted at a dose of 1×10^{12} to 5×10^{13} atoms/cm² through ion doping by using a doping gas of phosphine. As a result, strong N-type regions (sources and drains) **414** and **415** are formed. (FIG. 4C)

Next, a photoresist mask **416** is so formed as to cover the active layer **404** which constitutes the N-channel TFT of the TFTs **399** and the active layer **405** which constitutes the pixel TFT. Boron ions are implanted at a dose of 5×10^{14} to 8×10^{15} atoms/cm² through ion doping by using a doping gas of diborane (B₂H₆). As a result strong P-type regions **417** (source and drain) are formed. That is the strong N-type regions (sources and drains) **414** and **415** and the strong P-type regions (source and drain) **417** are formed through the above doping. (FIG. 4D)

Thereafter, thermal annealing is performed at 450-850° C. for 0.5-3 hours to repair damage by the doping, activate the doped impurities, and restore the crystallinity of silicon. A silicon oxide film of 3,000-6,000 Å in thickness as an interlayer insulating film **418** is then formed over the entire surface through plasma CVD. Alternatively a silicon nitride film or a, multi-layer film of a silicon oxide film and a silicon nitride film may be formed. Contact holes for the sources and drains are formed by etching the interlayer insulating film **418** through wet etching or dry etching.

Then, an aluminum film or a titanium/aluminum multi-layer film of 2,000-6,000 Å in thickness is formed through sputtering. By etching this film, electrodes/wiring lines **419-421** of the TFTs **399** of the driver circuit and electrodes/wiring lines **422** and **423** of the pixel TFT **400** are formed. (FIG. 4E) Further, a silicon nitride film **424** of 1,000-3,000 Å in thickness as a passivation film is formed through plasma etching and then etched to form a contact hole that reaches the electrode **423** of the pixel TFT **400**. Next, an ITO (indium tin oxide) film of 500-1,500 Å in thickness is formed through sputtering and then etched to form a pixel electrode **425**. Further, a 2,000-Å-thick silicon nitride film is formed through plasma CVD and then etched to become an interlayer film **426**. (FIG. 4F)

Next, a black matrix **427** made of a resin material is formed in regions except the pixel electrodes **425**, that is, formed on the TFTs **399** of the driver circuit and on wiring line regions including the pixel TFTs **400**. The black matrix **427** is formed by applying, through spin coating or printing, a solution in which carbon black having an average particle diameter of 1,000 Å is dispersed in an acrylic resin material. After pre-baking is performed at 100° C. for 2 min, the film is patterned by a known photolithography technique to form a black

matrix **427** on all the wiring lines and the TFTs **399** and **400** except only the pixel electrodes **425**. This patterning is performed by applying stronger ultraviolet light (more than 20 mW/cm²) than in ordinary patterning so that the patterning time is insufficient to allow reaction with oxygen. Also an oxygen shielding film of PVA (polyvinyl alcohol), for instance, may be formed after the application of the black matrix. The reason for the shielding from oxygen is that the existence of oxygen may cause the resin material to react with it and the quality of a resulting film is thereby lowered.

The development is performed by using a developing liquid in which TMAH is dissolved in water at 2.36 wt %. As a result, the 1-μm-thick black matrix **427** is formed on the peripheral driver circuit **399**, the pixel TFT **400**, and the gate/source wiring lines. The aperture ratio of the pixel region is 60%.

Next, the surface is planarized by applying a resin liquid mainly made of an acrylic resin to the black matrix **427** and the pixel region with a spin coater. The resin liquid is completely set into the planation film **428** by a heat treatment of 170° C. and 3 hours. The planation film **428** has a thickness of 1-2 μm. (FIG. 4G)

Examples of the material of the planation film **428** other than the acrylic resin as mentioned above include an aminosilane modified epoxy resin and a polyimide resin.

Where a planation film is formed as in this embodiment, a hat orientation film can be formed in the pixel region, resulting in improved orientation of a liquid crystal.

A liquid crystal panel is formed by bonding the thus-formed TFT substrate to an opposed substrate. The substrate gap is made uniform over the entire panel by interposing 5-μm-diameter spherical spacers between the two substrates. To bond and fix the two substrates to each other, they are sealed with an epoxy adhesive with a pattern that surrounds the pixel region and the peripheral driver circuit regions. After the two substrates are cut into a given shape, a liquid crystal material is injected between the two substrates.

In the liquid crystal display device, since the black matrix is made of a resin material, the interlayer insulating film between the TFTs of the driver circuits and the black matrix has a capacitance is negligibly small.

Although in this embodiment the part of the black matrix formed on the pixel TFTs is made of a resin material, it may be made of chromium. However, where the black matrix on the driver circuits and that on the pixel TFTs are formed with different materials, the number of manufacturing steps is increased. It is also possible to form no black matrix on the pixel TFTs.

Embodiment 4

This embodiment is directed to a case where a special feature is added to the TFT manufacturing processes of the first and third embodiments. This embodiment relates to a manufacturing method that has a feature for preventing semiconductor devices being manufactured from being broken by a high voltage pulse that is imparted from plasma in performing plasma CVD or sputtering.

FIGS. 5A-5F and 6A-6D show a general manufacturing process according to this embodiment. First, a step of FIG. 5A is described. A 3,000-Å-thick silicon oxide film as an undercoat film (not shown) is formed on a glass substrate **501** through plasma CVD or sputtering. Alternatively, the substrate **501** may be a quartz substrate.

Next, a 500-Å-thick amorphous silicon film (not shown) as a starting film of an active layer **502** is formed through plasma CVD or low-pressure thermal CVD. A crystalline silicon film (not shown) is obtained by crystallizing the amorphous silicon film by heating and/or laser light application. Alterna-

tively, a crystalline silicon film may be formed directly through low-pressure thermal CVD or plasma CVD.

The crystalline silicon film thus obtained is patterned into an active layer **502** (see FIG. 5A) for a thin-film transistor by using a first mask.

Next, a 1,000-Å-thick silicon oxide film **500** to serve as a gate insulating film is formed through plasma CVD.

Further, an aluminum film (not shown) for first-layer wiring lines **506-508** (see FIG. 5A) is formed through sputtering or electron beam evaporation.

To suppress occurrence of hillocks and whiskers in subsequent steps, it is effective that the aluminum film contain Sc, Y, or at least one of element selected from the lanthanoids and actinoids. In this embodiment, Sc is included in the aluminum film at 0.1 wt %.

Hillocks and whiskers are needle or prick-like protrusions that may be formed on the surface of an aluminum film when the film is heated to more than 300° C. or it is illuminated with laser light.

Further, a very thin, dense anodic oxide film (not shown) is formed on the surface of the aluminum film (not shown) to improve the adhesiveness of resist masks **503-505** to be formed on the aluminum film.

The anodization is performed by using an electrolyte that an ethylene glycol solution containing 3%-tartaric acid neutralized with aqueous ammonia. That is, the anodization is performed in the electrolyte with the aluminum film and a platinum plate used as the anode and cathode, respectively. The thickness of a resulting dense anodic oxide film is set at 150 Å. The thickness of a dense anodic oxide film can generally be controlled by the application voltage.

Resist masks **503-505** are then formed on the aluminum film. By virtue of the dense anodic oxide film (not shown) formed on the aluminum film, superior adhesiveness are attained between the resist masks **503-505** and the aluminum film. A second mask is used in forming the resist masks **503-505**.

Next, the aluminum film is patterned by using the resist film masks **503-505** into a gate electrode **506** and a gate line (not shown) extending therefrom, a part **507** of a shorting line for connecting the gate line and a source line later, and a part **503** of a wiring line for supplying current in later anodization of the gate electrode **506**. Thus, a state of FIG. 5A is obtained.

Next, with the resist masks **503** and **505** left as they are, porous anodic oxide films **509-511** are formed as shown in FIG. 5B by using a 3% aqueous solution of oxalic acid. Specifically, the anodization is performed in the above aqueous solution by electrifying between the first-layer wiring lines **506-508** (anode) formed in the FIG. 5A step and a platinum plate (cathode).

Because of the existence of the resist masks **503-505** on the respective aluminum patterns **506-508**, the electrolyte does not contact with the top surfaces of the aluminum patterns **506-508** and hence the anodization proceeds only on the side faces of the respective patterns **506-508**.

This anodization is performed by electrifying through the current supply line for anodization (reference numeral **508** denotes its part) to prevent a case that voltage drops otherwise cause resulting anodic oxide films to have different thicknesses at opposite ends of the active matrix region. In particular, the use of the current supply lines is necessary to produce a large-area liquid crystal panel.

The growth distance of the porous anodic oxide films **509-511** can be controlled by the anodization time, and can be selected from an approximate range of 3,000-10,000 Å. In this embodiment, the thickness (growth distance) of the porous anodic oxide films **509-511** is set at 5,000 Å. The

dimension of low-concentration impurity regions (formed later) can generally be determined by the growth distance of the porous anodic oxide film **509**.

As described later in detail, the porous anodic oxide regions **509-511** have the following important roles:

formation of low-concentration impurity regions (generally called LDD regions); and

suppressing the occurrence of defects at crossing points of the first-layer and second-layer wiring lines.

After the formation of the porous anodic oxide films **509-511** (see FIG. 5B), the resist films **503-505** (not shown in FIG. 5B) are removed and then the 150-Å-thick, dense anodic oxide films (not shown) are also removed.

Thereafter, dense anodic oxide films **512-514** are formed, which are very effective in suppressing the occurrence of hillocks and whiskers.

The dense anodic oxide films **512-514** are formed by using an electrolyte that an ethylene glycol solution containing 3%-tartaric acid neutralized with aqueous ammonia.

In this step, since the electrolyte enters the porous anodic oxide films **509-511**, the dense anodic oxide films **512-514** are formed on the surfaces of the residual aluminum electrodes and wiring lines **506-508**.

Also in this anodization step, anodization current is supplied through the current supply line for anodization (reference numeral **508** denotes its part), to uniformize the thickness of the resulting anodic oxide films over the entire active matrix region.

The thickness of the dense anodic oxide films **512-514** was set at 800 Å. If the thickness of the dense anodic oxide films **512-514** were made thicker (for instance, more than 2,000 Å), offset regions later formed in the active layer could also be made thicker as much. However, to this end, the application voltage needs to be increased to more than 200 V, which is not preferable in terms of reproducibility and safety of operation. Therefore, in this embodiment, to obtain the effects of suppressing the occurrence of hillocks and whiskers and increasing the breakdown voltage, the thickness of the dense anodic oxide films **512-514** is set at 800 Å.

As a result of the above step, the gate electrode and gate line **506** is formed as shown in FIG. 5B, whose dimension is smaller than the corresponding dimension in FIG. 5A by the anodization.

The dense anodic oxide films **513** and **514** and the porous anodic oxide films **510** and **511** are also formed around the part **507** of the shorting line for connecting the gate line **506** and the source line and the part **508** of the current supply line for anodization of the gate electrode **506**.

Thus, a state of FIG. 5B is obtained. Thereafter, the exposed portions of the silicon oxide film **503** are removed to form low-concentration impurity regions in the active layer **502** of the thin-film transistor. Thus, a state of FIG. 5C is obtained, in which silicon oxide films **515-517** remained.

Next, the porous anodic oxide films **509-511** are removed (see FIG. 5D). They can be removed selectively by using a mixed acid of phosphoric acid, acetic acid, and nitric acid.

In this state, impurity ions are implanted to form source and drain regions of the thin-film transistor. Specifically, phosphoric ions are implanted to form an N-channel thin-film transistor, To form a P-channel thin-film transistor rather than an N-channel one, boronic ions may be implanted.

In this step, a source region **518** and a drain region **522** as well as low-concentration impurity regions **519** and **521** are formed in a self-aligned manner. The low-concentration regions **521** that is formed between a channel forming region **520** and the drain region **522** is usually called a lightly doped drain. (FIG. 5D)

The low-concentration impurity regions **519** and **521** are very effective in producing a thin-film transistor having a small off-current characteristic. In particular, obtaining a small off-current characteristic by forming low-concentration impurity regions is advantageous in a thin-film transistor provided in each pixel of an active matrix region because it is required to have such a characteristic.

After the implantation of impurity ions, laser light is applied to activate the implanted impurity ions and to anneal the regions which are damaged by the ion implantation. In this operation, the previously formed dense anodic oxide films **512-514** prevent hillocks and whiskers from occurring in the gate electrode **506** and the wiring lines **507** and **508**.

Next, a 4,000-Å-thick silicon oxide film to serve as a first interlayer insulating film **523** is formed through plasma CVD using a TEOS material gas.

Alternatively, the interlayer insulating film may be a silicon nitride film or a silicon oxynitride film. In the case of forming a silicon nitride film, plasma CVD may be used with a material gas of ammonia. In the case of forming a silicon oxynitride film, plasma CVD may be used with material gases of TEOS and N₂O.

As a further alternative, the first interlayer insulating film **523** may be a laminate film of a plurality of films selected from a silicon oxide film, a silicon nitride film, and a silicon oxynitride film.

Thereafter, contact holes are formed through the first interlayer insulating film **523** by using a third mask, to obtain a state of FIG. 5E.

Second-layer electrodes and wiring lines (usually called second-layer wiring lines) are then formed each of which is a three-layer film consisting of a titanium film, an aluminum film, and a titanium film. The thickness of the titanium films may be less than several hundred angstrom because they are merely used to obtain good contact. A fourth mask is used in this step.

Although each of the second-layer wiring layers may be a single-layer aluminum film, the above-mentioned three-layer film is used in this embodiment to obtain good contact with other electrodes and wiring lines.

It is necessary to use different etchants for the etching of the titanium films and the aluminum films. In this embodiment, ammonium peroxide is used for the etching of the titanium films and an aluminum mixed acid was used for the etching of the aluminum films.

Thus, a state of FIG. 5F is obtained. In FIG. 5F, reference numeral **524** denotes a source electrode and wiring line and **525** denotes a gate electrode. The gate electrode **525** is so formed as to extend from the gate line **506**, though it is not shown in FIG. 5F. The wiring lines and electrodes **524** and **525** are second-layer wiring lines.

The source line, **524** and the gate electrode (gate line) **525**, which are second-layer wiring lines, are connected to each other via a shorting line. This structure eliminates a voltage difference between the source line **524** and the gate electrode **525**.

The source line **524** is so formed as to cross, i.e., overpass the current supply line **508** for anodization with the first interlayer insulating film **523** interposed in between.

FIG. 5F also shows dummy electrodes (called "electrodes" for convenience of description) **526-528** which do not serve as electrodes or wiring lines but are used in a later dividing step. That is, they play their roles in dividing the wiring line **507** and **508** in the final step.

Next, a 4,000-Å-thick silicon oxide film as a second interlayer insulating film **529** is formed. Alternatively, the second interlayer insulating film **529** may be a silicon nitride film, a

silicon oxynitride film, or a laminate film consisting of those insulating films and a silicon oxide film.

During the formation of the second interlayer insulating film **529**, the source line **524** and the gate electrode **525** are short-circuited with each other via the shorting line **507**. Therefore, it can be avoided that plasma causes a voltage difference between the source line **524** and the gate electrode **525** and the voltage difference in turn electrostatically breaks down the gate insulating film (silicon oxide film) **515**.

Next, contact holes **530-533** are formed by using a fifth mask, to obtain a state of FIG. 6A. Reference numeral **530** denotes a contact hole for the drain region **522**, an opening **531** that is necessary to divide the wiring line **507**, and openings **532** and **533** that are necessary to divide the wiring line **508**.

In this step, the surface of an end portion **534** of the source electrode and wiring line **524** is exposed, which portion later served as an external lead-out terminal. Actually, the source line **524** is connected to a peripheral driver circuit for driving the active matrix circuit and the terminal **534** is an external terminal of this peripheral driver circuit. However, to avoid complexity, the peripheral driver circuit is not shown in FIGS. 6A-6D.

Next, an ITO electrode **535** to constitute pixel electrodes is formed through sputtering, to obtain a state of FIG. 6B. The ITO electrode **535** is then patterned into a pixel electrode **536** by using a sixth mask.

In forming the pixel electrode **536**, after the removal of unnecessary portions of the ITO electrode **535**, the etching is continued to form holes through the electrodes (dummy electrodes; second-layer wiring lines) **526-528** and the first-layer wiring lines **507** and **508**.

That is, the openings **531-533** are extended through the second-layer and first-layer wiring lines, whereby the wiring lines **507** and **508** are divided.

In the above etching, since each of the second wiring lines is a laminate films of a titanium film and an aluminum film, different etchants need to be used for the respective films.

Thus, a state of FIG. 6C is obtained. Since the above step is performed at the same time as the pixel electrode **536** is formed by patterning, there is no need of using a new mask.

The reason why the first-layer and second-layer wiring lines can be removed at the same time is that only the metal materials can be removed selectively while the insulating films of silicon oxide films etc. are left.

In the above step, a part of the ITO film **537** was left on the surface of the lead-out electrode **534** of the liquid crystal panel extending from the source line **524**. This ITO film serves as a buffer layer for preventing corrosion and mutual diffusion between the lead-out terminal **534** and a metal wiring line or a conductive pad that is to contact with the lead-out terminal **534**.

For the following reason, it is important that the current supply line **508** for anodization be divided at the portions **532** and **533**. In a subsequent liquid crystal panel assembling process, a rubbing resin film is so formed as to cover the second interlayer insulating film and then rubbing is performed to orient a liquid crystal. In this operation, since the wiring line **508** is electrically in a floating state, there can be prevented art event that an undesired voltage difference occurs between the source line **524** and the wiring line **508**.

As shown in FIG. 6C, the wiring lines **507** and **508** are divided at one location and two locations, respectively. The dividing positions may be set as desired.

FIG. 7 is a sectional view taken along line A-A' in FIG. 6C. As shown in FIG. 7, the source line **524** overpasses the current supply wiring line **508** for anodization to provide a crossing.

It is noted that a portion 701 of the wiring line 508 has a step-like shape because of the previous formation of the porous anodic oxide film.

Therefore, a portion 702 of the first interlayer insulating film 523 is given a gently sloped surface, which prevents the source line 524 from being cut due to the existence of a step.

In the state of FIG. 6C, a black matrix 538 made of a resin material was formed in regions except the pixel electrodes, that is, formed on the TFTs of the driver circuit and on wiring line regions including the pixel TFTs. (FIG. 6D) The black matrix 538 is formed by applying, through spin coating or printing, a solution in which carbon black having an average particle diameter of 1,000 Å is dispersed in an acrylic resin material. After pre-baking is performed at 100° C. for 2 min, the film is patterned by a known photolithography technique to form a black matrix 538 on all the wiring lines and the TFTs except only the pixel electrodes. This patterning is performed by applying stronger ultraviolet light (more than 20 mW/cm²) than in ordinary patterning so that the patterning time is insufficient to allow reaction with oxygen also an oxygen shielding film of PVA (polyvinyl alcohol), for instance, may be formed after the application of the black matrix. The reason for the shielding from oxygen is that the existence of oxygen may cause the resin material to react with it and the quality of a resulting film is thereby lowered.

The development is performed by using a developing liquid in which TMAH is dissolved in water at 2.36 wt %. As a result, the 1-μm-thick black matrix 538 is formed on the peripheral driver circuit, the pixel TFT, and the gate/source wiring lines. The aperture ratio of the pixel region is 60%.

A liquid crystal panel is formed by bonding the thus-formed TFT substrate to an opposed substrate. The substrate gap is made uniform over the entire panel by interposing 5-μm-diameter spherical spacers between the two substrates. To bond and fix the two substrate to each other, they are sealed with an epoxy adhesive with a pattern that surrounds the pixel region and the peripheral driver circuit regions. After the two substrates are cut into a given shape, a liquid crystal material is injected between the two substrates.

In the liquid crystal display device thus formed, since the black matrix 538, is made of a resin material, the interlayer insulating film between the TFTs of the driver circuits and the black matrix 538 has a capacitance is negligibly small.

In forming the black matrix 538, the openings 531-533 are filled with the material of the black matrix 538. Since this material is a resin material, filling the openings 531-533 with the material of the black matrix 538 is effective in providing high reliability.

FIG. 8 shows part of an active matrix circuit of an active matrix liquid crystal panel which circuit is employed in this embodiment. FIG. 8 does not include a peripheral driver circuits for inputting drive signals to the source line 524 and the gate line 525.

In the configuration of FIG. 8, the gate line 525 and the source line 524 are short-circuited by the shorting line 507. The shorting line 507 is divided by the opening 531 in the step of FIG. 6C.

In the step of FIG. 6C, the current supply line 508 for anodization is divided by the openings 532 and 533. The source line 524 overpasses the portion of the current supply line 508 extending between the dividing portions with the interlayer insulating film 523 interposed in between.

Embodiment 5

This embodiment is directed to the shape of a first-layer wiring line that is divided by openings such as the openings 532 and 533 shown in FIG. 6C. For example, the wiring line 508 becomes unnecessary once the anodization is finished.

However, there is a concern that a pulse current caused by local abnormal discharge may flow through the long wiring line 508 during the formation of the first interlayer insulating line 523 or the second interlayer insulating line 529.

In forming the first interlayer insulating line 523 or the second interlayer insulating line 529, the wiring line 508 is connected to each gate electrode. Therefore, if a pulse current flows through the wiring line 508, a pulse voltage is applied to each gate electrode.

To solve this problem, in this embodiment, the wiring line 508 has a bracket shape at the dividing portions as shown in FIG. 9A, so that a pulse current is caused to disappear or attenuate at those portions. FIGS. 9A and 9B show states before and after the dividing.

The bracket-shaped portions are removed by the openings 532 and 533 shown in FIG. 6C. Although this configuration requires the openings 532 and 533 to be increased in size, it can be said that the increase in the size of the openings 532 and 533 is, rather, preferable if taking account of the viscosity etc. of the black matrix material that is finally filled up.

Embodiment 6

This embodiment is directed to a case where a planation film 539 is formed after the TFT manufacturing process of the fourth embodiment in the pixel region and the region where black matrix is formed.

After the black matrix is formed by the same process as in the fourth embodiment, the planation film 539 is formed by the same planation film forming method as in the third embodiment. An example is shown in FIG. 10.

According to the invention, by employing, in a liquid crystal display device, the structure in which a black matrix is formed on a peripheral driver circuit, it can be prevented that a capacitance occurs in an interlayer insulating film formed between TFTs of the driver circuit and the black matrix. As a result, the delay time of the driver circuit can be reduced, which makes it possible to produce high-resolution images.

By utilizing the invention, the whole structure of a liquid crystal display device can be made as simple as possible and its manufacturing cost can be reduced while high-quality images can be produced.

Further, by properly arranging peripheral driver circuits, reduction in production yield can be avoided even if the degree of integration of a liquid crystal panel is increased.

What is claimed is:

1. An active matrix display device comprising:

a substrate;

a thin film transistor over the substrate;

an interlayer insulating film over the thin film transistor;

a transparent conductive film over the interlayer insulating film and electrically connected to the thin film transistor; and

a resin layer over the interlayer insulating film, the resin layer comprising a resin and a pigment,

wherein the resin layer surrounds the transparent conductive film and extends over a periphery of the transparent conductive film, and the resin layer has an opening to expose a portion of the transparent conductive film therein, and

wherein the resin layer contacts the transparent conductive film.

2. The active matrix display device according to claim 1, wherein the pigment is an organic pigment.

3. The active matrix display device according to claim 1, wherein the resin layer is a black matrix.

4. The active matrix display device according to claim 1, wherein the resin layer is light shielding.

17

5. The active matrix display device according to claim 1, wherein the resin is a photosensitive resin.

6. The active matrix display device according to claim 1, wherein the active matrix display device is a liquid crystal device.

7. An active matrix display device comprising:

a substrate;

a thin film transistor over the substrate;

an interlayer insulating film over the thin film transistor;

a pixel electrode over the interlayer insulating film and

electrically connected to the thin film transistor; and

a resin layer over the interlayer insulating film, the resin layer comprising a resin and a pigment,

wherein the resin layer surrounds the pixel electrode and

covers a periphery of the pixel electrode, and the resin

layer has an opening to expose a portion of the pixel

electrode therein, and

wherein the resin layer contacts the pixel electrode.

8. The active matrix display device according to claim 7, wherein the pigment is an organic pigment.

9. The active matrix display device according to claim 7, wherein the resin layer is a black matrix.

10. The active matrix display device according to claim 7, wherein the resin layer is light shielding.

11. The active matrix display device according to claim 7, wherein the resin is a photosensitive resin.

12. The active matrix display device according to claim 7, wherein the active matrix display device is a liquid crystal device.

13. An active matrix display device comprising:

a substrate;

a thin film transistor over the substrate, the thin film transistor comprising a gate electrode;

a first interlayer insulating film over the gate electrode of the thin film transistor;

an electrode on the first interlayer insulating film and electrically connected to the thin film transistor;

a second interlayer insulating film over the electrode;

a transparent conductive film over the second interlayer insulating film and electrically connected to the thin film transistor through the electrode; and

a resin layer over the second interlayer insulating film, the resin layer comprising a resin and a pigment,

wherein the resin layer surrounds the transparent conductive film and covers a periphery of the transparent conductive film, and the resin layer has an opening to expose

a portion of the transparent conductive film therein, and

18

wherein the resin layer contacts the transparent conductive film.

14. The active matrix display device according to claim 13, wherein the pigment is an organic pigment.

15. The active matrix display device according to claim 13, wherein the resin layer is a black matrix.

16. The active matrix display device according to claim 13, wherein the resin layer is light shielding.

17. The active matrix display device according to claim 13, wherein the resin is a photosensitive resin.

18. The active matrix display device according to claim 13, wherein the active matrix display device is a liquid crystal device.

19. An active matrix display device comprising:

a substrate;

a thin film transistor over the substrate, the thin film transistor comprising a gate electrode;

a first interlayer insulating film over the gate electrode of the thin film transistor;

a conductive layer on the first interlayer insulating film and electrically connected to the thin film transistor;

a second interlayer insulating film over the conductive layer; and

a pixel electrode over the second interlayer insulating film and electrically connected to the thin film transistor through the conductive layer; and

a resin layer over the second interlayer insulating film, the resin layer comprising a resin and a pigment,

wherein the resin layer surrounds the pixel electrode and covers a periphery of the pixel electrode, and the resin

layer has an opening to expose a portion of the pixel electrode therein, and

wherein the resin layer contacts the pixel electrode.

20. The active matrix display device according to claim 19, wherein the pigment is an organic pigment.

21. The active matrix display device according to claim 19, wherein the resin layer is a black matrix.

22. The active matrix display device according to claim 19, wherein the resin layer is light shielding.

23. The active matrix display device according to claim 19, wherein the resin is a photosensitive resin.

24. The active matrix display device according to claim 19, wherein the active matrix display device is a liquid crystal device.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 8,446,537 B2
APPLICATION NO. : 13/345816
DATED : May 21, 2013
INVENTOR(S) : Shunpei Yamazaki et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

In the Specification

Column 1, line 56, replace “51-111580” with --58-111580--;

Column 8, line 2, after “It” replace “s” with --is--;

Column 8, line 8, replace “its” with --six--;

Column 8, line 33, replace “(R, and B)” with --(R, G and B)--;

Column 10, line 27, replace “hat” with --flat--;

Column 11, line 42, replace “503” with --508--;

Column 12, line 40, replace “gale” with --gate--;

Column 14, line 60, replace “art” with --an--;

Column 16, line 8, replace “503” with --508--;

Column 16, line 11, replace “503” with --508--.

Signed and Sealed this
Nineteenth Day of November, 2013



Teresa Stanek Rea
Deputy Director of the United States Patent and Trademark Office

专利名称(译)	具有树脂层的液晶显示装置与透明导电膜接触		
公开(公告)号	US8446537	公开(公告)日	2013-05-21
申请号	US13/345816	申请日	2012-01-09
[标]申请(专利权)人(译)	山崎俊平 NISHI TAKESHI		
申请(专利权)人(译)	山崎, 俊平 NISHI, TAKESHI		
当前申请(专利权)人(译)	半导体能源研究所有限公司.		
[标]发明人	YAMAZAKI SHUNPEI NISHI TAKESHI		
发明人	YAMAZAKI, SHUNPEI NISHI, TAKESHI		
IPC分类号	G02F1/136 G02F1/1345 G02F1/1333 G02F1/1335 G02F1/1362		
CPC分类号	G02F1/133512 G02F1/136209 G02F1/13454 G02F2001/136222		
代理机构(译)	FISH & RICHARDSON P.C.		
优先权	1995290373 1995-10-12 JP 12/498679 2010-12-14 US 11/116376 2009-07-07 US 09/443678 2005-05-31 US 08/728406 2001-01-16 US		
其他公开文献	US20120176560A1		
外部链接	Espacenet USPTO		

摘要(译)

在有源矩阵型液晶显示装置中，连接到薄膜晶体管（TFT）的多个像素以有源矩阵形式布置在像素部分中，并由驱动电路部分驱动。像素部分和驱动电路部分形成在一对绝缘基板中的一个上。液晶材料介于绝缘基板之间。在形成有驱动电路部分的一个绝缘基板上形成由有机树脂制成的黑色矩阵材料。在黑色矩阵材料上形成平膜。

