



US008976328B2

(12) **United States Patent**  
**Kim et al.**

(10) **Patent No.:** **US 8,976,328 B2**  
(45) **Date of Patent:** **Mar. 10, 2015**

(54) **LIQUID CRYSTAL DISPLAY DEVICE AND METHOD FOR FABRICATING THE SAME**

(71) Applicant: **LG Display Co., Ltd.**, Seoul (KR)  
(72) Inventors: **Jin-Tae Kim**, Gyeonggi-do (KR);  
**Myung-Woo Nam**, Gyeongbuk (KR);  
**Seung-Mok Shin**, Daegu (KR);  
**Soo-Jeong Choi**, Gyeonggi-do (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)  
(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 1 day.

(21) Appl. No.: **13/728,144**

(22) Filed: **Dec. 27, 2012**

(65) **Prior Publication Data**  
US 2013/0222723 A1 Aug. 29, 2013

(30) **Foreign Application Priority Data**  
Feb. 27, 2012 (KR) ..... 10-2012-0019514

(51) **Int. Cl.**  
**G02F 1/1343** (2006.01)  
**H01L 33/58** (2010.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 33/58** (2013.01); **G02F 1/136227** (2013.01); **G02F 1/136209** (2013.01); **G02F 1/13394** (2013.01); **G02F 1/134363** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... G02F 1/133514; G02F 2001/136222; G02F 1/13394  
USPC ..... 349/43, 106, 141  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2001/0026344 A1\* 10/2001 Sakamoto ..... 349/141  
2002/0140891 A1 10/2002 Tomioka et al.  
2003/0025857 A1 2/2003 Ochiai et al.

(Continued)

FOREIGN PATENT DOCUMENTS

KR 1020020070756 A 9/2002  
KR 1020030011692 A 11/2003

(Continued)

OTHER PUBLICATIONS

Office Action dated Apr. 30, 2014 from the Korean Patent Office in counterpart Korean application No. 10-2012-0019514.

(Continued)


*Primary Examiner* — Lucy Chien

(74) *Attorney, Agent, or Firm* — Morgan, Lewis & Bockius LLP

(57) **ABSTRACT**

A liquid crystal display device includes a first substrate having a thin film transistor (TFT) in each pixel region, a first inorganic protective film on the first substrate including the TFT, color filters on the first inorganic protective film in each pixel region excluding the TFT, a common electrode on the color filters, a second protective film over the entire first inorganic protective film including the common electrode, a pixel electrode on the second inorganic protective film with the pixel electrode connected to a drain electrode of the TFT exposed by selective removal of the first and second inorganic protective films, the pixel electrode forming a fringe field with the common electrode such that the second inorganic protective film is interposed between the pixel electrode and the common electrode, and a column spacer on the second inorganic protective film with the column spacer covering the TFT.

**6 Claims, 7 Drawing Sheets**



(51) **Int. Cl.** 2007/0171319 A1 7/2007 Fujita et al.  
*G02F 1/1362* (2006.01) 2011/0216275 A1\* 9/2011 Lee et al. .... 349/106  
*G02F 1/1339* (2006.01)

(52) **U.S. Cl.** FOREIGN PATENT DOCUMENTS  
CPC ..... *G02F 2001/13398* (2013.01); *G02F* KR 1020040016571 A 2/2004  
*2001/136222* (2013.01) KR 1020050052802 A 7/2005  
USPC ..... **349/141**; 349/43; 349/106 KR 1020070078389 A 7/2007

(56) **References Cited** OTHER PUBLICATIONS  
U.S. PATENT DOCUMENTS Office Action dated Nov. 28, 2014 from the Korean Patent Office in  
counterpart Korean application No. 10-2012-0019514.  
2005/0117094 A1 6/2005 Kim et al.  
2007/0002209 A1\* 1/2007 Tai et al. .... 349/58 \* cited by examiner

FIG. 1  
Related art




FIG. 2A  
Related art




FIG. 2B  
Related art




FIG. 2C  
Related art




FIG. 2D  
Related art




FIG. 2E  
Related art




FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E




FIG. 4F





FIG. 4G



## LIQUID CRYSTAL DISPLAY DEVICE AND METHOD FOR FABRICATING THE SAME

This application claims the benefit of Korean Patent Application No. 10-2012-0019514, filed on Feb. 27, 2012, which is hereby incorporated by reference as if fully set forth herein.

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

The present invention relates to a liquid crystal display device, and more particularly, to a liquid crystal display device and a method for fabricating the same to reduce a mask process and remove a photo active compound (PAC) and thereby improve productivity.

#### 2. Discussion of the Related Art

With the progress of information-dependent society, the demand for various forms of display devices has increased. To meet such a demand, efforts have recently been made to research flat panel display devices such as liquid crystal displays (LCDs), plasma display panels (PDPs), electro-luminescent displays (ELDs) and vacuum fluorescent displays (VFDs). Some types of such flat panel displays are being practically applied to various appliances for display purposes.

Of these, LCDs are currently the most widely used as substitutes for cathode ray tubes (CRTs) in association with mobile image display devices because LCDs have advantages of superior picture quality, lightness, slimness, and low power consumption. Various applications of LCDs are being developed as not only mobile image display devices such as monitors of notebook computers, but also monitors of TVs and laptop computers receiving broadcast signals and displaying images. Such a liquid crystal display device includes a first substrate provided with a thin film transistor array, a second substrate provided with a color filter array and a liquid crystal layer formed between the first and second substrates. The first substrate includes a plurality of pixel regions defined by gate lines and data lines that cross each other, a plurality of pixel electrodes formed in the respective pixel regions where data signals are supplied, respectively, and a plurality of thin film transistors to respectively drive the pixel electrodes. Also, the second substrate includes a color filter formed in each pixel region, a black matrix to prevent light leakage and a column spacer to maintain a gap between the first substrate and the second substrate.

The representative driving modes that are most commonly used for the liquid crystal display device include a twisted nematic (TN) mode in which liquid crystal directors are aligned to be twisted by 90° and are then controlled through application of a voltage thereto and an in-plane switching mode in which liquid crystals are driven by a horizontal electric field between a pixel electrode and a common electrode aligned in parallel on a substrate.

In particular, in the in-plane switching mode, pixel electrodes and common electrodes are alternately formed in an opening of the thin film transistor substrate and liquid crystal is aligned by a horizontal electric field generated between the pixel electrodes and common electrodes. An in-plane switching mode LCD device has a wide viewing angle, but drawbacks of low aperture ratio and low transmittance. In order to solve these drawbacks, a fringe field switching (FFS) mode LCD device is suggested.

The FFS mode liquid crystal display device includes a common electrode having a single electrode shape formed in a pixel region and a plurality of pixel electrodes having slit shapes formed on the common electrode, or includes a pixel electrode having a single electrode shape and a plurality of

common electrodes having slit shapes, thus operating liquid crystal molecules by a fringe field formed between the pixel and common electrodes.

Hereinafter, a method for fabricating a general fringe field switching mode liquid crystal display device will be described with reference to the annexed drawings.

FIG. 1 is a sectional view illustrating a general fringe field switching mode liquid crystal display device. FIGS. 2A to 2E are sectional views illustrating a step of connecting a drain electrode to a pixel electrode in the liquid crystal display device of FIG. 1.

Referring to FIG. 1, the method for fabricating the general fringe field switching mode liquid crystal display device comprises forming gate lines (not shown), gate electrodes 10a, gate pad lower electrodes 10b and data pad lower electrodes 10c on a first substrate 10 using a first mask, and forming a semiconductor layer 13 including an active layer 13a and an ohmic contact layer 13b stacked in this order using a second mask. Also, the method comprises forming source and drain electrodes 14a and 14b, and data lines DL using a third mask, and forming first and second protective films 15a and 15b to cover the source and drain electrodes 14a and 14b.

Also, the second protective film 15b is selectively removed using a fourth mask to expose the first protective film 15a corresponding to the drain electrode 14b, the gate pad lower electrode 10b and the data pad lower electrode 10c. Also, a common electrode 18 is formed on the second protective film 15b using a fifth mask. A third protective film 15c is formed to cover the common electrode 18 and the third protective film 15c is selectively removed using a sixth mask to expose the drain electrode 14b, the gate pad lower electrode 10b and the data pad lower electrode 10c.

Also, a pixel electrode 16a connected to the drain electrode 14b, a gate pad upper electrode 16b connected to the gate pad lower electrode 10b and a data pad upper electrode 16c connected to the data pad lower electrode 10c are formed on the third protective film 15c using a seventh mask. Also, although not shown, a black matrix, R, G and B color filters and column spacers are formed on the second substrate. In order to perform these steps, the general liquid crystal display device is formed using twelve masks in total. Accordingly, the overall process is complicated and fabrication cost is increased.

Meanwhile, the general liquid crystal display device includes a second protective film 15b formed of a photo active compound (PAC) such that the second protective film 15b is interposed between the first and third protective films 15a and 15c, to reduce data load between data lines DL and pixel electrodes 16a and thereby decrease power consumption. In this regard, generally, the second protective film 15b formed of PAC, an organic insulating film, is thicker than the first and third protective films 15a and 15c formed of an inorganic insulating film. For this reason, time required for formation of the second protective film 15b is greater than time required for formation of the first and third protective films 15a and 15c, thus causing a deterioration in yield.

Furthermore, since the organic insulating film and the inorganic insulating film cannot be patterned through the same mask process, in the general liquid crystal display device, the first protective film 15a and the second protective film 15b are sequentially formed, as shown in FIG. 2A. The second protective film 15b is patterned through a fourth mask process to expose the first protective film 15a, as shown in FIG. 2B. Also, a common electrode 18 is formed on the second protective film 15b.

Then, as shown in FIG. 2C, the third protective film 15c is formed such that the third protective film 15c covers the common electrode 18 and the exposed first protective film

15a. As shown in FIG. 2D, the first and third protective films 15a and 15c corresponding to a region where the second protective film 15b is removed, are patterned through a sixth mask process to expose the drain electrode 14b. Also, as shown in FIG. 2E, a pixel electrode 16a connected to the exposed drain electrode 14b is formed on the third protective film 15c.

That is, as described above, the general liquid crystal display device entails a complicated manufacturing process and has a deteriorated yield, since the first and third protective films 15a and 15c, and the second protective film 15b are formed of different materials and thus cannot be simultaneously patterned.

### SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to a liquid crystal display device and a method for fabricating the same that substantially obviate one or more problems due to limitations and disadvantages of the related art.

An object of the present invention is to provide a liquid crystal display device having a COT (color filter on TFT) structure fabricated using ten masks and a method for fabricating the same.

Additional advantages, objects, and features of the invention will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following or may be learned from practice of the invention. The objectives and other advantages of the invention may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these objects and other advantages and in accordance with the purpose of the invention, as embodied and broadly described herein, a liquid crystal display device includes: a first substrate having a plurality of pixel regions defined by a plurality of gate lines and a plurality of data lines crossing each other; a thin film transistor formed in each pixel region; a first inorganic protective film on the first substrate including the thin film transistor; color filters formed on the first inorganic protective film in each pixel region excluding the thin film transistor; a common electrode formed on the color filters; a second protective film formed over the entire surface of the first inorganic protective film including the common electrode; a pixel electrode formed on the second inorganic protective film, such that the pixel electrode is connected to a drain electrode of the thin film transistor exposed by selective removal of the first and second inorganic protective films, the pixel electrode forming a fringe field with the common electrode such that the second inorganic protective film is interposed between the pixel electrode and the common electrode; and a column spacer formed on the second inorganic protective film such that the column spacer covers the thin film transistor.

The liquid crystal display device may further include a second substrate joined to the first substrate, wherein an electrostatic emission plate is formed over the entire surface of the second substrate.

The electrostatic emission plate may be formed of a transparent conductive material selected from TO, ITO, IZO and ITZO.

The column spacer may be formed of a light shielding material.

The light shielding material may be at least one selected from carbon, titanium oxide and a color pigment.

The column spacer may include: a first pattern overlapping the thin film transistor, to compensate a height of the color filters; and a second pattern formed on the first pattern, wherein the second pattern contacts the second substrate and maintains a cell gap between the first substrate and the second substrate.

In another aspect of the present invention, a method for fabricating a liquid crystal display device includes: forming a plurality of gate lines and a plurality of data lines crossing each other via a gate insulating film to define pixel regions on a first substrate and forming thin film transistors connected to the gate lines and the data lines; forming a first inorganic protective film on the first substrate including the thin film transistor; forming color filters on the first inorganic protective film in each pixel region excluding the thin film transistor; forming a common electrode on the color filters; forming a second inorganic protective film on the common electrode, and selectively removing the first and second inorganic protective film to expose a drain electrode of the thin film transistor; forming a pixel electrode connected to the drain electrode on the second inorganic protective film; and forming a column spacer on the second protective film such that the column spacer covers the thin film transistor.

The method may further include: joining the first substrate to second substrate, the second substrate including an electrostatic emission plate on the entire surface thereof.

The electrostatic emission plate may be formed of a transparent conductive material selected from TO, ITO, IZO and ITZO.

The column spacer may be formed of a light shielding material.

The light shielding material may be at least one selected from carbon, titanium oxide and a color pigment.

It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the invention and together with the description serve to explain the principle of the invention. In the drawings:

FIG. 1 is a sectional view illustrating a general fringe field switching mode liquid crystal display device;

FIGS. 2A to 2E are sectional views illustrating a process of connecting a drain electrode to a pixel electrode in the liquid crystal display device of FIG. 1;

FIG. 3 is a sectional view illustrating a liquid crystal display device according to the present invention; and

FIGS. 4A to 4G are sectional views illustrating a method for fabricating the liquid crystal display device according to the present invention.

### DETAILED DESCRIPTION OF THE INVENTION

Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers will be used throughout the drawings to refer to the same or like parts.

In general, a liquid crystal display device includes a first substrate and a second substrate that face each other, and a

liquid crystal layer having dielectric anisotropy formed between the first and second substrates, wherein the first substrate is provided with thin film transistors (TFTs) and pixel electrodes in pixel regions defined by gate lines and data lines, and the second substrate is provided with color filters. In this case, when the first substrate is joined to the second substrate, light leakage is generated due to misalignment and an aperture ratio may be considerably deteriorated.

Accordingly, the liquid crystal display device according to the present invention has a COT (color filter on TFT) structure in which color filters and thin film transistors are formed on the first substrate. Such a structure is obtained by forming color filters and thin film transistors on the first substrate using ten masks in total, thus simplifying the overall process and reducing fabrication costs. As a result, join margin between the first substrate and the second substrate is reduced and an aperture ratio may thus be improved.

Hereinafter, with reference to the annexed drawings, the liquid crystal display device according to the present invention will be described.

FIG. 3 is a sectional view illustrating a liquid crystal display device according to the present invention.

As shown in FIG. 3, the liquid crystal display device according to the present invention includes thin film transistors formed in pixel regions defined by gate lines (not shown) and data lines DL that cross each other on the first substrate **100**, a first inorganic protective film **150a** formed over the entire surface of a gate insulating film **120** including the thin film transistors, R, G and B color filters **160a**, **160b** and **160c** formed in pixel regions excluding the thin film transistors on the first inorganic protective film **150a**, a common electrode **170** formed over the R, G and B color filters **160a**, **160b** and **160c**, a second inorganic protective film **150b** formed over the entire surface of the first inorganic protective film **150a** including the common electrode **170**, pixel electrodes **190a** formed on the second inorganic protective film **150b** such that the pixel electrodes are connected to a drain electrode of the thin film transistors exposed through selective removal of the first and second inorganic protective films **150a** and **150b**, and form a fringe electric field with the common electrode **170**, and column spacers **200** formed on the second protective film **150a** such that the column spacers overlap the thin film transistors.

Specifically, a plurality of gate lines (not shown) and data lines DL cross each other on the first substrate **100** to define a plurality of pixel regions, and the thin film transistors are formed at the intersections between the gate lines (not shown) and the data lines DL. Also, the liquid crystal display device includes a gate pad connected to the gate line (not shown) and a data pad connected to the data line DL.

The thin film transistor includes a gate electrode **110a**, a source electrode **140a** and a drain electrode **140b** that are spaced from each other, and a semiconductor layer **130** including an active layer **130a** and an ohmic contact layer **130b** stacked in this order. The gate electrode **110a** may protrude from the gate lines (not shown) to receive a scan signal from the gate lines (not shown) and may be defined by a part of the gate lines (not shown).

The active layer **130a** overlaps the gate electrode **110a** such that the gate insulating film **120** made of an inorganic insulating material such as silicon oxide (SiO<sub>x</sub>), silicon nitride (SiN<sub>x</sub>) is interposed between the active layer **130a** and the gate electrode **110a**. The ohmic contact layer **130b** formed on the active layer **130a** reduces contact resistance between the source and drain electrodes (**140a**, **140b**) and the active layer

**130a**, and the ohmic contact layer **130b** corresponding to the gap between the source and drain electrodes **140a** and **140b** is removed to form a channel.

The source electrode **140a** is connected to the data line DL to receive a pixel signal from the data line DL, and the drain electrode **140b** faces the source electrode **140a** such that the drain electrode **140b** is spaced from the source electrode **140a** by a predetermined distance. Also, the first inorganic protective film **150a** is formed over the gate insulating film **120** including the thin film transistors and the data lines DL. The first inorganic protective film **150a** may be formed of an inorganic insulating film such as SiN<sub>x</sub> and SiO<sub>x</sub>.

R, G and B color filters **160a**, **160b** and **160c** are formed in pixel regions on the first inorganic protective film **150a**. That is, thin film transistors, and R, G and B color filters **160a**, **160b** and **160c** are formed on the first substrate **100**, thus minimizing a join margin, when the first substrate **100** is joined to the second substrate **300**, thereby improving an aperture ratio.

In particular, as described above, preferably, the R, G and B color filters **160a**, **160b** and **160c**, are formed in pixel regions excluding the thin film transistors, so that the R, G and B color filters do not overlap thin film transistors. This aims at forming a drain contact hole **180a** to connect the pixel electrodes **190a** to the drain electrode **140b** using one mask, based on a configuration in which only the first and second inorganic protective films **150a** and **150b** overlap the thin film transistors on the drain electrode **140a**.

Also, the common electrode **170** is formed of a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO) and indium tin zinc oxide (ITZO) on the R, G and B color filters **160a**, **160b** and **160c**, and the common electrode **170** having a single electrode shape receives a common signal.

A second inorganic protective film **150b** is formed over the entire surface of the first inorganic protective film **150a** including the common electrode **170**. The second inorganic protective film **150b** is also formed of an inorganic insulating film such as SiN<sub>x</sub>. The first and second inorganic protective films **150a** and **150b** include a drain contact hole **180a** to expose the drain electrode **140b** of the thin film transistor.

Also, a plurality of slit-shaped pixel electrodes **190a** are formed on the second inorganic protective film **150b** and the pixel electrodes **190a** are connected to drain electrodes **140b** via the drain contact hole **180a**. The pixel electrodes **190a** are formed of a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO), and indium tin zinc oxide (ITZO).

In particular, the pixel electrodes **190a** form a fringe electric field with the common electrode **170**. The second inorganic protective film **150b** is interposed between the pixel electrodes **190a** and the common electrode **170**. Also, liquid crystal molecules are rotated by the fringe field due to dielectric anisotropy, and transmittance of light emitted to pixel regions is changed depending on the rotation level of the liquid crystal molecules, to realize an image.

Also, column spacers **200** are formed on the second inorganic protective film **150b** such that they overlap the thin film transistors. As shown in the drawing, the column spacers **200** are formed to have a double height including: a first pattern **200a** serving as PAC that overlaps the thin film transistors to compensate heights of the R, G and B color filters **160a**, **160b** and **160c**; and a second pattern **200b** formed on the first pattern **200a** such that second pattern **200b** contacts the second substrate **300** and maintains a cell gap between the first substrate **100** and the second substrate **300**. Also, the column spacers **200** may have a single, or triple or more height.

The column spacer **200** is formed of a light shielding material to eliminate the need for separate formation of a black matrix. Specifically, the column spacer **200** is preferably formed of an organic material absorbing light, such as carbon, titanium oxide (TiOx), or a color pigment, or a black organic material, for example, a black resin absorbing light.

Also, the gate pad supplies a scan signal from a gate driver (not shown) to the gate line (not shown). The gate pad includes a gate pad lower electrode **110b** connected to the gate line (not shown) and a gate pad upper electrode **180b** connected to the gate pad lower electrode **110b** via a gate contact hole **180b** that passes through the first and second inorganic protective films **150a** and **150b** and the gate insulating film **120**.

Also, the data pad supplies a pixel signal from the data driver (not shown) to the data line DL. The data pad includes a data pad lower electrode **140c** connected to the data lines DL, and a data pad upper electrode **180c** connected to the data pad lower electrode **140c** via a data contact hole **180c** that passes through the first and second inorganic protective films **150a** and **150b**.

The liquid crystal display device according to the present invention includes the thin film transistors, and R, G and B color filters **160a**, **160b** and **160c** formed on the first substrate **100**, thus reducing a join margin between the first and second substrates **100** and **300** and improving an aperture ratio. In particular, in the liquid crystal display device according to the present invention, the R, G and B color filters **160a**, **160b** and **160c** reduce a data load between the data lines DL and pixel electrodes **190a**, thus removing PAC.

A general liquid crystal display device includes an organic insulating film made of a photo active compound (PAC), formed between the first protective film and the pixel electrode, thus reducing data load between data lines and pixel electrodes. In this regard, PAC is thicker than the inorganic insulating film, thus entailing a long process time and deteriorating yield. Since the PAC and the inorganic insulating film should be patterned through separate mask processes, when a drain contact hole to connect the pixel electrodes and the drain electrode is formed, the overall process is complicated and fabrication costs increase.

However, in the liquid crystal display device according to the present invention, R, G and B color filters **160a**, **160b** and **160c** can reduce a data load between the data lines DL and the pixel electrodes **190a**, although the PAC is removed. Furthermore, the R, G and B color filters **160a**, **160b** and **160c** are formed to not overlap the thin film transistors, thereby selectively removing the first and second protective films **150a** and **150b** stacked in this order simultaneously in the process of exposing the drain electrode of thin film transistors.

Also, an electrostatic emission plate **310** for electrostatic emission is formed on the second substrate **300** that faces the first substrate **100**. The electrostatic emission plate **310** is formed of a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO), or indium tin zinc oxide (ITZO) over the entire surface of the second substrate **300**, to dissipate electrostatic charge generated during the module process outside.

That is, the electrostatic emission plate **310** is formed over the entire surface of the second substrate **300** and the second substrate **300** thus does not need a mask process. Accordingly, the second substrate **300** has a small thickness, thus reducing the thickness of the liquid crystal display device.

Hereinafter, with reference to the annexed drawings, a method for fabricating the liquid crystal display device according to the present invention will be described in detail.

FIGS. **4A** to **4G** are sectional views illustrating a method for fabricating the liquid crystal display device according to the present invention.

First, as shown in FIG. **4A**, a gate electrode **110a**, gate lines (not shown) and a gate pad lower electrode **110b** are formed using a first mask on a first substrate **100**. Specifically, a gate metal layer is formed by a deposition method such as sputtering on the first substrate **100**, and the gate metal layer is patterned to form a gate electrode **110a**, gate lines (not shown) and a gate pad lower electrode **110b**. Also, a gate insulating film **120** is formed over the entire surface of the first substrate **100** including the gate electrode **110a**, the gate lines (not shown) and the gate pad lower electrode **110b**.

Next, as shown in FIG. **4B**, a semiconductor layer **130** including an active layer **130a** and an ohmic contact layer **130b** stacked in this order is formed using the second mask. Source and drain electrodes **140a** and **140b** spaced from each other by a predetermined distance are formed on the semiconductor layer **130** using a third mask. At the same time, data lines DL and a data pad lower electrode **140c** are formed on the gate insulating film **120** using the third mask. The data lines DL cross gate lines to define a plurality of pixel regions.

In particular, although not shown, when a half tone mask or diffraction exposure mask is used as the second mask, the semiconductor layer **130**, the source and drain electrodes **140a** and **140b**, data lines DL and the data pad lower electrode **140c** can be formed using one mask and the manufacturing process can thus be simplified.

Also, although the data pad lower electrode **140c** and data lines DL are formed simultaneously, the data pad lower electrode **140c** may be formed together with the gate pad lower electrode **110b**, and in this case, a configuration to connect the data pad lower electrode **140c** to the data lines DL may be further required.

As a result, the thin film transistor including the gate electrode **110a**, the semiconductor layer **130**, and the source and drain electrodes **140a** and **140b** is formed. Also, a first inorganic protective film **150a** is formed over the entire surface of the gate insulating film **120** including the thin film transistor. The first inorganic protective film **150a** is preferably an inorganic insulating film such as SiNx.

Next, as shown in FIG. **4C**, R, G and B color filters **160a**, **160b** and **160c** are formed in pixel regions on the first inorganic protective film **150a** using fourth, fifth and sixth masks. As shown in FIG. **4D**, a common electrode **170** is formed on the R, G and B color filters **160a**, **160b** and **160c** using a seventh mask. The common electrode **170** is formed as a single electrode shape using a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO), and indium tin zinc oxide (ITZO).

In particular, preferably, the R, G and B color filters **160a**, **160b** and **160c** are formed in pixel regions excluding thin film transistors, so that the R, G and B color filters **160a**, **160b** and **160c** do not overlap the thin film transistors. This serves to form a drain contact hole **180a** to connect the pixel electrodes and the drain electrode **140b** using one mask.

Specifically, in accordance with the general liquid crystal display device, first and second protective films are sequentially formed such that they cover the thin film transistors. At this time, the first protective film is formed of an inorganic insulating film and the second protective film is formed of an organic insulating film, as a photo active compound (PAC).

The formation of the second protective film with a photo active compound (PAC) aims at reducing a data load between the pixel electrodes and the data lines.

Since a third protective film is formed of an inorganic insulating film on the second protective film in order to form

a fringe field, two mask processes in total are required for formation of a drain contact hole to connect the pixel electrode to the drain electrode.

That is, the first and third protective films are formed of inorganic insulating films, while the second protective film is formed of PAC as an organic insulating film. For this reason, the first, second and third protective films cannot be simultaneously patterned. Accordingly, the general liquid crystal display device has a configuration in which the second protective film is selectively removed to expose the first protective film, a third protective film is formed to cover the first protective film exposed through removal of the second protective film, and the first and third protective films stacked in this order are then selectively removed to expose the drain electrode.

However, as described above, in the liquid crystal display device according to the present invention, R, G and B color filters **160a**, **160b** and **160c** reduce data load between the pixel electrodes and data lines, thus removing PAC. In particular, R, G and B color filters **160a**, **160b** and **160c** are formed in pixel regions, excluding regions where thin film transistors are formed, thereby forming the drain contact hole using one mask.

Next, as shown in FIG. 4E, a second inorganic protective film **150b** is formed over the entire surface of the first inorganic protective film **150a** including the common electrode **170**. The second inorganic protective film **150b** is also formed of an inorganic insulating film such as SiNx, like the first inorganic protective film **150a**. In this case, since only the first inorganic protective film **150a** and the second inorganic protective film **150b** overlap the thin film transistor, the first and second inorganic protective films **150a** and **150b** are patterned using an eighth mask to form a drain contact hole **180a** exposing the drain electrode **140b**. At the same time, a gate pad contact hole **180b** and a data pad contact hole **180c** exposing the gate pad lower electrode **110b** and the data pad lower electrode **140c** are formed.

Also, as shown in FIG. 4F, a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO), and indium tin zinc oxide (ITZO) is deposited over the entire surface of the second inorganic protective film **150b** including the drain contact hole **180a**, the gate pad contact hole **180b** and the data pad contact hole **180c**, and is thus patterned using a ninth mask to form pixel electrodes **190a**, a gate pad upper electrode **190b** and a data pad upper electrode **190c**.

At this time, the pixel electrodes **190a** are formed to have a shape of a plurality of slits and are connected to the drain electrode **140b** through the drain contact hole **180a**. The pixel electrodes **190a** overlap the common electrode **170** via the second inorganic protective film **150b** to form a fringe field. Also, the gate pad upper electrode **190b** and the data pad upper electrode **190c** are connected through the gate pad contact hole **180b** and the data pad contact hole **180c** to the gate pad lower electrode **110b** and the data pad lower electrode **140c**, respectively.

Finally, as shown in FIG. 4G, a column spacer **200** is formed using an eleventh mask such as a half tone mask or a diffraction exposure mask on the second inorganic protective film **150b** that overlaps and covers the thin film transistor (**S40**). At this time, as shown in FIG. 4G, the column spacer **200** may have a double height including: a first pattern **200a** serving as PAC that overlaps and covers thin film transistors to compensate heights of the R, G and B color filters **160a**, **160b** and **160c**; and a second pattern **200b** formed on the first pattern **200a** such that second pattern **200b** contacts the sec-

ond substrate **300** and maintains a cell gap between the first substrate **100** and the second substrate **300**.

Also, the column spacer **200** may have a single, or triple or more height, if desired. The column spacer **200** is formed of a light shielding material to eliminate the necessity of a process for forming a black matrix.

Also, the first substrate **100** is joined to the second substrate **300** and a liquid crystal is then injected between the first substrate **100** and the second substrate **300** to form a liquid crystal layer **400**. In particular, an electrostatic emission plate **310** for electrostatic emission is formed on the second substrate **300**.

The electrostatic emission plate **310** is formed of a transparent conductive material such as tin oxide (TO), indium tin oxide (ITO), indium zinc oxide (IZO), or indium tin zinc oxide (ITZO) over the entire surface of the second substrate **300**, to dissipate electrostatic charge generated during the module process outside.

In accordance with the liquid crystal display device according to the present invention, thin film transistors, and R, G and B color filters **160a**, **160b** and **160c** are formed on the first substrate **100** using ten masks in total, thereby reducing fabrication costs and simplifying the overall manufacturing process. Furthermore, when the semiconductor layer **130**, the source and drain electrodes **140a** and **140b**, the data lines DL and the data pad lower electrode **140c** are formed using one mask, the liquid crystal display device can be formed using nine masks in total.

In particular, thin film transistors and R, G, B color filters (**160a**, **160b**, **160c**) are formed on the first substrate **100**, thus reducing a join margin of first and second substrates **100** and **300** and improving an aperture ratio. Also, the R, G and B color filters **160a**, **160b** and **160c** can reduce a data load between data lines DL and pixel electrodes **190a**, thus removing a photo active compound (PAC), reducing fabrication costs and decreasing process time. Also, removal of PAC enables formation of the drain contact hole **180a** to connect the drain electrode **140b** to the pixel electrode **190a** using one mask.

The liquid crystal display device and a method for fabricating the same according to the present invention have the following advantages.

First, color filters and thin film transistors are formed on a first substrate, thus reducing a join margin of the first and second substrates and improving an aperture ratio. In particular, the color filters formed on the first substrate reduce a data load between pixel electrodes and data lines, thus decreasing fabrication costs through removal of a photo active compound (PAC).

Second, since the PAC present between a first protective film and pixel electrode is removed, a drain contact hole to connect a drain electrode to a pixel electrode can be formed through one mask process.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the inventions. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A liquid crystal display device comprising:
  - a first substrate having a plurality of pixel regions defined by a plurality of gate lines and a plurality of data lines crossing each other;
  - a thin film transistor formed in each pixel region;

11

a first inorganic protective film on the first substrate including the thin film transistor;  
 color filters formed on the first inorganic protective film in each pixel region excluding the thin film transistor;  
 a common electrode formed on the color filters;  
 a second protective film formed over the entire surface of the first inorganic protective film including the common electrode;  
 a pixel electrode formed on the second inorganic protective film, such that the pixel electrode is connected to a drain electrode through a drain contact hole exposing the drain electrode; and  
 a column spacer formed on the second inorganic protective film such that the column spacer covers the thin film transistor,  
 wherein the first inorganic protective film directly contacts the second inorganic protective film at a portion surrounding the drain contact hole.

2. The liquid crystal display device according to claim 1, further comprising a second substrate joined to the first substrate,  
 wherein an electrostatic emission plate is formed over the entire surface of the second substrate.

3. The liquid crystal display device according to claim 1, wherein the column spacer is formed of a light shielding material.

4. The liquid crystal display device according to claim 3, wherein the light shielding material is at least one selected from carbon, titanium oxide and a color pigment.

12

5. The liquid crystal display device according to claim 2, wherein the column spacer comprises:  
 a first pattern covering the thin film transistor, to compensate a height of the color filters; and  
 a second pattern formed on the first pattern, wherein the second pattern contacts the second substrate and maintains a cell gap between the first substrate and the second substrate.

6. A method for fabricating a liquid crystal display device comprising:  
 forming a plurality of gate lines and a plurality of data lines crossing each other via a gate insulating film to define pixel regions on a first substrate and forming thin film transistors connected to the gate lines and the data lines;  
 forming a first inorganic protective film on the first substrate including the thin film transistor;  
 forming color filters on the first inorganic protective film in each pixel region excluding the thin film transistor;  
 forming a common electrode on the color filters;  
 forming a second inorganic protective film on the common electrode, and selectively removing only the first and second inorganic protective film to form a drain contact hole exposing a drain electrode of the thin film transistor;  
 forming a pixel electrode connected to the drain electrode on the second inorganic protective film; and  
 forming a column spacer on the second protective film such that the column spacer covers the thin film transistor.

\* \* \* \* \*

专利名称(译)	液晶显示装置及其制造方法		
公开(公告)号	<a href="#">US8976328</a>	公开(公告)日	2015-03-10
申请号	US13/728144	申请日	2012-12-27
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD. ,		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	KIM JIN TAE NAM MYUNG WOO SHIN SEUNG MOK CHOI SOO JEONG		
发明人	KIM, JIN-TAE NAM, MYUNG-WOO SHIN, SEUNG-MOK CHOI, SOO-JEONG		
IPC分类号	G02F1/1343 G02F1/1339 G02F1/1362 H01L33/58		
CPC分类号	H01L33/58 G02F1/136227 G02F1/136209 G02F1/13394 G02F1/134363 G02F2001/13398 G02F2001/136222		
优先权	1020120019514 2012-02-27 KR		
其他公开文献	US20130222723A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

摘要(译)

液晶显示装置包括：第一基板，在每个像素区域中具有薄膜晶体管（TFT）；第一基板上包括TFT的第一无机保护膜；在除TFT之外的每个像素区域中的第一无机保护膜上的滤色器，滤色器上的公共电极，包括公共电极的整个第一无机保护膜上的第二保护膜，第二无机保护膜上的像素电极，其中像素电极通过选择性去除而暴露于TFT的漏电极在第一无机保护膜和第二无机保护膜中，像素电极与公共电极形成边缘场，使得第二无机保护膜插入像素电极和公共电极之间，柱状间隔物与第二无机保护膜一起形成柱状衬垫覆盖TFT。

