



US009612377B2

(12) **United States Patent**  
**Chen et al.**

(10) **Patent No.:** **US 9,612,377 B2**  
(45) **Date of Patent:** **Apr. 4, 2017**

(54) **TOUCH SCREEN DISPLAY WITH  
TRANSPARENT ELECTRICAL SHIELDING  
LAYER**

*G02F 1/133502* (2013.01); *G02F 1/133514*  
(2013.01); *G02F 1/133528* (2013.01); *G06F*  
*3/041* (2013.01); *G06F 3/044* (2013.01);  
*G06F 3/0412* (2013.01); *H04N 9/3105*  
(2013.01); *H04N 9/3197* (2013.01); *G02F*  
*1/134363* (2013.01);

(71) Applicant: **Apple Inc.**, Cupertino, CA (US)

(Continued)

(72) Inventors: **Cheng Chen**, San Jose, CA (US);  
**Enkhamgalan Dorjgotov**, San  
Francisco, CA (US); **Masato**  
**Kuwabara**, Tsukuba (JP); **Wonjae**  
**Choi**, Cupertino, CA (US); **Martin P.**  
**Grunthaner**, Mountain View, CA (US);  
**Albert Lin**, Sunnyvale, CA (US); **John**  
**Z. Zhong**, Saratoga, CA (US); **Wei**  
**Chen**, Palo Alto, CA (US); **Steven P.**  
**Hotelling**, Los Gatos, CA (US); **Lynn**  
**R. Youngs**, Cupertino, CA (US)

(58) **Field of Classification Search**  
CPC ..... *G02F 2001/136218*; *G02F 2001/133334*  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,861,136 B2 3/2005 Verlinden et al.  
7,199,518 B2 4/2007 Couillard  
(Continued)

(73) Assignee: **Apple Inc.**, Cupertino, CA (US)

FOREIGN PATENT DOCUMENTS

(\* ) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 0 days.

CN 101075030 11/2007  
CN 101971345 2/2011  
(Continued)

(21) Appl. No.: **14/965,657**

*Primary Examiner* — Phu Vu

(22) Filed: **Dec. 10, 2015**

(74) *Attorney, Agent, or Firm* — Zachary D. Hadd;  
Joseph F. Guihan

(65) **Prior Publication Data**

US 2016/0097882 A1 Apr. 7, 2016

**Related U.S. Application Data**

(63) Continuation of application No. 13/549,311, filed on  
Jul. 13, 2012, now Pat. No. 9,329,314.


(51) **Int. Cl.**  
*G02F 1/1333* (2006.01)  
*G02B 5/30* (2006.01)  
(Continued)

(57) **ABSTRACT**

A polarizer includes a polarizer component having a top  
surface and an opposite bottom surface. The bottom surface  
is configured to couple to a color filter layer for a liquid  
crystal display. The polarizer also includes a transparent  
conducting layer disposed over the top surface. The trans-  
parent conducting layer being configured to electrically  
shield the LCD from a touch panel. The polarizer further  
includes a coating layer disposed over the transparent con-  
ducting layer.

(52) **U.S. Cl.**  
CPC ..... *G02B 5/3033* (2013.01); *G02B 1/11*  
(2013.01); *G02B 1/16* (2015.01); *G02F*  
*1/13338* (2013.01); *G02F 1/133308* (2013.01);

**21 Claims, 19 Drawing Sheets**



- (51) **Int. Cl.**
- |                    |           |                   |         |                       |
|--------------------|-----------|-------------------|---------|-----------------------|
| <i>H04N 9/31</i>   | (2006.01) | 8,164,698 B2      | 4/2012  | Kim et al.            |
| <i>G06F 3/041</i>  | (2006.01) | 8,294,869 B2      | 10/2012 | Yamaguchi et al.      |
| <i>G02B 1/16</i>   | (2015.01) | 8,482,713 B2      | 7/2013  | Qi et al.             |
| <i>G02B 1/11</i>   | (2015.01) | 8,692,948 B2      | 4/2014  | Park et al.           |
| <i>G02F 1/1335</i> | (2006.01) | 2004/0212599 A1   | 10/2004 | Cok et al.            |
| <i>G06F 3/044</i>  | (2006.01) | 2006/0204675 A1   | 9/2006  | Gao et al.            |
| <i>G02F 1/1362</i> | (2006.01) | 2007/0268243 A1   | 11/2007 | Choo et al.           |
| <i>G02F 1/1343</i> | (2006.01) | 2008/0062140 A1   | 3/2008  | Hotelling et al.      |
|                    |           | 2008/0218369 A1   | 9/2008  | Krans et al.          |
|                    |           | 2009/0147167 A1   | 6/2009  | Park                  |
|                    |           | 2009/0243817 A1   | 10/2009 | Son                   |
|                    |           | 2011/0216020 A1   | 9/2011  | Lee et al.            |
|                    |           | 2012/0127387 A1   | 5/2012  | Yamato et al.         |
|                    |           | 2013/0271697 A1   | 10/2013 | DeForest et al.       |
|                    |           | 2016/0097882 A1 * | 4/2016  | Chen ..... G06F 3/041 |
- (52) **U.S. Cl.**  
 CPC ..... *G02F 2001/133334* (2013.01); *G02F 2001/136218* (2013.01); *G02F 2202/28* (2013.01); *G06F 2203/04107* (2013.01)  
 349/96

(56) **References Cited**

FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS

7,231,733 B2	6/2007	Regelin
7,242,398 B2	7/2007	Nathan et al.
7,535,462 B2	5/2009	Spath et al.
8,094,247 B2	1/2012	Allemand et al.

CN	102279480	12/2011
JP	2012-8255	1/2012
KR	2001-0093352	10/2001
TW	200608272	3/2006

\* cited by examiner





FIG. 1A  
(PRIOR ART)



**FIG.1B**  
**(PRIOR ART)**




FIG. 1C  
(PRIOR ART)




FIG.2A




FIG.2B




FIG.3A




FIG.3B




FIG.4




FIG.5




FIG.6




FIG. 7




FIG.8A




FIG.8B




FIG.9A




FIG.9B




FIG.9C




FIG.9D




FIG. 10A




FIG.10B

## TOUCH SCREEN DISPLAY WITH TRANSPARENT ELECTRICAL SHIELDING LAYER

This application is a continuation of U.S. patent application Ser. No. 13/549,311, filed Jul. 13, 2012 which is hereby incorporated by reference herein in its entirety. This application claims the benefit of and claims priority to U.S. patent application Ser. No. 13/549,311, filed Jul. 13, 2012.

### TECHNICAL FIELD

The present invention generally relates to touch screen display that includes an in-plane switching (IPS) liquid crystal display (LCD) and a touch panel. More specifically, the invention relates to the touch screen display with a transparent shielding layer to reduce noise coupled from the IPS LCD into the touch panel.

### BACKGROUND

In-plane switching (IPS) LCD uses thin film transistor (TFT) technology to improve image quality. The IPS LCD delivers bright pictures with very good color consistency at a wide viewing angle. IPS LCDs are used in television sets, computer monitors, mobile phones, handheld systems, personal digital assistants, navigation systems, projectors, and many other devices.

An IPS LCD includes an array of pixels for displaying images. The pixels are addressed in rows and columns, reducing the connection count from millions for each individual pixel to thousands. The column and row wires attach to transistor switches, one transistor for each pixel. The one-way current passing characteristic of the transistor prevents the charge applied to the pixel from draining between refreshes to the display image.

In an IPS LCD, the liquid crystal extends horizontally across the panel and essentially provides a wide viewing angle, fast response speed, and a simple pixel structure. The IPS LCD employs pairs of electrodes at the sides of each cell, applying an electric field horizontally through the material. This approach keeps the liquid crystals parallel to the front of the panel, thereby increasing the viewing angle.

FIG. 1A illustrates a perspective view of an electronic device, such as an IPAD. The electronic device includes a touch screen display **100** enclosed by a housing **138**. The touch screen display **100** includes a touch panel **102** on a front and an LCD display behind the touch panel **102**, although alternative embodiments may employ an OLED layer instead of an LCD. A cross-section is taken along line **2-2** in FIG. 1A. FIG. 1B illustrates a simplified cross-section diagram for the touch screen display of FIG. 1A. Touch screen display **100** includes a touch panel **102** above an IPS LCD **104**. The touch screen display **100** may have an air gap **106** between the touch panel **102** and the IPS LCD **104**. Alternatively, in a full lamination design, an optically clear adhesive (OCA) may connect the touch panel and the LCD such that there is no air gap between the touch panel and display.

FIG. 1C illustrates a cross-section of an embodiment of an IPS LCD of FIG. 1B. The IPS LCD **104** includes a front polarizer **118**, a rear polarizer **108**, and liquid crystal layer **112** between the front and rear polarizers. The IPS LCD **104** also includes TFT layer arranged between the liquid crystal layer **112** and the rear polarizer **108**. The IPS LCD **104** further includes color filter (CF) layer or glass **114** arranged between the front polarizer **118** and the liquid crystal layer

**112**. The IPS LCD **104** further includes a backlight **130** configured to provide white light to the rear polarizer **108**.

The IPS LCD usually does not have common electrodes on the color filter (CF) glass, and so is vulnerable to electrostatic discharge (ESD). A conducting coating, for example, indium-tin oxide (ITO) coating, is often put on the top surface of the CF glass to help reduce vulnerability to ESD.

The IPS LCD **104** may also include an ITO coating **116** on a top surface of the CF glass **114**, such that the front polarizer **118** is disposed over the ITO coating **116**. The ITO coating **116** also provides shielding to the touch panel **102** from the TFT layer **110**. The front polarizer **118** may include an adhesive layer **136**, one or more optical films and/or compensation films **134**, a polyvinyl alcohol (PVA) with an iodine doping layer **126**, and a plastic film **128**, such as triacetylcellulose (TAC), cyclo-olefin polymer (COP), poly(ethylene terephthalate) (PET) or Poly(methyl methacrylate) (PMMA) film. The PVA absorbs light forming particular polarizers.

Generally, noise may be coupled from the IPS LCD **104** to the touch panel **102**. When the stackup of the touch panel and the IPS LCD becomes thinner, the noise in the touch panel may increase. In order to provide better shielding, the ITO coating may need to be thicker. However, optical transmittance may be reduced as a result of increasing thickness of the ITO coating. Acquiring both lower noise (or higher shielding) and higher light transmittance (or lower reflection) becomes challenges for thinner touch screen displays.

There may be a trade-off between aspects of product design and touch performance. Basically, it may be desirable not only to reduce product thickness, which may result in the touch panel and the LCD being closer to each other, but also to reduce light reflection from the front of the display. However, touch screen performance and operation may be affected by electrical noise.

There remains a need for developing techniques to resolve the above issues to meet the customer needs of new touch screen display products.

### SUMMARY

Embodiments described herein may provide an IPS LCD with a transparent conducting layer on a top surface of a front polarizer of the LCD. The conducting layer may include microscopic metal meshes, such as silver nano-wires (AGNW). Compared to the conventional display, the IPS LCD with a metal mesh coated front polarizer may improve display transmittance and reduce light reflection, while still providing adequate electrical shielding for a capacitive touch panel. The improved light transmittance may enable better power efficiency for the LCD, because less power would be required for the backlight of the LCD due to higher transmittance. The IPS LCD may also be thinner than the conventional display, due to replacement of the conventional thick ITO with a transparent AGNW mesh. The IPS LCD may also reduce the manufacturing complexity of a IPS-type of display by removing one post-cell process, as well as reducing the total reflectivity of the display.

In one embodiment, a polarizer includes a polarizer component having a top surface and an opposite bottom surface. The bottom surface is configured to couple to a color filter layer for a liquid crystal display. The polarizer also includes a transparent conducting layer disposed over the top surface. The transparent conducting layer being configured to electrically shield the LCD from a touch panel.

The polarizer further includes a coating layer disposed over the transparent conducting layer.

In another embodiment, an LCD device is provided. The LCD device includes a front polarizer and a transparent conductive layer on a top surface of the front polarizer. The LCD device also includes a color filter layer coupled to a bottom surface of the front polarizer and a rear polarizer at a bottom of a stack of the LCD. The LCD device further includes a liquid crystal layer between the rear polarizer and the color filter layer.

In yet another embodiment, a portable electronic device is provided. The electronic device includes a touch panel and an LCD (liquid crystal display). The LCD includes a front polarizer coupled to a bottom surface of the touch panel, a transparent conductive layer on a top surface of the front polarizer, and a color filter layer coupled to a bottom surface of the front polarizer. The LCD also includes a rear polarizer at a bottom of a stack of the LCD and a liquid crystal layer between the rear polarizer and the color filter layer.

In still yet another embodiment, a portable electronic device is provided. The device includes a touch panel and an LCD (liquid crystal display). The LCD includes a front polarizer coupled to a bottom surface of the touch panel, and a color filter layer coupled to a bottom surface of the front polarizer. The LCD also includes a transparent conductive layer on a top surface of the color filter and coupled between the front polarizer and the color filter. The LCD further includes a rear polarizer at a bottom of a stack of the LCD and a liquid crystal layer between the rear polarizer and the color filter layer.

Additional embodiments and features are set forth in part in the description that follows, and in part will become apparent to those skilled in the art upon examination of the specification or may be learned by the practice of the invention. A further understanding of the nature and advantages of the present invention may be realized by reference to the remaining portions of the specification and the drawings, which forms a part of this disclosure.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A illustrates a perspective view of an IPAD.

FIG. 1B illustrates a simplified cross-sectional diagram for a touch screen display (Prior Art).

FIG. 1C illustrates a cross-section of conventional IPS LCD (Prior Art).

FIG. 2A illustrates a stack of an IPS LCD with a transparent conducting layer in a first embodiment.

FIG. 2B illustrates a stack of an IPS LCD with a transparent conducting layer in a second embodiment.

FIG. 3A illustrates a first example touch screen display with a transparent conducting layer as shown in FIG. 2A or 2B.

FIG. 3B illustrates a second example touch screen display with a transparent conducting layer as shown in FIG. 2A or 2B.

FIG. 4 illustrates sample light reflections from various layers of an IPS LCD with an ITO coating on top of a CF glass.

FIG. 5 illustrates a sample total reflection contributed by various reflections from different coatings of area 1 of FIG. 4.

FIG. 6 illustrates a sample total reflection contributed by various reflections from different coatings of area 2 of FIG. 4.

FIG. 7 is a simplified system diagram for a touch screen display in an embodiment.

FIG. 8A illustrates LCM noise and the LCM noise coupled into the sense amplifier for the touch screen display of FIG. 7.

FIG. 8B shows spectra for the LCM noise of FIG. 8A.

FIG. 9A illustrates a top view of a first grounding configuration of a front polarizer with ITO as shown in FIG. 4.

FIG. 9B illustrates a top view of a second grounding configuration of a front polarizer without any conducting layer and/or grounding.

FIG. 9C illustrates a top view of a third grounding configuration of a front polarizer with AGNW as shown in FIG. 2A or 2B.

FIG. 9D illustrates a comparison of sample noises of the grounding configurations of FIGS. 9A-9C.

FIG. 10A illustrates a top view of a grounding configuration for a touch screen display with AGNW as shown in FIG. 2A or 2B.

FIG. 10B illustrates sample noise curves for the grounding configurations of FIG. 10A and FIG. 9B.

#### DETAILED DESCRIPTION

The present disclosure may be understood by reference to the following detailed description, taken in conjunction with the drawings as described below. It is noted that, for purposes of illustrative clarity, certain elements in various drawings may not be drawn to scale.

The present disclosure provides a thin conducting layer, such as silver nano wire (AGNW) mesh, to shield display noise coupled from a TFT layer of the LCD into a touch panel. The thin conducting layer may be placed at a different location than a conventional ITO layer in a typical IPS LCD. For example, the AGNW may be placed on the top surface of a front polarizer of a LCD. In contrast, the conventional ITO layer is typically placed on a top of a color filter (CF) glass or layer. The present disclosure potentially enables a thinner product design to meet both the shielding requirement and light transmission requirement.

FIG. 2A illustrates a stack of an IPS LCD with a transparent conducting layer in a first embodiment. An IPS LCD 200A includes a metal mesh coated front polarizer 218 formed from a transparent conducting layer 220, which may be silver nano wire (AGNW), on the top of a polarizer 118. Thin layers, such as hard coating, anti-glare (AG) coating, anti-fingerprint (AF) coating, or/and anti-reflection (AR) coating 232, may be placed on top of the AGNW to meet optical and reliability performance goals. The AGNW 220 may be a mesh. The mesh may be embedded in a dielectric matrix or a polymer matrix to provide more light transmission through the polarizer 218 than a solid film. The nano wires may have a few nanometers in diameter and tens of microns in length. The nano wires create a mesh that may not substantially degrade the light transmittance. A size of the mesh varies with the density of the nano wires in the polymer matrix. When the density of the nano wires increases, the sheet resistance of the AGNW coating may decrease and the mesh size may also decrease.

The polarizer 118 may include an adhesive layer 236, one or more optical films 234, a PVA with iodine layer 226, and a plastic film 228, such as TAC, COP, PET, or PMMA film among others. The plastic film 228 is a base film that protects the polarizer 118.

The IPS LCD 200A also includes an LCD 204. The LCD may have a backlight 230, a rear polarizer 208, a TFT layer 210, liquid crystal layer 212, and a CF layer or glass 214, similar to the conventional IPS LCD 104. However, the IPS LCD 200A does not include an ITO coating in this embodi-

ment. The backlight **230** is configured to provide white light to the rear polarizer **208**. For example, the backlight **230** may include a blue LED emitting blue light and red and green phosphors that emit red and green light when excited by the blue light from the blue LED. When all emitted colors are mixed, a white back light may be produced. Alternatively, the backlight LED **230** may include a blue LED emitting blue light and a yellow phosphor that emit yellow light when excited by blue light from the blue LED, again resulting in a white back light upon mixing. In a further example, the backlight **230** may also include a blue LED and red and green quantum dots to generate a white back light.

The LCD **204** also includes electrodes (not shown). The electrodes may be combined with the TFT layer. Each pixel of the LCD **204** has a corresponding transistor or switch for controlling voltage applied to the liquid crystal. The liquid crystal layer **212** may include rod-shaped polymers that naturally form into thin layers with a natural alignment. The electrodes may be made of a transparent conductor, such as an indium-tin-oxide material (commonly referred to as "ITO"). The two polarizers **218** and **208** are set at right angles. Normally, the LCD **204** may be opaque. When a voltage is applied across the liquid crystal layer **212**, the rod-shaped polymers align with the electric field and untwist. The voltage controls the light output from the front polarizer **218**. For example, when a voltage is applied to the liquid crystal layer **212**, the liquid crystal layer **212** rotates so that there is light output from the front polarizer **218**.

Transistors in the TFT layer **210** may take up only a small fraction of the area of each pixel; the rest of the silicon film may be etched away or essentially removed to allow light to pass through. Polycrystalline silicon may sometimes be used in displays requiring higher TFT performance. However, amorphous silicon-based TFTs are the most common technology due to its lower production cost. The silicon layer for the TFT-LCD is typically deposited over a glass substrate by using a PECVD process.

FIG. 2B shows that a thin ITO coating **216** may be included between the CF glass **214** and the front polarizer **218** in the IPS LCD **200B** in a second embodiment. In this embodiment, the thin ITO coating **216** may be placed on the top of the CF glass **214**. The ITO coating **216** may help with reducing ESD during processing. The ESD may be generated when stacking the front polarizer with the CF glass **214**. The thickness of the ITO coating **216** may be in a range of 10 nm to 30 nm so that the light transmission remains relatively high. Alternatively, an anti-static coating may be added on top of the CF glass **214** during integrating the front polarizer and the CF glass **214** to help reduce ESD. The anti-static coating may be removed prior to stacking the front polarizer on top of the CF glass **214**.

In this particular embodiment, the AGNW coating **220** may be placed on a front surface or top surface of the front polarizer **218**, rather than being placed between the front and rear polarizers. The AGNW may degrade a contrast ratio of the LCD, due to depolarization properties of the AGNW. The contrast ratio of a display refers to the ratio of the brightest white to the darkest black that the display may produce. Typically, a higher contrast ratio is associated with better image quality, such as improved clarity and/or brightness. "Light depolarization," as used herein, refers to the conversion of polarized light into unpolarized light. AGNW has a negative refraction index, which may depolarize light passing therethrough and so negatively impact the display's contrast ratio. By placing the AGNW coating **220** on the top surface of the front polarizer **218**, such depolarization may be minimized.

The AGNW **220** may be pre-coated onto the transparent plastic film **228**, such as triacetycellulose (TAC), cyclo olefin polymer (COP), Poly(methyl methacrylate) (PMMA) or poly(ethylene terephthalate) (PET), polyethylene naphthalate (PEN), polyether sulfone (PES), glass, reinforced glass, polycarbonate (PC), or mixtures of the foregoing thereof. The AGNW coated plastic film may be laminated with polyvinyl alcohol (PVA) which may be iodine doped and/or other optical films or compensation films for the polarizer **218**. The optical films or compensation films may compensate for phase difference. The doped PVA essentially absorbs light having particular directions. The AGNW **220** on the outer surface of the front polarizer **218** also does not de-polarize the light between the crossed polarizers of the LCD.

The AGNW **220** may have a sheet resistance ranging from 5 ohm/sq to 600 ohm/sq. The conducting layer, for example, the AGNW **220** may have sheet resistance less than 300 ohm/sq, or less than 150 ohm/sq. The AGNW **220** may have a high light transmittance (e.g. greater than 97% in the stack), a low light reflectance (e.g. less than 0.5%), and a low haze (e.g. less than 0.3%). In a particular embodiment, the AGNW coating **220** may have a light transmittance of 99% at an approximately 150 ohm/sq sheet resistance. In contrast, ITO coatings typically have a sheet resistance ranging from 500 to 1000 ohm/sq for the same transmittance.

Although the above example uses AGNW, it will be appreciated by those skilled in the art that the transparent conductive layer may also be nano wires including other metals, such as gold (Au), palladium (Pd), platinum (Pt), nickel (Ni), copper (copper), aluminum (Al), tin(Sn), and titanium (Ti) or a combination of these metals.

FIG. 3A illustrates a first example touch screen display with a transparent conducting layer as shown in FIG. 2A. Touch screen display **300A** includes a front polarizer **218** that has a transparent conducting layer or AGNW **220** on the top of a conventional front polarizer **118**. Touch screen display **300A** may also include an anti-reflection (AR) coating **312** on the top of the AGNW **220**. Touch screen display **300A** may further include a cover glass **302** bonded to a top surface of a touch panel **306** using a first adhesive **304**. Touch screen display **300A** may also include a plastic film (e.g. TAC) **310** bonded to a bottom surface of the touch panel **306** using a second adhesive **308**. The first adhesive **304** and the second adhesive **308** may be acrylic, polyurethane, epoxy and the like. The adhesives may also be double side adhesive tapes. Touch screen display **300A** may further include an anti-reflective (AR) coating **312A** on a bottom surface of the plastic film (e.g. TAC) **310**. FIGS. 3A and 3B show housing **138** coupled to the cover glass **302**. Note that there may be a gap between the housing **138** and the edges of the touch panel **306** and the LCD **204**. Alternatively, the housing **138** may contact the edges of the touch panel and the LCD **204**.

Touch screen display **300A** may also include an air gap **316** between two opposite AR coatings, i.e. the AR coating **312A** on the bottom surface of the plastic film **310** and the AR coating **312B** on the top of the transparent conducting layer or AGNW **220**. The AR coatings **312A** and **312B** may help reduce the reflections due to the air gap **316**. A reflection may generally occur at an interface between two materials or two layers with different refractive indexes. The reflection typically increases with the refractive index difference between the two materials. Air has a large difference in refractive index from the plastic film (e.g. TAC) **310**. The AR coating has a refractive index that is in between air and the plastic film, and so may reduce reflections otherwise

caused at the air-film junction. The LCD is similar to **200A** or **200B**, as shown in FIG. **2A** or FIG. **2B** and described above.

It will be appreciated by those skilled in the art that TAC **310** may be replaced with another transparent material, such as cyclo olefin polymer (COP), Poly(methyl methacrylate) (PMMA) or poly(ethylene terephthalate) (PET), polyethylene naphthalate (PEN), polyether sulfone (PES), glass, reinforced glass, polycarbonate (PC), or a mixture thereof

FIG. **3B** illustrates a second example touch screen display with a transparent conducting layer as shown in FIG. **2A**. Touch screen display **300B** includes a cover glass **302**, a first adhesive layer **304**, a touch panel **306**, and a second adhesive layer **308**, similar to touch screen display **300A**. Unlike touch screen display **300A**, there is no air gap in this embodiment such that the second adhesive layer **308** may be placed on the top of the transparent conducting layer (e.g. AGNW) **220**, which is in turn placed on the top surface of the front polarizer **218**. Note that there are no anti-reflection coatings **312A** and **312B** on either the bottom of the adhesive layer **308** or the top of the AGNW **220**. The TAC **310** is also absent in FIG. **3B** such that the second adhesive layer **308** may directly bond to the AGNW **220**.

It is known in the art that the ITO coating has a very high refractive index. Thus, the ITO may contribute a large portion to a total reflection from the front polarizer or the display due to a large difference between the refractive indexes of the ITO and the polarizer and/or display.

FIG. **4** illustrates sample light reflections from various layers of an IPS LCD with a relatively thick ITO coating. FIG. **4** illustrates a similar stack to FIG. **10**. The ITO coating **416** is similar to the conventional ITO coating **116**, but has a larger thickness than the conventional ITO coating **116**. There may be three main reflections from different surfaces or interfaces. Ray **402** illustrates reflection from a top surface of an anti-reflection (AR) layer **422**. Ray **404** illustrates reflection from the interface between the CF glass **214** and the ITO coating **416**.

The CF glass **214** includes a number of color filters **420B** arranged in subpixels, such as a red color filter, a green color filter, and a blue color filter. The red, green, and blue filters transmit a light having a specific wavelength of white light incident from the backlight source **230**. The filters **420B** transmit wavelengths of light corresponding to the color of each filter, and absorb other wavelengths. Accordingly, a light loss is generated in the liquid crystal display by the color filters. Each color filter is separated from another color filter by a black matrix **420A**, which includes ink that absorbs all color, acting like a black body.

A large portion of the black matrix **420A** is near an outer end of the CF glass **214**, while the CF filters **420B** and a small portion of the black matrix **420A** between the CF filters **420B** are in the middle portion of the CF glass **214**.

Turning to the left side of FIG. **4**, ray **406** illustrates reflection from the interface between the black matrix **420A** of the CF glass **214** and liquid crystal layer **212**. Now, turning to the right side of FIG. **4**, ray **408** illustrates reflection from the interface between the color filters **420B** of the CF glass **214** and the liquid crystal layer **212**.

The ITO contributes to a large portion of the total reflection of the polarizer. When the ITO becomes thicker, the reflection of the ITO becomes greater. Based upon modeling, reflections are estimated and exemplary results are presented below.

In an alternative embodiment, the ITO may be replaced by a transparent conductive layer, such as an AGNW layer, i.e. the AGNW layer on top of the CF glass **214**. The AGNW

layer may provide better light transmittance, low reflectance than the ITO while having a low sheet resistance to help shield the noise from the TFT to the touch panel. Unlike the embodiments as shown in FIGS. **2A-2B**, **3A-3B**, the image quality, such as clarity and/or brightness, may depend upon the AGNW depolarization properties.

FIG. **5** illustrates a sample total reflection contributed by various reflections from different coatings of area **1** of FIG. **4**. As discussed, earlier, the reflection of the ITO **416** varies with thickness or sheet resistance of the ITO. By using the sheet resistance of about 500 to 600 ohm/sq for the ITO, its reflection is estimated. This sheet resistance may be adequate for a relatively thick product, but not low enough for thinner display products. In a particular embodiment, a total reflection **500A** includes about 65% reflection **502** from the ITO coating **416**, about 10% reflection **504** from the AR coating **422**, about 18% reflection from the black matrix **420A**, and about 7% reflection from the CF filters **420B**. Accordingly, the ITO reflection constitutes a major portion of the total reflection **500A**.

As discussed above, the color filters **420B** and the black matrix **420A** are in the middle portion of the display so that a combined reflection from the black matrix and the color filters may represent the reflection for a product of area **2** of FIG. **4**. FIG. **6** illustrates a sample total reflection contributed by various reflections from different coatings of area **2** of FIG. **4**. The reflection is obtained based upon modeling using the sheet resistance of about 500 to 600 ohm/sq for the ITO **416**. The total reflection includes about 46% reflection from the ITO coating **416**, about 33% reflection from the top AR coating **422**, and about 33% reflection from a combination of black matrix **420A** and CF filters **420B**. Note that the reflection from the ITO coating **416** is still the largest contributor to the total reflection.

Generally, transmittance increases with sheet resistance for the ITO. The sheet resistance increases with decreasing thickness of the ITO **416**, while the transmittance decreases with the increasing thickness due to light absorption in the ITO coating. In one embodiment, the ITO coating may be about 50 nm thick and have a sheet resistance of about 150 ohm/sq and a light transmittance of about 90%. In another embodiment, the ITO coating may be 20 nm thick and have a sheet resistance of about 300 ohm/sq and a light transmittance of about 92%. In a further embodiment, the ITO coating may be 15 nm thick and have a sheet resistance of about 600 ohm/sq and a light transmittance of about 97%. These values may vary with deposition process.

In contrast, the transmittance for the AGNW may not vary substantially with the sheet resistance, and may be above 97% for all the sheet resistances. Compared to the ITO, the AGNW may be thinner, for example about 10 nm or less, which enables to deliver thinner touch screen displays. The AGNW may be embedded in a polymer matrix which may be pre-coated on a plastic film, such as a TAC film. The AGNW with the polymer matrix may have a thickness less than 1  $\mu\text{m}$ .

The AGNW may have less than 0.5% reflectance, which is much lower than the ITO. The reflectance for the AGNW may have less dependence upon the sheet resistance. In contrast, the reflectance for the ITO may increase with decreasing sheet resistance or increasing thickness, as the transmittance decreases with the increasing thickness due to absorption. Reflectance for the ITO under polarizer, i.e. for reflections as shown in FIG. **4** by Ray **404**, may be lower than the ITO, because the reflections may be reduced by the polarizer **218** on top of the ITO or AGNW.

In a particular embodiment, the haze may be below 0.5% or even below 0.3%. The reflectance for the AGNW may be below 0.5% or even 0.3%. The transmittance may be above 97%. An extra margin on the shielding to display capacitive noise may be achieved by adding the AGNW **220** on the top of the front polarizer and removal of the ITO coating **416** or reducing the ITO coating **416** to a minimum thickness.

Based upon the above results, it is noted that the ITO's optical properties are not adequate when the shielding requirement is met. Generally, lower sheet resistance provides more effective shielding. Less than 150 ohm/sq sheet resistance may be needed for sufficient shielding to noise for thinner display products. This requires the ITO layer to be relatively thick, such as about 50 nm thick or larger thickness, especially for ITO deposited at lower temperature, such as lower than 150° C. As a result, the thick ITO layer is highly reflective. The thick ITO layer **416** may also absorb blue light and transmit light in more yellow color. The loss of light transmittance may also be as high as 8% to achieve 150 ohm/sq sheet resistance. Practically, the ITO sheet resistance may be kept at a higher level as a trade-off between touch performance, display power, and display optical performance.

As demonstrated above, the thinner conducting layer (such as AGNW) may have both a low sheet resistance, such as about 150 ohm/sq or lower, and a very high transmittance, such as about 97% or higher, low reflectance, such as about 0.5% or lower, and a low haze, such as about 0.3% or lower. The AGNW **220** may be about 10 nm thick or even thinner. The AGNW **220** is much better than the conventional ITO layer **416**, because the AGNW is thinner, less reflective, and has higher transmission than the ITO, while having a low sheet resistance. This low sheet resistance provides an extra margin which helps tolerate a higher level of capacitive noise from the display, such that more power saving can be achieved.

FIG. 7 is a simplified system diagram for a touch screen display in an embodiment. System **700** includes an LCD **706**, sense electrode **702** and drive electrode **704** for a touch panel (not shown), and a sense amplifier **708**. The touch panel may capacitively sense touch and may have a capacitance  $C_{sig}$  between a sense electrode **702** and a drive electrode **704**. The  $C_{sig}$  may represent a touch signal from a user. FIG. 7 depicts an exemplary touch node, such as one defined by an intersection of sense electrode **702** and drive electrode **704**. The touch panel may include a number of such nodes. In an alternative embodiment, the node may be defined by other geometries than the intersection. The sense amplifier **708** is an exemplary receiving channel circuitry for the touch panel, which senses the total signal transmitted onto the drive electrode **704** through  $C_{sig}$ .

A typical active matrix LCD is switched line-by-line, at a line frequency ranging from kHz to MHz. This switching electrical field and its harmonics may be capacitively coupled into sense electrode **702** and drive electrode **704**, which causes inaccurate touch sensing, or total disfunction. The liquid crystal module (LCM) noise from the TFT and the LCM noise coupled into the sense amplifier **708** may be measured or monitored by an oscilloscope. The LCM noise may be coupled by a capacitance  $C_{toLCM}$  existing between the IPS LCD **104** and the touch panel **102**. The sense electrode **702** may be coupled to the sense amplifier **708**, which may include an input resistor with an input resistance  $R_{FB}$  at least one feedback resistor with a feedback resistance  $R_{FB}$ , a feedback capacitor with a feedback capacitance  $CFB$ , and operational amplifier **710** in some embodiment. The sense amplifier **708**. FIG. 7 shows the general case when both

resistive and capacitive feedback elements are utilized. The signal is coupled into the operational amplifier **710** as an inverting input. The non-inverting input to the operational amplifier **710** may be coupled to ground or a reference voltage.

FIG. 8A illustrates sample LCM noise from the LCD and the LCM noise coupled into the sense amplifier **708** of FIG. 7. The ITO coating is connected to a testing equipment ground. The sheet resistance of the ITO coating varies with the touch panel, and is normally in the range of 400 ohm/sq to 700 ohm/sq. As shown, trace **802** for LCM noise coupled into the sense amplifier **708** has similar noise patterns to trace **804** for LCM noise generated from the TFT source. FIG. 8B shows spectra for LCM noise of FIG. 8A. As shown, the LCM noise may be 0.3 mV<sub>rms</sub> in the frequency ranging from 100 kHz to 500 kHz. This is in the same range as the line frequency range. The noise may be much higher than the exemplary 0.3 mV<sub>rms</sub>, depending upon measurement conditions, the touch panel and display. The noise may be high enough to interfere the drive and thus may need to be reduced.

Proper grounding may help reduce the noise. In a particular embodiment, the polarizer may serve as an effective noise shielding layer and may provide ESD protection. The noise may be reduced by use of conductive tapes attached to a conductive layer such as ITO or AGNW. The conductive tapes may include copper. The noise may be further reduced by varying the attachment locations of the copper tapes to the AGNW or ITO.

FIG. 9A illustrates a top view of a first sample grounding configuration of a front polarizer with an ITO as shown in FIG. 4. Grounding configuration **900A** includes an ITO layer **908** under a polarizer **912** for grounding. In a particular embodiment, the ITO layer **908** may be on the outer surface of the CF glass of the LCD, as shown in FIG. 4. The polarizer **912** and the ITO layer **908** are in a substantially rectangular shape. The ITO layer **908** extends outwardly from the polarizer **912** from each side of the rectangle. In this configuration, a conductive tape **910** may contact the ITO layer **908** along four edges of the ITO layer **908**.

FIG. 9B illustrates a top view of a second sample grounding configuration of a front polarizer. Grounding configuration **900B** removes the ITO layer **908**, and thus has no need for the copper tape. Glass **914** covers the polarizer **912**. This is a configuration without any grounding.

FIG. 9C illustrates a top view of a third sample grounding configuration of a front polarizer with an AGNW mesh or an AGNW polarizer as shown in FIG. 2A or 2B. Configuration **900C** includes an AGNW polarizer **916**, which is in a substantially rectangular shape. The AGNW may be placed on the outer surface of the front polarizer so that the AGNW may be easily grounded. Conductive tapes **920A-D**, such as copper tapes, may be placed at the four corners and on top of the AGNW polarizer **916** to contact the AGNW on the outer surface of the polarizer. Although reference is generally made herein to copper tape, it should be appreciated that any suitable conductive tape may be used.

Two conductive bars **918A** and **918B** may contact two opposite edges of the AGNW polarizer **916**. For example, conductive bar **918A** may contact an edge of the AGNW polarizer **916** and may connect two conductive tapes **920A** and **920D** at two neighboring corners. Another conductive bar **918B** may contact an opposite edge of the AGNW polarizer **916** and may connect two conductive tapes **920B** and **920C** at two other neighboring corners. The conductive bars **918A** and **918B** may include or be formed from a

conductive paste, such as silver paste. The AGNW is coated on the polarizer and thus has the same size as the polarizer

The grounding configurations **900A**, **900B**, and **900C** have different grounding effects. To compare the grounding effects, noise may be measured with a spectrum analyzer, for example, Tektronix **3308A** Spectrum Analyzer. FIG. **9D** illustrates comparisons of noise from a polarizer with an ITO (grounding configuration **900A**), an AGNW polarizer (grounding configuration **900C**), and a polarizer without grounding (grounding configuration **900B**) in an embodiment. Note that curve **902** for the polarizer without ITO or AGNW shows the highest noise level, which generally is due to the fact that no grounding was provided to the polarizer. Curve **904** for the polarizer with an ITO on the outer surface of the CF glass reveals higher noise than the AGNW polarizer, but lower noise than the polarizer without ITO. As shown, the ITO coating on the outer-surface of CF glass provides a certain level of shielding to the display capacitive noise, especially when properly grounded. Curve **906** for the AGNW polarizer illustrates the lowest noise level, generally because the AGNW may have a lower sheet resistance than the ITO at a relatively thin coating, such as 10 nm thick.

FIG. **10A** illustrates a top view of a grounding configuration for the IPS LCD **200** with AGNW as shown in FIGS. **2A** and **2B**. As shown, a glass layer **1014** is at the bottom of an AGNW coating **220** which is below the active area of touch panel **1008**. The glass layer **1014** has a larger area than the active area of the touch panel **1008**. The AGNW coating **220** and the active area of the touch panel **1008** are substantially rectangular in shape. There are four positions **1**, **2**, **3**, and **4** at which copper tape is placed at the corner of the rectangle and on top of the AGNW coating **220**. One conductive bar **1012A** on top of the AGNW coating **220** may contact one edge of the AGNW coating **220** and may connect copper tapes **1010** at positions **1** and **2**. Another conductive bar **1012B** may contact an opposite edge of the AGNW coating **220** and may connect copper tapes at positions **3** and **4**. The conductive bars **1012A** and **1012B** may include conductive paste, such as silver paste.

The conductive bars and the conductive tapes are located outside the active area of the touch panel, which provides better grounding without impact on optical transmittance of the touch panel.

FIG. **10B** shows sample noise curves for several grounding configurations of FIG. **10A** and FIG. **9B** illustrating the effect of copper tape and the location of the copper tape on grounding. Typically, lower noise indicates better grounding. As shown, curve **1002** for grounding configuration **900B** shows the highest noise, because there is no grounding without ITO or AGNW as well as copper tapes.

Compared to curve **1002**, curve **1004** for grounding configuration **1000** with the copper tapes at corner positions **1** and **2** shows lower noise. Similarly, if copper tapes are placed at positions **3** and **4**, grounding results would be essentially the same as that of positions **1** and **2**.

Curve **1006** for the grounding configuration **1000** with the copper tapes at corner positions **1**, **2**, **3**, and **4** show the lowest noise. Curve **1009** represents the grounding configuration with copper tapes positioned at three corners, such as at any three of positions **1**, **2**, **3** and **4**. This suggests that the grounding configuration **1000** with the copper tape placed at three or four corners of the touch panel provides grounding and may reduce noise.

Generally, the ITO is deposited on the CF glass in a vacuum, such as by sputtering. The AGNW may be coated on a plastic film such as a TAC film by using a roll-to-roll

process. The roll-to-roll process is usually simpler and cheaper than the sputtering. Additionally, the AGNW may be easier to provide consistent thickness than the ITO during fabrication. For example, the ITO coating may be deposited over the CF glass by sputtering, which would have caused larger variation in a thicker ITO coating. This large variation in thickness may require a post processing to minimize the thickness variation and thus may increase fabrication complexity.

One of the benefits of the present disclosure is to enable a thinner display product. The transparent conducting layer may be much thinner than a conventional conducting layer, such as ITO, but provide the same sheet resistance and/or electrical shielding. The transparent conducting layer, such as silver nano-wire, may improve light transmittance and reduce reflection, and thus enable better power efficiency and/or longer battery life. High light transmittance and low sheet resistance may not be simultaneously achieved with the conventional conducting ITO layer. The AGNW layer may also reduce LCM noise from the TFT layer, which is coupled to a number of drive circuits. The AGNW layer may thus demonstrate a better shielding than the conventional conducting ITO layer.

Having described several embodiments, it will be recognized by those skilled in the art that various modifications, alternative constructions, and equivalents may be used without departing from the spirit of the invention. Additionally, a number of well-known processes and elements have not been described in order to avoid unnecessarily obscuring the present invention. Accordingly, the above description should not be taken as limiting the scope of the invention.

Those skilled in the art will appreciate that the presently disclosed embodiments teach by way of example and not by limitation. Therefore, the matter contained in the above description or shown in the accompanying drawings should be interpreted as illustrative and not in a limiting sense. The following claims are intended to cover all generic and specific features described herein, as well as all statements of the scope of the present method and system, which, as a matter of language, might be said to fall therebetween.

What is claimed is:

1. A display comprising:

- a color filter layer;
- a polarizer having opposing first and second surfaces;
- a transparent conductive layer on the first surface of the polarizer;
- an indium-tin oxide layer between the color filter layer and the second surface of the polarizer;
- a first conductive tape at a first corner of the transparent conductive layer;
- a second conductive tape at a second corner of the transparent conductive layer; and
- a conductive bar configured to connect the first and second conductive tapes.

2. The display defined in claim 1, wherein the transparent conductive layer comprises silver nano wire mesh.

3. The display defined in claim 1, wherein the transparent conductive layer has a transmittance of at least 97%.

4. The display defined in claim 1, wherein the display further comprises an anti-reflection coating on the transparent conductive layer.

5. The display defined in claim 1, wherein the indium tin oxide layer is a coating on the color filter layer, wherein the polarizer has a layer of adhesive that attaches the polarizer to the indium tin oxide layer, and wherein the display further comprises a cover glass that covers the polarizer.

## 13

6. A portable electronic device comprising:  
 a polarizer with first and second opposing surfaces;  
 a rectangular transparent conductive layer on the first  
 surface of the polarizer having first and second adjoining  
 edges that form a corner of the rectangular transparent  
 conductive layer;  
 an indium-tin oxide layer coupled to the second surface of  
 the polarizer; and  
 a conductive tape that overlaps the corner and extends  
 along the first and second adjoining edges, wherein the  
 conductive tape contacts the transparent conductive  
 layer.
7. The portable electronic device defined in claim 6,  
 wherein the transparent conductive layer comprises silver  
 nano wire mesh.
8. The portable electronic device defined in claim 6,  
 further comprising:  
 a glass layer, wherein the indium-tin oxide layer is inter-  
 posed between the glass layer and the polarizer.
9. The portable electronic device defined in claim 8,  
 wherein the indium-tin oxide layer is in direct contact with  
 the glass layer.
10. The portable electronic device defined in claim 8,  
 wherein the glass layer comprises a color filter glass layer.
11. The portable electronic device defined in claim 6,  
 further comprising:  
 a touch panel, wherein the transparent conductive layer is  
 interposed between the touch panel and the polarizer.
12. The portable electronic device defined in claim 11,  
 further comprising:  
 an adhesive layer, wherein the adhesive layer attaches the  
 touch panel directly to the transparent conductive layer.
13. A polarizer comprising:  
 a polarizer component;  
 a transparent conductive layer disposed over the polarizer  
 component;

## 14

- a first conductive tape contacting the transparent conduc-  
 tive layer at a first position;  
 a second conductive tape contacting the transparent conduc-  
 tive layer at a second position; and  
 a conductive bar configured to connect the first and  
 second conductive tapes.
14. The polarizer defined in claim 13, wherein the trans-  
 parent conductive layer comprises silver nano wire mesh.
15. The polarizer defined in claim 14, wherein the first  
 conductive tape and the second conductive tape each com-  
 prise copper.
16. The polarizer defined in claim 15, wherein the con-  
 ductive bar comprises silver.
17. An apparatus comprising:  
 a display;  
 a polarizer having opposing first and second surfaces;  
 a first transparent conductive coating on the display and  
 adjacent to the second surface of the polarizer;  
 a second transparent conductive coating on the first sur-  
 face of the polarizer; and  
 a conductive bar that contacts a portion of the second  
 transparent conductive coating along an edge of the  
 second transparent conductive coating.
18. The apparatus defined in claim 17, wherein the  
 conductive bar comprises silver.
19. The apparatus defined in claim 17, wherein the second  
 transparent conductive coating comprises silver nano wire  
 mesh.
20. The apparatus defined in claim 19, wherein the first  
 transparent conductive coating comprises a layer of indium  
 tin oxide.
21. The apparatus defined in claim 20, wherein the display  
 comprises a liquid crystal display.

\* \* \* \* \*

专利名称(译)	触摸屏显示器带有透明电屏蔽层		
公开(公告)号	<a href="#">US9612377</a>	公开(公告)日	2017-04-04
申请号	US14/965657	申请日	2015-12-10
[标]申请(专利权)人(译)	苹果公司		
申请(专利权)人(译)	苹果公司.		
当前申请(专利权)人(译)	苹果公司.		
[标]发明人	CHEN CHENG DORJGOTOV ENKHAMGALAN KUWABARA MASATO CHOI WONJAE GRUNTHANER MARTIN P LIN ALBERT ZHONG JOHN Z CHEN WEI HOTELLING STEVEN P YOUNGS LYNN R		
发明人	CHEN, CHENG DORJGOTOV, ENKHAMGALAN KUWABARA, MASATO CHOI, WONJAE GRUNTHANER, MARTIN P. LIN, ALBERT ZHONG, JOHN Z. CHEN, WEI HOTELLING, STEVEN P. YOUNGS, LYNN R.		
IPC分类号	G02F1/1333 G02F1/1335 G06F3/044 G02B1/11 G02B1/16 G06F3/041 H04N9/31 G02B5/30 G02F1/1343 G02F1/1362		
CPC分类号	G02B5/3033 G02B1/11 G02B1/16 G02F1/13338 G02F1/133308 G02F1/133502 G02F1/133514 G02F1/133528 G06F3/041 G06F3/044 G06F3/0412 H04N9/3105 H04N9/3197 G02F1/134363 G02F2001/133334 G02F2001/136218 G02F2202/28 G06F2203/04107		
其他公开文献	US20160097882A1		
外部链接	<a href="#">Espacenet</a> <a href="#">USPTO</a>		

#### 摘要(译)

偏振器包括具有顶表面和相对的底表面的偏振器部件。底表面被配置为耦合到用于液晶显示器的滤色器层。偏振器还包括设置在顶表面上方的透明导电层。透明导电层被配置为将LCD与触摸板电屏蔽。偏振器还包括设置在透明导电层上的涂层。

