



US009442331B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 9,442,331 B2**
(45) **Date of Patent:** **Sep. 13, 2016**

(54) **IN-PLANE SWITCHING MODE LIQUID CRYSTAL DISPLAY DEVICE INCLUDING POLARIZING PLATES HAVING COMPENSATION LAYERS AND METHOD OF FABRICATING THE SAME**

2413/13; G02F 2413/14; G02F 1/13439; G02B 5/3083; G02B 5/305

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,883,685 A 3/1999 Mazaki et al.
6,034,755 A 3/2000 Watanabe

(Continued)

FOREIGN PATENT DOCUMENTS

CN 1645205 A 7/2005
CN 1721940 A 1/2006

(Continued)

OTHER PUBLICATIONS

KIPO—Office Action for Korean Patent Application No. 10-2008-0132544—Issued on Jan. 25, 2013.

(Continued)

Primary Examiner — Huyen Ngo

(74) *Attorney, Agent, or Firm* — Morgan, Lewis & Bockius LLP

(57) **ABSTRACT**

An in-plane switching mode liquid crystal display device includes a first polarizing plate having a first compensating layer, a first polarizing layer and a first protecting layer on an outer surface of a first substrate, and a second polarizing plate having a second compensating layer, a second polarizing layer and a second protecting layer on an outer surface of a second substrate. The first compensating layer includes a positive B-plate where $n_z > n_x > n_y$, and the second compensating layer includes a positive B-plate where $n_z > n_x > n_y$, such that n_x , n_y , and n_z represents refractive indexes of the first and second compensating layers along the x, y, and z axes, respectively, wherein the x and y axes represents a plane direction of the first and second compensating layers, and the z-axis represents a thickness direction of the first and second compensating layers.

12 Claims, 16 Drawing Sheets

(71) Applicant: **LG DISPLAY CO., LTD.**, Seoul (KR)

(72) Inventors: **Jun-Hee Lee**, Gyeonggi-do (KR);
Jae-Hyun Lee, Busan (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 149 days.

(21) Appl. No.: **14/249,417**

(22) Filed: **Apr. 10, 2014**

(65) **Prior Publication Data**

US 2014/0218665 A1 Aug. 7, 2014

Related U.S. Application Data

(62) Division of application No. 12/630,380, filed on Dec. 3, 2009, now Pat. No. 8,743,320.

(30) **Foreign Application Priority Data**

Dec. 23, 2008 (KR) 10-2008-0132544

(51) **Int. Cl.**

G02F 1/13363 (2006.01)


G02F 1/1343 (2006.01)

(52) **U.S. Cl.**

CPC **G02F 1/134363** (2013.01); **G02F 1/13363** (2013.01); **G02F 1/13439** (2013.01)

(58) **Field of Classification Search**

CPC G02F 1/13363; G02F 1/133634; G02F 1/133528; G02F 2413/02; G02F 2001/133637; G02F 1/134363; G02F



(56)

References Cited

FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS


6,064,457 A 5/2000 Aminaka
6,977,696 B2 12/2005 Amimori et al.
7,532,283 B2 5/2009 Yano et al.
2005/0110933 A1 5/2005 Jeon et al.
2007/0154654 A1 7/2007 Greener et al.
2008/0239213 A1 10/2008 Ohmuro et al.
2009/0180059 A1 7/2009 Fukuda et al.
2014/0293198 A1* 10/2014 Iwasaki G02F 1/133632
349/96
2015/0036086 A1* 2/2015 Iwasaki G02F 1/133632
349/99

JP 2000-227520 A 8/2000
KR 10-2005-0049137 A 5/2005
KR 10-2008-0081007 A 9/2008
KR 10-2008-0086480 A 9/2008


OTHER PUBLICATIONS

Chinese Office Action dated May 12, 2011, with English translation.


* cited by examiner




(related art)
FIG. 1A




(related art)
FIG. 1B




(related art)
FIG. 2




(related art)
FIG. 3A



(related art)
FIG. 3B



(related art)
FIG. 4



(related art)
FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15

**IN-PLANE SWITCHING MODE LIQUID
CRYSTAL DISPLAY DEVICE INCLUDING
POLARIZING PLATES HAVING
COMPENSATION LAYERS AND METHOD
OF FABRICATING THE SAME**

This application is a divisional of U.S. patent application Ser. No. 12/630,380, filed on Dec. 3, 2009, which claims the benefit of Korean Patent Application No. 10-2008-0132544 filed on Dec. 23, 2008, the entire disclosure of each of which is hereby incorporated by reference in its entirety for all purposes.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present application relates to a liquid crystal display device, and more particularly, to an in-plane switching mode liquid crystal display device and a method of fabricating the in-plane switching mode liquid crystal display device.

2. Discussion of the Related Art

As information age progresses, display devices processing and displaying a large amount of information has been developed. Specifically, flat panel display (FPD) devices have been required for satisfying characteristics such as light weight, thin profile, and low power consumption. As a result, a liquid crystal display (LCD) devices having advantages in color reproducibility and profile have been suggested.

The LCD device uses the optical anisotropy and polarization properties of liquid crystal molecules to produce an image. Since the liquid crystal molecules have long thin shapes and a pretilt angle for alignment, the alignment direction of the liquid crystal molecules can be controlled by changing the pretilt angle due to an applied voltage. Accordingly, the alignment of the liquid crystal molecules changes in accordance with the alignment direction of the liquid crystal molecules controlled by applying a voltage to a liquid crystal layer. As a result, the image is displayed by modulating a polarized light due to the optical anisotropy of the liquid crystal molecules. Among several types of LCD devices, active matrix LCD (AM-LCD) devices where thin film transistors (TFTs) and pixel electrodes connected to the TFTs are disposed in matrix are currently widely used because of their high resolution and superior quality for displaying moving pictures.

A related art LCD device includes a color filter substrate having a common electrode, an array substrate having a pixel electrode, and a liquid crystal layer interposed between the color filter substrate and the array substrate. In the related art LCD device, the liquid crystal layer is driven by a vertical electric field between the pixel electrode and the common electrode. The related art LCD device provides a superior transmittance and a high aperture ratio. However, the related art LCD device has a narrow viewing angle because it is driven by the vertical electric field. To overcome the above disadvantages, various other types of LCD devices having wide viewing angles, such as in-plane switching mode (IPS) mode LCD device, have been developed.

FIG. 1A is a cross-sectional view of the related art in-plane switching mode liquid crystal display device in an ON state, and FIG. 1B is a cross-sectional view of the related art in-plane switching mode liquid crystal display device in an OFF state.

In FIGS. 1A and 1B, an in-plane switching (IPS) mode liquid crystal display (LCD) device 10 includes a first

substrate 20 having a thin film transistor (not shown), a second substrate 30 having a color filter layer and a black matrix and a liquid crystal layer 40 between the first and second substrates 20 and 30. A common electrode 22 and a pixel electrode 24 are alternately formed on the first substrate 20. An electric field E is generated according to a voltage applied to the common electrode 22 and the pixel electrode 24, and liquid crystal molecules 40a and 40b of the liquid crystal layer 40 are re-aligned along the electric field E.

In the ON state of FIG. 1A, the voltage is applied to the common electrode 22 and the pixel electrode 24, and the electric field E is generated. The electric field E has a vertical portion directly over the common electrode 22 and the pixel electrode 24, and a horizontal portion between the common electrode 22 and the pixel electrode 24. Accordingly, the first liquid crystal molecules 40a directly over the common electrode 22 and the pixel electrode 24 are not re-aligned, and the second liquid crystal molecules 40b between the common electrode 22 and the pixel electrode 24 are re-aligned along the electric field E. Since the liquid crystal layer 40 between the common electrode 22 and the pixel electrode 24 is re-aligned along the horizontal portion of the electric field E in the ON state, the IPS mode LCD device 10 displays images with a wide viewing angle. For example, the images may be displayed with a viewing angle of about 80° to about 85° along top, bottom, right and left directions with respect to a normal direction of the IPS mode LCD device.

In the OFF state of FIG. 1B, since the voltage is not applied to the common electrode 22 and the pixel electrode 24, and the electric field E is not generated. Accordingly, the first and second liquid crystal molecules 40a and 40b of the liquid crystal layer 40 are not re-aligned.

In the IPS mode LCD device according to the related art, a polarization state of the light passing through the IPS mode LCD device is adjusted by first and second polarizing plates on outer surfaces of the first and second substrates, respectively.

FIG. 2 is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to the related art.

In FIG. 2, an in-plane switching (IPS) mode liquid crystal display (LCD) device 10 includes first and second substrates 20 and 30 facing and spaced apart from each other, and a liquid crystal layer 40 between the first and second substrates 20 and 30. Although not shown in FIG. 2, a common electrode and a pixel electrode generating an electric field are formed on an inner surface of the first substrate 20.

In addition, first and second polarizing plates 52 and 54 are formed on outer surfaces of the first and second substrates 20 and 30, respectively. The first polarizing plate 52 includes a first supporting layer 52a, a first polarizing layer 52b and a first protecting layer 52c, and the second polarizing plate 54 includes a second supporting layer 54a, a second polarizing layer 54b and a second protecting layer 54c. Each of the first and second supporting layers 52a and 54a includes tri-acetyl cellulose (TAC) having a retardation of about 0. Each of the first and second polarizing layers 52b and 54b determining a polarization property is formed by stretching poly-vinyl alcohol (PVA) adsorbing iodine (I) or dye. Each of the first and second protecting layers 52c and 54c also includes TAC.

When the first and second polarizing plates 52 and 54 are disposed such that absorption axes of the first and second polarizing plates 52 and 54 are perpendicular to each other, the IPS mode LCD device is operated in a normally black

mode. Accordingly, when the IPS mode LCD device **10** has an OFF state, the horizontal electric field is not generated between the common electrode and the pixel electrode, and the liquid crystal molecules of the liquid crystal layer **40** are not re-aligned so that the incident light can penetrate the liquid crystal layer **40** without polarization. As a result, the linearly-polarized light passing through the first polarizing plate **52** to have a polarization axis perpendicular to the absorption axis of the first polarizing plate **52** penetrates the liquid crystal layer **40** without change of polarization state, and is completely absorbed by the second polarizing plate **54** having an absorption axis perpendicular to the absorption axis of the first polarizing plate **52**, thereby a black image displayed.

When the IPS mode LCD device has an OFF state, although the black image is displayed along a normal direction of the IPS mode LCD device, the brightness of the black image along up, down, right and left oblique directions of the IPS mode LCD device may increase due to light leakage. The light leakage is generated because the absorption axes of the polarizing plates are not perpendicular to each other.

FIGS. **3A** and **3B** are views showing absorption axes of polarizing plates of an in-plane switching mode liquid crystal display device according to the related art when viewed at a normal viewing angle and at an oblique viewing angle, respectively.

In FIG. **3A**, when an in-plane switching (IPS) mode liquid crystal display (LCD) device **10** (of FIG. **2**) is viewed at a normal viewing angle, a first absorption axis **ABS1** of a first polarizing plate **52** on an outer surface of a first substrate **20** (of FIG. **2**) and a second absorption axis **ABS2** of a second polarizing plate **54** on an outer surface of a second substrate **30** (of FIG. **2**) cross each other with a first angle α_1 .

In FIG. **3B**, however, when the IPS mode LCD device **10** is viewed at an oblique viewing angle, the first absorption axis **ABS1** of the first polarizing plate **52** and the second absorption axis **ABS2** of the second polarizing plate **54** cross each other with a second angle α_2 greater than the first angle α_1 . Accordingly, the first absorption axis **ABS1** of FIG. **3B** for the obliquely incident light to the IPS mode LCD device **10** is counterclockwise rotated with respect to the first absorption axis **ABS1** of FIG. **3A** for the normally incident light to the IPS mode LCD device **10**, and the second absorption axis **ABS2** of FIG. **3B** for the obliquely incident light to the IPS mode LCD device **10** is clockwise rotated with respect to the second absorption axis **ABS2** of FIG. **3A** for the normally incident light to the IPS mode LCD device **10**.

As a result, the obliquely incident light to the IPS mode LCD device **10** passes through the first polarizing plate **52** and is linearly polarized to have a polarization state having a polarization axis **PL** perpendicular to the first absorption axis **ABS1** of FIG. **3B**. However, since the polarization axis **PL** is not parallel to the second absorption axis **ABS2**, the obliquely incident light is not absorbed by the second polarizing plate **54** to cause the light leakage. Therefore, when the IPS mode LCD device **10** is viewed along up, down, right and left oblique directions, the luminosity of the black image is deteriorated due to the light leakage, thereby contrast ratio reduced.

FIG. **4** is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to the related art, and FIG. **5** is a view showing a brightness contour line of a black

image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to the related art.

In FIG. **4**, the obliquely incident light to an in-plane switching (IPS) mode liquid crystal display (LCD) device passes through a first polarizing plate **52** (of FIG. **2**) and is linearly polarized to have a polarization state having a polarization axis **PL** perpendicular to a first absorption axis **ABS1**. Since a second absorption axis **ABS2** of a second polarizing plate **54** (of FIG. **2**) is not perpendicular to the first absorption axis **ABS1**, the polarization axis **PL** is located at different position in the Poincare sphere from the second absorption axis **ABS2**. Accordingly, the obliquely incident light does not display a complete black image and light leakage occurs.

In FIG. **5**, the first polarizing plate **52** and the second polarizing plate **54** are disposed such that the first absorption axis **ABS1** and the second absorption axis **ABS2** are parallel to a horizontal direction and a vertical direction, respectively. When the IPS mode LCD device displays a black image, a complete black image without light leakage is viewed at a normal viewing angle having a polar angle θ of about 0° with respect to a z-axis normal to the IPS mode LCD device. However, a light leakage occurs at an oblique viewing angle along diagonal directions having azimuthal angles ϕ of about 45° , 135° , 225° and 315° with respect to an x-axis or a y-axis parallel to the IPS mode LCD device. Accordingly, brightness of the black image increases and contrast ratio is reduced at the oblique viewing angle of the IPS mode LCD device. For example, the black image may have relatively high brightness of about 0.018331 (arbitrary unit: A.U.) at an oblique viewing angle having a polar angle of about 60° and an azimuthal angle of about 45° . Although a compensation film having a complex retardation is used for the IPS mode LCD device to solve the above problems, the retardation film causes complication in fabrication process and increase in fabrication cost.

SUMMARY OF THE INVENTION

Accordingly, the present invention is directed to an in-plane switching mode liquid crystal display device and a method of fabricating the same that substantially obviates one or more of the problems due to limitations and disadvantages of the related art.

An object of the present invention is to provide an in-plane switching mode liquid crystal display device where brightness of a black image at an oblique viewing angle is reduced and contrast ratio is improved and a method of fabricating the in-plane switching mode liquid crystal display device.

Another object of the present invention is to provide an in-plane switching mode liquid crystal display device where a biaxial film having a retardation value is used as a supporting layer of a polarizing plate and a method of fabricating the in-plane switching mode liquid crystal display device.

Additional features and advantages of the invention will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, an in-plane switching mode liquid crystal

display device includes: first and second substrates facing and spaced apart from each other; a first polarizing plate including a supporting layer, a first polarizing layer and a first protecting layer sequentially on an outer surface of the first substrate; a second polarizing plate including a first compensating layer, a second compensating layer, a second polarizing layer and a second protecting layer sequentially on an outer surface of the second substrate, the first and second compensating layers including positive and negative biaxial retardation films, respectively; and a liquid crystal layer between the first and second substrates.

In another aspect, an in-plane switching mode liquid crystal display device includes: first and second substrates facing and spaced apart from each other; a first polarizing plate including a first compensating layer, a first polarizing layer and a first protecting layer sequentially on an outer surface of the first substrate, the first compensating layer including a positive biaxial retardation film; a second polarizing plate including a second compensating layer, a second polarizing layer and a second protecting layer sequentially on an outer surface of the second substrate, the second compensating layer including a positive biaxial retardation film; and a liquid crystal layer between the first and second substrates.

In another aspect, a method of fabricating an in-plane switching mode liquid crystal display device includes: forming a liquid crystal layer between first and second substrates facing and spaced apart from each other; forming a first polarizing plate including a supporting layer, a first polarizing layer and a first protecting layer on an outer surface of the first substrate; and forming a second polarizing plate including a first compensating layer, a second compensating layer, a second polarizing layer and a second protecting layer on an outer surface of the second substrate, the first and second compensating layers including positive and negative biaxial retardation films, respectively.

In another aspect, a method of fabricating an in-plane switching mode liquid crystal display device includes: forming a liquid crystal layer between first and second substrates facing and spaced apart from each other; forming a first polarizing plate including a first compensating layer, a first polarizing layer and a first protecting layer on an outer surface of the first substrate, the first compensating layer including a positive biaxial retardation film; and forming a second polarizing plate including a second compensating layer, a second polarizing layer and a second protecting layer on an outer surface of the second substrate, the second compensating layer including a positive biaxial retardation film.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention. In the drawings:

FIG. 1A is a cross-sectional view of the related art in-plane switching mode liquid crystal display device in an ON state;

FIG. 1B is a cross-sectional view of the related art in-plane switching mode liquid crystal display device in an OFF state;

FIG. 2 is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to the related art;

FIGS. 3A and 3B are views showing absorption axes of polarizing plates of an in-plane switching mode liquid crystal display device according to the related art when viewed at a normal viewing angle and at an oblique viewing angle, respectively;

FIG. 4 is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to the related art;

FIG. 5 is a view showing a brightness contour line of a black image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to the related art;

FIG. 6 is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIGS. 7A and 7B are views illustrating positive and negative biaxial retardation films, respectively, for a polarizing plate of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 8 is an exploded perspective view showing an absorption axis of a polarizing plate and polarization states of incident light passing through the polarization plate of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 9 is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 10 is view showing a brightness contour line of a black image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 11 is a view showing brightness distribution at an oblique viewing angle with respect to retardation values of first and second compensating layers of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 12 is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention;

FIG. 13 is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention;

FIG. 14 is view showing a brightness contour line of a black image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention; and

FIG. 15 is a view showing brightness distribution at an oblique viewing angle with respect to retardation values of first and second compensating layers of an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Reference will now be made in detail to the embodiments of the present invention, examples of which are illustrated in

the accompanying drawings. Wherever possible, similar reference numbers will be used to refer to the same or similar parts.

FIG. 6 is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention.

In FIG. 6, an in-plane switching (IPS) mode liquid crystal display (LCD) device 110 includes first and second substrates 120 and 130 facing and spaced apart from each other and a liquid crystal layer 140 between the first and second substrates 120 and 130.

A gate electrode 121 and a common electrode 122 are formed on an inner surface of the first substrate 120, and a gate insulating layer 123 is formed on the gate electrode 121 and the common electrode 122. An active layer 124 including an intrinsic semiconductor layer and an impurity-doped semiconductor layer is formed on the gate insulating layer 123 over the gate electrode 121, and source and drain electrodes 125 and 126 spaced apart from each other are formed on the active layer 124. In addition, a pixel electrode 127 connected to the drain electrode 126 is formed on the gate insulating layer 123. The pixel electrode 127 and the common electrode 122 are disposed to be horizontally spaced apart from each other. The gate electrode 121, the active layer 124, the source electrode 125 and the drain electrode 126 constitute a thin film transistor (TFT) T.

Although not shown in FIG. 6, a gate line and a data line are formed over the inner surface of the first substrate 120, and the TFT T is connected to the gate line and the data line. Further, a data signal of the data line is applied to the pixel electrode 127 according to a gate signal of the gate line by the TFT T. A passivation layer 128 is formed on the source electrode 125, the drain electrode 126 and the pixel electrode 127. A liquid crystal layer 140 is formed between the passivation layer 128 and an inner surface of the second substrate 130.

First and second polarizing plates 152 and 154 are formed on outer surfaces of the first and second substrates 120 and 130, respectively. Although not shown in FIG. 6, adhesive layers may be formed between the first substrate 120 and the first polarizing plate 152 and between the second substrate 130 and the second polarizing plate 154 for attachment.

The first polarizing plate 152 includes a first supporting layer 152a, a first polarizing layer 152b and a first protecting layer 152c. The first supporting layer 152a may include tri-acetyl cellulose (TAC) having a retardation of about 0. The first polarizing layer 152b substantially determining a polarization property may be formed by stretching polyvinyl alcohol (PVA) adsorbing iodine (I) or dye. In addition, the first protecting layer 152c may include TAC.

The second polarizing plate 154 includes a first compensating layer 154a, a second compensating layer 154b, a second polarizing layer 154c and a second protecting layer 154d. The first compensating layer 154a includes a positive biaxial retardation film and may be formed by stretching an acrylic resin film such as a polymethyl methacrylate (PMMA) film. The second compensating layer 154b includes a negative biaxial retardation film and may be formed by stretching a cyclo-olefin polymer (COP) film. In addition, the second polarizing layer 154c substantially determining a polarization property may be formed by stretching polyvinyl alcohol (PVA) adsorbing iodine (I) or dye, and the second protecting layer 154d may include TAC.

Hereinafter, the retardation film for the first and second compensating layers 154a and 154b of the second polarizing plate 154 will be illustrated.

FIGS. 7A and 7B are views illustrating positive and negative biaxial retardation films, respectively, for a polarizing plate of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention.

A retardation film may be classified into uniaxial and biaxial types according to the number of optical axes. In addition, a retardation film may be classified into positive and negative types according to difference between refractive indexes along an optical axis direction and along the other direction different than the optical axis direction. For example, a retardation film having one optical axis may be classified under a uniaxial type and a retardation film having two optical axes may be classified under a biaxial type. In addition, a retardation film where a refractive index along an optical axis direction is greater than a refractive index along the other direction may be classified under a positive type, and a retardation film where a refractive index along an optical axis direction is smaller than a refractive index along the other direction may be classified under a negative type.

A retardation film may be represented by refractive indexes along directions in an xyz coordinate. For example, when a retardation film is located in an xy plane, the x axis and the y axis represent a plane direction of the retardation film, and the retardation film has refractive indexes of n_x , n_y and n_z along the x, y and z axes, respectively. In addition, the retardation value of the retardation film along the plane direction, i.e., along the x axis or the y axis, is denoted by R_{in} , which is defined by $(n_x - n_y)$ and may be referred to as a plane directional retardation value, and the retardation value of the retardation film along a thickness direction, i.e., along the z axis, is denoted by R_{th} , which is defined by $(n_z - n_x)$ or $(n_z - n_y)$ and may be referred to as a thickness directional retardation value. A positive A-plate and a negative A-plate of a uniaxial retardation film satisfy relations of $(n_x > n_y = n_z)$ and $(n_x < n_y = n_z)$, respectively. Further, a positive C-plate and a negative C-plate satisfy relations of $(n_z > n_x = n_y)$ and $(n_z < n_x = n_y)$, respectively. Moreover, as shown in FIGS. 7A and 7B, a positive B-plate and a negative B-plate of a biaxial retardation film satisfy relations of $(n_z > n_x > n_y)$ and $(n_x > n_y > n_z)$, respectively.

The first and second compensating layers 154a and 154b (of FIG. 6) in the second polarizing plate 154 of the IPS mode LCD device 110 (of FIG. 6) may be formed of the positive and negative B-plates of FIGS. 7A and 7B, respectively. In the IPS mode LCD device 110, since the obliquely incident light passes through the first polarizing plate 152 and the polarization state of the obliquely incident light is changed by the first and second compensating layers 154a and 154b of the second polarizing plate 154, the obliquely incident light is completely absorbed by the second polarizing layer 154c of the second polarizing plate 154.

FIG. 8 is an exploded perspective view showing an absorption axis of a polarizing plate and polarization states of incident light passing through the polarization plate of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention, FIG. 9 is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention, and FIG. 10 is view showing a brightness contour line of a black image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention.

In FIG. 8, while passing through a first polarizing plate 152b having a first absorption axis ABS1, an obliquely incident light of an unpolarized state to an in-plane switch-

ing (IPS) mode liquid crystal display (LCD) device **110** (of FIG. **6**) is linearly polarized to have a first polarization state having a first polarization axis **PL1** such that a polarization component parallel to the first absorption axis **ABS1** is removed and a polarization component perpendicular to the first absorption axis **ABS1** remains. In addition, the light of the first polarization state is elliptically polarized to have a second polarization state having a rotating second polarization axis **PL2** while passing through a first compensating layer **154a** of a second polarizing plate **154** (of FIG. **6**), and the light of the second polarization state is linearly polarized to have a third polarization state having a third polarization axis **PL3** while passing through a second compensating layer **154b** of the second polarizing plate **154**. Since the third polarization axis **PL3** is parallel to a second absorption axis **ABS2** of a second polarizing layer **154c** of the second polarizing plate **154**, the light of the third polarization state is absorbed by the second polarizing plate **154**. As a result, the obliquely incident light is completely absorbed and the IPS mode LCD device **110** displays a black image. Each of optical axes of the first and second compensating layers **154a** and **154b** is parallel to the first absorption axis **ABS1** and perpendicular to the second absorption axis **ABS2**.

Although the first absorption axis **ABS1** of the first polarizing layer **152b** is not perpendicular to the second absorption axis **ABS2** of the second polarizing layer **152c** at an oblique viewing angle of the IPS mode LCD device **110**, the obliquely incident light has the first polarization state having the first polarization axis **PL1** perpendicular to the first absorption axis **ABS1** after passing through the first polarizing layer **152b** and has the third polarization state having the third polarization axis **PL3** parallel to the second absorption axis **ABS2** after passing through the first and second compensating layers **154a** and **154b**. Accordingly, the obliquely incident light is completely absorbed by the second polarizing layer **154c**.

The Poincare sphere representing all polarization states of light on a sphere has been widely used for designing a compensation film because polarization states are easily anticipated by using the Poincare sphere when an optical axis and a retardation value are given. An equator of the Poincare sphere represents a linear polarization. A positive third pole **S3** and a negative third pole—**S3** represent a left handed circular polarization and a right handed circular polarization, respectively. In addition, an upper hemisphere and a lower hemisphere represent a left handed elliptical polarization and a right handed elliptical polarization, respectively.

In FIG. **9**, red, green and blue (R, G and B) obliquely incident lights are linearly polarized by the first polarizing plate **152** having the first absorption axis **ABS1** to have the first polarization state having the first polarization axis **PL1** that is located adjacent to the equator of the Poincare sphere. In addition, the R, G and B obliquely incident lights is elliptically polarized by the first compensating layer **152a** to have the second polarization state having the rotating second polarization axis **PL2** that has the same longitude as the first polarization axis **PL1** on the Poincare sphere, and is linearly polarized by the second compensating layer **152b** to have the third polarization state having the third polarization axis **PL3** that is located adjacent to the equator of the Poincare sphere. Since the third polarization axis **PL3** has substantially the same coordinates as the second absorption axis **ABS2** of the second polarizing plate **154**, the R, G and B obliquely incident lights may be completely absorbed by the second polarizing plate **154**. As a result, the IPS mode LCD device **110** displays the black image even with the obliquely

incident light, and quality of the black image and contrast ratio of the IPS mode LCD device **110** are improved.

In FIG. **10**, when the IPS mode LCD device **110** displays a black image, a complete black image without light leakage is viewed at oblique viewing angles along diagonal directions having azimuthal angles ϕ of about 45° , 135° , 225° and 315° as well as at a normal viewing angle having a polar angle θ of about 0° . For example, the black image may have a brightness of about 0.000898 (arbitrary unit: A.U.) at an oblique viewing angle having a polar angle θ of about 60° and an azimuthal angle ϕ of about 45° . Accordingly, at the oblique viewing angle, the brightness of the black image may be reduced to about 5% of the brightness of the black image, which may be about 0.018331, of the related art IPS mode LCD device. Therefore, the brightness of the black image and the contrast ratio are improved at the oblique viewing angles of the IPS mode LCD device of the first embodiment of the present invention.

The retardation values of the first and second compensating layers **154a** and **154b** may be determined according to the minimum value of the brightness of the black image at the oblique viewing angles.

FIG. **11** and TABLE 1 are a view and a table, respectively, showing brightness distribution at an oblique viewing angle with respect to retardation values of first and second compensating layers of an in-plane switching mode liquid crystal display device according to a first embodiment of the present invention.

TABLE 1

		second compensating layer (Rin, nm)				
		80	90	100	115	125
first	50	6316	5003	4033	3671	4420
compensating	60	5447	3826	3623	2197	2939
layer	70	5265	3494	2180	1613	2347
(Rth, nm)	80	5405	3347	1819	898	1464
	90	5728	3532	1936	1088	1173

In FIG. **11** and TABLE 1, the brightness of the black image is minimized when a retardation value **Rth** of the positive B-plate of the first compensating layer **154a** (of FIG. **6**) along a thickness direction (z axis) is within a range of about 60 nm to about 100 nm and a retardation value **Rin** of the negative B-plate of the second compensating layer **154b** (of FIG. **6**) along a plane direction (x axis or y axis) is within a range of about 90 nm to about 130 nm. For example, when the retardation value **Rth** of the first compensating layer **154a** is within a range of about 70 nm to about 90 nm and the retardation value **Rin** of the second compensating layer **154b** is within a range of about 90 nm to about 110 nm, the black image may have the minimum brightness.

FIG. **12** is a cross-sectional view showing an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention.

In FIG. **12**, an in-plane switching (IPS) mode liquid crystal display (LCD) device **210** includes first and second substrates **220** and **230** facing and spaced apart from each other and a liquid crystal layer **240** between the first and second substrates **220** and **230**.

A gate electrode **221** and a common electrode **222** are formed on an inner surface of the first substrate **220**, and a gate insulating layer **223** is formed on the gate electrode **221** and the common electrode **222**. An active layer **224** including an intrinsic semiconductor layer and an impurity-doped semiconductor layer is formed on the gate insulating layer

223 over the gate electrode 221, and source and drain electrodes 225 and 226 spaced apart from each other are formed on the active layer 224. In addition, a pixel electrode 227 connected to the drain electrode 226 is formed on the gate insulating layer 223. The pixel electrode 227 and the common electrode 222 are disposed to be horizontally spaced apart from each other. The gate electrode 221, the active layer 224, the source electrode 225 and the drain electrode 226 constitute a thin film transistor (TFT) T.

Although not shown in FIG. 12, a gate line and a data line are formed over the inner surface of the first substrate 220, and the TFT T is connected to the gate line and the data line. Further, a data signal of the data line is applied to the pixel electrode 227 according to a gate signal of the gate line by the TFT T. A passivation layer 228 is formed on the source electrode 225, the drain electrode 226 and the pixel electrode 227. A liquid crystal layer 240 is formed between the passivation layer 228 and an inner surface of the second substrate 230.

First and second polarizing plates 252 and 254 are formed on outer surfaces of the first and second substrates 220 and 230, respectively. Although not shown in FIG. 12, adhesive layers may be formed between the first substrate 220 and the first polarizing plate 252 and between the second substrate 230 and the second polarizing plate 254 for attachment.

The first polarizing plate 252 includes a first compensating layer 252a, a first polarizing layer 252b and a first protecting layer 252c. The first compensating layer 252a may include a positive biaxial retardation film and may be formed by stretching an acrylic resin film such as a polymethyl methacrylate (PMMA) film. The first polarizing layer 252b substantially determining a polarization property may be formed by stretching poly-vinyl alcohol (PVA) adsorbing iodine (I) or dye. In addition, the first protecting layer 252c may include TAC.

The second polarizing plate 254 includes a second compensating layer 254a, a second polarizing layer 254b and a second protecting layer 254c. The second compensating layer 254a includes a positive biaxial retardation film and may be formed by stretching an acrylic resin film such as a polymethyl methacrylate (PMMA) film. The second polarizing layer 254b substantially determining a polarization property may be formed by stretching poly-vinyl alcohol (PVA) adsorbing iodine (I) or dye, and the second protecting layer 254c may include TAC.

Each of the first and second compensating layers 252a and 254a of the first and second polarizing plates 252 and 254 may be formed of a positive B-plate satisfying a relation of $n_z > n_x > n_y$. After the obliquely incident light to the IPS mode LCD device 210 passes through the first polarizing layer 252b of the first polarizing plate 252, the polarization state of the obliquely incident light is changed by the first and second compensating layers 252a and 254a of the first and second polarizing plates 252 and 254 to be completely absorbed by the second polarizing layer 254b of the second polarizing plate 254.

FIG. 13 is a Poincare sphere showing polarization states of obliquely incident light to an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention, and FIG. 14 is view showing a brightness contour line of a black image with respect to a viewing angle in an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention.

In FIG. 13, while red, green and blue (R, G and B) obliquely incident lights of an unpolarized state pass through the first polarizing layer 252b (of FIG. 12) of the first polarizing plate 252 (of FIG. 12) having the first absorption axis ABS1, a component parallel to the first absorption axis ABS1 is absorbed and a component perpendicular to the first absorption axis ABS1 remains. As a result, the R, G and B obliquely incident lights have a first polarization state having a first polarization axis PL1 that is located adjacent to the equator of the Poincare sphere. In addition, the first polarization state of the R, G and B obliquely incident lights is changed to an elliptic second polarization state having the rotating second polarization axis PL2 while passing through the first compensating layer 252a (of FIG. 12) of the first polarizing plate 252, and the second polarization state of the R, G and B obliquely incident lights is changed to an elliptic third polarization state having a rotating third polarization axis PL3 while passing through the liquid crystal layer 240 (of FIG. 12). Further, the third polarization state of the R, G and B obliquely incident lights is changed to a to an elliptic fourth polarization state having the rotating fourth polarization axis PL4 while passing through the second compensating layer 254a (of FIG. 12) of the second polarizing plate 254 (of FIG. 12). Since the fourth polarization axis PL4 has substantially the same coordinates as the second absorption axis ABS2 of the second polarizing layer 254b, the R, G and B obliquely incident lights may be completely absorbed by the second polarizing plate 254. As a result, the IPS mode LCD device 210 displays the black image even with the obliquely incident light, and quality of the black image and contrast ratio of the IPS mode LCD device 210 are improved. An optical axis of the first compensating layer 252a is parallel to the first absorption axis ABS1 and perpendicular to the second absorption axis ABS2, and an optical axis of the second compensating layer 254a is perpendicular to the first absorption axis ABS1 and parallel to the second absorption axis ABS2.

In FIG. 14, when the IPS mode LCD device 210 displays a black image, a complete black image without light leakage is viewed at oblique viewing angles along diagonal directions having azimuthal angles ϕ of about 45°, 135°, 225° and 315° as well as at a normal viewing angle having a polar angle θ of about 0°. For example, the black image may have a brightness of about 0.001295 (arbitrary unit: A.U.) at an oblique viewing angle having a polar angle θ of about 60° and an azimuthal angle ϕ of about 45°. Accordingly, at the oblique viewing angle, the brightness of the black image may be reduced to about 7% of the brightness of the black image, which may be about 0.018331, of the related art IPS mode LCD device. Therefore, the brightness of the black image and the contrast ratio are improved at the oblique viewing angles of the IPS mode LCD device of the second embodiment of the present invention.

The retardation values of the first and second compensating layers 252a and 254a may be determined according to the minimum value of the brightness of the black image at the oblique viewing angles.

FIG. 15 and TABLE 2 are a view and a table, respectively, showing brightness distribution at an oblique viewing angle with respect to retardation values of first and second compensating layers of an in-plane switching mode liquid crystal display device according to a second embodiment of the present invention.

TABLE 2

	second compensating layer (R _{in} , nm)					
	160	180	200	220	240	
first compensating layer (R _{in} , nm)	65	4283	3284	3245	4181	6059
second compensating layer (R _{in} , nm)	75	4213	2691	2234	2878	4607
	85	5523	2866	1447	1349	3026
	95	6886	3629	1829	1295	2958
	105	8702	4876	2756	1760	3137

In FIG. 15 and TABLE 2, the brightness of the black image is minimized when a retardation value R_{in} of the positive B-plate of the first compensating layer 252a (of FIG. 12) along a plane direction (x axis or y axis) is within a range of about 60 nm to about 110 nm and a retardation value R_{in} of the positive B-plate of the second compensating layer 254a (of FIG. 12) along a plane direction (x axis or y axis) is within a range of about 170 nm to about 240 nm. For example, when the retardation value R_{in} of the first compensating layer 252a is within a range of about 80 nm to about 100 nm and the retardation value R_{in} of the second compensating layer 254b is within a range of about 190 nm to about 220 nm, the black image may have the minimum brightness.

Consequently, in the IPS mode LCD device according to the present invention, since each of the first and second polarizing plates includes a biaxial retardation film, the obliquely incident light is compensated and the light leakage at the oblique viewing angle is prevented. As a result, the brightness of the black image at the oblique viewing angle is reduced, and the contrast ratio of the IPS mode LCD device at the oblique viewing angle is improved, thereby the display quality improved.

It will be apparent to those skilled in the art that various modifications and variations can be made in the IPS mode LCD device and the method of fabricating the IPS mode LCD device of the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An in-plane switching mode liquid crystal display device, comprising:

first and second substrates facing and spaced apart from each other;

a first polarizing plate including a first compensating layer, a first polarizing layer and a first protecting layer sequentially on an outer surface of the first substrate, the first compensating layer including a first biaxial retardation film;

a second polarizing plate including a second compensating layer, a second polarizing layer and a second protecting layer sequentially on an outer surface of the second substrate, the second compensating layer including a second biaxial retardation film; and

a liquid crystal layer between the first and second substrates,

wherein the first compensating layer includes a positive B-plate satisfying a relation of $n_z > n_x > n_y$,

wherein the second compensating layer includes a positive B-plate satisfying a relation of $n_z > n_x > n_y$, n_x , n_y , and n_z represents refractive indexes of each of the first and second compensating layers along the x, y, and z axes, respectively,

wherein the x and y axes represents a plane direction of each of the first and second compensating layers, and wherein the z-axis represents a thickness direction of each of the first and second compensating layers.

2. The device according to claim 1, wherein:

the first compensating layer has a plane directional retardation value (R_{in}) within a range of about 60 nm to about 110 nm; and

the second compensating layer has a plane directional retardation value (R_{in}) within a range of about 170 nm to about 240 nm.

3. The device according to claim 1, wherein each of the first and second compensating layers includes a stretched polymethyl methacrylate (PMMA) film.

4. The device according to claim 1, wherein:

each of the first and second polarizing layers includes a stretched poly-vinyl alcohol (PVA) adsorbing one of iodine (I) and dye; and

each of the first and second protecting layers includes tri-acetyl cellulose (TAC).

5. The device according to claim 1, wherein:

absorption axes of the first and second polarizing plates are perpendicular to each other;

an optical axis of the first compensating layer is parallel to the absorption axis of the first polarizing layer and perpendicular to the absorption axis of the second polarizing layer; and

an optical axis of the second compensating layer is perpendicular to the absorption axis of the first polarizing layer and parallel to the absorption axis of the second polarizing layer.

6. The device according to claim 1, wherein:

the first substrate includes a thin film transistor, a common electrode, and a pixel electrode;

the pixel electrode is connected to the thin film transistor and the pixel electrode; and

the common electrode is horizontally spaced apart from the pixel electrode.

7. The device according to claim 1, wherein:

red, green, and blue obliquely incident lights of an unpolarized state have a linear first polarization state having a first polarization axis after passing through the first polarizing layer;

the red, green, and blue obliquely incident lights of the first polarization state have an elliptic second polarization state having a second polarization axis after passing through the first compensating layer;

the red, green, and blue obliquely incident lights of the second polarization state have an elliptic third polarization state having a third polarization axis after passing through the liquid crystal layer;

the red, green, and blue obliquely incident lights of the third polarization state have a linear fourth polarization state having a fourth polarization axis after passing through the second compensating layer; and

the red, green, and blue obliquely incident lights of the fourth polarization state are absorbed by the second polarizing layer.

8. A method of fabricating an in-plane switching mode liquid crystal display device, the method comprising:

forming a liquid crystal layer between first and second substrates facing and spaced apart from each other;

forming a first polarizing plate including a first compensating layer, a first polarizing layer and a first protecting layer on an outer surface of the first substrate, the first compensating layer including a first biaxial retardation film; and

15

forming a second polarizing plate including a second compensating layer, a second polarizing layer and a second protecting layer on an outer surface of the second substrate, the second compensating layer including a second biaxial retardation film,

wherein the first compensating layer includes a positive B-plate satisfying a relation of $n_z > n_x > n_y$,

wherein the second compensating layer includes a positive B-plate satisfying a relation of $n_z > n_x > n_y$, n_x , n_y , and n_z represents refractive indexes of each of the first and second compensating layers along the x, y, and z axes, respectively,

wherein the x and y axes represents a plane direction of each of the first and second compensating layers, and wherein the z-axis represents a thickness direction of each of the first and second compensating layers.

9. The method according to claim 8, wherein:

the first compensating layer has a plane directional retardation value (R_{in}) within a range of about 60 nm to about 110 nm; and

the second compensating layer has a plane directional retardation value (R_{in}) within a range of about 170 nm to about 240 nm.

16

10. The method according to claim 8, wherein each of the first and second compensating layers is formed by stretching a polymethyl methacrylate (PMMA) film.

11. The method according to claim 8, wherein:

each of the first and second polarizing layers is formed by stretching a poly-vinyl alcohol (PVA) adsorbing one of iodine (I) and dye; and

each of the first and second protecting layers includes tri-acetyl cellulose (TAC).

12. The method according to claim 8, wherein:

absorption axes of the first and second polarizing plates are perpendicular to each other;

an optical axis of the first compensating layer is parallel to the absorption axis of the first polarizing layer and perpendicular to the absorption axis of the second polarizing layer; and

an optical axis of the second compensating layer is perpendicular to the absorption axis of the first polarizing layer and parallel to the absorption axis of the second polarizing layer.

* * * * *

专利名称(译)	面内切换模式液晶显示装置包括具有补偿层的偏振板及其制造方法		
公开(公告)号	US9442331	公开(公告)日	2016-09-13
申请号	US14/249417	申请日	2014-04-10
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	LEE JUN HEE LEE JAE HYUN		
发明人	LEE, JUN-HEE LEE, JAE-HYUN		
IPC分类号	G02F1/13363 G02F1/1343		
CPC分类号	G02F1/134363 G02F1/13363 G02F1/13439		
优先权	1020080132544 2008-12-23 KR		
其他公开文献	US20140218665A1		
外部链接	Espacenet USPTO		

摘要(译)

一种面内切换模式液晶显示装置，包括：第一偏振片，具有第一补偿层，第一偏振层和第一保护层，位于第一基板的外表面上；以及第二偏振片，具有第二补偿层，第二偏振层和第二基底的外表面上的第二保护层。第一补偿层包括正B板，其中 $n_z > n_x > n_y$ ，第二补偿层包括正B板，其中 $n_z > n_x > n_y$ ，使得 n_x ， n_y 和 n_z 表示第一和第二补偿层的折射率。第二补偿层分别沿 x ， y 和 z 轴，其中 x 和 y 轴表示第一和第二补偿层的平面方向， z 轴表示第一和第二补偿层的厚度方向。

