



US009140939B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 9,140,939 B2**
(45) **Date of Patent:** **Sep. 22, 2015**

(54) **LIQUID CRYSTAL DISPLAY AND
MANUFACTURING METHOD THEREOF**

(71) Applicant: **Samsung Display Co., Ltd.**, Yongin,
Gyeonggi-do (KR)

(72) Inventors: **Seon Uk Lee**, Seongnam-si (KR); **Won
Tae Kim**, Yongin-si (KR); **Yu Jin Kim**,
Yongin-si (KR); **Woo Jae Lee**, Yongin-si
(KR); **Kyung-Tae Chae**, Hwaseong-si
(KR)

(73) Assignee: **SAMSUNG DISPLAY CO., LTD.**,
Yongin, Gyeonggi-Do (KR)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 213 days.

(21) Appl. No.: **13/787,315**

(22) Filed: **Mar. 6, 2013**

(65) **Prior Publication Data**

US 2014/0104533 A1 Apr. 17, 2014

(30) **Foreign Application Priority Data**

Oct. 15, 2012 (KR) 10-2012-0114226

(51) **Int. Cl.**

G02F 1/1341 (2006.01)
G02F 1/1333 (2006.01)
G02F 1/1337 (2006.01)
G02F 1/1362 (2006.01)
G02F 1/1343 (2006.01)
G02F 1/139 (2006.01)

(52) **U.S. Cl.**

CPC **G02F 1/134363** (2013.01); **G02F 1/133377**
(2013.01); **G02F 1/1393** (2013.01); **G02F**

1/133707 (2013.01); **G02F 1/136209** (2013.01);
G02F 2001/134345 (2013.01)

(58) **Field of Classification Search**

CPC **G02F 1/133377**; **G02F 1/133707**;
G02F 1/136209; **G02F 1/1341**
USPC **349/158**, **187-190**, **156**, **154**; **438/30**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,386,307	A *	1/1995	Jang	349/81
6,141,072	A *	10/2000	Drabik et al.	349/122
6,469,761	B1	10/2002	Drabik et al.	
7,123,319	B2	10/2006	Broer et al.	
8,169,140	B2	5/2012	Han	
2012/0062448	A1 *	3/2012	Kim et al.	345/55

FOREIGN PATENT DOCUMENTS

JP	2000-330130	11/2000
KR	1020010005935	1/2001
KR	1020030063656	7/2003
KR	1020120026880	3/2012

* cited by examiner

Primary Examiner — Michael Caley

Assistant Examiner — Jia Pan

(74) *Attorney, Agent, or Firm* — F. Chau & Associates, LLC

(57) **ABSTRACT**

A manufacturing method of a liquid crystal display includes forming a sacrificial layer on a liquid crystal panel, forming an etch stop layer on the sacrificial layer, forming a photo resist pattern on the etch stop layer, completing the etch stop layer using the photo resist pattern as a mask, ashing the photo resist pattern and the sacrificial layer by using the completed etch stop layer as a mask, forming a microcavity by removing a portion of the sacrificial layer and forming a liquid crystal layer in the microcavity.

9 Claims, 36 Drawing Sheets




FIG. 1




FIG.2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 8A




FIG. 8B




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D




FIG. 9E




FIG. 9F




FIG. 9G




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 13A




FIG. 13B




FIG. 13C




FIG. 13D




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18





FIG. 19



LIQUID CRYSTAL DISPLAY AND MANUFACTURING METHOD THEREOF

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to Korean Patent Application No. 10-2012-0114226 filed on Oct. 15, 2012, the entire disclosure of which is hereby incorporated by reference herein in its entirety.

TECHNICAL FIELD

The present disclosure relates to a liquid crystal display and a manufacturing method thereof, and more particularly, to a liquid crystal display having a liquid crystal layer (nano crystal) included in a microcavity and a manufacturing method thereof.

DISCUSSION OF THE RELATED ART

A liquid crystal display which is one of the most common types of flat panel displays currently in use, includes two sheets of panels with field generating electrodes such as a pixel electrode, a common electrode, and the like and a liquid crystal layer interposed therebetween.

The liquid crystal display generates an electric field in the liquid crystal layer by applying voltage to the field generating electrodes, and determines the direction of liquid crystal molecules of the liquid crystal layer by the generated electric field, thereby controlling polarization of incident light so as to display images.

A liquid crystal display having an embedded microcavity (EM) structure (nano crystal structure) is a display device manufactured by, for example, forming a sacrificial layer with a photoresist, removing the sacrificial layer after coating a support member thereon, and filling a liquid crystal in an empty space formed by removing the sacrificial layer.

However, there may be a difficulty in that an aperture ratio is reduced due to a side wall of the EM structure. That is, the side wall of the EM structure has a tapered structure forming a predetermined angle, and as light leakage occurs in the liquid crystal layer positioned in the corresponding structure because a cell gap is different from other portions, the region should be covered by a light blocking member. As a result, the aperture ratio is reduced.

Further, a common electrode is formed along the side wall of the EM structure, and as a result, there is a difficulty in that an electric field is distorted.

SUMMARY

Exemplary embodiments of the present invention have been made in an effort to provide a liquid crystal display and a manufacturing method thereof having a liquid crystal layer (nano crystal) included in a microcavity with an increased aperture ratio. Further, exemplary embodiments of the present invention have been made in an effort to provide a liquid crystal display and a manufacturing method thereof having a liquid crystal layer (nano crystal) included in a microcavity with reduced distortion of an electric field.

An exemplary embodiment of the present invention provides a manufacturing method of a liquid crystal display which includes forming a sacrificial layer on a liquid crystal panel, forming an etch stop layer on the sacrificial layer, forming a photo resist pattern on the etch stop layer, completing the etch stop layer using the photo resist pattern as a mask,

ashing the photo resist pattern and the sacrificial layer by using the completed etch stop layer as a mask, forming a microcavity by removing a portion of the sacrificial layer and forming a liquid crystal layer in the microcavity.

In the forming of the sacrificial layer, the sacrificial layer may be formed by laminating a photo resist on the liquid crystal panel.

The etch stop layer may be made of a transparent conductive material such as ITO or IZO.

The gas used in the ashing may be oxygen or oxygen and sulfur hexafluoride (SF₆).

The etch stop layer may serve as a common electrode receiving common voltage.

The manufacturing method of a liquid crystal display may further include removing a portion of the etch stop layer before removing the portion of the sacrificial layer after ashing, and forming a common electrode, a lower insulating layer, or a roof layer at the removed etch stop layer portion.

The etch stop layer may be made of an insulating material such as SiNx or SiOx.

The ashing gas used in the ashing may be oxygen.

The manufacturing method of a liquid crystal display may further include forming a common electrode and a pixel electrode on the liquid crystal panel before forming the sacrificial layer.

An exemplary embodiment of the present invention provides a liquid crystal display, including: an insulation substrate, a microcavity disposed on the insulation substrate and having a sharp side wall, a pixel electrode disposed on the insulation substrate and in the microcavity and a liquid crystal layer disposed in the microcavity. A horizontal width occupied by the sharp side wall is about 1 to about 2 μm.

The liquid crystal display may further include a common electrode, in which the common electrode may be disposed only at a flat portion of the microcavity.

The liquid crystal display may further include a lower insulating layer covering the sharp side wall of the microcavity and the common electrode.

The liquid crystal display may further include a roof layer covering the sharp side wall of the microcavity and the common electrode.

The liquid crystal display may further include a common electrode, in which the common electrode is disposed at a flat portion of the microcavity and on the sharp side wall of the microcavity.

The liquid crystal display may further include a lower insulating layer covering the common electrode.

The liquid crystal display may further include a roof layer covering the common electrode.

The liquid crystal display may further include an etch stop layer, in which the etch stop layer may be disposed only at a flat portion of the microcavity.

The liquid crystal display may further include a lower insulating layer covering the sharp side wall of the microcavity and the etch stop layer.

The liquid crystal display may further include a roof layer covering the sharp side wall of the microcavity and the etch stop layer.

The liquid crystal display may further include a common electrode, in which the common electrode may be formed together with the pixel electrode on the insulation substrate and in the microcavity.

In accordance with an exemplary embodiment of the present invention, a liquid crystal display is provided. The liquid crystal display includes an insulation substrate, a gate line disposed on the insulation substrate, a storage voltage line disposed on the insulation substrate, a gate insulating

layer disposed on the gate line and the storage voltage line, a semiconductor disposed on the gate insulating layer, a data conductor including a data line disposed on the semiconductor, a first passivation layer disposed on the data conductor, the semiconductor and the gate insulating layer, a color filter disposed on the first passivation layer, a black matrix disposed on the color filter, a second passivation layer disposed on the color filter and the black matrix, a microcavity disposed on the second passivation layer and having a sharp side wall, a pixel electrode disposed on the second passivation layer and in the microcavity, a liquid crystal layer disposed in the microcavity, a common electrode disposed above the second passivation layer, a roof layer covering the common electrode and an upper insulating layer disposed on the roof layer. A horizontal width occupied by the sharp side wall of the microcavity is about 1 to about 2 μm .

According to exemplary embodiments of the present disclosure, when the sacrificial layer is etched, the common electrode or the etch stop layer formed at the upper portion of the sacrificial layer and etched to narrow the horizontal area occupied by the side wall of the sacrificial layer, and as a result, an aperture ratio is increased. Further, the common electrode is horizontally formed at the upper portion of the sacrificial layer and the common electrode is not formed on the side wall of the sacrificial layer, and as a result, a vertical electric field is generated without distortion.

BRIEF DESCRIPTION OF THE DRAWINGS

Exemplary embodiments of the present invention can be understood in further detail from the following detailed description taken in conjunction with the attached drawings in which:

FIG. 1 is a layout view of a liquid crystal display according to an exemplary embodiment of the present invention.

FIG. 2 is a cross-sectional view of FIG. 1 taken along line II-II.

FIG. 3 is a cross-sectional view of FIG. 11 taken along line III-III.

FIGS. 4 to 13D illustrate a manufacturing method of the liquid crystal display of FIG. 1 according to an exemplary embodiment.

FIGS. 14 and 15 are photographs comparing cross sections of liquid crystal displays according to an Example of the present invention and a Comparative Example.

FIG. 16 illustrates a liquid crystal display according to an exemplary embodiment of the present invention.

FIG. 17 illustrates a liquid crystal display according to an exemplary embodiment of the present invention.

FIG. 18 illustrates a liquid crystal display according to an exemplary embodiment of the present invention.

FIGS. 19(a)-(f) illustrate a method of manufacturing a sacrificial layer and etch stop layer used in forming the liquid crystal display of FIG. 18 in accordance with an exemplary embodiment of the present invention.

DETAILED DESCRIPTION OF EXEMPLARY EMBODIMENTS

Exemplary embodiments of the present invention will be described more fully hereinafter with reference to the accompanying drawings, in which exemplary embodiments of the invention are shown.

In the drawings, the thickness of layers, films, panels, regions, etc., may be exaggerated for clarity. Like reference numerals designate like elements throughout the specification. It will be understood that when an element such as a

layer, film, region, or substrate is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present.

As used herein, the singular forms, "a", "an", and "the" are intended to include plural forms as well, unless the context clearly indicates otherwise.

Hereinafter, a liquid crystal display according to an exemplary embodiment of the present invention will be described with reference to FIGS. 1 to 3.

FIG. 1 is a layout view of a liquid crystal display according to an exemplary embodiment of the present invention, FIG. 2 is a cross-sectional view of FIG. 1 taken along line II-II, and FIG. 3 is a cross-sectional view of FIG. 11 taken along line III-III.

A gate line 121 and a storage voltage line 131 are formed on an insulation substrate 110 made of, for example, transparent glass, quartz, plastic, or the like. Also, in an exemplary embodiment, the insulation substrate 110, may be formed of, for example, ceramic or silicon materials. Further, in an exemplary embodiment, the insulation substrate 110 may be, for example, a flexible substrate. Suitable materials for the flexible substrate include, for example, polyethersulfone (PES), polyethylenenaphthalate (PEN), polyethylene (PE), polyimide (PI), polyvinyl chloride (PVC), polyethylene terephthalate (PET), or combinations thereof.

The gate line 121 includes, for example, a first gate electrode 124a, a second gate electrode 124b, and a third gate electrode 124c. The storage voltage line 131 includes, for example, storage electrodes 135a and 135b and a protrusion 134 protruding in the gate line 121 direction. The storage electrodes 135a and 135b have, for example, a structure surrounding a first subpixel electrode 192h and a second subpixel electrode 192i of a front pixel. A horizontal portion 135b of the storage electrode of FIG. 1 may be, for example, one wiring which is not separated from the horizontal portion 135b of the front pixel. For example, the gate line 121 may be formed of one of aluminum (Al), copper (Cu), molybdenum (Mo), titanium (Ti), nickel (Ni), tungsten (W), gold (Au), palladium (Pd), platinum (Pt), chromium (Cr), neodymium (Nd), zinc (Zn), cobalt (Co), manganese (Mn) and any mixtures or alloys thereof. In addition, the gate line 121, may include, for example, a transparent conductive material such as an indium tin oxide (ITO), an indium zinc oxide (IZO) and an aluminum doped zinc oxide (AZO).

A gate insulating layer 140 is formed on the gate line 121 and the storage voltage line 131. A semiconductor 151 positioned below a data line 171, a semiconductor 155 positioned below a source/drain electrode, and a semiconductor 154 positioned at a channel part of a thin film transistor are formed on the gate insulating layer 140. For example, the gate insulating layer 140 may be made of silicon nitride (SiNx), silicon oxide (SiOx), silicon oxynitride (SiOxNy), aluminum oxide (AlOx), yttrium oxide (Y₂O₃), hafnium oxide (HfOx), zirconium oxide (ZrOx), aluminum nitride (AlN), aluminum oxynitride (AlNO), titanium oxide (TiOx), barium titanate (BaTiO₃), lead titanate (PbTiO₃), or a combination thereof.

The semiconductors 151, 154, 155, may be made of, for example, amorphous silicon (e.g. hydrogenated amorphous silicon). Alternatively, the semiconductors 151, 154, 155 may be formed of, for example, polysilicon, micro-crystal silicon, or single crystal silicon.

A plurality of ohmic contacts may be formed on the respective semiconductors 151, 154, and 155 and between the data line 171 and the source/drain electrode, and are omitted in the drawings.

On the respective semiconductors 151, 154, and 155 and the gate insulating layer 140, a data conductor 171, 173c,

175a, 175b, 175c that includes a plurality of data lines **171** including a first source electrode **173a** and a second source electrode **173b**, a first drain electrode **175a**, a second drain electrode **175b**, a third source electrode **173c**, and a third drain electrode **175c** is formed.

The first gate electrode **124a**, the first source electrode **173a**, and the first drain electrode **175a** form a first thin film transistor Qa together with the semiconductor **154**, and a channel of the thin film transistor is formed at the semiconductor portion **154** between the first source electrode **173a** and the first drain electrode **175a**. Similarly, the second gate electrode **124b**, the second source electrode **173b**, and the second drain electrode **175b** form a second thin film transistor Qb together with the semiconductor **154**, and a channel of the thin film transistor is formed at the semiconductor portion **154** between the second source electrode **173b** and the second drain electrode **175b**. The third gate electrode **124c**, the third source electrode **173c**, and the third drain electrode **175c** form a third thin film transistor Qc together with the semiconductor **154**, and a channel of the thin film transistor is formed at the semiconductor portion **154** between the third source electrode **173c** and the third drain electrode **175c**.

For example, the data line **171** of the present exemplary embodiment has a structure with a narrow width in a thin film transistor formation region around an extension **175c'** of the third drain electrode **175c**. This structure is a structure for keeping a distance from the adjacent wiring and reducing signal interference, but does not necessarily need to be formed like this.

A first passivation layer **180** is formed on the data conductor **171**, **173c**, **175a**, **175b**, and **175c** and the exposed semiconductor **154** portion. The first passivation layer **180** may include, for example, an inorganic insulator such as silicon nitride (SiNx) and silicon oxide (SiOx) or an organic insulator. For example, the organic insulator of the first passivation layer **180** may include benzocyclobutene (BCB), acryl-based resin or a combination thereof.

A color filter **230** is formed on the passivation layer **180**. The color filter **230** having the same color is formed in adjacent pixels in a vertical direction (data line direction). Further, adjacent pixels in a horizontal direction (gate line direction) have color filters **230** and **230'** having, for example, different colors, and two color filters **230** and **230'** may be overlapped with each other on the data line **171**. The color filters **230** and **230'** may display, for example, one color of primary colors such as three primary colors of red, green, and blue. However, the color is not limited to the three primary colors of red, green, and blue. Alternatively, for example, in an embodiment, the color filters **230** and **230'** may display one color of cyan, magenta, yellow, and white.

A black matrix **220** is formed, for example, on the color filters **230** and **230'**. The black matrix **220** is formed, for example, based on a region (hereinafter, referred to as a 'transistor formation region') where the gate line **121**, the storage voltage line **131**, and the thin film transistor are formed and a region where the data line **171** is formed and has a lattice structure having openings corresponding to a region displaying images. The color filter **230** is formed, for example, in the opening of the black matrix **220**. Further, the black matrix **220** is made of a material which does not transmit light.

A second passivation layer **185** covering the color filter **230** and the black matrix **220** is formed, for example, on the color filter **230** and the black matrix **220**. The second passivation layer **185** may contain, for example, an inorganic insulator such as silicon nitride (SiNx) and silicon oxide (SiOx) or an organic insulator. For example, the organic insulator of the

second passivation layer **185** may include benzocyclobutene (BCB), acryl-based resin or a combination thereof. Unlike those illustrated in cross-sectional views of FIGS. **2** and **3**, in the case where a step occurs due to a thickness difference between the color filter **230** and the black matrix **220**, the second passivation layer **185** may contain, for example, an organic insulator to reduce or remove the step.

A first contact hole **186a** and a second contact hole **186b** which expose the first drain electrode **175a** and an extension **175b'** of the second drain electrode **175b**, respectively are formed, for example, in the color filter **230**, the black matrix **220**, and the passivation layers **180** and **185**. Further, a third contact hole **186c** which exposes, for example, a protrusion **134** of the storage voltage line **131** and an extension **175c'** of the third drain electrode **175c** is formed in the color filter **230**, the black matrix **220**, and the passivation layers **180** and **185**.

In the exemplary embodiment, the contact holes **186a**, **186b**, and **186c** are formed, for example, even in the black matrix **220** and the color filter **230**, but the black matrix **220** and the color filter **230** may be actually difficult to etch the contact holes **186a**, **186b**, and **186c** as compared with the passivation layers **180** and **185** according to a material. Therefore, the black matrix **220** or the color filter **230** may be formed, for example, at the position where the contact holes **186a**, **186b**, and **186c** are formed in advance during etching of the black matrix **220** or the color filter **230**.

Meanwhile, according to an exemplary embodiment, the color filter **230** and the passivation layers **180** and **185** are just etched by changing a position of the black matrix **220** to form the contact holes **186a**, **186b**, and **186c**.

On the second passivation layer **185**, a pixel electrode **192** including the first subpixel electrode **192h** and the second subpixel electrode **192l** is formed. The pixel electrode **192** may be made of, for example, a transparent conductive material such as ITO, IZO, aluminum zinc oxide (AZO), cadmium tin oxide (CTO), or a reflective electric conductor such as, for example, aluminum (Al), gold (Au), silver (Ag), copper (Cu), iron (Fe), titanium (Ti), tantalum (Ta), molybdenum (Mo), rubidium (Rb), tungsten (W), and alloys, or combinations thereof. In addition, the pixel electrode **192** can be formed of, for example, transfective materials or a combination of transparent materials and reflective materials.

The first subpixel electrode **192h** and the second subpixel electrode **192l** are, for example, adjacent to each other in a column direction, have the overall quadrangular shape, and include a cross stem configured by a horizontal stem and a vertical stem crossing the horizontal stem. Further, the first subpixel electrode **192h** and the second subpixel electrode **192l** are, for example, divided into four subregions by the horizontal stem and the vertical stem, and each subregion includes a plurality of minute branches.

The minute branches of the first subpixel electrode **192h** and the second subpixel electrode **192l** form, for example, an angle of approximately 40 to 45 degrees with the gate line **121** or the horizontal stem. Further, the minute branches of two adjacent subregions may be, for example, perpendicular to each other. Further, a width of the minute branch may be, for example, gradually increased or distances between the minute branches may be different from each other.

The first subpixel electrode **192h** and the second subpixel electrode **192l** are physically and electrically connected with the first drain electrode **175a** and the second drain electrode **175b** through, for example, the contact holes **186a** and **186b** and receive data voltage from the first drain electrode **175a** and the second drain electrode **175b**.

Meanwhile, a connecting member **194** electrically connects the extension **175c'** of the third drain electrode **175c** and

the protrusion **134** of the storage voltage line **131** through, for example, the third contact hole **186c**. As a result, a part of the data voltage applied to the second drain electrode **175b** is divided through the third source electrode **173c**, and a magnitude of the voltage applied to the second subpixel electrode **192i** may be smaller than a magnitude of the voltage applied to the first subpixel electrode **192h**.

Here, an area of the second subpixel electrode **192i** may be, for example, about 1 to about 2 times larger than an area of the first subpixel electrode **192h**.

Meanwhile, an opening which, for example, may collect gas discharged from the color filter **230** and a cover which covers the corresponding opening with the same material as the pixel electrode **192** thereon may be formed in the second passivation layer **185**. The opening and the cover are structures for preventing gas discharged from the color filter **230** from being transferred to other elements and may be not necessarily included.

A common electrode **270** is positioned, for example, on the second passivation layer **185** and the pixel electrode **192** and above the liquid crystal layer **3** injected in a microcavity **305** (see FIGS. **13D** and **13E**). The common electrode **270** is formed, for example, only at a flat portion above the microcavity **305** or the liquid crystal layer **3** and formed only at a portion corresponding to the portion with the pixel electrode **192**. As the common electrode **270** is not positioned at the side of the microcavity **305** or the liquid crystal layer **3**, a vertical electric field between the common electrode **270** and the pixel electrode **192** may be uniformly formed except for the outer portion and thus there is a benefit in that distortion of the electric field is small. Further, the common electrode **270** may receive, for example, common voltage V_{com} from the outside through a separate constituent element, and the adjacent common electrodes **270** may be connected to each other through a transistor formation area (or around a liquid crystal injection hole **335**). In this case, some of the common electrodes **270** remain at the liquid crystal injection hole **335** portion to have a structure in which the adjacent common electrodes **270** are connected to each other.

The reason that the common electrode **270** may maintain level even on the microcavity is because a roof layer **312** to be described below supports the common electrode **270**.

The common electrode **270** is made of, for example, a transparent conductive material such as ITO, IZO, AZO, or CTO and serves to generate an electric field together with the pixel electrode **192** to control an alignment direction of the liquid crystal molecules **310**.

A lower insulating layer **311** is positioned on the common electrode **270** and the second passivation layer **185** and the side of the liquid crystal layer **3** (or the side of the microcavity **305**). The lower insulating layer **311** may have, for example, a liquid crystal injection hole **335** at one side thereof to fill the liquid crystal in the microcavity **305**. The lower insulating layer **311** may contain, for example, an inorganic insulating material such as silicon nitride (SiN_x). The liquid crystal injection hole **335** may be used when removing a sacrificial layer for forming the microcavity **305**. This will be described in detail when describing a manufacturing method.

Further, a side wall of the microcavity **305** in which the liquid crystal layer **3** is injected is sharply formed and thus there is a benefit in that a horizontal width in a region where a cell gap of the liquid crystal layer **3** is not sufficient is largely decreased. The horizontal width occupied by the side wall of the microcavity **305** or the liquid crystal layer **3** is, for example, about 1 to about 2 μm . As a result, a horizontal width

covering the microcavity **305** or the liquid crystal layer **3** by the black matrix **220** may be, for example, about 1 to about 2 μm .

Further, an alignment layer (not illustrated) may be formed, for example, in the microcavity **305** to align the liquid crystal molecules injected in the microcavity **305**. The alignment layer may contain at least one of materials such as, for example, polyamic acid, polysiloxane, or polyimide which are generally used as a liquid crystal alignment layer.

The liquid crystal layer **3** is formed, for example, in the microcavity **305** (accurately, in the alignment layer). The liquid crystal molecules **310** are initially aligned by the alignment layer and the alignment direction is changed according to the applied electric field. A height of the liquid crystal layer **3** corresponds to, for example, a height of the microcavity **305**. The liquid crystal layer **3** positioned in the microcavity **305** is referred to as a nano crystal.

The liquid crystal layer **3** formed in the microcavity **305** may be injected in the microcavity **305** by using, for example, capillary force, and the alignment layer may be formed by capillary force.

The roof layer **312** is formed, for example, on the lower insulating layer **311**. The roof layer **312** may serve to support a space between the pixel electrode **192** and the common electrode **270** (microcavity) and the nano crystal to be formed. The roof layer **312** according to the present exemplary embodiment serves to support the microcavity **305** above the common electrode **270** at a predetermined thickness and may have, for example, the liquid crystal injection hole **335** at one side so as to fill the liquid crystal in the microcavity **305**.

An upper insulating layer **313** is formed, for example, on the roof layer **312**. The upper insulating layer **313** may contain, for example, an inorganic insulating material such as silicon nitride (SiN_x). The roof layer **312** and the upper insulating layer **313** are, for example, patterned together with the lower insulating layer **311** to form the liquid crystal injection hole **335**.

Alternatively, for example, in an exemplary embodiment, the lower insulating layer **311** and the upper insulating layer **313** may be omitted.

A capping layer (not illustrated) is formed, for example, on the upper insulating layer **313** to prevent the liquid crystal molecules **310** from being discharged outside through the liquid crystal injection hole **335**.

A polarizer (not illustrated) is positioned below the insulation substrate **110** and above the upper insulating layer **313** (or above the capping layer). The polarizer may include, for example, a polarized element generating polarization and a tri-acetyl-cellulose (TAC) layer for ensuring durability, and according to an exemplary embodiment, directions in transmissive axes of an upper polarizer and a lower polarizer may be vertical or parallel to each other.

Hereinafter, a manufacturing method of the liquid crystal display according to an exemplary embodiment of the present invention will be described with reference to FIGS. **4** to **13D**.

FIGS. **4** to **13D** are diagrams sequentially arranging a manufacturing method of the liquid crystal display of FIG. **1** according to an exemplary embodiment.

First, FIG. **4** is a layout view of the gate line **121** and the storage voltage line **131** formed on the insulation substrate **110**.

Referring to FIG. **4**, the gate line **121** and the storage voltage line **131** are formed on the insulation substrate **110** made of, for example, transparent glass, quartz, or plastic. Also, in an exemplary embodiment, the insulation substrate **110**, may be formed of, for example, ceramic or silicon mate-

rials. Further, in an exemplary embodiment, the insulation substrate **110** may be, for example, a flexible substrate. Suitable materials for the flexible substrate include, for example, polyethersulfone (PES), polyethylenenaphthalate (PEN), polyethylene (PE), polyimide (PI), polyvinyl chloride (PVC), polyethylene terephthalate (PET), or combinations thereof.

The gate line **121** and the storage voltage line **131** may be simultaneously formed by the same mask with the same material. For example, in an exemplary embodiment, the gate line **121** and the storage voltage line **131** may each be formed of one of aluminum (Al), copper (Cu), molybdenum (Mo), titanium (Ti), nickel (Ni), tungsten (W), gold (Au), palladium (Pd), platinum (Pt), chromium (Cr), neodymium (Nd), zinc (Zn), cobalt (Co), manganese (Mn) and any mixtures or alloys thereof. In addition, the gate line **121** and storage voltage line **131**, may include, for example, a transparent conductive material such as an indium tin oxide (ITO), an indium zinc oxide (IZO) and an aluminum doped zinc oxide (AZO).

Further, the gate line **121** includes, for example, a first gate electrode **124a**, a second gate electrode **124b**, and a third gate electrode **124c**, and the storage voltage line **131** includes a protrusion **134** protruding in the direction of the storage electrodes **135a** and **135b** and the gate line **121**. The storage electrodes **135a** and **135b** have, for example, a structure surrounding the first subpixel electrode **192h** and the second subpixel electrode **192i** of a front pixel. As data voltage is applied to the gate line **121** and storage voltage is applied to the storage voltage line **131**, the gate line **121** and the storage voltage line **131** are separated from each other. The storage voltage may have a predetermined voltage level or have a swing voltage level.

The gate insulating layer **140** covering the gate line **121** and the storage voltage line **131** is formed on the gate line **121** and the storage voltage line **131**. For example, the gate insulating layer **140** may be made of silicon nitride (SiNx), silicon oxide (SiOx), silicon oxynitride (SiOxNy), aluminum oxide (AlOx), yttrium oxide (Y₂O₃), hafnium oxide (HfOx), zirconium oxide (ZrOx), aluminum nitride (AlN), aluminum oxynitride (AlNO), titanium oxide (TiOx), barium titanate (BaTiO₃), lead titanate (PbTiO₃), or a combination thereof.

Thereafter, as illustrated in FIGS. **5** and **6**, the semiconductors **151**, **154**, and **155**, the data line **171**, and the source/drain electrodes **173a**, **173b**, **173c**, **175a**, **175b**, and **175c** are formed on the gate insulating layer **140**.

FIG. **5** illustrates a layout view that the semiconductors **151**, **154**, and **155** are formed, and FIG. **6** illustrates a layout view that the data line **171** and the source/drain electrodes **173a**, **173b**, **173c**, **175a**, **175b**, and **175c** are formed, but the semiconductors **151**, **154**, and **155**, the data line **171**, and the source/drain electrodes **173a**, **173b**, **173c**, **175a**, **175b**, and **175c** may be actually formed together by, for example, the following process described below.

That is, materials for forming the semiconductors and material for forming the data line and the source/drain electrodes are, for example, sequentially laminated. Thereafter, for example, two patterns are formed together through one process of exposure, developing, and etching by using one mask (slit mask or transfective mask). In this case, so that the semiconductor **154** positioned at the channel part of the thin film transistor is not etched, the corresponding portion is exposed through, for example, the slit or transfective region of the mask.

A plurality of ohmic contacts may be formed on the respective semiconductors **151**, **154**, and **155** and between the data line **171** and the source/drain electrodes.

The first passivation layer **180** is formed all over the data conductor **171**, **173c**, **175a**, **175b**, **175c** and the exposed semi-

conductor **154** portion. The first passivation layer **180** may contain, for example, an inorganic insulator such as silicon nitride (SiNx) and silicon oxide (SiOx) or an organic insulator. For example, the organic insulator of the first passivation layer **180** may include benzocyclobutene (BCB), acryl-based resin or a combination thereof.

Thereafter, as illustrated in FIGS. **7A** and **7B**, the color filter **230** and the black matrix **220** are formed, for example, on the first passivation layer **180**. Here, FIG. **7A** is a layout view corresponding to FIG. **1**, FIG. **7B** is a cross-sectional view corresponding to FIG. **2**, and FIG. **7B** illustrates the color filter **230** and the black matrix **220** formed after exposing and etching.

For example, when forming the color filter **230** and the black matrix **220**, the color filter **230** is formed. The color filter **230** having one color is elongated, for example, in a vertical direction (data line direction), and the color filters **230** and **230'** having different colors are formed in adjacent pixels in a horizontal direction (gate line direction). As a result, exposing, developing, and etching processes should be performed for each color filter **230**. A liquid crystal display including, for example, three primary colors forms the color filter **230** by, for example, the exposing, developing, and etching processes three times. In this case, for example, the color filter **230'** which is first formed on the data line **171** is positioned at the lower portion and the color filter **230** which is formed thereafter is formed at the upper portion, and the color filter **230'** and the color filter **230** may be overlapped with each other.

The color filter **230** may be removed, for example, in advance at the position where the contact holes **186a**, **186b**, and **186c** are formed during etching of the color filter **230**.

The black matrix **220** is formed, for example, on the color filter **230** with a non-transmissive material. Referring to an oblique portion (illustrating the black matrix **220**) of FIG. **7A**, the black matrix **220** is formed in a lattice structure having an opening corresponding to a region where an image is displayed. The color filter **230** is formed, for example, in the opening.

The black matrix **220** has a portion formed, for example, in a horizontal direction along a transistor formation region with the gate line **121**, the storage voltage line **131**, and the thin film transistor and a portion formed in a vertical direction based on a region with the data line **171**, as illustrated in FIG. **7A**.

Referring to FIGS. **8A** and **8B**, the second passivation layer **185** is formed, for example, all over the color filter **230** and the black matrix **220**. The second passivation layer **185** may contain, for example, an inorganic insulator such as silicon nitride (SiNx) and silicon oxide (SiOx) or an organic insulator. For example, the organic insulator of the second passivation layer **185** may include benzocyclobutene (BCB), acryl-based resin or a combination thereof.

Thereafter, a first contact hole **186a** and a second contact hole **186b** exposing, for example, the first drain electrode **175a** and the extension **175b'** of the second drain electrode **175b**, respectively are formed in the color filter **230**, the black matrix **220**, and the passivation layers **180** and **185**. Further, for example, in the color filter **230**, the black matrix **220**, and the passivation layers **180** and **185**, the third contact hole **186c** exposing the protrusion **134** of the storage voltage line **131** and the extension **175c'** of the third drain electrode **175c** is formed.

Thereafter, the pixel electrode **192** including the first subpixel electrode **192h** and the second subpixel electrode **192i** is formed, for example, on the second passivation layer **185**. In this case, the pixel electrode **192** may be made of, for

example, a transparent conductive material such as ITO, IZO, AZO, CTO, or a reflective electric conductor such as, for example, aluminum (Al), gold (Au), silver (Ag), copper (Cu), iron (Fe), titanium (Ti), tantalum (Ta), molybdenum (Mo), rubidium (Rb), tungsten (W), and alloys, or combinations thereof. In addition, the pixel electrode **192** can be formed of, for example, transfective materials or a combination of transparent materials and reflective materials. Further, the first subpixel electrode **192h** and the second subpixel electrode **192i** are physically and electrically connected with the first drain electrode **175a** and the second drain electrode **175b** through the contact holes **186a** and **186b**, respectively. Further, the connecting member **194** that electrically connects the extension **175c'** of the third drain electrode **175c** and the protrusion **134** of the storage voltage line **131** through the third contact hole **186c** is formed. As a result, a part of the data voltage applied to the second drain electrode **175b** is divided through the third source electrode **173c**, and a magnitude of the voltage applied to the second subpixel electrode **192i** may be smaller than a magnitude of the voltage applied to the first subpixel electrode **192h**.

Here, FIG. 8B is a diagram corresponding to FIG. 2 and illustrates a cross-sectional view of the liquid crystal display formed up to FIG. 8A.

Thereafter, as illustrated in FIG. 9G, a sacrificial layer **300** and the common electrode **270** are formed. Here, the common electrode **270** serves as an etch stop layer of the sacrificial layer **300**.

As illustrated in FIG. 9G, the sacrificial layer **300** and the common electrode **270** are manufactured by, for example, the following method.

As illustrated in FIGS. 9A and 9B, a photo resist PR is, for example, laminated on the entire surface of the liquid crystal panel with the second passivation layer **185**, the pixel electrode **192**, and the like to form the sacrificial layer **300** and thereafter, a transparent conductive material such as ITO, IZO, AZO or CTO is laminated to form the common electrode **270**.

Thereafter, as illustrated in FIG. 9C, the photo resist PR is, for example, laminated and then exposed and developed to form a photo resist pattern **271**.

Next, as illustrated in FIG. 9D, the transparent conductive material is, for example, etched by using the photo resist pattern **271** as a mask to complete the common electrode **270**.

Next, as illustrated in FIGS. 9E and 9F, the exposed sacrificial layer **300** and photo resist pattern **271** are removed by, for example, ashing using the completed common electrode **270** as a mask. After ashing, the opening **301**, the region where the exposed sacrificial layer is removed, is formed between the sacrificial layers **300**. FIG. 9E is a cross-sectional view during the ashing process. Thus, the photo resist patterns not totally removed is also illustrates as **271'** in FIG. 9E. In this case, the ashing gas may include, for example, oxygen (O₂) or both oxygen (O₂) and sulfur hexafluoride (SF₆). As the common electrode **270** made of the transparent conductive material is not etched, but the sacrificial layer **300** and the photo resist pattern **271** made of the photo resist PR are just removed by the ashing gas, the ashing gas has a state like FIG. 9F via a state like FIG. 9E when the ashing is completed. For example, when the photo resist is removed by the ashing, anisotropic etching is performed in dry etch equipment and thus the side wall of the sacrificial layer **300** may be substantially vertically formed. As a result, the side wall of the sacrificial layer **300** does not largely occupy the horizontal area.

Accordingly, as illustrated in FIG. 9G, linear patterns of the sacrificial layer **300** and the common electrode **270** are completed.

Next, as illustrated in FIGS. 10A to 10C, the lower insulating layer **311** containing, for example, an inorganic insulating material such as silicon nitride (SiN_x) is formed on the entire surface of the liquid crystal panel with the linear patterns of the sacrificial layer **300** and the common electrode **270**. The lower insulating layer **311** covers, for example, the linear patterns of the sacrificial layer **300** and the common electrode **270**.

Next, as illustrated in FIGS. 11A to 11C, the roof layer **312** is formed. The roof layer **312** may contain, for example, an organic material, and the roof layer **312** is not formed in a region (hereinafter, referred to as a 'liquid crystal injection hole open region') etched during a process of forming the liquid crystal injection hole **335**. In FIG. 11A, the liquid crystal injection hole open region is formed to correspond to a thin film transistor formation region and has a structure extending in a formation direction of the gate line. Further, as the roof layer **312** is not formed in the region corresponding to the liquid crystal injection hole open region, FIGS. 10A to 10C indirectly illustrate that the lower insulating layer **311** which is formed on the entire surface of the liquid crystal panel is exposed by the roof layer **312** as explained below.

The roof layer **312** is formed by, for example, laminating a material for forming the roof layer containing an organic material on the entire region of the panel, exposing and developing the laminated material by using as a mask, and then removing the material for forming the roof layer in the region corresponding to the liquid crystal injection hole open region. In this case, the lower insulating layer **311** formed below the roof layer **312** is not etched but exposed. For example, in the liquid crystal injection hole open region, the sacrificial layer **300**, the common electrode **270**, and the lower insulating layer **311** are just formed, and in other regions, the sacrificial layer **300** or the opening **301**, the common electrode **270**, the lower insulating layer **311**, and the roof layer **312** are laminated.

Next, as illustrated in FIGS. 12A to 12C, a material for forming an upper insulating layer containing, for example, an inorganic insulating material such as silicon nitride (SiN_x) is laminated to form the upper insulating layer **313** on the entire surface of the liquid crystal panel.

Next, as illustrated in FIGS. 13A and 13D, the liquid crystal injection hole **335** is formed, for example, by etching the liquid crystal injection hole open region.

For example, as illustrated in FIG. 13B, the common electrode **270** remains by etching the lower insulating layer **311** and the upper insulating layer **313** formed in the liquid crystal injection hole open region of the upper insulating layer **313** and the lower insulating layer **311** laminated all over the entire region of the display panel made of an inorganic insulating material such as silicon nitride (SiN_x).

Next, as illustrated in FIG. 13C, the common electrode **270** formed in the liquid crystal injection hole open region is, for example, etched to expose the sacrificial layer **300**. In this case, according to an exemplary embodiment, a part of the common electrode **270** remains to electrically connect the adjacent common electrodes **270** to each other.

That is, to etch the liquid crystal injection hole open region, the photo resist PR is formed in the entire region, the photo resist PR corresponding to the liquid crystal injection hole open region is removed to form the photo resist pattern, and thereafter, etched according to the photo resist pattern to etch the liquid crystal injection hole open region. In this case, in the etched layer in the liquid crystal injection hole open

region, the material **313** for the upper insulating layer, the lower insulating layer **311**, the common electrode **270**, and the sacrificial layer **300** are, for example, etched and the layer therebelow is, for example, not etched. According to an exemplary embodiment, only a part of the sacrificial layer **300** may be etched or never be etched. Here, the process of etching the liquid crystal injection hole open region may be performed by, for example, dry etching, and in the case of an etchant that may etch the etching layer together, the process may be performed by, for example, wet etching.

Next, as illustrated in FIG. **13D**, the exposed sacrificial layer **300** is, for example, removed. In the present exemplary embodiment, as the sacrificial layer **300** is made of the photo resist PR, a process of removing the photo resist pattern formed on the upper insulating layer **313** may be, for example, performed together. That is, the photo resist pattern formed on the upper insulating layer **313** may be, for example, wet-etched together with the sacrificial layer **300** by immersing them in an etchant (for example, a photo resist stripper) for removing the photo resist pattern. According to the above process, the process of removing the photo resist PR formed on the upper insulating layer **313** and the process of removing the sacrificial layer **300** may be performed, for example, at the same time, and as a result, there is a benefit in that a manufacturing process is shortened. However, in the case of forming the sacrificial layer **300** with a material, not the photo resist PR, two separate processes may be performed. Further, the sacrificial layer **300** may be formed by, for example, dry etching, and not wet etching.

Thereafter, as illustrated in FIGS. **2** and **3**, an alignment layer (not illustrated) or the liquid crystal layer **3** are, for example, injected in the microcavity **305** by using capillary force.

Next, although not illustrated, a capping layer (not illustrated) is formed to prevent the liquid crystal layer **3** injected in the microcavity **305** from being leaked outside and then a process of sealing the microcavity **305** may be performed.

Alternatively, for example, in an exemplary embodiment, the lower insulating layer **311** and the upper insulating layer **313** may be omitted.

Further, a process of attaching a polarizer (not illustrated) below the insulation substrate **110** and on the upper insulating layer **313** may be further included. The polarizer may include, for example, a polarized element generating polarization and a tri-acetyl-cellulose (TAC) layer for ensuring durability, and according to an exemplary embodiment, directions in transmissive axes of an upper polarizer and a lower polarizer may be, for example, vertical or parallel to each other.

According to the manufacturing method according to the present exemplary embodiment of the present invention, the sacrificial layer **300** is, for example, etched at the upper portion to have a sharp side wall and thus the side wall of the microcavity **305** is sharp. The liquid crystal layer **3** injected in the microcavity **305** does not have a sufficient cell gap at the side wall and thus a light leakage phenomenon occurs. In the present exemplary embodiment of the present invention, as the side wall is sharp, the horizontal area is narrow and thus a wide opening area may be ensured.

The viewpoint will be described with reference to FIGS. **14** and **15** by comparing a nano crystal display device according to an Example of the present invention and a nano crystal display device according to Comparative Example.

FIGS. **14** and **15** are photographs comparing cross sections of liquid crystal displays according to an Example of the present invention and a Comparative Example. FIG. **14** is a cross-sectional view of the above-mentioned Example of the

present invention, and FIG. **15** is a cross-sectional view of the above-mentioned Comparative Example.

As illustrated in FIG. **14**, in the structure according to an Example of the present invention, as the side wall of the sacrificial layer **300** was sharp, the horizontal width was only about 1 μm . As a result, the sacrificial layer **300** portion may be ensured as the opening because a width of the portion covered by the black matrix **220** is covered only by about 1 μm .

In the Comparative Example, the sacrificial layer **300** was laminated with the photo resist PR and the photo resist PR was exposed and developed to form the pattern of the sacrificial layer **300**. In this case, the side wall of the sacrificial layer **300** has no choice but to have a tapered structure, and in the case of the tapered structure, the region corresponding to the side wall of the sacrificial layer **300** has a horizontal width of about 5 μm as illustrated in FIG. **15**. Thus, as a result, a greater area of the sidewall of the sacrificial layer **300** is covered by the black matrix **220** in the Comparative Example of FIG. **15** than is covered by the black matrix **220** in the present Example of FIG. **14**. Therefore, according to the above-mentioned Example of the present invention, a wider opening may be included than in the Comparative Example.

Hereinafter, an exemplary embodiment of the present invention will be described with reference to FIGS. **16** to **18**.

FIGS. **16** to **18** illustrate a liquid crystal display according to an exemplary embodiment of the present invention.

First, the present exemplary embodiment of FIG. **16** will be described.

FIG. **16** is a diagram corresponding to FIG. **2**.

In the present exemplary embodiment of FIG. **16**, the lower insulating layer **311** is omitted unlike the liquid crystal display of FIG. **2**. In addition, in the present exemplary embodiment, the common electrode **270** is formed, for example, at the sacrificial layer **300**, the microcavity **305**, or the side wall of the liquid crystal layer **3** unlike the liquid crystal display of FIG. **2**.

In the present exemplary embodiment of FIG. **16**, unlike the liquid crystal display of FIG. **2**, after the etch stop layer used when the sacrificial layer **300** is etched is removed, the common electrode **270** is, for example, formed on the side wall. That is, the common electrode **270** is positioned, for example, at the flat portion of the microcavity **305** or the liquid crystal layer **3** and on the side wall of the microcavity **305** or the liquid crystal layer **3**.

As such, in the present exemplary embodiment, when the sacrificial layer **300** made of the photo resist is etched by ashing, a separate layer (which may be various according to an exemplary embodiment and may use a transparent conductive material such as, for example, ITO and IZO or an insulating material such as, for example, SiNx and SiOx) is formed as the etch stop layer preventing etching and the sacrificial layer **300** is completed. Then, the etch stop layer is removed and the common electrode **270** is formed thereon.

Meanwhile, according to an exemplary embodiment, when the transparent conductive material such as, for example, ITO and IZO is used as the etch stop layer, the etch stop layer is not removed and the same transparent conductive material is laminated on the entire surface thereof to form the common electrode **270**.

Meanwhile, in the present exemplary embodiment of FIG. **17**, unlike the liquid crystal display of FIG. **16**, the lower insulating layer **311** is formed, for example, all over the upper portion of the common electrode **270**. Thus, the only difference between the liquid crystal display of FIG. **16** and the liquid crystal display of FIG. **17** is that the lower insulating layer **311** is additionally formed in FIG. **17**.

15

In FIG. 18, the common electrode 270 is not formed above the liquid crystal layer 3, but rather the common electrode 270 and the pixel electrode 192 are, for example, alternately formed on the same layer as each other. Further, instead of the transparent conductive material used as the etch stop layer in FIG. 2, the insulating material such as, for example, SiNx and SiOx is used as an etch stop layer 307.

In FIG. 18, the common electrode 270 is, for example, positioned between the pixel electrodes 192 and further, the etch stop layer 307 is positioned at the position of the common electrode 270. The etch stop layer 307 made of, for example, the insulating material such as, for example, SiNx and SiOx may be formed using, for example, oxygen (O₂) as the ashing gas.

In FIGS. 19 (a)-(d), a method for manufacturing the liquid crystal display of FIG. 18 is simply illustrated, and methods of forming the pixel electrode 192 and the common electrode 270 together may be various, and only the upper portion of the sacrificial layer 300 will be described. In particular, FIGS. 19(a)-(f) illustrate a method of manufacturing a sacrificial layer and etch stop layer used in forming the liquid crystal display of FIG. 18 in accordance with an exemplary embodiment of the present invention.

First, as shown in FIG. 19(a), the photo resist PR is, for example, laminated on the entire surface of the liquid crystal panel to form the sacrificial layer 300. Thereafter, as shown in FIG. 19(b), an insulating material 307 such as, for example, SiNx and SiOx is laminated on the entire surface.

Next, as shown in FIG. 19 (c), the photo resist PR is, for example, laminated and then exposed and developed to form a photo resist pattern 306.

Next, as shown in FIG. 19(d), the etch stop layer 307 made of, for example, the insulating material 307 such as SiNx and SiOx is completed by using, for example, the photo resist pattern 306 as a mask.

Next, as shown in FIGS. 19(e)-(f), the exposed sacrificial layer 300 and the photo resist pattern 306 are removed by ashing using the completed etched stop layer 307 as a mask. After ashing, the opening 301, the region where the exposed sacrificial layer is removed, is formed between the sacrificial layers 300. FIG. 19(e) is a cross-sectional view during the ashing process. Thus, the photo resist patterns not totally removed is also illustrates as 306' in FIG. 19(e). In this case, for example, oxygen (O₂) may be used as ashing gas. The etch stop layer 307 made of, for example, the insulating material such as SiNx and SiOx is not etched by the ashing gas, and the sacrificial layer 300 made of the photo resist PR and the photo resist pattern 306 are just removed. As a result, the structure of the sacrificial layer 300 and the etch stop layer 307 is completed. Even in the present exemplary embodiment, when the photo resist is removed by ashing, as anisotropic etching is performed in dry etching equipment, the side wall of the sacrificial layer 300 may be substantially vertically formed. As a result, the side wall of the sacrificial layer 300 does not largely occupy the horizontal area.

16

According to the manufacturing method of the present exemplary embodiment of the present invention, as the sacrificial layer 300 is etched at the upper portion to have a sharp side wall, the microcavity 305 has a sharp side wall. The liquid crystal layer 3 injected in the microcavity 305 does not have a sufficient cell gap at the side wall and thus a light leakage phenomenon occurs. In the present exemplary embodiment of the present invention, as the side wall of the microcavity 305 is sharp, the horizontal area occupied by the side wall of the microcavity 305 is narrow and thus a wide opening area may be ensured.

Having described exemplary embodiments of the present invention, it is further noted that it is readily apparent to those of ordinary skill in the art that various modifications may be made without departing from the spirit and scope of the invention which is defined by the metes and bounds of the appended claims.

What is claimed is:

1. A manufacturing method of a liquid crystal display, comprising:

forming a sacrificial layer on a liquid crystal panel;
forming an etch stop layer on the sacrificial layer;
forming a photo resist pattern on the etch stop layer;
completing the etch stop layer using the photo resist pattern as a mask;
ashing the photo resist pattern and the sacrificial layer by using the completed etch stop layer as a mask;
forming a microcavity by removing a portion of the sacrificial layer; and
forming a liquid crystal layer in the microcavity.

2. The method of claim 1, wherein in the forming of the sacrificial layer, the sacrificial layer is formed by laminating a photo resist on the liquid crystal panel.

3. The method of claim 2, wherein the etch stop layer includes one of indium tin oxide (ITO) or indium zinc oxide (IZO).

4. The method of claim 3, wherein an ashing gas is used in the ashing and wherein the ashing gas includes one of oxygen or oxygen and sulfur hexafluoride (SF₆).

5. The method of claim 4, wherein the etch stop layer serves as a common electrode receiving common voltage.

6. The method of claim 4, further comprising: removing a portion of the etch stop layer before removing the portion of the sacrificial layer after ashing, and forming a common electrode, a lower insulating layer, or a roof layer at the removed etch stop layer portion.

7. The method of claim 2, wherein the etch stop layer includes one of silicon nitride (SiNx) or silicon oxide (SiOx).

8. The method of claim 7, wherein an ashing gas is used in the ashing, and wherein the ashing gas includes oxygen.

9. The method of claim 8, further comprising: forming a common electrode and a pixel electrode on the liquid crystal panel before forming the sacrificial layer.

* * * * *

专利名称(译)	液晶显示器及其制造方法		
公开(公告)号	US9140939	公开(公告)日	2015-09-22
申请号	US13/787315	申请日	2013-03-06
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	LEE SEON UK KIM WON TAE KIM YU JIN LEE WOO JAE CHAE KYUNG TAE		
发明人	LEE, SEON UK KIM, WON TAE KIM, YU JIN LEE, WOO JAE CHAE, KYUNG-TAE		
IPC分类号	G02F1/1341 G02F1/1333 G02F1/1362 G02F1/1337 G02F1/1343 G02F1/139		
CPC分类号	G02F1/134363 G02F1/133377 G02F1/1393 G02F1/133707 G02F1/136209 G02F2001/134345		
助理审查员(译)	潘，贾		
优先权	1020120114226 2012-10-15 KR		
其他公开文献	US20140104533A1		
外部链接	Espacenet USPTO		

摘要(译)

一种液晶显示器的制造方法，包括在液晶面板上形成牺牲层，在牺牲层上形成蚀刻停止层，在蚀刻停止层上形成光刻胶图案，使用光刻胶图案完成蚀刻停止层作为掩模，通过使用完成的蚀刻停止层作为掩模来灰化光致抗蚀剂图案和牺牲层，通过去除牺牲层的一部分并在微腔中形成液晶层来形成微腔。

