



US009158157B2

(12) **United States Patent**
Kang et al.

(10) **Patent No.:** **US 9,158,157 B2**
(45) **Date of Patent:** **Oct. 13, 2015**

(54) **LIQUID CRYSTAL DISPLAY**

(75) Inventors: **Chihtsung Kang**, Shenzhen (CN); **Bo Hai**, Shenzhen (CN)

(73) Assignee: **SHENZHEN CHINA STAR OPTOELECTRONICS TECHNOLOGY CO., LTD.**, Shenzhen (CN)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/704,630**

(22) PCT Filed: **Sep. 6, 2012**

(86) PCT No.: **PCT/CN2012/081059**

§ 371 (c)(1),
(2), (4) Date: **Dec. 17, 2012**

(87) PCT Pub. No.: **WO2014/032323**

PCT Pub. Date: **Mar. 6, 2014**

(65) **Prior Publication Data**

US 2015/0177550 A1 Jun. 25, 2015

(30) **Foreign Application Priority Data**

Sep. 3, 2012 (CN) 2012 1 0321347

(51) **Int. Cl.**

G02F 1/13363 (2006.01)

G02F 1/1337 (2006.01)

G02F 1/1335 (2006.01)

(52) **U.S. Cl.**

CPC **G02F 1/13363** (2013.01); **G02F 1/1336** (2013.01); **G02F 1/1337** (2013.01); **G02F**

1/133634 (2013.01); **G02F 2001/133637** (2013.01); **G02F 2001/133746** (2013.01); **G02F 2413/12** (2013.01)

(58) **Field of Classification Search**

CPC **G02F 1/133634**; **G02F 2413/12**; **G02F 1/13363**; **G02F 1/1336**; **G02F 1/1337**; **G02F 2001/133746**

USPC **349/96**, **119**, **177**, **181**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2005/0099563 A1* 5/2005 Hsu et al. 349/119
2010/0026946 A1* 2/2010 Iwamoto 349/119
2010/0053522 A1* 3/2010 Iwamoto 349/119

* cited by examiner

Primary Examiner — Dung Nguyen

Assistant Examiner — Tai Duong


(74) *Attorney, Agent, or Firm* — Mark M. Friedman

(57) **ABSTRACT**

An LCD includes a TAC film, a PVA film, a biaxial compensation film, an LC cell, a second TAC film, a second PVA film, and a third TAC film from the incident surface to the emitting surface. The biaxial compensation film is used for providing a first retardation value and a second retardation value by adjusting thickness and by adjusting a first refractive index, a second refractive index, and a third refractive index. The second TAC film is used for providing a third retardation value by adjusting thickness and by adjusting a fourth refractive index, a fifth refractive index, and a sixth refractive index corresponding to the light in the first direction, the light in the second direction, and the light in the third direction, respectively. Leakage of light is controlled according to the first retardation value, the second retardation value, and the third retardation value in the LCD.

8 Claims, 6 Drawing Sheets

10






Fig. 1

A1 Pre-tilt angle=85° Ro_v/Rth_b=84/280 A7 Pre-tilt angle=87° Ro_v/Rth_b=60/200
 A2 Pre-tilt angle=85° Ro_v/Rth_b=72/240 A8 Pre-tilt angle=87° Ro_v/Rth_b=48/160
 A3 Pre-tilt angle=85° Ro_v/Rth_b=60/200 A9 Pre-tilt angle=89° Ro_v/Rth_b=84/280
 A4 Pre-tilt angle=85° Ro_v/Rth_b=48/160 A10 Pre-tilt angle=89° Ro_v/Rth_b=72/240
 A5 Pre-tilt angle=87° Ro_v/Rth_b=84/280 A11 Pre-tilt angle=89° Ro_v/Rth_b=60/200
 A6 Pre-tilt angle=87° Ro_v/Rth_b=72/240 A12 Pre-tilt angle=89° Ro_v/Rth_b=48/160




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8

LIQUID CRYSTAL DISPLAY

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a liquid crystal display (LCD), and more particularly to an LCD comprising a biaxial compensation film.

2. Description of the Prior Art

Owing to their low-profile, thin, and lightweight features, LCDs have become the mainstream display devices in recent years. Liquid crystal screens are widely used in electronic devices such as cellphones, personal digital assistants (PDAs), digital cameras, computers, notebooks, etc.

An LCD comprises an LC cell. An alignment of LC molecules in the LC cell is determined by variation of an electric field applied on the LC cell, and the transmission of light in the LC cell is adjusted accordingly. An LC material has a property of birefringence, which means that the refractive index of light in the direction of the long axis of the molecules is different from the refractive index of light in the direction of the short axis of the molecules. Therefore, linearly polarized incident light has diverse phases through different paths in the LC cell in the polarized direction. The feature of color and the transmission of light at a slant viewing angle are different from those at a front viewing angle.

Birefringence index of the LC molecules in the LC cell varies with an observation inclination. With the observation inclination increases, both of the contrast ratio of an image and image resolution decrease. To enhance the contrast ratio of the image obviously at a specific viewing angle and to reduce leakage of light in dark state on the LCD, a compensator film is attached to the LC panel of a conventional LCD. The birefringence of the LC molecules can be symmetrically compensated because the retardation value of light in different directions is compensated using the compensator film.

A bi-layered compensator film has advantages of reducing leakage of light in dark state on the LCD effectively and enhancing the contrast ratio and resolution at a wide viewing angle. However, the bi-layered compensator film is expensive, so production cost cannot be reduced. Contrarily, production cost can be effectively reduced using a unilayered compensator film while an increase in leakage of light in dark state of the LCD seems inevitable.

SUMMARY OF THE INVENTION

An object of the present invention is to provide an LCD comprising a unilayered compensator film. A retardation value of a triacetate cellulose film (TAC) film can be adjusted by adjusting thickness of the TAC film or the refractive index of the TAC film. In addition, leakage of light in dark state of the LCD where the unilayered compensator film is used can be prevented.

According to the present invention, a liquid crystal display (LCD), comprising a backlight source for generating light; a first triacetate cellulose (TAC) film; a first polyvinyl alcohol (PVA) film; a first phase compensator film, for providing a first retardation value and a second retardation value by adjusting thickness of the first phase compensator film and by adjusting a first refractive index, a second refractive index, and a third refractive index corresponding to the light in a first direction, the light in a second direction, and the light in a third direction, respectively; a liquid crystal (LC) cell; a second phase compensator film, for providing a third retardation value by adjusting thickness of the second phase compensator film and by adjusting a fourth refractive index, a fifth refrac-

tive index, and a sixth refractive index corresponding to the light in the first direction, the light in the second direction, and the light in the third direction, respectively; a second PVA film; and a third TAC film. The black-state light leakage at a wide viewing angle is controlled according to the first retardation value, the second retardation value, and the third retardation value in the LCD.

In one aspect of the present invention, a phase delay of the LC cell determined by $(n_e - n_o) \times d$ is between 342.8 nm and 361.4 nm, where n_e indicates an extraordinary refractive index, n_o indicates an ordinary refractive index, and d indicates thickness of the LC cell.

In another aspect of the present invention, the first retardation value is determined by the first refractive index, the second refractive index, and thickness of the first phase compensator film.

In another aspect of the present invention, the first retardation value of the first phase compensator film is between 45.6 nm and 85.8 nm.

In another aspect of the present invention, the second retardation value is determined by the first refractive index, the second refractive index, the third refractive index, and thickness of the first phase compensator film.

In another aspect of the present invention, the second retardation value is between 152 nm and 286 nm.

In another aspect of the present invention, a pretilt angle of LC molecules in the LC cell is between 85 and 90 angles while 90 degrees are excluded.

In another aspect of the present invention, the third retardation value is determined by the fourth refractive index, the fifth refractive index, the sixth refractive index, and thickness of the second phase compensator film.

In another aspect of the present invention, the third retardation value is between Y_1 nm and Y_2 nm where $Y_1 = 0.0052854x^2 - 3.15264x + 502.64$ and $Y_2 = -0.0064882x^2 + 1.85x + 57.78$ stand, and x indicates the second retardation value.

In another aspect of the present invention, the first phase compensator film is a biaxial compensation film, and the second phase compensator film is a second TAC film.

In another aspect of the present invention, the LCD further comprises a third phase compensator film, the first phase compensator film is attached to the second phase compensator film, the first phase compensator film is a biaxial compensation film, the second phase compensator film is a second TAC film, and the third phase compensator film is a fourth TAC film.

In another aspect of the present invention, the third phase compensator film is used for providing a fourth retardation value by adjusting thickness of the third phase compensator film and by adjusting a seventh refractive index, an eighth refractive index, and a ninth refractive index corresponding to the light in the first direction, the light in the second direction, and the light in the third direction, respectively, where leakage of light is controlled according to the first retardation value, the second retardation value, the third retardation value, and the fourth retardation value in the LCD.

Contrast to the conventional technology, the LCD where a single biaxial compensation film is used is provided in the present invention. When a phase delay of the LC cell is between 342.8 nm and 361.4 nm (the phase delay corresponding to a wavelength of 550 nm) and a pretilt angle of LC molecules in the LC cell is between 85 and 90 angles (but 90 degrees are excluded), a first retardation value Ro_b of a first phase compensator film is controlled between 45.6 nm and 85.8 nm, a second retardation value Rth_b of the first phase compensator film is controlled between 152 nm and 286 nm,

and a third retardation value of a second phase compensator film is controlled between Y_1 nm and Y_2 nm where $Y_1=0.0052854x^2-3.15264x+502.64$ and $Y_2=-0.0064882x^2+1.85x+57.78$ stand, and x indicates the second retardation value. The maximum black-state light leakage on the LCD in the present invention is smaller than the maximum black-state light leakage on the conventional LCD where the single biaxial compensation film is used. Moreover, the contrast ratio and resolution of a wide viewing angle (not a horizontal or vertical azimuth) of the LCD in the present invention are effectively enhanced.

These and other objectives of the claimed invention will no doubt become obvious to those of ordinary skill in the art after reading the following detailed description of the preferred embodiment that is illustrated in the various figures and drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows a schematic diagram of an LCD according to a first embodiment of the present invention.

FIG. 2 and FIG. 3 showing diagrams of the relation of the third retardation value Rth_T of the second TAC film and the value of leakage of light when the LC molecules are at difference pretilt angles and the first retardation value Ro_b and the second retardation value Rth_b of difference biaxial compensation films provided that the phase delay of the LC cell is 342.8 nm and 361.4 nm.

FIG. 4 showing a schematic diagram of an LCD according to a second embodiment of the present invention.

FIG. 5 showing a schematic diagram of an LCD 20 according to a third embodiment of the present invention.

FIG. 6 showing a schematic diagram of an LCD 20 according to a fourth embodiment of the present invention.

FIG. 7 showing a schematic diagram of an LCD 20 according to a fifth embodiment of the present invention.

FIG. 8 showing a schematic diagram of an LCD 60 according to a sixth embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Spatially relative terms, such as "beneath", "below", "lower", "above", "upper" and the like, may be used herein for ease of description to describe one element or feature's relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures.

FIG. 1 shows a schematic diagram of an LCD 10 according to a first embodiment of the present invention. The LCD 10 comprises an LC cell 16, a first polarizer 12, a second polarizer 14, and a backlight source 18. The backlight source 18 is used for generating light. The LC cell 16 is glued to the first polarizer 12 and to the second polarizer 14 which faces the first polarizer 12 with a pressure sensitive adhesive (PSA) 2. The first polarizer 12 and the second polarizer 14 are used for deflecting incident light. A first optical axis of the first polarizer 12 is perpendicular to a second optical axis of the second polarizer 14.

The first polarizer 12 comprises a first polyvinyl alcohol (PVA) film 121, a first triacetate cellulose (TAC) film 122, and a first phase compensator film 123. The PVA film 121 is inserted between the first TAC film 122 and the first phase compensator film 123. The second polarizer 14 comprises a second PVA film 141, a second phase compensator film 142,

and a third TAC film 143. The second PVA film 141 is inserted between the second phase compensator film 142 and the third TAC film 143. In this embodiment, the first phase compensator film 123 is a biaxial compensation film. The second phase compensator film 142 is a second TAC film. The first phase compensator film 123 is used for providing a first retardation value and a second retardation value. The second phase compensator film 142 is used for providing a third retardation value. The slow axis of the first phase compensator film 123 forms a 90 degree angle with the absorption axis of the first PVA film 121. The slow axis of the second phase compensator film 142 forms a 90 degree angle with the absorption axis of the second PVA film 141. The method of determination of the first retardation value, the second retardation value, and the third retardation value will be detailed in the following description. The phase delay of the LC cell 16, the retardation value of the TAC film, and the retardation value of the biaxial compensation film all are values corresponding to a wavelength of 550 nm in the following embodiments.

Refer to FIG. 2 and FIG. 3 showing diagrams of the relation of the third retardation value Rth_T of the second TAC film and the value of leakage of light when the LC molecules are at difference pretilt angles and the first retardation value Ro_b and the second retardation value Rth_b of difference biaxial compensation films provided that the phase delay of the LC cell 16 is 342.8 nm and 361.4 nm (the phase delay corresponding to a wavelength of 550 nm). In the present invention, the incident light generated by the backlight source 18 belongs to Lambertian distribution. Luminance in the center of the incident light is defined as 100 nit. The pretilt angle of the LC molecules in the LC cell 16 is between 85 and 90 angles (but 90 degrees are excluded). The phase delay of the LC cell 16 is determined by $(n_e - n_o) \times d$. The phase delay of the LC cell 16 is between 342.8 nm and 361.4 nm where n_e indicates an extraordinary refractive index of the LC cell 16, n_o indicates an ordinary refractive index of the LC cell 16, and d indicates thickness of the LC cell 16.

In FIG. 2 and FIG. 3, Ro_b indicates the first retardation value of the first phase compensator film 123 in the X-Y plane. Rth_b indicates the second retardation value of the first phase compensator film 123 in the axial (Z) direction. Rth_T indicates the third retardation value of the second phase compensator film 142 in the axial (Z) direction. Ro_b , Rth_b , and Rth_T are determined by values plugged into the following equations:

$$Ro_b = (Nx_b - Ny_b) \times D_b;$$

$$Rth_b = [(Nx_b + Ny_b)/2 - Nz_b] \times D_b;$$

$$Rth_T = [(Nx_T + Ny_T)/2 - Nz_T] \times D_T;$$

where Nx_b , Ny_b , and Nz_b indicate refractive indexes of the light generated by the backlight source 18 corresponding to the X-, Y- and Z-axes of three-dimensional Cartesian coordinates, respectively, when the light passes through the first phase compensator film 123. Nx_T , Ny_T , and Nz_T indicate refractive indexes of the light generated by the backlight source 18 corresponding to the X-, Y-, and Z-axes of three-dimensional Cartesian coordinates, respectively, when the light passes through the second phase compensator film 142. D_b and D_T indicate thickness of the first phase compensator film 123 and thickness of the second phase compensator film 142, respectively.

Line segments A1 and A2 as shown in FIG. 2, when the phase delay of the LC cell 16 is 342.8 nm and the pretilt angle of the LC molecules is 85 degrees, the value of leakage of light of the LCD 10 is smaller than $(Ro_b, Rth_b) = (72 \text{ nm}, 240$

nm), provided that $(Ro_b, Rth_b)=(72 \text{ nm}, 240 \text{ nm})$ stands where Ro_b indicates the first retardation value of the first phase compensator film **123**, and Rth_b indicates the second retardation value of the first phase compensator film **123**. Line segments A3 and A4 as shown in FIG. 2, when the phase delay of the LC cell **16** is 342.8 nm and the pretilt angle of the LC molecules is 85 degrees, the value of leakage of light of the LCD **10** is smaller than $(Ro_b, Rth_b)=(48 \text{ nm}, 160 \text{ nm})$, provided that $(Ro_b, Rth_b)=(60 \text{ nm}, 200 \text{ nm})$ stands.

Line segments A5, A6, A9, and A10 as shown in FIG. 2, when the phase delay of the LC cell **16** is 342.8 nm and the pretilt angle of the LC molecules is 87 and 89 degrees, the value of leakage of light of the LCD **10** is smaller than $(Ro_b, Rth_b)=(84 \text{ nm}, 280 \text{ nm})$, provided that $(Ro_b, Rth_b)=(72 \text{ nm}, 240 \text{ nm})$ stands. Line segments A7, A8, A11, and A12 as shown in FIG. 2, when the phase delay of the LC cell **16** is 342.8 nm and the pretilt angle of the LC molecules is 87 and 89 degrees, the value of leakage of light of the LCD **10** is smaller than $(Ro_b, Rth_b)=(48 \text{ nm}, 160 \text{ nm})$, provided that $(Ro_b, Rth_b)=(60 \text{ nm}, 200 \text{ nm})$ stands. Preferably, the value of leakage of light of the LCD **10** will be smaller when the third retardation value Rth_T between 106.2 nm and 129.8 nm is taken into considerations.

Line segments C1, C2, C5, C6, C9, and C10 as shown in FIG. 3, when the phase delay of the LC cell **16** is 361.4 nm and the pretilt angle of the LC molecules is 85, 87 and 89 degrees, the value of leakage of light of the LCD **10** is smaller than $(Ro_b, Rth_b)=(84 \text{ nm}, 280 \text{ nm})$, provided that $(Ro_b, Rth_b)=(72 \text{ nm}, 240 \text{ nm})$ stands. Line segments C3, C4, C7, C8, C11, and C12 as shown in FIG. 3, when the phase delay of the LC cell **16** is 361.4 nm and the pretilt angle of the LC molecules is 85, 87 and 89 degrees, the value of leakage of light of the LCD **10** is smaller than $(Ro_b, Rth_b)=(48 \text{ nm}, 160 \text{ nm})$, provided that $(Ro_b, Rth_b)=(60 \text{ nm}, 200 \text{ nm})$ stands.

Even though the first retardation value Ro_b is between 48 nm and 84 nm and the second retardation value Rth_b is between 160 nm and 280 nm as shown in FIG. 2 and FIG. 3, the first retardation value Ro_b and the second retardation value Rth_b can be slightly adjusted. In other words, the first retardation value Ro_b is between 45.6 nm and 85.8 nm, and the second retardation value Rth_b is between 152 nm and 286 nm if the minimal amount of light that leaks through the display in the dark state is 0.2 nit. To ensure that the minimal amount of light that leaks through the display in the dark state is less than 0.2 nit when the first retardation value Ro_b is between 45.6 nm and 85.8 nm, and the second retardation value Rth_b is between 152 nm and 286 nm, the third retardation value Rth_T is between the Y_1 nm and Y_2 nm where $Y_1=0.0052854x^2-3.15264x+502.64$ and $Y_2=-0.0064882x^2+1.85x+57.78$ stand, and x indicates the second retardation value Rth_b .

Provided that the phase delay of the LC cell is 352.1 nm, the first retardation value Ro of the biaxial compensation film is 72 nm, the second retardation value Rth of the biaxial compensation film is 240 nm, and the third retardation value Rth of the second TAC film is 240 nm in the conventional LCD where the single biaxial compensation film is used, leakage of light in dark state occurs at $\phi=20^\circ-40^\circ$, $\phi=140^\circ-160^\circ$, $\phi=200^\circ-220^\circ$, and $\phi=310^\circ-330^\circ$ where ϕ indicates an angle formed by the X axis and a projection of the axis of the LC molecules in the X-Y plane. However, an experiment proves that light leakage can still be prevented in the LCD **10** where the single first phase compensator film **123** according to the first retardation value Ro_b , the second retardation value Rth_b , and the third retardation value Rth_T when the phase delay of the LC cell **16** is between 342.8 nm and 361.4 nm and the pretilt angle of the LC molecules in the LC cell **16** is between 85 and 90

angles (but 90 degrees are excluded). In other words, the first retardation value Ro_b is controlled between 45.6 nm and 85.8 nm, and the second retardation value Rth_b is controlled between 152 nm and 286 nm. Meanwhile, the third retardation value Rth_T of the second phase compensator film **142** is adjusted according to the adjusted second retardation value Rth_b . In this way, the third retardation value Rth_T can be between Y_1 nm and Y_2 nm where $Y_1=0.0052854x^2-3.15264x+502.64$ and $Y_2=-0.0064882x^2+1.85x+57.78$ stand, and x indicates the second retardation value Rth_b . The value of black-state light leakage on the LCD **10** is smaller than the value of black-state light leakage on the conventional LCD where the single biaxial compensation film is used.

The first phase compensator film **123** and the second phase compensator film **142** are not limited to the positions as shown in FIG. 1. Other embodiments which have the same effects are elaborated in the following.

Refer to FIG. 4 showing a schematic diagram of an LCD **20** according to a second embodiment of the present invention. The difference between FIG. 4 and FIG. 1 is that, in FIG. 4, a first polarizer film **22** in the LCD **20** comprises a first TAC film **122**, a first PVA film **121**, and a second phase compensator film **142** from the incident surface to the emitting surface. A second polarizer film **24** in the LCD **20** comprises a first phase compensator film **123**, a second PVA film **141**, and a third TAC film **143** from the incident surface to the emitting surface. The second phase compensator film **142** is a second TAC film. The first phase compensator film **123** is a biaxial compensation film.

Refer to FIG. 5 showing a schematic diagram of an LCD **30** according to a third embodiment of the present invention. The difference between FIG. 5 and FIG. 1 is that, in FIG. 5, a first polarizer film **32** in the LCD **30** comprises a first TAC film **122** and a first PVA film **121** from the incident surface to the emitting surface. A second polarizer film **34** in the LCD **30** comprises a second phase compensator film **142**, a first phase compensator film **123**, a second PVA film **141**, and a third TAC film **143** from the incident surface to the emitting surface. The first phase compensator film **123** is a biaxial compensation film, and the second phase compensator film **142** is a second TAC film in this embodiment. The slow axis of the first phase compensator film **123** and the slow axis of the second phase compensator film **142** form a 90 degree angle with the absorption axis of the second PVA film **141**, respectively.

Refer to FIG. 6 showing a schematic diagram of an LCD **40** according to a fourth embodiment of the present invention. The difference between FIG. 6 and FIG. 5 is that, in FIG. 6, a first polarizer film **42** in the LCD **40** comprises a first TAC film **122**, a first PVA film **121**, a first phase compensator film **123**, and a second phase compensator film **142** from the incident surface to the emitting surface. A second polarizer film **44** in the LCD **40** comprises a second PVA film **141** and a third TAC film **143** from the incident surface to the emitting surface. The first phase compensator film **123** is a biaxial compensation film, and the second phase compensator film **142** is a second TAC film in this embodiment. The slow axis of the first phase compensator film **123** and the slow axis of the second phase compensator film **142** form a 90 degree angle with the absorption axis of the first PVA film **121**, respectively.

Refer to FIG. 7 showing a schematic diagram of an LCD **50** according to a fifth embodiment of the present invention. The difference between FIG. 7 and FIG. 5 is that, in FIG. 7, a first polarizer film **52** in the LCD **50** comprises a first TAC film **122**, a first PVA film **121**, and a third phase compensator film **124** from the incident surface to the emitting surface. A sec-

ond polarizer film 54 in the LCD 50 comprises a second phase compensator film 142, a first phase compensator film 123, a second PVA film 141, and a third TAC film 143 from the incident surface to the emitting surface. The first phase compensator film 123 is a biaxial compensation film, the second phase compensator film 142 is a second TAC film, and the third phase compensator film 124 is a fourth TAC film in this embodiment. The slow axis of the first phase compensator film 123 and the slow axis of the second phase compensator film 142 form a 90 degree angle with the absorption axis of the second PVA film 141, respectively. The third phase compensator film 124 provides a fourth retardation value R_{th_7} , by adjusting thickness of the third phase compensator film 124 and by adjusting refractive indexes of the light generated by the backlight source 18 corresponding to the X-, Y-, and Z-axes of three-dimensional Cartesian coordinates. The leakage of light in the LCD 50 is controlled according to the first retardation value Ro_b , the second retardation value R_{th_b} , the third retardation value R_{th_7} , and the fourth retardation value R_{th_7} . What is worth noting is that, the sum of the third retardation value R_{th_7} provided by the second phase compensator film 142 and the fourth retardation value R_{th_7} provided by the third phase compensator film 124 in the LCD 50 as shown in FIG. 7 is equal to the third retardation value R_{th_7} provided by the second phase compensator film 142 in the LCD 10 as shown in FIG. 1.

Refer to FIG. 8 showing a schematic diagram of an LCD 60 according to a sixth embodiment of the present invention. The difference between FIG. 8 and FIG. 7 is that, in FIG. 8, a first polarizer film 62 in the LCD 60 comprises a first TAC film 122, a first PVA film 121, a first phase compensator film 123, and a second phase compensator film 142 from the incident surface to the emitting surface. A second polarizer film 64 in the LCD 60 comprises a third phase compensator film 124, a second PVA film 141, and a third TAC film 143 from the incident surface to the emitting surface. The first phase compensator film 123 is a biaxial compensation film, the second phase compensator film 142 is a second TAC film, and the third phase compensator film 124 is a fourth TAC film in this embodiment. The slow axis of the first phase compensator film 123 and the slow axis of the second phase compensator film 142 form a 90 degree angle with the absorption axis of the second PVA film 141, respectively. The third phase compensator film 124 provides a fourth retardation value R_{th_7} , by adjusting thickness of the third phase compensator film 124 and by adjusting refractive indexes of the light produced by the backlight source 18 corresponding to the X-, Y-, and Z-axes of three-dimensional Cartesian coordinates. The leakage of light in the LCD 60 is controlled according to the first retardation value Ro_b , the second retardation value R_{th_b} , the third retardation value R_{th_7} , and the fourth retardation value R_{th_7} . What is worth noting is that, the sum of the third retardation value R_{th_7} provided by the second phase compensator film 142 and the fourth retardation value R_{th_7} provided by the third phase compensator film 124 in the LCD 60 as shown in FIG. 8 is equal to the third retardation value R_{th_7} provided by the second phase compensator film 142 in the LCD 10 as shown in FIG. 1.

Each of the LCDs 20, 30, 40, 50, and 60 as shown in FIGS. 4 to 8 is similar to the LCD 10 as shown in FIG. 1. Leakage of light in each of the LCDs 20, 30, 40, 50, and 60 can be controlled by adjusting the first retardation value Ro_b , the second retardation value R_{th_b} , the third retardation value R_{th_7} , and the fourth retardation value R_{th_7} . The adjustment range of the first retardation value Ro_b , of the second retardation value R_{th_b} , of the third retardation value R_{th_7} , and of

the fourth retardation value R_{th_7} for each of the LCDs 20, 30, 40, 50, and 60 is similar to that for the LCD 10, so no further information will be provided.

Those skilled in the art will readily observe that numerous modifications and alterations of the device may be made while retaining the teachings of the invention. Accordingly, the above disclosure should be construed as limited only by the metes and bounds of the appended claims.

What is claimed is:

1. A liquid crystal display (LCD), comprising a backlight source for generating light, and the LCD also comprising a first triacetate cellulose (TAC) film; a first polyvinyl alcohol (PVA) film; a first phase compensator film, for providing a first retardation value and a second retardation value by adjusting thickness of the first phase compensator film and by adjusting a first refractive index, a second refractive index, and a third refractive index corresponding to the light in a first direction, the light in a second direction, and the light in a third direction, respectively; a liquid crystal (LC) cell; a second phase compensator film, for providing a third retardation value by adjusting thickness of the second phase compensator film and by adjusting a fourth refractive index, a fifth refractive index, and a sixth refractive index, respectively; a second PVA film; and a third TAC film; wherein black-state light leakage at a wide viewing angle is controlled according to the first retardation value, the second retardation value, and the third retardation value in the LCD, wherein the third retardation value is determined by the fourth refractive index, the fifth refractive index, the sixth refractive index, and thickness of the second phase compensator film, and the third retardation value is between Y_1 nm and Y_2 nm where $Y_1 = 0.0052854x^2 - 3.15264x + 502.64$ and $Y_2 = -0.0064882x^2 + 1.85x + 57.78$ stand, and x indicates the second retardation value.
2. The LCD as claimed in claim 1, wherein a phase delay of the LC cell determined by $(n_e - n_o) \times d$ is between 342.8 nm and 361.4 nm, where n_e indicates an extraordinary refractive index, n_o indicates an ordinary refractive index, and d indicates thickness of the LC cell.
3. The LCD as claimed in claim 1, wherein the first retardation value is determined by the first refractive index, the second refractive index, and thickness of the first phase compensator film.
4. The LCD as claimed in claim 2, wherein the first retardation value of the first phase compensator film is between 45.6 nm and 85.8 nm.
5. The LCD as claimed in claim 1, wherein the second retardation value is determined by the first refractive index, the second refractive index, the third refractive index, and thickness of the first phase compensator film.
6. The LCD as claimed in claim 5, wherein the second retardation value is between 152 nm and 286 nm.
7. The LCD as claimed in claim 1, wherein the first phase compensator film is a biaxial compensation film, and the second phase compensator film is a second TAC film.
8. The LCD as claimed in claim 1, wherein the LCD further comprises a third phase compensator film, the first phase compensator film is attached to the second phase compensator film, the first phase compensator film is a biaxial compen-

sation film, the second phase compensator film is a second TAC film, and the third phase compensator film is a fourth TAC film.

* * * * *

专利名称(译)	液晶显示器		
公开(公告)号	US9158157	公开(公告)日	2015-10-13
申请号	US13/704630	申请日	2012-09-06
[标]申请(专利权)人(译)	深圳市华星光电技术有限公司		
申请(专利权)人(译)	深圳中星光电科技有限公司		
当前申请(专利权)人(译)	深圳市中国星光电科技有限公司.		
[标]发明人	KANG CHIHTSUNG HAI BO		
发明人	KANG, CHIHTSUNG HAI, BO		
IPC分类号	G02F1/13363 G02F1/1337 G02F1/1335		
CPC分类号	G02F1/13363 G02F1/1336 G02F1/1337 G02F1/133634 G02F2413/12 G02F2001/133637 G02F2001/133746 G02F1/1393 G02F2413/02 G02F2413/03 G02F2413/05 G02F2413/06 G02F2413/11		
代理人(译)	FRIEDMAN, MARK M.		
审查员(译)	NGUYEN, 龚便		
优先权	201210321347.7 2012-09-03 CN		
其他公开文献	US20150177550A1		
外部链接	Espacenet USPTO		

摘要(译)

LCD包括TAC膜，PVA膜，双轴补偿膜，LC单元，第二TAC膜，第二PVA膜和从入射表面到发射表面的第三TAC膜。双轴补偿膜用于通过调节厚度和通过调节第一折射率，第二折射率和第三折射率来提供第一延迟值和第二延迟值。第二TAC膜用于通过调节厚度和通过调节第四折射率，第五折射率和第六折射率来提供第三延迟值，第四折射率，第五折射率和第六折射率对应于第一方向上的光，第二方向上的光和分别是第三方向的光。根据LCD中的第一延迟值，第二延迟值和第三延迟值来控制光的泄漏。

