



US009851603B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 9,851,603 B2**
(45) **Date of Patent:** **Dec. 26, 2017**

(54) **OPTICAL COMPENSATION FILM AND
LIQUID CRYSTAL DISPLAY INCLUDING
THE SAME**

2001/1398; G02F 2413/06; G02F
1/13363; G02F 2202/40; G02F
2001/133637; G02B 5/3016; C08J 5/18;
C09K 19/38

(75) Inventors: **Hee Kyung Kim**, Seongnam-si (KR);
Jang-Kun Song, Seoul (KR)

USPC 349/117-121
See application file for complete search history.

(73) Assignees: **SAMSUNG ELECTRONICS CO.,
LTD.**, Gyeonggi-Do (KR);
**SUNGKYUNKWAN UNIVERSITY
FOUNDATION FOR CORPORATE
COLLABORATION**, Gyeonggi-Do
(KR)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,198,917 A * 3/1993 Togashi G02F 1/133753
349/126
5,504,603 A * 4/1996 Winker C23C 14/226
349/117
5,557,434 A * 9/1996 Winker et al. 349/117
5,619,352 A 4/1997 Koch et al.
6,912,030 B1 * 6/2005 Coates et al. 349/119
6,995,825 B2 2/2006 Graham et al.
7,428,030 B2 * 9/2008 Kobayashi et al. 349/122
7,477,343 B2 1/2009 Skjonnemand et al.
7,515,231 B2 4/2009 Hale et al.
7,538,841 B2 * 5/2009 Murakami et al. 349/117
7,671,945 B2 3/2010 Hale et al.
2002/0089629 A1 * 7/2002 Kim et al. 349/117
2004/0183973 A1 * 9/2004 Roska et al. 349/117
2005/0219447 A1 * 10/2005 Slaney et al. 349/117
2006/0066804 A1 3/2006 Tasaka

(Continued)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 250 days.

(21) Appl. No.: **13/447,805**

(22) Filed: **Apr. 16, 2012**

(65) **Prior Publication Data**

US 2012/0327342 A1 Dec. 27, 2012

(30) **Foreign Application Priority Data**

Jun. 24, 2011 (KR) 10-2011-0061908

(51) **Int. Cl.**

G02F 1/1335 (2006.01)
G02F 1/13363 (2006.01)

(52) **U.S. Cl.**

CPC **G02F 1/13363** (2013.01); **G02F**
2001/133633 (2013.01); **G02F 2413/04**
(2013.01); **G02F 2413/06** (2013.01); **G02F**
2413/12 (2013.01)

(58) **Field of Classification Search**

CPC G02F 1/133634; G02F 1/133528; G02F
1/133632; G02F 2413/02; G02F
2001/133633; G02F 2413/12; G02F

FOREIGN PATENT DOCUMENTS

JP 2006091551 4/2006
JP 2010049192 3/2010
JP 2010107958 5/2010

Primary Examiner — Edward Glick


Assistant Examiner — David Chung

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP

(57) **ABSTRACT**

A compensation film for a liquid crystal film includes a first
layer including splayed rod-shaped nematic liquid crystal
material and a second layer disposed on a surface of the first
layer and including at least one of a biaxial layer and an
A-plate.

11 Claims, 19 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2007/0085951	A1 *	4/2007	Hale	G02F 1/13363 349/117
2007/0222927	A1 *	9/2007	Uehara et al.	349/117
2009/0128718	A1 *	5/2009	Nakagawa	349/8
2009/0180056	A1	7/2009	Ohsawa et al.	
2009/0231517	A1 *	9/2009	Shiraogawa	G02F 1/133632 349/75

* cited by examiner

FIG. 1





FIG. 2






FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18





FIG. 19



OPTICAL COMPENSATION FILM AND LIQUID CRYSTAL DISPLAY INCLUDING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priority to Korean Patent Application No. 10-2011-0061908 filed on Jun. 24, 2011, and all the benefits accruing therefrom under 35 U.S.C. §119, the content of which in its entirety is herein incorporated by reference.

BACKGROUND

1. Field

Provided is a liquid crystal display and an optical compensation film for the liquid crystal display.

2. Description of the Related Art

A twisted nematic ("TN") mode liquid crystal display ("LCD") is widely used in various devices, such as a monitor and a television set, for example. In a TN mode LCD, a nematic liquid crystal material is typically homogeneously aligned with a slight pretilt angle, and the azimuthal angle of the liquid crystal molecules is gradually twisted from a substrate to the other substrate by about a right angle. The director of the liquid crystal molecules is varied by applying a vertical electric field to the liquid crystal layer of the TN LCD to adjust optical transmittance, thereby displaying images.

In the TN mode LCD, unlike vertical alignment ("VA") and in-plane switching ("IPS") mode LCD, the average direction of the liquid crystal director may point downward relative to the front direction such that image quality may be impaired when viewing the TN mode LCD upwardly and downwardly. However, the TN mode LCD has a better image quality in leftward and rightward directions compared to the VA and IPS mode LCD.

A wide-viewing ("WV") film may be used to improve the upward and downward viewing characteristics of the TN mode LCD. The WV film is manufactured by aligning a liquid crystal material with a discotic nematic phase such that the direction of the liquid crystal director gradually changes along the thickness direction.

However, discotic liquid crystal material, which is typically used in the WV film, may not be cost-effective when used for a large-sized WV film since the discotic liquid crystal materials are substantially expensive.

In addition, light leakage may occur in a black state of a normally white TN mode LCD, thereby decreasing the contrast ratio.

SUMMARY

In an embodiment, a compensation film for a liquid crystal display includes: a first layer including splayed rod-shaped nematic liquid crystal material; and a second layer disposed on a surface of the first layer and including at least one of a biaxial layer and an A-plate.

In an embodiment, an optical axis of the second layer may be at an angle of about 90 degrees with respect to a splay plane of the first layer, and liquid crystal molecules of the first layer may have polar angles decreasing as moving toward the second layer.

In an embodiment, a difference in the polar angles of the liquid crystal molecules at opposing surfaces of the first layer may be equal to or greater than about 30 degrees.

In an embodiment, retardation of the second layer in plane direction may be about 120 nanometers (nm) to about 220 nanometers (nm), retardation of the second layer in thick-

ness direction may be about -80 nm to about -180 nm, and retardation of the first layer may be about 50 nm to about 150 nm.

In an embodiment, the splayed rod-shaped nematic liquid crystal material of the first layer may have a twist alignment with a twist angle in a range from about 2 degrees to about 10 degrees.

In an embodiment, the compensation film may further include: a polarizer disposed opposite to the first layer such that the second layer is interposed between the polarizer and the first layer; and a first protective layer disposed opposite to the second layer such that the polarizer is interposed between the first protective layer and the second layer.

In an embodiment, the compensation film may further include a second protective layer disposed between the polarizer and the second layer.

In another embodiment, a liquid crystal display includes: a twisted nematic mode liquid crystal panel; a compensation film disposed on an outer surface of the twisted nematic mode liquid crystal panel; and a polarizing film disposed on an outer surface of the compensation film, where the compensation film includes: a first layer including splayed rod-shaped nematic liquid crystal material; and a second layer disposed on an outer surface of the first layer and including at least one of a biaxial layer and an A-plate.

In an embodiment, an optical axis of the second layer may be at an angle of about 90 degrees with respect to a splay plane of the first layer, and liquid crystal molecules of the first layer may have polar angles decreasing as moving toward the second layer.

In an embodiment, a difference in the polar angles of the liquid crystal molecules at opposing surfaces of the first layer may be equal to or greater than about 30 degrees.

In an embodiment, retardation of the second layer in plane direction may be about 120 nm to about 220 nm, retardation of the second layer in thickness direction may be about -80 nm to about -180 nm, and retardation of the first layer may be about 50 nm to about 150 nm.

In an embodiment, the splayed rod-shaped nematic liquid crystal material of the first layer may have a twist alignment with a twist angle in a range from about 2 degrees to about 10 degrees.

In an embodiment, the polarizing film may include: a polarizer disposed on an outer surface of the second layer; and a first protective layer disposed on an outer surface of the polarizer.

In an embodiment, the polarizing film may further include a second protective layer disposed between the polarizer and the second layer.

In another embodiment, a liquid crystal display includes: a twisted nematic mode liquid crystal panel; a compensation film disposed on an outer surface of the panel; and a polarizing film disposed on an outer surface of the compensation film, where the compensation film discotic nematic liquid crystal material with a splay-twist alignment, and the twist angle of the compensation film is in a range from about 2 degrees to about 10 degrees.

BRIEF DESCRIPTION OF THE DRAWINGS

The above and other features of the invention will become more apparent by describing in detailed exemplary embodiments thereof with reference to the accompanying drawings, in which:

FIGS. 1 and 2 are schematic cross-sectional views of embodiments of a liquid crystal display ("LCD") including optical compensation films;

FIG. 3 is a schematic view of liquid crystal molecules in liquid crystal panels of the LCDs shown in FIGS. 1 and 2, showing arrangements thereof with respect to various voltages in the liquid crystal panels;

FIG. 4 is a schematic view of liquid crystal molecules in upper and lower compensation films shown in FIGS. 1 and 2, showing arrangements thereof;

FIG. 5 is a schematic view of liquid crystal molecules in the liquid crystal panel and the compensation film shown in FIG. 1, showing arrangements thereof;

FIG. 6 is a graph illustrating contrast versus viewing angle showing viewing characteristics of a comparative example of the LCD;

FIG. 7 is a graph illustrating contrast versus viewing angle showing viewing characteristics of an embodiment of the LCD;

FIG. 8 is graph illustrating contrast ratio versus viewing angle showing viewing characteristics of the comparative example of the LCD and an embodiment of LCD shown in FIGS. 6 and 7;

FIG. 9 is a schematic cross-sectional view of another embodiment of an LCD;

FIG. 10 is a graph showing contrast ratio ("CR") for various viewing angles as function of in-plane retardation R_o of a biaxial layer in the LCD shown in FIG. 9;

FIG. 11 is a graph showing CR for various viewing angles as function of thickness retardation R_{th} of a biaxial layer in the LCD shown in FIG. 9;

FIG. 12 is a graph showing CR for various viewing angles as function of retardation $\Delta n d$ of a splayed layer in the LCD shown in FIG. 9;

FIG. 13 is a graph showing azimuthal angle and polar angle of a liquid crystal molecule of the LCD shown in FIGS. 1 and 2 in the presence of applied voltage;

FIG. 14 is a graph illustrating contrast versus viewing angle showing viewing characteristics of a comparative example of the LCD;

FIG. 15 is a graph illustrating contrast versus viewing angle showing viewing characteristics of an embodiment of the LCD;

FIG. 16 is graph illustrating contrast ratio versus viewing angle showing viewing characteristics of the comparative LCD and the embodiment of the LCD shown in FIGS. 15 and 16;

FIG. 17 is a graph showing a front contrast ratio as function of twist angle of a rod-shaped splayed layer with twist;

FIG. 18 is a graph showing a front contrast ratio as function of twist angle of a discotic splayed layer with twist; and

FIG. 19 is a graph showing a front contrast ratio as function of twist angle of a discotic splayed layer with twist.

DETAILED DESCRIPTION

The invention now will be described more fully herein-after with reference to the accompanying drawings, in which various embodiments are shown. This invention may, however, be embodied in many different forms, and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. Like reference numerals refer to like elements throughout.

It will be understood that when an element is referred to as being "on" another element, it can be directly on the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being "directly on" another element, there are no intervening elements present. As used herein, the term "and/or" includes any and all combinations of one or more of the associated listed items.

It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers and/or sections, these elements,

components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Thus, a first element, component, region, layer or section discussed below could be termed a second element, component, region, layer or section without departing from the teachings of the invention.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms "a," "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms "comprises" and/or "comprising," or "includes" and/or "including" when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

Furthermore, relative terms, such as "lower" or "bottom" and "upper" or "top," may be used herein to describe one element's relationship to another element as illustrated in the Figures. It will be understood that relative terms are intended to encompass different orientations of the device in addition to the orientation depicted in the Figures. For example, if the device in one of the figures is turned over, elements described as being on the "lower" side of other elements would then be oriented on "upper" sides of the other elements. The exemplary term "lower," can therefore, encompass both an orientation of "lower" and "upper," depending on the particular orientation of the figure. Similarly, if the device in one of the figures is turned over, elements described as "below" or "beneath" other elements would then be oriented "above" the other elements. The exemplary terms "below" or "beneath" can, therefore, encompass both an orientation of above and below.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

Embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

All methods described herein can be performed in a suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., "such as"), is intended merely to better illustrate the invention and does not pose a limitation on the scope of the invention unless otherwise claimed. No language in the specification should be construed as indicating any non-claimed element as essential to the practice of the invention as used herein.

Hereinafter, embodiments will be described in further detail with reference to the accompanying drawings.

Embodiments of a liquid crystal display ("LCD") and an optical compensation film therefor will now be described in detail with reference to FIGS. 1 to 5.

FIGS. 1 and 2 are schematic cross-sectional views of embodiments of LCDs including optical compensation films, FIG. 3 is a schematic view of liquid crystal molecules in liquid crystal panels of the LCDs shown in FIGS. 1 and 2, showing arrangements thereof with respect to various voltages in the liquid crystal panels, FIG. 4 is a schematic view of liquid crystal molecules in upper and lower compensation films shown in FIGS. 1 and 2, showing arrangements of the liquid crystal molecules, and FIG. 5 a schematic view of liquid crystal molecules in the liquid crystal panel and the compensation film shown in FIG. 1, showing arrangements of the liquid crystal molecules.

In an embodiment, as shown in FIG. 1, the LCD may be a twisted nematic ("TN") LCD including nematic liquid crystal material. In such an embodiment, the LCD may include a pair of optical compensation films (e.g., a first optical compensation film 121 and a second optical compensation film 131), a liquid crystal panel 110 disposed between inner surfaces of the optical compensation films 121 and 131, and a pair of polarizing films (e.g., a first polarizing film 124 and a second polarizing film 134) disposed on outer surfaces the compensation films 121 and 131, respectively.

Each of the optical compensation films 121 and 131 may have a dual-layered structure that includes a splayed layer 122 or 132 and a biaxial layer 123 or 133. The splayed layer 122 or 132 may be disposed close to the liquid crystal panel 110, while the biaxial layer 123 or 133 may be disposed close to a corresponding polarizing film 124 or 134 of the pair of polarizing films. In an embodiment, adhesive films (not shown) may be disposed between the compensation films 121 and 131 and the liquid crystal panel 110.

Each of the polarizing films 124 and 134 may include a polarizer 126 or 136 and protective layers 125, 127 or 135, 137 disposed on two opposing surfaces of the polarizer 126 or 136, e.g., outer and inner surfaces of the polarizer 126 or 136.

In an embodiment, each of the optical compensation films 121 or 131 and a corresponding polarizing film 124 or 134 may be formed as a single film, that is, may be formed as a single unitary and indivisible unit.

Hereinafter, a film or a layer 121 to 127 or 131 to 137 may be referred based on a position thereof relative to the liquid crystal panel 110 for convenience of description. In one embodiment, for example, the one disposed on the liquid crystal panel 110 among the pair of compensation films 121 and 131 may be referred to as an "upper" compensation film 121, while the other disposed under the liquid crystal panel 110 among the pair of compensation films 121 and 131 may be referred to as a "lower" compensation film 131.

Another embodiment of an LCD 200 shown in FIG. 2, which may be a TN LCD, may have substantially the same layered structure as the embodiment of the LCD 100 shown in FIG. 1. In such an embodiment, the LCD 200 may include a liquid crystal panel 210, upper and lower compensation films 221 and 231, and upper and lower polarizing films 224 and 234, and each of the upper and lower compensation films 221 and 231 may have a double layered structure including a splayed layer 222 or 232 and a biaxial layer 223 or 233.

In an embodiment, as shown in FIG. 2, the protective layers 135 and 125 disposed an inner surface of the polarizers 126 and 136 shown in FIG. 1 may be omitted. In such an embodiment, each of the polarizing films 224 and 234 in the LCD 200 may include a polarizer 226 or 236 and a single

protective layer 227 or 237. The single protective layer 227 or 237 is disposed at the outer surface of the polarizer 226 or 236.

Referring to FIGS. 1 and 2, the liquid crystal panel 110 or 210 may include a pair of substrates (not shown) and a liquid crystal layer disposed between the substrates. In an embodiment, the liquid crystal layer may be a nematic liquid crystal layer.

Referring to FIG. 3, liquid crystal molecules in the liquid crystal layer may be homogeneously aligned with a slight pretilt angle. The liquid crystal molecules may gradually twist from one substrate to the other substrate by a predetermined angle, for example, by about 90 degrees. Such a liquid crystal alignment may be obtained by an alignment layer (not shown) disposed on an inner surface of a substrate. In one embodiment, for example, the homogeneous alignment of the liquid crystal molecules may be obtained by employing predetermined materials for the alignment layer, and the azimuthal angle of liquid crystal directors may be determined based on rubbing or irradiation of ultraviolet ray.

A plurality of electrodes (not shown) that generate vertical electric field in the liquid crystal layer may be disposed on the inner surfaces of the substrates.

FIG. 3 shows arrangements of liquid crystal molecules along the z-axis, which is vertical to the liquid crystal layer, when various voltages are applied to the electrodes. As shown in FIG. 3, as the voltage applied to the electrodes increases, i.e., as the electric field generated in the liquid crystal layer increases, the longitudinal directions of the liquid crystal molecules become more parallel to the direction of the electric field. However, liquid crystal molecules disposed substantially close to the inner surface of the substrate may tend to maintain their initial orientations since the liquid crystal molecules disposed substantially close to the inner surface of the substrate are affected more by the alignment layer than by the electric field.

Referring to FIG. 4, in an embodiment, the splayed layers 122, 132, 222 and 232 may include rod-type nematic liquid crystal molecules 300 that are splay-aligned. The liquid crystal molecules 300 in the splayed layers 122, 132, 222 and 232 may be aligned such that the polar angles θ of the liquid crystal molecules 300 increase as moving from the polarizing films 124 and 134 to the liquid crystal panel panels 110 and 210, and the difference in the polar angles θ from one surface to the opposing surface of the splayed layers 122, 132, 222 and 232 may be equal to or greater than about 30 degrees. In FIG. 4, a substantial portion of the longitudinal axes of the liquid crystal molecules 300 may be disposed on a plane (referred to as a "splay plane" hereinafter) that may make an angle of about 45 degrees with both the x-axis and the y-axis. Here, directions of the x-axis and the y-axis are corresponding to rubbing directions of the inner surfaces of the substrates of the liquid crystal panel 110 or 210, and the liquid crystal molecules in the liquid crystal panel 110 or 210 may be aligned along a direction of a vector sum of the rubbing directions of the inner surfaces of the substrates of the liquid crystal panel 110 or 210. In FIG. 4, the z-axis corresponds to a direction perpendicular to an x-y plane (e.g., a plane defined by the x-axis and the y-axis).

The refractive anisotropy Δn of the splayed layers 122, 132, 222 and 232 may be in a range from about 0.05 to about 0.2, and the retardation $\Delta n d$ of the splayed layers 122, 132, 222 and 232 may be in a range from about 50 nanometers (nm) to about 150 nanometers (nm).

The biaxial layers 123, 133, 223 and 233 may include rod-shaped liquid crystal molecules 400 that may be aligned substantially along a predetermined direction. In an embodiment, an optical axis, e.g., the longitudinal axes of the liquid crystal molecules 400, of the biaxial layers 123, 133, 223

and **233** may be substantially perpendicular to the splay plane of the splayed layer **122**, **132**, **222** or **232**, as shown in FIG. 4.

The retardation in plane direction R_o (also referred to as “in-plane retardation”) of the biaxial layer **123**, **133**, **223** or **233** may be in a range from about 120 nm to about 220 nm, and the retardation R_{th} in thickness direction (also referred to as “thickness retardation”) may be in a range from about -80 nm to about -180 nm. Here, $R_o = (N_x - N_y)d$, and $R_{th} = [N_z - (N_x + N_y)/2]d$, where d denotes the thickness of the biaxial layer **123**, **133**, **223** or **233**, and N_x , N_y and N_z denote the refractive indices in the x-axis, y-axis and z-axis directions, respectively. The retardations of the biaxial layers **123**, **133**, **223** and **233** may be determined based on various factors of the liquid crystal panels **110** and **210**, e.g., properties of film materials, and also based on characteristics of the splayed layers **122**, **132**, **222** and **232**.

The biaxial layers **123**, **133**, **223** and **233** may be substituted with A-plate that may have substantially the same retardations. A-plate may be a uniaxial phase retardation plate having an optical axis parallel to a surface thereof.

In an embodiment, the polarizers **126**, **136**, **226** and **236** may include, for example, polyvinyl alcohol (“PVA”) and additional iodine. The protective layers **125**, **127**, **135**, **137**, **227** and **237** may support and protect the polarizers **126**, **136**, **226** and **236**. In an embodiment, the protective layers **125**, **127**, **135**, **137**, **227** and **237** may include, for example, triacetyl cellulose (“TAC”).

The splayed layers **122**, **132**, **222** and **232** in the LCDs **100** and **200** may compensate for vertical asymmetry of liquid crystal alignment, and the biaxial layers **123**, **133**, **223** and **233** may compensate for viewing angles in all directions.

Referring again to FIG. 3, when there is no electric field in the liquid crystal layer of the liquid crystal panels **110** and **210**, although the pretilt may cause substantially slight asymmetry in the liquid crystal alignment, the asymmetry may be substantially ignorable. However, when the electric field is generated in the liquid crystal layer, the electric field may begin to tilt the liquid crystal molecules near a center in a direction. Then, one of opposing two longitudinal ends of the liquid crystal molecules may be seen when viewed from one of top and bottom directions (e.g., the bottom direction), while sides of the liquid crystal molecules may be seen from the other of the top and bottom directions (e.g., the top direction). When a display screen is viewed from a position where the sides of the liquid crystal molecules are seen, the brightness of the screen may increase or the contrast may decrease. When the screen is viewed from a position where the one of the longitudinal ends of the liquid crystal molecules are seen, the brightness of the screen may decrease, and the gray inversion may occur in the screen.

Referring now to FIG. 5, liquid crystal molecules **301**, **302** and **302** of the splayed layers **122** and **132** may be aligned in a manner substantially opposite to a manner in which liquid crystal molecules **111**, **112** and **113** of the liquid crystal panel **110** are aligned in the presence of electric field to compensate for the asymmetry of liquid crystal alignment of the liquid crystal panel **110**. The liquid crystal molecules **301**, **302** and **302** of the splayed layers **122** and **132** may align corresponding to respective liquid crystal molecules **111**, **112** and **113** of the liquid crystal panel **110**, which are connected in dotted lines such that the optical characteristics of LCDs is substantially improved.

Referring again to FIG. 4, the liquid crystal molecules **400** in the biaxial layers **123**, **133**, **223** and **233** are substantially uniformly aligned. In such an embodiment, longitudinal axes of the liquid crystal molecules **400** in the biaxial layers **123**, **133**, **223** and **233** may be substantially parallel to outer surfaces of the liquid crystal panel **110** or **210** and substantially perpendicular to the liquid crystal molecules in the

liquid crystal panels **110** and **210**. In such an embodiment, the longitudinal axes of the liquid crystal molecules **400** in the biaxial layers **123**, **133**, **223** and **233** may be substantially perpendicular to the outer surfaces of the liquid crystal panel **110** or **210** in the presence of the electric field such that the side viewing characteristics of the LCDs is substantially improved.

Hereinafter, an exemplary experiment on viewing characteristics of an embodiment of the LCD will now be described in detail with reference to FIGS. 6 to 8.

FIG. 6 is a graph illustrating contrast versus viewing angle, showing viewing characteristics of a comparative example of the LCD, FIG. 7 is a graph illustrating contrast versus viewing angle, showing viewing characteristics of an embodiment of the LCD, and FIG. 8 is graph illustrating contrast ratio versus viewing angle, showing viewing characteristics of the comparative example of the LCD and the embodiment of the LCD shown in FIGS. 6 and 7.

The embodiment of the LCD includes the upper and lower splayed layers **122** and **132**, as shown in FIG. 1, and each of the upper and lower splayed layers **122** and **132** has a thickness of about 1.6 microns (μm), extraordinary refractive index N_e of about 1.6038, and ordinary refractive index N_o of about 1.543. The azimuthal angles of the liquid crystal directors are about 45 degrees in the lower splayed layer **132**, and about 135 degrees in the upper splayed layer **122**. Polar angles of the liquid crystal directors in each of the upper and lower splayed layers **122** and **132** are in a range from about 24 degrees to about 79 degrees. Each of the biaxial layers **123** and **133**, which has a structure similar to a structure of an A-plate, has a thickness of about 11.4 μm , in-plane retardation R_o of about 171 nm, thickness retardation R_{th} of about -125.4 nm, N_x of about 1.4985, N_y of about 1.4835, and N_z of about 1.48.

The comparative example of the LCD includes a compensation film including disc-shaped liquid crystal materials instead of rod-shaped splayed layers **122** and **132**.

In the comparative example of the LCD, as shown in FIGS. 6 and 8, the reference viewing angles, where the contrast is about 10, for top, bottom, left and right directions are about 57 degrees, about 69 degrees, about 72 degrees, and about 72 degrees. In an embodiment, as shown in FIGS. 7 and 8, the reference viewing angle, where the contrast is about 10, is equal to or greater than about 89 degrees for all of the directions, e.g., the top, bottom, left and right directions. In another embodiment, e.g., the embodiment shown FIG. 2, the reference viewing angle of the LCD may be equal to or greater than about 89 degrees for all of the directions, similarly to the embodiment used in the exemplary experiment.

Hereinafter, another exemplary experiment on viewing characteristics will now be described in detail with reference to FIGS. 9 to 12.

FIG. 9 is a schematic cross-sectional view of another embodiment of the LCD, FIG. 10 is a graph showing contrast ratio (“CR”) for various viewing angles as function of in-plane retardation R_o of a biaxial layer in the LCD shown in FIG. 9, FIG. 11 is a graph showing CR for various viewing angles as function of thickness retardation R_{th} of the biaxial layer in the LCD shown in FIG. 9, and FIG. 12 is a graph showing CR for various viewing angles as function of retardation $\Delta n d$ of a splayed layer in the LCD shown in FIG. 9.

Referring to FIG. 9, an embodiment of the LCD includes a liquid crystal panel **710**, a pair of optical compensation films **721** and **731**, a pair of polarizing films **724** and **734**, and a substrate **740**.

The liquid crystal panel **710** of the embodiment includes upper and lower electrodes **714** and **716**, a liquid crystal layer **712** disposed between the upper and lower electrodes **714** and **716**, and a plurality of color filters **718** disposed on

the upper electrode **714**. The color filters **718** may include a red color filter R, a green color filter G, and a blue color filter B.

In an embodiment, the characteristic parameters of liquid crystal material of the liquid crystal panel **710** are as follows: splay, twist, bend elastic coefficients: $K_{11}=11.4$ piconewtons (pN), $K_{22}=4.8$ pN, $K_{33}=11.5$ pN; permittivity: $\epsilon_{\parallel}=7.7$, $\epsilon_{\perp}=3.1$; pitch: -70 μm ; thickness: 3.2 μm ;

refractive index: $N_e=1.605096$, $N_o=1.480096$; refractive anisotropy Δn : 0.125 ; and retardation: 400 nm.

Each of the compensation films **721** and **731** of the embodiment includes splayed layers **722** and **732**, and biaxial layers **723** and **733**.

In the embodiment of the LCD, front contrast ratio and lateral 89-degree contrast ratio for the in-plane retardation Ro of the biaxial layer **723** or **733** are as shown in Table 1 and FIG. 10.

TABLE 1

Nx	Ny	Nz	d (μm)	Ro (nm)	Rth (nm)	front CR	lateral 89-degree CR			
							$\phi = 0$	$\phi = 90$	$\phi = 180$	$\phi = 270$
1.497	1.485	1.48	11.4	136.708	-125.316	687	12.9	5.6	12.9	15.1
1.4975	1.4845	1.48	11.4	148.119	-125.331	687	24.1	7.4	24	31.3
1.498	1.484	1.48	11.4	159.528	-125.343	687	51.5	8.9	51.4	84.2
1.4985	1.4835	1.48	11.4	170.933	-125.351	687	70.2	8.3	70.9	69.4
1.499	1.483	1.48	11.4	182.338	-125.357	687	32.5	5	33	18.4
1.4995	1.4825	1.48	11.4	193.741	-125.362	687	13.3	2.4	13.5	6.3
1.5	1.482	1.48	11.5	206.44	-126.158	687	6.5	1.1	6.6	2.6

In Table 1, ϕ denotes polar angle.

As shown in Table 1 and FIG. 10, the contrast ratio in various angles was substantially improved when the in-plane retardation Ro of the biaxial layer **723** or **733** was about 170 nm, or when the in-plane retardation Ro of the biaxial layer **723** or **733** is in a range of about (170 ± 20) nm. As described above, the retardation of the liquid crystal material in the liquid crystal panel **710** is about 400 nm. In an embodiment, the retardation of the liquid crystal material in the liquid crystal panel **710** may be in a range of about (400 ± 30) nm, and an effective range of the in-plane retardation Ro of the biaxial layer **723** or **733** may be extended to a range of about (170 ± 50) nm, i.e., a range from about 120 nm to about 220 nm considering the range of the retardation of the liquid crystal material.

In the embodiment of the LCD, the front contrast ratio and the lateral 89-degree contrast ratio for the thickness retardation Rth of the biaxial layer **723** or **733** are as shown in Table 2 and FIG. 11.

TABLE 2

Nx	Ny	Nz	d (μm)	Ro (nm)	Rth (nm)	front CR	lateral 89-degree CR			
							$\phi = 0$	$\phi = 90$	$\phi = 180$	$\phi = 270$
1.4985	1.4835	1.477	11.4	136.708	-159.6	687	15.7	25.6	15.8	8.9
1.4985	1.4835	1.478	11.4	148.119	-148.2	687	38	35.3	38.2	19.4
1.4985	1.4835	1.479	11.4	159.528	-136.8	687	93.5	18.2	94.2	37.4
1.4985	1.4835	1.48	11.4	170.933	-125.4	687	70.2	8.3	70.9	69.4
1.4985	1.4835	1.481	11.4	182.338	-114	687	29.1	4.5	29.4	34.7
1.4985	1.4835	1.482	11.4	193.741	-102.6	687	14.6	2.9	14.7	13.8
1.4985	1.4835	1.483	11.4	206.44	-91.2	687	8.7	2.1	8.8	6.9

As shown in Table 2 and FIG. 11, the contrast ratio in various angles is substantially improved when the thickness retardation Rth of the biaxial layer **723** or **733** is about -130 nm, or when the thickness retardation Rth is in a range of about (-130 ± 20) nm. Considering the retardation of the liquid crystal material that may be in a range as described above, an effective range of the thickness retardation Rth of the biaxial layer **723** or **733** may be extended to a range of about (-130 ± 50) nm, i.e., a range from about -80 nm to about -180 nm.

In the embodiment, the front contrast ratio and the lateral 89-degree contrast ratio for the retardation $\Delta n d$ of the splayed layer **722** or **732** were as shown in Table 3 and FIG. 12.

TABLE 3

								front	lateral 89-degree CR			
Ne	No	Δn	d (μm)	$\Delta n d$ (nm)	Ro (nm)	Rth (nm)	CR	$\phi = 0$	$\phi = 90$	$\phi = 180$	$\phi = 270$	
1.6038	1.543	0.0608	1.3	79	136.708	-79.04	687	51.1	6.3	51.9	8.1	
1.6038	1.543	0.0608	1.4	85.1	148.119	-85.12	687	65.3	6.9	66.3	14.9	
1.6038	1.543	0.0608	1.5	91.2	159.528	-91.2	687	73.8	7.5	74.8	32.2	
1.6038	1.543	0.0608	1.6	97.3	38.563	-97.28	687	70.2	8.3	70.9	69.4	
1.6038	1.543	0.0608	1.7	103.4	182.338	-103.36	687	57.8	9.1	58.2	65.9	
1.6038	1.543	0.0608	1.8	109.4	193.741	-109.44	687	44	10.1	44.2	32	
1.6038	1.543	0.0608	1.9	115.5	206.44	-115.52	687	32.7	11.3	32.9	16.6	

As shown in Table 3 and FIG. 12, the contrast ratio in various angles was substantially improved when the retardation $\Delta n d$ of the splayed layer 722 and 732 is about 100 nm, or when the retardation $\Delta n d$ of the splayed layer 722 and 732 is in a range of about (100 $\pm$ 20) nm. Considering the retardation of the liquid crystal material that may be in a range as described above, an effective range of the retardation $\Delta n d$ of the splayed layer 722 and 732 may be extended to a range of about (100 $\pm$ 50) nm, i.e., a range from about 50 nm to about 150 nm.

Referring now to FIG. 13 and again to FIGS. 1 to 3, an embodiment of a compensation film for an LCD will be described in detail.

FIG. 13 is a graph showing azimuthal angle and polar angle of an embodiment of a liquid crystal molecule of the LCD shown in FIGS. 1 and 2 when a voltage is generated.

When an electric field is applied to the liquid crystal layer of the liquid crystal panel 110 or 210 shown in FIGS. 1 and 2, the liquid crystal molecules near the center of the liquid crystal layer may be aligned substantially in a vertical direction, e.g., a direction vertical to a surface of the substrates of the liquid crystal layer, while the liquid crystal molecules near the surfaces of the substrates of the liquid crystal panel 110 or 210 may not tend to be changed from initial orientations where they are aligned substantially parallel to the surfaces of the substrates. In such an embodiment, as shown in FIG. 13, the polar angle of the liquid crystal molecules near the surface of the substrates may be about 90 degrees and the polar angle of the liquid crystal molecules near the center of the liquid crystal layer may be about zero (0) degree, and may substantially continuously and gradually changed from the substrate surface to the layer center. Here, the definition of the polar angle is substantially the same as the definition of the polar angle shown in FIG. 4.

The azimuthal angles of the liquid crystal molecules near the surfaces of the two substrates are twisted by about a right angle. In FIG. 13, when an edge of a rectangular shaped surface of the liquid crystal panel 110 or 210 is defined as a reference line, i.e., zero (0) degree, the azimuthal angles of the liquid crystal molecules near the surfaces of the two substrates are about 45 degrees and about 135 degrees. The liquid crystal molecules near the substrate surfaces may maintain a homogeneous alignment thereof and do not change azimuthal orientation thereof even when a strong vertical electric field is applied thereto. In such an embodiment, a twisted alignment of the liquid crystal molecules may change the polarization of incident light.

In one embodiment, for example, in a normally white mode, where the transmission axes of the upper polarizing film 124 or 224 are in a right angle, i.e., an angle of about 90 degrees, with respect to the transmission axes of the lower polarizing film 134 and 234, a substantially strong vertical electric field applied to the liquid crystal layer may

cause a black state of the LCD. The change of the polarization of the incident light may cause light leakage, and thus the brightness in the black state may increase such that the contrast ratio is substantially decreased.

In an embodiment, the twisted orientations of the liquid crystal molecules in the splayed layers 122 and 132 or 222 and 232 may compensate for the light leakage due to the twisted orientations of the liquid crystal molecules in the liquid crystal panel 110 or 210. In an LCD, a substantial portion of the liquid crystal molecules, which are arranged in the thickness direction, in the splayed layers 122, 132, 222 and 232 may have substantially the same azimuthal angle, while having gradually changing polar angles. In an embodiment, however, the azimuthal angles of the liquid crystal molecules in the splayed layers 122 and 132 or 222 and 232 may slightly vary in addition to the variation of the polar angles thereof. The twist angle, which is the difference between the azimuthal angles of the liquid crystal molecules at opposing surfaces of the splayed layers 122, 132, 222 and 232, may be in a range from about 2 degrees to about 10 degrees.

According to another embodiment, the splayed layers 122, 132, 222 and 232 may include splay-twist aligned discotic liquid crystal molecules instead of rod-shaped liquid crystal molecules. In such an embodiment, the primary axes of the discotic liquid crystal molecules may be aligned with the longitudinal direction of the rod-shaped liquid crystal molecules shown in FIG. 4, and the twist angle may be in a range from about 2 degrees to about 10 degrees.

Hereinafter, an exemplary experiment on viewing characteristics of an embodiment of the LCD will now be described in detail with reference to FIGS. 14 to 16.

FIG. 14 is a graph illustrating contrast versus viewing angle, showing viewing characteristics of a comparative example of the LCD, FIG. 15 is a graph illustrating contrast versus viewing angle, showing viewing characteristics of an embodiment of the LCD, and FIG. 16 is graph illustrating contrast versus viewing angle, showing viewing characteristics of the comparative example of the LCD and the embodiment of the LCD shown in FIGS. 14 and 15.

The embodiment of the LCD has a structure substantially the same as the structure of the embodiment shown in FIG. 1. In such an embodiment, each of the splayed layers 122 and 132 has a thickness of about 1.6 μm , extraordinary refractive index Ne of about 1.6038, and ordinary refractive index No of about 1.543. The azimuthal angle and the polar angle of the liquid crystal director in the lower splayed layer 132 are varied from about 45 degrees and about 24 degrees to about 42 degrees and about 79 degrees, respectively. In such an embodiment, the azimuthal angle and the polar angle of the liquid crystal director in the upper splayed layer 122 are varied from about 135 degrees and about 24 degrees to about 138 degrees and about 79 degrees, respectively. Each of the biaxial layers 123 and 133, which had a structure

substantially similar to an A-plate, has a thickness of about 11.4 μm , in-plane retardation R_o of about 171 nm, thickness retardation R_{th} of about -125.4, N_x of about 1.4985, N_y of about 1.4835, and N_z of about 1.48.

The comparative example of the LCD includes a compensation film including discotic liquid crystal material without twist instead of rod-shaped splayed layers 122 and 132 with twist.

In the comparative example of the LCD, as shown in FIGS. 14 and 16, the reference viewing angles, where the contrast is about 10, for the top, bottom, left, and right directions are about 57 degrees, about 69 degrees, about 72 degrees, and about 72 degrees. In the embodiment, as shown in FIGS. 15 and 16, the reference viewing angle, where the contrast is about 10, are equal to or greater than about 89 degrees for all of the top, bottom, left, and right directions.

Hereinafter, an exemplary experiment on a front contrast ratio will now be described in detail with reference to FIGS. 17 to 19.

FIG. 17 is a graph showing a front contrast ratio as function of twist angle of a rod-shaped splayed layer with twist, and each of FIGS. 18 and 19 is a graph showing a front contrast ratio as function of twist angle of a discotic splayed layer with twist.

FIG. 17 shows the front contrast ratio with respect to various twist angles of the splayed layer 122 of the upper compensation film 121 and without twist in the splayed layer 132 of the lower compensation film 131 in FIG. 1. As shown in FIG. 17, the addition of the twist may increase the front contrast ratio by about 15% to about 20%, and the front contrast ratio may have a peak when the twist angle is about -6.

When twist exists in both the upper and lower splayed layers 122 and 132, the front contrast ratio substantially increases when the sum of the twist angles is about 6 degrees.

FIGS. 18 and 19 shows the front contrast ratio with respect to various twist angles of the splayed layers 122 and 132 including the discotic liquid crystal molecules. In such an embodiment, the biaxial layers 123 and 133 may be omitted.

FIG. 18 was obtained by fixing the azimuthal angle of the lower splayed layer 132 and giving twist to the upper splayed film 122, and FIG. 19 was obtained by fixing the azimuthal angle of the upper splayed film 122 and giving twist to the lower splayed layer 132. In FIG. 18, the azimuthal angle of the liquid crystal molecules disposed near the top surface of the upper splayed film 122 was fixed to about -135 degrees, and the azimuthal angle of the liquid crystal molecules disposed near the bottom surface was varied. In FIG. 19, the azimuthal angle of the liquid crystal molecules disposed near the bottom surface of the lower splayed layer 132 was fixed to about -45 degrees, and the azimuthal angle of the liquid crystal molecules disposed near the top surface was varied.

As shown in FIGS. 18 and 19, the splay-twist alignment of the discotic liquid crystal molecules may increase the contrast ratio for all directions, and in particular, the front contrast ratio may increase by about 20%.

While this disclosure has been described in connection with what is presently considered to be practical exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims.

What is claimed is:

1. A twisted nematic liquid crystal display comprising:
 - a twisted nematic mode liquid crystal panel having a first surface and a second surface;
 - a first compensation film disposed on the first surface of the twisted nematic mode liquid crystal panel;
 - a first polarizing film disposed on an outer surface of the first compensation film;
 - a second compensation film disposed on the second surface of the panel; and
 - a second polarizing film disposed on an outer surface of the second compensation film,
 wherein the compensation film comprising:
 - a first layer comprising splayed rod-shaped nematic liquid crystal material; and
 - a second layer disposed on an outer surface of the first layer and comprising a biaxial layer,
 wherein an optical axis of the second layer is at an angle of about 90 degrees with respect to a splay plane of the first layer, and
 wherein the splay plane of the first layer is substantially parallel to a vector sum of rubbing directions of the twisted nematic mode liquid crystal panel,
 wherein the second compensation film comprises:
 - a third layer comprising splayed rod-shaped nematic liquid crystal material; and
 - a fourth layer disposed on an outer surface of the third layer and comprising a second biaxial layer,
 wherein an optical axis of the fourth layer is at an angle of about 90 degrees with respect to a splay plane of the third layer,
 wherein the splay plane of the third layer is substantially parallel to the splay plane of the first layer.
2. The liquid crystal display of claim 1, wherein liquid crystal molecules of the first layer have polar angles decreasing as moving toward the second layer.
3. The liquid crystal display of claim 2, wherein a difference between the polar angles of the liquid crystal molecules at opposing surfaces of the first layer is equal to or greater than about 30 degrees.
4. The liquid crystal display of claim 3, wherein
 - retardation of the second layer in plane direction is in a range from about 120 nanometers to about 220 nanometers,
 - retardation of the second layer in thickness direction is in a range from about -80 nanometers to about -180 nanometers, and
 - retardation of the first layer is about 50 nanometers to about 150 nanometers.
5. The liquid crystal display of claim 1, wherein the splayed rod-shaped nematic liquid crystal material of the first layer has a twist alignment with a twist angle in a range from about 2 degrees to about 10 degrees.
6. The liquid crystal display of claim 5, wherein the first polarizing film comprises:
 - a polarizer disposed on an outer surface of the second layer; and
 - a first protective layer disposed on an outer surface of the polarizer.
7. The liquid crystal display of claim 6, wherein the first polarizing film further comprises a second protective layer disposed between the polarizer and the second layer.
8. The liquid crystal display of claim 1, wherein the first polarizing film comprises:
 - a polarizer disposed on an outer surface of the second layer; and

15

a first protective layer disposed on an outer surface of the polarizer.

9. The liquid crystal display of claim 8, wherein the first polarizing film further comprises a second protective layer disposed between the polarizer and the second layer.

10. The liquid crystal display of claim 1, wherein the splay plane of the first layer makes at an angle of about 45 degrees with the rubbing direction.

11. A twisted nematic liquid crystal display comprising:
a twisted nematic mode liquid crystal panel having a first surface and a second surface opposing the first surface;
a first compensation film disposed on the first surface of the panel;

a first polarizing film disposed on an outer surface of the first compensation film;

a second compensation film disposed on the second surface of the panel; and

a second polarizing film disposed on an outer surface of the second compensation film,

wherein the first compensation film comprises:

a first layer comprising discotic nematic liquid crystal material with a first splay-twist alignment; and

16

a second layer disposed on an outer surface of the first layer and comprising a first biaxial layer,

wherein an optical axis of the second layer is at an angle of about 90 degrees with respect to a splay plane of the first layer,

wherein the splay plane of the first layer is substantially parallel to a vector sum of rubbing directions of the twisted nematic mode liquid crystal panel,

wherein the second compensation film comprises:

a third layer comprising discotic nematic liquid crystal material with a second splay-twist alignment; and

a fourth layer disposed on an outer surface of the third layer and comprising a second biaxial layer,

wherein an optical axis of the fourth layer is at an angle of about 90 degrees with respect to a splay plane of the third layer,

wherein the splay plane of the third layer is substantially parallel to the splay plane of the first layer, and

wherein the twist angle of the discotic nematic liquid crystal material in the first layer is in a range from about 2 degrees to about 10 degrees.

* * * * *

专利名称(译)	光学补偿膜和包括其的液晶显示器		
公开(公告)号	US9851603	公开(公告)日	2017-12-26
申请号	US13/447805	申请日	2012-04-16
[标]申请(专利权)人(译)	三星电子株式会社		
申请(专利权)人(译)	韩国成均馆大学基金会为企业协作 SAMSUNG ELECTRONICS CO. , LTD.		
当前申请(专利权)人(译)	SAMSUNG ELECTRONICS CO. , LTD. 韩国成均馆大学基金会为企业协作		
[标]发明人	KIM HEE KYUNG SONG JANG KUN		
发明人	KIM, HEE KYUNG SONG, JANG-KUN		
IPC分类号	G02F1/1335 G02F1/13363		
CPC分类号	G02F1/13363 G02F2001/133633 G02F2413/12 G02F2413/06 G02F2413/04		
代理机构(译)	康托科尔伯恩LLP		
助理审查员(译)	CHUNG , DAVID		
优先权	1020110061908 2011-06-24 KR		
其他公开文献	US20120327342A1		
外部链接	Espacenet USPTO		

摘要(译)

一种用于液晶膜的补偿膜，包括第一层和第二层，第一层包括张开的棒状向列液晶材料，第二层设置在第一层的表面上并包括双轴层和A板中的至少一个。

