



(11) **EP 1 933 402 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
01.09.2010 Bulletin 2010/35

(51) Int Cl.:
H01L 51/52 (2006.01)

(21) Application number: **07254793.8**

(22) Date of filing: **12.12.2007**

(54) **Organic light emitting display apparatus**

Organische lichtemittierende Vorrichtung

Appareil d'affichage électroluminescent organique

(84) Designated Contracting States:
DE FR GB

(30) Priority: **13.12.2006 KR 20060127305**

(43) Date of publication of application:
18.06.2008 Bulletin 2008/25

(73) Proprietor: **Samsung Mobile Display Co., Ltd.**
Suwon-si
Gyeonggi-do (KR)

(72) Inventors:
• **Choe, Won-Kyu**
c/o Y.P. Lee, Mock & Partners
Seocho-Gu
Seoul 137-875 (KR)

• **Baek, Ji-Yeon**
c/o Y.P. Lee, Mock & Partners
Seocho-Gu
Seoul 137-875 (KR)

(74) Representative: **Mounteney, Simon James**
Marks & Clerk LLP
90 Long Acre
London
WC2E 9RA (GB)

(56) References cited:
US-A1- 2004 012 747 US-A1- 2004 032 202
US-A1- 2005 179 377

EP 1 933 402 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

BACKGROUND

Technical Field

[0001] This disclosure relates generally to an organic light emitting display apparatus, and more particularly, to an organic light emitting display apparatus that resists deterioration of organic emission layers from contact with impurities such as oxygen and moisture.

Description of the Related Art

[0002] Organic light emitting display apparatuses have emission layers formed of organic substances disposed between a pixel electrode and an opposite electrode. In some organic light emitting display apparatuses, when positive and negative voltages are applied to the electrodes, holes injected from the pixel electrode move into a emission layer through a hole transport layer, and electrons injected from the opposite electrode move to the emission layer through an electron transport layer. The electrons and holes combine, forming excitons in the emission layer. As the excitons go from an excited state to a ground state, they transfer energy to phosphor molecules in the emission layer, causing the phosphor molecules to emit light, thereby forming images.

[0003] Organic light emitting apparatuses are regarded as next-generation display devices because of their fast response times, wide viewing angles, and excellent contrasts. However, organic layers, including organic emission layers, can be moisture and oxygen sensitive, and thus, the life span of devices is seriously degraded when moisture and/or oxygen infiltrates into the display regions of the light emitting units.

[0004] In typical organic light emitting display apparatuses, the peripheries of a display region are encapsulated with a metal cap or an encapsulating substrate, and sealed thereto with a sealant. Furthermore, some arrangements comprise a moisture absorbent within the sealed space. However, these methods do not sufficiently block external oxygen or moisture in many cases.

[0005] US 2004/0012747 discloses a light-emitting device and display device comprising a pair of flexible organic resin substrates, a light emitting element between the substrates, a sealing member between the end portions of the substrate and a coating film formed in end portions of the substrates and on outer surfaces of the sealing member.

SUMMARY OF THE INTENTION

[0006] Provided herein is an organic light emitting display apparatus that resists infiltration of external moisture and oxygen.

[0007] Some embodiments provide an organic light emitting display apparatus comprising: a substrate com-

prising a plurality of thin film transistor (TFT) devices; and a display region formed on the substrate, wherein the display region comprises: a base layer comprising first electrodes, which are electrically connected to the TFT devices, and defining a pixel region; an organic layer formed on the base layer; and a second electrode layer formed as a structure covering the base layer and organic layers. In some embodiments, the second electrode entirely covers the base layer.

[0008] According to an aspect of the invention, there is provided an organic light emitting display apparatus as set out in Claim 1. Preferred features of this aspect are set out in Claims 2 to 13.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] The above and other features and advantages of the present invention will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings, in which:

[0010] FIG. 1 is a schematic plan view of an organic light emitting display apparatus according to one embodiment;

[0011] FIG. 2 is a cross-sectional view of the apparatus of FIG. 1 taken along section line II-II;

[0012] FIG. 3 is an enlarged view of detail III in FIG. 2;

[0013] FIG. 4 is a plan view of an organic light emitting display apparatus according to another embodiment;

[0014] FIG. 5 is a cross-sectional view of the apparatus of FIG. 4 taken along section line V-V;

[0015] FIG. 6 is a plan view of an organic light emitting display apparatus according to a comparative example;

[0016] FIG. 7 is a cross-sectional view of the apparatus of FIG. 6 taken along section line VII-VII;

[0017] FIG. 8 is a schematic plan view of an organic light emitting display apparatus according to still another embodiment;

[0018] FIG. 9 is a schematic plan view of an organic light emitting display apparatus according to still another embodiment;

[0019] FIG. 10 is a schematic plan view of an organic light emitting display apparatus according to still another embodiment;

[0020] FIG. 11 is a cross-sectional view taken along section line XI-XI of FIG. 10; and

[0021] FIGS. 12 and 13 are schematic plan views of organic light emitting apparatuses according to other embodiments.

DETAILED DESCRIPTION OF CERTAIN EMBODIMENTS

[0022] Certain embodiments will now be described more fully with reference to the accompanying drawings, in which exemplary embodiments are shown.

[0023] FIGS. 1 through 13 illustrate an organic light emitting display apparatus according to one embodiment of the invention. FIG. 1 is a schematic plan view of the

organic light emitting display apparatus of the current embodiment. FIG. 2 is a cross-sectional view of the apparatus of FIG. 1 taken along section line II-II, and FIG. 3 is an enlarged cross-sectional view of detail III in FIG. 2. Referring to FIGS. 1 through 3, the organic light emitting display apparatus includes a display region 200 including a base layer 210, an organic layer 220, and a second electrode layer 230 on a substrate 100, which includes a plurality of thin film transistor (TFT) devices 110 (FIG. 2), wherein the second electrode layer 230 entirely covers the base layer 210 and the organic layer 220.

[0024] The substrate 100 according to the current embodiment can be formed of various materials including glass, plastic, such as an acrylic, metal, and the like. As best seen in FIG. 2, a buffer layer 111, which is formed of SiO_2 , or the like, is formed on the substrate 100. The buffer layer 111 prevents moisture or impurities from the substrate 100 from diffusing therethrough, and/or helps crystallization of a semiconductor layer 121 by controlling a heat transmission speed during crystallization.

[0025] The semiconductor layer 121 can be formed of an amorphous silicon thin film or a polycrystalline silicon thin film on the buffer layer 111. The semiconductor layer 121 can also be formed of an organic semiconductor material. Although not shown in FIGS. 1 through 3, the semiconductor layer 121 can include source regions and drain regions, which are doped with N-type or P-type dopants, and channel regions as necessary.

[0026] A gate electrode 122 is disposed above the semiconductor layer 121. A source electrode and a drain electrode electrically communicate with each other according to signals applied to the gate electrode 122. The gate electrode 122 is formed of a material such as MoW, Al/Cu, and the like, in consideration of the closeness to adjacent layers, surface flatness of layers to be deposited, and processability.

[0027] A gate insulation film 112, which is formed of SiO_2 or the like, for example by plasma enhanced chemical vapor deposition (PECVD), is formed between the semiconductor layer 121 and the gate electrode 122 as an insulator between them. Using SiO_2 , SiN_x , or the like, a single or a plurality of inter-insulator layers 113 are formed above the gate electrode 122 such that each of source and drain electrodes 123 contacts the source and drain regions of semiconductor layer 121 through contact holes 124 formed therethrough.

[0028] A planarization film 114 is disposed on the source and drain electrodes 123 to protect and planarize the thin film transistors 110. Additionally, a passivation layer in various forms, not shown in FIGS. 1 through 3, can be disposed between the planarization film 114 and the inter-insulator 113.

[0029] Although only the thin film transistor devices 110, which are connected to pixel electrodes 211, are illustrated in FIG. 2, the organic light emitting display apparatus of the current embodiment can further include a switching device. Moreover, various devices such as a capacitor can be included as desired, and the number of

devices is not limited. In addition, the thin film transistors 110 illustrated in FIG. 2 are top-gate-type devices. However, the thin film transistor devices are not limited thereto, and bottom-gate-type devices in which gate electrodes 122 are formed below semiconductor layers 121 can also be included in some embodiments.

[0030] A base layer 210, which includes first electrodes 211 and defines pixel regions, is formed on the planarization film 114. Here, "a pixel region" refers not only to a pixel itself, which includes an emission layer, but also to structures which separate each pixel and define each pixel's emission region such as a pixel defining layer 212. In the current embodiment, the pixel defining layer 212 is formed between first electrodes 211 with a predetermined thickness.

[0031] The first electrodes 211 are electrically coupled to the source or drain electrodes 123 below through holes 125. The first electrodes 211 can be of a transparent or reflective type. Transparent type electrodes can be formed of indium tin oxide (ITO), indium zinc oxide (IZO), ZnO, In_2O_3 , or the like. In the current embodiment, reflective anodes are used. The reflective anodes can be formed using ITO, IZO, ZnO, In_2O_3 , or the like on a reflective film after forming the reflective film using Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr, and alloys and/or mixtures thereof.

[0032] The pixel defining layers (PDLs) 212 are formed between first electrodes 211 with a predetermined thickness. In addition to defining emission regions, the PDLs 212 prevent short circuits between the first electrodes 211 and the second electrodes 230 by reducing the concentration of electric field at edge portions of the first electrodes 211 by increasing the distance between the edges of first electrodes 211 and the second electrodes 230. The base layer 210 according to the current embodiment includes the PDLs 212; however, in other embodiments, any structure separating each pixel and defining an emission region of each pixel can form the base layer 210.

[0033] As best seen in FIG. 3, the organic layer 220, including at least an organic emission layer 223, are formed on the base layer 210. Because the organic layer 220 comprises a plurality of layers, the organic layer 220 is also referred to as "organic layers 220." The organic emission layer 223 can comprise small-molecule or polymeric organic substances. When the organic emission layer 223 comprises polymeric organic substances, the organic emission layer 223 includes a hole transport layer and an emission layer. In some embodiments, polyethylenedioxythiophene (PEDOT) is used for the hole transport layer and polymeric organic substances, such as polyphenylenevinylenes (PPVs) and polyfluorenes, are used for the emission layer.

[0034] In embodiments comprising small-molecule organic substances, the organic emission layer 223 can be formed by depositing a hole injection layer (HIL) 221, a hole transport layer (HTL) 222, an emission layer (EML) 223, an electron transport layer (ETL) 224, an electron injection layer (EIL) 225, and the like, as single layers or

in a more complex structure as illustrated in FIG. 3. Examples of organic substances that can be used for depositing the organic emission layer include copper phthalocyanine (CuPc), *N,N*-di(naphthalene-1-yl)-*N,N*-diphenyl-benzidine (NPB), tris-8-hydroxyquinoline aluminum (Alq₃), and the like.

[0035] In some embodiments, some of the organic layers 220 do not entirely cover a pixel region, that is, only certain portions of some of the organic layers 220 are selectively formed as desired. Although not illustrated in FIG. 3, a hole blocking layer (HBL) can further be disposed between the emission layer 223 and the electron transport layer 224. Likewise, some embodiments of the organic layers 220 include various other organic layers. Also, when the first electrodes 211 function as cathodes and the second electrodes 230 function as anodes, the order of the organic layers 220 is changed as would be understood by those skilled in the art.

[0036] The small-molecule organic layers 220 are formed on the base layer 210 by vacuum deposition using a mask. In the current embodiment, the organic emission layer 223 is formed by patterning each first electrode for each pixel using a fine mask, and the other organic layers 221, 222, 224, and 225 are sequentially deposited on the base layer 210 through an open mask without being patterned for each pixel.

[0037] Referring to FIGS. 1 and 2, the organic layers 220 including the emission layer are deposited on area *B*, which has either the same area or a slightly larger area than area *A* of the base layer 210. The open mask for depositing the organic layers 221, 222, 224 and 225 is usually designed so that area *B* over which the organic layers 220 are deposited covers area *A* over which the base layer 210 is deposited.

[0038] FIGS. 1 and 2 illustrate an embodiment in which the organic layers 221, 222, 224, and 225 are ideally aligned over the base layer 210; that is, in which area *B*, where the organic layers 220 are deposited, entirely covers area *A*, where the base layer 210 is deposited. Moreover, when a second electrode layer 230 is deposited over area *C* completely covering area *B*, edges of the organic layers 220 are not exposed because the second electrode layer 230 also entirely covers the organic layers 220. Therefore, external moisture and/or oxygen cannot penetrate between interstices at the edges of the organic layers 221, 222, 224, and 225 of the organic layers 220.

[0039] However, when depositing the organic layers 220, there are instances in which the organic layers 220 are not ideally aligned over the base layer 210 as described above. FIGS. 4 and 5 illustrate an embodiment in which the organic layers 220 are not ideally aligned over the base layer, yet are not exposed to exterior on any side of the second electrodes 230.

[0040] The open mask used in depositing the organic layers 221, 222, 224, and 225 is designed to cover at least area *A* where the base layer 210 is formed. However, due to manufacturing tolerances in the process of manufacturing the mask or alignment errors in aligning

the mask on the substrate 100, the organic layers 220 are not deposited ideally on the base layer 210.

[0041] FIGS. 4 and 5 illustrate an embodiment in which the manufacturing tolerances of the right and left sides of the mask used for deposition of the organic layers 221, 222, 224, and 225 are off, or when the organic layers 220 are deposited with the mask misaligned to the right side because an alignment error. Referring to FIGS. 4 and 5, the organic layers 220 are formed to the right side on the base layer 210; however the organic layers 220 are not exposed to the external environment on the left side because the second electrode layer 230 is formed over area *C*, which entirely covers area *A*, where the base layer 210 is formed, in addition to area *B*, where the organic layers 220 are formed.

[0042] In the arrangement illustrated in FIGS. 6 and 7, organic layers 220 are formed to the right side on the base layer 210 as in FIGS. 4 and 5. That is, area *B*, where the organic layers 220 are formed, is at the right side, extending slightly beyond area *A*, where the base layer 210 is formed. If the manufacturing tolerances of the mask used in depositing the organic layers 220, or alignment errors when aligning the mask on the base layer 210 are not taken into consideration when depositing a second electrode layer 230, the second electrode layer 230 usually covers the area where the base layer 210 is formed. In this case, the right edges of organic layers 220 are not entirely covered by the second electrode layer 230, as in the embodiment illustrated in FIGS. 4 and 5. Thus, moisture and oxygen can reach the organic emission layer 223 through interstices between the exposed edges of organic layers 220, causing deterioration of the organic emission layer 223.

[0043] However, in the organic light emitting display apparatus according to the embodiments illustrated in FIGS. 1-5, the second electrode layer 230 covers both the base layer 210 and the organic layers 220. Thus, deterioration of the organic emission layer 223 due to exposure of the organic layers 220 to the external environment can largely be prevented and thus the life span of the organic light emitting display apparatus can be extended.

[0044] The second electrode layer 230 can comprise transparent or reflective electrodes. When the second electrode layer 230 comprises transparent electrodes, metals with low work functions such as Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, and alloys and mixtures thereof are thinly deposited over the organic emission layer, and an auxiliary electrode layer or bus electrode lines can be formed on the second electrode layer 230 using materials suitable for transparent electrodes such as ITO, IZO, ZnO, In₂O₃, or the like. Using reflective electrodes, the second electrode layer 230 is formed by depositing, for example, Li, Ca, LiF/Ca, LiF/Al, Al, Ag, Mg, or alloys and/or mixtures thereof, on the entire surface. Second electrode layer 230 according to the current embodiment, which are formed of light-permeable electrodes, function as cathodes of organic emission layer 223 and as com-

mon electrodes.

[0045] Embodiments in which the organic layers 220, except for the emission layer 223, are formed using an open mask are described above. However, those skilled in the art will understand that depositing some or all of the organic other layers 220 for each pixel using a fine mask is also possible. The organic emission layer 223 is usually formed on a central portion of each pixel, in other words, on the first electrode 211 between pixel defining layers 212, and the materials forming the organic emission layer 223 can be disposed slightly out of the position of each pixel of the base layer 210 due to manufacturing tolerances of the fine mask or alignment errors of the mask. Even in this case, deterioration due to exposure of the organic emission layer 223 can be prevented if the second electrode layer 230 covers both the base layer 210 and the organic layers 220 including the organic emission layer 223.

[0046] FIG. 8 is a schematic plan view of an organic light emitting display apparatus according to another embodiment. Referring to FIG. 8, a base layer 210 formed in area A includes a dummy pixel region 214 in addition to first electrodes and a pixel region. Organic layers 220 are formed in area B on the base layer 210 including the dummy pixel region 214, and a second electrode layer 230 is formed in area C on the organic layers 220.

[0047] When manufacturing organic light emitting display apparatuses, it is desirable to check whether pixels are correctly formed or to test features of TFTs of each pixel. Some embodiments use one or more parts of a dummy pixel for such testing. The parts of the dummy pixel can include portions of a display device for light emission, or devices such as a TFT, which control the display device.

[0048] According to the current embodiment, the organic layers 220 are formed on the base layer 210 including the dummy pixel region 214 of a display device, and the second electrode layer 230 entirely covers the base layer 210 and the organic layers 220. Therefore, the organic layers 220 formed on the dummy pixel region 214, which is used to test the display device, are formed at the periphery of a display region and thus have high risk of being exposed to the exterior. However, the organic layers 220 are completely covered by the second electrode layer 230 according to the current embodiment, and thus permeation of external moisture and oxygen thereto can be prevented.

[0049] In FIG. 8, the dummy pixel region 214 is formed at one side of the display region. However, those skilled in the art will understand that in other embodiments, the dummy pixel region can also be formed at one or more other sides along the periphery of the display region.

[0050] FIG. 9 is a schematic plan view of an organic light emitting display apparatus according to still another embodiment. Referring to FIG. 9, a display region includes a base layer 210, organic layers 220, and a second electrode layer 230, all formed on a substrate 100. An electrode wiring portion 300 is electrically coupled to

the second electrode layer 230 and is formed on one side of the display region.

[0051] The electrode wiring portion 300 supplies the second electrode layer 230, which operates as a common electrode, with electric power. The second electrode layer 230 according to the current embodiment covers the electrode wiring portion 300. An insulation layer is disposed between the second electrode layer 230 and the electrode wiring portion 300, and the second electrode layer 230 and the electrode wiring portion 300 are interconnected through a plurality of contact holes.

[0052] In the organic light emitting display apparatuses including an electrode wiring portion 300, organic layers 220 formed on a base layer 210 are not formed on the electrode wiring portion 300; however a second electrode layer 230 is formed on the electrode wiring portion 300. Therefore, in embodiments in which the organic layers 220 are deposited on the right-left and/or top/bottom areas of the display area, instances are atypical in which the second electrode layer 230 does not cover the portion (s) of the organic layers 220 adjacent to the electrode wiring portion 300. However, when organic layers 220 are deposited on the side(s) of the display area at which the electrode wiring portion 300 is not formed, the organic layers 220 may not completely cover the base layer 210. Nevertheless, the second electrode layer 230 according to the current embodiment covers the base layer 210 and the organic layers 220 even in these cases, and thus prevents exposure of the organic layers 220 to the external environment.

[0053] Further, the organic light emitting display apparatus according to the current embodiment can include an encapsulating structure that seals the display region. In the organic light emitting display apparatus according to the current embodiment, the second electrode layer completely encloses the organic layers and thus largely prevents external oxygen and moisture from permeating through the organic layers. However, external oxygen and moisture can be blocked more effectively by further including a structure that encapsulates the display region. Examples of encapsulating structures include any suitable encapsulating structure, for example, a metal cap with a sealant, an encapsulating substrate with a sealant, or a thin encapsulating structure formed by alternately depositing insulating organic and inorganic layers. Thus, various encapsulating structures sealing the display region using various substances and methods can further be included.

[0054] FIGS. 10 through 13 illustrate an organic light emitting display apparatus according to still another embodiment. FIG. 10 is a schematic plan view of the organic light emitting display apparatus, and FIG. 11 is a schematic cross-sectional view taken along section line XI-XI of FIG. 10. FIGS. 12 through 13 are schematic cross-sectional views of organic light emitting display apparatuses according to other embodiments.

[0055] Referring to FIGS. 10 through 13, the organic light emitting display apparatus according to the current

embodiments includes a display region 500 including a base layer 510, organic layers 520 and a second electrode layer 530 on a substrate 400 including a plurality of TFT devices, wherein the second electrode layer 530 covers the organic layers 520, extending past the periphery thereof by a width D of greater than about 100 μm . Hereinafter, some differences between the organic light emitting display apparatus according to the current embodiment and the organic light emitting display apparatus according to the previous embodiments are described.

[0056] First, the second electrode layer 530 of the current embodiment entirely covers the organic layers 520, but may or may not cover all of the base layer 510. FIGS. 10 and 11 illustrate an instance in which the second electrode layer 530 covers both the base layer 510 and organic layers 520, extending beyond the periphery of the organic layers by a width D . On the other hand, FIG. 12 illustrates an instance in which the second electrode layer 530 covers the organic layers 520, extend past the periphery by a width D , but does not cover the left side edge of the base layer 510. In the organic light emitting display apparatus according to some of the previous embodiments, the organic layers 220 are designed to cover at least the base layer 210 and thus the second electrode layer 230 covering the organic layers 220 also covers the base layer 210. On the contrary, the current embodiment includes instances in which the organic layers 520 does not entirely cover the base layer 510, and includes an instance in which a pixel defining layer formed on the outer periphery of display region is not covered with the organic layers 520.

[0057] In addition, in the current embodiments, an error of about 100 μm can occur in depositing the organic layers 520 using a mask, manufacturing tolerances for the mask are about 50 μm , and alignment errors in aligning the mask on the substrate are about 50 μm . That is, a maximum error of about 100 μm in position in the process of depositing the organic layers 520 on the substrate 400 is taken into account. Thus, since in some embodiments the dimension of the second electrode layer 530 is larger than the organic layers 520 by greater than about 100 μm along the periphery thereof, the second electrode layer 530 completely covers the organic layers 520. That is, the second electrode layer 530 covers the sides of the organic layers 520, extending past the periphery thereof by greater than about 100 μm even when the organic layers 520 are deposited out of the position. In other words, in some embodiments, the second electrode layer 530 is arranged to extend by a width of greater than about 100 μm beyond an outer edge of the organic layer 520, the outer edge being located in a peripheral region of the organic layer 520. In other embodiments, the second electrode layer 530 is arranged to extend by a width of greater than about 100 μm beyond all the outer edges of the organic layer 520.

[0058] FIGS. 10 through 12 illustrate an instance in which the region on which the organic layers 520 are deposited is smaller than the region on which the base

layer 510 is deposited. However, those skilled in the art will understand that in some embodiments, the region of organic layers 520 is larger than or the same as the region of base layer 510. Referring to FIG. 13, even when the organic layers 520 are formed over the right edge of the base layer 510 due to manufacturing tolerances or alignment errors, external oxygen or moisture can still be prevented from reaching the organic layers 520 by forming the second electrode layer 530 to cover the organic layers 520 with a margin of width D around the periphery thereof.

[0059] Although not described in the above embodiments and drawings, the organic light emitting display apparatuses according to some embodiments can further include, for example, a device unit for sending signals, a power supply unit for supplying electric power, and the like, formed on the substrate, in addition to a display region. Also, it will be understood by those of ordinary skill in the art that various functional means in various forms may be further included therein.

[0060] Advantages provided by the organic light emitting display apparatuses according to the embodiments of the present invention include one or more of the following. First, deterioration of an emission layer due to exterior moisture and oxygen can be reduced or prevented by covering the organic layers with a second electrode layer regardless of the manufacturing tolerances of a mask for depositing the organic layers. Second, deterioration of an emission layer due to external moisture and/or oxygen infiltration can be prevented by covering the organic layers with the second electrode layer regardless of the alignment errors which can occur when aligning the substrate and mask for depositing the organic layers.

[0061] While certain embodiments have been particularly shown and described herein, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the scope of the present disclosure as defined by the following claims.

Claims

1. An organic light emitting display apparatus comprising:

a substrate (100) comprising a plurality of thin film transistor (TFT) devices; and
a display region (200) formed on the substrate (100),
wherein the display region (200) comprises:

a base layer (210) comprising a plurality of pixel defining layers (212) and a plurality of first electrodes (211) electrically coupled to the TFT devices;
an organic layer (220) covering the top of the plurality of pixel defining layers (212)

- and the plurality of first electrodes (211), wherein the organic layer (220) comprises an organic emission layer (223) disposed on the first electrodes (211) and between the pixel defining layers (212) and the organic layer (220) has a peripheral region comprising a number of outer edges that extend around the periphery of the organic layer (220); and **characterised by** a second electrode layer (230) at least partially covering the base layer (210) and entirely covering the organic layer (220), wherein the second electrode layer (230) directly contacts the peripheral region of the organic layer (220) so as to cover all the outer edges of the organic layer (220).
2. An organic light emitting display apparatus according to claim 1, wherein the second electrode layer (230) is arranged to extend by a width of greater than about 100 μm beyond an outer edge of the organic layer (220).
 3. An organic light emitting display apparatus according to claim 2, wherein the second electrode layer (230) is arranged to extend by a width of greater than about 100 μm beyond all the outer edges of the organic layer (220).
 4. An organic light emitting display apparatus according to any one of claims 1 to 3, wherein the organic emission layer (220) comprises at least one small-molecule organic substance.
 5. An organic light emitting display apparatus according to claim 4, wherein the organic layer (220) comprises at least one of a hole injection layer (221), a hole transport layer (222), an electron injection layer (225), an electron transport layer (224), and a hole blocking layer.
 6. An organic light emitting display apparatus according to any one of claims 1 to 5, wherein the base layer (210) further comprises a dummy pixel region.
 7. An organic light emitting display apparatus according to any one of claims 1 to 6, further comprising an electrode wiring portion disposed on a side of the display region (200) and electrically coupled to the second electrode layer (230), wherein second electrode layer (230) covers the electrode wiring portion.
 8. An organic light emitting display apparatus according to any one of claims 1 to 7, further comprising a planarization film between the TFT devices and the first electrodes (211).
 9. An organic light emitting display apparatus accord-
 10. An organic light emitting display apparatus according to any one of claims 1 to 9, further comprising a device unit configured for sending signals to the display region and a power supply unit supplying electric power to the display region (200), wherein the device unit and the power supply unit are formed on the substrate (100).
 11. An organic light emitting display apparatus according to any one of claims 1 to 9, further comprising at least one of a device unit configured for sending signals to the display region and a power supply unit supplying electric power to the display region (200).
 12. An organic light emitting display apparatus according to any one of claims 1 to 11, further comprising an encapsulating structure disposed on the substrate sealing the display region (200).
 13. An organic light emitting display apparatus according to claim 12, wherein the encapsulating structure comprises alternate organic layers and inorganic layers disposed over the display region (200).
- Patentansprüche**
1. Organische lichtemittierende Displayvorrichtung, Folgendes umfassend:

ein Substrat (100), eine Vielzahl von TFT(Dünnschichttransistor)-Einrichtungen umfassend; und einen auf dem Substrat (100) geformten Displaybereich (200), worin der Displaybereich (200) Folgendes umfasst:

eine Bodenschicht (210), die eine Vielzahl von pixeldefinierenden Schichten (212) umfasst, und eine Vielzahl von ersten Elektroden (211), die an die TFT-Einrichtungen elektrisch gekoppelt sind;

eine organische Schicht (220), die das Oberteil der Vielzahl von pixeldefinierenden Schichten (212) und die Vielzahl von ersten Elektroden (211) bedeckt, worin die organische Schicht (220) eine organische Emissionsschicht (223) umfasst, die auf den ersten Elektroden (211) und zwischen den pixeldefinierenden Schichten (212) angeordnet ist, und die organische Schicht (220) einen Peripheriebereich hat, der eine Anzahl von Außenkanten umfasst, die um die Peripherie der organischen Schicht (220)

- herum verlaufen; und **gekennzeichnet durch** eine zweite Elektrodenschicht (230), die die Bodenschicht (210) mindestens teilweise bedeckt und die organische Schicht (220) völlig bedeckt, worin die zweite Elektrodenschicht (230) den Peripheriebereich der organischen Schicht (220) direkt kontaktiert, sodass alle Außenkanten der organischen Schicht (220) bedeckt sind.
2. Organische lichtemittierende Displayvorrichtung nach Anspruch 1, worin die zweite Elektrodenschicht (230) so angeordnet ist, dass sie sich um eine Breite von mehr als ungefähr 100 µm über eine Außenkante der organischen Schicht (220) hinaus erstreckt.
 3. Organische lichtemittierende Displayvorrichtung nach Anspruch 2, worin die zweite Elektrodenschicht (230) so angeordnet ist, dass sie sich um eine Breite von mehr als ungefähr 100 µm über alle Außenkanten der organischen Schicht (220) hinaus erstreckt.
 4. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 3, worin die organische Emissionsschicht (220) mindestens eine organische Kleinmolekülschicht umfasst
 5. Organische lichtemittierende Displayvorrichtung nach Anspruch 4, worin die organische Schicht (220) mindestens eine von Folgenden umfasst: eine Löcherinjektionsschicht (221), eine Löchertransportsschicht (222), eine Elektroneninjektionsschicht (225), eine Elektronentransportsschicht (224) und eine Löcherblockierschicht.
 6. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 5, worin die Bodenschicht (210) außerdem einen Dummypixelbereich umfasst.
 7. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 6, außerdem einen Elektrodenverdrahtungsabschnitt umfassend, der auf einer Seite des Displaybereichs (200) angeordnet ist und an die zweite Elektrodenschicht (230) elektrisch gekoppelt ist, worin die zweite Elektrodenschicht (230) den Elektrodenverdrahtungsabschnitt bedeckt.
 8. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 7, außerdem einen Planarisierungsfilm zwischen den TFT-Einrichtungen und den ersten Elektroden (211) umfassend.
 9. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 8, worin die zweite Elektrodenschicht (230) ein transparentes Material
- umfasst.
10. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 9, außerdem eine Einrichtungseinheit umfassend, die zum Senden von Signalen an den Displaybereich konfiguriert ist, und eine Netzanschlusseinheit, die den Displaybereich (200) mit elektrischem Strom versorgt, worin die Einrichtungseinheit und die Netzanschlusseinheit auf dem Substrat (100) geformt sind.
 11. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 9, außerdem mindestens eine von Folgenden umfassend: eine Einrichtungseinheit, die zum Senden von Signalen an den Displaybereich konfiguriert ist, und eine Netzanschlusseinheit, die den Displaybereich (200) mit elektrischem Strom versorgt.
 12. Organische lichtemittierende Displayvorrichtung nach einem der Ansprüche 1 bis 11, außerdem eine Verkapselungsstruktur umfassend, die auf dem Substrat angeordnet ist und den Displaybereich (200) versiegelt.
 13. Organische lichtemittierende Displayvorrichtung nach Anspruch 12, worin die Verkapselungsstruktur abwechselnd organische Schichten und anorganische Schichten umfasst, die über dem Displaybereich (200) angeordnet sind.

Revendications

1. Dispositif d'affichage électroluminescent organique comprenant :
 - un substrat (100) comprenant une pluralité de dispositifs formant transistors à couches minces (TFT) ; et
 - une région d'affichage (200) formée sur le substrat (100), dans lequel la région d'affichage (200) comprend :
 - une couche de base (210) comprenant une pluralité de couches définissant des pixels (212) et une pluralité de premières électrodes (211) couplées électriquement aux dispositifs TFT ;
 - une couche organique (220) recouvrant le dessus de la pluralité de couches définissant des pixels (212) et de la pluralité de premières électrodes (211), dans lequel la couche organique (220) comprend une couche d'émission organique (223) disposée sur les premières électrodes (211) et entre les couches définissant des pixels (212) et

- la couche organique (220) a une région périphérique comprenant un certain nombre de bords extérieurs qui s'étendent autour de la périphérie de la couche organique (220) ; et **caractérisé par** une deuxième couche d'électrode (230) recouvrant au moins partiellement la couche de base (210) et recouvrant entièrement la couche organique (220), dans lequel la deuxième couche d'électrode (230) est directement en contact avec la région périphérique de la couche organique (220) de manière à recouvrir tous les bords extérieurs de la couche organique (220).
2. Dispositif d'affichage électroluminescent organique selon la revendication 1, dans lequel la deuxième couche d'électrode (230) est agencée pour s'étendre sur une largeur supérieure à environ 100 μm au-delà d'un bord extérieur de la couche organique (220).
 3. Dispositif d'affichage électroluminescent organique selon la revendication 2, dans lequel la deuxième couche d'électrode (230) est agencée pour s'étendre sur une largeur supérieure à environ 100 μm au-delà de tous les bords extérieurs de la couche organique (220).
 4. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 3, dans lequel la couche d'émission organique (220) comprend au moins une substance organique à petites molécules.
 5. Dispositif d'affichage électroluminescent organique selon la revendication 4, dans lequel la couche organique (220) comprend au moins l'une d'une couche d'injection de trous (221), d'une couche de transport de trous (222), d'une couche d'injection d'électrons (225), d'une couche de transport d'électrons (224), et d'une couche de blocage de trous.
 6. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 5, dans lequel la couche de base (210) comprend en outre une région d'absence de pixel.
 7. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 6, comprenant en outre une partie de câblage d'électrode disposée d'un côté de la région d'affichage (200) et couplée électriquement à la deuxième couche d'électrode (230), dans lequel la deuxième couche d'électrode (230) recouvre la partie de câblage d'électrode.
 8. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 7, comprenant en outre un film de planarisation entre les dispositifs TFT et les premières électrodes (211).
 9. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 8, dans lequel la deuxième couche d'électrode (230) comprend un matériau transparent.
 10. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 9, comprenant en outre une unité de dispositif configurée pour envoyer des signaux à la région d'affichage et une unité d'alimentation délivrant une énergie électrique à la région d'affichage (200), dans lequel l'unité de dispositif et l'unité d'alimentation sont formées sur le substrat (100).
 11. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 9, comprenant en outre au moins l'une d'une unité de dispositif configurée pour envoyer des signaux à la région d'affichage et d'une unité d'alimentation délivrant une énergie électrique à la région d'affichage (200).
 12. Dispositif d'affichage électroluminescent organique selon l'une quelconque des revendications 1 à 11, comprenant en outre une structure d'encapsulation disposée sur le substrat scellant la région d'affichage (200).
 13. Dispositif d'affichage électroluminescent organique selon la revendication 12, dans lequel la structure d'encapsulation comprend des couches organiques et des couches inorganiques alternées disposées sur la région d'affichage (200).

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12





FIG. 13



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20040012747 A [0005]

专利名称(译)	有机发光显示装置		
公开(公告)号	EP1933402B1	公开(公告)日	2010-09-01
申请号	EP2007254793	申请日	2007-12-12
[标]申请(专利权)人(译)	三星斯笛爱股份有限公司		
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星移动显示器有限公司.		
发明人	CHOE, WON-KYU C/O Y.P. LEE, MOCK & PARTNERS BAEK, JI-YEON C/O Y.P. LEE, MOCK & PARTNERS		
IPC分类号	H01L51/52		
CPC分类号	H01L27/3244 H01L27/3223 H01L51/5225 H01L51/5253		
优先权	1020060127305 2006-12-13 KR		
其他公开文献	EP1933402A1		
外部链接	Espacenet		

摘要(译)

一种减少外部水分和氧气渗透的有机发光显示装置，包括：包括多个 TFT 器件的基板；以及在基板上形成的显示区域；其中显示区域包括基层，基层包括电连接到 TFT 器件并限定像素区域的第一电极，形成在基层上的有机层，以及形成完全覆盖基层和有机层的结构的第二电极层。

FIG. 1

