



(11) **EP 1 944 803 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
16.07.2008 Bulletin 2008/29

(51) Int Cl.:
H01L 27/02 (2006.01) H01L 27/32 (2006.01)

(21) Application number: **07112632.0**

(22) Date of filing: **17.07.2007**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE
SI SK TR**
Designated Extension States:
AL BA HR MK RS

(30) Priority: **15.01.2007 KR 20070004437**

(71) Applicant: **Samsung SDI Co., Ltd.**
Suwon-si
Gyeonggi-do (KR)

(72) Inventors:
• **Jeong, Seon**
Gyeonggi-do (KR)

• **Choi, Michael**
Gyeonggi-do (KR)

(74) Representative: **Hengelhaupt, Jürgen et al**
Anwaltskanzlei
Gulde Hengelhaupt Ziebig & Schneider
Wallstrasse 58/59
10179 Berlin (DE)

Remarks:

Amended claims in accordance with Rule 137(2)
EPC.

(54) **Organic light emitting diode display and fabricating method thereof**

(57) An organic light emitting diode display and a fabricating method thereof are disclosed. Embodiments provide an organic light emitting diode display and a fabricating method thereof which prevents a pixel and a driver included in the organic light emitting diode display from

being damaged due to an electrostatic discharge by forming a protective layer along at least one edge region of a substrate having a pixel region and a non-pixel region.

EP 1 944 803 A1

Description

BACKGROUND

Field of the Invention

[0001] The field relates to an organic light emitting diode display and a fabricating method thereof, and in particular, an organic light emitting diode display and a fabricating method thereof which includes a protection circuit for preventing a pixel and a driver included in an organic light emitting diode display from being damaged by an electrostatic discharge.

Description of the Related Technology

[0002] An organic light emitting diode display is one of flat panel displays using an Organic Light Emitting Device (OLED) which emits a light by recombination of the electrons provided from a cathode and the holes provided from an anode. Such an organic light emitting diode display has the advantages such as a thin thickness, a wide viewing angle, and a very fast response.

[0003] The organic light emitting diode display is classified into a passive matrix display and an active matrix display depending on a driving method. The passive matrix method is a method, in which an anode and a cathode are formed vertically on a substrate, and a line is selected, thereby driving the diode. On the contrary, the active matrix method is a method which provides a driving current corresponding to a data signal to an organic light emitting device (OLED) by using a thin film transistor (TFT) formed in each pixel, and light is emitted from the organic light emitting device (OLED) by the driving current, thereby an image is displayed, and because of stable brightness, the power consumption is low as compared with the passive matrix method. Accordingly, there is an advantage that it is very useful for applications of a high resolution and a large display.

[0004] A conventional organic light emitting diode display includes a pixel region in which the pixels are arranged in a matrix format, and a non-pixel region having a power source and a driver for driving the pixels. The pixels in the pixel region include a thin film transistor and an organic light emitting diode required for driving or switching. The pixel region and the non-pixel region are coupled to each other via multiple lines.

[0005] The conventional organic light emitting diode display described above is fabricated through at least a step of forming a thin film transistor, a step of forming an organic light emitting diode, an encapsulation step, and a modulating step. In the organic light emitting diodes display, while these steps are being performed, static electricity can be generated due to environmental factors inside and outside. The static electricity can be generated during almost all fabricating processes such as deposition, etching etc. for fabricating the organic light emitting diode display, or can be generated due to outside envi-

ronment while an image is being displayed on the organic light emitting diode display.

[0006] In the conventional organic light emitting diodes display, there is a problem that the inside circuit can be damaged due to ElectroStatic Discharge (ESD) generated by outside environment during above-mentioned fabricating processes.

SUMMARY OF CERTAIN INVENTIVE ASPECTS

[0007] An electrostatic discharge circuit which prevents a pixel and a driver included in an organic light emitting diode display from being damaged by an electrostatic discharge is disclosed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] The accompanying drawings are included to provide a further understanding, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments, together with the description, serve to explain the principles disclosed.

FIG. 1 illustrates a schematic diagram of an organic light emitting diode display according to one embodiment.

FIG. 2 illustrates a layout showing A portion of FIG. 1. FIG. 3 illustrates a cross-section cut along I-I line of FIG. 2.

FIG. 4 illustrates a cross-section cut along II-II line of FIG. 2.

FIG. 5 illustrates a path through which the static electricity is discharged in an organic light emitting diode display according to one embodiment.

FIG. 6 illustrates a sequential flow chart showing a method for fabricating an organic light emitting diode display according to one embodiment.

FIGs. 7a to 7f illustrate steps of fabricating an organic light emitting diode display.

FIG. 8 illustrates a pixel region and a non-pixel region of an organic light emitting diode display fabricated according to one embodiment.

FIG. 9 illustrates a schematic diagram of an organic light emitting diode display according to one embodiment.

DETAILED DESCRIPTION OF CERTAIN INVENTIVE EMBODIMENTS

[0009] Certain embodiments will be described more fully with reference to the accompanying drawings, in which embodiments are shown.

[0010] Referring to the attached drawings and the embodiments, an organic light emitting diode display will be explained in detail as below.

[0011] FIG. 1 illustrates a schematic diagram of an organic light emitting diode display according to one embodiment.

[0012] Referring to FIG. 1, the organic light emitting diode display 100 according to one embodiment includes a pixel region 110a including the pixels P arranged in a matrix format, and a substrate 110 including non-pixel region 110b formed in an outer region of the pixel region 110a; and an electrostatic discharge circuit 120 formed on the non-pixel region 110b.

[0013] The substrate 110 includes a pixel region 110a of a substantially rectangular shape, and a non-pixel region 110b formed outside the pixel region 110a. Here, a data driver 130, a scan driver 140, and an emission control driver 150 can be further coupled to the substrate 110.

[0014] The pixel region 110a is the region where a plurality of pixels arranged in a matrix format is driven thereby displaying an image. Each pixel is formed on a region near which a data line, a scan line, and an emission control line intersect. Though the pixels P are not illustrated in detail in the drawings, a driving element formed by a thin film transistor, at least one switching transistor, a storage capacitor, and an organic light emitting diode can be included in each pixel.

[0015] The non-pixel region 110b is formed on a region outside the pixel region 110a on the substrate 110. In the non-pixel region 110b, the electrostatic discharge circuit 120, a data driver 130, a scan driver 140, and an emission control driver 150 for providing a driving signal to a data line, a scan line and an emission control line respectively, can be formed. Further, in the non-pixel region 110b, a pad unit 160 can be included for electrically coupling the pixels P, the data driver 130, the scan driver 140, and the emission control driver 150 to an external module.

[0016] The electrostatic discharge circuit 120 can be formed on the non-pixel region 110b of the substrate 110. The electrostatic discharge circuit 120 can be formed on one side of the end portions of the substrate 110. The electrostatic discharge circuit 120 can be formed on each side of the remaining regions except for the region of the substrate 110 on which the pad unit 160, which will be described later, is formed. The electrostatic discharge circuit 120 can be integrally formed for each side of the substrate 110. The electrostatic discharge circuit 120 prevents the inside circuits, for example, a driving element included in the pixels P, the switching transistor, or the organic light emitting diode from being damaged by the electrostatic discharge which can be generated during or after the processes of fabricating the organic light emitting diode display 100. The electrostatic discharge circuit 120 can protect the circuits which are formed in the non-pixel region 110b, for example, the data driver 130, the scan driver 140, the emission control driver 150, and the pad unit 160 that will be explained later. The electrostatic discharge circuit 120 may be formed on the end portions of a substrate as illustrated above, but the present invention is not limited to this formation, and it is natural that the electrostatic discharge circuit 120 can be formed on the other portions of the substrate 110 which are vulnerable to the electrostatic discharge. Embodiments of the structure of the electro-

static discharge circuit 120 will be explained in detail below.

[0017] The data driver 130, the scan driver 140, and the emission control driver 150 can be formed as an IC (Integrated Circuit) on the non-pixel region 110b of the substrate 110. The data driver 130, the scan driver 140, and the emission control driver 150 can be formed on the same layer as the pixel region 110a which forms the thin film transistor (not shown) included in the pixels. On the other hand, the data driver 130, the scan driver 140, and the emission control driver 150 can also be formed on another substrate. The respective driver 130, 140, 150 formed on another substrate (not shown) may be any type, for example each of the drivers may be any of TCP(Tape Carrier Package), FPC(Flexible Printed Circuit), TAB(Tape Carrier Package), COG(Chip On Glass) and the equivalents thereof, and can be coupled to the substrate 110. The shape, the formation position and etc. of drivers 130, 140 150 is not limited.

[0018] The pad unit 160 is formed in the non-pixel region 110b of the substrate 110. The pad unit 160 is formed on one side of the substrate 110 for coupling the external circuit module (not shown) and the drivers 130, 140, 150 or the external circuit module and the pixels P. The electrostatic discharge circuit 120 can be coupled to a ground pad 160a formed on at least one side of the pad unit 160.

[0019] The electrostatic discharge circuit 120 used in the organic light emitting diode display 100 according to one embodiment of the present invention will be explained in greater detail.

[0020] FIG. 2 illustrates the layout corresponding to some portions (A of FIG. 1) of the electrostatic discharge circuit 120 of the organic light emitting diode display 100 according to an exemplary embodiment of the present invention, FIG. 3 illustrates a cross-section of the electrostatic discharge circuit 120 cut along I-I line of FIG. 2, and FIG. 4 illustrates a cross-section of the electrostatic discharge circuit 120 cut along II-II line of FIG. 2. The electrostatic discharge circuit 120 explained below means the electrostatic discharge circuit 120 formed on other all portions as well as some portions (A of FIG. 1) of the substrate 110.

[0021] Referring to FIG. 2 through FIG. 4, the electrostatic discharge circuit 120 used in the organic light emitting diode display 100 according to one embodiment includes a buffer layer 120a formed on the substrate 110, a semiconductor layer 120b formed on the buffer layer 120a, a gate insulating layer 120c formed on the semiconductor layer 120b, a gate electrode 120d formed on the gate insulating layer 120c, an interlayer dielectric layer 120e covering the gate electrode 120d, and a source/drain electrode 120f formed on the interlayer dielectric layer 120e.

[0022] In this embodiment, the substrate 110 is formed in a planar type having an upper side and a lower side, and there is thickness of 0.05 -1mm between the upper side and the lower side. If the thickness of the substrate 110 is thinner than 0.05mm, there is a shortcoming that

the substrate can be easily damaged by washing, etching and heat treatment during the processes, or easily influenced by the external forces. On the contrary, if the thickness of the substrate 110 is thicker than 1mm, there is a shortcoming that it is difficult to apply it to various kinds of diodes displays which are preferably thin. The substrate 110 can be formed, for example, with any one of a glass, a plastic, a stainless steel, a nano -compound material, and the equivalents thereof, but the present invention does not limit the materials of the substrate. The substrate 110 has the pixel region 110a including the thin film transistor (not shown) and the organic light emitting diode (not shown), and the non -pixel region 110b on which various kinds of drivers are formed.

[0023] The buffer layer 120a can prevent humidity (H_2O), hydrogen (H_2) or oxygen (O_2) and the like from penetrating into the electrostatic discharge circuit 120 including the semiconductor layer 120b, which will be explained later below. For this purpose, the buffer layer 120a can be formed by using at least any of a silicon oxidation film (SiO_2), a silicon nitration film (Si_3N_4), an inorganic film and the equivalents thereof, and can be fabricated during a semiconductor process, but the present invention does not limit the materials of the buffer layer 120. Further, this buffer layer 120a can be omitted.

[0024] The semiconductor layer 120b is formed on the upper side of the buffer layer 120a or the upper side of the substrate 110. The semiconductor layer 120b induces an electro static discharge together with the gate electrode 120d and the source/drain electrode 120f which will be explained below. The semiconductor layer 120b can be any of an amorphous silicon, a micro silicon (which has grain size between the amorphous silicon and the polycrystal silicon), an organic material, and the equivalents thereof, and the present invention does not limit the materials of the semiconductor layer 120b.

[0025] The gate insulating layer 120c can be formed on the upper side of the semiconductor layer 120b. The gate insulating layer 120c is formed for securing electrical insulation between the gate electrode 120d that will be explained below, and the semiconductor layer 120b. The gate insulating layer 120c can be formed by using at least any of a silicon oxidation film, a silicon nitration film, an inorganic film and the equivalents thereof, and can be obtained during a semiconductor process, but the present invention does not limit the materials of the gate insulating layer 120c. The gate insulating layer 120c can be formed on the buffer layer 120a along the semiconductor layer 120b. Since the gate insulating layer 120c discharges the static electricity by inducing dielectric breakdown of the gate insulating layer 120c to the gate electrode 120d or the source/drain electrode 120f, it is possible to prevent the pixels P in the pixel region 110a and the drivers 130, 140, 150 of the non -pixel region 110b from being damaged by the electrostatic discharge. Because the gate insulating layer 120c has the thickness (T1 of FIG. 4) of approximately $1\mu m$ below is formed between the gate electrode 120d and the semiconductor

layer 120b, a dielectric breakdown occurs when relatively low static electricity corresponding to a few hundreds of volts is generated. Accordingly, the organic light emitting diode display 100 can be protected from the electrostatic discharge.

[0026] The gate electrode 120d is formed on the upper side of the gate insulating layer 120c. More specifically, the gate electrode 120d can be formed on the region corresponding to the semiconductor layer 120 of the upper side of the gate insulating layer 120c. The gate electrode 120d can be coupled to the ground pad (160a of FIG. 1) included in the pad unit (160 of FIG. 1). The gate electrode 120d can be formed by at least one metal (e.g. Mo, MoW, Ti, Cu, Al, AlNd, Cr, Mo alloy, Cu alloy, Al alloy, and the like), and doped poly -silicon and the equivalents thereof, but the present invention does not limit the materials of the gate electrode 120d.

[0027] The interlayer dielectric layer 120e is formed on the upper side of the gate electrode 120d. The interlayer dielectric layer 120e can also be formed on the gate insulating layer 120c formed on inner circumference of the gate electrode 120d. Here, the interlayer dielectric layer 120e can be formed by any one selected from polymer group, plastic group, glass group, and the equivalent groups, but the present invention does not limit the materials of the interlayer dielectric layer 120e. The interlayer dielectric layer 120e can be formed by the material identical to the material of the gate insulating layer 120c. Like the gate insulating layer 120c, the interlayer dielectric layer 120e can experience a dielectric breakdown due to the static electricity introduced via the gate electrode 120d or the source/drain electrode 120f.

[0028] The source/drain electrode 120f can be formed on the upper side of the interlayer dielectric layer 120e. Here, an electrically conductive contact c1 penetrating through the interlayer dielectric layer 120e can be formed between the source/drain electrode 120f and the semiconductor layer 120b. The source/drain electrode 120f can be coupled to the semiconductor layer 120b by the conductive contact c1. Here, the horizontal distance (ℓ_1 of FIG. 4) can be spaced apart by $1\mu m - 10\mu m$ between the source/drain electrode 120f and the gate electrode 120d. If the horizontal distance (ℓ_1 of FIG. 4) is shorter than $1\mu m$, since the resistance between the source/drain electrode 120f and the gate electrode 120d becomes low, the voltage level which is protected by the electrostatic discharge circuit 120 becomes low. That is, it will be difficult to control high static electricity of more than thousands of volts. On the contrary, If the horizontal distance (ℓ_1 of FIG. 4) is longer than $10\mu m$, since the resistance is higher, the protected voltage level is higher, but since the region of the electrostatic discharge circuit 120 which can be formed in the non -pixel region 110b is limited, it is desirable that the horizontal distance (ℓ_1 of FIG. 4) is controlled to be less than $10\mu m$. On the other hand, the thickness (T2) having approximately $1\mu m$ can be formed between the source/drain electrode 120f and the semiconductor layer 120b. Since the

source/drain electrode 120f is integrally formed such that a source region and a drain region are coupled, it does not operate when the organic light emitting diode display 100 operates normally. The source/drain electrode 120f can be formed by the metal material identical to that of the above-mentioned gate electrode 120d, and the present invention does not limit the materials of the source/drain electrode 120f.

[0029] A protective layer 120g and a planarization layer 120h can be further formed on the upper side of the source/drain electrode 120f. The protective layer 120g covers the source/drain electrode 120f and the interlayer dielectric layer 120e, and thus protects the source/drain electrode 120f and the interlayer dielectric layer 120e. The protective layer 120g can be formed of at least one selected from a common inorganic film and the equivalents thereof, but the present invention does not limit the materials of the protective layer 120g. In addition, since the planarization layer 120h covers the protective layer 120g, it is very helpful for flattening the whole surface of the electrostatic discharge circuit. The planarization layer 120h can be formed by coating or depositing at least one selected from BCB (Benzo Cyclo Butene), acrylic, and the equivalents thereof. The present invention does not limit the materials or the formation methods of the planarization layer 120h.

[0030] The electrode layer 120i can be further formed on the upper side of the planarization layer 120h. The electrode layer 120i is coupled to the source/drain electrode 120f via an electrically conductive via hole v1. When the static electricity is generated, the electrode layer 120i allows the static electricity to be discharged via an electrically conductive via hole v1 and the source/drain electrode 120f. The electrode layer 120i can be formed by a metal material identical to that of the above-mentioned gate electrode layer 120d, and the present invention does not limit the materials of the electrode layer 120i.

[0031] Next, the operations of the electrostatic discharge circuit 120 formed according to one embodiment will be explained in greater detail.

[0032] FIG. 5 illustrates a path through which the static electricity is discharged in an organic light emitting diode display 100 according to one embodiment. According to the embodiment, the static electricity can be discharged via mainly the first path (①) between the source/drain electrode 120f and the gate electrode 120d, the second path (②) between the source/drain electrode 120f and the semiconductor layer 120b, and the third path (③) between the gate electrode 120d and the semiconductor layer 120b.

[0033] The first path (①) is the path through which discharge is performed via the interlayer dielectric layer 120e between the source/drain electrode 120f and the gate electrode 120d, and the static electricity having a relatively high voltage level generated from the source/drain electrode 120f can be swiftly discharged to the direction of the gate electrode 120d. In the interlayer dielectric layer 120e formed between the source/drain elec-

trode 120f and the gate electrode 120d, a dielectric breakdown is generated and thus the electrostatic discharge is shunted. The static electricity generated from the source/drain electrode 120f can be shunted to the ground pad 160a coupled to the gate electrode 120d. The source/drain electrode 120f is spaced apart from the gate electrode 120d by about 1 μm to about 10 μm in the horizontal direction with the interlayer dielectric layer 120e being sandwiched between them. If the horizontal distance ($\ell 1$) between the source/drain electrode 120f and the gate electrode is shorter than 1 μm , since the resistance between the source/drain electrode 120f and the gate electrode becomes low, the voltage level protected by the electrostatic discharge circuit 120 becomes low. That is, it will be difficult to control high static electricity of more than thousands of volts. On the contrary, if the horizontal distance $\ell 1$ between the source/drain electrode 120f and the gate electrode is longer than 10 μm , since the resistance is higher, the protected voltage level is higher, but since the region of the electrostatic discharge circuit 120 which can be formed in the non-pixel region 110b is limited, it is desirable that the horizontal distance $\ell 1$ is controlled to be within 10 μm .

[0034] The second path (②) is the path through which discharge is performed via the interlayer dielectric layer 120e and the gate insulating layer 120c between the source/drain electrode 120f and the semiconductor layer 120b. The static electricity having a relatively low voltage level which is generated from the source/drain electrode 120f can be discharged to the direction on which the semiconductor layer 120b is formed. In this case, in the interlayer dielectric layer 120e and the gate insulating layer 120c, as a dielectric breakdown is generated, the electrostatic discharge can be shunted. Since the thickness (T_2), which is approximately 1 μm , is formed between the source/drain electrode 120f and the semiconductor layer 120b, it protects an organic light emitting diode display 100 from the static electricity having a relatively low voltage level.

[0035] The third path (③) is the path through which discharge is performed via the gate insulating layer 120c between the gate electrode 120d and the semiconductor layer 120b. The static electricity generated from the gate electrode 120d can be discharged to the direction on which the semiconductor layer 120b is formed. In this case, since the dielectric breakdown is generated in the gate insulating layer 120c, it becomes possible to protect the organic light emitting diode display 100 from the electrostatic discharge. Since the thickness (T_1), which is approximately 1 μm , is formed between the gate electrode 120d and the semiconductor layer 120b, it becomes possible to protect the organic light emitting diode display 100 from the static electricity having a relatively low voltage. On the other hand, the static electricity generated from the gate electrode 120d does not cause the dielectric breakdown of the gate insulating layer 120c, but can be discharged to the ground pad 160a.

[0036] According to above-mentioned organic light

emitting diode display, there is an advantage that the electrostatic discharge circuit 120 protects the static electricity ranging from a relatively high level to a relatively low level.

[0037] Next, a method for fabricating an organic light emitting diode display 100 according to an exemplary embodiment of the present invention will be explained.

[0038] FIG. 6 is a sequential flow chart showing a method for fabricating an organic light emitting diode display according to one embodiment. FIGs 7a to 7f illustrate an organic light emitting diode display formed in sequence according to the fabricating processes of FIG. 6, and FIG. 8 illustrates the pixel region 110a and the non-pixel region 110b of an organic light emitting diode display 100 which is completed according to one embodiment.

[0039] Referring to FIGs. 6 to 8, a method for fabricating an organic light emitting diode display according to one embodiment includes the step S1 of preparing a substrate having a pixel region 110a and a non-pixel region 110b, the step S2 of forming a semiconductor layer, the step S3 of forming a gate insulating layer, the step S4 of forming a gate electrode, the step S5 of forming an interlayer dielectric layer, and the step S6 of forming a source/drain electrode, and at least a thin film transistor 170 is formed in the pixel region 110a, and an electrostatic discharge circuit 120 is formed in the non-pixel region 110b.

[0040] Referring to FIG. 7a, the step S1 of preparing a substrate is preparing a substrate on the pixel region 110a and the non-pixel region 110b. The step S1 can further include the washing step of preventing foreign substances from being introduced into the substrate 110 having the upper side and the lower side formed in a plate shape, and the pre-compaction step of allowing the substrate not to be easily deformed by heat or pressure at the fabricating processes. It may be preferable that the substrate 110 having the thickness of 0.05mm to 1mm is prepared. If the thickness of the substrate 110 is thinner than 0.05mm, there is a shortcoming that the substrate can be easily damaged by washing, etching and heat treatment during the processes, or easily influenced by the external forces. On the contrary, if the thickness of the substrate 110 is thicker than 1mm, there is a shortcoming that it is difficult to apply it to various kinds of diodes displays which are getting slimmer and slimmer recently. However, these shortcomings are not problematic in some embodiments. The substrate 110 can be classified into the pixel region 110a including the thin film transistor 170 and the organic light emitting diode 180, and the non-pixel region 110b where the electrostatic discharge circuit 120 and various kinds of drivers are formed.

[0041] If the substrate 110 is prepared, a buffer layer 170a, 120a having a predetermined thickness is formed on the pixel region 110a and the non-pixel region 110b of the substrate 110, respectively. The buffer layer 170a, 120a can be formed on the pixel region 110a and the non-pixel region 110b of the substrate 110, simultane-

ously or independently. The buffer layer 170a, 120a prevents foreign substances from being introduced into inside circuits such as the thin film transistor 170, the organic light emitting diode 180, and the electrostatic discharge circuit 120 via the substrate 110. Further, the buffer layer 170a, 120a enables the semiconductor layer 170a, 120a to be formed on the surface thereof smoothly. This buffer layer 170a, 120a can be formed by using at least one of a silicon oxidation film (SiO_2), a silicon nitration film (Si_3N_4), an inorganic film and the equivalents thereof which can be fabricated during a semiconductor process, but the present invention does not limit the materials of the buffer layer 170a, 120a. Here, this buffer layer 170a, 120a can be formed as a multiple structure, and the buffer layer 170a, 120a can be omitted.

[0042] Referring to FIG. 7b, at the step S2 of forming a semiconductor layer, the semiconductor layer 170b, 120b are formed on the pixel region 110a and the non-pixel region 110b of the substrate 110. The semiconductor layer 170b, 120b can be formed on the pixel region 110a and the non-pixel region 110b simultaneously or independently. Here, the buffer layer 170a, 120a can further be formed between the substrate 110 and the semiconductor layer 170b, 120b.

[0043] The buffer layer 170a, 120a having a predetermined thickness is formed on the pixel region 110a and the non-pixel region 110b of the upper side of the substrate 110, respectively. The buffer layer 170a, 120a can be formed on the pixel region 110a and the non-pixel region 110b simultaneously or independently. The buffer layer 170a, 120a prevents foreign substances from being introduced into inside circuits such as the thin film transistor 170, the organic light emitting diode 180, and the electrostatic discharge circuit 120 via the substrate 110. Further, the buffer layer 170a, 120a enables the semiconductor layer 170a, 120a to be formed on the surface thereof smoothly. This buffer layer 170a, 120a can be formed by using at least one of a silicon oxidation film (SiO_2), a silicon nitration film (Si_3N_4), an inorganic film, and the equivalents thereof which can be fabricated during a semiconductor process, but the present invention does not limit the materials of the buffer layer 170a, 120a. Here, this buffer layer 170a, 120a can be formed as a multiple structure, and the buffer layer 170a, 120a can be omitted.

[0044] The semiconductor layer 170b, 120b includes a source region and a drain region (not shown) on opposing sides, and a channel region (not shown) between the source and the drain. The semiconductor layer 170b, 120b can be formed from any of an amorphous silicon, a micro silicon, an organic material, and the equivalents thereof, and the present invention does not limit the materials of the semiconductor layer 170, 120b. For example, the semiconductor layer 170, 120b can be formed as a desired shape at a desired position through a silicon crystallization step, and a polycrystal silicon patterning step.

[0045] At the silicon crystallization step, an amorphous

silicon is deposited on the upper side of the buffer layer 170a, 120a, and then the amorphous silicon is crystallized into a polysilicon. The polysilicon can be formed through crystallization of a micro silicon. The amorphous silicon can be deposited on the upper side of the buffer layer 170a, 120a by any of a PECVD (Plasma Enhanced Chemical Vapor Deposition), a LPCVD (Low Pressure Chemical Vapor Deposition), a sputtering method, and the equivalents thereof. However, the present invention does not limit the method for forming the amorphous silicon. After the amorphous silicon is deposited on the buffer layer 120, the amorphous silicon is crystallized into a polysilicon according to the methods which will be described below.

[0046] The amorphous silicon can be crystallized by any of a laser crystallization method using an ELA (Excimer Laser Annealing), a Metal Induced Crystallization using a promoting material, and a SPC (Solid Phase Crystallization). In addition, a SLS (Sequential Lateral Solidification) in which a mask is added to a conventional laser crystallization method can be employed.

[0047] The laser crystallization method is the method which is used very widely, can use the crystallization method of a conventional polycrystal liquid crystal pixel device, and the process is simple, and the technology related to the process has been already developed.

[0048] The Metal Induced Crystallization is one of the methods which can perform crystallization at a low temperature without using the laser crystallization method. It is the method in which initially, a metal catalyst such as Ni, Co, Pd, Ti and the like, are deposited or spincoated on the surface of the amorphous silicon, the metal of the metal catalysts is directly deposited into the surface of the amorphous silicon, the phase of the amorphous silicon is changed, and crystallization is realized.

[0049] According to another type of the Metal Induced Crystallization using a promoting material, there is an advantage that when inserting a metal layer into the surface of the amorphous silicon, the contaminated substance such as a nickel silicide can be prevented from being introduced into the specific region of the thin film transistor by using a mask. This crystallization method is called MILC (Metal Induced Lateral Crystallization). A shadow mask can be employed as a mask used in this MILC method, and the shadow mask can be a linear mask or a dot type mask.

[0050] Another type of the Metal Induced Crystallization using a promoting material is a MICC (Metal Induced Crystallization with Capping Layer) in which a capping layer is inserted when depositing or spincoating the metal catalyst layer on the surface of the amorphous silicon in order to control the amount of the metal catalyst introduced into the amorphous silicon. A silicon nitride layer can be used as a capping layer. According to the thickness of the silicon nitride layer, the amount of the metal catalyst introduced into the amorphous silicon from the metal catalyst layer is changed. Here, the metal catalyst introduced into the silicon nitride layer can be formed on

the entire surface of the silicon nitride layer, or can be formed selectively by using the shadow mask. After the metal catalyst layer crystallizes the amorphous silicon into polycrystal silicon, the capping layer can be removed selectively. Wet etching or dry etching can be used for removing capping. After the polycrystal silicon is formed, a via hole (not shown) is formed on the interlayer dielectric layer 170e, 120e which will be explained below, and then impurities are injected into the crystallized polycrystal silicon through the via hole, and the metal catalyst impurities formed inside of it can be eliminated. Here, the method for eliminating the metal catalyst impurities is called a gettering process. This gettering process includes a heating process for heating the thin film transistor at a low temperature as well as the process for injecting impurities. Through such a gettering process, an excellent thin film transistor can be realized.

[0051] The micro silicon has a size of a crystallization particle which ranges from the size of the amorphous silicon to that of the polycrystal silicon, a size of 1nm to 100nm is commonly employed. The electron mobility of the micro silicon is more than 1 and less than 50, and the hole mobility is more than 0.01 and less than 0.2. Since the size of a crystallization particle is smaller as compared with the polycrystal silicon, and the protrusion region of the crystallization particles is small, when the electrons move between the crystallization particles, there are no problems and thus uniform characteristics can be exhibited.

[0052] A thermal crystallization method and a laser crystallization method can be enumerated as methods related to the crystallization particles of the micro silicon. The thermal crystallization method is classified into the method for obtaining a crystallization structure, substantially simultaneously depositing the amorphous silicon, and the reheating method. The laser crystallization method is the method for obtaining a crystallization structure by using a laser after processing the amorphous silicon by a chemical vapor deposition, and at this time, a diode laser may be used as a laser. The diode laser may use a red wavelength of 800nm band, and the laser enables the crystallization particles of the micro silicon to be crystallized substantially uniformly.

[0053] In the polycrystal silicon formed by using the above-mentioned methods, the desired area of the semiconductor layer 170b, 120b are formed at a desired position through the patterning step. The patterning step of the polycrystal silicon includes the processes such as a photoresist coating, exposure, development, etching and a photoresist peeling.

[0054] Referring to FIG. 7c, the step S3 of forming a gate insulating layer, the gate insulating layer 170c, 120c having a predetermined thickness are formed on the upper side of the semiconductor layer 170b, 120b. The gate insulating layer 170c, 120c can be formed on the pixel region 110a and the non-pixel region 110b of the substrate 110, simultaneously or respectively. Here, the gate insulating layer 170c, 120c can be formed on the upper

side of the buffer layer 170a, 120a which is inner circumference of the semiconductor layer 170b, 120b. The gate insulating layer 170c, 120c can be formed by at least one of PECVD, LPCVD, sputtering, and the equivalents thereof. Here, the gate insulating layer 170c, 120c can be formed by at least one of a silicon oxidation film (SiO_2), a silicon nitration film (Si_3N_4), an inorganic layer and the equivalents thereof, but the present invention does not limit the materials of the gate insulating layer 170c 120c.

[0055] Referring to FIG. 7d, at the step S4 of forming a gate electrode, the gate electrode 170d, 120d is formed at the positions corresponding to the semiconductor layer 170b, 120b on the upper sides of the gate insulating layer 170c, 120c of the pixel region 110a and the non-pixel region 100b. The gate electrode 170d, 120d can be deposited on the upper side of the gate insulating layer 170c, 120c by at least one method from PECVD, LPCVD, sputtering, and the equivalents thereof. After the gate electrode 170d, 120d is deposited on the upper side of the gate insulating layer 170c, 120c, desired areas of it can be formed at the desired positions through the processes such as a photoresist coating, exposure, development, etching and a photoresist peeling. This gate electrode 170d, 120d can be formed by any of a common metal (Mo, MoW, Ti, Cu, Al, AlNd, Cr, Mo alloy, Cu alloy, Al alloy and the like), and the doped polycrystal silicon and the equivalents thereof, but the present invention does not limit the materials of the gate electrode 170d, 120d.

[0056] Referring to FIG. 7e, at the step S5 of forming an interlayer dielectric layer, the interlayer dielectric layer 170e, 120e are formed on the upper side of the gate electrode 170d, 120d of each of the pixel region 110a and the non-pixel region 110b. The interlayer dielectric layer 170e, 120e can be formed on the gate insulating layer 170c, 120c and the gate electrode 170d, 120d. Here, a contact hole can be formed on the interlayer dielectric layer 170e, 120e by an etching process for coupling the semiconductor layer 170b, 120b and the source/drain electrode 170f, 120f which will be explained below. The interlayer dielectric layer 170e, 120e can be formed by any one of a polymer group, a plastic group, a glass group, and the equivalent groups, but the present invention does not limit the materials of the interlayer dielectric layer 170e, 120e.

[0057] Referring to FIG. 7f, at the step S6 of forming a source/drain electrode, the source/drain electrode 170f, 120f and the conductive contact c2, c1 are formed on the upper side of the interlayer dielectric layer 170e, 120e of each of the pixel region 110a and the non-pixel region 110b. The source/drain electrode 170f, 120f can be deposited by at least one method from PECVD, LPCVD, sputtering, and the equivalents thereof, and subsequently, a desired area of it can be patterned at the desired positions through a processes such as a photoresist coating, exposure, development, etching and a photoresist peeling. Here, the conductive contact c2, c1

are formed by filling the conductive material into the contact hole formed at the step S5 of forming an interlayer dielectric layer. The conductive contact c2, c1 can be formed by the metal material identical to those of the gate electrode 170d, 120d and the source/drain electrode 170f, 120f, and the present invention does not limit the materials of the conductive contact c2, c1. In connection with the source/drain electrode 170f of the pixel region 110a, the source region (not shown) and the drain region (not shown) of the semiconductor layer 170b can be formed independently, but in connection with the source/drain electrode 120f of the non-pixel region 110b, an electrode contacting with the source region and the drain region is integrally formed. Therefore, when a general driving voltage is applied, the electrostatic discharge circuit 120 does not operate.

[0058] According to one embodiment, referring to FIG. 8, the thin film transistor 170 is formed on the pixel region 110a of the substrate 110 for providing a driving current to an organic light emitting diode 180, and the electrostatic discharge circuit 120 is formed on the non-pixel region 110b for preventing the thin film transistor 170 and the organic light emitting diode 180 from being damaged due to the electrostatic discharge.

[0059] A protective layer 170g, 120g and a planarization layer 170h, 120h can be further formed on the upper side of the source/drain electrode 170f, 120f formed on the region of the pixel region 110a and the non-pixel region 110b, respectively. The pixel region 110a and the non-pixel region 110b can be formed such that they can be coupled to the organic light emitting diode 180 and the electrode 210i through the conductive via hole v2, v1.

[0060] The pixel region 110a may be formed near the center portion of the substrate 110, the pixels included in the pixel region 110a each include at least one thin film transistor 170. Here, the electrostatic discharge circuit 120 formed on the non-pixel region 110b is formed along at least one edge region of the substrate 110 outside of the pixel region 110a.

[0061] According to the above-mentioned fabricating method, since the electrostatic discharge circuit 120 can be fabricated by a method almost identical to that of the thin film transistor 170, the present invention is very efficient in terms of the cost and the time for fabricating the organic light emitting diode display 100.

[0062] Once the electrostatic discharge circuit 120 is at least partially formed, the thin film transistor 170 and the organic light emitting diode 180 can be protected from the static electricity which can be generated during the process for forming the conductive via hole v2 for coupling the thin film transistor 170 and the organic light emitting diode 180 of the pixel region 110a. The electrostatic discharge circuit 120 can prevent at least one driver (refer to 130, 140, 150 of FIG. 1) formed on the non-pixel region 110b from being damaged due to the electrostatic discharge.

[0063] FIG. 9 illustrates a schematic diagram of an organic light emitting diode display according to another

embodiment.

[0064] Referring to FIG. 9, the organic light emitting diode display 200 according to another embodiment includes an electrostatic discharge circuit 220 which is formed independently on each side of the substrate 210 including the pixel region 210a and the non-pixel region 210b. Therefore, there is an advantage that the electrostatic discharge circuit 220 can be selectively formed only on the region, in which the electrostatic discharge is frequently generated, or other desired regions. The electrostatic discharge circuit 220 can be coupled to the ground pad (not shown) of the pad unit 260 formed on the substrate 210. The specific structure of the electrostatic discharge circuit 220 is formed similar to that described above.

[0065] In connection with the method for fabricating the above-mentioned organic light emitting diode display 100, explanation is made with concentrating on a front light-emitting method which emits lights toward the upper direction of the substrate 110, but the present invention is not limited to this method, and embodiments can be applied to both the back light-emitting method which emits lights toward the lower direction of the substrate 110 and the method which emits lights toward the upper and the lower directions of the substrate 110 simultaneously.

[0066] According to some embodiments, since the organic light emitting diode display includes an electrostatic discharge circuit formed on at least one side of a substrate, the pixels or the drivers can be prevented from being damaged by the electrostatic discharge generated due to the internal reasons and other external environment during the manufacturing processes.

[0067] The organic light emitting diode of some embodiments is composed of an anode (ITO), an organic layer and a cathode (metal). The organic layer can include an emitting layer (EML) in which a hole and an electron contact, such that an exciton is formed to emit a light, an electron transport layer (ETL) for transporting an electron, and a hole transport layer (HTL) transporting a hole. Further, an electron injecting layer (EIL) for injecting the electrons is formed on one side of the electron transport layer, and a hole injecting layer (HIL) for injecting the holes can be further formed on one side of the hole transport layer. In addition, in case of a phosphorescence organic light emitting diode, a hole blocking layer (HBL) can be selectively formed between the emitting layer (EML) and the electron transport layer (ETL), and an electron blocking layer (EBL) can be selectively formed between the emitting layer (EML) and the hole transport layer (HTL).

[0068] Further, the organic layer can also be formed as a slim OLED structure which is formed with multiple layers. For example, a hole injection transport layer (HITL) structure which allows the hole injection layer and the hole transport layer to be formed simultaneously, and an electron injection transport layer (EITL) structure which allows the electron injection layer and the electron

transport layer to be formed simultaneously can be selectively formed. A benefit of the organic light emitting diode of in slim type is to increase emission efficiency. Further, a buffer layer can be formed as a selection layer between the anode (ITO) and the light-emitting layer. The buffer layer can be classified into an electron buffer layer for buffering the electrons and a hole buffer layer for buffering the holes.

[0069] The electron buffer layer can be selectively formed between the cathode (Metal) and the electron injection layer (EIL), and can be formed instead of the electron injection layer (EIL). Here, the stack structure of the organic layer can include the emitting layer (EML)/the electron transport layer (ETL)/the electron buffer layer/a cathode (Metal). Further, the hole buffer layer can be selectively formed between an anode (ITO) and the hole injection layer (HIL) and can be formed instead of the hole injection layer (HIL). Here, the stack structure of the organic layer can include the anode (ITO)/a hole buffer layer/the hole transport layer (HTL)/the emitting layer (EML).

[0070] In connection with the above structure, some stack structures which can be used are as follows.

a) Normal Stack Structure

- 1) an anode/a hole injection layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron injection layer/a cathode.
- 2) an anode/a hole buffer layer/a hole injection layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron injection layer/a cathode.
- 3) an anode/a hole injection layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron injection layer/an electron buffer layer/a cathode.
- 4) an anode/a hole buffer layer/a hole injection layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron injection layer/an electron buffer layer/a cathode.
- 5) an anode/a hole injection layer/a hole buffer layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron injection layer/a cathode.
- 6) an anode/a hole injection layer/a hole transport layer/a light emitting layer/an electron transport layer/an electron buffer layer/an electron injection layer/a cathode.

b) Normal Slim Structure

- 1) an anode/a hole injection and transport layer/a light emitting layer/an electron transport layer/an electron injection layer/a cathode.
- 2) an anode/a hole buffer layer/a hole injection and transport layer/a light emitting layer/an electron transport layer/an electron injection layer/a

cathode.

3) an anode/a hole injection layer/a hole transport layer/a light emitting layer/an electron injection layer/an electron buffer layer/a cathode.

4) an anode/a hole buffer layer/a hole transport layer/a light emitting layer/an electron injection and transport layer/an electron buffer layer/a cathode.

5) an anode/a hole injection and transport layer/a hole buffer layer/a light emitting layer/an electron transport layer/an electron injection layer/a cathode.

6) an anode/a hole injection layer/a hole transport layer/a light emitting layer/an electron buffer layer/an electron injection and transport layer/a cathode.

c) Inverted Stack Structure

1) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole injection layer/an anode.

2) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole injection layer/a hole buffer layer/an anode.

3) a cathode/an electron buffer layer/an electron injection layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole injection layer/an anode.

4) a cathode/an electron buffer layer/an electron injection layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole buffer layer/an anode.

5) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole buffer layer/a hole injection layer/an anode.

6) a cathode/an electron injection layer/an electron buffer layer/an electron transport layer/a light emitting layer/a hole transport layer/a hole injection layer/an anode.

d) Inverted Slim Structure

1) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole injection and transport layer/an anode.

2) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole injection and transport layer/a hole buffer layer/an anode.

3) a cathode/an electron buffer layer/an electron injection and transport layer/a light emitting layer/a hole transport layer/a hole injection layer/an anode.

4) a cathode/an electron buffer layer/an electron injection and transport layer/a light emitting layer/a

er/a hole transport layer/a hole buffer layer/an anode.

5) a cathode/an electron injection layer/an electron transport layer/a light emitting layer/a hole buffer layer/a hole injection and transport layer/an anode.

6) a cathode/an electron injection and transport layer/an electron buffer layer/a light emitting layer/a hole transport layer/a hole injection layer/an anode.

[0071] A passive matrix method and an active matrix method are widely known as a method for driving such an organic light emitting diode. In the case of the passive matrix method, there is an advantage that the processes are simple and the investment money is very small since the anode and the cathode are crossed and driving is performed by a line selection, but much current consumption is required for realizing a large screen. In the case of the active matrix method, there is an advantage that the current consumption is not so much required, the screen quality and the lifespan are good, and it can be applied to a middle screen and a large screen since the active element such as the thin film transistor and the storage capacitor are formed on each pixel.

[0072] As illustrated above, in the organic light emitting diode display and the fabrication method thereof, there is an effect that the pixels and the drivers can be prevented from being damaged due to the electrostatic discharge since an electrostatic discharge circuit is formed on at least one side of a substrate.

[0073] Accordingly, there may be an effect that a static electricity having a relatively high voltage level can be controlled, since the horizontal distance between the source/drain electrode and the gate electrode of an electrostatic discharge circuit is controlled.

[0074] Accordingly, there may be an effect that the electrostatic discharge of the organic light emitting diode display can be protected since the gate insulating layer and the interlayer dielectric layer included in an electrostatic discharge circuit induces a dielectric breakdown from the static electricity generated between the source/drain electrode and the semiconductor layer or the gate electrode and the semiconductor.

[0075] Further, there may be an efficient effect in terms of the cost and the time required for fabricating the organic light emitting diode display since an electrostatic discharge circuit of the non-pixel region is formed by a fabricating method similar to the fabricating method of the thin film transistor of the pixel region.

Claims

1. An organic light emitting diode display, comprising a substrate including a pixel region and a non-pixel region; and an electrostatic discharge circuit formed in the non-pixel region of the substrate, the electro-

static discharge circuit comprising:

a semiconductor layer formed on the substrate;
a gate insulating layer formed on the semiconductor layer;
a gate electrode formed on the gate insulating layer;
an interlayer dielectric layer formed on the gate electrode, the interlayer dielectric layer extending along a first direction; and
a source/drain electrode formed on the interlayer dielectric layer.

2. The organic light emitting diode display as claimed in claim 1, wherein the source/drain electrode is spaced apart from the gate electrode by about 1 μm to about 10 μm along the first direction.
3. The organic light emitting diode display as claimed in one of claims 1 or 2, wherein the non-pixel region further comprises:

a driver having an output connected to a pixel of the pixel region and an input connected to a pad unit configured to electrically couple the driver to an external module.
4. The organic light emitting diode display as claimed in claim 3, wherein the electrostatic discharge circuit is formed along an edge region of the substrate except for a region where the pad unit is formed.
5. The organic light emitting diode display as claimed in claim 4, wherein the electrostatic discharge circuit is independently or integrally formed along the edge region of the substrate.
6. The organic light emitting diode display as claimed in one of claims 3 through 5, wherein the gate electrode is coupled to a ground pad formed on the pad unit.
7. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a buffer layer formed between the substrate and the semiconductor layer.
8. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a protective layer on the source/drain electrode.
9. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a conductive contact for electrically coupling the source/drain electrode and the semiconductor layer.

10. The organic light emitting diode display as claimed in claim 8 or in claims 8 and 9, wherein the electrostatic discharge circuit further comprises an electrode layer formed on the protective layer.

11. The organic light emitting diode display as claimed in claim 8, wherein the electrode layer is coupled to the source/drain electrode through a conductive via hole.

12. A method of fabricating an organic light emitting display, the method comprising:

determining a pixel region and a non-pixel region on a substrate;
forming a semiconductor layer on each of the pixel region and the non-pixel region;
forming a gate insulating layer on each of the semiconductor layers of the pixel region and the non-pixel region;
forming a gate electrode on each of the gate insulating layers of the pixel region and the non-pixel region;
forming an interlayer dielectric layer extending along a first direction and covering each of the gate electrodes of the pixel region and the non-pixel region; and
forming a source/drain electrode on each of the interlayer dielectric layers of the pixel region and the non-pixel region,

wherein at least a thin film transistor is formed in the pixel region, and an electrostatic discharge circuit is formed in the non-pixel region.

13. The method of fabricating an organic light emitting diode display as claimed in claim 10, wherein the electrostatic discharge circuit and the thin film transistor are formed with the same layers.

14. The method of fabricating an organic light emitting diode display as claimed in one of claims 10 or 11, wherein in the step of forming the source/drain electrode of the non-pixel region the source/drain electrode is formed apart from the gate electrode of the non-pixel region by about 1 μm to about 10 μm along the first direction.

15. The method of fabricating an organic light emitting diode display as claimed in one of the claims 10 through 12, the method further comprising the steps of:

forming a driver having an output connected to a pixel of the pixel region; and
forming a pad unit connected to an input of the driver configured to electrically couple the driver to an external module.

16. The method of fabricating an organic light emitting diode display as claimed in claim 15, wherein the electrostatic discharge circuit is formed along an edge region of the substrate except for a region where the pad unit is formed. 5
17. The method for fabricating an organic light emitting diode display as claimed in claim 16, wherein the electrostatic discharge circuit is independently or integrally formed along the edge region of the substrate. 10
18. The method for fabricating an organic light emitting diode display as claimed in one of the claims 15 through 17, the method further comprising a step of forming a ground pad on the pad unit and a step of coupling the gate electrode to the ground pad. 15
19. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 18, the method further comprising a step of forming a buffer layer between the substrate and the semiconductor layer. 20
20. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 19, the method further comprising a step of forming a protective layer after the step of forming the source/drain electrode. 25
21. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 20, the method further comprising a step of forming a conductive contact for electrically coupling the source/drain electrode and the semiconductor layer. 30
22. The method for fabricating an organic light emitting diode display as claimed in claim 20 or claims 20 and 21, the method further comprising a step of forming an electrode layer after the step of forming the protective layer. 35
23. The method for fabricating an organic light emitting diode display as claimed in claim 22, the method further comprising a step of forming a conductive via hole and a step of coupling the electrode layer to the source/drain electrode through the conductive via hole. 40
- 45
- 50

Amended claims in accordance with Rule 137(2) EPC.

1. An organic light emitting diode display, comprising 55
- a substrate including a pixel region and a non-pixel region; and an electrostatic discharge circuit

formed in the non-pixel region of the substrate, the electrostatic discharge circuit comprising:

a semiconductor layer formed on the substrate;
 a gate insulating layer formed on the semiconductor layer;
 a gate electrode formed on the gate insulating layer;
 an interlayer dielectric layer formed on the gate electrode, the interlayer dielectric layer extending along a first direction; and
 a source/drain electrode formed on the interlayer dielectric layer, wherein the source/drain electrode is integrally formed such that a source region and a drain region are directly coupled to one another, such that static electricity may be discharged via a first path between the source/drain electrode and the gate electrode, or via a second path between the source/drain electrode and the semiconductor layer, or via a third path between the gate electrode and the semiconductor layer.

2. The organic light emitting diode display as claimed in claim 1, wherein the source/drain electrode is spaced apart from the gate electrode by about 1 μm to about 10 μm along the first direction.

3. The organic light emitting diode display as claimed in one of claims 1 or 2, wherein the non-pixel region further comprises:

a driver having an output connected to a pixel of the pixel region and an input connected to a pad unit configured to electrically couple the driver to an external module.

4. The organic light emitting diode display as claimed in claim 3, wherein the electrostatic discharge circuit is formed along an edge region of the substrate except for a region where the pad unit is formed.

5. The organic light emitting diode display as claimed in claim 4, wherein the electrostatic discharge circuit is independently or integrally formed along the edge region of the substrate.

6. The organic light emitting diode display as claimed in one of claims 3 through 5, wherein the gate electrode is coupled to a ground pad formed on the pad unit.

7. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a buffer layer

er formed between the substrate and the semiconductor layer.

8. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a protective layer on the source/drain electrode.

9. The organic light emitting diode display as claimed in any of the preceding claims, wherein the electrostatic discharge circuit further comprises a conductive contact for electrically coupling the source/drain electrode and the semiconductor layer.

10. The organic light emitting diode display as claimed in claim 8 or in claims 8 and 9, wherein the electrostatic discharge circuit further comprises an electrode layer formed on the protective layer.

11. The organic light emitting diode display as claimed in claim 8, wherein the electrode layer is coupled to the source/drain electrode through a conductive via hole.

12. A method of fabricating an organic light emitting display, the method comprising:

determining a pixel region and a non-pixel region on a substrate;
forming a semiconductor layer on each of the pixel region and the non-pixel region;
forming a gate insulating layer on each of the semiconductor layers of the pixel region and the non-pixel region;
forming a gate electrode on each of the gate insulating layers of the pixel region and the non-pixel region;
forming an interlayer dielectric layer extending along a first direction and covering each of the gate electrodes of the pixel region and the non-pixel region; and
forming a source/drain electrode on each of the interlayer dielectric layers of the pixel region and the non-pixel region,

wherein at least a thin film transistor is formed in the pixel region, and an electrostatic discharge circuit is formed in the non-pixel region, wherein the source/drain electrode is integrally formed such that a source region and a drain region are directly coupled to one another, such that static electricity may be discharged via a first path between the source/drain electrode and the gate electrode, or via a second path between the source/drain electrode and the semiconductor layer, or via a third path between the gate electrode and the semiconductor layer.

13. The method of fabricating an organic light emit-

ting diode display as claimed in claim 10, wherein the electrostatic discharge circuit and the thin film transistor are formed with the same layers.

14. The method of fabricating an organic light emitting diode display as claimed in one of claims 10 or 11, wherein in the step of forming the source/drain electrode of the non-pixel region the source/drain electrode is formed apart from the gate electrode of the non-pixel region by about 1 μm to about 10 μm along the first direction.

15. The method of fabricating an organic light emitting diode display as claimed in one of the claims 10 through 12, the method further comprising the steps of

forming a driver having an output connected to a pixel of the pixel region; and
forming a pad unit connected to an input of the driver configured to electrically couple the driver to an external module.

16. The method of fabricating an organic light emitting diode display as claimed in claim 15, wherein the electrostatic discharge circuit is formed along an edge region of the substrate except for a region where the pad unit is formed.

17. The method for fabricating an organic light emitting diode display as claimed in claim 16, wherein the electrostatic discharge circuit is independently or integrally formed along the edge region of the substrate.

18. The method for fabricating an organic light emitting diode display as claimed in one of the claims 15 through 17, the method further comprising a step of forming a ground pad on the pad unit and a step of coupling the gate electrode to the ground pad.

19. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 18, the method further comprising a step of forming a buffer layer between the substrate and the semiconductor layer.

20. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 19, the method further comprising a step of forming a protective layer after the step of forming the source/drain electrode.

21. The method for fabricating an organic light emitting diode display as claimed in one of the claims 12 through 20, the method further comprising a step of forming a conductive contact for electrically coupling the source/drain electrode and the semiconductor

layer.

22. The method for fabricating an organic light emitting diode display as claimed in claim 20 or claims 20 and 21, the method further comprising a step of forming an electrode layer after the step of forming the protective layer. 5

23. The method for fabricating an organic light emitting diode display as claimed in claim 22, the method further comprising a step of forming a conductive via hole and a step of coupling the electrode layer to the source/drain electrode through the conductive via hole. 10

15

20

25

30

35

40

45

50

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7a




FIG. 7b




FIG. 7c




FIG. 7d




FIG. 7e




FIG. 7f




FIG. 8





FIG. 9





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 07 11 2632

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 2005/087769 A1 (YAMAZAKI SHUNPEI [JP] ET AL) 28 April 2005 (2005-04-28) * paragraphs [0269], [0272]; figures 17,20 *	1-21	INV. H01L27/02 H01L27/32
X	US 2006/022601 A1 (KITAZAWA TAKAYUKI [JP]) 2 February 2006 (2006-02-02) * paragraph [0037] *	1-21	
X	US 2004/256996 A1 (OSAME MITSUAKI [JP] ET AL) 23 December 2004 (2004-12-23) * abstract * * paragraphs [0017], [0096] * * figure 4 * * claims 1,3,4 *	1-21	
A	US 2006/103772 A1 (LEE KEUN-SOO [KR]) 18 May 2006 (2006-05-18) * abstract * * paragraphs [0006] - [0010], [0018], [0042], [0044] *	1-21	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (IPC)
			H01L
Place of search		Date of completion of the search	Examiner
Berlin		17 October 2007	Morena, Enrico
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

2
EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 07 11 2632

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-10-2007

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 2005087769	A1	28-04-2005	CN	1620215 A	25-05-2005

US 2006022601	A1	02-02-2006	JP	2006065280 A	09-03-2006
			KR	20060049436 A	19-05-2006

US 2004256996	A1	23-12-2004	CN	1573847 A	02-02-2005
			JP	2005011974 A	13-01-2005

US 2006103772	A1	18-05-2006	CN	1790731 A	21-06-2006
			JP	2006146200 A	08-06-2006
			KR	20060054665 A	23-05-2006

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	EP1944803A1	公开(公告)日	2008-07-16
申请号	EP2007112632	申请日	2007-07-17
[标]申请(专利权)人(译)	三星斯笛爱股份有限公司		
申请(专利权)人(译)	三星SDI CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	JEONG SEON CHOI MICHAEL		
发明人	JEONG, SEON CHOI, MICHAEL		
IPC分类号	H01L27/02 H01L27/32		
CPC分类号	H01L27/0248		
代理机构(译)	hengelhaupt , Jürgen		
优先权	1020070004437 2007-01-15 KR		
其他公开文献	EP1944803B1		
外部链接	Espacenet		

摘要(译)

公开了一种有机发光二极管显示器及其制造方法。实施例提供一种有机发光二极管显示器及其制造方法，其通过沿着至少一个边缘区域形成保护层来防止有机发光二极管显示器中包含的像素和驱动器由于静电放电而被损坏。衬底具有像素区域和非像素区域。

