



(11) **EP 2 390 939 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
01.11.2017 Bulletin 2017/44

(51) Int Cl.:
H01L 51/52 ^(2006.01) **H01L 51/56** ^(2006.01)

(21) Application number: **11159340.6**

(22) Date of filing: **23.03.2011**

(54) **Organic light emitting diode display and method for manufacturing the same**

Organische Leuchtdiodenanzeige und Verfahren zu deren Herstellung

Affichage à diode électroluminescente organique et son procédé de fabrication

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **28.05.2010 KR 20100050488**

(43) Date of publication of application:
30.11.2011 Bulletin 2011/48

(73) Proprietor: **Samsung Display Co., Ltd.
Gyeonggi-do (KR)**

(72) Inventors:
• **Kang, Dong-Hun
Gyunggi-Do 446-711 (KR)**
• **Suh, Min-Chul
Gyunggi-Do 446-711 (KR)**

- **Han, Dong-Won
Gyunggi-Do 446-711 (KR)**
- **Kwack, Jin-Ho
Gyunggi-Do 446-711 (KR)**
- **Shin, Dae-Beom
Gyunggi-Do 446-711 (KR)**
- **Kim, Hyo-Jin
Gyunggi-Do 446-711 (KR)**

(74) Representative: **Walaski, Jan Filip et al
Venner Shipley LLP
200 Aldersgate
London EC1A 4HD (GB)**

(56) References cited:
JP-A- 2009 193 914 KR-A- 20090 073 358
US-A1- 2008 129 194 US-A1- 2009 015 148
US-A1- 2009 128 457

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The described technology generally relates to an organic light emitting diode (OLED) display, and more particularly, to an OLED display that has an encapsulation thin film and a manufacturing method thereof.

[0002] OLED displays are generally lightweight and have a thin profile. In addition, they are self-emissive and thus they do not require a separate light source. Furthermore, since the displays have characteristics of low power consumption, high luminance and high reaction speed, they have received much attention as the next generation display.

[0003] US2008129194 discloses an organic EL display that comprises a substrate, an organic EL element formed on the substrate, comprising an organic layer including a light emitting layer and a pair of electrode layers disposed on both sides of the organic layer. The organic layer comprises a first organic material. The organic EL display further comprises a capping layer comprising a second organic material having a glass transition point lower than one of the first organic material and a protective layer on the capping layer.

[0004] JP2009193914 discloses an electronic device that includes: an element mounted on a substrate; and an evaporated polymerization film covering the element, wherein the latter has a peripheral edge section where a film thickness is reduced.

[0005] US2009015148 discloses a display device including an array substrate which includes, in an active area of a wiring substrate, a self-luminous element provided in each of matrix-arrayed pixels, and a partition wall separating the pixels. The array substrate further includes a support member which is isolated from the self-luminous element and has a predetermined height from a major surface of the wiring substrate.

An OLED display includes a substrate on which an organic light emitting diode is formed. If moisture and oxygen penetrates into the organic light emitting diode that is made of an organic material, its performance degrades. Accordingly, an encapsulation method is generally used in order to prevent penetration of moisture and oxygen into OLED displays.

One inventive aspect is an organic light emitting diode (OLED) display that suppresses performance degradation of an organic light emitting diode by internal penetration of moisture and oxygen.

Another aspect is a method for manufacturing an organic light emitting diode (OLED) display that suppresses the occurrence of particles.

According to a first aspect of the invention, there is provided an organic light emitting diode (OLED) display as set out in claim 1. Preferred features are set out in claims 2 to 8.

[0006] The height of the spacer may be higher than the height of the layered structure of the driving circuit and the organic light emitting diode.

The height of the spacer may be higher than the height

of the layered structure of the driving circuit and the organic light emitting diode and the encapsulation thin film. The height of the spacer may be 3 μm to 5 μm .

The spacer may include any one of acryl, urethane and polyimide (PI).

[0007] The spacer is directly contacted with the encapsulation thin film along the circumference of the encapsulation thin film.

The encapsulation thin film may include at least a pair of inorganic film and organic film, and may be formed by alternately layering the inorganic film and the organic film.

[0008] According to another aspect of the invention, there is provided method of manufacturing an organic light emitting diode (OLED) display as set out in claim 9.

Preferred features are set out in claims 10 to 12. The spacer directly contacts the encapsulation layer along the perimeter of the encapsulation layer. The encapsulation thin film may be formed by alternately layering at least a pair of inorganic film and organic film. The organic light emitting diode (OLED) display may comprise a substrate; a driving circuit formed on the substrate; the organic light emitting diodes formed on the substrate and electrically connected to the driving circuit; the encapsulation thin film formed on the driving circuit and organic light emitting diodes. The spacer is formed on the substrate and surrounds the encapsulation thin film.

[0009] In the above display, the height of the spacer may be greater than the height of the layered structure of the driving circuit and the organic light emitting diode.

In the above display, the height of the spacer may be greater than the height of the layered structure of i) the driving circuit, ii) the organic light emitting diode and iii) the encapsulation thin film. In the above display, the height of the spacer may be about 3 μm to about 5 μm .

[0010] In the above display, the spacer may be formed at least partially of acryl, urethane and polyimide (PI). In the above display, the spacer directly contacts the encapsulation thin film along the circumference of the encapsulation thin film. In the above display, the encapsulation thin film may include at least a pair of an inorganic film and an organic film which are alternately formed.

[0011] In the above method, the height of the spacer may be greater than the height of the layered structure of the driving circuit and the organic light emitting diodes.

In the above method, the height of the spacer may be greater than the height of the layered structure of i) the driving circuit, ii) the organic light emitting diodes and iii) the encapsulation thin film. In the above method, the height of the spacer may be about 3 μm to about 5 μm .

In the above method, the spacer may be formed at least partially of acryl, urethane and polyimide (PI).

[0012] In the above method, the encapsulation thin film contacts the spacer. In the above method, the encapsulation thin film may be formed by alternately layering at least a pair of an inorganic film and an organic film. In the above method, the spacer substantially completely surrounds the encapsulation thin film in a selected plane: In the above display, the spacer contacts the encapsu-

lation layer: In the above display, the spacer substantially completely surrounds the encapsulation layer in a selected plane: In the above display, the spacer is greater in height than the encapsulation layer, and wherein the height is defined from the surface of the substrate. In the above display, the height of the spacer may be about 3 μm to about 5 μm .

[0013] Embodiments of the invention will now be described by way of example with reference to the accompanying drawings, in which:

FIG. 1 is a top plan view of an organic light emitting diode (OLED) display according to an embodiment. FIG. 2 is a cross-sectional view of an organic light emitting diode (OLED) display according to an embodiment, which is taken along the line II-II of FIG. 1. FIG. 3 is a plan layout view of a pixel of an organic light emitting diode (OLED) display according to an embodiment.

FIG. 4 is a cross-sectional view of a pixel of an organic light emitting diode (OLED) display according to an embodiment, which is taken along the line IV-IV of FIG. 3.

FIG. 5 is a view that illustrates a contact of an organic light emitting diode (OLED) display and a mask according to an embodiment.

[0014] In general, the substrate for an OLED display is encapsulated by using metal or glass. However, if glass is used, there is a lower limit as to by how much the thickness of the entire display device can be reduced. In addition, flexible OLED displays are possible, and in view of the hardness of metal and glass, they are not suitable for such designs.

[0015] In manufacturing OLED displays, a mask is generally used to pattern OLED elements such as an organic light emitting diode and a driving circuit for supplying electrical signals to it. The mask may contact the substrate in the patterning process and particles may be introduced by the contact. The particles penetrate into the OLED display in conjunction with moisture and oxygen causing a deleterious effect to the organic light emitting diode, such that the life-span of the OLED display is reduced.

[0016] Hereinafter, embodiments will be described more fully hereinafter with reference to the accompanying drawings.

[0017] The drawings and description are to be regarded as illustrative in nature and not restrictive, and the size and thickness of each component shown in the drawings are arbitrarily shown for understanding and ease of description. In addition, it will be understood that when an element such as a layer, film is referred to as being "on" another element, it can be directly on the other element or intervening elements may also be present.

[0018] Referring to FIGS. 1 and 2, an OLED display includes a display substrate 110, an encapsulation thin film 210 and spacer 300.

[0019] The display substrate 110 is configured to dis-

play an image, a driving circuit (DC) is formed on the display substrate 110, an organic light emitting diode 70 is formed on the driving circuit (DC), thus implementing the image through it. The organic light emitting diode 70 includes the organic emission layer that is made of an organic material, and is driven by a driving circuit (DC) that includes a thin film transistor and a capacitor, thus emitting light.

[0020] The encapsulation thin film 210 is formed on the organic light emitting diode 70, thus sealing the organic light emitting diode 70. The encapsulation thin film 210 is formed so that the organic film and the inorganic film are alternately layered on the organic light emitting diode 70 to cover the organic light emitting diode 70 and driving circuit (DC).

In one embodiment, the OLED display requires a low water vapour transmission rate (WVTR) in order to ensure a sufficient life-span. In one embodiment, by sealing the organic light emitting diode 70 using the encapsulation thin film 210, it suppresses the penetration of moisture and oxygen into the organic light emitting diode 70 and driving circuit (DC), thereby implementing the low water vapour transmission rate of about 10^{-6} g/m²/day or less. The spacer 300 surrounds the circumference of the encapsulation thin film 210 on the display substrate 110. The spacer 300 is configured to support the mask in order to form the driving circuit (DC) and organic light emitting diode 70, and will be described later.

In one embodiment, the plane shape of the spacer 300 is determined according to the plane shape of the organic light emitting diode 70 and the encapsulation thin film 210. In one embodiment, since the plane shape of the organic light emitting diode 70 and the encapsulation thin film 210 is a substantially rectangular shape, the spacer 300 that surrounds the encapsulation thin film 210 has a substantially rectangular band plane shape. The encapsulation thin film 210 contacts the spacer 300. That is, the encapsulation thin film 210 contacts the spacer 300, and is formed in substantially the entire area on the display substrate 110 that is partitioned by the spacer 300. In one embodiment, the height of the spacer 300 is greater than the height of the layered structure of the driving circuit (DC) and the organic light emitting diode 70. The height of the spacer 300 may be greater than the height of the layered structure of driving circuit (DC), organic light emitting diode 70 and encapsulation thin film 210. The height of the spacer may be about 3 μm to about 5 μm , but in the case of when the height of the encapsulation thin film 210 is lower than about 3 μm , the height of the spacer may be lower than about 3 μm .

[0021] The spacer 300 may be formed of the same material as the pixel definition film that will be described later. For example, the spacer 300 may be formed of an organic material such as acryl, urethane, and polyimide (PI). As described above, in the case of when the spacer 300 is formed of the same material as the pixel definition film, while the pixel definition film is formed, the spacer 300 is formed at the same time, such that a whole process

may be simplified. However, the material of the above spacer is an example only and various modifications may be possible by those who are skilled in the art.

[0022] As described above, it is possible to more efficiently suppress the penetration of moisture and oxygen into by forming the spacer 300 that surrounds the circumference of the encapsulation thin film 210. In addition, in the manufacturing process, it is possible to lower the occurrence of defects and prolong a life-span of the OLED display by suppressing the occurrence of particles, and this will be described later.

[0023] Referring to FIG. 3 and FIG. 4, an active matrix (AM) type organic light emitting diode (OLED) display that has a 2Tr-1Cap structure which includes two thin film transistors (TFT), and one capacitor for one pixel is shown, but is not considered limiting. For example, the OLED display may be provided with three or more thin film transistors and two or more capacitors for one pixel, and a disposition of the wire may be changed to provide various structures. Here, the pixel means a minimum unit that displays an image, and the OLED display displays an image through a plurality of pixels.

[0024] The display substrate 110 includes a switching thin film transistor 10, a driving thin film transistor 20, a capacitor 80 and an organic light emitting diode (OLED) 70 for each one pixel. In addition, the display substrate 110 further includes a gate line 151 that is disposed along a predetermined direction, and a data line 171 and a common electric power line 172 that insulately cross the gate line 151.

[0025] The organic light emitting diode 70 includes the first electrode 710, the organic emission layer 720 that is formed on the first electrode 710, and the second electrode 730 that is formed on the first organic emission layer 720. In one embodiment, the pixel electrode 710 is an anode that is a hole injection electrode and the common electrode 730 is a cathode that is an electron injection electrode. The holes and electrons are injected from the pixel electrode 710 and common electrode 730 to the organic emission layer 720, and when the exciton that is combined with the injected hole and electron falls from the excited state to the bottom state, light emission is implemented.

[0026] The capacitor 80 includes the first capacitor plate 158 and the second capacitor plate 178 that are disposed between gate insulating layers 140 that act as a dielectric material. The capacitor capacitance is determined by the charge that is accumulated in the capacitor 80 and the voltage between both capacitor plates 158 and 178.

[0027] The switching thin film transistor 10 includes a switching semiconductor layer 131, switching gate electrode 152, a switching source electrode 173 and a switching drain electrode 174. The driving thin film transistor 20 includes a driving semiconductor layer 132, a driving gate electrode 155, a driving source electrode 176 and a driving drain electrode 177. The switching thin film transistor 10 is a switching element that selects the pixel that

emits light. The switching gate electrode 152 is electrically connected to the gate line 151, the switching source electrode 173 is electrically connected to the data line 171, and the switching drain electrode 174 is separated from the switching source electrode 173 and connected to the first capacitor plate 158.

[0028] The driving thin film transistor 20 applies a driving power for emitting light of the organic emission layer 720 of the organic light emitting diode 70 to the pixel electrode 710 in the selected pixel. The driving gate electrode 155 is electrically connected to the first capacitor plate 158, the source electrode 176 and the second capacitor plate 178 are electrically connected to the common power line 172, and the driving drain electrode 177 is electrically connected to the pixel electrode 710 of the organic light emitting diode 70 through a contact hole 182.

[0029] By the above structure, the switching thin film transistor 10 is operated by the gate voltage that is applied to the gate line 151 and transfers the data voltage that is applied to the data line 171 to the driving thin film transistor 20. The voltage that corresponds to a difference in the common voltage that is applied from the common power line 172 to the driving thin film transistor 20 and the data voltage that is transferred from the switching thin film transistor 10 is stored in the capacitor 80. Further, the current that corresponds to the voltage that is stored in the capacitor 80 flows through the driving thin film transistor 20 to the organic light emitting diode 70 to allow the organic light emitting diode 70 to emit light.

[0030] Referring to FIG. 4, a method of manufacturing an OLED display according to one embodiment will be described.

[0031] In one embodiment, the substrate member 111 of the display substrate 110 is formed of an insulating substrate such as glass and the like, and the buffer layer 120 is formed on the first substrate member 111. The buffer layer 120 may be formed of silicon nitride (SiNx), silicon oxide (SiOx), silicon nitroxide (SiOxNy) and the like, and the buffer layer 120 may be omitted according to the kind of substrate member 111 and the process condition. The driving semiconductor layer 132 is formed on the buffer layer 120. The driving semiconductor layer 132 includes a channel region 135 in which an impurity is not doped, and a source region 136 and a drain region 137 that are p+ doped to both ends of the channel region 135. In one embodiment, the doped ion material is a P type impurity such as boron (B).

[0032] In one embodiment, a thin film transistor that has a PMOS structure that uses the P type impurity as the driving thin film transistor 20 is used. Alternatively, a thin film transistor that has an NMOS structure or CMOS structure may be used. In addition, in one embodiment, the driving thin film transistor 20 is a polycrystalline thin film transistor that includes a polysilicon film, but the switching thin film transistor 10 not shown in FIG. 4 may be a polycrystalline thin film transistor or amorphous thin film transistor that includes an amorphous silicon film.

[0033] In one embodiment, the gate insulating layer

140 that is formed at least partially of silicon nitride or silicon oxide is formed on the driving semiconductor layer 132. The gate wire that includes the gate electrode 155 is formed on the gate insulating layer 140, and the gate wire further includes the gate line 151, the first capacitor plate 158 and the other wires. In addition, the driving gate electrode 155 is formed so as to overlap with at least a portion of the driving semiconductor layer 132, particularly the channel region 135. On the gate insulating layer 140, the interlayer insulating layer 160 that covers the driving gate electrode 155 is formed. The gate insulating layer 140 and the interlayer insulating layer 160 have holes that expose the source region 136 and drain region 137 of the driving semiconductor layer 132. In one embodiment, the interlayer insulating layer 160 is formed at least partially of silicon nitride, silicon oxide and the like likewise the gate insulating layer 140. The data wire that includes the driving source electrode 176 and driving drain electrode 177 is formed on the interlayer insulating layer 160, and the data wire further includes the data line 171, the common power line 172, the second capacitor plate 178 and the other wires. In addition, the driving source electrode 176 and driving drain electrode 177 are electrically connected to the source region 136 and drain region 137 of the driving semiconductor layer 132 through the holes that are formed on the interlayer insulating layer 160 and gate insulating layer 140.

[0034] As described above, the driving semiconductor layer 132, driving gate electrode 155, driving source electrode 176 and driving drain electrode 177 are formed, and the configuration of the driving thin film transistor 20 is not limited to the above examples but may be variously modified by those who are skilled in the art.

[0035] A planarization layer 180 that covers a data wire is formed on the interlayer insulating layer 160, and the contact hole 182 that exposes a portion of the drain electrode 177 is formed on the planarization layer 180. Meanwhile, any one of the interlayer insulating layer 160 and planarization layer 180 may be omitted.

[0036] The pixel electrode 710 of the organic light emitting diode 70 is formed on the planarization layer 180, and the pixel electrode 710 is electrically connected through the contact hole 182 to the drain electrode 177. In addition, a pixel definition film 190 that has a plurality of openings 199 that expose each pixel electrode 710 is formed on the planarization layer 180. The portion on which the pixel definition film 190 is formed substantially becomes a non-light emitting area and the portion on which the opening 199 of the pixel definition film 190 is formed substantially becomes a light emitting area. The organic emission layer 720 is formed on the pixel electrode 710, and the common electrode 730 is formed on the organic emission layer 720, thereby constituting the organic light emitting diode 70. The organic emission layer 720 is formed of a low molecular organic material or high molecular organic material, and the organic emission layer 720 may be formed of a multilayer that includes one or more of a hole injection layer (HIL), hole transport

layer (HTL), electron transport layer (ETL) and electron injection layer (EIL).

[0037] An encapsulation thin film 210 for sealing the organic light emitting diode 70 is formed on the common electrode 730. The encapsulation thin film 210 includes one pair or more of organic films 211 and 213 and inorganic films 212 and 214, and is formed by alternately layering the organic films 211 and 213 and inorganic films 212 and 214. In one embodiment, the encapsulation thin film 210 includes two pairs of organic films 211 and 213 and inorganic films 212 and 214, but it is not limited thereto.

[0038] As described above, the encapsulation thin film 210 that is obtained by alternately layering the organic films 211 and 213 and the inorganic films 212 and 214 is formed on the organic light emitting diode 70, such that the contacting of moisture or oxygen to the organic light emitting diode 70 is suppressed to prevent performance degradation.

[0039] Meanwhile, the switching thin film transistor 10, the driving thin film transistor 20, the capacitor 80 and the organic light emitting diode 70 are patterned by using the mask. In this patterning process, the mask contacts the display substrate 110 to generate particles. The particles penetrate into the OLED display to deteriorate the performance of the organic light emitting diode, and may be a cause of the occurrence of defects of the OLED display and life-span deterioration thereof. Accordingly, in one embodiment, as described above, the occurrence of defects of the OLED display and the life-span deterioration thereof are suppressed by forming the spacer 300 on the display substrate 110.

[0040] FIG. 5 is a view that illustrates a contact of an OLED display and a mask according to an embodiment, and a manufacturing method of the OLED display will be described with reference to it.

[0041] In one embodiment, the OLED display is manufactured by preparing a display substrate 110, forming a spacer 300 along an edge of the display substrate 110, forming a driving circuit (DC) and organic light emitting diode 70, and forming an encapsulation thin film 210 to cover the driving circuit (DC) and organic light emitting diode 70. As shown in FIG. 5, the driving circuit (DC) and organic light emitting diode 70 are formed in an internal area of the areas that are partitioned by the spacer 300 on the display substrate 110, and are formed through deposition and patterning processes using the mask 400.

[0042] As described above, if the mask 400 contacts the display substrate 110, the particles are generated and moisture and oxygen may easily penetrate into the OLED device, as a result, the performance of the OLED display may be deteriorated and defects may be generated. However, according to one embodiment, the spacer 300 is formed on the display substrate 110, the mask 400 is disposed to be supported on the spacer 300, thereby suppressing the above problems.

[0043] In one embodiment, since the driving circuit (DC) and organic light emitting diode 70 are formed by

using the mask 400, the height of the spacer 300 that supports the mask 400 is greater than the height of the layered structure of the driving circuit (DC) and organic light emitting diode 70.

[0044] In addition, the height of the spacer 300 may be greater than the height of the layered structure of the driving circuit (DC), organic light emitting diode 70 and encapsulation thin film 210. In the area that is partitioned by the spacer 300, the encapsulation thin film 210 is layered to cover the driving circuit (DC) and organic light emitting diode 70. If the height of the spacer 300 is greater than the height of the layered structure of the driving circuit (DC), organic light emitting diode 70 and encapsulation thin film 210, in the area that is partitioned by the spacer 300, the process for layering the encapsulation thin film 210 may be easily performed.

[0045] In one embodiment, the encapsulation thin film 210 is formed by alternately layering at least a pair of inorganic film and organic film. In addition, since the encapsulation thin film 210 is layered in the area that is partitioned by the spacer 300 on the organic light emitting diode 70, it directly contacts the spacer 300.

[0046] By this process, the organic light emitting diode 70 may be sealed by the encapsulation thin film 210 and an external boundary may be formed by the spacer 300. Accordingly, it is possible to easily suppress the penetration of moisture and oxygen into the OLED display and to suppress the occurrence of particles in the process.

[0047] According to at least one of the disclosed embodiments, it is possible to prevent performance degradation of an organic light emitting diode (OLED) display by suppressing penetration of moisture and oxygen into the display.

[0048] In addition, in the process of manufacturing the OLED display, it is possible to suppress the occurrence of defects of the display and prolong life-span.

[0049] While this disclosure has been described in connection with certain embodiments, it is to be understood that the disclosed embodiments are not limiting. Thus, the appended claims are intended to cover various modifications and equivalent arrangements.

Claims

1. An organic light emitting diode (OLED) display, comprising:

a substrate (110); a plurality of organic light emitting diodes (70) formed on a surface of the substrate;

an encapsulation layer (210) formed on the plurality of organic light emitting diodes (70); **characterised in that** a spacer (300) is formed on the substrate (110) and surrounds the encapsulation layer (210) and the plurality of organic light emitting diodes (70), wherein the spacer (300) directly contacts the encapsulation layer (210)

along the perimeter of the encapsulation layer (210), wherein a height of the spacer (300) is greater than a height of the encapsulation layer (210), wherein the height is defined from the surface of the substrate.

2. The display of claim 1, further comprising a driving circuit formed on the substrate, wherein the plurality of organic light emitting diodes (70) are electrically connected to the driving circuit and the encapsulation layer (210) is formed on the driving circuit and the plurality of organic light emitting diodes (70).
3. The display of claim 2, wherein the plurality of organic light emitting diode (70) are formed on the driving circuit in a layered structure, the height of the spacer (300) being greater than the height of the layered structure.
4. The display of claim 3, wherein the height of the spacer (300) is greater than the height of the layered structure of i) the driving circuit, ii) the plurality of organic light emitting diodes and iii) the encapsulation layer (210).
5. The display of any one of the preceding claims, wherein the height of the spacer (300) is 3 μm to 5 μm .
6. The display of any one of the preceding claims, wherein the spacer (300) comprises at least one of acryl, urethane and polyimide (PI).
7. The display of any one of the preceding claims, wherein the encapsulation layer (210) comprises an encapsulation thin film.
8. The display of claim 7, wherein the encapsulation thin film includes at least a pair of an inorganic film and an organic film which are alternately formed.
9. A method of manufacturing an organic light emitting diode (OLED) display, comprising:

preparing a substrate (110);
forming a spacer (300) on the substrate (110) along an edge of the substrate;
forming a plurality of organic light emitting diodes (70) on the substrate (110) to be surrounded by the spacer (300); and
forming an encapsulation layer (210) so as to cover the plurality of organic light emitting diodes (70), wherein the mask (400) that is used in the forming of the plurality of organic light emitting diodes (70) is supported by and contacts the spacer (300); and
wherein, in the organic light emitting diode (OLED) display, the spacer (300) directly con-

tacts the encapsulation layer (210) along the perimeter of the encapsulation layer (210) and surrounds the encapsulation layer (210) and the plurality of organic light emitting diodes (70), wherein a height of the spacer (300) is greater than a height of the encapsulation layer (210), wherein the height is defined from the surface of the substrate.

10. The method of claim 9, further comprising:

forming a driving circuit on the substrate; and forming the plurality of organic light emitting diodes on the driving circuit.

11. The method of claim 9 or 10, further comprising forming the encapsulation layer (210) so that the encapsulation layer (210) contacts the surface of the substrate (300).

12. The method of any one of claims 9 to 11, wherein the encapsulation layer (210) is formed by alternately layering at least a pair of an inorganic film and an organic film.

Patentansprüche

1. Organische Leuchtdioden-(OLED-)Anzeige, umfassend:

ein Substrat (110);
eine Mehrzahl von auf einer Oberfläche des Substrats ausgebildeten organischen Leuchtdioden (70);
eine auf der Mehrzahl von organischen Leuchtdioden (70) ausgebildete Verkapselungsschicht (210); **dadurch gekennzeichnet, dass**
auf dem Substrat (110) ein Abstandhalter (300) ausgebildet ist und die Verkapselungsschicht (210) und die Mehrzahl von organischen Leuchtdioden (70) umgibt, wobei der Abstandhalter (300) die Verkapselungsschicht (210) entlang des Umfangs der Verkapselungsschicht (210) unmittelbar berührt, wobei eine Höhe des Abstandhalters (300) größer ist als eine Höhe der Verkapselungsschicht (210), wobei die Höhe ab der Oberfläche des Substrats definiert ist.

2. Anzeige nach Anspruch 1, weiterhin umfassend einen auf dem Substrat ausgebildeten Treiberkreis, wobei die Mehrzahl von organischen Leuchtdioden (70) mit dem Treiberkreis elektrisch verbunden ist und die Verkapselungsschicht (210) auf dem Treiberkreis und der Mehrzahl von organischen Leuchtdioden (70) ausgebildet ist.

3. Anzeige nach Anspruch 2, wobei die Mehrzahl von

organischen Leuchtdioden (70) auf dem Treiberkreis in einer geschichteten Struktur ausgebildet ist, wobei die Höhe des Abstandhalters (300) größer ist als die Höhe der geschichteten Struktur.

4. Anzeige nach Anspruch 3, wobei die Höhe des Abstandhalters (300) größer ist als die Höhe der geschichteten Struktur i) des Treiberkreises, ii) der Mehrzahl von organischen Leuchtdioden und iii) der Verkapselungsschicht (210).

5. Anzeige nach einem der vorangehenden Ansprüche, wobei die Höhe des Abstandhalters (300) 3 µm bis 5 µm beträgt.

6. Anzeige nach einem der vorangehenden Ansprüche, wobei der Abstandhalter (300) zumindest eines von Acryl, Urethan und Polyimid (PI) umfasst.

7. Anzeige nach einem der vorangehenden Ansprüche, wobei die Verkapselungsschicht (210) eine Dünnschichtverkapselung umfasst.

8. Anzeige nach Anspruch 7, wobei die Dünnschichtverkapselung zumindest ein Paar eines anorganischen Films und eines organischen Films einschließt, die abwechselnd ausgebildet sind.

9. Verfahren zur Herstellung einer organischen Leuchtdioden-(OLED-)Anzeige, umfassend:

Vorbereiten eines Substrats (110);
Ausbilden eines Abstandhalters (300) auf dem Substrat (110) entlang einer Kante des Substrats;
Ausbilden einer Mehrzahl von von dem Abstandhalter (300) zu umgebenden organischen Leuchtdioden (70) auf dem Substrat (110); und
Ausbilden einer Verkapselungsschicht (210), um die Mehrzahl von organischen Leuchtdioden (70) abzudecken,
wobei die bei der Ausbildung der Mehrzahl von organischen Leuchtdioden (70) verwendete Maske von dem Abstandhalter (300) getragen wird und diesen berührt; und
wobei in der organischen Leuchtdioden-(OLED-)Anzeige der Abstandhalter (300) die Verkapselungsschicht (210) entlang des Umfangs der Verkapselungsschicht (210) unmittelbar berührt und die Verkapselungsschicht (210) und die Mehrzahl von organischen Leuchtdioden (70) umgibt, wobei eine Höhe des Abstandhalters (300) größer ist als eine Höhe der Verkapselungsschicht (210), wobei die Höhe ab der Oberfläche des Substrats definiert ist.

10. Verfahren nach Anspruch 9, weiterhin umfassend:

Ausbilden eines Treiberkreises auf dem Substrat; und
Ausbilden der Mehrzahl von organischen Leuchtdioden auf dem Treiberkreis.

11. Verfahren nach Anspruch 9 oder 10, weiterhin umfassend Ausbilden der Verkapselungsschicht (210) so, dass die Verkapselungsschicht (210) die Oberfläche des Substrats (300) berührt.
12. Verfahren nach einem der Ansprüche 9 bis 11, wobei die Verkapselungsschicht (210) ausgebildet ist durch abwechselndes Schichten zumindest eines Paares eines anorganischen Films und eines organischen Films.

Revendications

1. Afficheur à diodes électroluminescentes organiques (OLED), comprenant :

un substrat (110) ;
une pluralité de diodes électroluminescentes organiques (70) formées sur une surface du substrat ;
une couche d'encapsulation (210) formée sur la pluralité de diodes électroluminescentes organiques (70) ;

caractérisé en ce que

un élément d'espacement (300) est formé sur le substrat (110) et entoure la couche d'encapsulation (210) et la pluralité de diodes électroluminescentes organiques (70), dans lequel l'élément d'espacement (300) est directement en contact avec la couche d'encapsulation (210) le long du périmètre de la couche d'encapsulation (210), dans lequel une hauteur de l'élément d'espacement (300) est supérieure à une hauteur de la couche d'encapsulation (210), dans lequel la hauteur est définie à partir de la surface du substrat.

2. Afficheur selon la revendication 1, comprenant en outre un circuit de commande formé sur le substrat, dans lequel la pluralité de diodes électroluminescentes organiques (70) sont connectées électriquement au circuit de commande et la couche d'encapsulation (210) est formée sur le circuit de commande et la pluralité de diodes électroluminescentes organiques (70).
3. Afficheur selon la revendication 2, dans lequel la pluralité de diodes électroluminescentes organiques (70) sont formées sur le circuit de commande en une structure en couches, la hauteur de l'élément d'espacement (300) étant supérieure à la hauteur de la structure en couches.

4. Afficheur selon la revendication 3, dans lequel la hauteur de l'élément d'espacement (300) est supérieure à la hauteur de la structure en couches constituée i) du circuit de commande, ii) de la pluralité de diodes électroluminescentes organiques et iii) de la couche d'encapsulation (210).

5. Afficheur selon l'une quelconque des revendications précédentes, dans lequel la hauteur de l'élément d'espacement (300) est de 3 μm à 5 μm .

6. Afficheur selon l'une quelconque des revendications précédentes, dans lequel l'élément d'espacement (300) comprend au moins l'un de l'acrylique, de l'uréthane et du polyimide (PI).

7. Afficheur selon l'une quelconque des revendications précédentes, dans lequel la couche d'encapsulation (210) comprend un film mince d'encapsulation.

8. Afficheur selon la revendication 7, dans lequel le film mince d'encapsulation comprend au moins une paire d'un film inorganique et d'un film organique qui sont formés alternativement.

9. Procédé de fabrication d'un afficheur à diodes électroluminescentes organiques (OLED), comprenant :

la préparation d'un substrat (110) ;
la formation d'un élément d'espacement (300) sur le substrat (110) le long d'un bord du substrat ;
la formation d'une pluralité de diodes électroluminescentes organiques (70) sur le substrat (110) de manière à ce qu'elles soient entourées par l'élément d'espacement (300) ; et
la formation d'une couche d'encapsulation (210) de manière à recouvrir la pluralité de diodes électroluminescentes organiques (70), dans lequel le masque (400) qui est utilisé dans la formation de la pluralité de diodes électroluminescentes organiques (70) est supporté par et est en contact avec l'élément d'espacement (300) ; et
dans lequel, dans l'afficheur à diodes électroluminescentes organiques (OLED), l'élément d'espacement (300) est directement en contact avec la couche d'encapsulation (210) le long du périmètre de la couche d'encapsulation (210) et entoure la couche d'encapsulation (210) et la pluralité de diodes électroluminescentes organiques (70),
dans lequel une hauteur de l'élément d'espacement (300) est supérieure à une hauteur de la couche d'encapsulation (210), dans lequel la hauteur est définie à partir de la surface du substrat.

10. Procédé selon la revendication 9, comprenant en outre :

la formation d'un circuit de commande sur le substrat ; et
la formation de la pluralité de diodes électroluminescentes organiques sur le circuit de commande.

5

11. Procédé selon la revendication 9 ou 10, comprenant en outre la formation de la couche d'encapsulation (210) de sorte que la couche d'encapsulation (210) soit en contact avec la surface du substrat (300).

10

12. Procédé selon l'une quelconque des revendications 9 à 11, dans lequel la couche d'encapsulation (210) est formée en déposant en couches alternativement au moins une paire d'un film inorganique et d'un film organique.

15

20

25

30

35

40

45

50

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4





FIG. 5



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 2008129194 A [0003]
- JP 2009193914 B [0004]
- US 2009015148 A [0005]

专利名称(译)	有机发光二极管显示器及其制造方法		
公开(公告)号	EP2390939B1	公开(公告)日	2017-11-01
申请号	EP2011159340	申请日	2011-03-23
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	KANG DONG HUN SUH MIN CHUL HAN DONG WON KWACK JIN HO SHIN DAE BEOM KIM HYO JIN		
发明人	KANG, DONG-HUN SUH, MIN-CHUL HAN, DONG-WON KWACK, JIN-HO SHIN, DAE-BEOM KIM, HYO-JIN		
IPC分类号	H01L51/52 H01L51/56		
CPC分类号	H01L51/56 H01L27/3244 H01L51/0011 H01L51/5253		
优先权	1020100050488 2010-05-28 KR		
其他公开文献	EP2390939A2 EP2390939A3		
外部链接	Espacenet		

摘要(译)

公开了一种有机发光二极管 (OLED) 显示器。在一个实施例中, 显示器包括i) 基板, ii) 形成在基板 (110) 上的驱动电路 (DC), iii) 形成在基板 (110) 上并且电连接到基板 (110) 的有机发光二极管 (70)。驱动电路 (DC), iv) 形成在驱动电路 (DC) 和有机发光二极管 (70) 上的封装薄膜 (210) 和形成在基板 (110) 上并围绕封装的间隔物 (300) 薄膜 (210)。

FIG. 1




FIG. 2

