



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
31.12.2014 Bulletin 2015/01

(51) Int Cl.:
H01L 51/50 ^(2006.01) **H01L 27/32** ^(2006.01)
G07F 7/08 ^(2006.01) **G09G 3/32** ^(2006.01)
G06K 19/06 ^(2006.01)

(21) Application number: **14162722.4**

(22) Date of filing: **31.03.2014**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME

(71) Applicant: **Samsung Display Co., Ltd.**
Gyeonggi-Do (KR)

(72) Inventor: **Seo, Hae-Kwan**
Gyeonggi-Do (KR)

(74) Representative: **Taor, Simon Edward William**
Venner Shipley LLP
200 Aldersgate
London EC1A 4HD (GB)


(30) Priority: **25.06.2013 KR 20130073307**

(54) **Organic Light-Emitting Device for Outputting Image and Security Pattern, and Display Panel Including the Same**

(57) In an aspect, an organic light-emitting device includes a first electrode (131), a second electrode (139) facing the first electrode, and an organic layer (132) between the first electrode and the second electrode,

wherein the organic layer includes a light-emitting layer (135) which emits light in a visible spectrum and light in a non-visible spectrum.

FIG. 1



Description

[0001] This disclosure relates to an organic light-emitting display panel for outputting an image including a security signal, and an identification card including the display panel.

[0002] Electronic identifications, such as an electronic passport in which the appearance of a person is displayed as a digital image instead of a photograph by using an organic light-emitting display (OLED) panel have been developed. Counterfeiting or tampering with electronic identifications, such as an electronic passport, may be possible by changing an OLED panel in a manner similar counterfeiting or tampering with a typical identification card by changing a photo. Therefore, security techniques for preventing the counterfeiting or tampering with electronic identifications have been investigated.

[0003] Some embodiments provide an organic light-emitting device that may prevent counterfeiting or tampering with a display panel.

[0004] Some embodiments provide a display panel that may prevent counterfeiting or tampering.

[0005] Some embodiments provide an electronic identification, including the display panel that may prevent counterfeiting or tampering.

[0006] According to an aspect of the present embodiments, there is provided an organic light-emitting device including: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer includes a light-emitting layer which emits light in a visible spectrum and light in a non-visible spectrum.

In some embodiments, the light-emitting layer may include a first material which emits light in the visible spectrum and light in the non-visible spectrum. In this case, the first material may include AlInGa_N, InGa_N, AlP, AlAs, GaP, InN, AlInGaP, or AlGaAs.

[0007] In some embodiments, the light-emitting layer may include a first light-emitting layer emitting light in the visible spectrum and a second light-emitting layer emitting light in the non-visible spectrum. In some embodiments, the second light-emitting layer may include a second material which emits light in an infrared region. For example, the second material may include tris(acetylacetonato)(1,10-phenanthroline)erbium, tris(acetylacetonato)(1,10-phenanthroline)neodymium, tris(acetylacetonato)(1,10-phenanthroline)holmium, GaAsP, InP, or GaAs. In some embodiments, the second light-emitting layer may include a third material which emits light in an ultraviolet region. For example, the third material may include N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine (TPD), N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine (alpha-NPD), N,N'-bis(naphthalen-1-yl)-N,N'-bis(phenyl)benzidine (alpha-NPB), N,N'-di(naphthalen-2-yl)-N,N'-diphenyl-benzidine (beta-NPB), 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), AlGa_N, or AlN.

[0008] In some embodiments, the second light-emitting

layer may act as a hole transport layer or an electron transport layer.

[0009] In some embodiments, the organic layer may further include at least one of a hole injection layer, a hole transport layer, an electron transport layer, or an electron injection layer.

[0010] In some embodiments, the first electrode may be an anode and the second electrode may be a cathode, or the first electrode may be a cathode and the second electrode may be an anode.

[0011] According to another aspect of the present embodiments, there is provided a display panel including: a first substrate; a thin film transistor on the first substrate; an insulating layer on the thin film transistor; the organic light-emitting device disposed on the insulating layer and electrically connected to the thin film transistor; and a second substrate on the organic light-emitting device.

[0012] In some embodiments, at least one of the first substrate and the second substrate may be transparent.

[0013] In some embodiments, a digital image may be generated by light in the visible spectrum and a digital security pattern may be generated by light in the non-visible spectrum.

[0014] In some embodiments, the digital image and the digital security pattern may be generated with a time difference.

[0015] In some embodiments, the digital image may be formed of a plurality of time-sequential digital image frames, and the digital security pattern may be generated at least any one time between the plurality of digital image frames or at a predetermined time before or after beginning of the plurality of digital image frames.

[0016] In some embodiments, the digital security pattern may be formed of a plurality of digital security pattern frames, and the plurality of digital security pattern frames may be generated at regular intervals between the plurality of digital image frames. In this case, the plurality of digital security pattern frames of the digital security pattern may be the same or may be different.

[0017] In some embodiments, the digital security pattern may be generated only during an operation of detecting the digital security pattern without generation of the digital image.

[0018] In some embodiments, the digital security pattern may be a barcode or a quick response (QR) code.

[0019] In some embodiments, a plurality of the thin film transistors and the organic light-emitting devices may be arranged to generate a full color image.

[0020] Some embodiments provide a method of electronic identification with a display panel as disclosed and described herein including: generating a digital image; and generating a digital security pattern, wherein the digital image is generated by the light in the visible spectrum and a digital security pattern is generated by the light in the non-visible spectrum.

[0021] In some embodiments, the digital image and the digital security pattern are generated with a time difference.

[0022] In some embodiments, the digital image is formed of a plurality of digital image frames that are time-sequential, and the digital security pattern is generated at least any one time between the plurality of digital image frames or at a predetermined time before or after a beginning of the plurality of digital image frames.

[0023] In some embodiments, the digital security pattern is formed of a plurality of digital security pattern frames, and the plurality of digital security pattern frames are generated at regular intervals between the plurality of digital image frames.

[0024] In some embodiments, the plurality of digital security pattern frames of the digital security pattern are same. In some embodiments, the digital security pattern is generated only during an operation of detecting the digital security pattern without generation of the digital image.

[0025] In some embodiments, the digital security pattern is a barcode or a quick response (QR) code.

[0026] In some embodiments, a plurality of thin film transistors and organic light-emitting devices are arranged to generate a full color image.

[0027] According to an aspect of the invention, there is provided an organic light-emitting device as set out in claim 1. Preferred features of this aspect are set out in claims 2 to 8.

[0028] According to an aspect of the invention, there is provided a display device as set out in claim 9. Preferred features of this aspect are set out in claims 9 to 15.

[0029] The above and other features and advantages of the present embodiments will become more apparent by describing in detail exemplary embodiments thereof with reference to the attached drawings in which:

FIG. 1 is a schematic view illustrating an organic light-emitting device, according to an embodiment;
FIG. 2 is a schematic view illustrating an organic light-emitting device, according to another embodiment; and
FIG. 3 is a cross-sectional view schematically illustrating a sub-pixel of a display panel, according to an embodiment.

[0030] Embodiments of the present invention will now be described more fully with reference to the accompanying drawings, in which exemplary embodiments are shown. The invention may, however, be embodied in many different forms and should not be construed as being limited to the embodiments set forth herein. In the drawings, the thicknesses of layers and regions are exaggerated for clarity. Like reference numerals refer to like elements throughout.

[0031] FIG. 1 is a schematic view illustrating an organic light-emitting device, according to an embodiment.

In some embodiments, an organic light-emitting device 130 includes a first electrode 131, a second electrode 139 facing the first electrode 131, and an organic layer 132 disposed between the first electrode 131 and the

second electrode 139 as shown in FIG. 1.

[0032] In some embodiments, the first electrode 131 may be an anode, and in this case, the first electrode 131 may be selected from high work function materials so as to facilitate hole injection. In some embodiments, the first electrode 131 may be a transmissive electrode or a reflective electrode. In some embodiments, the first electrode 131 may be formed of indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), Al-doped zinc oxide (AZO), indium oxide (In₂O₃), or tin oxide (SnO₂). Also, the first electrode 131 may be formed as a reflective electrode by using magnesium (Mg), silver (Ag), aluminum (Al), Al: lithium (Li), calcium (Ca), Ag: ITO, Mg: In, or Mg: Ag. The first electrode 131 may have a single-layer structure or a multilayer structure of two or more layers. For example, the first electrode 131 may have a three-layer structure of ITO/Ag/ITO. However, the first electrode 131 is not limited thereto.

[0033] In some embodiments, the organic layer 132 in the organic light-emitting device 130 may include at least an emissive layer (EML), and may further include layers for hole injection and transport, electron injection and transport, and charge balance, in addition to the EML.

[0034] In some embodiments, the organic layer 132 may include a hole injection layer (HIL) 133, a hole transport layer (HTL) 134, a light-emitting layer 135, an electron transport layer (ETL) 136, and an electron injection layer (EIL) 137.

[0035] In some embodiments, the HIL 133 may use a phthalocyanine compound, such as copper phthalocyanine, N,N'-diphenyl-N,N'-bis-[4-(phenyl-m-tolyl-amino)-phenyl]-biphenyl-4,4'-diamine (DNTPD), 4,4',4"-tris-(3-methylphenylphenylamino)triphenylamine (m-MTDATA), 4,4',4"-tris(N,N-diphenylamino)triphenylamine (TDATA), 4,4',4"-tris(N,N'-(2-naphthyl)-N-phenylamino)-triphenylamine (2T-NATA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), polyaniline/camphorsulfonic acid (PANI/CSA), or polyaniline/poly(4-styrenesulfonate) (PANI/PSS). However, the embodiments of the present invention are not limited thereto.

[0036] In some embodiments, the HTL 134 may use carbazole derivatives, such as N-phenylcarbazole and polyvinylcarbazole, triphenylamine-based materials, such as N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1-biphenyl]-4,4'-diamine (TPD), N,N'-di(1-naphthyl)-N,N'-diphenylbenzidine (NPB), or 4,4',4"-tris(N-carbazolyl)triphenylamine (TCTA). However, embodiments of the present invention are not limited thereto.

[0037] In some embodiments, the light-emitting layer 135 may include a material that may simultaneously emit light in a visible spectrum and light in a non-visible spectrum. For example, the light-emitting layer 135 may include a material that may emit light in an infrared or ultraviolet region of the non-visible spectrum as well as light in the visible spectrum, such as red, green, blue, white, purple, or orange light. In some embodiments, the

light-emitting layer 135 may include a material, such as AlInGaN, InGaN, AlP, AlAs, GaP, InN, AlInGaP, and AlGaAs.

[0038] In some embodiments, the light-emitting layer 135 may emit both of the light in the visible spectrum and the light in the non-visible spectrum. For example, the light in the visible spectrum may be used to generate a digital image, and the light in the non-visible spectrum may be used to generate a digital security pattern. In some embodiments, the digital security pattern may be used to determine the presence of counterfeiting or tampering since the digital security pattern may be detected by a detection device. In some embodiments, the digital security pattern may be a barcode or a quick response (QR) code. However, the digital security pattern is not limited thereto.

[0039] In some embodiments, the ETL 136 may use a known material, such as tris(8-quinolinolate)aluminum (Alq3), 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), 4,7-diphenyl-1,10-phenanthroline (Bphen), 3-(4-biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole (TAZ), 4-(naphthalen-1-yl)-3,5-diphenyl-4H-1,2,4-triazole (NTAZ), 2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole (tBu-PBD), bis(2-methyl-8-quinolinolato-N1,O8)-(1,1'-biphenyl-4-olato)aluminum (BALq), beryllium bis(benzoquinolin-10-olate) (Bebq2), and 9,10-di(naphthalene-2-yl)anthracene (ADN). However, the embodiments of the present invention are not limited thereto.

[0040] In some embodiments, the EIL 137 may use, for example, any material known as a material of an electron injection layer, such as LiF, NaCl, CsF, Li₂O, and BaO. However, embodiments of the present invention are not limited thereto.

[0041] In some embodiments, the second electrode 139 may be a cathode, and in this case, a low work function metal, an alloy, an electrically conductive compound, or a mixture of two or more thereof may be used as the second electrode 139. For example, the second electrode 139 may be included as a transparent electrode or a reflective electrode. In a case where the second electrode 139 is included as the transparent electrode, the second electrode 139 may include a thin film formed of Li, Ca, Al, Mg, Mg-In, Mg-Ag, LiF-Al, LiF-Ca, or a compound thereof, and an auxiliary electrode formed of a transparent conductive material, such as ITO, IZO, ZnO, or In₂O₃, that is disposed on the thin film. In contrast, in a case where the second electrode 139 is included as the reflective electrode, the second electrode 139, for example, may be formed of Li, Ca, Al, Mg, Mg-In, Mg-Ag, LiF-Al, LiF-Ca, or a compound thereof.

[0042] FIG. 2 is a schematic view illustrating an organic light-emitting device, according to another embodiment.

[0043] In some embodiments, an organic light-emitting device 230 may include a first electrode 131, a second electrode 139 facing the first electrode 131, and an organic layer 232 disposed between the first electrode 131 and the second electrode 139 as shown in FIG. 1. In

some embodiments, the organic layer 232 includes an HIL 133, an HTL 134, a light-emitting layer 235, an ETL 136, and an EIL 137.

[0044] In some embodiments, the organic light-emitting device 230 may be different from the organic light-emitting device 130 in that the light-emitting layer 235 is composed of a first light-emitting layer 235a emitting light in the visible spectrum and a second light-emitting layer 235b emitting light in the non-visible spectrum. Although the second light-emitting layer 235b is disposed on the first light-emitting layer 235a in FIG. 2, the sequence of disposing the first light-emitting layer 235a and the second light-emitting layer 235b may be reversed. In some embodiments, another layer may be disposed between the first light-emitting layer 235a and the second light-emitting layer 235b. For example, in a case where one of the first light-emitting layer 235a and the second light-emitting layer 235b is a layer formed of an inorganic material, the other is a layer formed of an organic material, and the layer formed of the inorganic material is formed later, a buffer layer (not shown) for protecting the layer formed of the organic material during the formation of the layer formed of the inorganic material may be further included between the first light-emitting layer 235a and the second light-emitting layer 235b.

In some embodiments, the first light-emitting layer 235a may use a known single light-emitting material or known host and dopant materials as a material emitting light in the visible spectrum

[0045] In some embodiments, one or more known materials may be included as materials for emitting light having a red, green, or blue wavelength where the host and the dopant materials are used.

[0046] In some embodiments, the host of the first light-emitting layer 235a may use Alq3, 4,4'-bis(N-cabazoly-1,1'-biphenyl) (CBP), poly(n-vinylcabazole) (PVK), ADN, 4,4',4"-tris(carbazol-9-yl)-triphenylamine (TCTA), 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di(naphth-2-yl)anthracene (TBADN), distyrylarylene (DSA), 2,7-bis(9,9-diethylfluoren-2-yl)-9,9-diethylfluorene (E3), or 4,4'-bis(9-carbazolyl)-2,2'-dimethyl-biphenyl (CDBP). However, the embodiments of the present invention are not limited thereto.

[0047] In some embodiments, the dopant of the first light-emitting layer 235a may use at least one of a known fluorescent dopant or phosphorescent dopant. In some embodiments, the phosphorescent dopant may be iridium (Ir), platinum (Pt), osmium (Os), rhenium (Re), titanium (Ti), zirconium (Zr), hafnium (Hf), or an organic metal complex including a combination of two or more thereof. However, the embodiments of the present invention are not limited thereto.

[0048] In some embodiments, a known red dopant may be used such as Pt(II) octaethylporphine (PtOEP), tris(2-phenylisoquinoline)iridium (Ir(piq)₃), or bis(2-(2'-benzothienyl)-pyridinato-N,C3')iridium(acetylacetonate) (Btp2Ir(acac)). However, embodiments of the present in-

vention are not limited thereto.

[0049] In some embodiments, a known green dopant may be used such as Tris(2-phenylpyridine)iridium ($\text{Ir}(\text{ppy})_3$), bis(2-phenylpyridine)(acetylacetonato)iridium(III) ($\text{Ir}(\text{ppy})_2(\text{acac})$), tris(2-(4-tolyl)phenylpyridine)iridium ($\text{Ir}(\text{mpp})_3$), or 10-(2-benzothiazolyl)-1,1,7,7-tetramethyl-2,3,6,7-tetrahydro-1H,5H,11H-[1]benzopyrano[6,7,8-ij]-quinolizin-11-one (C545T). However, embodiments of the present invention are not limited thereto.

[0050] In some embodiments, a known blue dopant may be used such as Bis[3,5-difluoro-2-(2-pyridyl)phenyl](picolinato)iridium(III) (F_2lrpic), (F_2ppy) $_2\text{Ir}(\text{tmd})$, $\text{Ir}(\text{dfppz})_3$, 4,4'-bis(2,2'-diphenylethen-1-yl)biphenyl (DPV-Bi), 4,4'-bis[4-(diphenylamino)styryl]biphenyl (DPAVBi), or 2,5,8,11-tetra-tert-butyl perylene (TBPe). However, the embodiments of the present invention are not limited thereto.

[0051] In some embodiments, light in the non-visible spectrum of the second light-emitting layer 235b may include light in the infrared region or light in the ultraviolet region. In some embodiments, a material for emitting the light in the infrared region may include tris(acetylacetonato)(1,10-phenanthroline)erbium, tris(acetylacetonato)(1,10-phenanthroline)neodymium, tris(acetylacetonato)(1,10-phenanthroline)holmium, GaAsP, InP, GaAs, AlGaIn, or AlN.

[0052] In some embodiments, a material for emitting the light in the ultraviolet region may include N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine (TPD), N,N'-di(naphthalene-1-yl)-N,N'-diphenyl-benzidine (α -NPD), N,N'-bis(naphthalene-1-yl)-N,N'-bis(phenyl)benzidine (α -NPB), N,N'-di(naphthalene-2-yl)-N,N'-diphenyl-benzidine (β -NPB), 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), AlGaIn, or AlN.

[0053] In some embodiments, the second light-emitting layer 235b may not only selectively act as a light-emitting layer of the light in the non-visible spectrum, but may also act as an HTL or an ETL. In some embodiments, the second light-emitting layer 235b including tris(acetylacetonato)(1,10-phenanthroline)erbium, tris(acetylacetonato)(1,10-phenanthroline)neodymium, or tris(acetylacetonato)(1,10-phenanthroline)holmium may simultaneously act as an ETL.

[0054] In some embodiments, the light in the visible spectrum emitted from the first light-emitting layer 235a may generate a digital image, and the light in the non-visible spectrum emitted from the second light-emitting layer 235b may generate a digital security pattern. In some embodiments, the digital security pattern may be used to determine the presence of counterfeiting or tampering since the digital security pattern may be detected by a detection device. In some embodiments, the digital security pattern may be a barcode or a QR code. However, the digital security pattern is not limited thereto.

[0055] FIG. 3 is a cross-sectional view schematically illustrating a sub-pixel of a display panel, according to an embodiment. In some embodiments, a pixel unit of the

display panel may include a plurality of pixels each formed of red, green, and blue sub-pixels. In some embodiments, the sub-pixels include the above-described organic light-emitting device, and thus, may further emit light in the non-visible spectrum in addition to red, green, and blue light. In some embodiments, the colors of emitted light are not limited to red, green, and blue, and may further include white, purple, or orange.

[0056] It is described above that the light emission in the visible spectrum and the light emission in the non-visible spectrum are performed in the same layer or in different layers in a stack structure. However, a sub-pixel selectively emitting light in the visible spectrum and a sub-pixel selectively emitting light in the non-visible spectrum may be separately present in the device. For example, a sub-pixel formed of an organic material that emits light in the visible spectrum and a sub-pixel formed of an inorganic material light that emits light in the non-visible spectrum may both be present in the device.

[0057] Referring to FIG. 3, a pixel unit 100 of the display panel of the present invention includes a lower substrate 101, an upper substrate 150, a thin film transistor (TFT) 120 between the lower substrate 101 and the upper substrate 150, an organic light-emitting device 130 electrically connected to the TFT 120.

[0058] In some embodiments, the lower substrate 101 may use a substrate formed of various materials, such as glass, plastic, silicon, or metal. In a case where the digital image is generated through the lower substrate 101, a transparent glass substrate or plastic substrate may be used as the lower substrate 101. In this case, infrared or ultraviolet light may also transmit through the lower substrate 101.

[0059] In some embodiments, a buffer layer 111 for preventing the diffusion of impurity atoms or ions from the lower substrate 101 into the TFT or an organic layer disposed thereon, for preventing the penetration of moisture, and for planarizing a surface of the lower substrate 101 may be formed on the surface of the lower substrate 101. In some embodiments, a buffer layer 111 may be formed on the surface of the lower substrate 101. In some embodiments, a buffer layer 111 may prevent the diffusion of impurity atoms or ions from the lower substrate 101 into the TFT. In some embodiments, a buffer layer 111 may prevent the penetration of moisture into the TFT. In some embodiments, a buffer layer 111 may planarize a surface of the lower substrate 101. In some embodiments, the buffer layer 111 may be formed of an inorganic material, such as silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, titanium oxide, and titanium nitride, an organic material, such as polyimide, polyester, and acryl, or a stack thereof. In some embodiments, the buffer layer 111 may be omitted if necessary.

[0060] In some embodiments, the TFT 120 as a driving circuit may be formed on the buffer layer 111. In some embodiments, the TFT 120 includes an active layer 121, a gate dielectric layer 123, a gate electrode 125, and

source and drain electrodes 127.

[0061] In some embodiments, the active layer 121 on the buffer layer 111 may be formed of an inorganic semiconductor material, such as amorphous silicon, polysilicon, and an oxide semiconductor, or an organic semiconductor material. For example, the oxide semiconductor may include an oxide of a material selected from the group consisting of Group 12, 13, and 14 metal elements, such as Zn, In, gallium (Ga), Sn, cadmium (Cd), germanium (Ge), and Hf, and a combination thereof. For example, the semiconductor active layer 121 may include $[(\text{In}_2\text{O}_3)_a(\text{Ga}_2\text{O}_3)_b(\text{ZnO})_c]$ (GIZO) (where $a \geq 0$, $b \geq 0$, and $c > 0$). In some embodiments, the active layer 121 may have a source region, a drain region, and a channel region therebetween.

[0062] In some embodiments, the gate electrode 125 may be included on the gate dielectric layer 123 and an interlayer dielectric 113 may be formed to cover the gate electrode 125. In some embodiments, the source and drain electrodes 127 may be formed on the interlayer dielectric 113, and the source and drain electrodes 127 are connected to the source and drain regions of the active layer 121 through the interlayer dielectric 113. Although a top-gate type TFT is illustrated in the present embodiment, a bottom-gate type TFT may be included. That is, embodiments of the present invention are not necessarily limited to the stack structure of the TFT as described above, and TFTs having various structures may be used.

[0063] In some embodiments, a first planarization layer 115 may be formed on the source and drain electrodes 127. In some embodiments, the organic light-emitting device 130 or 230 as described above may be formed on the first planarization layer 115. In some embodiments, a first electrode 131 of the organic light-emitting device 130 or 230 may be formed on the first planarization layer 115, and the first electrode 131 is connected to the source and drain electrodes 127 through the first planarization layer 115. In some embodiments, each organic light-emitting device 130 or 230 may be separated by a pixel-defining layer 117. In some embodiments, a second planarization layer 119 may be formed on the organic light-emitting device 130 or 230. In some embodiments, the first planarization layer 115, the pixel-defining layer 117, and the second planarization layer 119 may be formed in a single or multilayer structure of an insulating inorganic material, organic material, or organic/inorganic composite.

[0064] In some embodiments, the upper substrate 150 may be formed on the second planarization layer 119. As described regarding the lower substrate 101, a substrate formed of various materials, such as glass, plastic, silicon, or metal, may be used as the upper substrate 150. In some embodiments, the upper substrate 150 may be formed in a thin film encapsulation structure which prevents the penetration of outside air and moisture into the organic light-emitting device 130 thereunder and is formed by stacking one or more insulating organic and

inorganic layers. In a case where the digital image is generated through the upper substrate 150, the upper substrate 150 may be formed to be transparent by using a glass substrate or a plastic substrate. In this case, light in the non-visible spectrum, such as infrared or ultraviolet light, may also transmit through the upper substrate 150.

[0065] In some embodiments, the display panel may generate a specific digital security pattern as a security signal before and after the digital image or between the digital images. Also, separate from the generation of the digital image, the digital security pattern may be generated only during an operation for the detection of the counterfeiting or tampering. Since human eyes can only see light in the visible spectrum, the digital security pattern in the non-visible spectrum may not be visually identified.

[0066] In some embodiments, the digital image and the digital security pattern may be generated with a time difference. In some embodiments, the digital image may be formed of a plurality of sequential digital image frames, and the digital security pattern may be generated at least any one time between the plurality of sequential digital image frames or may be generated at a predetermined time before or after the beginning of the plurality of sequential digital image frames. In some embodiments, the digital security pattern may be formed of a plurality of digital security pattern frames. In some embodiments, the plurality of digital security pattern frames may be generated at regular intervals between the plurality of digital image frames. In this case, the plurality of digital security pattern frames may be the same or may be different from one another. That is, the digital security pattern may exist in a single frame, may dynamically exist in many frames, and may periodically exist between the digital image frames.

[0067] In some embodiments, the security signal pattern may exhibit a unique value that is predetermined in the panel. In some embodiments, the digital security pattern may be a barcode or a QR code. However, the digital security pattern is not limited thereto. The presence of counterfeiting or tampering with the display panel may be easily identified by the detection of the digital security pattern by using a detector.

[0068] In some embodiments, the display panel may be used in various security documents, which include images and require the identification of the presence of counterfeiting or tampering with the images, as well as electronic passports or identifications.

[0069] In some embodiments, the organic light-emitting device may be an active matrix-type organic light-emitting display panel. In some embodiments, the organic light-emitting device may also be used in any apparatus as long as it is a display apparatus including a pixel-defining layer, such as a passive matrix-type organic light-emitting display panel.

[0070] In some embodiments, the light in a visible spectrum may be used to generate a digital image and the light in a non-visible spectrum may be used to gen-

erate a digital security pattern since a light-emitting layer of an organic light-emitting device constituting a display panel emits light in a non-visible spectrum as well as light in a visible spectrum. Thus, counterfeiting or tampering with the digital image may be identified by the detection of the digital security pattern.

[0071] As discussed, embodiments of the invention provide an organic light-emitting device comprising: a first electrode; a second electrode facing the first electrode; and an organic layer between the first electrode and the second electrode, wherein the organic layer comprises a light-emitting layer arranged to emit light in a visible spectrum and light in a non-visible spectrum.

[0072] Embodiments of the invention can also provide a display device including: a first substrate; a thin film transistor on the first substrate; an insulating layer on the thin film transistor; an organic light-emitting device according to the above mentioned embodiments disposed on the insulating layer and electrically connected to the thin film transistor; and a second substrate on the organic light-emitting device.

[0073] While the embodiments have been particularly shown and described with reference to exemplary embodiments thereof, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the scope of the embodiments as defined by the following claims.

Claims

1. An organic light-emitting device comprising:

a first electrode;
a second electrode facing the first electrode; and
an organic layer between the first electrode and the second electrode,
wherein the organic layer comprises a light-emitting layer which is arranged to emit light in a visible spectrum and light in a non-visible spectrum.

2. The organic light-emitting device of claim 1, wherein the light-emitting layer comprises a first material arranged to emit the light in the visible spectrum and the light in the non-visible spectrum; optionally wherein the first material comprises AlInGa_N, InGa_N, AlP, AlAs, GaP, InN, AlInGaP, or AlGaAs.

3. The organic light-emitting device of claim 1, wherein the light-emitting layer comprises a first light-emitting layer arranged to emit the light in the visible spectrum and a second light-emitting layer arranged to emit the light in the non-visible spectrum.

4. The organic light-emitting device of claim 3, wherein

the first light-emitting layer comprises a first material arranged to emit the light in the visible spectrum; optionally wherein the first light-emitting layer 235a comprises Alq₃, 4,4'-bis(N-cabazoyl-1,1'-biphenyl (CBP), poly(n-vinylcabazole) (PVK), ADN, 4,4',4"-tris(carbazol-9-yl)-triphenylamine (TCTA), 1,3,5-tris(N-phenylbenzimidazole-2-yl)benzene (TPBI), 3-tert-butyl-9,10-di(naphth-2-yl)anthracene (TBADN), distyrylarylene (DSA), 2,7-bis(9,9-diethylfluoren-2-yl)-9,9-diethylfluorene (E3), or 4,4'-bis(9-carbazoyl)-2,2'-dimethyl-biphenyl (CDBP).

5. The organic light-emitting device of claim 4, wherein the second light-emitting layer comprises a second material arranged to emit light in an infrared region of the non-visible spectrum; optionally wherein the second material comprises tris(acetylacetonato)(1,10-phenanthroline)erbium, tris(acetylacetonato)(1,10-phenanthroline)neodymium, tris(acetylacetonato)(1,10-phenanthroline)holmium, GaAsP, InP, or GaAs.

6. The organic light-emitting device of any one of claims 3 to 5, wherein the second light-emitting layer comprises a third material arranged to emit light in an ultraviolet region of the non-visible spectrum; optionally wherein the third material comprises N,N'-bis(3-methylphenyl)-N,N'-bis(phenyl)-benzidine (TPD), N,N'-di(naphthalene-1-yl)-N,N'-diphenylbenzidine (alpha-NPD), N,N'-bis(naphthalen-1-yl)-N,N'-bis(phenyl)benzidine (alpha-NPB), N,N'-di(naphthalen-2-yl)-N,N'-diphenylbenzidine (beta-NPB), 2,9-dimethyl-4,7-diphenyl-1,10-phenanthroline (BCP), AlGa_N, or AlN.

7. The organic light-emitting device of any one of claims 3 to 6, wherein the second light-emitting layer also acts as a hole transport layer or an electron transport layer.

8. The organic light-emitting device of any one of claims 1 to 7, wherein the organic layer further comprises at least one of a hole injection layer, a hole transport layer, an electron transport layer, or an electron injection layer.

9. A display device including:

a first substrate;
a thin film transistor on the first substrate;
an insulating layer on the thin film transistor;
an organic light-emitting device according to any one of claims 1 to 8 disposed on the insulating layer and electrically connected to the thin film transistor; and
a second substrate on the organic light-emitting device.

10. A display device according to claim 9, wherein the organic light-emitting device is arranged to generate a digital image using light in the visible spectrum and to generate a digital security pattern using light in the non-visible spectrum. 5
11. A display device according to claim 9 or 10, wherein the organic light-emitting device is arranged to generate the digital image and the digital security pattern with a time difference. 10
12. A display device according to any one of claims 9 to 11, wherein the organic light-emitting device is arranged to form the digital image from a plurality of time-sequential digital image frames, and wherein the organic light-emitting device is arranged to generate the digital security pattern at least any one time between the plurality of digital image frames or at a predetermined time before or after beginning of the plurality of digital image frames. 15
20
13. A display device according to any one of claims 9 to 12, wherein the organic light-emitting device is arranged to form the digital security pattern from a plurality of digital security pattern frames, and wherein the organic light-emitting device is arranged to generate the plurality of digital security pattern frames at regular intervals between the plurality of digital image frames. 25
30
14. A display device according to any one of claims 9 to 13, wherein the organic light-emitting device is arranged to generate the digital security pattern only during an operation of detecting the digital security pattern without generation of the digital image. 35
15. A display device according to any one of claims 9 to 14, wherein the digital security pattern may be a bar-code or a quick response (QR) code. 40

45

50

55

FIG. 1




FIG. 2





FIG. 3





EUROPEAN SEARCH REPORT

 Application Number
 EP 14 16 2722

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	CN 102 769 025 A (SHENZHEN CHINA STAR OPTOELECTRONICS TECH) 7 November 2012 (2012-11-07) * figures *	1,3-5, 7-15	INV. H01L51/50 H01L27/32
X,P	-& US 2014/034911 A1 (LIU YAWEI [CN] ET AL) 6 February 2014 (2014-02-06) * paragraphs [0021], [0029], [0040] - [0042]; figures *	1,3-5, 7-15	ADD. G07F7/08 G09G3/32 G06K19/06
X	CN 102 769 105 A (SHENZHEN CHINA STAR OPTOELECTRONICS TECH) 7 November 2012 (2012-11-07) * figure 1 *	1,3,4, 6-15	
X,P	-& US 2014/034912 A1 (LIU YAWEI [CN] ET AL) 6 February 2014 (2014-02-06) * paragraphs [0007], [0018]; figure 1 *	1,3,4, 6-15	
X	SHARMA ASHA ET AL: "Polysilane based organic light emitting diodes: Simultaneous ultraviolet and visible emission", JOURNAL OF APPLIED PHYSICS, AMERICAN INSTITUTE OF PHYSICS, US, vol. 102, no. 8, 24 October 2007 (2007-10-24), pages 84506-84506, XP012102154, ISSN: 0021-8979, DOI: 10.1063/1.2800173 * the whole document *	1,2,8,9	TECHNICAL FIELDS SEARCHED (IPC) H01L G06K G07F G09G
X	US 2013/037785 A1 (FUJITA TETSUJI [JP] ET AL) 14 February 2013 (2013-02-14) * paragraph [0051]; claim 1 * * figures *	1,3-5, 7-9	
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 19 November 2014	Examiner De Laere, Ann
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03.82 (P04C01)



EUROPEAN SEARCH REPORT

Application Number
EP 14 16 2722

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	ETORI H ET AL: "Design of multilayer structure for UV organic light-emitting diodes based on 2-(2-naphthyl)-9,9'-spirobifluorene", JAPANESE JOURNAL OF APPLIED PHYSICS, JAPAN SOCIETY OF APPLIED PHYSICS, JP, vol. 46, no. 8A, 1 August 2007 (2007-08-01), pages 5071-5075, XP001518056, ISSN: 0021-4922, DOI: 10.1143/JJAP.46.5071 * figure 3b * * page 5073, column 1, last paragraph - page 5074, column 1, line 1 *	1,3,4, 6-9	
A	WO 2012/093669 A1 (NIPPON KOGAKU KK [JP]; YAGI TAKESHI [JP]) 12 July 2012 (2012-07-12) * figures 11-16 *	1-15	
			TECHNICAL FIELDS SEARCHED (IPC)
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 19 November 2014	Examiner De Laere, Ann
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 14 16 2722

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

19-11-2014

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
CN 102769025 A	07-11-2012	CN 102769025 A	07-11-2012
		WO 2014023038 A1	13-02-2014
US 2014034911 A1	06-02-2014	NONE	
CN 102769105 A	07-11-2012	CN 102769105 A	07-11-2012
		WO 2014023054 A1	13-02-2014
US 2014034912 A1	06-02-2014	NONE	
US 2013037785 A1	14-02-2013	CN 102956841 A	06-03-2013
		JP 2013038245 A	21-02-2013
		US 2013037785 A1	14-02-2013
WO 2012093669 A1	12-07-2012	JP 2012155318 A	16-08-2012
		WO 2012093669 A1	12-07-2012

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

专利名称(译)	用于输出图像和安全图案的有机发光装置，以及包括该装置的显示面板		
公开(公告)号	EP2819197A1	公开(公告)日	2014-12-31
申请号	EP2014162722	申请日	2014-03-31
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	三星DISPLAY CO. , LTD.		
[标]发明人	SEO HAE KWAN		
发明人	SEO, HAE-KWAN		
IPC分类号	H01L51/50 H01L27/32 G07F7/08 G09G3/32 G06K19/06		
CPC分类号	H01L27/3213 H01L51/5012 H01L51/504 H01L51/5044 H01L51/52 H01L27/3262 H01L51/0038 H01L51/5203 H05B33/14 H05B33/22 G06K19/06046 G07F7/0846 G09G3/32 H01L27/3244		
优先权	1020130073307 2013-06-25 KR		
外部链接	Espacenet		

摘要(译)

在一个方面，有机发光装置包括第一电极（131），面对第一电极的第二电极（139），以及在第一电极和第二电极之间的有机层（132），其中有机层包括发光层（135），其发射可见光谱中的光并且发射不可见光谱中的光。

FIG. 1

