

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 May 2005 (12.05.2005)

PCT

(10) International Publication Number
WO 2005/042666 A1

(51) International Patent Classification⁷: **C09K 11/06**

(21) International Application Number:
PCT/KR2004/002822

(22) International Filing Date:
4 November 2004 (04.11.2004)

(25) Filing Language: Korean

(26) Publication Language: English

(30) Priority Data:
10-2003-0077707
4 November 2003 (04.11.2003) KR

(71) Applicant (for all designated States except US): **LG CHEM, LTD.** [KR/KR]; LG Twin Tower, 20, Yoido-dong, Youngdungpo-gu, Seoul 150-721 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BAE, Jae-Soon** [KR/KR]; 106-305, Expo Apartment, Daejeon 305-761,

Jeonmin-dong, Yuseong-gu, Daejeon 305-761 (KR).
KANG, Min-Soo [KR/KR]; 114-1407, Hanmaul Apartment, Songgang-dong, Yuseong-gu, Daejeon 305-503 (KR).


(74) Agent: **KIM, Seong-Ki**; 14F., Kukdong Building, 60-1., Chungmuro3-ka, Chung-ku, Seoul 100-705 (KR).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

[Continued on next page]

(54) Title: NEW COMPOUND CAPABLE OF BEING USED IN ORGANIC LAYER OF ORGANIC LIGHT EMITTING DEVICE



(57) Abstract: Disclosed is a compound represented by the following formula 1 as a light emitting material: [formula 1] wherein each of R₀, R₁ and R₂ is the same as defined herein. An organic light emitting device including a first electrode, an organic film having one or more layers and a second electrode, laminated successively, is also disclosed. At least one layer of the organic film includes at least one compound represented by formula 1. The organic light emitting device shows excellent characteristics in terms of light emitting efficiency, life time and thermal stability.



(1)



FR, GB, GR, HU, IE, IS, IT, LU, MC, NL, PL, PT, RO, SE,
SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*

**NEW COMPOUND CAPABLE OF BEING USED IN ORGANIC LAYER OF
ORGANIC LIGHT EMITTING DEVICE**

Technical Field

5 The present invention relates to a novel compound for use in an organic film in an organic light emitting device and an organic light emitting device using the same.

Background Art

10 In general, the so-called "organic light emitting" phenomenon (organic electroluminescence) refers to a phenomenon in which electric energy is transformed into light energy by means of an organic substance. Particularly, when an organic film is disposed between an anode and a
15 cathode and then electric potential is applied between both electrodes, holes and electrons are injected into the organic film from the anode and the cathode, respectively. When the holes and electrons injected as described above are recombined, excitons are formed. Further, when the excitons
20 drop to a ground state, lights are emitted.

 Generally, the organic film has a multi-layer structure including different materials in each layer so as to increase the efficiency and stability of the organic light emitting device using the same film. In order to
25 obtain high light emitting efficiency, the amounts of the holes and electrons injected from both electrodes should be similar. However, there is a great difference between the movability of holes and that of electrons in one organic substance. Therefore, it is preferable that each of the hole
30 transport layer, light emitting layer and an electron

transport layer is formed individually to permit holes and electrons to be transferred efficiently to the light emitting layer, so that density of holes and that of electrons can be balanced, thereby increasing light emitting efficiency.

Light emitting materials used in the above-described organic light emitting device can be classified into fluorescent substances derived from excited singlet states and phosphorescent substances derived from excited triplet states. Further, they can be classified into blue, green and red light emitting materials depending on light colors, and yellow and orange light emitting materials needed for realizing more natural colors. The organic substance forming a light emitting layer in a light emitting device determines the color of the light emitted from the device. Additionally, substances emitting red, green or blue light are used appropriately to realize the full spectrum of color.

Meanwhile, host/dopant systems are generally used in order to increase color purity and light emitting efficiency by means of energy transition. The principle of a host/dopant system is as follows. When a host forming a light emitting layer is mixed with a small amount of a dopant having a smaller gap between both energy zones compared to the host substance, excitons generated from the host are transported to the dopant, resulting in highly efficient light emission. During the above process, wavelength of the light emitted from the host shifts to that of the dopant. Therefore, it is possible to obtain light with a desired wavelength depending on the kind of dopant.

Among such light emitting materials, red light emitting materials intrinsically have disadvantages in that energy efficiency is low, a so-called quenching effect occurs at high concentration due to intermolecular
5 interactions through expanded pi (π)-electrons, and that color purity decreases due to a broad light emitting range. Such disadvantages of red light emitting materials were the most serious problems inhibiting practical use of full color organic light emitting devices. Due to the above problems,
10 red light emitting materials would rather be used as a dopant together with a host than used alone. In the former case, it is possible to improve light emitting efficiency and color purity by using an energy transition from the host substance to the red light emitting material as a dopant, as
15 described above.

However, host/dopant-based light emitting devices tend to show degradation of color purity because light emission caused by the host may occur or the dopant may be trapped at high voltage. Such problematic phenomena result from an
20 insufficient energy transition from the host.

Hamada et al. suggested a solution for improving light emitting efficiency and color purity in [*Applied Phys. Lett.* 75, 1682 (1999)]. More particularly, they suggested an organic light emitting device having a light emitting layer
25 comprising at least two dopants. However, it is very difficult to deposit a host substance along with two kinds of dopant substances at the same time in a practical process for manufacturing a light emitting device. Further, when either one kind of dopant or at least two kinds of dopants
30 are used in a light emitting layer, wavelength of the light

emitted from the light emitting layer shifts to the orange zone according to the increase of current density.

Accordingly, there is a continuous demand in the art for a light emitting material providing high light emitting efficiency and color purity.


Disclosure of the Invention

It is an object of the present invention to design a light emitting material that can solve the problems caused by intermolecular interactions. To satisfy the object, we prepared a light emitting material as an asymmetric compound such as an enantiomer by introducing a sterically bulky cycloalkyl group derived from camphorquinone into the thiophene-pyrazine molecular skeleton that is a main light emitting site; and by introducing a substituent (R_0) into the cycloalkyl group derived from camphorquinone to form a cycloalkyl group having a chiral carbon atom. When the light emitting material prepared as described above was incorporated into an organic film of an organic light emitting device in the form of an enantiomer or a racemate, it was possible to decrease intermolecular interactions to the highest degree. Ultimately, we have found a compound providing low quenching effect, high color purity and high light emitting efficiency, due to the decreased intermolecular interactions. Further, the compound was shown to improve the life time, efficiency and thermal stability of organic light emitting devices and to permit low-voltage drive of an organic light emitting device, when used in an organic light emitting device.

According to an aspect of the present invention, there

is provided a compound represented by the following formula 1:

[formula 1]



5 wherein R_0 represents a lower alkyl group having 1-6 carbon atoms; and

R_1 and R_2 are identical or different, and each is selected from the group consisting of H; an aromatic compound and derivatives thereof; a 5-membered or 6-membered
 10 heteroaromatic compound and derivatives thereof; an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; an alkylamine including an alkyl group having 1-20 carbon atoms, which is non-substituted or substituted with at least one substituent selected from the
 15 group consisting of an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; an aralkylamine including an alkyl group having 1-20 carbon atoms, which is non-substituted or substituted with at least one substituent selected from the group consisting of an aliphatic
 20 hydrocarbon having 1-20 carbon atoms, an aromatic compound, a heteroaromatic compound and derivatives thereof; an arylamine non-substituted or substituted with at least one substituent selected from the group consisting of an aromatic compound, a heteroaromatic compound and derivatives
 25 thereof; and a silicon or boron compound non-substituted or

substituted with at least one substituent selected from the group consisting of an aromatic compound, a heteroaromatic compound and derivatives thereof;

R1 and R2 may form a fused ring together; or

5 R1 and R2 are linked linearly to permit the compound represented by formula 1 to form a polymer.

According to another aspect of the present invention, there is provided an organic light emitting device comprising an organic film using the compound represented by
10 formula 1.

Hereinafter, the present invention will be explained in detail.

The present invention provides the compound represented by formula 1.

15 The compound represented by formula 1 can be used as a light emitting material, particularly as a green, yellow, orange or red light emitting material and as a light emitting host or dopant in an organic light emitting device.

According to the present invention, the thiophen
20 pyrazine skeleton in the compound of formula 1 accomplishes absorption or emission of light and determines the main wavelength of light to be emitted.

The compound according to the present invention is characterized in that the thiophen[3,4-b]pyrazine skeleton
25 is directly linked to a cycloalkyl group through the condensation with a sterically bulky camphorquinone compound, as depicted in the above formula 1.

The cycloalkyl group introduced through the condensation with a camphorquinone compound is a relatively
30 bulky and spherical alkyl group and thus can increase the

melting point and glass transition temperature of the compound. Additionally, the cycloalkyl group can solidify the molecular structure of the compound so as to provide relatively high quantum efficiency, and can make the molecular structure so bulky that the compound is subjected to steric hindrance. Therefore, the cycloalkyl group can reduce side effects caused by intermolecular interactions, including the so-called quenching effect and decrease in color purity due to a broad light emitting range, thereby representing the characteristics of the compound itself as highly as possible. Further, introduction of the sterically bulky cycloalkyl group into the molecule of the compound of formula 1 can improve the function of the compound as a dopant capable of inhibiting intermolecular interactions in a host.

Further, the sterically bulky cycloalkyl group can serve to collect electrons on the pyrazine skeleton and thus to diversify the range of light emission by the interaction between substituents R1 and R2. The compound of formula 1 may be provided with a suitable conjugation length so as to modify the wavelength of light, or may be provided with a substituent having high electron-donating activity, such as an alkylamine group, an aralkylamine group or an arylamine group, so as to emit light. Particularly, the compound of formula 1 can provide a material that has high efficiency and is stable in the range of red light.

It is another characteristic of the present invention that the substituent (R₀) present on the cycloalkyl group to which the pyrazine in the thiophen[3,4-b]pyrazine skeleton is linked may provide a chiral carbon atom, thereby forming

the compound of formula 1 as an asymmetric compound such as an enantiomer or as a racemate.

The present invention also includes the compounds in which R₀ is other substituents than a lower alkyl group having 1-6 carbon atoms, with the proviso that the compound of formula 1 can perform desired functions in an organic film of an organic light emitting device.

The compound of formula 1 can provide the effects resulting from the above-mentioned structural characteristics of formula 1, in both cases of (S)-isomer and (R)-isomer. However, when the compound of formula 1 is applied to an organic light emitting device as a racemate containing (S)-isomer and (R)-isomer in the ratio of 1:1, it is possible to obtain a light emitting efficiency increased by about 10% compared to the cases wherein each isomer is used alone. Therefore, the compound of formula 1 is preferably a mixture of (S)-isomer and (R)-isomer, such as a racemic mixture. When the compound of formula 1 is present as a racemic mixture, it is possible to reduce interactions between both enantiomeric compounds to the highest degree and thus to solve the problems of quenching effect or decrease in color purity.

Substituents R₁ and R₂ in the compound of formula 1 serve to modify the wavelength of light to be emitted. It is preferable that substituents R₁ and R₂ are substituted with a substituent increasing a conjugation length or an electron-donating or electron-withdrawing substituent.

The main skeleton of the compound of formula 1, i.e., thiophen[3,4-b]pyrazine structure is an electron-accepting portion. R₁ and R₂ in the 2,5-position of thiophen

preferably serve as electron-donating portions so as to be balanced with the electron-accepting portion. Examples of electron-donating substituents include alkylamine groups, arylamine groups and aromatic compounds. Such substituents
5 abundant with electrons can have a stabilized resonance structure by donating electrons to an electron-accepting portion, thereby stabilizing the whole molecular structure of the compound.

When R1 or R2 in the compound of formula 1 includes an
10 aromatic compound, there is no particular limitation in kind of the aromatic compound because of the following reasons.

When an aromatic compound is linked with the thiophen ring on a complete plane in formula 1, a wavelength shift to a longer wavelength can be made according to the increase of
15 conjugation bond length. However, when an aromatic compound is a sterically hindered aromatic compound that is a multicyclic compound so bulky as to twist away from the plane of the thiophen pyrazine skeleton (for example substituted or non-substituted naphthalene, anthracene,
20 perylene, pyrene, etc.), it is difficult to make a shift to a longer wavelength. Therefore, the range of the wavelength of light to be emitted still remains in the range of red light. Accordingly, the kind of the aromatic compound included in the compound of formula 1 does not affect
25 whether the compound could emit the light in the visible range. However, the kind of the aromatic compound has an accompanying affect on the melting point and sublimation temperature of the compound.

The above principle for the case wherein each of R1
30 and R2 is an aromatic compound is also applied to the cases

wherein each of R1 and R2 is a derivative of aromatic compound, or an arylamine group or aralkylamine group including an aromatic compound.

Meanwhile, when the compound of formula 1 includes an
5 alkyl group, in other words, when R1 or R2 is an alkyl group or an alkyl-substituted substituent, there is no particular limitation in length of the alkyl group. Because the length of an alkyl group included in the compound does not affect the conjugation length of the compound, it has no direct
10 effect on the wavelength of the compound or on characteristics of a device. However, the length of an alkyl group may affect the selection of a method of applying the compound to an organic light emitting device (for example, a vacuum deposition method or a solution coating method).
15 Therefore, there is no particular limitation in length of the alkyl group that may be included in the structure represented by formula 1.

Hereinafter, substituents R1 and R2 in the compound of formula 1 will be explained in more detail.

20 Examples of aromatic compounds as R1 and R2 in formula 1 include monocyclic aromatic rings such as phenyl, biphenyl and terphenyl, and multicyclic aromatic rings such as naphthyl, anthracenyl, pyrenyl and perylenyl.







Examples of heteroaromatic compounds as R1 and R2 in
25 formula 1 include thiophene, furan, pyrrole, imidazole, thiazole, oxazole, oxadiazole, thiadiazole, triazole, pyridyl, pyridazyl, pyrazine, quinoline and isoquinoline groups.

Aliphatic hydrocarbons having 1-20 carbon atoms
30 include both linear aliphatic hydrocarbons and branched




aliphatic hydrocarbons, and particular examples thereof include alkyl groups such as methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, isobutyl, t-butyl, pentyl and hexyl groups; alkenyl groups, such as styryl group, having a
 5 double bond; and alkynyl groups, such as acetylene group, having a triple bond.


The aromatic compounds, aliphatic hydrocarbons and alkyl groups that may be included in the substituted or non-substituted alkylamine groups, aralkylamine groups,
 10 arylamine groups and silicon or boron compounds are the same as defined above.

Particular examples of R1 and R2 in formula 1 include the following compounds, but are not limited thereto:



15





5 wherein

R3 is selected from the group consisting of an aromatic hydrocarbon and derivatives thereof; a 5-membered or 6-membered heteroaromatic compound and derivatives thereof; an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; and a cycloalkyl group having 5-20 carbon atoms; and

X is selected from the group consisting of an aromatic


hydrocarbon and derivatives thereof; a 5-membered or 6-membered heteroaromatic compound and derivatives thereof; an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; a cycloalkyl group having 5-20 carbon atoms; H, an arylamine group, aralkylamine group, alkylamine group, aryloxy group, nitrile group, formyl group, acetyl group, benzoyl group, amide group, ester group, styryl group, acetylene group, alkoxy group, aryloxy group, alkylthioxy group and arylthioxy group; or X may form a fused ring.

Examples of aromatic compounds as R3 and X are the same as defined above with regard to R1 and R2. Examples of heteroaromatic compounds as R3 and X are the same as defined above with regard to R1 and R2.


Examples of aliphatic hydrocarbons as R3 and X include linear or branched alkyl groups having 1-20 carbon atoms (for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, t-butyl, n-pentyl and 2-ethylhexyl). These alkyl groups may be substituted with at least one substituent selected from the group consisting of an aryl group, alkoxy group, nitro group, nitrile group, halogen atom, etc.

Particular examples of the compound of formula 1 include the compounds represented by the following formulae 1-1 to 1-41, but are not limited thereto:


[formula 1-1]



[formula 1-2]




[formula 1-3]




5


[formula 1-4]




[formula 1-5]



[formula 1-6]




[formula 1-7]




5


[formula 1-8]




[formula 1-9]




[formula 1-10]




[formula 1-11]




5 [formula 1-12]




[formula 1-13]




[formula 1-14]



[formula 1-15]




[formula 1-16]




5


[formula 1-17]




[formula 1-18]




[formula 1-19]




[formula 1-20]




[formula 1-21]




[formula 1-22]



[formula 1-23]




[formula 1-24]




5


[formula 1-25]




[formula 1-26]



[formula 1-27]




[formula 1-28]




5


[formula 1-29]




[formula 1-30]



[formula 1-35]




[formula 1-36]




5

[formula 1-37]




wherein n is an integer of 2 or more.

[formula 1-38]




wherein n is an integer of 2 or more.

[formula 1-39]




- 5 wherein n is an integer of 2 or more; and each of R4 and R5 is independently or simultaneously selected from the group consisting of H, an linear or branched aliphatic hydrocarbon having 1-20 carbon atoms, and an alkoxy group including a linear or branched aliphatic hydrocarbon having 1-20 carbon
- 10 atoms; or R4 and R5 may form a fused ring together.

[formula 1-40]



wherein n is an integer of 2 or more.

[formula 1-41]



wherein n is an integer of 2 or more; and each of R_4 and R_5 is independently or simultaneously selected from the group consisting of H, an linear or branched aliphatic hydrocarbon having 1-20 carbon atoms, and an alkoxy group including a linear or branched aliphatic hydrocarbon having 1-20 carbon atoms; or R_4 and R_5 may form a fused ring together.

Preferably, in the compounds of formula 1-37 to 1-41, the maximum value of n is 50.

The polymeric materials such as compounds of formula 1-37 and 1-38 can be used as red light emitting materials, while the thiophen polymeric materials such as compounds of formula 1-39 to 1-41 can be used also as conductive polymers, electrochromic materials, etc.

In general, the compound represented by formula 1 can be prepared by two types of methods as described hereinafter.

The first method is as follows.


Boronic acid having a substituent R_1 , boronic acid having a substituent R_2 and 2,5-dihalogen 3,4-dinitrothiophen are coupled in an organic solvent such as dioxane, tetrahydrofuran or toluene in the presence of a base such as K_2CO_3 or Na_2CO_3 by adding a palladium (Pd)

catalyst. The nitro groups (NO_2) in the resultant compound are reduced into amino groups (NH_2) by using a Fe or Sn compound. Then, the resultant compound is reacted with camphorquinone represented by the following formula 3-1, 3-2 or 3 in a solvent such as ethanol, acetic acid or a mixture thereof to form pyrazine simultaneously with dehydration (removal of water molecules). By doing so, it is possible to obtain the compound represented by formula 1.


[formula 3-1]

[formula 3-2]


[formula 3]



(R)



(S)




Racemic

10

The first method may be depicted by the following reaction scheme 1.

[reaction scheme 1]




15 wherein X is a halogen atom.

The second method is as follows.

A halogen atom (X) is introduced into the 2,5-position in 3,4-diaminothiophene by using a halogenating agent such as Br_2 or NBS and Cl_2 or NCS. The resultant 2,5-dihalogen-
20 3,4-diaminothiophene compound is reacted with camphorquinone represented by the above formula 3-1, 3-2 or 3 in a solvent

such as ethanol, acetic acid or a mixture thereof to form a thianopyrazine compound. Then, the resultant thianopyrazine compound, boronic acid having a substituent R1 and boronic acid having a substituent R2 are coupled in an organic solvent such as dioxane, tetrahydrofuran or toluene in the presence of a base such as K_2CO_3 or Na_2CO_3 by adding a palladium (Pd) catalyst. By doing so, it is possible to obtain the compound represented by formula 1. The second method may be depicted by the following reaction scheme 2.

[reaction scheme 2]



wherein X is a halogen atom.

In the above methods, the halogen atom is preferably a bromine atom (Br).

Although the compounds represented by formula 1-1 to 1-36 may be prepared by using either the first method or the second method, polymeric compounds such as the compounds represented by formula 1-37 to 1-39 are preferably prepared by using the second method. Meanwhile, the polymeric compound represented by formula 1-40 may be prepared by the second method as a polymer, in the presence or absence of the step of introducing a halogen atom. Additionally, the polymeric compound represented by formula 1-41 may be prepared by using either the first method or the second method.

In a variant, each of polymeric materials of formulae 1-39, 1-40 and 1-41 may be prepared by forming a monomer first and then performing electro-polymerization of the monomer.

5 Methods for preparing the compound represented by formula 1 will be explained in detail with reference to the following Preparation Examples.

 The present invention also provides an organic light emitting device including a first electrode, an organic film
10 having one or more layers and a second electrode, laminated successively, wherein at least one layer of the organic film contains at least one compound represented by formula 1.

 The organic light emitting device according to the present invention includes a substrate, an anode, a cathode
15 and an organic film disposed between the anode and cathode, the organic film having one or more layers. The organic film disposed between the anode and cathode may have an increased number of layers by further specializing the function of each layer. On the other hand, the organic film may have a
20 decreased number of layers by using a multi-functional layer.

 Preferably, the organic light emitting device according to the present invention have a structure including a substrate, anode, hole injection layer, hole
25 transport layer, light emitting layer, electron transport layer and a cathode, when viewed from the bottom to the top. Additionally, a separate hole block layer may be interposed between the electron transport layer and the light emitting layer for the purpose of preventing holes from moving toward
30 the electron transport layer.

Structures of the organic light emitting device according to the present invention are exemplified in FIGs. 1 to 5, but are not limited thereto. As shown in FIG. 1, the device includes an organic film having four layers. FIG. 2 shows a preferred embodiment including a light emitting layer having both functions as an electron transport layer and as a light emitting layer. FIG. 3 shows a preferred embodiment including a hole transport layer having both functions as a hole injection layer and as a hole transport layer. FIG. 4 shows a preferred embodiment including a light emitting layer having three functions as a hole injection layer, as a hole transport layer and as a light emitting layer at the same time. Further, FIG. 5 shows a preferred embodiment including a light emitting layer having four functions as a hole injection layer, as a hole transport layer, an electron transport layer and as a light emitting layer at the same time.

In the organic light emitting device according to the present invention, each layer can be formed as a thin film, which can be prepared by a conventional method known to one skilled in the art depending on the kinds of the materials used in each layer. More particularly, the thin film may be formed by using CVD (Chemical Vapor Deposition), EB (Electron Beam Vapor Deposition), thermal vapor deposition, sputtering or high-vacuum thermal evaporation methods. Otherwise, the thin film may be formed by a solution coating method including a spin coating, roll coating, screen printing, dip coating, doctor blading, ink jet printing and thermal transfer methods.

The compound of formula 1 may be used as a light

emitting material in organic light emitting devices having structures as described above. In a variant, the compound of formula 1 may be used as a light emitting host for the shift of excitation energy facilitating the light emission of other dopants, or as a dopant. Two or more of compounds represented by formula 1 may be used in combination. Further, as long as the characteristics of the present invention can be maintained, the compound of formula 1 may be used in combination with other light emitting pigments.

When the compound of formula 1 is used as a dopant having an energy gap smaller than that of the host forming a light emitting layer, excitons generated in the host are transported to the dopant, thereby permitting an increase in light emitting efficiency. Further, when the compound of formula 1 has a cycloalkyl group derived from a sterically bulky camphorquinone compound, and specially has a chiral carbon atom on the cycloalkyl group, the light emitting material of formula 1 can form a racemate capable of reducing the packing phenomenon among molecules, resulting in minimization of quenching effect.

When the compound of formula 1 is used as a dopant, it may be doped totally or partially on the layer containing the same compound. The compound of formula 1 may be doped on the layer uniformly in the direction of the thickness or may have a concentration gradient along the thickness. The amount of the compound of formula 1 to be doped preferably ranges from 10^{-3} to 15 wt%, and more preferably ranges from 0.1 to 10 wt%, based on the weight of the host substance.

Additionally, the compound of formula 1 can have other functions needed for an organic film of an organic light

emitting device (for example, hole injection, hole transport, electron transport or electron injection) in addition to the above-described light emitting function.

Among the compounds represented by formula 1, the
5 compound of formula 1-1 has a HOMO (Highest Occupied Molecular Orbital) level of 5.2 eV, which is similar to HOMO values of conventional materials used in a hole transport layer. Further, the compound of formula 1-1 has a work function of 4.7 eV, and thus can be used as a hole transport
10 material. Meanwhile, when the compound of formula 1 has a longer conjugation bond or forms a polymer, it is expected that the compound has a HOMO level similar to that of poly(ethylenedioxythiophene) (PEDOT), which is a hole injection material. Meanwhile, when R1 and R2 in the
15 compound of formula 1 are substituted with a heteroaromatic substituent (particularly, imidazole, thiazole, oxazole, pyridine, pyrazine groups, etc.), the resultant compound has a HOMO level of about 5.7 eV, which is the energy level of Alq3 as a typical example of electron transport materials.
20 As described above, introduction of various substituents permits the compound to be transformed into a substance having n-type characteristics. When R1 and R2 are substituted with an aryl group such as phenyl or naphthyl, the resultant compound has a large energy gap corresponding
25 to a short wavelength (for example, orange and yellow), and thus can serve also as a light emitting host.

The compound of formula 1 is preferably included in the light emitting layer in an organic light emitting device. When a hole transport layer and/or electron
30 transport layer has an additional function as a light

emitting layer without using a separately formed light emitting layer, the compound of formula 1 may be included in the hole transport layer and/or electron transport layer.

The light emitting device including the compound of formula 1 has improved life time and thermal stability. According to the introduction of a sterically bulky cycloalkyl group, (1) it is possible to increase the melting point and glass transition temperature of the compound of formula 1, resulting in improvement in thermal stability, and (2) it is possible to cause the compound of formula 1 to represent amorphous characteristics predominantly, thereby preventing the light emitting device from being damaged by crystallization caused by Joule heat generated during the operation of the organic light emitting device.

15

Brief Description of the Drawings

FIGS. 1 to 5 are sectional views each showing the structure of an organic light emitting device applicable to the present invention, wherein reference numeral 1 is a substrate, 2 is an anode, 3 is a hole injection layer, 4 is a hole transport layer, 5 is a light emitting layer, 6 is an electron transport layer and 7 is a cathode 107.

20


Mode for Carrying Out the Invention

Hereinafter, the present invention will be explained in more detail through Preparation Examples, Examples, and Comparative Examples. It is to be understood that the following examples are illustrative only and the present invention is not limited thereto.

30

Preparation Example 1**Synthesis of Compound represented by Formula 1-1**

1-1. Synthesis of the following compound as intermediate




5

To a 500 ml flask, 17.2 g (0.1 mol) of 4-bromoaniline, 50 g (0.24 mol) of iodobenzene, 32 g (0.8 mol) of potassium hydroxide, 0.04 g (0.04 mol, 0.4 eq.) of cuprous chloride and 0.08 g (0.04 mol, 0.4 eq.) of phenanthroline were introduced and stirred for 12 hours at 180 °C under nitrogen atmosphere. The reaction mixture was cooled to room temperature and the insoluble solid salt was filtered off. The filtrate was extracted with toluene and distilled water two times and then the organic layer was collected. Toluene was removed from the organic layer under reduced pressure to provide an organic compound. The organic compound was purified by column chromatography using n-hexane as an eluent. Then, the product was precipitated with a small amount of ethanol to provide 21 g of diphenylamino 4-bromobenzene (yield 65%).
m/z 324 (M+).


20

1-2. Synthesis of the following compound as intermediate



17 g (52.4 mmol) of diphenylamino 4-bromobenzene obtained from the above step 1-1 was dissolved in 200 ml of tetrahydrofuran. Next, t-butyl lithium (t-BuLi, 52 ml, 78.7 mmol, 2.5M solution in pentane) was gradually added thereto at -78°C under nitrogen atmosphere. After 1 hour, trimethyl borate (157 mmol, 18 ml) was gradually added thereto. After 30 minutes, the cooling bath was removed and the reaction mixture was reacted for 3 hours at room temperature. After the completion of the reaction, 1N HCl (100 ml) was added and the mixture was extracted with ethyl ether. The product was dried over anhydrous magnesium sulfate, concentrated under reduced pressure and crystallized with ether. The crystallized product was filtered and dried to provide 9.8 g of diphenyl 4-aminobenzene boronic acid (yield 65%). $[\text{M}+\text{H}]^{+}$ 325.


1-3. Synthesis of the following compound as intermediate



3 g (9 mmol) of 2,5-dibromo-3,4-dinitrothiophene and 8 g (27.7 mmol) of diphenyl 4-aminobenzene boronic acid obtained from the above step 1-2 were dissolved in 50 ml of

tetrahydrofuran (THF). The resultant mixture, 55 ml of 2M potassium carbonate (K_2CO_3) and tetrakis(triphenylphosphine)palladium(0) ($Pd(PPh_3)_4$) (0.1 g, 0.09 mmol) were introduced into a 250 ml round-bottom flask and then the reaction mixture was refluxed for 24 hours. After the completion of the reaction, the reaction mixture was cooled to room temperature, and tetrahydrofuran (THF) was removed therefrom. The resultant solid was filtered after adding a small amount of ethanol, washed with water and ethanol and dried in a vacuum oven. The resultant solid was added to ethyl acetate, heated with stirring, washed to remove impurities and then dried to provide 5 g (7.6 mmol, yield 84%) of 2,5-di(triphenylamino)-3,4-dinitrothiophen. $[M+H]^+$ 660.

15 1-4. Synthesis of Compound of Formula 1-1



5 g of 2,5-di(triphenylamino)-3,4-dinitrothiophen (7.6 mmol) obtained from the above step 1-3 was introduced into 40 ml of tetrahydrofuran (THF), 20 ml of EtOH and 10 ml of water. Then, 2.5 g (44.7 mmol, 6 eq.) of iron (Fe) powder was added thereto and the reaction mixture was refluxed for 48 hours. The reaction mixture was cooled to room temperature and unreacted Fe or salts thereof were filtered

off. Next, the solvents were removed from the filtrate under reduced pressure. 100 ml of ethanol and 50 ml of water were added thereto and the mixture was stirred to provide a 2,5-disubstituted 3,4-diaminothiophen compound having amino groups reduced from nitro groups as a crude solid compound.

0.5 g (0.83 mmol) of the compound obtained from the above was stirred, without further purification, together with 0.14 g (0.84 mmol) of (R)-camphorquinone in 30 ml of acetone for 48 hours at 120°C to form a solid. The resultant solid was cooled to room temperature, 30 ml of ethanol was added thereto and then the mixture was stirred to obtain a reddish purple solid. Next, the resultant solid was filtered, washed with ethanol and then dried. The product was purified by column chromatography (n-hexane/THF: 8/1) and precipitated with ethanol. The resultant product was filtered and dried to provide 0.5 g of the compound of formula 1-1 (yield 81%).

m.p.: 239.9°C

¹H NMR in CDCl₃ δ : 8.15 (d, 2H), 8.02 (d, 2H), 7.29 (m, 10H), 7.19 (m, 12H), 7.04 (t, 4H), 2.94 (d, 1H), 2.25 (m, 1H), 2.00 (t, 1H), 1.52 (d, 2H), 1.36 (s, 3H), 1.11 (s, 3H), 0.74 (s, 3H)


Absorption Spectrum: λ_{max} 490 nm (solvent: 2x10⁻⁵M toluene)

Fluorescence Spectrum: λ_{max} 641 nm (excitation wavelength 492nm, solvent: 2x10⁻⁵M toluene)

[M+H]⁺ 853.

Preparation Example 2

Synthesis of Compound represented by Formula 1-2



Preparation Example 1 was repeated to provide 0.4 g (yield 67%) of the compound of formula 1-2, except that racemic camphorquinone was used instead of (R)-camphorquinone in the above step 1-4.

m.p. ; 255.3°C

¹H NMR in CDCl₃ δ : 8.15 (d,2H), 8.02 (d,2H), 7.29 (m,10H), 7.19 (m,12H), 7.04 (t,4H), 2.94 (d,1H), 2.25 (m,1H), 2.00 (t,1H), 1.52 (d,2H), 1.36 (s,3H), 1.11 (s,3H), 0.74 (s,3H)

Absorption Spectrum: λ_{max} 490 nm (solvent: 2x10⁻⁵M toluene)


Fluorescence Spectrum: λ_{max} 643 nm (excitation wavelength 492nm, solvent: 2x10⁻⁵M toluene)

[M+H]⁺ 853.

Preparation Example 3


Synthesis of Compound of Formula 1-5

3-1. Synthesis of the following compound as intermediate



26 g (123 mmol) of 4-bromo t-butylbenzene, 4.6 g (49 mmol) of aniline, 7 g (73 mmol, 1.5 eq.) of sodium t-butoxide, 0.3 g (1 mmol) of $\text{Pd}_2(\text{ba})_3$ and 0.1 g (1.5 mmol) of $\text{P}(\text{t-Bu})_3$ were introduced to 300 ml of toluene and the
5 reaction mixture was refluxed for 10 hours under nitrogen atmosphere. The reaction mixture was cooled to room temperature and 200 ml of distilled water was added thereto, followed by stirring. Then, the toluene phase was extracted, dried over anhydrous magnesium sulfate, filtered and was
10 subjected to reduced pressure to remove the solvents. The reaction mixture was purified by column chromatography using n-hexane as an eluent to provide 7.4 g (20.7 mmol, yield 42%) of a white solid. $[\text{M}+\text{H}]^+$ 358.


3-2. Synthesis of the following compound as
15 intermediate



7.4 g (20.7 mmol) of the compound obtained from the above step 3-1 was introduced to 100 ml of DMF, followed by stirring. 3.7 g (20.7 mmol) of NBS was added to the reaction
20 mixture, followed by stirring for 2 hours at 50°C. Then, 200 ml of distilled water was poured thereto, followed by stirring. The resultant solid was filtered off, dissolved in THF, and dried over anhydrous magnesium sulfate. THF used as solvent was removed under reduced pressure to obtain a


liquid reaction mixture forming a solid with the lapse of time. 50 ml of ethanol was added thereto and then the resultant mixture was stirred, washed to remove impurities, filtered and dried to provide 3.2 g (7.3 mmol, yield 35%) of the target compound, N,N'-t-butylidiphenyl 4-bromoaniline. m/z 436.

3-3. Synthesis of the following compound as intermediate




3.2 g (7.3 mmol) of the compound obtained from the above step 3-2 was dissolved in 80 ml of THF and 8 ml of t-butyl lithium (t-BuLi, 14 mmol, 2 eq. 1.7M solution in pentane) was gradually added thereto at -78°C. After 1 hour, 2.5 ml (22 mmol, 3 eq.) of trimethylborate was added thereto. After 30 minutes, the cooling bath was removed and the reaction mixture was reacted for 3 hours at room temperature. After the completion of the reaction, 50 ml of 1N HCl and 100 ml of ethyl ether were added thereto, followed by stirring for 1 hour and extraction. The resultant product was dried over anhydrous magnesium sulfate, filtered and subjected to reduced pressure to remove the organic solvents. The resultant solid was filtered, washed with petroleum ether and dried to provide 2 g (5 mmol, yield 68%) of a crude compound. [M+H]⁺ 437.

3-4. Synthesis of the following compound as intermediate



0.6 g (2 mmol) of 2,5-dibromo-3,4-dinitrothiophen
5 dissolved in 4 ml of THF, 2 g (5 mmol) of the compound
obtained from the above step 3-3, 20 ml of 2M potassium
carbonate (K_2CO_3) and tetrakis(triphenylphosphine)
palladium(0) ($Pd(PPh_3)_4$) (0.1 g, 0.09 mmol) were introduced
into a 250 ml round-bottom flask and then the reaction
10 mixture was refluxed for 24 hours. After the completion of
the reaction, the reaction mixture was cooled to room
temperature. THF was removed from the reaction mixture and a
small amount of ethanol was added thereto. The resultant
solid was filtered and washed with water and ethanol and
15 dried in a vacuum oven. The resultant solid was added to
ethyl acetate, heated with stirring, washed to remove
impurities, filtered and then dried to provide 1.7 g (1.8
mmol, yield 90%) of the target compound. $[M+H]^+$ 885.

3-5. Synthesis of compound of formula 1-5



[formula 1-5]

1.7 g (1.8 mmol) of the compound obtained from the above step 3-4 was introduced into 150 ml of THF, 5 ml of EtOH and 10 ml of water. Then, 0.6 g (11 mmol, 6 eq.) of iron (Fe) powder was added thereto and the reaction mixture was refluxed for 48 hours. The reaction mixture was cooled to room temperature and unreacted Fe or salts thereof were filtered off. Next, the solvents were removed from the filtrate under reduced pressure. After filtering, the product was washed with distilled water and n-hexane to provide about 1 g of the compound having amino groups reduced from nitro groups as a crude solid. 1 g of the compound obtained from the above was stirred, without further purification, together with 0.28 g (1.7 mmol) of racemic camphorquinone in 30 ml of acetic acid for 48 hours at 120°C to form a solid. The resultant solid was cooled to room temperature, 30 ml of ethanol was added thereto and then the mixture was stirred to obtain a reddish purple solid. Next, the resultant solid was filtered, washed with ethanol and then dried. The product was purified by column chromatography (n-hexane/THF: 8/1) and precipitated with ethanol. The resultant product was filtered and dried to provide 0.5 g of the compound of formula 1-5 (yield 81%).

m.p. : 298°C

^1H NMR in CDCl_3 δ : 8.11 (d, 2H), 7.98 (d, 2H), 7.28 (m, 10H), 7.10 (m, 12H), 2.91 (m, 1H), 2.25 (m, 1H), 2.00 (t, 1H), 1.52 (d, 2H), 1.36 (s, 36H), 1.09 (s, 3H), 0.72 (s, 3H)

Absorption Spectrum: λ_{max} 500 nm (solvent: 2×10^{-5} M toluene)


Fluorescence Spectrum: λ_{max} 652 nm (excitation wavelength 500nm, solvent: 2×10^{-5} M toluene)

$[\text{M}+\text{H}]^+$ 955.

Preparation Example 4


10 Synthesis of Compound represented by formula 1-6

4-1. Synthesis of the following compound as intermediate



3.8 g (11.4 mmol) of 2,5-dibromo-3,4-dinitrothiophene, 5 g (29 mmol, 2.6 eq.) of naphthalene 2-boronic acid and 0.05 g (0.4 mol%) of $\text{Pd}(\text{PPh}_3)_4$ were refluxed in 30 ml of 2M potassium carbonate (K_2CO_3) solution and 50 ml of THF for 12 hours and then treated in the same manner as described in step 1-3 of Preparation Example 1 to provide 4.2 g (yield 86%) of the intermediate of the above formula. $[\text{M}+\text{H}]^+$ 427.

4-2. Synthesis of compound of formula 1-6



[formula 1-6]

4.2 g (9.8 mmol) of the compound obtained from the

above step 4-1 as intermediate and 3.2 g (58.8 mmol) of Fe powder were reacted in the same manner as described in step 1-4 of Preparation Example 1 to provide diaminothiophene.

Then, step 1-4 of Preparation Example 1 was repeated to provide 0.3 g (yield 60%) of the compound of formula 1-6, except that 0.17 g (1 mmol) of racemic camphorquinone was used instead of 0.14 g (0.84 mmol) of (R)-camphorquinone.

m.p. : 194.4 °C

^1H NMR in CDCl_3 δ : 8.8 (s, 2H), 8.64 (s, 2H), 8.43 (d, 2H), 8.33 (d, 2H), 7.97 (m, 8H), 7.87 (d, 4H), 7.53 (m, 8H), 3.05 (d, 1H), 2.25 (m, 1H), 2.11 (t, 1H), 1.58 (d, 2H), 1.46 (s, 3H), 1.16 (s, 3H), 0.80 (s, 3H)

Absorption Spectrum: λ_{max} 450nm (solvent: $2 \times 10^{-5}\text{M}$ toluene)


Fluorescence Spectrum: λ_{max} 584nm (excitation wavelength nm, solvent: $2 \times 10^{-5}\text{M}$ toluene)

$[\text{M}+\text{H}]^+$ 497.

Preparation Example 5

Synthesis of Compound represented by Formula 1-13


5-1. Synthesis of the following compound as intermediate



To a 500 ml flask, 7.7 g (0.45 mol) of 4-bromoaniline, 21.8 g (0.1 mol) of 3-iodotoluene, 34.4 g (0.86 mol, 8.6 eq.) of potassium hydroxide, 0.18 g (1.8 mol, 0.04 eq.) of

cuprous chloride and 0.36 g (1.8 mmol, 0.04 eq.) of 1,10-phenanthroline were introduced and stirred for 12 hours at 180 °C under nitrogen atmosphere. The reaction mixture was cooled to room temperature and the insoluble solid salt was filtered off. The filtrate was extracted with toluene and distilled water two times and then the organic layer was collected. Toluene was removed from the organic layer under reduced pressure to provide an organic compound. The organic compound was purified by column chromatography using n-hexane as an eluent. Then, the product was precipitated with a small amount of ethanol to provide 8 g of 3,3'-dimethyldiphenylamino 4-bromobenzene (yield 51%). m/z 352 (M+).


5-2. Synthesis of the following compound as intermediate



0.68 g (28 mmol, 1.4 eq.) of magnesium was introduced into a flask and then activated. Bromotriarylamine, 200 ml of THF and one drop of dibromoethane were added dropwise thereto. The reaction temperature was increased and the reaction mixture was refluxed for 4 hours. When a black solution was formed, the reaction temperature was maintained at -78 °C and trimethyl borate (59.7 mmol, 6.2 ml, 3 eq.) was gradually added thereto. After 30 minutes, the cooling bath was removed and the reaction mixture was reacted for 3 hours


at room temperature. After the completion of the reaction, 1N HCl (100 ml) was added, followed by stirring for 1 hour and extraction with ethyl ether. The product was dried over anhydrous magnesium sulfate, concentrated under reduced pressure, crystallized with ether, filtered and then dried to provide 1.8 g (yield 32%) of the target compound. $[M+H]^+$ 353.

5-3. Synthesis of the following compound as intermediate



10

0.5 g (1.5 mmol) of 2,5-dibromo-3,4-dinitrothiophene and 1.8 g (6 mmol) of the boronic acid obtained from the above step 5-2 were dissolved in 30 ml of tetrahydrofuran (THF). The resultant mixture, 20 ml of 2M potassium carbonate (K_2CO_3) and tetrakis(triphenyl phosphine)palladium(0) ($Pd(PPh_3)_4$) (0.1 g, 0.09 mmol) were introduced into a 250 ml round-bottom flask and then the reaction mixture was refluxed for 24 hours. After the completion of the reaction, the reaction mixture was cooled to room temperature and tetrahydrofuran (THF) was removed therefrom. A small amount of ethanol was added to the resultant solid. The solid was filtered, washed with water and ethanol, and dried in a vacuum oven. The resultant solid was added to ethyl acetate, heated with stirring, washed to remove impurities, filtered and then dried to provide 0.9 g (1.2 mmol, yield 80%) of the target compound. $[M+H]^+$ 717.

5-4. Synthesis of Compound of Formula 1-13

[formula 1-13]

0.9 g (1.2 mmol) of the compound obtained from the above step 5-3 was introduced into 40 ml of tetrahydrofuran (THF) and 10 ml of water. Then, 0.67 g (12 mmol, 10 eq.) of iron (Fe) powder was added thereto and the reaction mixture was refluxed for 48 hours. The reaction mixture was cooled to room temperature and unreacted Fe or salts thereof were filtered off. Next, the solvents were removed from the filtrate under reduced pressure. A small amount of ethanol was added to the resultant solid. The solid was filtered, washed with water and ethanol, and dried in a vacuum oven to obtain about 0.8 g of a crude solid. 0.8 g of the compound obtained from the above and 0.24 g (1.4 mmol) of camphorquinone were refluxed in 20 ml of acetic acid for 24 hours and the reaction mixture was cooled to room temperature. 20 ml of ethanol was added thereto, and the mixture was stirred for 1 hour and then filtered. The product was purified by column chromatography (n-hexane/ethyl acetate: 8/1) and precipitated with ethanol. The resultant product was filtered and dried to provide 0.37 g of the compound of formula 1-13 (yield 40%).

m.p. 207.9 °C.

¹H NMR in CDCl₃ δ : 8.13 (d, 2H), 8.01 (d, 2H),
 25 7.17 (m, 8H), 6.98 (m, 8H), 6.87 (m, 4H), 2.93 (d, 1H), 2.28 (m, 13H),

2.03 (q, 1H), 1.52 (t, 2H), 1.35 (s, 3H), 1.10 (s, 3H), 0.73 (s, 3H)

Absorption Spectrum: $\lambda_{\max}$ 499nm (solvent: 2×10^{-5} M toluene)


Fluorescence Spectrum: $\lambda_{\max}$ nm (excitation wavelength 5 nm, solvent: 2×10^{-5} M toluene)

$[M+H]^+$ 787.

Preparation Example 6


Synthesis of Compound represented by formula 1-14

6-1. Synthesis of the following compound as
10 intermediate



1 g (4.5 mmol) of 2,5-dibromo-3,4-dinitrothiophen,
1.73 g (13.5 mmol, 3 eq.) of thiophene 2-boronic acid and
0.05 g (1 mol%) of $\text{Pd}(\text{PPh}_3)_4$ (tetrakis(triphenyl
15 phosphine)palladium(0)) were refluxed in 10 ml of 2M
potassium carbonate (K_2CO_3) solution and 20 ml of THF for 12
hours and then treated in the same manner as described in
step 1-3 of Preparation Example 1 to provide 0.4 g (yield
24.4%) of the intermediate of the above formula.

20 6-2. Synthesis of compound of formula 1-14



[formula 1-14]

The compound obtained from the above step 6-1 was
reacted with Fe powder in the same manner as described in

step 1-4 of Preparation Example 1 to provide
diaminothiophene. Then, diaminothiophene was reacted with
camphorquinone in acetic acid and the resultant product was
purified by column chromatography (n-hexane/ethyl acetate:
5 8/1) to provide 0.2 g (yield 42%) of the compound of formula
1-14.

m.p. : Oil

^1H NMR in CDCl_3 δ : 7.63 (d,2H), 7.35 (d,2H), 7.12
(t,2H), 3.00 (d,1H), 2.47 (m,1H), 2.06 (m,1H), 1.53 (d,2H),
10 1.42 (s,3H), 1.13 (s,3H), 0.75 (s,3H)

Absorption Spectrum: λ_{max} 485nm (solvent: $2 \times 10^{-5}\text{M}$
toluene)


Fluorescence Spectrum: λ_{max} 630nm (excitation
wavelength 481nm, solvent: $2 \times 10^{-5}\text{M}$ toluene)

15 $[\text{M}+\text{H}]^+$ 409.

Preparation Example 7

Synthesis of Compound represented by Formula 1-15

7-1. Synthesis of the following compound as
intermediate




20

To the mixture containing 8.4 g (50 mmol) of
carbazole, 16 g (57mmol, 1.1 eq.) of 4-bromo-1-iodobenzene ,
6.4 g (100 mmol, 2 eq.) of Cu, 13.8 g (100 mmol, 2 eq.) of
 K_2CO_3 and 0.05 g (1 mmol) of 18-crown-6, 100 ml of
25 dichlorobenzene was added and the resultant mixture was
refluxed for 16 hours under nitrogen atmosphere. The


reaction mixture was cooled to room temperature, filtered to remove insoluble solid salts, and then subjected to reduced pressure to remove the organic solvents. The resultant mixture was purified by column chromatography using n-hexane as an eluent to provide 5.2 g (16.1 mmol, yield 32%) of the target compound. m/z 322 (M+).

7-2. Synthesis of the following compound as intermediate




5.2 g (16.1 mmol) of the compound obtained from the above step 7-1 was dissolved in 80 ml of THF and 13.7 ml of t-butyl lithium (23.3 mmol, 1.5 eq. 1.7M solution in pentane) was gradually added thereto at -78°C. After 1 hour, 4.8 ml (46 mmol, 3 eq.) of trimethylborate was added thereto. After 30 minutes, the cooling bath was removed and the reaction mixture was reacted for 3 hours at room temperature. After the completion of the reaction, 30 ml of 1N HCl and 100 ml of ethyl ether were added thereto, followed by stirring for 1 hour and extraction. The resultant product was dried over anhydrous magnesium sulfate, filtered and subjected to reduced pressure to remove the organic solvents. The resultant solid was filtered, washed with petroleum ether and dried to provide 3.8 g (5 mmol, yield 75%) of a crude compound. [M+H]⁺ 323.

7-3. Synthesis of the following compound as intermediate



To a 100 ml round-bottom flask, 1.5 g (4.5 mmol) of 2,5-dibromo-3,4-dinitrothiophen, 3 g (10 mmol) of the compound obtained from the above step 7-2, 20 ml of 2M
 5 potassium carbonate (K_2CO_3), 30 ml of THF and tetrakis(triphenyl phosphine)palladium(0) ($Pd(PPh_3)_4$) (0.1 g, 0.09 mmol) were introduced. Then the reaction mixture was refluxed for 24 hours. After the completion of the reaction, the reaction mixture was cooled to room temperature. THF was
 10 removed from the reaction mixture and a small amount of ethanol was added thereto, followed by stirring to form a solid. The resultant solid was filtered and washed with water and ethanol and dried in a vacuum oven to provide 1.2 g (1.83 mmol, yield 41%) of the target compound. $[M+H]^+$ 657.

15 7-4. Synthesis of compound of formula 1-15



[formula 1-15]

1.2 g (1.83 mmol) of the compound obtained from the above step 7-3 was introduced into 150 ml of THF, 5 ml of EtOH and 10 ml of water. Then, 0.6 g (11 mmol, 6 eq.) of
 20 iron (Fe) powder was added thereto and the reaction mixture

was refluxed for 48 hours. The reaction mixture was cooled to room temperature and unreacted Fe or salts thereof were filtered off. Next, the solvents were removed from the filtrate under reduced pressure. After filtering, the product was washed with distilled water and n-hexane to provide about 1 g of a crude solid.

1 g of the crude compound, i.e., 2,5-disubstituted 3,4-diaminothiophene obtained from the above and 0.17 g (1 mmol) of camphorquinone were stirred in 20 ml of acetic acid for 48 hours at 120°C. The reaction mixture was cooled to room temperature, 20 ml of ethanol was added thereto and then the mixture was stirred to obtain a reddish purple solid. Next, the resultant solid was filtered, washed with ethanol and then dried. The product was loaded on silica gel and purified by column chromatography (n-hexane/ethyl acetate: 8/1). The product was precipitated with ethanol, and the resultant product was filtered and dried to provide 0.1 g of the compound of formula 1-15 (yield 81%).

m.p. : 336 °C

¹H NMR in CDCl₃ δ : 8.57 (d,2H), 8.47 (d,2H), 8.20 (d,4H), 7.50 (m,16H), 3.08(d,1H), 2.32 (m,1H), 2.14 (t,1H), 1.60(d,5H), 1.18 (s,3H), 0.83 (s,3H)

Absorption Spectrum : λ_{max} 450nm (solvent :2x10⁻⁵M toluene)

Fluorescence Spectrum: λ_{max} 582nm (excitation wavelength 446nm, solvent: 2x10⁻⁵M toluene)

[M+H]⁺ 727.

Hereinafter, the present invention will be explained in detail with reference to preferred embodiments of organic light emitting devices using the compounds obtained from the

above Preparation Examples.


Example 1

A glass substrate on which a thin film of ITO (indium tin oxide) was coated to a thickness of 1000Å was immersed
5 in distilled water containing a detergent to wash the substrate with ultrasonic waves. The detergent was a product commercially available from Fisher Co. The distilled water has been filtered two times by using a filter commercially available from Millipore Co. The ITO-coated substrate was
10 washed with distilled water for 30 minutes and then further washed with ultrasonic waves two times, each for 10 minutes. After the completion of washing with distilled water, washing with ultrasonic waves was carried out by using solvents such as isopropyl alcohol, acetone and methanol, in
15 turn. The resultant product was dried and transferred to a plasma cleaner.

Then, the substrate was cleaned for 5 minutes by using nitrogen plasma and transferred to a vacuum deposition device.


20 On the ITO transparent electrode prepared as described above, hexanitrile hexaazatriphenylene represented by the following formula 4 was coated to a thickness of 500Å by thermal vacuum deposition, thereby forming a hole injection layer.

25 [Formula 4]




Next, NPB [N,N-bis(naphthalen-1-yl)-N,N-bis(phenyl) benzidine] of the following formula 5 as a hole transport material was coated thereon to a thickness of 400Å by vacuum deposition, thereby forming a hole transport layer.

[formula 5]




Additionally, Alq3 of the following formula 6-1 as a light emitting host was mixed with 2% of the compound of formula 1-1 obtained from Preparation Example 1 as a red dopant. Then, the mixture was coated on the hole transport layer to a thickness of 300Å by vacuum deposition to form a light emitting layer.

[formula 6-1]



On the light emitting layer, the compound represented by the following formula 7 capable of functioning as an electron injection/transport layer was coated to a thickness of 200Å by vacuum deposition to complete the formation of a thin organic film.

[formula 7]




Next, on the electron injection/transport layer, lithium fluoride (LiF) and aluminum were sequentially deposited to a thickness of 12Å and 2500Å, respectively, to form a cathode. In the above process, deposition rate of each organic substance was maintained at 0.3 to 0.8 Å/sec and deposition rates of lithium fluoride and aluminum were maintained at 0.3 Å/sec and 1.5-2.5 Å/sec, respectively.

After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 6.47 V was formed. Additionally, spectrum with a luminance of 2386 nit was observed with x=0.512 and y=0.449 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.5}) needed for reducing the luminance to a value corresponding to 50% of the initial luminance was 420 hours.

Example 2

Example 1 was repeated to provide an organic light emitting device, except that the compound of the following formula 6 was used as a light emitting host when forming a light emitting layer.

5 [formula 6]



After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 5.60 V was formed. Additionally, spectrum with a luminance of 1891 nit was observed with x=0.649 and y=0.337 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.75}) needed for reducing the luminance to a value corresponding to 75% of the initial luminance was 1200 hours.

Example 3

Example 1 was repeated to provide an organic light emitting device, except that the compound of formula 1-2
20 obtained from Preparation Example 2 was used as a dopant when forming a light emitting layer.

After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 7.75 V was formed.

Additionally, spectrum with a luminance of 1224 nit was observed with $x=0.646$ and $y=0.351$ based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm^2 , the time
5 ($L_{0.7}$) needed for reducing the luminance to a value corresponding to 70% of the initial luminance was 600 hours.

Example 4

Example 1 was repeated to provide an organic light emitting device, except that the compound of the above
10 formula 6 and the compound of formula 1-2 obtained from Preparation Example 2 was used as a light emitting host and a dopant, respectively, when forming a light emitting layer.

After a forward current of 100 mA/cm^2 was applied to the resultant organic light emitting device, an electric
15 field with the driving voltage of 6.22 V was formed. Additionally, spectrum with a luminance of 1888 nit was observed with $x=0.653$ and $y=0.345$ based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm^2 , the time
20 ($L_{0.8}$) needed for reducing the luminance to a value corresponding to 80% of the initial luminance was 600 hours.

Example 5

Example 1 was repeated to provide an organic light emitting device, except that the compound of the above
25 formula 6 and the compound of formula 1-5 obtained from Preparation Example 3 was used as a light emitting host and a dopant, respectively, when forming a light emitting layer.

After a forward current of 100 mA/cm^2 was applied to the resultant organic light emitting device, an electric
30 field with the driving voltage of 6.38 V was formed.

Additionally, spectrum with a luminance of 875 nit was observed with $x=0.667$ and $y=0.331$ based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm^2 , the time
5 ($L_{0.95}$) needed for reducing the luminance to a value corresponding to 95% of the initial luminance was 300 hours.


Example 6

Example 1 was repeated to provide an organic light emitting device, except that the compound of the above
10 formula 6 and the compound of formula 1-6 obtained from Preparation Example 4 was used as a light emitting host and a dopant, respectively, when forming a light emitting layer.

After a forward current of 100 mA/cm^2 was applied to the resultant organic light emitting device, an electric
15 field with the driving voltage of 5.08 V was formed. Additionally, spectrum with a luminance of 3576 nit was observed with $x=0.482$ and $y=0.505$ based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm^2 , the time
20 ($L_{0.85}$) needed for reducing the luminance to a value corresponding to 85% of the initial luminance was 50 hours.

Comparative Example 1

Example 1 was repeated to provide an organic light emitting device, except that DCJTB [4-(dicyanomethylene)-2-t-
25 butyl-6-(1,1,7,7-tetramethyljulolidyl-9-enyl)-4H-pyran] represented by the following formula was used as a dopant when forming a light emitting layer.



After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 9.02 V was formed. Additionally, spectrum with a luminance of 1037 nit was observed with x=0.616 and y=0.379 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.5}) needed for reducing the luminance to a value corresponding to 50% of the initial luminance was 200 hours.

Comparative Example 2

Example 1 was repeated to provide an organic light emitting device, except that the compound of the above formula 6 and DCJTBT were used as a light emitting host and a dopant, respectively, when forming a light emitting layer.

After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 5.48 V was formed. Additionally, spectrum with a luminance of 2958 nit was observed with x=0.614 and y=0.379 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.5}) needed for reducing the luminance to a value corresponding to 50% of the initial luminance was 950 hours.

Comparative Example 3

Example 1 was repeated to provide an organic light

emitting device, except that no dopant was used when forming a light emitting layer.

After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 5.70 V was formed. Additionally, spectrum with a luminance of 3381 nit was observed with x=0.331 and y=0.561 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.5}) needed for reducing the luminance to a value corresponding to 50% of the initial luminance was 400 hours.

Comparative Example 4

Example 2 was repeated to provide an organic light emitting device, except that the compound of the above formula 6 was used as a light emitting host and no dopant was used, when forming a light emitting layer.

After a forward current of 100 mA/cm² was applied to the resultant organic light emitting device, an electric field with the driving voltage of 5.35 V was formed. Additionally, spectrum with a luminance of 4134 nit was observed with x=0.378 and y=0.580 based on the 1931 CIE color coordinate. Further, when a constant direct current was applied at a current density of 100 mA/cm², the time (L_{0.5}) needed for reducing the luminance to a value corresponding to 50% of the initial luminance was 750 hours.

The results obtained from the above Examples and Comparative Examples are summarized in the following Table 1.

5 [Table 1]

Ex. Comp. Ex.	Host	Dopant (conc. %)	Voltage (V)	Max. Emission Wave length (nm)	External quantum efficiency (%) /Luminance (cd/m ²) @ 100 mA	Life time (hr) (L _A)*	Color Coordinate (x, y)
Ex. 1	Alq3	formula 1-1 (2 %)	6.47	642	1.47/2386	420 (L _{0.5})	(0.512, 0.449)
Ex. 2	formula 6	formula 1-1 (2 %)	5.60	640	2.33/1891	1200 (L _{0.75})	(0.638, 0.358)
Ex. 3	Alq3	formula 1-2 (2 %)	7.75	642	1.08/1224	600 (L _{0.7})	(0.646, 0.351)
Ex. 4	formula 6	formula 1-2 (2 %)	6.22	640	2.46/1888	600 (L _{0.8})	(0.653, 0.345)
Ex. 5	6	formula 1-5 (2 %)	6.38	650	1.70/875	300 (L _{0.95})	(0.667, 0.331)
Ex. 6	formula 6	formula 1-6 (2 %)	5.08	570	0.24/3576	50 (L _{0.85})	(0.482, 0.505)
Comp.Ex.1	Alq3	DCJTB (2 %)	9.02	615	0.94/1037	200 (L _{0.5})	(0.616, 0.379)
Comp.Ex.2	formula 6	DCJTB (2 %)	5.48	610	2.03/2958	950 (L _{0.5})	(0.614, 0.379)
Comp.Ex.3	Alq3	No	5.70	535	1.0/3381	400 (L _{0.5})	(0.331, 0.561)
Comp.Ex.4	formula 6	No	5.35	540	1.21/4134	750 (L _{0.5})	(0.378/0.580)
(L _A)* means the life time during which the luminance reduces to A x 100% of the initial luminance.							

As shown in Table 1, when the compound of formula 1 is used in an organic light emitting device, it is possible to obtain excellent red color purity, to cause the device to be driven at low voltage, and to improve the life time of the device.

Example 6 using the compound of formula 1-6 as a dopant shows a lower efficiency compared to other Examples using the compound according to the present invention. However, it is considered that a preferred organic light emitting device can be provided according to Example 6 by using a suitable host.

Comparative Example 5

Example 1 was repeated to provide an organic light emitting device, except that a compound similar to the compound of formula 1-1 (with the exception that the compound was substituted with dimethyl group instead of cycloalkyl group) was used as a dopant, when forming a light emitting layer.

In the compound used in this example, a stacking phenomenon occurred among flat-like molecules resulting in intermolecular interactions, and thus the light emitting efficiency decreased. In fact, when doped to Alq3 at a concentration of 2%, the compound of formula 1-1 and the dimethyl-substituted compound showed quantum efficiency/luminance (cd/m²) results of 1.08/1224 (cd/m²) and 0.19/61 (cd/m²), respectively, at a current density of 100 mA/m².

Industrial Applicability

As can be seen from the foregoing, the compound of formula 1 according to the present invention can provide a highly efficient light emitting material that is capable of emitting yellow, orange or red light and has excellent thermal stability. Further, when the compound of formula 1 is used as a light emitting host or dopant in an organic light emitting device, it is possible to improve the life


time of the device and to cause the device to be driven at low voltage.

While this invention has been described in connection with what is presently considered to be the most practical
5 and preferred embodiment, it is to be understood that the invention is not limited to the disclosed embodiment and the drawings. On the contrary, it is intended to cover various modifications and variations within the spirit and scope of the appended claims.

Claims

1. A compound represented by formula 1:

[formula 1]



5

wherein R_0 represents a lower alkyl group having 1-6 carbon atoms; and

R_1 and R_2 are identical or different, and each is selected from the group consisting of H; an aromatic compound and derivatives thereof; a 5-membered or 6-membered heteroaromatic compound and derivatives thereof; an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; an alkylamine including an alkyl group having 1-20 carbon atoms, which is non-substituted or substituted with at least one substituent selected from the group consisting of an aliphatic hydrocarbon having 1-20 carbon atoms and derivatives thereof; an aralkylamine including an alkyl group having 1-20 carbon atoms, which is non-substituted or substituted with at least one substituent selected from the group consisting of an aliphatic hydrocarbon having 1-20 carbon atoms, an aromatic compound, a heteroaromatic compound and derivatives thereof; an arylamine non-substituted or substituted with at least one substituent selected from the group consisting of an aromatic compound, a heteroaromatic compound and derivatives


thereof; and a silicon or boron compound non-substituted or substituted with at least one substituent selected from the group consisting of an aromatic compound, a heteroaromatic compound and derivatives thereof;

5 R1 and R2 may form a fused ring together; or


R1 and R2 are linked linearly to permit the compound represented by formula 1 to form a polymer.

2. The compound according to claim 1, wherein the
10 compound is selected from the group consisting of compounds represented by formulae 1-1 to 1-46:

[formula 1-1]




[formula 1-2]




15

[formula 1-3]




[formula 1-4]




5


[formula 1-5]




[formula 1-6]




[formula 1-7]




[formula 1-8]




[formula 1-9]




[formula 1-10]




[formula 1-11]




[formula 1-12]




[formula 1-13]




[formula 1-14]




[formula 1-15]




[formula 1-16]




[formula 1-17]




[formula 1-18]




[formula 1-19]




[formula 1-20]




[formula 1-21]




[formula 1-22]




[formula 1-23]




[formula 1-24]




[formula 1-25]




[formula 1-26]




[formula 1-27]




[formula 1-28]




[formula 1-29]




[formula 1-30]




[formula 1-31]




[formula 1-32]




[formula 1-33]




[formula 1-34]




[formula 1-35]



[formula 1-36]




[formula 1-37]



5


wherein n is an integer of 2 or more.

[formula 1-38]




wherein n is an integer of 2 or more.

[formula 1-39]




wherein n is an integer of 2 or more; and each of R4 and R5
 5 is independently or simultaneously selected from the group
 consisting of H, an linear or branched aliphatic hydrocarbon
 having 1-20 carbon atoms, and an alkoxy group including a
 linear or branched aliphatic hydrocarbon having 1-20 carbon
 atoms; or R4 and R5 may form a fused ring together.

10 [formula 1-40]



wherein n is an integer of 2 or more.

[formula 1-41]



wherein n is an integer of 2 or more; and each of R4 and R5 is independently or simultaneously selected from the group consisting of H, an linear or branched aliphatic hydrocarbon having 1-20 carbon atoms, and an alkoxy group including a
5 linear or branched aliphatic hydrocarbon having 1-20 carbon atoms; or R4 and R5 may form a fused ring together.

3. The compound according to claim 1, wherein the compound represented by formula 1 is for use in an organic
10 light emitting device as a light emitting material.

4. A method for preparing the compound represented by formula 1 according to claim 1, comprising the steps of:

(a) coupling a boronic acid having a substituent R1, a
15 boronic acid having a substituent R2 and 2,5-dihalo-3,4-dinitrothiophene in the presence of a base by adding a Pd-containing catalyst, wherein R1 and R2 are the same as defined in claim 1;

(b) reducing nitro (NO₂) groups in the compound
20 obtained from step (a) into amino (NH₂) groups; and

(c) reacting the compound obtained from step (b) with camphorquinone.

5. A method for preparing the compound represented by
25 formula 1 according to claim 1, comprising the steps of:

(a) introducing halogen atoms into 2,5-position of 3,4-diaminothiophene compound;

(b) reacting the compound obtained from step (a) with camphorquinone to form a thianopyrazine compound; and

30 (c) coupling a boronic acid having a substituent R1, a

boronic acid having a substituent R2 and 2,5-dihalogen thianopyrazine compound obtained from step (b) in the presence of a base by adding a Pd-containing catalyst, wherein R1 and R2 are the same as defined in claim 1.

5

6. An organic light emitting device including a first electrode, an organic film having one or more layers and a second electrode, laminated successively, wherein at least one layer of the organic film includes at least one compound represented by formula 1 defined in any one of claims 1 to 3.

7. The organic light emitting device according to claim 6, wherein the compound represented by formula 1 is present in at least one form selected from the group consisting of (R)-isomer, (S)-isomer and mixtures thereof.

1/2

FIG. 1




FIG. 2





FIG. 3



2/2

FIG. 4





FIG. 5



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2004/002822

A. CLASSIFICATION OF SUBJECT MATTER**IPC7 C09K 11/06**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7 C07D265/32, C09K11/06, H05B33/14

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
Korean Patents and applications for inventions since 1975
Korean Utility models and applications for Utility models since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NPS, PAJ, USPAT, STN

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6,413,658 B1 (FUJI PHOTO FILM CO., LTD.) 02. JULY 2002 abstract, column2 line8-column3 line15, example1-2	1,3-6
A	US 6,379,823 B1 (FUJI PHOTO FILM CO., LTD.) 30. APRIL 2002 column2 line5-column3 line21, claim1	1, 3,6
A	JP 10-251633 A (TOYO INK MANUFACTURING CO., LTD.) 22. SEPTEMBER 1998 claim1, table1, example1-2	1,3,6
A	WO 00/58418 A1 (BAYER AKTIENGESSELLSCHAFT) 05. OCTOBER 2000 page7 line1-page10 line13, claim1	1

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 FEBRUARY 2005 (18.02.2005)

Date of mailing of the international search report

23 FEBRUARY 2005 (23.02.2005)

Name and mailing address of the ISA/KR



Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

CHOI, Seung Keun

Telephone No. 82-42-481-5575



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2004/002822

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 6,413,658 B1	02.07.2002	JP 2001-19947 A2	23.01.2001
US 6,379,823 B1	30.04.2002	JP 11-193351 A2	02.06.1999
JP 10-251633 A	22.09.1998	US 6,280,859 BA EP 934,992 B1	28.08.2001 21.07.2004
WO 00/58418 A1	05.10.2000	US 6,344,918 BA JP 2002-540486 T2 EP 1181339 A1	05.02.2002 26.11.2002 27.02.2002

专利名称(译)	能够用于有机发光器件的有机层的新化合物		
公开(公告)号	EP1680481A1	公开(公告)日	2006-07-19
申请号	EP2004800013	申请日	2004-11-04
[标]申请(专利权)人(译)	乐金化学股份有限公司		
申请(专利权)人(译)	LG化学有限公司.		
当前申请(专利权)人(译)	LG化学有限公司.		
[标]发明人	BAE JAE SOON KANG MIN SOO		
发明人	BAE, JAE-SOON KANG, MIN-SOO		
IPC分类号	C09K11/06 C07D495/08 C07D519/00 C08G61/12 H01L51/00 H01L51/50 H05B33/14		
CPC分类号	C07D495/08 C08G61/12 C08G61/124 C08G61/126 C09K11/06 C09K2211/1044 C09K2211/1092 H01L51/0036 H01L51/0043 H01L51/0052 H01L51/006 H01L51/0061 H01L51/0069 H01L51/5012 H05B33/14 Y10S428/917		
优先权	1020030077707 2003-11-04 KR		
其他公开文献	EP1680481A4 EP1680481B1		
外部链接	Espacenet		

摘要(译)

公开了由下式1表示的化合物作为发光材料：[式1]其中R₀，R₁和R₂中的每一个与本文中定义的相同。还公开了一种有机发光器件，其包括连续层压的第一电极，具有一层或多层的有机膜和第二电极。至少一层有机膜包括至少一种由式1表示的化合物。该有机发光器件在发光效率，寿命和热稳定性方面表现出优异的特性。