

(19)



(11)

EP 2 555 595 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

04.03.2015 Bulletin 2015/10

(51) Int Cl.:

H01L 27/32 ^(2006.01)

H01L 51/52 ^(2006.01)

(86) International application number:

PCT/JP2012/000160

(21) Application number: **12751820.7**

(22) Date of filing: **12.01.2012**

(87) International publication number:

WO 2012/117656 (07.09.2012 Gazette 2012/36)

(54) **ORGANIC EL PANEL AND METHOD FOR MANUFACTURING SAME**

ORGANISCHE EL-TAFEL UND VERFAHREN ZU IHRER HERSTELLUNG

PANNEAU ÉLECTROLUMINESCENT (EL) ORGANIQUE ET SON PROCÉDÉ DE FABRICATION

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **02.03.2011 JP 2011045014**

(43) Date of publication of application:

06.02.2013 Bulletin 2013/06

(73) Proprietor: **Panasonic Corporation**

Osaka 571-8501 (JP)

(72) Inventor: **MIYAZAWA, Kazutoshi**

Osaka 540-6207 (JP)

(74) Representative: **Schwabe - Sandmair - Marx**

Patentanwälte

Stuntzstraße 16

81677 München (DE)

(56) References cited:

JP-A- 2002 260 857

JP-A- 2002 343 567

JP-A- 2004 281 328

JP-A- 2008 159 930

US-A1- 2001 017 517

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 555 595 B1

Description

Technical Field

[0001] The present invention relates to organic EL panels and methods of manufacturing the same.

Background Art

[0002] An active matrix organic EL panel includes a TFT panel incorporated with thin-film transistors (TFTs) for controlling each individual sub-pixel, and organic EL devices disposed over the TFT panel.

[0003] Each organic EL device used in organic EL displays generally includes a pixel electrode formed over the surface of the TFT panel; an organic functional layer disposed over the pixel electrode, which organic functional layer contains fluorescent molecules; and a counter electrode disposed over the organic functional layer.

[0004] Recent increases in size and definition of organic EL panels has resulted in high probability of generation of defects in which portions of interconnects (e.g., pixel electrodes) on the TFT panel's surface are lost. For improved production yields, various approaches have been proposed that aim to repair such defects generated in the interconnects on the TFT panel (see, e.g., Patent Literatures 1 to 3).

[0005] For example, Patent Literature 1 discloses repairing defective interconnects by coating the defect with a conductive repair paste (repair liquid) and baking the same by irradiation with a laser beam. Patent Literature 2 discloses repairing defective interconnects by depositing metal in the defect by irradiation with a laser beam using laser CVD apparatus. Patent Literature 3 discloses repairing defective interconnects by firmly attaching a metal film-bearing transfer member to the defect and irradiating the same with a laser beam to transfer the metallic film into the defect.

[0006] Other known approaches include applying a laser beam onto a heat-sensitive layer on the out-coupling side of a defective pixel of an organic EL device to form a light diffusion zone in the heat-sensitive layer, to lessen luminance reduction at the defective pixel (see, e.g., Patent Literatures 4 and 5); detecting, after formation of an organic luminescent layer, a pattern defect in the organic luminescent layer using infrared rays before proceeding to the subsequent step (see, e.g., Patent Literatures 6 and 7); covering the defect in the pixel electrode with insulating material prior to counter electrode formation (see, e.g., Patent Literature 8); cutting, among the multiplicity of interconnection layers stacked on top of each other, only the interconnect in the defective interconnection layer by laser etching based on the stored data such that the defect is electrically separated (see, e.g., Patent Literature 9); configuring organic EL devices to include pixel electrodes disposed on the planarized surface of a TFT panel (see, e.g., Patent Literatures 10 and 11); and configuring organic EL devices to include insulating films

between the electrode layers of TFTs for preventing short circuits between the electrodes (see, e.g., Patent Literatures 12 and 13).

5 Citation List

Patent Literature

[0007]

10

[PTL 1] Japanese Patent Application Laid-Open No.08-203898

[PTL 2] Japanese Patent Application Laid-Open No.2002-131888

15

[PTL 3] Japanese Patent Application Laid-Open No.2009-251119

[PTL 4] Japanese Patent Application Laid-Open No.2009-027036

[PTL 5] U.S. Patent Application Publication No.2009/0021156

20

[PTL 6] Japanese Patent Application Laid-Open No.2009-158126

[PTL 7] U.S. Patent Application Publication No.2009/0159817

25

[PTL 8] Japanese Patent Application Laid-Open No.2004-253214

[PTL 9] Japanese Patent Application Laid-Open No.2007-123616

30

[PTL 10] Japanese Patent Application Laid-Open No.2002-083691

[PTL 11] U.S. Patent Application Publication No.2000/0047567

[PTL 12] Japanese Patent Application Laid-Open No.2004-103488

35

[PTL 13] U.S. Patent Application Publication No.2004/0119399

Summary of Invention

40 Technical Problem

[0008] All of the repairing methods disclosed by Patent Literatures 1 to 3 require expensive equipment such as laser CVD apparatus or transfer apparatus, contributing to increased production costs. These repairing methods are also time-consuming and therefore rapid repair of interconnects has been difficult.

45

[0009] Furthermore, the repairing methods disclosed by Patent Literatures 1 to 3 are directed to repair of relatively large defects. For example, difficulties have been encountered with these methods in repairing defects of 20 μm or less in diameter. More specifically, when attempting to repair relatively small defects by laser CVD as taught in Patent Literature 2, it becomes more likely that the device is contaminated with foreign substance, which is undesirable. Moreover, when attempting to repair relatively small defects by attachment of new interconnect material as taught in Patent Literature 1 or 3,

50

55

there are cases where the interconnect material is misplaced or where the repaired interconnect becomes non-uniform in thickness.

[0010] It has thus been difficult with the conventional repairing methods to successfully repair defective pixel electrodes having a relatively small defect. The defect in the pixel electrode becomes a non-luminescent area (defect) in the resultant organic EL device. Accordingly, unless any proper measure is taken, even a small defect causes a local luminance reduction in the organic EL device, leading to poor organic EL panel quality.

[0011] The present invention has been accomplished in an aim to overcome the foregoing drawback pertinent in the art, and an object of the present invention is to provide a method of manufacturing an organic EL panel, which method enables to easily lessen local luminance reductions at defects in pixel electrodes in short time.

[0012] The prior art document JP 2002-343567 A discloses the following:

The problem to be solved is to provide a manufacturing method of an organic EL element that can prevent growth of a non-emission part (dark spot) by filling the electrode breakage part and cut-out part by a simple method, and further provide a manufacturing method of an exposure device and an light-emission device or the like that have arranged the organic EL element in an array shape or a matrix shape or the like. The solution is a liquid drop containing a non-conductive material is injected in the defective part 503 of the electrode layer 502 that is formed on a transparent substrate 501, and by heating and evaporating the solvent of the liquid drop entered in the defective part 503, the non-conductive membrane is formed, and thereby, the defective part is filled.

[0013] The document US 2001/017517 AI discloses the following:

A light emitting device having superior responsibility is provided. A pixel electrode (anode) connected to a drain wiring or a current control TFT has a slit. The slit becomes a path for the light emitted from an EL layer, and emitted light can be extracted using a light shielding metallic film as the pixel electrode. A material having a low resistance can thus be used as the pixel electrode, and therefore a light emitting device having superior responsibility can be obtained.

Solution to Problem

[0014] The inventor has established that luminance reduction caused by defects in pixel electrodes can be avoided by roughening the exposed surface of the TFT panel at the defects without having to repair the defects. The inventor then completed the present invention with additional studies.

[0015] The object is solved by the subject-matter of the independent claims. The dependent claims are directed to embodiments of advantage.

Advantageous Effects of Invention

[0016] The present invention enables to lessen luminance reductions at defects in pixel electrodes in short time without relying on expensive equipment. The present invention thus enables rapid and inexpensive manufacture of organic EL panels having minimized luminance unevenness.

Brief Description of Drawings

[0017]

FIG.1 is a flowchart of a method of manufacturing an organic EL panel according to an embodiment of the present invention;

FIG.2 is a graph of luminance at the center of a defect versus defect size;

FIG.3 is a graph showing light transmittance of a TFT panel with and without a roughened surface;

FIG.4 is a cross-sectional view of an organic EL device according to an embodiment of the present invention;

FIG.5 is a cross-sectional view of an organic EL device not forming part of the present invention;

FIG.6 is a perspective view of a pixel electrode having a defect; and

FIG.7 illustrates a flow of manufacture of an organic EL panel according to an embodiment of the present invention.

Description of Embodiments

1. Method of Manufacturing Organic EL Panel

[0018] The present invention is effective particularly for the manufacture of large-screen organic EL panels. The reason for this is that manufacture of large-screen organic EL displays suffers from high risk of generation of defects in the pixel electrodes and therefore it is highly necessary to lessen luminance reductions caused by such defects. A manufacturing method according to an embodiment of the present invention will now be described with reference to the flowchart depicted in FIG.1.

[0019] As seen from the flowchart depicted in FIG.1, the manufacturing method according to an embodiment of the present invention includes: 1) a first step of providing a TFT panel (S1100); 2) a second step of patterning pixel electrodes on a surface of the TFT panel (S1200); 3) a third step of detecting in the pixel electrodes any defect in which the surface of the TFT panel is exposed (S1300); 4) a fourth step of roughening a surface of the TFT panel by applying a laser beam thereon, the surface being exposed through the defect in the pixel

electrode (S1400); 5) a fifth step of forming an organic functional layer over the pixel electrode and the surface of the TFT panel exposed through the defect in the pixel electrode (S1500); and 6) a sixth step of forming a counter electrode over the organic functional layer (S1600). Each step will now be described in detail.

1) In the first step, a TFT panel is provided. Pixel electrodes (later described), i.e., organic EL devices are disposed on a surface of the TFT panel. The TFT panel includes a substrate, thin-film transistors (hereinafter may simply referred to as "TFTs") disposed over the substrate in matrix arrangement; and a planarization film disposed over the substrate so as to cover the TFTs. The planarization film constitutes the surface of the TFT panel. The TFT panel may be provided by applying resin material, a material of the planarization film, over a surface of a substrate having TFTs disposed in matrix arrangement and by curing the resin material. Examples of the resin material to be applied include photosensitive resins. Thus the planarization film is formed of, for example, a cured product of photosensitive resin.

2) In the second step, pixel electrodes are patterned on the surface of the TFT panel in matrix arrangement or other arrangement. Patterning of pixel electrodes on the surface of the TFT panel in matrix arrangement may be accomplished by depositing a metal film made of pixel electrode material onto the entire surface of the TFT panel by sputtering, vapor deposition or other method, and etching the deposited metal film by photolithography.

There are cases where during etching of the metal film to pattern pixel electrodes an otherwise un-etched area of the metal film is also etched, resulting in a portion of the patterned pixel electrode being lost. Such a defect in the pixel electrode (hereinafter may simply referred to as "defect") becomes a non-luminescent area in the resulting organic EL device. If such a defect in the pixel electrode is left without being repaired, the organic EL device exhibits reduced luminance.

The following description of the third and fourth steps is directed to a measure with which to lessen luminance reductions at such defects in the pixel electrodes.

3) In the third step, the pixel electrodes are checked for the presence of a defect, where the surface of the TFT panel is exposed. There are no particular limitations on the method of detection of defects; examples include microscopic visual inspection, image inspection, and pattern inspection. Image inspection and pattern inspection includes the die-to-die inspection mode in which the images of adjacent dies are compared for detecting defects, and the die-to-database inspection mode in which dies are compared with corresponding design data for detecting defects.

When any defect has been detected, the process proceeds to the fourth step, where a measure is taken to lessen luminance reduction at the defect. On the other hand, when no defects have been detected, the process skips the fourth step and proceeds to the subsequent step.

4) In the fourth step, a laser beam is applied onto a portion of the surface of the TFT panel, which portion includes a surface exposed through the defect in the pixel electrode (hereinafter may simply referred to as "exposed surface"), to roughen the exposed surface. The expression "laser beam is applied onto a surface of a TFT panel" as used herein means to focus a laser beam on the exposed surface of the TFT panel.

[0020] There are no particular limitations on the laser source used for laser irradiation; examples include flash lamp-pumped Nd:YAG laser. When an Nd:YAG laser is employed, the wavelength of laser beam can be selected from 1,064 nm (fundamental), 532 nm (second harmonics), 355 nm (third harmonics), and 266 nm (fourth harmonics) wavelengths.

[0021] The wavelength of the laser beam to be applied onto the surface of the TFT panel is preferably 532 nm or less, most preferably 400 nm or less. That is, when employing an Nd:YAG laser, the third or fourth harmonics wavelength may be employed. This is because laser beams with a wavelength of 400 nm or less are more likely to be absorbed by the planarization film that constitutes the TFT panel's surface and therefore are capable of roughening of the panel's surface at high energy efficiency.

[0022] The energy (energy density) of the laser beam to be applied may be set to a level enough to effect roughening of the TFT panel's surface. The energy level of the laser beam is determined according to the material and/or thickness of the planarization film that constitutes the TFT panel's surface.

[0023] For example, when the TFT panel's surface (planarization film material: positive-type photosensitive resin, thickness: 5 μm) is to be roughened using an Nd:YAG laser, it is preferable to employ the third harmonics wavelength (355 nm) with the energy density set at 0.35 J/cm² or above.

[0024] Roughening of a TFT panel's surface exposed through a defect in a pixel electrode (hereinafter may simply referred to as "roughening of a defect") as described above enables to lessen luminance reduction at the defect. How roughening of a defect is associated with lessening of luminance reduction at the defect will be described in detail later in the section titled "2. Organic EL panel."

[0025] In some embodiments, only some selected defects may be roughened rather than roughening all of the defects detected. When roughening is intended for only selected defect(s), the manufacturing method according to an embodiment of the present invention includes, be-

tween the third and fourth steps, the steps of: a) determining a criteria on which to select a defect to be repaired; and b) selecting, from the defects that have been detected, defect(s) that comply with the criteria.

[0026] In step a), a criteria on which to select a defect to be repaired is determined. The "criteria on which to select a defect to be repaired" herein is the distance between a point within a defect, which point is the farthest away from all the points along the edge of the defect, and the edge of the defect (hereinafter may also referred to as "maximum distance"). The "criteria on which to select a defect to be repaired" varies depending on the required luminance at the defect.

[0027] FIG.2 is an exemplary graph of luminance at a given point in a defect versus distance between the point and the edge of the defect (the boundary between the luminescent area and defect). The luminance at a point within a defect is expressed as percent of the luminance at the luminescent area. As seen from FIG.2, luminance at a given point within a defect decreases as it becomes farther away from the edge of the defect. More specifically, in the case of a roughened defect, the defect exhibits 80% luminance at a point spaced from the edge of the defect by 2.5 μm , and 50% luminance at a point spaced from the edge of the defect by 10 μm . On the other hand, in the case of a non-roughened defect, the defect exhibits 80% luminance at a point spaced from the edge of the defect by 0.5 μm , and 50% luminance at a point spaced from the edge of the defect by 2 μm .

[0028] Accordingly, when the required luminance at defects is 50% or more of the luminance at the luminescent area, the "criteria on which to select a defect to be repaired" may be set to 2 μm to 10 μm . Roughening of defects having a maximum distance of 10 μm or less ensures that the luminance at the defects is 50% or more of the luminance at the luminescent area. Moreover, with regard to defects having a maximum distance of less than 2 μm , the luminance at the defects does not decrease to 50% or less of the luminance at the luminescent area even when they are not roughened. On the other hand, with regard to defects having a maximum distance exceeding 10 μm , the luminance at the defects cannot be increased to a level exceeding 50% of the luminance at the luminescent area even when they are roughened. Thus, when intending to increase the luminance at defects having a maximum distance exceeding 10 μm to a level exceeding 50% of the luminance of the luminescent area, they are preferably repaired in the manner commonly known in the art - by forming new films of electrode material within the defects.

[0029] When the required luminance at defects is 80% or more of the luminance at the luminescent area, the "criteria on which to select a defect to be repaired" may be set to 0.5 μm to 2.5 μm . Roughening of defects having a maximum distance of 2.5 μm or less ensures that the luminance at the defects is 80% or more of the luminance at the luminescent area. Moreover, with regard to defects having a maximum distance of less than 0.5 μm , the lu-

minance at the defects does not decrease to 80% or less of the luminance at the luminescent area even when they are not roughened. On the other hand, with regard to defects having a maximum distance exceeding 2.5 μm , the luminance at the defects cannot be increased to a level exceeding 80% of the luminance at the luminescent area even when they are roughened.

Thus, when intending to increase the luminance at defects having a maximum distance exceeding 2.5 μm to a level exceeding 80% of the luminance of the luminescent area, it is preferable to repair these defects in the manner commonly known in the art - by forming new electrode films in the defects.

[0030] As described above, the "criteria on which to select a defect to be repaired" is determined based on the relationship between the distance from the edge of the defect and luminances of the TFT panel surface before and after roughening. This relationship can be found experimentally by, for example, roughening a surface of a model TFT panel (later described) to a desired level.

5) In the fifth step, an organic functional layer is formed over the pixel electrode and a surface of the TFT panel exposed through the defect in the pixel electrode. The formation of the organic functional layer in an organic EL device may be accomplished either by vapor deposition or coating techniques. In view of achieving a large-screen organic EL display, the organic functional layer is preferably formed by coating techniques. Formation of the organic functional layer by coating techniques may be accomplished by applying an ink containing the material of the organic functional layer and a solvent by inkjet printing, dispensing nozzle coating, spin coating, intaglio printing, relief printing or other coating technique, followed by drying the applied ink.

6) In the sixth step, a counter electrode is formed over the organic functional layer. The counter electrode is formed by, for example, sputtering.

[0031] In this way the present invention enables lessening of luminance reduction at defects without having to form new films of electrode material within the defects, which has been carried out in the art. The present invention thus enables to lessen luminance reductions of organic EL devices at low costs.

2. Organic EL Panel

[0032] An organic EL panel according to an embodiment of the present invention is one manufactured by the above-described manufacturing method of the present invention. The organic EL panel is of the top-emission type as well as of the active matrix type, including a TFT panel and organic EL devices disposed over the surface of the TFT panel in matrix arrangement.

[0033] The TFT panel includes a substrate, thin-film transistors (hereinafter may simply referred to as "TFTs")

disposed over the substrate in matrix arrangement; and a planarization film disposed over the substrate so as to cover the TFTs.

[0034] Examples of the material of the substrate include silicon carbide (SiC), alumina (Al₂O₃), aluminum nitride (AlN), glass, silicon, and germanium wafer.

[0035] Each TFT includes a source electrode; a drain electrode; a channel formed of a semiconductor layer for connecting together the source electrode and drain electrode; a gate electrode for controlling the channel; and a gate insulation film for electrically isolating the gate electrode from the source electrode and drain electrode.

[0036] There are no particular limitations on the material of the planarization film as long as it is electrically insulating and a pattern of contact holes or like pattern can be formed therein; examples thereof include acrylic and polyimide resins.

[0037] Each organic EL device includes a pixel electrode disposed over the surface of the TFT panel; an organic functional layer disposed over the pixel electrode; and a counter electrode disposed over the organic functional layer. The organic EL devices may further include a bank for defining the organic functional layer.

[0038] The pixel electrode is an electrically conductive member. The pixel electrode generally serves as an anode, but may serve as a cathode. The pixel electrode preferably has light reflectivity. Examples of materials of the pixel electrode include APC alloys (silver-palladium-copper alloys), ARA alloys (silver-ruthenium-gold alloys), MoCr alloys (molybdenum/chrome alloys), and NiCr alloys (nickel/chrome alloys). The pixel electrode may be connected to the drain electrode or source electrode of a TFT through a contact hole provided in the planarization film on the TFT panel.

[0039] The organic functional layer includes an organic luminescent layer containing organic luminescent material. The organic luminescent material contained in the organic luminescent layer is preferably polymeric organic luminescent material so that the layer can be formed by coating methods. Examples of the polymeric organic luminescent material include polyphenylenevinylene and its derivatives, polyacetylene and its derivatives, polyphenylene and its derivatives, poly para phenylene ethylene and its derivatives, poly(3-hexylthiophene) and its derivatives, and polyfluorene and its derivatives.

[0040] The organic luminescent layer emits red, green or blue light depending on the position of the organic EL device. The organic functional layer may further include a hole injection layer, a hole transport layer, an electron transport layer, and other layers.

[0041] The bank is an insulating partition wall for defining the organic functional layer. The bank may be patterned by exposing and developing a resist material, which is a photosensitive material.

[0042] The counter electrode is an electrically conductive member disposed over the organic functional layer. The counter electrode generally serves as a cathode, but may also serve as an anode. The counter electrode pref-

erably has a light transmittance. Examples of materials of the counter electrode include ITO and IZO. The counter electrode is about 100 nm in thickness.

[0043] A feature of the present invention is that the surface of the TFT panel exposed through a defect in a pixel electrode is roughened. There are no particular limitations on the degree to which the exposed surface is roughened, as long as the TFT panel exhibits reduced light transmittance (or luminance) at the exposed surface due to light diffusion. The exposed surface is roughened to an arithmetic average roughness of 0.25 μm or more which is preferably smaller than the thickness of the planarization film. Measurement of arithmetic average roughness of the roughened exposed surface can be accomplished using any of the general surface roughness analyzers.

[0044] In the present invention the surface of the TFT panel exposed through a defect in a pixel electrode is roughened as described above, whereby luminance reduction at the defect, a non-luminescent area, is lessened. How roughening of a defect is associated with lessening of luminance reduction at the defect will now be described with reference to the accompanying drawings.

[0045] FIG.3 shows light transmittances of a TFT panel model before and after roughening, where the TFT panel model includes a 0.7 mm-thick glass substrate and a 5 μm-thick resin film disposed on the glass substrate. The wavelength of a laser beam used to roughen the resin surface of the TFT panel model is 355 nm with energy density set at 0.35 J/cm². Light beams of different wavelengths are then applied onto the resin surface of the TFT panel, measuring intensities of the light beams passed through the glass substrate to measure light transmittance of the manufactured TFT panel. As seen from FIG.3, for example, a TFT panel having a roughened surface successfully exhibited approximately 10% reduced transmittance to light having a wavelength of 500 nm to 800 nm. The fact that a TFT panel that has a roughened resin surface exhibited reduced light transmittance suggests that the TFT panel exhibits increased light reflectivity correspondingly.

[0046] As described above, a TFT panel having a roughened surface exhibits reduced light transmittance. How reduced light transmittance of a TFT panel is associated with lessening of luminance reduction at a defect will now be described.

[0047] FIG.4 illustrates an organic EL device having defect 121 in pixel electrode 120. Organic EL device 100 includes TFT panel 110, pixel electrode 120, organic functional layer 130, counter electrode 140, and sealing layer 150. Organic EL device 100 has defect 121 in which a portion of pixel electrode 120 is lost. A surface of TFT panel 110 is exposed through - defect 121. Surface 111 of TFT panel 110 exposed through defect 121 is roughened.

[0048] Since defect 121 is a non-luminescent area (defect) as described above, organic functional layer 130 does not emit light at a position corresponding to defect

121. Nevertheless, light beams emitting from other areas of organic functional layer 130 around defect 121 also travel into defect 121. Thus, light can also be out-coupled from defect 121, a non-luminescent area. Moreover, since TFT panel 110 exhibits reduced light transmittance at roughened surface 111 as described above, light beams travelled into defect 121, where roughened surface 111 is present, are less likely to pass through TFT panel 110. Thus, most of the light beams travelled into defect 121 do not pass through TFT panel 110 and can be out-coupled from counter electrode 140 side. In this way the present invention makes it possible to out-couple light from defect 121 even when defect 121 forms a non-luminescent area, lessening luminance reduction at defect 121.

[0049] On the other hand, when surface 111 of the TFT panel exposed through defect 121 is not roughened as illustrated in FIG.5, the TFT panel exhibits high light transmittance. Thus, light beams travelled into defect 121 from surrounding areas of organic functional layer 130 are more likely to pass through TFT panel 110 to the outside. Thus, when surface 111 of the TFT panel exposed through defect 121 is not roughened, the amount of light which can be out-coupled from counter electrode 140 side is reduced by an amount corresponding to the amount of light passing through the TFT panel to the outside, resulting in reduced luminance.

[0050] A method of manufacturing an organic EL display according to an embodiment of the present invention will now be described with reference to the accompanying drawings. The following description is focused on the manufacturing steps subsequent to the third step in which detection of defects is carried out.

[0051] FIG.6 is a perspective view of a pixel electrode having a defect detected in the third step (step of detecting any defect in the pixel electrodes). FIG.7A is a cross-sectional view of the defective pixel electrode illustrated in FIG.6, which is cut along dashed line AA.

[0052] As illustrated in FIG.6 and FIG.7A, surface 111 of TFT panel 110 is exposed through a defect in the pixel electrode. The TFT panel includes substrate 113 having thereon TFTs, and planarization film 115 disposed over the substrate so as to cover the TFTs.

[0053] FIG.7B illustrates the fourth step (laser irradiation step) according to the present invention. As illustrated in FIG.7B, in the third step, laser beam 170 is applied onto surface 111 exposed through defect 121.

[0054] By irradiation with laser beam 170, the surface of the TFT panel exposed through defect 121 is roughened (FIG.7C).

[0055] FIG.7D illustrates the fifth step according to the present invention. As illustrated in FIG.7D, in the fifth step, organic functional layer 130 is formed over pixel electrode 120 and surface 111 by application of a material solution of organic functional layer 130.

[0056] FIG.7E illustrates the sixth step according to the present invention. As illustrated in FIG.7E, in the sixth step, counter electrode 140 is formed over organic func-

tional layer 130 by, for example, sputtering.

Industrial Applicability

- 5 **[0057]** The manufacturing method according to an embodiment of the present invention enables lessening of luminance reduction at defects in pixel electrodes without needing having to repair the defects, whereby reduced defects rates and improved quality are realized for organic EL panels.

Reference Signs List

[0058]

- 15 100 Organic EL device
110 TFT panel
111 Surface of TFT panel exposed through defect
113 Substrate
20 115 Planarization Film
120 Pixel electrode
121 Defect
130 Organic functional layer
140 Counter electrode
25 150 Sealing film
170 Laser beam

Claims

- 30 1. A method of manufacturing an organic EL panel, comprising:
- 35 providing a TFT panel (110);
patterning pixel electrodes (120) on a surface of the TFT panel (110);
detecting in the pixel electrodes (120) defects (121) in which the surface of the TFT panel (110) is exposed;
40 roughening a portion of the surface of the TFT panel (110) by applying a laser beam onto the portion, the portion including a surface exposed through the defect (121) in the pixel electrode (120);
45 forming an organic functional layer (130) over the pixel electrodes (120) and the surface of the TFT panel (110) exposed through the defect (121) in the pixel electrode (120); and
forming a counter electrode (140) over the organic functional layer (130).
- 50 2. The method according to claim 1, wherein the laser beam has a wavelength of 400 nm or less.
- 55 3. The method according to claim 1, further comprising:
- determining a criteria on which to select one or more of the defects (121) to be repaired; and

selecting, from the defects (121) detected, one or more of the defects (121) that comply with the criteria,
wherein the laser beam is applied onto the surface of the TFT panel (110), the surface exposed through the one or more of the defects (121) selected.

4. An organic EL panel comprising:

a TFT panel (110); and
organic EL devices (100) disposed over a surface of the TFT panel (110) in matrix arrangement, each of the organic EL devices (100) including a pixel electrode (120) disposed over the surface of the TFT panel (110), an organic luminescent layer disposed over the pixel electrode (120), and a counter electrode (140) disposed over the organic functional layer (130), wherein at least one of the organic EL devices (100) has a defect (121) in which the surface of the TFT panel (110) is exposed;

characterized in that

the surface exposed through the defect (121) has an arithmetic average roughness of $0.25\text{ }\mu\text{m}$ or more.

5. The organic EL panel according to claim 4, wherein the TFT panel (110) includes a substrate (113), TFTs disposed over the substrate (113) in matrix arrangement, and a planarization film (115) disposed over the substrate (113) so as to cover the TFTs, the planarization film (115) constituting the surface of the TFT panel (110).

6. The organic EL panel according to claim 5, wherein the planarization film (115) is formed of a cured product of a photosensitive resin.

Patentansprüche

1. Verfahren zum Herstellen einer organischen EL-Tafel, das Folgendes umfasst:

Bereitstellen einer TFT-Tafel (110);
Mustern von Pixelelektroden (120) auf einer Oberfläche der TFT-Tafel (110);
Detektieren von Fehlern (121) in den Pixelelektroden (120), in denen die Oberfläche der TFT-Tafel (110) freigelegt ist;
Aufräumen eines Abschnitts der Oberfläche der TFT-Tafel (110) durch Anwenden eines Laserstrahls auf den Abschnitt, wobei der Abschnitt eine Oberfläche enthält, die durch den Schaden (121) in der Pixelelektrode (120) freigelegt ist;
Bilden einer organischen Funktionsschicht (130) über den Pixelelektroden (120) und der

Oberfläche der TFT-Tafel (110), die durch den Fehler (121) in der Pixelelektrode (120) freigelegt ist, und
Bilden einer Gegenelektrode (140) über der organischen Funktionsschicht (130).

2. Verfahren nach Anspruch 1, wobei der Laserstrahl eine Wellenlänge von 400 nm oder weniger hat.

3. Verfahren nach Anspruch 1, das ferner Folgendes umfasst:

Bestimmen eines Kriteriums, nach dem einer oder mehrere der Fehler (121), die ausgebessert werden sollen, ausgewählt werden, und
Auswählen eines oder mehrerer der Fehler (121) aus den detektierten Fehlern (121), die das Kriterium erfüllen,
wobei der Laserstrahl auf die Oberfläche der TFT-Tafel (110) angewendet wird, wobei die Oberfläche durch den einen oder die mehreren der ausgewählten Fehler (121) freigelegt ist.

4. Organische EL-Tafel, die Folgendes umfasst:

eine TFT-Tafel (110) und
organische EL-Vorrichtungen (100), die über einer Oberfläche der TFT-Tafel (110) in Matrixgestalt angeordnet sind, wobei jede der organischen EL-Vorrichtungen (100) eine Pixelelektrode (120), die über der Oberfläche der TFT-Tafel (110) angeordnet ist, eine organische Lumineszenzschicht, die über der Pixelelektrode (120) angeordnet ist, und eine Gegenelektrode (140), die über der organischen Funktionsschicht (130) angeordnet ist, enthält,
wobei mindestens eine der organischen EL-Vorrichtungen (100) einen Fehler (121) besitzt, in dem die Oberfläche der TFT-Tafel (110) freigelegt ist;

dadurch gekennzeichnet, dass

die Oberfläche, die durch den Fehler (121) freigelegt ist, eine arithmetische Durchschnittsrauigkeit von $0,25\text{ }\mu\text{m}$ oder mehr hat.

5. Organische EL-Tafel nach Anspruch 4, wobei die TFT-Tafel (110) ein Substrat (113), TFTs, die in einer Matrixgestalt über dem Substrat (113) angeordnet sind, und einen Planarisierungsfilm (115), der über dem Substrat (113) angeordnet ist, um die TFTs abzudecken, enthält, wobei der Planarisierungsfilm (115) die Oberfläche der TFT-Tafel (110) ausmacht.

6. Organische EL-Tafel nach Anspruch 5, wobei der Planarisierungsfilm (115) aus einem gehärteten Erzeugnis aus einem lichtempfindlichen Harz gebildet ist.

Revendications

1. Procédé de fabrication d'un panneau électroluminescent (EL) organique, comportant :

la mise à disposition d'un panneau TCM (110) ;
 la mise en configuration d'électrodes de pixel (120) sur une surface du panneau TCM (110) ;
 la détection de défauts (121) dans les électrodes de pixel (120) par lesquels la surface du panneau TCM (110) est exposée ;
 le fait de rendre rugueuse une partie de la surface du panneau TCM (110) en y appliquant un rayon laser, ladite partie comportant une surface exposée en raison du défaut (121) dans l'électrode de pixel (120) ;
 la formation d'une couche fonctionnelle organique (130) par-dessus les électrodes de pixel (120) et la surface du panneau TCM (110) exposées en raison du défaut (121) dans l'électrode de pixel (120) ;
 et la formation d'une contre-électrode (140) par-dessus la couche fonctionnelle organique (130).

2. Procédé selon la revendication 1, où le rayon laser a une longueur d'onde de 400 nm ou moins.

3. Procédé selon la revendication 1, comportant en outre :

la détermination d'un critère sur la base duquel sont sélectionnés un ou plusieurs défauts (121) à réparer ; et
 la sélection parmi les défauts (121) détectés, d'un ou plusieurs défauts (121) conformes à ce critère,
 où le rayon laser est appliqué à la surface du panneau TCM (110), sur la surface exposée par un ou plusieurs des défauts (121) sélectionnés.

4. Panneau électroluminescent (EL) organique, comportant :

un panneau TCM (110) ; et
 des dispositifs EL organiques (100) disposés sur une surface du panneau TCM (110) sous forme de matrice, chacun des dispositifs EL organiques (100) comportant une électrode de pixel (120) disposée par-dessus la surface du panneau TCM (110), une couche luminescente organique disposée sur l'électrode de pixel (120) et une contre-électrode (140) disposée sur la couche fonctionnelle organique (130) ;
 où au moins un des dispositifs EL organiques (100) a un défaut (121) en raison duquel la surface du panneau TCM (110) est exposée ;
caractérisé en ce que
 la surface exposée en raison du défaut (121) a

une rugosité dont la moyenne arithmétique est de 0,25 μm ou plus.

5. Panneau EL organique selon la revendication 4, où le panneau TCM (110) inclut un substrat (113), des TCM disposés par-dessus le substrat (113) sous forme de matrice, et un film d'aplanissement (115) disposé par-dessus le substrat (113) de manière à couvrir les TCM, le film d'aplanissement (115) formant la surface du panneau TCM (110).
6. Panneau EL organique selon la revendication 5, où le film d'aplanissement (115) est constitué d'un produit durci d'une résine photosensible.




FIG.1




FIG.2




FIG.3




FIG.4




FIG.5




FIG. 6

FIG.7A




FIG.7B




FIG.7C




FIG.7D





FIG.7E



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 8203898 A [0007]
- JP 2002131888 A [0007]
- JP 2009251119 A [0007]
- JP 2009027036 A [0007]
- US 20090021156 A [0007]
- JP 2009158126 A [0007]
- US 20090159817 A [0007]
- JP 2004253214 A [0007]
- JP 2007123616 A [0007]
- JP 2002083691 A [0007]
- US 20000047567 A [0007]
- JP 2004103488 A [0007]
- US 20040119399 A [0007]
- JP 2002343567 A [0012]
- US 2001017517 A1 [0013]

专利名称(译)	有机EL板及其制造方法		
公开(公告)号	EP2555595B1	公开(公告)日	2015-03-04
申请号	EP2012751820	申请日	2012-01-12
[标]申请(专利权)人(译)	松下电器产业株式会社		
申请(专利权)人(译)	松下电器产业株式会社		
当前申请(专利权)人(译)	JOLED INC.		
[标]发明人	MIYAZAWA KAZUTOSHI		
发明人	MIYAZAWA, KAZUTOSHI		
IPC分类号	H01L27/32 H01L51/52		
CPC分类号	H01L27/3244 H01L2251/568		
优先权	2011045014 2011-03-02 JP		
其他公开文献	EP2555595A4 EP2555595A1		
外部链接	Espacenet		

摘要(译)

本发明通过快速简便的方法防止像素电极中的缺陷局部亮度降低。本发明提供一种制造有机EL面板的方法，该有机EL面板包括TFT面板和以矩阵排列设置在TFT面板表面上的有机EL器件，每个有机EL器件包括设置在TFT表面上的像素电极面板，设置在像素电极上的有机发光层和设置在有机功能层上的对电极。该方法包括以下步骤：提供TFT面板；图案化TFT面板表面上的像素电极；检测像素电极中暴露出TFT面板表面的缺陷；通过在该部分上施加激光束来粗糙化TFT面板的一部分表面，该部分包括通过像素电极中的缺陷暴露的表面；在像素电极和TFT面板表面上形成有机功能层，通过像素电极中的缺陷露出；在有机功能层上形成对电极。




FIG. 1