



(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(43) Date of publication:
05.08.2015 Bulletin 2015/32

(51) Int Cl.:
H01L 51/50 ^(2006.01) **C07F 5/02** ^(2006.01)
C09K 11/06 ^(2006.01)

(21) Application number: **13841725.8**

(86) International application number:
PCT/JP2013/075937

(22) Date of filing: **25.09.2013**

(87) International publication number:
WO 2014/050904 (03.04.2014 Gazette 2014/14)

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME

- **KAI, Takahiro**
Kitakyushu-shi
Fukuoka 804-8503 (JP)
- **KOMORI, Masaki**
Kitakyushu-shi
Fukuoka 804-8503 (JP)
- **YAMAMOTO, Toshihiro**
Tokyo 101-0021 (JP)
- **TADA, Masashi**
Kitakyushu-shi
Fukuoka 804-8503 (JP)

(30) Priority: **28.09.2012 JP 2012216564**

(71) Applicant: **Nippon Steel & Sumikin Chemical Co., Ltd.**
Chiyoda-ku
Tokyo 101-0021 (JP)


(74) Representative: **Vossius & Partner**
Patentanwälte Rechtsanwälte mbB
Siebertstrasse 3
81675 München (DE)

(72) Inventors:
• **SANNOMIYA, Rumi**
Kitakyushu-shi
Fukuoka 804-8503 (JP)

(54) **COMPOUND FOR ORGANIC ELECTROLUMINESCENT ELEMENTS, AND ORGANIC ELECTROLUMINESCENT ELEMENT**

(57) Provided are an organic EL device practically satisfactory in terms of its light-emitting characteristics, driving voltage, and durability, and a compound for an organic EL device to be used in the device. The organic EL device has a structure in which an anode, a plurality of organic layers including a light-emitting layer, and a cathode are laminated on a substrate, and the organic EL device contains an indolocarbazole compound in at least one organic layer selected from the light-emitting layer, a hole-transporting layer, an electron-transporting layer, a hole-blocking layer, and an electron-blocking layer. The indolocarbazole compound is a compound having, in a molecule thereof, at least one boron-containing group having such a structure that boron of the boron-containing group is bonded to an atom on a linking group bonded to a nitrogen atom of an indolocarbazole ring or to a carbon atom of the ring.

FIG. 1



Description

Technical Field

5 **[0001]** The present invention relates to a novel compound for an organic electroluminescent device and an organic electroluminescent device using the compound, and more specifically, to a thin-film-type device that emits light when an electric field is applied to a light-emitting layer formed of an organic compound.

Background Art

10 **[0002]** In general, an organic electroluminescent device (hereinafter referred to as organic EL device) is constructed of a light-emitting layer and a pair of counter electrodes interposing the light-emitting layer therebetween in its simplest structure. That is, the organic EL device uses the phenomenon that, when an electric field is applied between both the electrodes, electrons are injected from a cathode and holes are injected from an anode, and each electron and each
15 hole recombine in the light-emitting layer to emit light.

[0003] In recent years, progress has been made in developing an organic EL device using an organic thin film. In order to enhance luminous efficiency particularly, the optimization of the kind of electrodes has been attempted for the purpose of improving the efficiency of injection of carriers from the electrodes. As a result, there has been developed a device in which a hole-transporting layer formed of an aromatic diamine and a light-emitting layer formed of an 8-
20 hydroxyquinoline aluminum complex (hereinafter referred to as Alq3) are formed between electrodes as thin films, resulting in a significant improvement in luminous efficiency, as compared to related-art devices in which a single crystal of anthracene or the like is used. Thus, the development of the above-mentioned organic EL device has been promoted in order to accomplish its practical application to a high-performance flat panel having features such as self-luminescence and rapid response.

25 **[0004]** Further, studies have been made on using phosphorescent light rather than fluorescent light as an attempt to raise the luminous efficiency of a device. Many kinds of devices including the above-mentioned device in which a hole-transporting layer formed of an aromatic diamine and a light-emitting layer formed of Alq3 are formed emit light by using fluorescent light emission. However, by using phosphorescent light emission, that is, by using light emission from a triplet excited state, luminous efficiency is expected to be improved by from about three times to four times, as compared
30 to the case of using related-art devices in which fluorescent light (singlet) is used. In order to accomplish this purpose, studies have been made on adopting a coumarin derivative or a benzophenone derivative as a light-emitting layer, but extremely low luminance has only been provided. Further, studies have been made on using a europium complex as an attempt to use a triplet state, but highly efficient light emission has not been accomplished. In recent years, many studies on a phosphorescent light-emitting dopant material centered on an organic metal complex such as an iridium
35 complex have been made, as described in Patent Literature 1, for the purpose of attaining high luminous efficiency and a long lifetime.

Citation List

40 Patent Literature

[0005]

45 [PTL 1] WO 01/041512 A
[PTL 2] JP 2001-313178 A
[PTL 3] JP 11-162650 A
[PTL 4] JP 11-176578 A
[PTL 5] WO 2008/056746 A
[PTL 6] WO 2008/146839 A
50 [PTL 7] WO 2010/114243 A

[0006] In order to obtain high luminous efficiency, host materials that are used with the dopant materials described above play an important role. A typical example of the host materials proposed is 4,4'-bis(9-carbazolyl)biphenyl (hereinafter referred to as CBP) as a carbazole compound disclosed in Patent Literature 2. When CBP is used as a host
55 material for a green phosphorescent light-emitting material typified by a tris (2-phenylpyridine) iridium complex (hereinafter referred to as Ir(ppy)₃), the injection balance between charges is disturbed because CBP has the characteristic of facilitating the delivery of holes and not facilitating the delivery of electrons. Thus, excessively delivered holes flow out into an electron-transporting layer side, with the result that the luminous efficiency from Ir(ppy)₃ lowers.

[0007] In order to provide high luminous efficiency to an organic EL device as described above, it is necessary to use a host material that has high triplet excitation energy, and is striking a good balance in both charge (hole and electron)-injecting/transporting property. Further desired is a compound that has electrochemical stability, has high heat resistance, and has excellent amorphous stability, and hence further improvement has been demanded.

[0008] Patent Literature 3 discloses an indolocarbazole compound having a diphenylamino group as a hole-transporting material. Patent Literature 4 discloses a diphenylindolocarbazole compound as a hole-transporting material. Patent Literature 5 and Patent Literature 6 disclose nitrogen-containing heterocyclic group-substituted indolocarbazole compounds having a substituent as phosphorescent host materials, and disclose that organic EL devices using the compounds are improved in luminous efficiency and have high driving stability.


[0009] Each of Patent Literatures 1 to 6 discloses that a compound having an indolocarbazole skeleton is used in an organic EL device, but none of the literatures discloses a compound having a boron-containing group on an indolocarbazole skeleton. In addition, Patent Literature 7 teaches a compound obtained by substituting a fused five-membered ring with various substituents but does not teach any compound having a boron-containing group on an indolocarbazole skeleton.

Summary of Invention

[0010] In order to apply an organic EL device to a display device in a flat panel display or the like, it is necessary to improve the luminous efficiency of the device and also to ensure sufficiently the stability in driving the device at a low driving voltage or the like. The present invention has an object to provide, in view of the above-mentioned circumstances, an organic EL device that has high efficiency, has high luminance stability when driven, and is practically useful and a compound suitable for the organic EL device.

[0011] The inventors of the present invention have made intensive studies and have consequently found that, when a compound having an indolocarbazole skeleton with a specific structure is used in an organic EL device, the organic EL device exhibits excellent characteristics. As a result, the present invention has been completed.

[0012] A compound for an organic EL device of the present invention is represented by the following general formula (1).



[0013] In the general formula (1), a ring I represents an aromatic hydrocarbon ring represented by the formula (1a) to be fused to adjacent rings at arbitrary positions, and a ring II represents a heterocycle represented by the formula (1b) to be fused to adjacent rings at arbitrary positions.

[0014] In the general formula (1) and the formula (1b), L₁ and L₂ each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group formed by linking two to six of the substituted or



unsubstituted aromatic rings, the linked aromatic group may be linear or branched, and the aromatic rings to be linked may be identical to or different from each other. Further, L_1 represents an $i+1$ -valent group and L_2 represents a $k+1$ -valent group.



[0015] In the general formula (1) and the formula (1b), Z represents a boron-containing group represented by the formula (1c), and in the formula (1c), A_1 and A_2 each independently represent hydrogen, deuterium, an alkyl group having 1 to 12 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, a hydroxyl group, chlorine, bromine, fluorine, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, and A_1 and A_2 may be bonded to adjacent A_1 and A_2 or substituents of A_1 and A_2 to form a ring.

[0016] In the general formula (1) and the formula (1a), Rs each independently represent deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a cyano group, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an amino group, a nitro group, an acyl group having 2 to 12 carbon atoms, an alkoxycarbonyl group having 2 to 12 carbon atoms, a carboxyl group, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a hydroxyl group, an amide group, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a boron-containing group represented by the formula (1c).

[0017] In the general formula (1), p and q each independently represent an integer of from 0 to 4, and in the formula (1a), r represents an integer of from 0 to 2. In the general formula (1) and the formula (1b), i and k each represent an integer of from 0 to 5, provided that $p+q+r+i+k \geq 1$ and when both of i and k represent 0, at least one of Rs represents a boron-containing group represented by the formula (1c), and when p, q, r, i, and k each represent 2 or more, Rs and Zs may be identical to or different from each other.

[0018] Examples of the compound for an organic EL device represented by the general formula (1) include compounds represented by the following general formulae (2) to (5).





[0019] In the general formulae (2) to (5), L_1 , L_2 , Z , R , p , q , r , i , and k each have the same meaning as that of the general formula (1).

[0020] In the general formulae (1) to (5) and the formula (1a), it is preferred that R s each independently represent deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an acyl group having 2 to 12 carbon atoms, an alkoxy carbonyl group having 2 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a boron-containing group represented by the formula (1c).

[0021] In the formula (1c), it is preferred that A_1 and A_2 each independently represent an alkyl group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, and it is more preferred that A_1 and A_2 each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms.

[0022] In addition, it is preferred that in each of the general formulae (1) to (5), $i+k \geq 1$ and R s not represent boron-containing groups each represented by the formula (1c).

[0023] In addition, the present invention relates to an organic EL device including an organic layer containing the compound for an organic EL device. The organic layer is preferably at least one layer selected from a light-emitting layer, a hole-transporting layer, a hole-injecting layer, an electron-transporting layer, and an electron-injecting layer. It is more preferred that the light-emitting layer contain a phosphorescent light-emitting dopant and the compound for an organic EL device represented by any one of the general formulae (1) to (5) as a host material.

Effects of Invention

[0024] The indolocarbazole compound for an organic EL device of the present invention has at least one boron-containing group in a molecule of the indolocarbazole compound. A boron atom of the boron-containing group has an unoccupied orbital on its molecular orbital, and hence the group has a low lowest unoccupied molecular orbital (LUMO) energy level and has a characteristic by which an energy gap with respect to the valence band of a cathode is reduced. Accordingly, the use of the compound of the present invention in an organic EL device can be expected to exhibit an effect by which charge-injecting/transporting properties are improved and hence the voltage of the organic EL device is reduced.

[0025] Because of the foregoing, the organic EL device using the indolocarbazole compound can realize a carrier balance optimum for various dopants in its light-emitting layer. As a result, an organic EL device significantly improved in light-emitting characteristics can be provided. Further, the indolocarbazole compound can improve stability in each

of active states, i.e., oxidation, reduction, and excitation, and at the same time, has a good amorphous characteristic. Accordingly, the compound can realize an organic EL device that can be driven at a low voltage and has high durability.

Brief Description of Drawings

[0026]

FIG. 1 is a sectional view illustrating a structure example of an organic EL device.

FIG. 2 shows the $^1\text{H-NMR}$ chart of Compound B9 for an organic EL device of the present invention.


Description of Embodiments

[0027] A compound for an organic EL device of the present invention is represented by the general formula (1).


[0028] In the general formula (1), a ring I represents an aromatic hydrocarbon ring represented by the formula (1a) to be fused to adjacent rings at arbitrary positions, and a ring II represents a heterocycle represented by the formula (1b) to be fused to adjacent rings at arbitrary positions.

[0029] In the indolocarbazole skeleton represented by the general formula (1), the aromatic hydrocarbon ring represented by the formula (1a) may be fused with two adjacent rings at arbitrary positions, but there is a position at which the aromatic hydrocarbon ring cannot be fused with the rings from the structural viewpoint. The aromatic hydrocarbon ring represented by the formula (1a) has six sides, and is not fused with the two adjacent rings through two adjacent sides. Further, the heterocycle represented by the formula (1b) may be fused with two adjacent rings at arbitrary positions, but there is a position at which the heterocycle cannot be fused with the rings from the structural viewpoint. That is, the heterocycle represented by the formula (1b) has five sides, and is not fused with the two adjacent rings through two adjacent sides and is not fused with an adjacent ring through a side including a nitrogen atom. Thus, there is a limitation on the kind of the indolocarbazole skeleton.


[0030] The general formula (1), the indolocarbazole skeleton is preferably represented by any one of the following structures. Preferred fusion positions of the aromatic hydrocarbon ring and the heterocycle in the indolocarbazole skeleton are understood from these examples.




(IC-1)



(IC-2)



(IC-3)



(IC-4)


[0031] In the general formula (1), L_1 represents an $i+1$ -valent group, and L_2 represents a $k+1$ -valent group. L_1 and L_2 each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group in which two to six of aromatic rings of the aromatic hydrocarbon groups or the aromatic heterocyclic groups are linked, preferably a substituted or unsubstituted aromatic hydrocarbon group having 6 to 12 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 12 carbon atoms, or a substituted or unsubstituted linked aromatic group produced by linking two to six of the substituted or unsubstituted aromatic rings. In the case of the linked aromatic group, the group may be linear or branched, and the aromatic rings to be linked may be identical to or different from each other.



[0032] Specific examples of the case where L_1 and L_2 each represent an unsubstituted aromatic hydrocarbon group, aromatic heterocyclic group, or linked aromatic group in which two to six of the substituted or unsubstituted aromatic rings are linked include: a group produced by removing $i+1$ or $k+1$ hydrogen atoms from an aromatic compound such as benzene, pentalene, indene, naphthalene, anthracene, phenanthrene, pyrrole, imidazole, pyrazole, thiazole, thiophene, pyridine, pyrazine, pyrimidine, pyridazine, triazine, isoindole, indazole, purine, benzimidazole, indolizine, chromene, benzoxazole, isobenzofuran, quinolizine, isoquinoline, imidazole, naphthyridine, phthalazine, quinazoline, quinoxaline, cinnoline, quinoline, pteridine, perimidine, phenanthroline, phenanthridine, acridine, phenazine, phenothiazine, phenoxazine, phenazasiline, dibenzodioxin, carboline, indole, indoloindole, carbazole, furan, benzofuran, isobenzofuran, benzothiazole, oxanthrene, dibenzofuran, thiophene, thioxanthene, thianthrene, phenoxathiin, thionaphthene, isothianaphthene, thiophthene, thiophanthrene, or dibenzothiophene; and a group produced by removing $i+1$ or $k+1$ hydrogen atoms from an aromatic compound in which two to six of such groups are linked.

[0033] As a substituent in the case where L_1 and L_2 each represent an aromatic hydrocarbon group having a substituent, an aromatic heterocyclic group having a substituent, or a linked aromatic group having a substituent, there is given deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a cyano group, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an amino group, a nitro group, an acyl group, an alkoxy carbonyl group having 2 to 12 carbon atoms, a carboxyl group, an alkoxyl group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a hydroxyl group, an amide group, a phenoxy group, or an alkylthio group having 1 to 12 carbon atoms.

[0034] Of those, the following substituent is preferred: deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an acyl group having 2 to 12 carbon atoms, an alkoxy carbonyl group having 2 to 12 carbon atoms, an alkoxyl group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a phenoxy group, or an alkylthio group having 1 to 12 carbon atoms.


[0035] Here, when L_1 and L_2 each represent an unsubstituted monovalent linked aromatic group, examples of the structure of the linked aromatic group include such structures as represented by the following formulae (6) to (8). It should be noted that when i or k represents 1 or more, structures each produced by removing i or k hydrogen atoms from any one of those structures are adopted.






[0036] In the formulae (6) to (8), Ar₁ to Ar₆ each represent an unsubstituted monocyclic or fused aromatic ring, and may be identical to or different from one another.

[0037] Specific examples of the case where L₁ and L₂ each represent an unsubstituted linked aromatic group, and the case where L₁ and L₂ are each represented by any one of the formulae (6) to (8) include such groups as shown below and groups each produced by removing i or k hydrogen atoms from any one of these groups.





[0038] In the formulae, R' represents an aromatic hydrocarbon group having 6 to 18 carbon atoms or an aromatic heterocyclic group having 3 to 17 carbon atoms. Specific examples of the aromatic hydrocarbon group and the aromatic heterocyclic group are the same as those described for L₁ and L₂ in the general formula (1) except that the valence of each of the examples is one.

[0039] In the general formula (1) and the formula (1b), Z represents a boron-containing group represented by the formula (1c).

[0040] In the formula (1c), A₁ and A₂ each independently represent hydrogen, deuterium, an alkyl group having 1 to 12 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, a hydroxyl group, chlorine, bromine, fluorine, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, preferably a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms. In addition, when A₁ and A₂ each represent an aromatic hydrocarbon group or an aromatic heterocyclic group, the groups may be bonded

to each other to form a ring. For example, the two aromatic rings may be bonded to form a ring together with B. Further, substituents of the two aromatic rings may be bonded to each other to form a ring. In addition, one aromatic ring and a substituent of the other aromatic ring may be bonded to form a ring.

[0041] A substituent in the case where A_1 and A_2 each represent an aromatic hydrocarbon group having a substituent or an aromatic heterocyclic group having a substituent is deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a cyano group, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an amino group, a nitro group, an acyl group, an alkoxy carbonyl group having 2 to 12 carbon atoms, a carboxyl group, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a hydroxyl group, chlorine, bromine, fluorine, an amide group, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, an aromatic hydrocarbon group having 6 to 18 carbon atoms, or an aromatic heterocyclic group having 3 to 17 carbon atoms. Of those, the following substituent is preferred: deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, an aromatic hydrocarbon group having 6 to 18 carbon atoms, or an aromatic heterocyclic group having 3 to 17 carbon atoms.

[0042] In the general formula (1), the formula (1a), and the formula (1b), Rs each independently represent deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 2 to 12 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a cyano group, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an amino group, a nitro group, an acyl group having 2 to 12 carbon atoms, an alkoxy carbonyl group having 2 to 12 carbon atoms, a carboxyl group, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a hydroxyl group, an amide group, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a boron-containing group represented by the formula (1c), preferably deuterium, an alkyl group having 1 to 12 carbon atoms, a cycloalkyl group having 3 to 10 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 12 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 12 carbon atoms, or a boron-containing group. The substituent in the case where Rs each represent an aromatic hydrocarbon group having a substituent or an aromatic heterocyclic group having a substituent has the same meaning as the substituent in the case where A_1 and A_2 each represent an aromatic hydrocarbon group having a substituent or an aromatic heterocyclic group having a substituent.

[0043] In the general formula (1), the formula (1a), and the formula (1b), p and q each independently represent an integer of from 0 to 4, r represents an integer of from 0 to 2, and i and k each represent an integer of from 0 to 5. It is preferred that p, q, r, i, and k each independently represent 0 or 1.


[0044] Here, $p+q+r+i+k \geq 1$ and at least one boron-containing group represented by the formula (1c) is present in the general formula (1). It is preferred that $i+k$ be 1 or more and Rs each represent a group except a boron-containing group represented by the formula (1c). When p, q, r, i, and k each represent 2 or more, Rs and Zs may be identical to or different from each other.

[0045] Preferred examples of the indolocarbazole compound represented by the general formula (1) include indolocarbazole compounds each represented by any one of the general formulae (2) to (5). In the general formulae (2) to (5), symbols common to the general formula (1), the formula (1a), the formula (1b), and the formula (1c) each have the same meaning.


[0046] A skeleton represented by any one of the formulae (IC-1) to (IC-4) is available as a preferred skeleton of the indolocarbazole compound represented by the general formula (1). The general formula (1) is a concept comprehending the skeletons represented by the formulae (IC-1) to (IC-4), and these skeletons can be described by taking the compound represented by the general formula (1) as a typical example.

[0047] Such skeletons as represented in the forms of the formulae (IC-1) to (IC-4) are each conceivable as the skeleton of the indolocarbazole compound represented by the general formula (1), and these skeletons can each be synthesized by employing a known approach from a raw material selected in accordance with the structure of a target compound.


[0048] For example, the indolocarbazole skeleton represented by the formula (IC-1) can be synthesized by the following reaction formula with reference to a synthesis example described in Synlett, 2005, No. 1, p42-48.



[0049] Further, the indolocarbazole skeleton represented by the formula (IC-3) can be synthesized by the following reaction formula with reference to a synthesis example described in Archiv der Pharmazie (Weinheim, Germany) 1987, 320(3), p280-2.




[0050] Specific examples of the indolocarbazole compound represented by the general formula (1) are shown below. However, the material for an organic EL device of the present invention is not limited thereto.




5

10




A9




A10

15

20




A11




A12

25


30



A13



A14




A15


35

40


45



A16




A17




A18

50


55




A19




A20




A21




A22




A23




A24




A25




A26




A27




A28




A29




A30




A31




A32




A33




A34




A35




A36




A37




A38




A39




A40




A41



A42




A43




A44


5
10
15
20
25
30
35
40
45
50
55




A45




B1




B2




B3




B4




B5




B6




B7




B8




B9




B10




B11




B12




B13




B14




B15




B16




B17




B18




B19




B20




B21




B22




B23




B24




B25




B26




B27




B28




B29




B30




B31




B32




B33




B34




B35




B36




B37




B38




B39




B40




B41




C1







C2




C3




C4







C12




C13




C14




C15




C16




C17




C18




C19




C20




C21




C22




D1




D2




D3




D4




D5




D6




D7




D8




D9




D10




D11



D12



D13



D14

5

10

15

20

25

30


35

40


45

50


55




D15




D16




D17







D18




D19




D20







E11




E12




E13




E14




E15




E16




E17



E18



E19



E20

[0051] When the indolocarbazole compound represented by the general formula (1) (hereinafter sometimes referred to as compound of the present invention) is contained in at least one of a plurality of organic layers of an organic EL device formed by laminating an anode, the plurality of organic layers, and a cathode on a substrate, an excellent organic electroluminescent device is provided. A light-emitting layer, a hole-transporting layer, an electron-transporting layer, a hole-blocking layer, or an electron-blocking layer is suitable as the organic layer in which the indolocarbazole compound is contained. Here, when the compound of the present invention is used in the light-emitting layer, the compound can be used as a host material for the light-emitting layer containing a fluorescent light-emitting, delayed fluorescent light-emitting, or phosphorescent light-emitting dopant. In addition, the compound of the present invention can be used as an organic light-emitting material that radiates fluorescence and delayed fluorescence. The compound of the present invention is particularly preferably incorporated as a host material for the light-emitting layer containing the phosphores-

cent light-emitting dopant.

[0052] Next, an organic EL device of the present invention is described.

[0053] The organic EL device of the present invention includes organic layers including at least one light-emitting layer between an anode and a cathode laminated on a substrate. In addition, at least one of the organic layers contains the indolocarbazole compound. The compound for an organic EL device of the present invention is advantageously contained in the light-emitting layer together with a phosphorescent light-emitting dopant.

[0054] Next, the structure of the organic EL device of the present invention is described with reference to the drawings. However, the structure of the organic EL device of the present invention is by no means limited to one illustrated in the drawings.

[0055] FIG. 1 is a sectional view illustrating a structure example of a general organic EL device used in the present invention. Reference numeral 1 represents a substrate, reference numeral 2 represents an anode, reference numeral 3 represents a hole-injecting layer, reference numeral 4 represents a hole-transporting layer, reference numeral 5 represents a light-emitting layer, reference numeral 6 represents an electron-transporting layer, and reference numeral 7 represents a cathode. The organic EL device of the present invention may include an exciton-blocking layer adjacent to the light-emitting layer, or may include an electron-blocking layer between the light-emitting layer and the hole-injecting layer. The exciton-blocking layer may be inserted on any of the anode side and the cathode side of the light-emitting layer, and may also be inserted simultaneously on both sides. The organic EL device of the present invention includes the substrate, the anode, the light-emitting layer, and the cathode as its essential layers. The organic EL device of the present invention preferably includes a hole-injecting/transporting layer and an electron-injecting/transporting layer in addition to the essential layers, and more preferably includes a hole-blocking layer between the light-emitting layer and the electron-injecting/transporting layer. It should be noted that the hole-injecting/transporting layer means any one or both of the hole-injecting layer and the hole-transporting layer, and that the electron-injecting/transporting layer means any one or both of an electron-injecting layer and the electron-transporting layer.

[0056] It should be noted that it is possible to adopt a reverse structure as compared to FIG. 1, that is, the reverse structure being formed by laminating the layers on the substrate 1 in the order of the cathode 7, the electron-transporting layer 6, the light-emitting layer 5, the hole-transporting layer 4, and the anode 2. In this case as well, some layers may be added or eliminated if necessary.

-Substrate-

[0057] The organic EL device of the present invention is preferably supported by a substrate. The substrate is not particularly limited, and any substrate that has long been conventionally used for an organic EL device may be used. For example, a substrate made of glass, a transparent plastic, quartz, or the like may be used.

-Anode-

[0058] Preferably used as the anode in the organic EL device is an anode formed by using, as an electrode substance, any of a metal, an alloy, an electrically conductive compound, and a mixture thereof, all of which have a large work function (4 eV or more). Specific examples of such electrode substance include metals such as Au and conductive transparent materials such as CuI, indium tin oxide (ITO), SnO_2 , and ZnO. Further, it may be possible to use a material such as IDIXO ($\text{In}_2\text{O}_3\text{-ZnO}$), which may be used for manufacturing an amorphous, transparent conductive film. In order to produce the anode, it may be possible to form any of those electrode substances into a thin film by using a method such as vapor deposition or sputtering and form a pattern having a desired shape thereon by photolithography. Alternatively, in the case of not requiring high pattern accuracy (about 100 μm or more), a pattern may be formed via a mask having a desired shape when any of the above-mentioned electrode substances is subjected to vapor deposition or sputtering. Alternatively, when a coatable substance such as an organic conductive compound is used, it is also possible to use a wet film-forming method such as a printing method or a coating method. When luminescence is taken out from the anode, the transmittance of the anode is desirably controlled to more than 10%. Further, the sheet resistance as the anode is preferably several hundred $\Omega/\square$ or less. Further, the thickness of the film is, depending on its material, selected from usually the range of from 10 to 1,000 nm, preferably the range of from 10 to 200 nm.

-Cathode-

[0059] On the other hand, used as the cathode is a cathode formed by using, as an electrode substance, any of a metal (referred to as electron-injecting metal), an alloy, an electrically conductive compound, and a mixture thereof, all of which have a small work function (4 eV or less). Specific examples of such electrode substance include sodium, a sodium-potassium alloy, magnesium, lithium, a magnesium/copper mixture, a magnesium/silver mixture, a magnesium/aluminum mixture, a magnesium/indium mixture, an aluminum/aluminum oxide (Al_2O_3) mixture, indium, a lithium/alu-

minum mixture, and a rare earth metal. Of those, for example, a mixture of an electron-injecting metal and a second metal as a stable metal having a larger work function value than the former metal, such as a magnesium/silver mixture, a magnesium/aluminum mixture, a magnesium/indium mixture, an aluminum/aluminum oxide (Al_2O_3) mixture, or a lithium/aluminum mixture, or aluminum is suitable from the viewpoints of electron-injecting property and durability against oxidation or the like. The cathode may be produced by forming any of those electrode substances into a thin film by using a method such as vapor deposition or sputtering. Further, the sheet resistance as the cathode is preferably several hundred $\Omega/\square$ or less, and the thickness of the film is selected from usually the range of from 10 nm to 5 μm , preferably the range of from 50 to 200 nm. It should be noted that, in order for luminescence produced to pass through, any one of the anode and cathode of the organic EL device is preferably transparent or semi-transparent, because the light emission luminance improves.

[0060] Further, after any of the above-mentioned metals is formed into a film having a thickness of from 1 to 20 nm as a cathode, any of the conductive transparent materials mentioned in the description of the anode is formed into a film on the cathode, thereby being able to produce a transparent or semi-transparent cathode. Then, by applying this, it is possible to produce a device in which both the anode and cathode have transparency.

-Light-emitting Layer-

[0061] The light-emitting layer is a layer that emits light after the production of an exciton by the recombination of a hole injected from the anode and an electron injected from the cathode, and the light-emitting layer contains an organic light-emitting material and a host material.

[0062] When the light-emitting layer is a fluorescent light-emitting layer, a fluorescent light-emitting material can be used alone in the light-emitting layer. However, it is preferred that the fluorescent light-emitting material be used as a fluorescent light-emitting dopant and the host material be mixed.

[0063] The indolocarbazole compound represented by the general formula (1) can be used as the fluorescent light-emitting material in the light-emitting layer. However, the fluorescent light-emitting material is known through, for example, many patent literatures, and hence can be selected therefrom. Examples thereof include a benzoxazole derivative, a benzothiazole derivative, a benzimidazole derivative, a styrylbenzene derivative, a polyphenyl derivative, a diphenylbutadiene derivative, a tetraphenylbutadiene derivative, a naphthalimide derivative, a coumarine derivative, a fused aromatic compound, a perinone derivative, an oxadiazole derivative, an oxazine derivative, an aldazine derivative, a pyrrolidine derivative, a cyclopentadiene derivative, a bisstyrylanthracene derivative, a quinacridone derivative, a pyrrolopyridine derivative, a thiadiazolopyridine derivative, a styrylamine derivative, a diketopyrrolopyrrole derivative, an aromatic dimethyldiene compound, various metal complexes typified by a metal complex of a 8-quinolinol derivative, and a metal complex, rare earth complex, or transition metal complex of a pyrromethene derivative, polymer compounds such as polythiophene, polyphenylene, and polyphenylene vinylene, and an organic silane derivative. Of those, for example, the following compound is preferred: a fused aromatic compound, a styryl compound, a diketopyrrolopyrrole compound, an oxazine compound, or a pyrromethene metal complex, transition metal complex, or lanthanoid complex. For example, the following compound is more preferred: naphthacene, pyrene, chrysene, triphenylene, benzo[c]phenanthrene, benzo[a]anthracene, pentacene, perylene, fluoranthene, acenaphthofluoranthene, dibenzo[a, j]anthracene, dibenzo[a, h]anthracene, benzo[a]naphthacene, hexacene, anthanthrene, naphtho[2,1-f]isoquinoline, α -naphthaphenanthridine, phenanthroxazole, quinolino[6,5-f]quinoline, or benzothiophanthrene. Those compounds may each have an alkyl group, aryl group, aromatic heterocyclic group, or diarylamino group as a substituent.

[0064] The indolocarbazole compound represented by the general formula (1) can be used as a fluorescent host material in the light-emitting layer. However, the fluorescent host material is known through, for example, many patent literatures, and hence can be selected therefrom. For example, the following material can be used: a compound having a fused aryl ring such as naphthalene, anthracene, phenanthrene, pyrene, chrysene, naphthacene, triphenylene, perylene, fluoranthene, fluorene, or indene, or a derivative thereof; an aromatic amine derivative such as N,N'-dinaphthyl-N,N'-diphenyl-4,4'-diphenyl-1,1'-diamine; a metal chelated oxinoid compound typified by tris(8-quinolinato)aluminum(III); a bisstyryl derivative such as a distyrylbenzene derivative; a tetraphenylbutadiene derivative; an indene derivative; a coumarin derivative; an oxadiazole derivative; a pyrrolopyridine derivative; a perinone derivative; a cyclopentadiene derivative; a pyrrolopyrrole derivative; a thiadiazolopyridine derivative; a dibenzofuran derivative; a carbazole derivative; an indolocarbazole derivative; a triazine derivative; or a polymer-based derivative such as a polyphenylene vinylene derivative, a poly-p-phenylene derivative, a polyfluorene derivative, a polyvinyl carbazole derivative, or a polythiophene derivative. However, the fluorescent host material is not particularly limited thereto.

[0065] When the fluorescent light-emitting material is used as a fluorescent light-emitting dopant and the host material is contained, the content of the fluorescent light-emitting dopant in the light-emitting layer desirably falls within the range of from 0.01 to 20 wt%, preferably from 0.1 to 10 wt%.

[0066] An organic EL device typically injects charges from both of its electrodes, i.e., its anode and cathode into a light-emitting substance to produce a light-emitting substance in an excited state, and causes the substance to emit


light. In the case of a charge injection-type organic EL device, 25% of the produced excitons are said to be excited to a singlet excited state and the remaining 75% are said to be excited to a triplet excited state. As described in Advanced Materials 2009, 21, 4802-4806., it has been known that after a specific fluorescent light-emitting substance has undergone an energy transition to a triplet excited state as a result of intersystem crossing or the like, the substance is subjected to inverse intersystem crossing to a singlet excited state by triplet-triplet annihilation or the absorption of a thermal energy to radiate fluorescence, thereby expressing thermally activated delayed fluorescence. The organic EL device of the present invention can also express delayed fluorescence. In this case, the light emission can include both fluorescent light emission and delayed fluorescent light emission, provided that light emission from the host material may be present in part of the light emission.

[0067] When the light-emitting layer is a delayed fluorescent light-emitting layer, a delayed fluorescent light-emitting-material can be used alone in the light-emitting layer. However, it is preferred that the delayed fluorescent light-emitting material be used as a delayed fluorescent light-emitting dopant and the host material be mixed.

[0068] Although the indolocarbazole compound represented by the general formula (1) can be used as the delayed fluorescent light-emitting material in the light-emitting layer, a material selected from known delayed fluorescent light-emitting materials can also be used. Examples thereof include a tin complex, an indolocarbazole derivative, a copper complex, and a carbazole derivative. Specific examples thereof include, but not limited to, compounds described in the following non patent literatures and patent literature.

[0069] Adv. Mater. 2009, 21, 4802-4806, Appl. Phys. Lett. 98, 083302 (2011), JP 2011-213643 A, and J. Am. Chem. Soc. 2012, 134, 14706-14709.

[0070] Specific examples of the delayed fluorescent light-emitting material are shown below, but the delayed fluorescent light-emitting material is not limited to the following compounds.



[0071] When the delayed fluorescent light-emitting material is used as a delayed fluorescent light-emitting dopant and the host material is contained, the content of the delayed fluorescent light-emitting dopant in the light-emitting layer desirably falls within the range of from 0.01 to 50 wt%, preferably from 0.1 to 20 wt%, more preferably from 0.01 to 10%.



[0072] The indolocarbazole compound represented by the general formula (1) can be used as the delayed fluorescent host material in the light-emitting layer. However, the delayed fluorescent host material may be selected from compounds other than the indolocarbazole. For example, the following compound can be used: a compound having a fused aryl ring such as naphthalene, anthracene, phenanthrene, pyrene, chrysene, naphthacene, triphenylene, perylene, fluoranthene, fluorene, or indene, or a derivative thereof; an aromatic amine derivative such as N,N'-dinaphthyl-N,N'-diphenyl-4,4'-diphenyl-1,1'-diamine; a metal chelated oxinoid compound typified by tris(8-quinolino)aluminum(III); a bisstyryl derivative such as a distyrylbenzene derivative; a tetraphenylbutadiene derivative; an indene derivative; a coumarin derivative; an oxadiazole derivative; a pyrrolopyridine derivative; a perinone derivative; a cyclopentadiene derivative; a

pyrrolopyrrole derivative; a thiadiazolopyridine derivative; a dibenzofuran derivative; a carbazole derivative; an indolo-carbazole derivative; a triazine derivative; or a polymer-based derivative such as a polyphenylene vinylene derivative, a poly-p-phenylene derivative, a polyfluorene derivative, a polyvinyl carbazole derivative, a polythiophene derivative, or an arylsilane derivative. However, the delayed fluorescent host material is not particularly limited thereto.


[0073] When the light-emitting layer is a phosphorescent light-emitting layer, the light-emitting layer contains a phosphorescent light-emitting dopant and a host material. It is recommended to use, as a material for the phosphorescent light-emitting dopant, a material containing an organic metal complex including at least one metal selected from ruthenium, rhodium, palladium, silver, rhenium, osmium, iridium, platinum, and gold. Specific examples thereof include, but not limited to, the compounds disclosed in the following patent publications.

[0074] For example, WO 2009/073245 A1, WO 2009/046266 A1, WO 2007/095118 A3, WO 2008/156879 A1, WO 2008/140657 A1, US 2008/261076 A1, JP 2008-542203 A, WO 2008/054584 A1, JP 2008-505925 A, JP 2007-522126 A, JP 2004-506305 A, JP 2006-513278 A, JP 2006-50596 A, WO 2006/046980 A1, WO 2005/113704 A3, US 2005/260449 A1, US 2005/2260448 A1, US 2005/214576 A1, WO 2005/076380 A3, US 2005/119485 A1, WO 2004/045001 A3, WO 2004/045000 A3, WO 2006/100888 A1, WO 2007/004380 A1, WO 2007/023659 A1, WO 2008/035664 A1, JP 2003-272861 A, JP 2004-111193 A, JP 2004-319438 A, JP 2007-2080 A, JP 2007-9009 A, JP 2007-227948 A, JP 2008-91906 A, JP 2008-311607 A, JP 2009-19121 A, JP 2009-46601 A, JP 2009-114369 A, JP 2003-253128 A, JP 2003-253129 A, JP 2003-253145 A, JP 2005-38847 A, JP 2005-82598 A, JP 2005-139185 A, JP 2005-187473 A, JP 2005-220136 A, JP 2006-63080 A, JP 2006-104201 A, JP 2006-111623A, JP2006-213720A, JP2006-290891A, JP2006-298899 A, JP 2006-298900 A, WO 2007/018067 A1, WO 2007/058080 A1, WO 2007/058104 A1, JP 2006-131561 A, JP 2008-239565 A, JP 2008-266163 A, JP 2009-57367 A, JP 2002-117978 A, JP 2003-123982 A, JP2003-133074 A, JP 2006-93542 A, JP 2006-131524 A, JP 2006-261623 A, JP 2006-303383 A, JP 2006-303394 A, JP2006-310479A, JP2007-88105A, JP 2007-258550 A, JP 2007-324309 A, JP 2008-270737 A, JP 2009-96800 A, JP 2009-161524 A, WO 2008/050733 A1, JP 2003-73387 A, JP 2004-59433 A, JP 2004-155709 A, JP 2006-104132 A, JP 2008-37848 A, JP 2008-133212 A, JP 2009-57304 A, JP 2009-286716 A, JP 2010-83852 A, JP2009-532546 A, JP2009-536681 A, and JP 2009-542026 A.


[0075] Preferred examples of the phosphorescent light-emitting dopant include complexes such as Ir (ppy) 3, complexes such as Ir (bt)2 · acac3, and complexes such as PtOEt3, the complexes each having a noble metal element such as Ir as a central metal. Specific examples of those complexes are shown below, but the complexes are not limited to the compounds described below.



5




10




15

20




25

30



35

 $R_3: \text{CH}_3, \text{CH}_2\text{CH}_3$


[0076] It is desirable that the content of the phosphorescent light-emitting dopant in the light-emitting layer be in the range of from 2 to 40 wt%, preferably from 5 to 30 wt%.

[0077] When the light-emitting layer is a phosphorescent light-emitting layer, it is preferred to use, as a host material in the light-emitting layer, the indolocarbazole compound represented by the general formula (1). However, when the indolocarbazole compound is used in any of the organic layers other than the light-emitting layer, the material to be used in the light-emitting layer may be another host material other than the indolocarbazole compound, or the indolocarbazole compound and any other host material may be used in combination. Further, a plurality of kinds of known host materials may be used in combination.

[0078] It is preferred to use, as a usable known host compound, a compound that has a hole-transporting ability or an electron-transporting ability, is capable of preventing luminescence from having a longer wavelength, and has a high glass transition temperature.

[0079] Such other host materials are known because they are mentioned in many patent literatures and the like, and hence a suitable host material may be chosen from those in the patent literatures and the like. Specific examples of the host material include, but are not particularly limited to, an indole derivative, a carbazole derivative, a triazole derivative, an oxazole derivative, an oxadiazole derivative, an imidazole derivative, a polyarylethane derivative, a pyrazoline derivative, a pyrazolone derivative, a phenylenediamine derivative, an arylamine derivative, an amino-substituted chalcone derivative, a styrylanthracene derivative, a fluorenone derivative, a hydrazone derivative, a stilbene derivative, a silazane derivative, an aromatic tertiary amine compound, a styrylamine compound, an aromatic dimethyldiene-based compound, a porphyrin-based compound, an anthraquinodimethane derivative, an anthrone derivative, a diphenylquinone derivative, a thiopyran dioxide derivative, a heterocyclic tetracarboxylic acid anhydride such as naphthalene perylene, a phthal-

cyanine derivative, various metal complexes typified by a metal complex of an 8-quinolinol derivative, a metal phthalocyanine, and metal complexes of benzoxazole and benzothiazole derivatives, and polymer compounds such as a polysilane-based compound, a poly(N-vinylcarbazole) derivative, an aniline-based copolymer, a thiophene oligomer, a polythiophene derivative, a polyphenylene derivative, a polyphenylenevinylene derivative, and a polyfluorene derivative.

[0080] The light-emitting layer, which may be any one of a fluorescent light-emitting layer, a delayed fluorescent light-emitting layer, and a phosphorescent light-emitting layer, is preferably the phosphorescent light-emitting layer.

-Injecting Layer-

[0081] The injecting layer refers to a layer formed between an electrode and an organic layer for the purpose of lowering a driving voltage and improving light emission luminance, and includes a hole-injecting layer and an electron-injecting layer. The injecting layer may be interposed between the anode and the light-emitting layer or the hole-transporting layer, or may be interposed between the cathode and the light-emitting layer or the electron-transporting layer. The injecting layer may be formed as required.

-Hole-blocking Layer-

[0082] The hole-blocking layer has, in a broad sense, the function of an electron-transporting layer, and is formed of a hole-blocking material that has a remarkably small ability to transport holes while having a function of transporting electrons, and hence the hole-blocking layer is capable of improving the probability of recombining an electron and a hole by blocking holes while transporting electrons.

[0083] It is preferred to use the indolocarbazole compound represented by the general formula (1) for the hole-blocking layer. However, when the indolocarbazole compound is used in any other organic layer, a known material for a hole-blocking layer may be used. Further, it is possible to use, as a material for the hole-blocking layer, any of the below-mentioned materials for the electron-transporting layer as required.

-Electron-blocking Layer-

[0084] The electron-blocking layer is formed of a material that has a remarkably small ability to transport electrons while having a function of transporting holes, and hence the electron-blocking layer is capable of improving the probability of recombining an electron and a hole by blocking electrons while transporting holes.

[0085] Although the indolocarbazole compound represented by the general formula (1) according to the present invention can be used as a material for the electron-blocking layer, another material, i. e. , any of the below-mentioned materials for the hole-transporting layer can be used as required. The thickness of the electron-blocking layer is preferably from 3 to 100 nm, more preferably from 5 to 30 nm.

-Exciton-blocking Layer-

[0086] The exciton-blocking layer refers to a layer for blocking excitons produced by the recombination of a hole and an electron in the light-emitting layer from diffusing into charge-transporting layers. Inserting this layer enables effective confinement of the excitons in the light-emitting layer, thereby being able to improve the luminous efficiency of the device. The exciton-blocking layer may be inserted on any of the anode side and the cathode side of the adjacent light-emitting layer, and may also be inserted simultaneously on both sides.

[0087] Although the indolocarbazole compound represented by the general formula (1) can be used as a material for the exciton-blocking layer, another material therefor, there are given, for example, 1,3-dicarbazolylbenzene (mCP) and bis(2-methyl-8-quinolinolato)-4-phenylphenolatoaluminum(III) (BALq).

-Hole-transporting Layer-

[0088] The hole-transporting layer is formed of a hole-transporting material having a function of transporting holes, and a single hole-transporting layer or a plurality of hole-transporting layers may be formed.

[0089] The hole-transporting material has hole-injecting property or hole-transporting property or has electron-blocking property, and any of an organic material and an inorganic material may be used as the hole-transporting material. Although it is preferred to use the indolocarbazole compound represented by the general formula (1) for the hole-transporting layer, any compound selected from conventionally known compounds may be used. Examples of the known hole-transporting material that may be used include a triazole derivative, an oxadiazole derivative, an imidazole derivative, a polyarylethane derivative, a pyrazoline derivative, and a pyrazolone derivative, a phenylenediamine derivative, an arylamine derivative, an amino-substituted chalcone derivative, an oxazole derivative, a styrylanthracene derivative,

afluorenone derivative, a hydrazone derivative, a stilbene derivative, a silazane derivative, an aniline-based copolymer, and a conductive high-molecular weight oligomer, in particular, a thiophene oligomer. However, a porphyrin compound, an aromatic tertiary amine compound, or a styrylamine compound is preferably used, and an aromatic tertiary amine compound is more preferably used.

-Electron-transporting Layer-

[0090] The electron-transporting layer is formed of a material having a function of transporting electrons, and a single electron-transporting layer or a plurality of electron-transporting layers may be formed.

[0091] An electron-transporting material (which also serves as a hole-blocking material in some cases) only needs to have a function of transferring electrons injected from the cathode into the light-emitting layer. Although it is preferred to use the material represented by the general formula (1) according to the present invention for the electron-transporting layer, any compound selected from conventionally known compounds may be used. Examples thereof include a nitro-substituted fluorene derivative, a diphenylquinone derivative, a thiopyran dioxide derivative, a carbodiimide, a fluorenylidene methane derivative, anthraquinodimethane, an anthrone derivative, and an oxadiazole derivative. Further, it is also possible to use, as the electron-transporting material, a thiadiazole derivative prepared by substituting an oxygen atom on an oxadiazole ring with a sulfur atom in the oxadiazole derivative and a quinoxaline derivative that has a quinoxaline ring known as an electron withdrawing group. Further, it is also possible to use a polymer material in which any of those materials is introduced in a polymer chain or is used as a polymer main chain.

Examples


[0092] Hereinafter, the present invention is described in more detail by way of Examples. It should be appreciated that the present invention is not limited to Examples below and may be carried out in various forms as long as the various forms do not deviate from the gist of the present invention.

[0093] The route described below was used to synthesize an indolocarbazole compound to be used as a material for a phosphorescent light-emitting device. It should be noted that the number of each compound corresponds to the number given to the exemplified compound.


Synthesis Example 1

Synthesis of Compound B9

[0094]



[0095] Under a nitrogen atmosphere, 5.00 g (0.0150 mol) of a compound (A), 25.0 g (0.106 mol) of dibromobenzene, 6.10 g (0.0960 mol) of copper, 22.8 g (0.165 mol) of potassium carbonate, and 30 ml of 1,3-dimethyl-2-imidazolidinone (DMI) were added and stirred at 190°C for 6 hr. The reaction solution was cooled to room temperature and poured into 800 ml of water, and the mixture was stirred at room temperature for 12 hr. A precipitated solid was separated by filtration and dissolved in 200 ml of tetrahydrofuran (THF), and 200 ml of 2 M HCl were added to the solution. After that, the mixture was extracted with 100 ml of ethyl acetate three times. An organic layer was dried with anhydrous magnesium sulfate, and then magnesium sulfate was separated by filtration and the solvent was removed. The resultant residue was purified by silica gel column chromatography to provide 6.18 g (0.0126 mol, 84% yield) of an intermediate (B) as a white solid.



[0096] Under a nitrogen atmosphere, 6.00 g (0.0123 mol) of the intermediate (B) and 100 ml of THF were added and cooled to -78°C . 7.7 ml (0.0123 mol) of 1.59 M n-BuLi were added to the mixture, and the whole was stirred at -78°C for 30 min. After that, 4.96 g (0.0185 mol) of dimesitylfluoroborane were added to the resultant and the mixture was stirred at room temperature for 2 hr. After that, the solvent was removed, and the resultant residue was purified by silica gel column chromatography and recrystallization to provide 1.90 g (0.00289 mol, 23% yield) of Compound B9 as a pale yellow solid.

[0097] The APCI-TOFMS of the compound showed an $[\text{M}+1]$ peak at an m/z of 657. FIG. 2 shows the results of its $^1\text{H-NMR}$ measurement (measurement solvent: THF-d_8).

Example 1

[0098] Each thin film was laminated by a vacuum deposition method at a degree of vacuum of 4.0×10^{-5} Pa on a glass substrate on which an anode formed of ITO having a thickness of 110 nm had been formed. First, copper phthalocyanine (CuPC) was formed into a layer having a thickness of 25 nm on the ITO. Next, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPB) was formed into a layer having a thickness of 40 nm to serve as a hole-transporting layer. Next, Compound (B9) as a host material and tris(2-phenylpyridine)iridium(III) ($\text{Ir}(\text{ppy})_3$) as a phosphorescent light-emitting dopant were co-deposited from different deposition sources onto the hole-transporting layer to form a light-emitting layer having a thickness of 40 nm. The concentration of $\text{Ir}(\text{ppy})_3$ in the light-emitting layer was 10.0 wt%. Next, tris(8-hydroxyquinolato)aluminum(III) (Alq_3) was formed into a layer having a thickness of 20 nm to serve as an electron-transporting layer. Further, lithium fluoride (LiF) was formed into a layer having a thickness of 1.0 nm to serve as an electron-injecting layer on the electron-transporting layer. Finally, aluminum (Al) was formed into a layer having a thickness of 70 nm to serve as an electrode on the electron-injecting layer. Thus, an organic EL device was produced.

[0099] An external power source was connected to the resultant organic EL device to apply a DC voltage to the device. As a result, it was confirmed that the device had such light-emitting characteristics as shown in Table 1. The columns "luminance", "voltage", and "luminous efficiency" in Table 1 show values at 20 mA/cm^2 . It was found that the local maximum wavelength of the emission spectrum of the device was 520 nm and hence light emission from $\text{Ir}(\text{ppy})_3$ was obtained.

Examples 2 to 12

[0100] Compounds A1, A27, A33, A41, B4, B22, B33, C9, D8, D17, and E11 were synthesized in the same manner as in Synthesis Example 1.


[0101] Organic EL devices were each produced in the same manner as in Example 1 except that Compounds A1, A27, A33, A41, B4, B22, B33, C9, D8, D17, and E11 were each used instead of Compound B9 as the host material for the light-emitting layer of Example 1. It was found that the local maximum wavelength of the emission spectrum of each of the devices was 520 nm, and hence light emission from $\text{Ir}(\text{ppy})_3$ was obtained. Table 1 shows the respective light-emitting characteristics.

Comparative Example 1

[0102] An organic EL device was produced in the same manner as in Example 1 except that CBP was used as the host material for the light-emitting layer.

Comparative Example 2


[0103] An organic EL device was produced in the same manner as in Example 1 except that the following compound Ho-1 was used as the host material for the light-emitting layer.



Ho-1

Comparative Example 3

[0104] An organic EL device was produced in the same manner as in Example 1 except that the following compound Ho-2 was used as the host material for the light-emitting layer.



Ho-2

[0105] It was found that the local maximum wavelength of the emission spectrum of each of the organic EL devices produced in Comparative Examples 1 to 3 was 520 nm, and hence light emission from Ir(ppy)₃ was obtained. Table 1 shows the compounds each used as the host material and the respective light-emitting characteristics (at 20 mA/cm²).

[Table 1]

	Compound	Luminance (cd/m ²)	Voltage (V)	Visual luminous efficiency (lm/W)
Example 1	B9	5,020	5.4	14.6
2	A1	5,155	6.0	13.5
3	A2 7	4,990	5.6	14.0
4	A33	4,925	6.0	12.9
5	A41	5,050	6.1	13.0
6	B4	5,000	6.0	13.1
7	B22	5,295	6.3	13.2
8	B33	5,090	6.2	12.9
9	C9	5,005	5.5	14.3
10	D8	5,135	5.6	14.4
11	D17	4,985	5.4	14.5
12	E11	5,280	6.1	13.6
Comparative Example 1	CBP	4,860	9.3	8.2
2	Ho-1	4,713	7.4	10.0
3	Ho-2	3,980	6.1	10.2


[0106] It is found from Table 1 that the organic EL device using the indolocarbazole compound represented by the general formula (1) has a low driving voltage and shows good light-emitting characteristics as compared to those in the case where CBP generally known as a phosphorescent host is used. It is also found that the device shows good light-emitting characteristics as compared to those in the case where any one of Ho-1 and Ho-2 as compounds each having no boron-containing group on a linking group bonded to N of indolocarbazole or on benzene of indolocarbazole is used. The superiority of the organic EL device using the indolocarbazole compound is apparent from the foregoing.

Industrial Applicability

[0107] The organic EL device according to the present invention has light-emitting characteristics, driving voltage, and durability at practically satisfactory levels. Thus, the organic EL device has a large technical value in applications to flat panel displays (display devices for mobile phones, in-vehicle display devices, display devices for OA computers, televisions, and the like), light sources utilizing characteristics of planar light emitters (light sources in lighting equipment and copying machines and backlight sources in liquid crystal displays and instruments), sign boards, sign lamps, and the like.

Claims

1. A compound for an organic electroluminescent device, which is represented by the following general formula (1):



wherein:

a ring I represents an aromatic hydrocarbon ring represented by the formula (1a) to be fused to adjacent rings at arbitrary positions and a ring II represents a heterocycle represented by the formula (1b) to be fused to adjacent rings at arbitrary positions;

L_1 and L_2 each independently represent an $i+1$ -valent or $k+1$ -valent group selected from a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, and a linked aromatic group formed by linking two to six of aromatic rings of the substituted or unsubstituted aromatic hydrocarbon groups and the substituted or unsubstituted aromatic heterocyclic groups, the linked aromatic group may be linear or branched, and the aromatic

rings to be linked may be identical to or different from each other;



Z represents a boron-containing group represented by the formula (1c);



Rs each independently represent deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a cyano group, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an amino group, a nitro group, an acyl group having 2 to 12 carbon atoms, an alkoxycarbonyl group having 2 to 12 carbon atoms, a carboxyl group, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a hydroxyl group, an amide group, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a boron-containing group represented by the formula (1c);

A₁ and A₂ each independently represent hydrogen, deuterium, an alkyl group having 1 to 12 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, a hydroxyl group, chlorine, bromine, fluorine, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, and A₁ and A₂ may be bonded to adjacent A₁ and A₂ or substituents of A₁ and A₂ to form a ring; and

p and q each independently represent an integer of from 0 to 4, r represents an integer of from 0 to 2, and i and k each represent an integer of from 0 to 5, provided that p+q+r+i+k≥1 and when both of i and k represent 0, at least one of Rs represents a boron-containing group represented by the formula (1c), and when p, q, r, i, and k each represent 2 or more, Rs and Zs may be identical to or different from each other.

2. A compound for an organic electroluminescent device according to claim 1, wherein the compound is represented by any one of the general formulae (2) to (5):





in the general formulae (2) to (5), L_1 , L_2 , Z , R , p , q , r , i , and k each have the same meaning as that of the general formula (1).

3. A compound for an organic electroluminescent device according to claim 1, wherein:

R_s each independently represent deuterium, an alkyl group having 1 to 12 carbon atoms, an aralkyl group having 7 to 19 carbon atoms, an alkenyl group having 2 to 12 carbon atoms, an alkynyl group having 2 to 12 carbon atoms, a dialkylamino group having 2 to 24 carbon atoms, a diarylamino group having 6 to 36 carbon atoms, a diaralkylamino group having 14 to 38 carbon atoms, an acyl group having 2 to 12 carbon atoms, an alkoxycarbonyl group having 2 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, an alkylsulfonyl group having 1 to 12 carbon atoms, a haloalkyl group having 1 to 12 carbon atoms, a phenoxy group, an alkylthio group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a boron-containing group represented by the formula (1c); and

A_1 and A_2 each independently represent an alkyl group having 1 to 12 carbon atoms, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms.

4. A compound for an organic electroluminescent device according to claim 1, wherein $i+k$ is 1 or more and R_s each represent a group except a boron-containing group.
5. A compound for an organic electroluminescent device according to claim 1, wherein A_1 and A_2 each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, or a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms.
6. An organic electroluminescent device, comprising an organic layer containing the compound for an organic electroluminescent device according to any one of claims 1 to 5.
7. An organic electroluminescent device according to claim 6, wherein the organic layer containing the compound for an organic electroluminescent device comprises at least one layer selected from a light-emitting layer, a hole-transporting layer, a hole-injecting layer, an electron-transporting layer, and an electron-injecting layer.
8. An organic electroluminescent device according to claim 6, wherein the organic layer containing the compound for an organic electroluminescent device comprises a light-emitting layer, and the light-emitting layer contains a phosphorescent light-emitting dopant and the compound for an organic electroluminescent device as a host material.

FIG. 1





FIG. 2



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2013/075937

A. CLASSIFICATION OF SUBJECT MATTER

H01L51/50(2006.01)i, C07F5/02(2006.01)i, C09K11/06(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

H01L51/50, C07F5/02, C09K11/06

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho	1922-1996	Jitsuyo Shinan Toroku Koho	1996-2013
Kokai Jitsuyo Shinan Koho	1971-2013	Toroku Jitsuyo Shinan Koho	1994-2013

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CAplus/REGISTRY (STN)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X A	WO 2011/125020 A1 (BASF SE), 13 October 2011 (13.10.2011), claims & JP 2013-528929 A & EP 002556075 A & CN 102933582 A	1-3, 5-8 4
A	JP 2012-140367 A (Idemitsu Kosan Co., Ltd.), 26 July 2012 (26.07.2012), entire text; all drawings (Family: none)	1-8

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search
18 October, 2013 (18.10.13)Date of mailing of the international search report
29 October, 2013 (29.10.13)Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 01041512 A [0005]
- JP 2001313178 A [0005]
- JP 11162650 A [0005]
- JP 11176578 A [0005]
- WO 2008056746 A [0005]
- WO 2008146839 A [0005]
- WO 2010114243 A [0005]
- JP 2011213643 A [0069]
- WO 2009073245 A1 [0074]
- WO 2009046266 A1 [0074]
- WO 2007095118 A3 [0074]
- WO 2008156879 A1 [0074]
- WO 2008140657 A1 [0074]
- US 2008261076 A1 [0074]
- JP 2008542203 A [0074]
- WO 2008054584 A1 [0074]
- JP 2008505925 A [0074]
- JP 2007522126 A [0074]
- JP 2004506305 A [0074]
- JP 2006513278 A [0074]
- JP 2006050596 A [0074]
- WO 2006046980 A1 [0074]
- WO 2005113704 A3 [0074]
- US 2005260449 A1 [0074]
- US 20052260448 A1 [0074]
- US 2005214576 A1 [0074]
- WO 2005076380 A3 [0074]
- US 2005119485 A1 [0074]
- WO 2004045001 A3 [0074]
- WO 2004045000 A3 [0074]
- WO 2006100888 A1 [0074]
- WO 2007004380 A1 [0074]
- WO 2007023659 A1 [0074]
- WO 2008035664 A1 [0074]
- JP 2003272861 A [0074]
- JP 2004111193 A [0074]
- JP 2004319438 A [0074]
- JP 2007002080 A [0074]
- JP 2007009009 A [0074]
- JP 2007227948 A [0074]
- JP 2008091906 A [0074]
- JP 2008311607 A [0074]
- JP 2009019121 A [0074]
- JP 2009046601 A [0074]
- JP 2009114369 A [0074]
- JP 2003253128 A [0074]
- JP 2003253129 A [0074]
- JP 2003253145 A [0074]
- JP 2005038847 A [0074]
- JP 2005082598 A [0074]
- JP 2005139185 A [0074]
- JP 2005187473 A [0074]
- JP 2005220136 A [0074]
- JP 2006063080 A [0074]
- JP 2006104201 A [0074]
- JP 2006111623 A [0074]
- JP 2006213720 A [0074]
- JP 2006290891 A [0074]
- JP 2006298899 A [0074]
- JP 2006298900 A [0074]
- WO 2007018067 A1 [0074]
- WO 2007058080 A1 [0074]
- WO 2007058104 A1 [0074]
- JP 2006131561 A [0074]
- JP 2008239565 A [0074]
- JP 2008266163 A [0074]
- JP 2009057367 A [0074]
- JP 2002117978 A [0074]
- JP 2003123982 A [0074]
- JP 2003133074 A [0074]
- JP 2006093542 A [0074]
- JP 2006131524 A [0074]
- JP 2006261623 A [0074]
- JP 2006303383 A [0074]
- JP 2006303394 A [0074]
- JP 2006310479 A [0074]
- JP 2007088105 A [0074]
- JP 2007258550 A [0074]
- JP 2007324309 A [0074]
- JP 2008270737 A [0074]
- JP 2009096800 A [0074]
- JP 2009161524 A [0074]
- WO 2008050733 A1 [0074]
- JP 2003073387 A [0074]
- JP 2004059433 A [0074]
- JP 2004155709 A [0074]
- JP 2006104132 A [0074]
- JP 2008037848 A [0074]
- JP 2008133212 A [0074]
- JP 2009057304 A [0074]
- JP 2009286716 A [0074]
- JP 2010083852 A [0074]
- JP 2009532546 A [0074]
- JP 2009536681 A [0074]
- JP 2009542026 A [0074]

Non-patent literature cited in the description

- *Synlett*, 2005, vol. 1, 42-48 **[0048]**
- *Archiv der Pharmazie (Weinheim, Germany)*, 1987, vol. 320 (3), 280-2 **[0049]**
- *Advanced Materials*, 2009, vol. 21, 4802-4806 **[0066]**
- *Adv. Mater.*, 2009, vol. 21, 4802-4806 **[0069]**
- *Appl. Phys. Lett.*, 2011, vol. 98, 083302 **[0069]**
- *J. Am. Chem. Soc.*, 2012, vol. 134, 14706-14709 **[0069]**

专利名称(译)	用于有机电致发光元件的化合物和有机电致发光元件		
公开(公告)号	EP2903048A1	公开(公告)日	2015-08-05
申请号	EP2013841725	申请日	2013-09-25
[标]申请(专利权)人(译)	新日铁化学株式会社		
申请(专利权)人(译)	NIPPON STEEL住金化工有限公司.		
当前申请(专利权)人(译)	NIPPON STEEL住金化工有限公司.		
[标]发明人	SANNOMIYA RUMI KAI TAKAHIRO KOMORI MASAKI YAMAMOTO TOSHIHIRO TADA MASASHI		
发明人	SANNOMIYA, RUMI KAI, TAKAHIRO KOMORI, MASAKI YAMAMOTO, TOSHIHIRO TADA, MASASHI		
IPC分类号	H01L51/50 C07F5/02 C09K11/06		
CPC分类号	C07F5/027 C09K11/06 C09K2211/1029 H01L51/0052 H01L51/0067 H01L51/0072 H01L51/5016 H01L51/5056 H05B33/14 C09B57/00 C09K11/025 H01L51/0073 H01L51/008 H01L51/5221 H01L51/5012 H01L51/5072 H01L51/5088 H01L51/5092 H01L51/5096 H01L51/5206 H01L2251/301 H01L2251/308		
优先权	2012216564 2012-09-28 JP		
其他公开文献	EP2903048A4 EP2903048B1		
外部链接	Espacenet		

摘要(译)

本发明提供一种在发光特性，驱动电压和耐久性方面实际上令人满意的有机EL器件，以及用于该器件的有机EL器件用化合物。有机EL器件具有这样的结构，其中阳极，包括发光层的多个有机层和阴极层叠在基板上，并且有机EL器件在选自的至少一个有机层中含有吡啶并咪唑化合物。发光层，空穴传输层，电子传输层，空穴阻挡层和电子阻挡层。吡啶并咪唑化合物是在其分子中具有至少一个含硼基团的化合物，所述含硼基团具有这样的结构：含硼基团的硼与键合到吡啶并咪唑环的氮原子上的连接基团上的原子键合。或环的碳原子。

FIG. 1

