



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 657 762 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
17.05.2006 Bulletin 2006/20

(51) Int Cl.:
H01L 51/52 (2006.01)

(21) Application number: **05022909.5**

(22) Date of filing: **20.10.2005**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI
SK TR**
Designated Extension States:
AL BA HR MK YU

(72) Inventor: **Son, Woo Hyun**
Gum-si
Gyeongsangbuk-do (KR)

(74) Representative: **Zech, Stefan Markus et al**
Meissner, Bolte & Partner GbR
(Depotstrasse 5 1/2, 86199 Augsburg)
Postfach 10 26 05
86016 Augsburg (DE)

(30) Priority: **11.11.2004 KR 2004092139**

(71) Applicant: **LG ELECTRONICS INC.**
Seoul (KR)


(54) **Organic electro-luminescence display device and fabricating method thereof**

(57) There are disclosed an organic electro luminescence display device that is adaptive for preventing a defect in forming a barrier rib, and a fabricating method thereof.

An organic electro luminescence display device according to an embodiment of the present invention includes first and second electrodes formed to cross each

other with an organic light emitting layer therebetween; a barrier rib which crosses the first electrode and is parallel to the second electrode; and an insulating film which is located between the barrier rib and the first electrode and defines an area of forming the organic light emitting layer, and wherein the insulating film has at least one groove which is provided in a contact area with the barrier rib.

FIG.4



Description

[0001] This application claims the benefit of the Korean Patent Application No. P2004-92139 filed on November 11, 2004, which is hereby incorporated by reference.

BACKGROUND OF THE INVENTION

Field of the Invention

[0002] The present invention relates to an organic electro luminescence display device, and more particularly to an organic electro luminescence display device that is adaptive for preventing a defect in forming a barrier rib, and a fabricating method thereof.

Description of the Related Art

[0003] Recently, there have been developed a variety of flat panel display devices that can reduce their weight and size, which are a disadvantage of a cathode ray tube CRT. The flat panel display device includes a liquid crystal display LCD, a field emission display FED, a plasma display panel PDP and an electro luminescence EL display device.

[0004] Especially, the EL display device basically has a shape of sticking an electrode to both side surfaces of an organic light emitting layer which is made up of a hole transport layer, a light emitting layer and an electron transport layer, and the EL display device attracts attention as a next generation flat panel display because of its wide viewing angle, high aperture ratio, high color sense and so on.

[0005] The EL display device is largely divided into an inorganic EL display device and an organic EL display device in accordance with a material used. The organic EL display device among these has an advantage of being driven with lower voltage than an inorganic EL display device because electrons and holes form pairs and then they become extinct to emit light when electric charges are injected into an organic EL layer which is formed between a hole injection electrode and an electron injection electrode. Further, the organic EL display device can form elements even on a transparent substrate which is flexible like plastics, and the organic EL display device can be driven at a low voltage of below 10V, has relatively low power consumption and has excellent color sense in comparison with the PDP or the inorganic EL display device.

[0006] FIG. 1 is a perspective view representing a related art organic EL display device, and FIG. 2 is a diagram representing the organic EL display device shown in FIG. 1, taken along the line I-I'.

[0007] The organic EL display device shown in FIG. 1 has a first electrode (or an anode electrode) 4 and a second electrode (or a cathode electrode) 12 formed on a substrate 2 in a direction of crossing each other.

[0008] A plurality of anode electrodes 4 are formed on

the substrate 2 to be separated from each other with a designated gap. An insulating film 6 having an aperture part for each EL cell area is formed on the substrate 2 where the anode electrode 4 is formed. Barrier ribs 8 are located on the insulating film 6 for separating an organic light emitting layer 10 and the cathode electrode 12 which are to be formed thereon. The barrier ribs 8 are formed in a direction of crossing the anode electrode 4 and have a reverse taper structure where an upper end part has a wider width than a lower end part. The organic light emitting layer 10 and the cathode electrode 12 formed of an organic compound are sequentially deposited over the entire surface of the insulating film 6 where the barrier ribs 8 are formed. The organic light emitting layer 10 has a hole transport layer, a light emitting layer and an electron transport layer deposited and formed on the insulating film. The organic EL display device has electrons and holes emitted if a driving signal is applied to the anode electrode 4 and the cathode electrode 12, and the electrons and holes emitted from the anode electrode 4 and the cathode electrode 12 are recombined within the organic light emitting layer 10 to generate a visible ray. At this moment, the generated visible ray exits to the outside through the anode electrode 4 to display a designated picture or image.

[0009] Hereinafter, in reference to FIGs. 3A to 3E, a fabricating method of the related art organic EL display device is described as follows.

[0010] Firstly, after depositing a transparent conductive metal material on the substrate 2 which is formed by use of soda lime or hard glass, the transparent conductive metal material is patterned by a photolithography process and an etching process, thereby forming the anode electrode 4, as shown in FIG. 3A. Herein, the metal material is indium tin oxide or SnO₂.

[0011] After a photo sensitive insulating material is coated by a spin coating method on the substrate 2 where the anode electrode 4 is formed, the photo sensitive insulating material is patterned by the photolithography process and the etching process, thereby forming an insulating film 6 for the light emitting area to be exposed, as shown in FIG. 3B.

[0012] After a photo sensitive organic material is deposited on the insulating film 6, the photo sensitive organic material is patterned by the photolithography process and the etching process, thereby forming the barrier rib 8, as shown in FIG. 3C. The barrier rib 8 is formed in a non light emitting area to cross a plurality of anode electrodes 4 for dividing pixels.

[0013] An organic material is deposited on the substrate where the barrier rib 8 is formed by use of a thermal deposition method and a vacuum deposition method in use of a shadow mask, thereby forming the organic light emitting layer 10, as shown in FIG. 3D.

[0014] A metal material is deposited on the substrate 2 where the organic light emitting layer 10 is formed, thereby forming the cathode electrode 12, as shown in FIG. 3E.

[0015] On the other hand, the related art barrier rib 8 is formed in a reverse taper shape for dividing the cathode electrode 12, thus a contact area with the insulating film 6 becomes narrow. Hereby, there often occurs a defect that the barrier rib 8 is separated from the insulating film 6 upon a cleaning process among the process of forming the barrier rib 8 or in case that a small impact is applied to the organic EL display device.

SUMMARY OF THE INVENTION

[0016] Accordingly, it is an object of the present invention to provide an organic electro luminescence display device that is adaptive for preventing a defect in forming a barrier rib, and a fabricating method thereof.

[0017] In order to achieve these and other objects of the invention, an organic electro luminescence display device according to an aspect of the present invention includes first and second electrodes formed to cross each other with an organic light emitting layer therebetween; a barrier rib which crosses the first electrode and is parallel to the second electrode; and an insulating film which is located between the barrier rib and the first electrode and defines an area of forming the organic light emitting layer, and wherein the insulating film has at least one groove which is provided in a contact area with the barrier rib.

[0018] In the organic electro luminescence display device, the groove is filled with part of the barrier rib.

[0019] A fabricating method of an organic electro luminescence display device according to another aspect of the present invention includes the steps of forming a first electrode on a substrate; forming an insulating film which partially exposes the first electrode to define a light emitting area; forming a barrier rib which crosses the first electrode; forming an organic light emitting layer in the light emitting area; and forming a second electrode which crosses the first electrode with the organic light emitting layer therebetween, and wherein the step of forming the insulating film has the step of forming at least one groove which is filled with part of the barrier rib in a contact area with the barrier rib.

[0020] In the fabricating method, the step of forming the at least one groove includes the step of forming an insulating material on the substrate where the first electrode is formed; aligning a halftone mask which has a transmitting part, a shielding part and a semi transmitting part corresponding to an area where the groove is to be formed, on the substrate where the insulating material is formed; and patterning the insulating material by a photolithography process by use of the halftone mask.

BRIEF DESCRIPTION OF THE DRAWINGS

[0021] These and other objects of the invention will be apparent from the following detailed description of the embodiments of the present invention with reference to the accompanying drawings, in which:

[0022] FIG. 1 a perspective view briefly illustrating a related art organic electro luminescence display device;

[0023] FIG. 2 is a diagram representing the organic electro luminescence display device shown in FIG. 1, taken along the line I-I' ;

[0024] FIGs . 3A to 3E are diagrams representing a fabricating method of a related art organic electro luminescence display device;

[0025] FIG. 4 is a sectional diagram representing an organic electro luminescence display device according to the present invention;

[0026] FIGs. 5A to 5E are diagrams representing a fabricating method of an organic electro luminescence display device according to the present invention; and

[0027] FIG. 6 is a diagram for explaining that a groove provided in an insulating film is formed by a halftone mask.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

[0028] Reference will now be made in detail to the preferred embodiments of the present invention, examples of which are illustrated in the accompanying drawings.

[0029] With reference to FIGs. 4 to 6, embodiments of the present invention will be explained as follows.

[0030] FIG. 4 is a sectional diagram representing an organic EL display device according to the present invention.

[0031] The organic EL display device shown in FIG. 4 has a first electrode (or an anode electrode) 104 and a second electrode (or a cathode electrode) 112 formed on a substrate 102 in a direction of crossing each other.

[0032] A plurality of anode electrodes 104 are formed on the substrate 102 to be separated from each other with a designated gap. An insulating film 106 having an aperture part for each EL cell area is formed on the substrate 102 where the anode electrode 104 is formed. Barrier ribs 108 are located on the insulating film 106 for separating an organic light emitting layer 110 and the cathode electrode 112 which are to be formed thereon. The barrier ribs 108 are formed in a direction of crossing the anode electrode 104 and have a reverse taper structure where an upper end part has a wider width than a lower end part. The organic light emitting layer 110 and the cathode electrode 112 formed of an organic compound are sequentially deposited over the entire surface of the insulating film 106 where the barrier ribs 108 are formed. The organic light emitting layer 110 has a hole transport layer, a light emitting layer and an electron transport layer deposited and formed on the insulating film 106.

[0033] At least one groove 150 is formed in a contact area of the barrier rib 108 and the insulating film 106. The groove 150 is formed on the insulating film 106 and part of the barrier rib 108 is filled into the groove 150, thus the contact area of the barrier rib 108 and the insulating film 106 is widened. Accordingly, the adhesive

strength between the barrier rib 106 and the insulating film 106 is improved.

[0034] In this way, the organic EL display device according to the present invention has at least one groove 150 which is located at the contact area of the barrier rib 108 and the insulating film 106, and which is provided in the insulating film 106. Accordingly, the barrier rib 108 is not separated from the insulating film 106 upon the cleaning process of the barrier rib 108 or even when a small impact is applied to the organic EL display device.

[0035] Hereinafter, in reference to FIGs. 5A to 5E, a fabricating method of the related art organic EL display device is described as follows.

[0036] Firstly, after depositing a transparent conductive metal material on the substrate 102 which is formed by use of soda lime or hard glass, the transparent conductive metal material is patterned by a photolithography process and an etching process, thereby forming the anode electrode 104, as shown in FIG. 5A. Herein, the metal material is indium tin oxide or SnO₂.

[0037] On the substrate 102 where the anode electrode 104 is formed, as shown in FIG. 5B, the light emitting area is exposed and there is formed the insulating film 106 having at least one groove 150 which is located at the contact area with the barrier rib 108 that is to be formed later.

[0038] In reference to FIG. 6, the process of forming the insulating film is specifically described as follows.

[0039] Firstly, a photo sensitive insulating material is coated by a spin coating method on the substrate 102 where the anode electrode 104 is formed. And then, a halftone mask 152 having a transmitting part P1, a shielding part P2 and a semi transmitting part P3 are aligned on the substrate 102. Herein, the semi transmitting part P3 corresponds to an area where the groove 150 is to be formed, and the shielding part P2 corresponds to an area where the insulating film 106 is to be formed. The photolithography process is performed by use of the halftone mask 152, thereby forming the insulating film 106 having the groove 150, as shown in FIG. 5B.

[0040] After a photo sensitive organic material is deposited on the substrate 102 where the insulating film 106 is formed, the photo sensitive organic material is patterned by the photolithography process and the etching process, thereby forming the barrier rib 108, as shown in FIG. 5C. The barrier rib 108 is formed in a non light emitting area to cross a plurality of anode electrodes 104 for dividing pixels. Herein, the part of the barrier rib 108 is filled into the groove 150 which formed on the insulating film 106, thus the barrier rib 108 can be firmly in contact with the insulating film 106.

[0041] An organic material is deposited on the substrate 102 where the barrier rib 108 is formed by use of a thermal deposition method and a vacuum deposition method in use of a shadow mask, thereby forming the organic light emitting layer 110, as shown in FIG. 5D.

[0042] A metal material is deposited on the substrate 102 where the organic light emitting layer 110 is formed,

thereby forming the cathode electrode 112, as shown in FIG. 5E.

[0043] As described above, the organic EL display device and the fabricating method thereof according to the present invention has at least one groove which is located at the contact area of the barrier rib and the insulating film, and which is provided in the insulating film. Accordingly, the contact area of the barrier rib and the insulating film is widened, thereby improving the adhesive strength between the barrier rib and the insulating film. As a result, it is possible to prevent the defect in forming the barrier rib, e.g., the barrier rib being separated from the insulating film.

[0044] Although the present invention has been explained by the embodiments shown in the drawings described above, it should be understood to the ordinary skilled person in the art that the invention is not limited to the embodiments, but rather that various changes or modifications thereof are possible without departing from the spirit of the invention. Accordingly, the scope of the invention shall be determined only by the appended claims and their equivalents.

Claims

1. An organic electro luminescence display device, comprising:

first and second electrodes formed to cross each other with an organic light emitting layer therebetween;
a barrier rib which crosses the first electrode and is parallel to the second electrode; and
an insulating film which is located between the barrier rib and the first electrode and defines an area of forming the organic light emitting layer,

and

wherein the insulating film has at least one groove which is provided in a contact area with the barrier rib.

2. The organic electro luminescence display device according to claim 1, wherein the groove is filled with part of the barrier rib.

3. A fabricating method of an organic electro luminescence display device, comprising the steps of:

forming a first electrode on a substrate;
forming an insulating film which partially exposes the first electrode to define a light emitting area;
forming a barrier rib which crosses the first electrode;
forming an organic light emitting layer in the light emitting area; and
forming a second electrode which crosses the

first electrode with the organic light emitting layer therebetween,

and

wherein the step of forming the insulating film has the step of forming at least one groove which is filled with part of the barrier rib in a contact area with the barrier rib. 5

4. The fabricating method according to claim 3, wherein the step of forming the at least one groove includes the step of: 10

forming an insulating material on the substrate where the first electrode is formed; 15
aligning a halftone mask which has a transmitting part, a shielding part and a semi transmitting part corresponding to an area where the groove is to be formed, on the substrate where the insulating material is formed; and 20
patterning the insulating material by a photolithography process by use of the halftone mask.

25

30

35

40

45

50

55

FIG. 1
RELATED ART




FIG.2
RELATED ART




FIG. 3A
RELATED ART




FIG.3B
RELATED ART




FIG.3C
RELATED ART




FIG.3D
RELATED ART




FIG.3E
RELATED ART




FIG. 4




FIG.5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E





FIG. 6





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 05 02 2909

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 5 701 055 A (NAGAYAMA ET AL) 23 December 1997 (1997-12-23) * figures 7A-H,14A-D,16,22,23,25 *	1-4	H01L51/52
A	US 2002/110940 A1 (YAMAGATA HIROKAZU ET AL) 15 August 2002 (2002-08-15) * the whole document *	1-4	
A	US 2003/015961 A1 (YAMAZAKI SHUNPEI) 23 January 2003 (2003-01-23) * the whole document *	1-4	
A	US 2004/113550 A1 (ADACHI MASAYA ET AL) 17 June 2004 (2004-06-17) * the whole document *	1-4	
			TECHNICAL FIELDS SEARCHED (IPC)
			H01L
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 13 February 2006	Examiner Saldamli, S
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

2

EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 05 02 2909

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-02-2006

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5701055	A	23-12-1997	NONE	
US 2002110940	A1	15-08-2002	TW 525402 B	21-03-2003
US 2003015961	A1	23-01-2003	JP 2003092191 A	28-03-2003
US 2004113550	A1	17-06-2004	JP 2004192977 A	08-07-2004

专利名称(译)	有机电致发光显示装置及其制造方法		
公开(公告)号	EP1657762A1	公开(公告)日	2006-05-17
申请号	EP2005022909	申请日	2005-10-20
申请(专利权)人(译)	LG电子株式会社.		
当前申请(专利权)人(译)	LG电子株式会社.		
[标]发明人	SON WOO HYUN		
发明人	SON, WOO HYUN		
IPC分类号	H01L51/52		
CPC分类号	H01L27/3283		
优先权	1020040092139 2004-11-11 KR		
外部链接	Espacenet		

摘要(译)

公开了一种适用于防止形成障壁的缺陷的有机电致发光显示装置及其制造方法。根据本发明实施方案的有机电致发光显示装置包括第一电极和第二电极，所述第一电极和第二电极形成为彼此交叉，其间具有有机发光层；阻挡肋，其与第一电极交叉并与第二电极平行；绝缘膜位于阻挡肋和第一电极之间并限定形成有机发光层的区域，并且其中绝缘膜具有至少一个凹槽，该凹槽设置在与阻挡肋的接触区域中。

FIG. 4

