

(19)



(11)

**EP 2 765 832 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:

**04.04.2018 Bulletin 2018/14**

(21) Application number: **13194341.7**

(22) Date of filing: **26.11.2013**

(51) Int Cl.:

|                                             |                                             |
|---------------------------------------------|---------------------------------------------|
| <b>H05B 33/14</b> <small>(2006.01)</small>  | <b>C09K 11/06</b> <small>(2006.01)</small>  |
| <b>C07F 7/08</b> <small>(2006.01)</small>   | <b>H01L 51/00</b> <small>(2006.01)</small>  |
| <b>C07C 211/54</b> <small>(2006.01)</small> | <b>C07D 263/57</b> <small>(2006.01)</small> |
| <b>C07D 209/08</b> <small>(2006.01)</small> | <b>C07D 277/66</b> <small>(2006.01)</small> |
| <b>C07D 209/86</b> <small>(2006.01)</small> | <b>C07C 13/62</b> <small>(2006.01)</small>  |
| <b>C07C 13/66</b> <small>(2006.01)</small>  |                                             |

(54) **Multicyclic aromatic compound and organic light emitting device using the same**

Multizyklische aromatische Verbindung und organische lichtemittierende Vorrichtung damit

Composé aromatique multi-cyclique et dispositif électroluminescent organique l'utilisant

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**

(30) Priority: **26.11.2012 KR 20120134761**

(43) Date of publication of application:

**13.08.2014 Bulletin 2014/33**

(73) Proprietor: **Heesung Material Ltd.**

**Yongin-City 449-884 (KR)**

(72) Inventors:

- **Lee, Do-Hyung**  
**448-985 Yongin-City (KR)**
- **Kim, Dong-Jun**  
**447-706 Osan-City (KR)**
- **No, Young-Seok**  
**363-813 Cheongwon-gun (KR)**
- **Chun, Hyundong**  
**110-837 Seoul (KR)**
- **Lee, Joo-Dong**  
**463-763 Seongnam-City (KR)**

(74) Representative: **Goddard, Heinz J.**

**Boehmert & Boehmert**  
**Anwaltpartnerschaft mbB**  
**Pettenkoferstrasse 22**  
**80336 München (DE)**

(56) References cited:

**KR-A- 20070 101 430 US-A1- 2009 230 854**

- **ZERUBBA U. LEVI ET AL:** "Synthesis and Electronic Properties of Extended, Fused-Ring Aromatic Systems Containing Multiple Pentalene Units", JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 132, no. 32, 18 August 2010 (2010-08-18), pages 11012-11014, XP55112102, ISSN: 0002-7863, DOI: 10.1021/ja1043159-& Zerubba Levi ET AL: "Supporting Information for: Synthesis and Electronic Properties of Extended, Fused-Ring Aromatic Systems Containing Multiple Pentalene Units", , 27 July 2010 (2010-07-27), pages S1-27, XP55114166, Retrieved from the Internet: URL: [http://pubs.acs.org/doi/suppl/10.1021/ja1043159/suppl\\_file/ja1043159\\_si\\_001.pdf](http://pubs.acs.org/doi/suppl/10.1021/ja1043159/suppl_file/ja1043159_si_001.pdf) [retrieved on 2014-04-15]
- **DANIEL T. CHASE ET AL:** "Electron-Accepting 6,12-Diethynylindeno[1,2-b]fluorenes: Synthesis, Crystal Structures, and Photophysical Properties", ANGEWANDTE CHEMIE INTERNATIONAL EDITION, vol. 50, no. 47, 18 November 2011 (2011-11-18), pages 11103-11106, XP55114418, ISSN: 1433-7851, DOI: 10.1002/anie.201104797
- **TAKESHI KAWASE ET AL:** "Dinaphthopentalenes: Pentalene Derivatives for Organic Thin-Film Transistors", ANGEWANDTE CHEMIE INTERNATIONAL EDITION, vol. 49, no. 42, 11 October 2010 (2010-10-11), pages 7728-7732, XP55114412, ISSN: 1433-7851, DOI: 10.1002/anie.201003609

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 2 765 832 B1**

- BAIDOSI W ET AL: "Selective Transformations of Phenylated Dienes to Polycyclic Compounds by the RhCl<sub>3</sub>- and PtCl<sub>4</sub>-Aliquat 336<sup>®</sup> Ion Pair Catalysts", TETRAHEDRON, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 52, no. 24, 10 June 1996 (1996-06-10), pages 8349-8364, XP004103883, ISSN: 0040-4020, DOI: 10.1016/0040-4020(96)00394-8
- YACOB BADRIEH ET AL: "Some Unusual Reactions of 1,2-Bis(phenylethynyl)benzene with Sulfur, Carbon Monoxide and Alkyl Acetylenedicarboxylates", CHEMISCHE BERICHTE, vol. 125, no. 3, 1 March 1992 (1992-03-01), pages 667-674, XP55114385, ISSN: 0009-2940, DOI: 10.1002/cber.19921250321
- A. STEPHEN K. HASHMI ET AL: "Gold-Catalyzed Synthesis of Dibenzopentalenes - Evidence for Gold Vinylidenes", ADVANCED SYNTHESIS & CATALYSIS, vol. 354, no. 4, 23 March 2012 (2012-03-23), pages 555-562, XP55114388, ISSN: 1615-4150, DOI: 10.1002/adsc.201200086
- FABIN GERSON ET AL: "Radical Ions of Conjugated Polycyclic Hydrocarbons Containing Two Phenalenyl  $\pi$ -Systems", HELVETICA CHIMICA ACTA, vol. 67, no. 4, 20 June 1984 (1984-06-20), pages 934-938, XP55114355, ISSN: 0018-019X, DOI: 10.1002/hlca.19840670403
- JONGTAE YANG ET AL: "Synthesis and Characterization of 5,10-Bis(2-thienyl)indeno[2,1-a]indene Derivatives: The First Examples of Conducting Polymers Containing a Rigid Bis(thienyl)butadiene Core", THE JOURNAL OF ORGANIC CHEMISTRY, vol. 65, no. 20, 1 October 2000 (2000-10-01), pages 6739-6742, XP55083843, ISSN: 0022-3263, DOI: 10.1021/jo991140y
- KAZUHIRO NAKASUJI ET AL: "Design and synthesis of a highly amphoteric condensed hydrocarbon with the highest reduction potential. Pentaleno[1,2,3-cd:4,5,6-c'd']diphenalene", JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 105, no. 15, 1 July 1983 (1983-07-01), pages 5136-5137, XP55114381, ISSN: 0002-7863, DOI: 10.1021/ja00353a049
- M. BALLESTER ET AL: "Perchlorotolane. A new synthesis and its thermal dimerization", TETRAHEDRON LETTERS, vol. 21, no. 29, 1 January 1980 (1980-01-01), pages 2845-2848, XP55112128, ISSN: 0040-4039, DOI: 10.1016/S0040-4039(00)78624-2

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

**Description**Field of the Invention

5   **[0001]** The present invention relates to a novel organic light emitting device.

Background of the Invention

10   **[0002]** An electroluminescent device is one type of self-luminescent-type display devices, and has advantages in that it has a wide viewing angle, an excellent contrast, and quick response time.

15   **[0003]** An organic light emitting device has a structure in which an organic thin film is disposed between two electrodes. When voltage is applied to an organic light emitting device having such a structure, light emits by electrons and holes injected from the two electrodes being dissipated after the electrons and holes make a pair by bonding in the organic thin film. The organic thin film may be formed as a monolayer or a multilayer as necessary.

20   **[0004]** Materials of an organic thin film may have a light emitting function when necessary. For example, as the material of an organic thin film, compounds capable of forming a light emitting layer alone may be used, or compounds capable of performing as a host or a dopant of a host-dopant-based light emitting layer may also be used. In addition to these, compounds capable of performing hole injection, hole transfer, electron blocking, hole blocking, electron transfer, electron injection, or the like, may also be used as the material of an organic thin film.

25   **[0005]** There have been continuous demands for the development of organic thin film materials in order to improve the performance, life span or efficiency of an organic light emitting device.

30   **[0006]** For example, CBP has been mostly widely known so far as a host material of a phosphorescent light emitting body, and an organic light emitting device in which a hole blocking layer such as BCP and BAQ is applied, and an organic light emitting device in which BAQ derivatives are used as a host are well known.

35   **[0007]** However, existing materials have advantages in the aspect of light emitting properties, but have disadvantages such that the materials change when going through a high-temperature deposition process under vacuum due to a low glass transition temperature and very low thermal stability. In an organic light emitting device, power efficiency = (n/voltage) x current efficiency, therefore, power efficiency is inversely proportional to voltage, and power efficiency needs to be high in order to have low power consumption of the organic light emitting device. In fact, an organic light emitting device that uses a phosphorescent light emitting material has quite high current efficiency (cd/A) compared to an organic light emitting device that uses a fluorescent light emitting material, however, when existing materials such as CBP or BAQ are used as the host of a phosphorescent light emitting material, there are no huge advantages in terms of power efficiency (lm/w) since driving voltage is high compared to that of an organic light emitting device using a fluorescent material. In addition, the life span of an organic light emitting device is not at all satisfactory, therefore, there have been demands for the development of host materials that are more stable and show more excellent performances.

40   KR20070101430 A discloses an organic electronic device comprising at least two electrodes and at least one organic layer placed between the electrodes, wherein more than one layer of the organic layer comprises a compound of fused aromatic rings, a specific substitution pattern comprising thienyl or dithienyl.

Summary of the Invention


45   **[0008]** The present invention provides a novel organic light emitting device according to claim 1. Further embodiments are disclosed in the dependent claims.

50   **[0009]** The present invention provides an organic light emitting device comprising: a first electrode; a second electrode; and one or more organic material layers provided between the first electrode and the second electrode, wherein one or more layers of the organic material layers include the compound of the following Chemical Formula 1:

55

55

[Chemical Formula 1]



wherein, in Chemical Formula 1, at least one of  $R_1$  and  $R_2$  is hydrogen; halogen; substituted or unsubstituted  $C_1$ - $C_{30}$  alkyl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si, and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si are fused; cyano;  $-NR_{11}R_{12}$ ;  $-SiR_{13}R_{14}R_{15}$ ;  $-OR_{16}$ ;  $-SR_{17}$ ; substituted or unsubstituted ( $C_6$ - $C_{30}$ ) ar ( $C_1$ - $C_{30}$ ) alkyl; substituted or unsubstituted  $C_1$ - $C_{30}$  alkylamino;  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si in which  $-SiR_{18}R_{19}R_{20}$  is substituted; substituted or unsubstituted  $C_6$ - $C_{30}$  arylamino; substituted or unsubstituted  $C_2$ - $C_{30}$  alkenyl; substituted or unsubstituted  $C_2$ - $C_{30}$  alkynyl; carboxyl; nitro or hydroxy; or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through  $C_3$ - $C_{30}$  alkylene or  $C_3$ - $C_{30}$  alkenylene that does or does not include a fused ring;

the other of  $R_1$  and  $R_2$  is hydrogen; halogen; substituted or unsubstituted  $C_1$ - $C_{30}$  alkyl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si, and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si are fused; cyano;  $-NR_{11}R_{12}$ ;  $-SiR_{13}R_{14}R_{15}$ ;  $-CR_{16}$ ;  $-SR_{17}$ ; substituted or unsubstituted ( $C_6$ - $C_{30}$ ) ar ( $C_1$ - $C_{30}$ ) alkyl; substituted or unsubstituted  $C_1$ - $C_{30}$  alkylamino;  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si in which  $-SiR_{18}R_{19}R_{20}$  is substituted; substituted or unsubstituted  $C_6$ - $C_{30}$  arylamino; substituted or unsubstituted  $C_2$ - $C_{30}$  alkenyl; substituted or unsubstituted  $C_2$ - $C_{30}$  alkynyl; carboxyl; nitro or hydroxy; or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through  $C_3$ - $C_{30}$

alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring;

R<sub>11</sub> to R<sub>20</sub> are each independently hydrogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; or substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl including one or more heteroatoms selected from N, O and Si, or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to

an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring;

R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen or a monovalent organic substituent; and

R<sub>3</sub> and R<sub>4</sub>, R<sub>4</sub> and R<sub>5</sub>, R<sub>5</sub> and R<sub>6</sub>, R<sub>7</sub> and R<sub>8</sub>, R<sub>8</sub> and R<sub>9</sub> or R<sub>9</sub> and R<sub>10</sub> form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.

**[0010]** According to one embodiment, the organic material layer that includes the compound of Chemical Formula 1 is a light emitting layer.

**[0011]** According to another embodiment, the organic material layer that includes the compound of Chemical Formula 1 further includes a light emitting dopant.

**[0012]** According to still another embodiment, the organic material layer that includes the compound of Chemical Formula 1 further includes a phosphorescent dopant.

#### Advantageous Effects

**[0013]** A Compound may be used as the material of an organic material layer of an organic light emitting device. The compound may be used as a hole injection material, a hole transfer material, a light emitting material, an electron transfer material, an electron injection material or the like in an organic light emitting device. In particular, the compound may be used as a light emitting material of an organic light emitting device. In addition, the compound may be used as a host material, particularly, a phosphorescent host material of the light emitting layer of an organic light emitting device.

**[0014]** When the compound is used as a light emitting material, there are advantages in that the material has excellent light emitting efficiency compared to existing materials, long life span of a device can be expected due to excellent life span properties of the material, and an organic light emitting device having improved power consumption can be manufactured by inducing the enhancement of power efficiency. In addition, the compound can accomplish appropriate color coordinates. Therefore, by using the compound, an organic light emitting device having high efficiency and long life span can be provided.



#### Brief Description of the Drawings

**[0015]** Figs. 1 to 3 illustrate the laminating order of electrodes and organic material layers of an organic light emitting device according to embodiments of the present invention.

#### Detailed Description of the Embodiments

**[0016]** Hereinafter, the present invention will be described in detail.

**[0017]** A compound used according to the present invention may be represented by Chemical Formula 1. The compound used according to the present invention is used as the material of an organic material layer of an organic light emitting device depending on the structural and physical properties of a core structure. Specifically, Chemical Formula 1 has dibenzopentalene as the core structure. Dibenzopentalene is an antiaromatic molecule having a pentalene skeleton. According to a Hückel rule, all the carbon molecules within the skeleton share  $n$  electrons, and the molecule having  $4n$  number of  $n$  electrons has 'antiaromaticity', and in this structure, reactivity improves due to the mobility improvement of the  $\pi$  electrons within the structure having a covalent bonding. In addition, the molecule can have aromaticity with excellent stability due to easy modification to a divalent anion form. Furthermore, the molecule having pentalene as a skeleton has high stability disregard of its antiaromaticity, therefore, the molecule is useful in preparing transition metal complexes having a sandwich form, and is useful as the material of an organic semiconductor or a dye having high oxidation/reduction potential as a  $\pi$  electron conjugation molecule having a trapezoid form. In this respect, the core structure of Chemical Formula 1 is different from the structure of dihydropentalene at the position of  $n$  electrons as shown below.



**[0018]** In "substituted or unsubstituted" of  $R_1$  to  $R_{10}$ , substituted means being each independently further substituted with one or more selected from the group consisting of deuterium, halogen,  $C_1$ - $C_{30}$  alkyl in which halogen is substituted or unsubstituted,  $C_6$ - $C_{30}$  aryl,  $C_3$ - $C_{30}$  heteroaryl in which  $C_6$ - $C_{30}$  aryl is substituted or unsubstituted, 5-membered to 7-membered heterocycloalkyl, 5-membered to 7-membered heterocycloalkyl in which one or more aromatic rings are fused,  $C_3$ - $C_{30}$  cycloalkyl,  $C_3$ - $C_{30}$  cycloalkyl in which one or more aromatic rings are fused, tri( $C_1$ - $C_{30}$ ) alkylsilyl, di( $C_1$ - $C_{30}$ ) alkyl ( $C_6$ - $C_{30}$ ) arylsilyl, tri ( $C_6$ - $C_{30}$ ) arylsilyl,  $C_2$ - $C_{30}$  alkenyl,  $C_2$ - $C_{30}$  alkynyl, cyano, carbazolyl,  $-NR_{31}R_{32}$ ,  $-SiR_{33}R_{34}R_{35}$ ,  $-OR_{36}$ ,  $-SR_{37}$ , ( $C_6$ - $C_{30}$ ) ar ( $C_1$ - $C_{30}$ ) alkyl, ( $C_1$ - $C_{30}$ ) alkyl ( $C_6$ - $C_{30}$ ) aryl,  $C_1$ - $C_{30}$  alkyloxy,  $C_1$ - $C_{30}$  alkylthio,  $C_6$ - $C_{30}$  aryloxy,  $C_6$ - $C_{30}$  arylthio, carboxyl, nitro or hydroxy, and  $R_{31}$  to  $R_{37}$  are each independently hydrogen,  $C_1$ - $C_{30}$  alkyl,  $C_6$ - $C_{30}$  aryl or  $C_3$ - $C_{30}$  heteroaryl, or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through  $C_3$ - $C_{30}$  alkylene or  $C_3$ - $C_{30}$  alkenylene that does or does not include a fused ring.

**[0019]** The substituent including "alkyl", "alkoxy" and additional "alkyl" parts, which is described in the present specification, includes all linear or branched forms.

**[0020]** In the present specification, cycloalkyl includes monocyclic or multicyclic having 3 to 30 carbon atoms, and specifically, includes all substituted or unsubstituted adamantyl, or substituted or unsubstituted  $C_7$ - $C_{30}$  bicycloalkyl. Herein, multicyclic means a group in which cycloalkyl is directly bonded to or condensed with other ring groups. Herein, the other ring groups may be cycloalkyl, but may also be other types of ring groups, for example, heterocycloalkyl, an aromatic ring, heteroaryl or the like. The number of cycloalkyl carbon atoms may be 3 to 30, specifically 3 to 20, and more specifically 5 to 12.

**[0021]** In the present specification, heterocycloalkyl includes S, O or N as a heteroatom, includes monocyclic or multicyclic having 2 to 30 carbon atoms, and may be further substituted with other substituents. Herein multicyclic means a group in which heterocycloalkyl is directly bonded to or condensed with other ring groups. Herein, the other ring groups may be heterocycloalkyl, but may also be other types of ring groups, for example, cycloalkyl, an aromatic ring, heteroaryl or the like. The number of heterocycloalkyl carbon atoms may be 2 to 30, specifically 2 to 20, and more specifically 3 to 12.

**[0022]** In the present specification, aryl is an organic radical derived from aromatic hydrocarbon by removing one hydrogen, and includes a single or fused ring including a 4-membered to 7-membered ring and more preferably a 5-membered or 6-membered ring, and also includes a structure in which one or more aryl are bonded through chemical bonding. Specific examples of the aryl include phenyl, naphthyl, biphenyl, anthryl, indenyl, fluorenyl, phenanthryl, triphenylenyl, pyrenyl, perylenyl, chrysenyl, naphthacenyl, fluoranthenyl, or the like, but are not limited thereto.

**[0023]** In the present specification, heteroaryl means an aryl group in which 1 to 4 heteroatoms selected from N, O and S are included as an aromatic ring skeleton atoms, and the rest of the aromatic ring skeleton atoms is carbon, and includes 5- to 6-membered monocyclic heteroaryl or multicyclic heteroaryl condensed with one or more benzene rings, and may be partially saturated. In addition, the heteroaryl in the present specification also includes a structure in which one or more heteroaryl are bonded through chemical bonding. The heteroaryl group includes a divalent aryl group in which the heteroatom within the ring is oxidized or becomes 4-membered, and for example, an N-oxide or quaternary salt is formed. Specific examples of the heteroaryl includes monocyclic heteroaryl such as furyl, thienyl, pyrrolyl, imidazolyl, pyrazolyl, thiazolyl, thiadiazolyl, isothiazolyl, isoxazolyl, oxazolyl, oxadiazolyl, triazinyl, tetrazinyl, triazolyl, tetrazolyl, furazanyl, pyridyl, pyrazinyl, pyrimidinyl or pyridazinyl, multicyclic heteroaryl such as benzofuryl, benzothieryl, isobenzofuryl, benzoimidazolyl, benzothiazolyl, benzoisothiazolyl, benzoisoxazolyl, benzooxazolyl, isoindolyl, indolyl, indazolyl, benzothiadiazolyl, quinolyl, isoquinolyl, cinnolyl, quinazolinyl, quinolizynyl, quinoxalynyl, carbazolyl, phenanthridinyl or benzodioxolyl, a corresponding N-oxide thereof such as pyridyl N-oxide or quinolyl N-oxide, a quaternary salt thereof, or the like, but are not limited thereto.

**[0024]** In addition, a " $C_1$ - $C_{30}$  alkyl" group described in the present specification includes  $C_1$ - $C_{20}$  alkyl or  $C_1$ - $C_{10}$  alkyl, a " $C_6$ - $C_{30}$  aryl" group includes  $C_6$ - $C_{20}$  aryl or  $C_6$ - $C_{12}$  aryl. A " $C_3$ - $C_{30}$  heteroaryl" group includes  $C_3$ - $C_{20}$  heteroaryl or  $C_3$ - $C_{12}$  heteroaryl, a " $C_3$ - $C_{30}$  cycloalkyl" group includes  $C_3$ - $C_{20}$  cycloalkyl or  $C_3$ - $C_7$  cycloalkyl. A " $C_2$ - $C_{30}$  alkenyl or alkynyl" group includes  $C_2$ - $C_{20}$  alkenyl or alkynyl, or  $C_2$ - $C_{10}$  alkenyl or alkynyl.

**[0025]** In the present specification, halogen includes F, Cl, Br and I.

**[0026]** According to one embodiment of the present invention,  $R_1$  to  $R_{10}$  are each independently hydrogen, halogen, substituted or unsubstituted  $C_1$ - $C_{30}$  alkyl, substituted or unsubstituted  $C_6$ - $C_{30}$  aryl, substituted or unsubstituted  $C_6$ - $C_{30}$  aryl in which one or more substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyls are fused, substituted or unsubstituted  $C_3$ - $C_{30}$

heteroaryl, substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl, 5-membered to 7-membered heterocycloalkyl in which one or more substituted or unsubstituted aromatic rings are fused, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, C<sub>3</sub>-C<sub>30</sub> cycloalkyl in which one or more substituted or unsubstituted aromatic rings are fused, cyano, -NR<sub>11</sub>R<sub>12</sub>, -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>, -OR<sub>16</sub>, -SR<sub>17</sub>, substituted or unsubstituted (C<sub>6</sub>-C<sub>30</sub>) ar (C<sub>1</sub>-C<sub>30</sub>) alkyl, substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkylamino, C<sub>3</sub>-C<sub>30</sub> heteroaryl in which -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> is substituted, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> arylamino, substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl, substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkynyl, carboxyl, nitro or hydroxy, or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring; [0027] R<sub>11</sub> to R<sub>20</sub> are each independently substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl or substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl, or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through (C<sub>3</sub>-C<sub>30</sub>) alkylene or (C<sub>3</sub>-C<sub>30</sub>) alkenylene that does or does not include a fused ring; the heterocycloalkyl and heteroaryl include one or more heteroatoms selected from N, O, S and Si.

[0028] According to one embodiment of the present invention, R<sub>1</sub> to R<sub>10</sub> are each independently selected from hydrogen, halogen, alkyl such as methyl, ethyl, propyl, butyl, pentyl, hexyl, ethylhexyl, heptyl or octyl, aryl such as phenyl, naphthyl, fluorenyl, biphenyl, phenanthryl, terphenyl, pyrenyl, perylenyl, spirobifluorenyl, fluoranthenyl, chrysenyl or triphenylenyl, aryl in which one or more cycloalkyl are fused, such as 1,2-dihydroacenaphthyl, heteroaryl such as dibenzothiophenyl, dibenzofuryl, carbazolyl, pyridyl, furyl, thienyl, quinolyl, triazinyl, pyrimidinyl, pyridazinyl, quinoxalyl or phenanthrolinyl, heterocycloalkyl in which one or more aromatic rings are fused, such as benzopyrrolidino, benzopiperidino, dibenzomorpholino or dibenzoazepino, or amino in which aryl such as phenyl, naphthyl, fluorenyl, biphenyl, phenanthryl, terphenyl, pyrenyl, perylenyl, spirobifluorenyl, fluoranthenyl, chrysenyl or triphenylenyl, or heteroaryl such as dibenzothiophenyl, dibenzofuryl, carbazolyl, pyridyl, furyl, thienyl, quinolyl, triazinyl, pyrimidinyl, pyridazinyl, quinoxalyl, phenanthrolinyl is substituted, aryloxy such as biphenyloxy, arylthio such as biphenylthio, aralkyl such as biphenylmethyl or triphenylmethyl, carboxyl, nitro or hydroxy, but R<sub>1</sub> to R<sub>10</sub> are not limited thereto, and may be further substituted as in Chemical Formula 1.

[0029] According to one embodiment of the present invention, R<sub>1</sub> and R<sub>2</sub> are each independently halogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; cyano; -NR<sub>11</sub>R<sub>12</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituted or unsubstituted (C<sub>6</sub>-C<sub>30</sub>) ar (C<sub>1</sub>-C<sub>30</sub>) alkyl; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkylamino; C<sub>3</sub>-C<sub>30</sub> heteroaryl in which -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> is substituted; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> arylamino; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkynyl; carboxyl; nitro or hydroxy; or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.

[0030] According to one embodiment of the present invention, at least one of R<sub>1</sub> and R<sub>2</sub> has seven or more carbons in ring members.

[0031] According to one embodiment of the present invention, at least one of R<sub>1</sub> and R<sub>2</sub> includes two or more rings.

[0032] According to one embodiment of the present invention, R<sub>1</sub> and R<sub>2</sub> are different from each other.

[0033] According to one embodiment of the present invention, at least one of R<sub>1</sub> and R<sub>2</sub> is C<sub>1</sub>-C<sub>30</sub> alkyl.

[0034] According to one embodiment of the present invention, R<sub>1</sub> and R<sub>2</sub> may be selected from hydrogen, alkyl, phenyl, naphthyl, anthracenyl, phenanthrenyl, pyrenyl, phenyl- or alkyl-substituted fluorenyl, phenyl-substituted or unsubstituted carbazolyl, naphthyl-substituted phenyl, biphenyl, indenyl, acenaphthylenyl, fluoranthenyl, phenyl-substituted naphthyl, indolyl, benzoxazolyl, benzothiazolyl and arylamine-substituted phenyl.

[0035] According to one embodiment of the present invention, R<sub>1</sub> and R<sub>2</sub> may be selected from alkyl, naphthyl, anthracenyl, phenanthrenyl, pyrenyl, phenyl- or alkyl-substituted fluorenyl, phenyl-substituted or unsubstituted carbazolyl, naphthyl-substituted phenyl, biphenyl, indenyl, acenaphthylenyl, fluoranthenyl, phenyl-substituted naphthyl, indolyl, benzoxazolyl, benzothiazolyl and arylamine-substituted phenyl.

[0036] In Chemical Formula 1, R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen; or a monovalent organic substituent. As specific examples, R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen; halogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl in which one or more of substituted or

unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; cyano; -NR<sub>11</sub>R<sub>12</sub>; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituted or unsubstituted (C<sub>6</sub>-C<sub>30</sub>) ar (C<sub>1</sub>-C<sub>30</sub>) alkyl; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkylamino; C<sub>3</sub>-C<sub>30</sub> heteroaryl in which -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> is substituted; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> arylamino; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkynyl; carboxyl; nitro or hydroxy; or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.

**[0037]** According to one embodiment of the present invention, R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; or may form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.


**[0038]** According to one embodiment of the present invention, R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen; methyl or phenyl, or may form a phenyl group with an adjacent substituent.

**[0039]** According to one embodiment of the present invention, R<sub>5</sub> and R<sub>9</sub> are each independently hydrogen; methyl or phenyl, or form a phenyl group with an adjacent substituent, and R<sub>3</sub>, R<sub>4</sub>, R<sub>6</sub>, R<sub>7</sub>, R<sub>8</sub> and R<sub>10</sub> are hydrogen.


**[0040]** According to one embodiment of the present invention, R<sub>4</sub>, R<sub>5</sub>, R<sub>8</sub> and R<sub>9</sub> are each independently hydrogen; methyl or phenyl, or form a phenyl group with an adjacent substituent, and R<sub>3</sub>, R<sub>6</sub>, R<sub>7</sub> and R<sub>10</sub> are hydrogen.

**[0041]** According to one embodiment of the present invention, Chemical Formula 1 may be represented by any one of Chemical Formulae 2 to 9.


[Chemical Formula 2]




[Chemical Formula 3]




[Chemical Formula 4]




[Chemical Formula 5]




[Chemical Formula 6]




[Chemical Formula 7]



[Chemical Formula 8]



[Chemical Formula 9]




**[0042]** In Chemical Formulae 2 to 9,


R<sub>1</sub>, R<sub>2</sub>, R<sub>3</sub> and R<sub>4</sub> are the same as those defined in Claim 1,


p and q each independently represent an integer of 1 to 4,


Y<sub>1</sub> to Y<sub>4</sub> represent one of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl, substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl and substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, or a ring in which two or more of these rings are fused.


**[0043]** According to one embodiment, Chemical Formula 1 may be illustrated by the following structural formulae, however, the scope of the present invention is not limited thereto.














5




145




146




147



148




149




150


10




151




152




153



154




155




156

15


20




157




158




159



160




161




162

25


30




163




164




165



166




167




168

35


40




169




170




171



172




173




174

45


50




175




176




177



178





179




180

55







[0044] The compounds described in the present specification may be prepared with reference to preparation examples

described later.

**[0045]** The present invention provides an organic light emitting device that includes a first electrode, a second electrode, and one or more organic material layers provided between the first electrode and the second electrode, wherein one or more layers of the organic material layers include the compound of Chemical Formula 1.

**[0046]** The laminating order of the electrodes and the organic material layers of the organic light emitting device according to embodiments of the present invention is illustrated in Figs. 1 to 3. However, these diagrams are not intended to limit the scope of the present invention, and the structures of organic light emitting devices known in the related art may also be applied to the present invention.

**[0047]** According to Fig. 1, an organic light emitting device in which an anode (200), an organic material layer (300) and a cathode (400) are laminated on a substrate (100) in consecutive order is shown by the diagram. However, the structure of the organic light emitting device is not limited to this structure only, and as shown in Fig. 2, an organic light emitting device in which a cathode, an organic material layer and an anode are laminated on a substrate in consecutive order may be included.

**[0048]** Fig. 3 illustrates the case in which the organic material layer is a multilayer. An organic light emitting device according to Fig. 3 includes a hole injection layer (301), a hole transfer layer (302), a light emitting layer (303), an electron transfer layer (304) and an electron injection layer (305). However, the scope of the present invention is not limited to this laminated structure, and when necessary, other layers except a light emitting layer may not be included, and other necessary layers having other functions may be added.

**[0049]** An organic light emitting device according to the present invention may be prepared using methods known in the related art except that the compound of Chemical Formula 1 is included in one or more layers of the organic material layers.

**[0050]** The compound of Chemical Formula 1 may form one or more layers of the organic material layers alone in the organic light emitting device. However, when necessary, the compound of Chemical Formula 1 may form the organic material layers by being mixed with other materials.

**[0051]** The compound of Chemical Formula 1 may be used as a hole injection material, a hole transfer material, a light emitting material, an electron transfer material, an electron injection material or the like in an organic light emitting device. Particularly, the compound of Chemical Formula 1 may be used as a light emitting material of an organic light emitting device, specifically as a host material of the light emitting layer, and particularly, as a phosphorescent host material, and in this case, an organic light emitting device having high efficiency and long life span can be provided.

According to one specific example, the compound of Chemical Formula 1 may be used as a fluorescent blue host material. **[0052]** According to one embodiment, the compound of Chemical Formula 1 may particularly function as an organic light emitting compound, therefore, the organic material layer that includes the compound of Chemical Formula 1 is a light emitting layer.

**[0053]** According to another embodiment, the compound of Chemical Formula 1 may function as a light emitting host material, therefore, the organic material layer that includes the compound of Chemical Formula 1 further includes a light emitting dopant.

**[0054]** According to another embodiment, the organic material layer that includes the compound of Chemical Formula 1 further includes a fluorescent dopant.


**[0055]** According to another embodiment, the organic material layer that includes the compound of Chemical Formula 1 further includes a blue fluorescent dopant.

**[0056]** According to another embodiment, the organic material layer that includes the compound of Chemical Formula 1 further includes a phosphorescent dopant.

**[0057]** The light emitting dopant applied to an organic light emitting device of the present invention is not particularly limited, however, the compounds of the following Chemical Formula 10 may be illustrated.



**[0058]** Herein,  $\text{M}^1$  is selected from the group consisting of metals of group 7, group 8, group 9, group 10, group 11, group 13, group 14, group 15 and group 16, and ligands  $\text{L}^{101}$ ,  $\text{L}^{102}$  and  $\text{L}^{103}$  are each independently selected from the following structures.



**[0059]** In Chemical Formula 10,

R<sub>201</sub> to R<sub>203</sub> are each independently hydrogen, deuterium, C<sub>1</sub>-C<sub>30</sub> alkyl in which halogen is substituted or unsubstituted, C<sub>6</sub>-C<sub>30</sub> aryl in which C<sub>1</sub>-C<sub>30</sub> alkyl is substituted or unsubstituted, or halogen;

R<sub>204</sub> to R<sub>219</sub> are each independently hydrogen, deuterium, substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl, substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkoxy, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, substituted or unsubstituted mono- or di-(C<sub>1</sub>-C<sub>30</sub>) alkylamino, substituted or unsubstituted mono- or di-(C<sub>6</sub>-C<sub>30</sub>) arylamino, SF<sub>5</sub>, substituted or unsubstituted tri(C<sub>1</sub>-C<sub>30</sub>) alkylsilyl, substituted or unsubstituted di (C<sub>1</sub>-C<sub>30</sub>) alkyl (C<sub>6</sub>-C<sub>30</sub>) arylsilyl, substituted or unsubstituted tri (C<sub>6</sub>-C<sub>30</sub>) arylsilyl, cyano, or halogen;

R<sub>220</sub> to R<sub>223</sub> are each independently hydrogen, deuterium, C<sub>1</sub>-C<sub>30</sub> alkyl in which halogen is substituted or unsubstituted, C<sub>6</sub>-C<sub>30</sub> aryl in which C<sub>1</sub>-C<sub>30</sub> alkyl is substituted or unsubstituted;

R<sub>224</sub> and R<sub>225</sub> are each independently hydrogen, deuterium, substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, or halogen, or R<sub>224</sub> and R<sub>225</sub> may form a monocyclic or multicyclic aliphatic ring, or a monocyclic

or multicyclic aromatic ring, by being linked through C<sub>3</sub>-C<sub>12</sub> alkylene or C<sub>3</sub>-C<sub>12</sub> alkenylene that does or does not include a fused ring;

R<sub>226</sub> is substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl, or halogen;


R<sub>227</sub> to R<sub>229</sub> are each independently hydrogen, deuterium, substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl, substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, or halogen;

R<sub>230</sub> and R<sub>231</sub> are each independently hydrogen, C<sub>1</sub>-C<sub>20</sub> alkyl in which halogen is substituted or unsubstituted, C<sub>6</sub>-C<sub>20</sub> aryl, halogen, cyano, tri (C<sub>1</sub>-C<sub>20</sub>)alkylsilyl, di (C<sub>1</sub>-C<sub>20</sub>) alkyl (C<sub>6</sub>-C<sub>20</sub>)arylsilyl, tri(C<sub>6</sub>-C<sub>20</sub>)arylsilyl, C<sub>1</sub>-C<sub>20</sub> alkoxy, C<sub>1</sub>-C<sub>20</sub> alkylcarbonyl, C<sub>6</sub>-C<sub>20</sub> arylcarbonyl, di (C<sub>1</sub>-C<sub>10</sub>)alkylamino or di (C<sub>6</sub>-C<sub>20</sub>) arylamino, or R<sub>230</sub> and R<sub>231</sub> form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked through C<sub>3</sub>-C<sub>12</sub> alkylene or C<sub>3</sub>-C<sub>12</sub> alkenylene that does or does not include a fused ring;

The alkyl, aryl, or a monocyclic or multicyclic aliphatic ring or a monocyclic or multicyclic aromatic ring formed by being linked through C<sub>3</sub>-C<sub>12</sub> alkylene or C<sub>3</sub>-C<sub>12</sub> alkenylene that does or does not include a fused ring, which are included in R<sub>230</sub> and R<sub>231</sub>, may be further substituted with one or more substituents selected from C<sub>1</sub>-C<sub>20</sub> alkyl in which halogen is substituted or unsubstituted, halogen, cyano, tri (C<sub>1</sub>-C<sub>20</sub>) alkylsilyl, di (C<sub>1</sub>-C<sub>20</sub>) alkyl (C<sub>6</sub>-C<sub>20</sub>) arylsilyl, tri(C<sub>6</sub>-C<sub>20</sub>)arylsilyl, C<sub>1</sub>-C<sub>20</sub> alkoxy, C<sub>1</sub>-C<sub>20</sub> alkylcarbonyl, C<sub>6</sub>-C<sub>20</sub> arylcarbonyl, di (C<sub>1</sub>-C<sub>20</sub>) alkylamino, di (C<sub>6</sub>-C<sub>20</sub>) arylamino, phenyl, naphthyl, anthryl, fluorenyl or spirobifluorenyl, or may be further substituted with phenyl or fluorenyl in which one or more substituents selected from the group consisting of (C<sub>1</sub>-C<sub>20</sub>) alkyl in which halogen is substituted or unsubstituted, halogen, cyano, tri(C<sub>1</sub>-C<sub>20</sub>)alkylsilyl, di(C<sub>1</sub>-C<sub>20</sub>) alkyl (C<sub>6</sub>-C<sub>20</sub>) arylsilyl, tri (C<sub>6</sub>-C<sub>20</sub>) arylsilyl, (C<sub>1</sub>-C<sub>20</sub>) alkoxy, (C<sub>3</sub>-C<sub>20</sub>) alkylcarbonyl, (C<sub>6</sub>-C<sub>20</sub>) arylcarbonyl, di(C<sub>1</sub>-C<sub>20</sub>)alkylamino, di(C<sub>6</sub>-C<sub>20</sub>)arylamino, phenyl, naphthyl, anthryl, fluorenyl, and spirobifluorenyl are substituted;

R<sub>232</sub> to R<sub>239</sub> are each independently hydrogen, (C<sub>1</sub>-C<sub>20</sub>)alkyl in which halogen is substituted or unsubstituted, (C<sub>1</sub>-C<sub>20</sub>) alkoxy, (C<sub>3</sub>-C<sub>12</sub>) cycloalkyl, halogen, cyano, (C<sub>6</sub>-C<sub>20</sub>)aryl, (C<sub>4</sub>-C<sub>20</sub>) heteroaryl, tri (C<sub>1</sub>-C<sub>20</sub>) alkylsilyl, di (C<sub>1</sub>-C<sub>20</sub>) alkyl (C<sub>6</sub>-C<sub>20</sub>) arylsilyl or tri (C<sub>6</sub>-C<sub>20</sub>) arylsilyl; and

Q is



and R<sub>241</sub> to R<sub>252</sub> are each independently hydrogen, C<sub>1</sub>-C<sub>60</sub> alkyl in which halogen is substituted or unsubstituted, C<sub>1</sub>-C<sub>30</sub> alkoxy, halogen, C<sub>6</sub>-C<sub>60</sub> aryl, cyano, C<sub>5</sub>-C<sub>60</sub> cycloalkyl, or R<sub>241</sub> to R<sub>252</sub> may form a C<sub>5</sub>-C<sub>7</sub> spiro ring or a C<sub>5</sub>-C<sub>9</sub> fused ring by being linked to an adjacent substituent through alkylene or alkenylene, or may form a C<sub>5</sub>-C<sub>7</sub> fused ring by being linked to R<sub>207</sub> or R<sub>208</sub> through alkylene or alkenylene.

[0060] m<sup>1</sup> is selected from Ir, Pt, Pd, Rh, Re, Os, Tl, Pb, Bi, In, Sn, Sb, Te, Au and Ag, and the compound of Chemical Formula 10 includes those illustrated in Korean Patent Application No. 10-2009-0037519, but is not limited thereto.

[0061] In the organic light emitting device of the present invention, the organic material layer that includes the compound of Chemical Formula 1 may further include one or more compounds selected from the group consisting of arylamine-based compounds or styrylarylamine-based compounds. The arylamine-based compound or styrylarylamine-based compound also includes those illustrated in Korean Patent Application No. 10-2008-0123276 or Korean Patent Application No. 10-2008-0107606, but is not limited thereto.

[0062] In addition, in the organic light emitting device of the present invention, the organic material layer that includes the compound of Chemical Formula 1 may further include one or more metals or complex compounds selected from the group consisting of group 1, group 2, period 4 and period 5 transition metals, lanthanide-series metals, and organic metals of d-transition atoms.

[0063] The organic light emitting device according to the present invention may be manufactured as an organic light emitting device that emits white light by further including one or more organic materials that emit blue, red or green light in addition to the compound of Chemical Formula 1. For example, the organic light emitting device may be manufactured to emit white light by including two or more light emitting materials in one organic material layer, or including two or more light emitting layers that emit different light emitting colors.

[0064] The organic light emitting device may include a light emitting layer and a charge generation layer together.

[0065] In the organic light emitting device according to the present invention, materials other than the compound of Chemical Formula 1 are illustrated below, however, these are for the illustrative purposes only, and do not intend to limit the scope of the present invention, and these materials may be substituted with materials known in the related art.

[0066] As the anode material, materials having relatively large work function may be used, and transparent conductive oxides, metals, conductive polymers or the like may be used.

[0067] As the cathode material, materials having relatively small work function may be used, and metals, metal oxides,

conductive polymers or the like may be used.

**[0068]** As the hole transfer material, a pyrazoline derivative, an arylamine-based derivative, a stilbene derivative, a triphenyldiamine derivative or the like may be used, and a low molecular or high molecular material may also be used.

**[0069]** As the light emitting material, a red, green or blue light emitting material may be used, and when necessary, two or more light emitting materials may be mixed and used. In addition, as the light emitting material, a fluorescent material may be used, but a phosphorescent material may also be used. As the light emitting material, materials that emit alone by bonding the holes and the electrons injected from an anode and a cathode, respectively, may be used, however, materials in which a host material and a dopant material are both involved in light emitting may also be used.


**[0070]** As the electron transfer material, an oxadiazole derivative, anthraquinodimethane and a derivative thereof, benzoquinone and a derivative thereof, naphthoquinone and a derivative thereof, anthraquinone and a derivative thereof, tetracyanoanthraquinodimethane and a derivative thereof, a fluorenone derivative, diphenyldicyanoethylene and a derivative thereof, a diphenoquinone derivative, 8-hydroxyquinoline and a metal complex of a derivative thereof, or the like, may be used, and a high molecular material as well as a low molecular material may also be used.

**[0071]** As the electron injection material, for example, LiF is typically used in the related industry, however, the present invention is not limited thereto.

**[0072]** Hereinafter, an organic light emitting compound according to the present invention, the preparation method thereof, and light emitting properties of the device will be described with reference to representative compounds of the present invention in order to understand the present invention in detail, however, this is only to illustrate the embodiments, and the scope of the present invention is not limited to these compounds.

[Preparation Example 1] Preparation of Compound 1

**[0073]**



Preparation of Compound 1-1

**[0074]** After 10 g (42.7 mmol) of dibenzopentalenedione and 22.5 g (108 mmol) of phosphorus pentachloride were placed in a vessel, the vessel was sealed and heated until a liquid formed, and then an excess acetic acid solution was added thereto and the result was stirred for 48 hours. After the reaction completed, the compound was filtered using water, and then the liquid was extracted using water and diethylether. The solution was vacuum distilled, and separated and purified using a column, resulting in 5.8 g (16.9 mmol) of Compound 1-1.

Preparation of Compound 1-2


**[0075]** 5 g (14.6 mmol) of Compound 1-1 was dissolved in acetic acid, and then the mixture was heated under reflux for 4 hours. After the reaction completed, the result was extracted using diethylether and water, and recrystallized using ethyl acetate, resulting in 3 g (14.6 mmol) of Compound 1-2.

Preparation of Compound 1

**[0076]** A solution in which 6 g (29.4 mmol) of Compound 1-2 and 0.12 ml (4.7 mmol) of bromine were dissolved in 300 ml of carbon disulfide was stirred for 12 hours at 0°C. After the stirring, the carbon disulfide was removed by vacuum distillation, and 19.6 g (117.5 mmol) of silver nitrate was added thereto. The mixture was dissolved in 250 ml of benzene, and the result was heated under reflux for 2 hours. After the reaction completed, the solution was vacuum distilled, and separated and purified using a column, resulting in 2.8 g (14.1 mmol) of Compound 1.

[Preparation Example 2] Preparation of Compound 5

**[0077]**



#### Preparation of Compound 5-1


**[0078]** To a solution in which 337 mg (1.77 mmol) of CuI and 744 mg (1.06 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 150 ml of triethylamine, 3.2 g (31.8 mmol) of phenylacetylene and 10 g (35.3 mmol) of 1-bromo-2-iodobenzene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution and then extracted using ethyl acetate. The solution was vacuum distilled, and separated and purified using a column, resulting in 9 g (35.0 mmol) of Compound 5-1.

#### Preparation of Compound 5

**[0079]** After 4.3 g (39 mmol) of hydroquinone, 12.67 g (38.9 mmol) of  $\text{Cs}_2\text{CO}_3$ , 5.9 g (38.9 mmol) of CsF, 0.12 g (0.59 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.27 g (0.29 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, a solution in which 5 g (19.45 mmol) of Compound 5-1 was dissolved in 150 ml of 1,4-dioxane was added thereto, and then the mixture was stirred for 24 hours at 120°C. After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 5.5 g (15.5 mmol) of Compound 5.

#### [Preparation Example 3] Preparation of Compound 6

##### [0080]



#### Preparation of Compound 6-1

**[0081]** A solution in which 15 g (82.4 mmol) of 2-bromobenzonitrile and 16.2 g (98.9 mmol) of  $\text{PhSOOH}$  were dissolved in 100 ml of DMF was heated under reflux for 2 hours at 80°C. After the reaction completed, the result was extracted using ethyl acetate and water, and the solution obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 18.0 g (70.0 mmol) of Compound 6-1 was obtained.

#### Preparation of Compound 6-2

**[0082]** 15 g (58.3 mmol) of Compound 6-1, 60 ml of 1M DIBAL solution and 45 ml of dichloromethane was placed in a reaction vessel in consecutive order, and the mixture was stirred for 2 hours at -78°C. After that, an excess 1M ammonium chloride solution was added thereto and the result was stirred for additional 1 hour. After the reaction completed, the result was extracted using dichloromethane and a hydrochloric acid solution, and the solution obtained

was vacuum distilled. The obtained solid was separated and purified using a column, and 12.1 g (46.6 mmol) of Compound 6-2 was obtained.

#### Preparation of Compound 6-3

**[0083]** After 10 g (38.4 mmol) of Compound 6-2 and 7 ml (46 mmol) of  $\text{ClP(O)OEt}_2$  were dissolved in 125 ml of THF, the mixture was stirred for 15 minutes at  $-78^\circ\text{C}$ . After that, 75 ml of an 1M LiHMDS solution was placed in a reaction vessel, and the result was stirred for 2 hours at room temperature. After the temperature of the reaction vessel was again lowered to  $-78^\circ\text{C}$ , 200ml of an 1M DIBAL solution was added thereto, and the result was stirred for 2 hours at room temperature. After the reaction completed, an ammonium chloride solution was added thereto, the result was shortly stirred, then the solution was extracted using dichloromethane, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 4.6 g (23 mmol) of Compound 6-3 was obtained.

#### Preparation of Compound 6-4

**[0084]** After 5 g (25 mmol) of Compound 6-3 and 4.7 g (27.4 mmol) of IBr were dissolved in 150 ml of dichloromethane, the mixture was stirred for 1 hour at  $-78^\circ\text{C}$ . After the reaction completed, a sodium sulfite solution was added thereto, and then the result was shortly stirred. Next, the solution was extracted using an organic solvent, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 6.3 g (15.4 mmol) of Compound 6-4 was obtained.

#### Preparation of Compound 6-5


**[0085]** After 5 g (12.2 mmol) of Compound 6-4, 3.1 g (18.4 mmol) of 1-naphthyl boronic acid, 1.4 g (1.2 mmol) of  $\text{Pd(PPh}_3)_4$ , and 7.8 g (36.9 mmol) of  $\text{K}_3\text{PO}_4$  were dissolved in 37 ml of 1,4-dioxane and 13 ml of water, the mixture was heated under reflux for 2 hours at  $90^\circ\text{C}$ . After the reaction completed, an ammonium chloride solution was added thereto, the solution was extracted using an organic solvent, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 4.3 g (10.4 mmol) of Compound 6-5 was obtained.

#### Preparation of Compound 6

**[0086]** After 6 g (14.7 mmol) of Compound 6-5, 2.7 g (22.1 mmol) of phenylboronic acid, 1.7 g (1.5 mmol) of  $\text{Pd(PPh}_3)_4$  and 9.4 g (44.2 mmol) of  $\text{K}_3\text{PO}_4$  were dissolved in 45 ml of 1,4-dioxane and 15 ml of water, the mixture was heated under reflux for 2 hours at  $90^\circ\text{C}$ . After the reaction completed, an ammonium chloride solution was added thereto, the solution was extracted using an organic solvent, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 5.4 g (13.3 mmol) of Compound 6 was obtained.

[Preparation Example 4] Preparation of Compound 66

#### [0087]




**[0088]** After 5 g (12.2 mmol) of Compound 6-5, 5.8 g (18.4 mmol) of phenylboronic acid, 1.4 g (1.2 mmol) of  $\text{Pd(PPh}_3)_4$ , and 7.8 g (36.9 mmol) of  $\text{K}_3\text{PO}_4$  were dissolved in 37 ml of 1,4-dioxane and 13 ml of water, the mixture was heated

under reflux for 2 hours at 90°C. After the reaction completed, an ammonium chloride solution was added thereto, the solution was extracted using an organic solvent, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 5.5 g (9.2 mmol) of Compound 66 was obtained.

#### [Preparation Example 5] Preparation of Compound 82

[0089]



#### Preparation of Compound 82-1

[0090] After 4 g (10 mmol) of 2,3,5,6-tetrabromobenzene and 5 ml (70 mmol) of furan were dissolved in 50 ml of THF, 25 ml of a 0.5M n-BuLi solution was added thereto at -78°C, and then the mixture was stirred for 18 hours. After the reaction completed, small amount of methanol was added thereto, the result was extracted using an organic solvent, and the solution obtained was vacuum distilled. The obtained solid was recrystallized using hexane and methanol, and 2.0 g (6.5 mmol) of Compound 82-1 was obtained.

#### Preparation of Compound 82-2

[0091] 8.7 g (132 mmol) of zinc powder and 8.7 ml (79 mmol) of titanium tetrachloride were dissolved in 200 ml of THF, and the mixture was heated under reflux for 18 hours. After the mixture was cooled to room temperature, a solution in which 4 g (13.2 mmol) of Compound 82-1 was dissolved in THF was added thereto, and the result was heated under reflux for 18 hours. After the reaction completed, an HCl solution was introduced thereto, the result was extracted using an organic solvent, and the solution obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 3.1 g (11.0 mmol) of Compound 82-2 was obtained.


#### Preparation of Compound 82-3

[0092] 2 g (7.0 mmol) of Compound 82-2, 0.7 g (7.0 mmol) of phenylacetylene, 0.3 g (0.3 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  and 4.5 g (21.0 mmol) of CuI were placed in a reaction vessel in consecutive order, dissolved in 30 ml of triethylamine, and the mixture was heated under reflux for 18 hours at 100°C. After the reaction completed, an HCl solution was introduced thereto, the result was extracted using an organic solvent, and then residual water was removed using sodium sulfate. After the solution was vacuum distilled, the obtained solid was separated and purified using a column, and 1.0 g (3.3 mmol) of Compound 82-3 was obtained.

#### Preparation of Compound 82

[0093] 5.5 g (18.0 mmol) of Compound B2-3, 5.9 g (9.0 mmol) of  $\text{Ni}(\text{PPh}_3)_2\text{Cl}_2$  and 1.8 g (26.9 mmol) of zinc powder were placed in a reaction vessel in consecutive order, were dissolved in 80 ml of tetrahydrofuran and 20 ml of diethylether, and the mixture was heated under reflux for 24 hours at 80°C. After the reaction completed, the result was extracted using an organic solvent, and the solution obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 1.5 g (3.2 mmol) of Compound 82 was obtained.

[Preparation Example 6] Preparation of Compound 107


**[0094]**Preparation of Compound 107-1

**[0095]** 4 g (14.0 mmol) of Compound 82-2, 2.1 g (14.0 mmol) of phenylacetylene, 0.5 g (0.7 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  and 8.9 g (42.0 mmol) of  $\text{CuI}$  were placed in a reaction vessel in consecutive order, were dissolved in 60 ml of triethylamine, and the mixture was heated under reflux for 18 hours at  $100^\circ\text{C}$ . After the reaction completed, an  $\text{HCl}$  solution was introduced thereto, the result was extracted using an organic solvent, and then residual water was removed using sodium sulfate. After the solution was vacuum distilled, the obtained solid was separated and purified using a column, and 2.1 g (5.9 mmol) of Compound 107-1 was obtained.


Preparation of Compound 107

**[0096]** 4 g (11.2 mmol) of Compound 107-1, 3.7 g (5.6 mmol) of  $\text{Ni}(\text{PPh}_3)_2\text{Cl}_2$  and 1.1 g (16.8 mmol) of zinc powder were placed in a reaction vessel in consecutive order, were dissolved in 48 ml of tetrahydrofuran and 12 ml of diethylether, and the mixture was heated under reflux for 24 hours at  $80^\circ\text{C}$ . After the reaction completed, the result was extracted using an organic solvent, and the solution obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 683 mg (1.2 mmol) of Compound 107 was obtained.

[Preparation Example 7] Preparation of Compound 116


**[0097]**Preparation of Compound 116-1

**[0098]** After 10 g (55.2 mmol) of 3-bromophenylacetylene, 14.3 g (82.9 mmol) of 2-naphthyl boronic acid, 6.4 g (5.5 mmol) of  $\text{Pd}(\text{PPh}_3)_4$  and 35.2 g (165 mmol) of  $\text{K}_3\text{PO}_4$  were dissolved in 150 ml of 1,4-dioxane and 50 ml of water, the mixture was heated under reflux for 2 hours at  $90^\circ\text{C}$ . After the reaction completed, an ammonium chloride solution was added thereto, the solution was extracted using an organic solvent, and the liquid obtained was vacuum distilled. The obtained solid was separated and purified using a column, and 10.2 g (44.7 mmol) of Compound 116-1 was obtained.



#### Preparation of Compound 116-2

**[0099]** To a solution in which 417 mg (2.2 mmol) of CuI and 922 mg (1.3 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 400 ml of triethylamine, 10 g (43.8 mmol) of Compound 116-1 and 12.5 g (43.8 mmol) of Compound 82-2 were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 9 g (43.4 mmol) of Compound 116-2.




#### Preparation of Compound 116-3

**[0100]** After the temperature of a solution in which 8 g (24.0 mmol) of 2-bromo-3-iodonaphthalene was dissolved in 12 ml of tetrahydrofuran was lowered to  $-78^\circ\text{C}$ , a 2.5M n-BuLi solution was added thereto, and the mixture was stirred for 40 minutes. After the reaction vessel was warmed to room temperature, 8.6 g (26.4 mmol) of  $\text{SnBu}_3\text{Cl}$  was added thereto, and the result was stirred for 18 hours. When the reaction completed, the result was washed with an ammonium chloride solution, extracted using an organic solvent, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 11.9 g (24.0 mmol) of 116-3.

#### Preparation of Compound 116-4

**[0101]** To a solution in which 38 mg (0.1 mmol) of CuI and 85 mg (0.1 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 20 ml of triethylamine, 2 g (4.0 mmol) of Compound 116-3 and 0.6 g (4.0 mmol) of 1-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 2.2 g (3.9 mmol) of Compound 116-4.




#### Preparation of Compound 116

**[0102]** 1.1 g (9.7 mmol) of hydroquinone, 3.2 g (9.7 mmol) of  $\text{Cs}_2\text{CO}_3$ , 1.5 g (9.7 mmol) of CsF, 0.03 g (0.15 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.07 g (0.07 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, and after a solution in which 2.1 g (4.8 mmol) of Compound 116-2 and 3 g (5.3 mmol) of Compound 116-4 were dissolved in 75 ml of 1,4-dioxane was added thereto, the mixture was stirred for 24 hours at  $150^\circ\text{C}$ . After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 1.2 g (1.8 mmol) of Compound 116.

#### [Preparation Example 8] Preparation of Compound 139

##### Preparation of Compound 139-1


###### [0103]



**[0104]** To a solution in which 0.17 g (0.9 mmol) of CuI and 0.37 g (0.5 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 400 ml of triethylamine, 5 g (17.5 mmol) of 1,2-dibromonaphthalene and 2.7 g (17.5 mmol) of 2-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 3 g (8.4 mmol) of Compound 139-1.

##### Preparation of Compound 139-2


###### [0105]



**[0106]** To a solution in which 0.17 g (0.9 mmol) of CuI and 0.37 g (0.5 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 400 ml of triethylamine, 5 g (17.5 mmol) of 1,2-dibromonaphthalene and 1.8 g (17.5 mmol) of phenylacetylene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 2.3 g (7.3 mmol) of Compound 139-2.

#### Preparation of Compound 139

**[0107]**




**[0108]** 1.3 g (11.8 mmol) of hydroquinone, 3.8 g (11.8 mmol) of  $\text{Cs}_2\text{CO}_3$ , 1.8 g (11.8 mmol) of CsF, 0.03 g (0.17 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.08 g (0.09 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, and after a solution in which 2 g (4.8 mmol) of Compound 139-1 and 2 g (5.3 mmol) of Compound 139-2 were dissolved in 60 ml of 1,4-dioxane was added thereto, the mixture was stirred for 24 hours at 150°C. After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 1.5 g (3.0 mmol) of Compound 139.

[Preparation Example 9] Preparation of Compound 163

#### Preparation of Compound 163-1


**[0109]**



**[0110]** To a solution in which 0.17 g (0.9 mmol) of CuI and 0.37 g (0.5 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 400 ml of triethylamine, 5 g (17.5 mmol) of 1,2-dibromonaphthalene and 3.5 g (17.5 mmol) of 9-ethynylantracene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 2.8 g (6.8 mmol) of Compound 163-1.

#### Preparation of Compound 163-2


**[0111]**



**[0112]** To a solution in which 0.17 g (0.9 mmol) of CuI and 0.37 g (0.5 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 400 ml of triethylamine, 5 g (17.5 mmol) of 1,2-dibromonaphthalene and 2.7 g (17.5 mmol) of 1-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 2.9 g (8.2 mmol) of Compound 163-2.

#### Preparation of Compound 163

**[0113]**




**[0114]** 1.7 g (15.2 mmol) of hydroquinone, 5.0 g (15.2 mmol) of  $\text{Cs}_2\text{CO}_3$ , 2.3 g (15.2 mmol) of CsF, 0.05 g (0.23 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.10 g (0.11 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, and after a solution in which 3.1 g (7.6 mmol) of Compound 163-1 and 3 g (8.4 mmol) of Compound 163-2 were dissolved in 100 ml of 1,4-dioxane was added thereto, the mixture was stirred for 24 hours at 150°C. After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 1.8 g (3.0 mmol) of Compound 163.

[Preparation Example 10] Preparation of Compound 206

#### Preparation of Compound 206-1

**[0115]**




**[0116]** To a solution in which 0.1 g (0.5 mmol) of CuI and 0.22 g (0.3 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 200

ml of triethylamine, 3 g (10.5 mmol) of 1,2-dibromonaphthalene and 1.6 g (10.5 mmol) of 2-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 1.6 g (4.5 mmol) of Compound 206-1.

#### Preparation of Compound 206-2


[0117]



[0118] To a solution in which 0.1 g (0.5 mmol) of CuI and 0.22 g (0.3 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 200 ml of triethylamine, 3 g (10.5 mmol) of 1,2-dibromonaphthalene and 1.6 g (10.5 mmol) of 1-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 1.2 g (3.3 mmol) of Compound 206-2.

#### Preparation of Compound 206

[0119]




[0120] 1.1 g (10.1 mmol) of hydroquinone, 3.3 g (10.1 mmol) of  $\text{Cs}_2\text{CO}_3$ , 1.5 g (10.1 mmol) of CsF, 0.04 g (0.2 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.07 g (0.08 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, and after a solution in which 1.8 g (5.0 mmol) of Compound 206-1 and 2 g (5.5 mmol) of Compound 206-2 were dissolved in 100 ml of 1,4-dioxane was added thereto, the mixture was stirred for 24 hours at 150°C. After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 1.1 g (2.0 mmol) of Compound 206.

[Preparation Example 11] Preparation of Compound 244

#### Preparation of Compound 244-1


[0121]



**[0122]** To a solution in which 0.07 g (0.4 mmol) of CuI and 0.15 g (0.2 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 60 ml of triethylamine, 2 g (7.0 mmol.) of 1-bromo-2-iodobenzene and 1.1 g (7.0 mmol) of 1-ethynynaphthalene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 1.7 g (5.6 mmol) of Compound 244-1.

#### Preparation of Compound 244-2


**[0123]**



**[0124]** To a solution in which 0.07 g (0.4 mmol) of CuI and 0.15 g (0.2 mmol) of  $\text{Pd}(\text{PPh}_3)_2\text{Cl}_2$  were dissolved in 80 ml of triethylamine, 2 g (7.0 mmol) of 1,2-dibromonaphthalene and 1.7 g (7.0 mmol) of 9,9-diethyl-2-ethynyl-9H-fluorene were added in consecutive order, and the mixture was stirred for 24 hours at room temperature. After the reaction completed, the result was washed with an ammonium chloride solution, and then extracted using ethyl acetate. The solution was vacuum distilled, and then separated and purified using a column, resulting in 1.1 g (2.5 mmol) of Compound 244-2.

#### Preparation of Compound 244

**[0125]**



**[0126]** 1.3 g (11.2 mmol) of hydroquinone, 3.8 g (11.2 mmol) of  $\text{Cs}_2\text{CO}_3$ , 1.8 g (11.2 mmol) of  $\text{CsF}$ , 0.04 g (0.18 mmol) of  $\text{P}(\text{t-Bu})_3$  and 0.08 g (0.09 mmol) of  $\text{Pd}_2(\text{dba})_3$  were placed in a reaction vessel, and after a solution in which 1.8 g (5.9 mmol) of Compound 244-1 and 2.9 g (6.4 mmol) of Compound 244-2 were dissolved in 60 ml of 1,4-dioxane was added thereto, the mixture was stirred for 24 hours at  $150^\circ\text{C}$ . After the reaction completed, the reaction solution was dissolved in toluene and then extracted, and residual water was removed using magnesium sulfate. The solution was vacuum distilled, and separated and purified using a column, resulting in 1.5 g (2.6 mmol) of Compound 244.

**[0127]** In addition, various compounds represented by Chemical Formulae 1 to 6 may be synthesized by introducing various substituents using well-known methods with any one, two or more mixtures selected from 2,4-dichloropyrido[2,3-d]pyrimidine (manufactured by OChem Incorporation), 2-chloro-pyrido[3,2-d]pyrimidine (manufactured by Anichem LLC), pyrido[4,3-d]pyrimidin-4(3H)-one (manufactured by Aces Pharma, Inc.), 2-chloro-6,7-dimethyl-pteridine (manufactured by International Laboratory Limited), 2-chloropteridine (manufactured by Princeton BioMolecular Research, Inc.), 3-chloroquinoline (manufactured by Texas Biochemicals Inc.), 2,4-dichloroquinoline (manufactured by Shanghai PI Chemicals Ltd), 2,3-dichloroquinoline (manufactured by Aces Pharma, Inc.), 1-chloroisoquinoline (manufactured by Alfa Aesar, China Ltd.), 1,3-dichloroisoquinoline (manufactured by Aalen Chemical Co. Ltd.) and 1,4-dichloroisoquinoline (manufactured by Bepharma Ltd) as a starting material.

**[0128]** Compound 1 to Compound 285 were prepared using the methods of Preparation Examples 1 to 11, and  $^1\text{H}$  NMR and MS/FAB of the prepared compounds are shown in Table 1.

[Table 1]

| Compound | $^1\text{H}$ NMR( $\text{CDCl}_3$ , 200MHz)                                                                                                                                                                                                                                                    | MS/FAB |            |
|----------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|------------|
|          |                                                                                                                                                                                                                                                                                                | Found  | Calculated |
| Ex       | $\delta=7.41\sim 7.52(15\text{H}, \text{m}), 7.67(2\text{H}, \text{d}), 8.22(1\text{H}, \text{s}), 8.54(2\text{H}, \text{d}), 8.57(1\text{H}, \text{s})$ .                                                                                                                                     | 407.51 | 407.17     |
| 1        | $\delta=8.42(4\text{H}, \text{d}), 8.10(4\text{H}, \text{d})$                                                                                                                                                                                                                                  | 202.25 | 202.08     |
| 3        | $\delta=8.42(4\text{H}, \text{d}), 8.10(4\text{H}, \text{d}), 2.34(6\text{H}, \text{s})$                                                                                                                                                                                                       | 230.30 | 230.11     |
| 5        | $\delta=7.68(4\text{H}, \text{d}), 7.54(4\text{H}, \text{t}), 7.47(2\text{H}, \text{t}), 7.21(2\text{H}, \text{d}), 7.03(2\text{H}, \text{d}), 6.92(2\text{H}, \text{t}), 6.85(2\text{H}, \text{t})$                                                                                           | 354.14 | 354.14     |
| 6        | $\delta=8.55(1\text{H}, \text{d}), 8.42(5\text{H}, \text{d}), 8.10(4\text{H}, \text{d}), 8.08(1\text{H}, \text{d}), 8.04(1\text{H}, \text{d}), 7.61(1\text{H}, \text{t}), 7.55(2\text{H}, \text{d}), 7.52(2\text{H}, \text{d}), 7.51(2\text{H}, \text{t}), 7.41(1\text{H}, \text{t})$          | 404.50 | 404.16     |
| 10       | $\delta=8.93(2\text{H}, \text{d}), 8.55(1\text{H}, \text{d}), 8.42(4\text{H}, \text{d}), 8.12(2\text{H}, \text{t}), 8.10(4\text{H}, \text{d}), 7.93(1\text{H}, \text{d}), 7.88\sim 7.82(4\text{H}, \text{m}), 7.52(2\text{H}, \text{d}), 7.51(2\text{H}, \text{t}), 7.41(1\text{H}, \text{t})$ | 454.56 | 454.17     |
| 13       | $\delta=8.55(1\text{H}, \text{d}), 8.42(4\text{H}, \text{d}), 8.12(1\text{H}, \text{d}), 8.10(4\text{H}, \text{d}), 7.94(1\text{H}, \text{d}), 7.63\sim 7.25(10\text{H}, \text{m})$                                                                                                            | 443.54 | 443.17     |
| 16       | $\delta=8.42(4\text{H}, \text{d}), 8.10(4\text{H}, \text{d}), 7.70(1\text{H}, \text{s}), 7.57(1\text{H}, \text{t}), 7.52(4\text{H}, \text{d}), 7.51(4\text{H}, \text{t}), 7.48(2\text{H}, \text{d}), 7.41(2\text{H}, \text{t})$                                                                | 430.54 | 430.17     |
| 19       | $\delta=8.42(4\text{H}, \text{d}), 8.10(4\text{H}, \text{d}), 8.00(2\text{H}, \text{d}), 7.92(1\text{H}, \text{d}), 7.73\sim 7.48(12\text{H}, \text{m}), 7.41(1\text{H}, \text{t})$                                                                                                            | 480.60 | 480.19     |

**EP 2 765 832 B1**

(continued)

| Compound | <sup>1</sup> H NMR(CDCI <sub>3</sub> , 200MHz)                                                                                                                                                                                | MS/FAB |            |
|----------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|------------|
|          |                                                                                                                                                                                                                               | Found  | Calculated |
| 21       | δ=8.42(4H, d), 8.10(4H, d), 7.83(1H, s), 7.52(4H, d), 7.51(4H, t), 7.41(2H, t), 7.21(2H, d), 6.58(1H, d), 6.39(1H, ds), 3.22(1H, d),                                                                                          | 392.49 | 392.16     |
| 24       | δ=8.42(5H, d), 8.10(4H, d), 7.96(1H, t), 7.90(1H, d), 7.80(1H, d), 7.58(1H, t), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.15(2H, s)                                                                                            | 428.52 | 428.16     |
| 27       | δ=8.55(2H, d), 8.42(4H, d), 8.10(4H, d), 8.01(2H, s), 7.55(2H, d), 7.52(2H, d), 7.51(4H, t), 7.49(2H, d), 7.41(2H, t)                                                                                                         | 480.60 | 480.19     |
| 30       | δ=8.42(4H, d), 8.10(4H, d), 7.92(2H, d), 7.73(2H, d), 7.58(2H, s), 7.52(4H, d), 7.51(4H, t), 7.41(2H, t)                                                                                                                      | 480.60 | 480.19     |
| 32       | δ=8.42(4H, d), 8.10(4H, d), 8.06(1H, s), 7.87~7.53(4H, m), 7.52(4H, d), 7.51(4H, t), 7.41(2H, t), 7.38~7.28(4H, s), 1.72(6H, s)                                                                                               | 546.70 | 546.23     |
| 35       | δ=8.55(1H, d), 8.42(4H, d), 8.10(4H, d), 7.98~7.69(4H, m), 7.58(2H, t), 7.52(6H, m), 7.45(1H, t), 7.41(1H, t), 7.33~7.25(2H, d)                                                                                               | 519.63 | 519.20     |
| 41       | δ=8.55(2H, d), 8.42(6H, d), 8.10(4H, d), 8.06(4H, d), 7.61(2H, t), 7.55(4H, d)                                                                                                                                                | 454.56 | 454.17     |
| 45       | δ=8.93(2H, d), 8.55(1H, d), 8.42(5H, d), 8.12(2H, d), 8.10(4H, d), 8.06(2H, d), 7.93(1H, d), 7.85(4H, t), 7.61(1H, t), 7.55(2H, d)                                                                                            | 504.62 | 504.19     |
| 47       | δ=8.55(2H, d), 8.42(5H, d), 8.10(4H, d), 8.06(2H, d), 7.90(2H, dd), 7.77~7.55(6H, m), 7.38~7.28(2H, m), 1.72(6H, s)                                                                                                           | 520.66 | 520.22     |
| 50       | δ=8.55(2H, d), 8.42(5H, d), 8.10(4H, d), 8.06(2H, d), 7.61(1H, t), 7.55(2H, d), 7.52(4H, dt), 7.41(1H, t), 7.25(4H, s)                                                                                                        | 480.60 | 480.19     |
| 52       | δ=8.55(2H, d), 8.42(6H, d), 8.10(4H, d), 8.06(4H, d), 7.61(2H, t), 7.55(4H, d), 7.25(4H, s)                                                                                                                                   | 530.66 | 530.20     |
| 57       | δ=8.55(1H, d), 8.42(5H, d), 8.10(4H, d), 8.06(2H, d), 7.61(1H, t), 7.55(2H, d), 7.33(1H, d), 7.26(1H, d), 7.21(2H, t), 6.94(1H, s), 3.22(1H, s)                                                                               | 442.55 | 442.17     |
| 59       | δ=8.55(1H, d), 8.42(5H, d), 8.10(4H, d), 8.06(2H, d), 7.96~7.79(4H, d), 7.61(1H, t), 7.58(1H, t), 7.55(2H, d), 7.15(2H, s)                                                                                                    | 478.58 | 478.17     |
| 66       | δ=8.55(1H, d), 8.42(5H, d), 8.10(4H, d), 8.06(2H, d), 7.61(1H, t), 7.58(1H, t), 7.55(2H, d), 7.25(4H, s)                                                                                                                      | 596.76 | 596.25     |
| 69       | δ=8.55(1H, d), 8.42(5H, d), 8.10(4H, d), 8.08(1H, d), 8.04(1H, d), 7.87(2H, d), 7.77(2H, s), 7.69(2H, d), 7.61(1H, t), 7.55(2H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t)                                                     | 569.69 | 569.21     |
| 71       | δ=8.55(1H, d), 8.42(5H, d), 8.18(1H, d), 8.10(4H, d), 8.08(1H, d), 8.04(1H, d), 8.00(1H, d), 7.87(1H, d), 7.77(2H, s), 7.69(1H, d), 7.58(2H, t), 7.55(2H, d), 7.52(2H, d), 7.51(2H, t), 7.50(2H, d), 7.45(2H, d), 7.41(1H, d) | 645.79 | 645.25     |
| 76       | δ=8.55(1H, d), 8.42(5H, d), 8.10(4H, d), 8.08(1H, d), 8.04(1H, d), 7.61(1H, d), 7.55(2H, d), 7.54(2H, d), 7.20(4H, t), 6.81(2H, d), 6.69(2H, d), 6.63(4H, d)                                                                  | 571.71 | 571.23     |
| 79       | δ=8.16(4H, d), 7.67(8H, d)                                                                                                                                                                                                    | 302.37 | 302.11     |
| 82       | δ=8.16(4H, d), 7.67(8H, d), 2.34(2H, s)                                                                                                                                                                                       | 330.42 | 330.14     |
| 86       | δ=8.31(2H, s), 8.16(4H, d), 7.91(2H, d), 7.87(1H, d), 7.67(8H, d), 7.61(1H, d), 7.52(2H, d), 7.51(2H, t), 7.45(1H, t), 7.41(1H, t), 7.39(2H, d)                                                                               | 554.68 | 554.20     |
| 87       | δ=8.27(1H, s), 8.16(4H, d), 7.91(4H, d), 7.67(8H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.39(4H, d)                                                                                                                      | 554.68 | 554.20     |

EP 2 765 832 B1

(continued)

| Compound | <sup>1</sup> H NMR(CDCl <sub>3</sub> , 200MHz)                                                                                                                                                                                | MS/FAB |            |
|----------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|------------|
|          |                                                                                                                                                                                                                               | Found  | Calculated |
| 90       | δ=8.16(4H, d), 7.93(1H, d), 7.87(1H, d), 7.77(1H, s), 7.67(8H, d), 7.63(1H, d), 7.55(1H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.38(1H, t), 7.28(1H, t), 1.72(2H, s)                                                     | 570.72 | 570.23     |
| 93       | δ=8.16(4H, d), 8.00(2H, d), 7.92(1H, d), 7.73(1H, d), 7.70(1H, s), 7.67(8H, d), 7.59(2H, d), 7.58(1H, s), 7.57(1H, t), 7.52(2H, d), 7.51(2H, t), 7.48(2H, d), 7.41(1H, t)                                                     | 580.71 | 580.22     |
| 96       | δ=8.16(4H, d), 7.67(8H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.33(1H, d), 7.26(1H, d), 7.21(2H, d), 6.94(1H, s), 3.22(1H, s)                                                                                            | 492.61 | 492.19     |
| 100      | δ=8.16(4H, d), 7.90(2H, d), 7.79(2H, d), 7.67(8H, d), 7.63(1H, d), 7.58(2H, t), 7.52(2H, d), 7.51(2H, t), 7.48(1H, s), 7.41(1H, t), 7.19(1H, d)                                                                               | 578.70 | 578.20     |
| 105      | δ=8.18(1H, d), 8.16(4H, d), 8.01(1H, d), 7.67(8H, d), 7.53(2H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t)                                                                                                                      | 511.63 | 511.24     |
| 107      | δ=8.55(2H, d), 8.42(2H, d), 8.16(4H, d), 8.08(2H, d), 8.04(2H, d), 7.67(8H, d), 7.61(2H, d), 7.55(4H, d)                                                                                                                      | 554.68 | 554.20     |
| 110      | δ=8.55(1H, s), 8.42(1H, d), 8.27(1H, s), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 7.91(4H, d), 7.67(8H, d), 7.61(1H, d), 7.55(2H, d), 7.39(4H, d)                                                                               | 604.74 | 604.22     |
| 115      | δ=8.55(1H, s), 8.42(1H, d), 8.16(4H, d), 8.12(1H, d), 8.08(1H, d), 8.04(1H, d), 7.87(1H, d), 7.77(1H, s), 7.69(1H, d), 7.67(8H, d), 7.63(1H, d), 7.61(1H, d), 7.55(2H, d), 7.50(1H, t), 7.29(1H, t)                           | 593.71 | 593.21     |
| 116      | δ=8.55(1H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 8.00(2H, d), 7.92(1H, d), 7.73(1H, d), 7.70(1H, s), 7.67(8H, d), 7.61(1H, d), 7.59(2H, d), 7.58(1H, s), 7.57(1H, t), 7.55(2H, d), 7.48(2H, d)              | 630.77 | 630.23     |
| 119      | δ=8.55(1H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 7.67(8H, d), 7.61(1H, d), 7.55(2H, d), 7.33(1H, d), 7.26(1H, d), 7.21(2H, d), 6.94(1H, s), 3.22(1H, s)                                                     | 542.67 | 542.20     |
| 124      | δ=8.55(2H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 7.94(1H, d), 7.87(1H, d), 7.77(1H, s), 7.69(1H, d), 7.67(8H, d), 7.61(1H, d), 7.58(2H, d), 7.55(2H, t), 7.50(2H, d), 7.45(1H, t), 7.33(1H, t), 7.25(1H, t) | 669.81 | 669.25     |
| 126      | δ=8.55(1H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 7.67(8H, d), 7.61(1H, d), 7.55(2H, d), 7.33(1H, t), 7.26(1H, t), 7.23(1H, d), 7.01(1H, d), 3.05(1H, d)                                                     | 543.65 | 543.20     |
| 132      | δ=8.54(2H, d), 8.16(4H, d), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t)                                                                                                                                   | 378.46 | 378.14     |
| 136      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, d), 7.55(2H, d), 2.34(1H, s)                                                                               | 442.55 | 442.17     |
| 139      | δ=8.54(2H, d), 8.16(4H, d), 8.00(2H, d), 7.92(1H, d), 7.81(2H, d), 7.73(1H, d), 7.67(4H, d), 7.59(2H, d), 7.58(1H, s), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t)                                                                  | 504.62 | 504.19     |
| 142      | δ=8.93(2H, d), 8.54(2H, d), 8.16(4H, d), 8.12(1H, d), 7.93(1H, s), 7.88(2H, t), 7.82(2H, dt), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t)                                                                 | 554.68 | 554.20     |
| 147      | δ=8.54(2H, d), 8.16(4H, d), 8.00(2H, d), 7.92(1H, d), 7.81(2H, d), 7.73(1H, d), 7.70(1H, s), 7.67(4H, d), 7.59(3H, s), 7.57(1H, t), 7.52(2H, d), 7.51(2H, t), 7.48(2H, d), 7.41(1H, t)                                        | 580.71 | 580.22     |
| 150      | δ=8.54(2H, d), 8.16(4H, d), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.33(1H, d), 7.26(1H, d), 7.21(2H, d), 6.94(1H, s), 3.22(1H, s)                                                                  | 492.61 | 492.19     |

**EP 2 765 832 B1**

(continued)


|    | Compound | <sup>1</sup> H NMR(CDCl <sub>3</sub> , 200MHz)                                                                                                                                                                  | MS/FAB |            |
|----|----------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|------------|
|    |          |                                                                                                                                                                                                                 | Found  | Calculated |
| 5  | 152      | δ=8.54(2H, d), 8.16(4H, d), 7.96(1H, d), 7.90(1H, d), 7.81(2H, d), 7.80(2H, d), 7.67(4H, d), 7.58(1H, d) 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.15(2H, s)                                                     | 528.64 | 582.19     |
| 10 | 158      | δ=8.54(2H, d), 8.16(4H, d), 7.81(2H, d), 7.74(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.39(2H, d)                                                                                           | 495.57 | 495.16     |
| 15 | 162      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 8.00(2H, d), 7.92(1H, d), 7.81(2H, d), 7.73(1H, d), 7.67(4H, d), 7.61(1H, t), 7.59(2H, d), 7.58(1H, d), 7.55(2H, d)                          | 554.68 | 554.20     |
| 20 | 164      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.27(1H, s), 8.16(4H, d), 8.06(2H, d), 7.91(4H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.39(4H, d)                                                    | 604.74 | 604.22     |
| 25 | 167      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 7.93(1H, d), 7.87(1H, d), 7.81(2H, d), 7.77(1H, s), 7.67(4H, d), 7.63(1H, d), 7.61(1H, t), 7.55(3H, d), 7.38(1H, t), 7.28(1H, t), 1.72(6, s) | 593.71 | 593.21     |
| 30 | 171      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.10(1H, d), 8.06(2H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.28(2H, d), 6.58(1H, d), 6.39(1H, t), 3.22(1H, d)                          | 542.67 | 542.20     |
| 35 | 176      | δ=8.55(1H, d), 8.54(2H, d), 8.42(3H, d), 8.16(4H, d), 8.10(2H, d), 8.06(2H, d), 7.96(1H, d), 7.90(1H, d), 7.81(3H, d), 7.67(4H, d), 7.61(1H, t), 7.58(1H, d), 7.55 (2H, d)                                      | 628.76 | 628.22     |
| 40 | 181      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 7.81(2H, d), 7.74(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.39(2H, d)                                                                 | 545.63 | 545.18     |
| 45 | 183      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.54(2H, d), 7.20(4H, t), 6.81(2H, t), 6.69(2H, d), 6.63(4H, d)                          | 671.83 | 671.26     |
| 50 | 189      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, dt), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t)                                                   | 454.56 | 454.17     |
| 55 | 194      | δ=8.54(2H, d), 8.16(4H, d), 7.98(9H, s), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t), 4.82(2H, s)                                                                                           | 580.71 | 580.22     |
|    | 196      | δ=8.55(1H, d), 8.54(2H, d), 8.16(4H, d), 8.12(1H, d), 7.94(1H, d), 7.81(2H, d), 7.67(4H, d), 7.63(1H, d), 7.52(2H, d), 7.51(2H, d), 7.50(1H, t), 7.41(1H, t), 7.33(1H, t), 7.29(1H, d), 7.25(1H, d)             | 543.65 | 543.20     |
|    | 199      | δ=8.54(2H, d), 8.16(4H, d), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t), 7.33(1H, d), 7.26(1H, d), 7.21(2H, d), 6.94(1H, s), 3.22(1H, s)                                                    | 492.61 | 492.19     |
|    | 204      | δ=8.54(2H, d), 8.16(4H, d), 7.81(2H, d), 7.74(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t), 7.39(2H, d)                                                                                           | 445.51 | 445.15     |
|    | 206      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 8.00(2H, d), 7.92(1H, d), 7.81(2H, d), 7.73(1H, d), 7.67(4H, d), 7.61(1H, t), 7.59(2H, d), 7.58(1H, s), 7.55(2H, d)                          | 554.68 | 554.20     |
|    | 213      | δ=8.55(1H, d), 8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.06(2H, d), 7.81(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.33(1H, t), 7.26(1H, t), 7.23(1H, d), 7.01(1H, d), 3.05(1H, s)                          | 543.65 | 543.20     |
|    | 217      | δ=8.55(1H, d), 8.54(2H, d), 8.42(3H, dd), 8.16(4H, d), 8.10(2H, d), 8.06(2H, d), 7.96(1H, d), 7.90(1H, d), 7.81(2H, d), 7.80(1H, d), 7.79(1H, d), 7.67(4H, d), 7.61(1H, t), 7.58(1H, t), 7.55(2H, d)            | 628.76 | 628.22     |
|    | 220      | δ=8.54(1H, d), 8.16(4H, d), 7.81(1H, d), 7.67(6H, ds), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t)                                                                                                                    | 378.46 | 378.14     |

**EP 2 765 832 B1**

(continued)

| Compound | <sup>1</sup> H NMR(CDCl <sub>3</sub> , 200MHz)                                                                                                                                                                                                             | MS/FAB |            |
|----------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------|------------|
|          |                                                                                                                                                                                                                                                            | Found  | Calculated |
| 222      | δ= δ=8.54(1H, d), 8.16(4H, d), 7.81(1H, d), 7.67(6H, ds), 7.52(4H, d), 7.51(4H, d), 7.41(2H, t)                                                                                                                                                            | 454.56 | 454.17     |
| 225      | δ= δ=8.54(1H, d), 8.31(2H, s), 8.16(4H, d), 7.91(2H, d), 7.87(1H, d), 7.81(1H, d), 7.67(6H, ds), 7.61(1H, d), 7.52(2H, d), 7.51(1H, d), 7.45(1H, t), 7.41(1H, t), 7.39(2H, d)                                                                              | 554.68 | 554.20     |
| 230      | δ=8.55(1H, d), 8.54(2H, s), 8.16(4H, d), 8.12(1H, d), 7.94(1H, d), 7.81(2H, d), 7.67(4H, d), 7.63(1H, d), 7.52(2H, d), 7.51(3H, m), 7.41(1H, t), 7.33(1H, t), 7.27(2H, t)                                                                                  | 543.65 | 543.20     |
| 233      | δ=8.54(2H, s), 8.16(4H, d), 7.81(2H, d), 7.67(4H, d), 7.52(2H, d), 7.51(2H, t), 7.41(1H, t), 7.33(1H, d), 7.26(1H, d), 7.21(2H, dd), 6.94(1H, s), 3.22(1H, s)                                                                                              | 492.61 | 492.19     |
| 238      | δ=8.54(1H, d), 8.16(4H, d), 7.81(1H, d), 7.74(2H, d), 7.67(6H, ds), 7.52(2H, d), 7.51(2H, d), 7.41(1H, t), 7.39(3H, dd)                                                                                                                                    | 495.57 | 495.16     |
| 240      | 5=8.54(2H, d), 8.42(1H, d), 8.16(4H, d), 8.08(1H, d), 8.04(1H, d), 8.00(2H, d), 7.92(1H, d), 7.81(1H, t), 7.73(1H, d), 7.67(6H, ds), 7.61(1H, t), 7.59(2H, d), 7.58(1H, s), 7.55(2H, d)                                                                    | 554.68 | 554.20     |
| 244      | δ=8.55(1H, d), 8.54(1H, d), 8.42(3H, dd), 8.16(2H, d), 8.10(2H, d), 8.06(2H, dd), 7.93(1H, d), 7.87(1H, d), 7.81(1H, t), 7.77(1H, s), 7.67(2H, d), 7.63(1H, d), 7.61(1H, t), 7.55(3H, dd), 7.38(1H, d), 7.28(1H, t), 1.91(4H, d), 0.90(6H, s)              | 598.77 | 598.27     |
| 246      | δ=8.55(2H, dd), 8.54(1H, d), 8.42(3H, dd), 8.16(2H, d), 8.10(2H, d), 8.06(2H, dd), 7.94(1H, d), 7.87(1H, d), 7.81(1H, t), 7.77(1H, s), 7.69(1H, d), 7.67(2H, d), 7.61(1H, t), 7.58(2H, t), 7.55(2H, d), 7.50(2H, d), 7.45(1H, t), 7.33(1H, t), 7.25(1H, t) | 619.75 | 619.23     |
| 249      | δ=8.55(1H, d), 8.42(3H, d), 8.16(2H, d), 8.10(2H, d), 8.06(2H, d), 7.67(4H, d), 7.61(1H, t), 7.55(2H, d), 7.26(1H, d), 7.21(2H, t), 7.18(1H, d), 6.58(1H, d), 6.39(1H, d), 4.74(1H, d)                                                                     | 492.61 | 492.19     |
| 253      | δ=7.57(2H, s), 7.45(2H, d), 7.23(2H, d), 2.34(6H, s)                                                                                                                                                                                                       | 203.30 | 203.11     |
| 258      | δ=8.93(4H, d), 8.12(4H, d), 7.93(2H, s), 7.88(4H, t), 7.82(4H, t), 7.57(2H, s), 7.45(2H, d), 7.23(2H, d), 2.34(6H, s)                                                                                                                                      | 582.73 | 582.23     |
| 260      | δ=8.18(2H, d), 8.12(2H, d), 8.04(2H, d), 7.88(2H, d), 7.82(2H, t), 7.71(8H, s), 7.57(2H, s), 7.45(2H, d), 7.23(2H, d), 2.34(6H, s)                                                                                                                         | 630.77 | 630.23     |
| 265      | δ=7.83(2H, s), 7.57(2H, s), 7.45(2H, d), 7.24(2H, d), 7.23(2H, d), 7.21(2H, d), 6.58(2H, d), 6.39(2H, t), 3.22(2H, s), 2.34(6H, s)                                                                                                                         | 458.59 | 458.20     |
| 269      | δ=7.52(4H, d), 7.51(4H, t), 7.45(4H, d), 7.41(2H, t), 2.34(12H, s)                                                                                                                                                                                         | 410.55 | 410.20     |
| 273      | δ=8.93(4H, d), 8.12(4H, d), 7.93(2H, s), 7.88(4H, t), 7.82(4H, t), 7.45(4H, d), 2.34(12H, s)                                                                                                                                                               | 610.78 | 610.27     |
| 277      | δ=8.55(2H, d), 8.12(2H, d), 7.94(2H, d), 7.63(2H, d), 7.50(2H, d), 7.45(4H, d), 7.33(2H, t), 7.29(2H, t), 7.25(2H, t), 2.34(12H, s)                                                                                                                        | 588.74 | 588.26     |
| 281      | δ=7.45(4H, d), 7.26(2H, d), 7.21(4H, dd), 7.18(2H, d), 6.58(2H, t), 6.39(2H, t), 4.74(2H, d), 2.34(12H, s)                                                                                                                                                 | 486.64 | 486.23     |
| 285      | 5=8.93(6H, ds), 8.12(6H, ds), 7.88(4H, t), 7.82(4H, t), 7.52(4H, d), 7.51(4H, t), 7.41(2H, t)                                                                                                                                                              | 654.79 | 654.23     |

**[0129]** As the verification of Compound 5 of the following Chemical Formula, the following data were verified.



UV: 261, 285 nm

PL: 365 nm


HOMO: -5.7 eV

LUMO: -3.3 eV


Bg: 2.4 eV

#### Experimental Example: Manufacture of OLED Device

**[0130]** A transparent ITO thin film obtained from an OLED glass (manufactured by Samsung Corning Co. Ltd.) was ultrasonic cleaned using trichloroethylene, acetone, ethanol and distilled water in consecutive order. An ITO substrate was placed on the substrate folder of a vacuum deposition apparatus, and was exhausted until the degree of vacuum within the chamber reaches  $10^{-6}$  torr, and then a hole injection layer having a thickness of 200 Å was deposited on the ITO substrate by applying current to the cells within the vacuum deposition apparatus and thereby evaporating 2-TNATA. A hole transfer layer having a thickness of 600 Å was deposited on the hole injection layer by applying current to another cell and thereby evaporating the following N,N'-bis( $\alpha$ -naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB). In one cell of the vacuum deposition apparatus, the compound prepared in the synthesis examples described in Table 2, or H1 was placed as a host material, and in another cell, the following dopant material D1 was placed and evaporated by applying current to the cell.



H1



D1

**[0131]** Subsequently, a light emitting layer was deposited to a thickness of 400 Å on the hole transfer layer by heating and depositing the two cells together with the deposition rate ratio of the dopant to be 5% by weight (host:dopant=95:5). Next, the following tris(8-hydroxyquinoline)aluminum (III) (Alq) was deposited to a thickness of 200 Å as an electron transfer layer. After that, the following lithium fluoride (LiF) compound was deposited to a thickness of 10 Å as an electron injection layer. Next, an OLED was manufactured by depositing Al cathode to a thickness of 1000 Å. Meanwhile, the OLED was manufactured by purifying each of all the organic compound materials necessary for the manufacture of the OLED device through vacuum sublimation purification under  $10^{-6}$  to  $10^{-8}$  torr.

#### Test Example: Evaluation of OLED Device Characteristics

**[0132]** The results of the current density and the life span of the OLED device manufactured in Experimental Examples 1 to 50 and Comparative Example 1, which were measured at 1000 cd/m<sup>2</sup> and 50% efficiency, are as shown in the following Table 2.

## EP 2 765 832 B1

[Table 2]

| No | Compound No. | Cd/A @1000 cd/m <sup>2</sup> | Life Span (T50) |
|----|--------------|------------------------------|-----------------|
|    | H1           | 4.5                          | 250             |
| 1  | 1            | 4.7                          | 450             |
| 2  | 3            | 4.6                          | 440             |
| 3  | 5            | 4.5                          | 410             |
| 4  | 6            | 4.8                          | 460             |
| 5  | 10           | 5.1                          | 500             |
| 6  | 13           | 5.1                          | 400             |
| 7  | 16           | 4.6                          | 410             |
| 8  | 19           | 4.8                          | 450             |
| 9  | 21           | 4.8                          | 460             |
| 10 | 24           | 4.6                          | 430             |
| 11 | 27           | 4.6                          | 430             |
| 12 | 30           | 4.5                          | 410             |
| 13 | 32           | 4.8                          | 450             |
| 14 | 35           | 4.9                          | 400             |
| 15 | 41           | 4.9                          | 470             |
| 16 | 45           | 4.7                          | 450             |
| 17 | 47           | 4.9                          | 430             |
| 18 | 50           | 4.6                          | 440             |
| 19 | 52           | 4.8                          | 450             |
| 20 | 57           | 4.9                          | 460             |
| 21 | 59           | 4.8                          | 440             |
| 22 | 66           | 5.0                          | 400             |
| 23 | 69           | 4.9                          | 410             |
| 24 | 71           | 5.1                          | 410             |
| 25 | 76           | 5.0                          | 400             |
| 26 | 79           | 4.8                          | 460             |
| 27 | 82           | 4.8                          | 450             |
| 28 | 86           | 4.9                          | 470             |
| 29 | 87           | 4.9                          | 490             |
| 30 | 90           | 5.1                          | 430             |
| 31 | 93           | 5.0                          | 450             |
| 32 | 96           | 4.7                          | 440             |
| 33 | 100          | 4.7                          | 430             |
| 34 | 105          | 4.7                          | 400             |
| 35 | 107          | 4.8                          | 460             |
| 36 | 110          | 4.7                          | 440             |
| 37 | 11.5         | 4.7                          | 400             |

(continued)

| No | Compound No. | Cd/A @1000 cd/m <sup>2</sup> | Life Span (T50) |
|----|--------------|------------------------------|-----------------|
| 38 | 116          | 4.9                          | 450             |
| 39 | 119          | 4.8                          | 440             |
| 40 | 124          | 5.0                          | 390             |
| 41 | 126          | 4.9                          | 400             |
| 42 | 132          | 4.7                          | 450             |
| 43 | 136          | 4.8                          | 430             |
| 44 | 139          | 4.9                          | 460             |
| 45 | 142          | 4.8                          | 460             |
| 46 | 147          | 4.6                          | 430             |
| 47 | 150          | 4.9                          | 460             |
| 48 | 152          | 4.8                          | 450             |
| 49 | 158          | 4.9                          | 400             |
| 50 | 162          | 4.7                          | 460             |

[Reference]

**[0133]**


100 Substrate  
 200 Anode  
 300 Organic Material Layer  
 301 Hole Injection Layer  
 302 Hole Transfer Layer  
 303 Light Emitting Layer  
 304 Electron Transfer Layer  
 305 Electron Injection Layer  
 400 Cathode

**Claims**

1. An organic light emitting device comprising:

a first electrode;  
 a second electrode; and  
 one or more organic material layers provided between the first electrode and the second electrode,  
 wherein one or more layers of the organic material layers include the compound of the following Chemical Formula 1:

[Chemical Formula 1]



wherein, in Chemical Formula 1,

at least one of  $R_1$  and  $R_2$  is hydrogen; halogen; substituted or unsubstituted  $C_1$ - $C_3$  alkyl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si, and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si are fused; cyano;  $-NR_{11}R_{12}$ ;  $-SiR_{13}R_{14}R_{15}$ ;  $-OR_{16}$ ;  $-SR_{17}$ ; substituted or unsubstituted  $(C_6-C_{30})ar(C_1-C_{30})alkyl$ ; substituted or unsubstituted  $C_1$ - $C_{30}$  alkylamino;  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O and Si in which  $-SiR_{18}R_{19}R_{20}$  is substituted; substituted or unsubstituted  $C_6$ - $C_{30}$  arylamino; substituted or unsubstituted  $C_2$ - $C_{30}$  alkenyl; substituted or unsubstituted  $C_2$ - $C_{30}$  alkynyl; carboxyl; nitro or hydroxy; or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through  $C_3$ - $C_{30}$  alkylene or  $C_3$ - $C_{30}$  alkenylene that does or does not include a fused ring; the other of  $R_1$  and  $R_2$  is hydrogen; halogen; substituted or unsubstituted  $C_1$ - $C_{30}$  alkyl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl; substituted or unsubstituted  $C_6$ - $C_{30}$  aryl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si, and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si; substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and substituted or unsubstituted  $C_3$ - $C_{30}$  heteroaryl including one or more heteroatoms selected from N, O, S and Si are fused; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl; substituted or unsubstituted  $C_3$ - $C_{30}$  cycloalkyl in which one or more of substituted or unsubstituted  $C_3$ - $C_{30}$  heterocycloalkyl including one or more heteroatoms selected from N, O, S and Si, a substituted or unsubstituted  $C_6$ - $C_{30}$  aromatic ring and

substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl including one or more heteroatoms selected from N, O, S and Si are fused; cyano; -NR<sub>11</sub>R<sub>12</sub>; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituted or unsubstituted (C<sub>6</sub>-C<sub>30</sub>)ar(C<sub>1</sub>-C<sub>30</sub>)alkyl; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkylamino; C<sub>3</sub>-C<sub>30</sub> heteroaryl including one or more heteroatoms selected from N, O, S and Si in which -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> is substituted; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> arylamino; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkynyl; carboxyl; nitro or hydroxy; or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring;

R<sub>11</sub> to R<sub>20</sub> are each independently hydrogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; or substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl including one or more heteroatoms selected from N, O and Si, or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring;

R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen or a monovalent organic substituent; and

R<sub>3</sub> and R<sub>4</sub>, R<sub>4</sub> and R<sub>5</sub>, R<sub>5</sub> and R<sub>6</sub>, R<sub>7</sub> and R<sub>8</sub>, R<sub>8</sub> and R<sub>9</sub> or R<sub>9</sub> and R<sub>10</sub> form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.

2. The organic light emitting device of Claim 1, wherein R<sub>3</sub> to R<sub>10</sub> are each independently hydrogen; halogen; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkyl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl are fused; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl; substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl; substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl in which one or more of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heterocycloalkyl, a substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aromatic ring and substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl are fused; cyano; -NR<sub>11</sub>R<sub>12</sub>; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituted or unsubstituted (C<sub>6</sub>-C<sub>30</sub>)ar(C<sub>1</sub>-C<sub>30</sub>)alkyl; substituted or unsubstituted C<sub>1</sub>-C<sub>30</sub> alkylamino; C<sub>3</sub>-C<sub>30</sub> heteroaryl in which -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> is substituted; substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> arylamino; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkenyl; substituted or unsubstituted C<sub>2</sub>-C<sub>30</sub> alkynyl; carboxyl; nitro or hydroxy; or form a monocyclic or multicyclic aliphatic ring, or a monocyclic or multicyclic aromatic ring, by being linked to an adjacent substituent through C<sub>3</sub>-C<sub>30</sub> alkylene or C<sub>3</sub>-C<sub>30</sub> alkenylene that does or does not include a fused ring.


3. The organic light emitting device of Claim 1, wherein R<sub>1</sub> to R<sub>10</sub> are each independently selected from hydrogen; halogen; methyl; ethyl; propyl; butyl; pentyl; hexyl; ethylhexyl; heptyl; octyl; phenyl; naphthyl; fluorenyl; biphenyl; phenanthryl; terphenyl; pyrenyl; perylenyl; spirobifluorenyl; fluoranthenyl; chrysenyl; triphenylenyl; 1,2-dihydroacenaphthyl; dibenzothiophenyl; dibenzofuryl; carbazolyl; pyridyl; furyl; thienyl; quinolyl; triazinyl; pyrimidinyl; pyridazinyl; quinoxalyl; phenanthrolinyl; benzopyrolidino; benzopiperidino; dibenzomorpholino; dibenzoazepino; amino substituted by phenyl, naphthyl, fluorenyl, biphenyl, phenanthryl, terphenyl, pyrenyl, perylenyl, spirobifluorenyl, fluoranthenyl, chrysenyl, triphenylenyl, dibenzothiophenyl, dibenzofuryl, carbazolyl, pyridyl, furyl, thienyl, quinolyl, triazinyl, pyrimidinyl, pyridazinyl, quinoxalyl or phenanthrolinyl; biphenyloxy; biphenylthio; biphenylmethyl; triphenylmethyl; carboxyl; nitro or hydroxy.

4. The organic light emitting device of Claim 1, wherein at least one of R<sub>1</sub> and R<sub>2</sub> is a substituent having seven or more carbons in ring members, a substituent including two or more rings, or C<sub>6</sub>-C<sub>30</sub> alkyl.


5. The organic light emitting device of Claim 1, wherein R<sub>1</sub> and R<sub>2</sub> are different from each other.

6. The organic light emitting device of Claim 1, wherein Chemical Formula 1 is represented by any one of Chemical Formulae 2 to 9:


[Chemical Formula 2]




[Chemical Formula 3]




[Chemical Formula 4]




[Chemical Formula 5]




[Chemical Formula 6]




[Chemical Formula 7]



[Chemical Formula 8]



[Chemical Formula 9]




wherein, in Chemical Formulae 2 to 9,

$R_1$ ,  $R_2$ ,  $R_3$  and  $R_4$  are the same as those defined in Claim 1,  
 $p$  and  $q$  each independently represent an integer of 1 to 4,


Y1 to Y4 represent one of substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> cycloalkyl, substituted or unsubstituted C<sub>3</sub>-C<sub>30</sub> heteroaryl, substituted or unsubstituted 5-membered to 7-membered heterocycloalkyl and substituted or unsubstituted C<sub>6</sub>-C<sub>30</sub> aryl, or a ring in which two or more of these rings are fused.

7. The organic light emitting device of Claim 1, wherein Chemical Formula 1 is selected from the following structural formulae:




5


10




25




26




27



28




29




30

15


20




31




32




33



34




35




36

25


30




37




38




39



40



41




42


35

40


45




43




44




45



46




47




48

50


55




49




50




51



52




53




54


5




55




56




57



58




59




60


10




61




62




63



64



65



66


15

20


25

30


35




67




68




69



70




71




72


40




73




74




75



76




77




78

45


50




79




80




81



82




83









84







55



5









10









15

20









25

30









35

40




45

50




55


5




157




158




159



160




161




162


10




163




164




165



166




167




168

15


20




169




170




171



172




173




174

25


30




175




176




177



178




179




180

35


40




181




182




183



184




185




186

45


50




187




188




189



190




191




192

55


5




193




194




195



196




197




198


10




199




200




201



202




203




204

15


20




205




206




207



208




209




210

25


30




211




212




213



214




215




216

35


40




217




218




219



220




221




222

45


50




223




224




225



226





227



228

55





8. The organic light emitting device of Claim 1, wherein the organic material layer that includes the compound of Chemical Formula 1 is a light emitting layer.

9. The organic light emitting device of Claim 1, wherein the organic material layer that includes the compound of Chemical Formula 1 further includes a fluorescent dopant or a phosphorescent dopant.

10. The organic light emitting device of Claim 1, wherein the organic material layer that includes the compound of Chemical Formula 1 further includes a blue fluorescent dopant.

11. The organic light emitting device of Claim 1, wherein the organic material layer that includes the compound of Chemical Formula 1 further includes one or more compounds selected from the group consisting of arylamine-based compounds and styrylamine-based compounds, or one or more metals or complex compounds selected from the group consisting of group 1, group 2, period 4 and period 5 transition metals, lanthanide-series metals, and organic metals of d-transition atoms.

12. The organic light emitting device of Claim 1, further comprising:

one or more organic materials emitting blue, red or green light, in addition to the compound of Chemical Formula 1.

13. The organic light emitting device of Claim 1, further comprising:

one or more organic material layers emitting blue, red or green light, in addition to the organic material layer including the compound of Chemical Formula 1.


14. The organic light emitting device of Claim 1, which emits white light.

## Patentansprüche

1. Organische lichtemittierende Vorrichtung, umfassend:

eine erste Elektrode;  
eine zweite Elektrode; und  
eine oder mehrere organische Materialschichten, die zwischen der ersten Elektrode und der zweiten Elektrode bereitgestellt sind,  
wobei eine oder mehrere Schichten der organischen Materialschichten die Verbindung der folgenden chemischen Formel 1 einschließt. bzw. einschließen:

[Chemische Formel 1]



wobei in chemischer Formel 1 wenigstens eines von  $R_1$  und  $R_2$  Wasserstoff; Halogen; substituiertes oder unsubstituiertes  $C_1$ - $C_{30}$ -Alkyl; substituiertes oder unsubstituiertes  $C_6$ - $C_3$ -Aryl; substituiertes oder unsubstituiertes  $C_6$ - $C_{30}$ -Aryl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Cycloalkyl, substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si kondensiert sind; substituiertes oder unsubstituiertes  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si; substituiertes oder unsubstituiertes  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, bei dem eines oder mehrere von substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Cycloalkyl, einem substituierten oder unsubstituierten  $C_6$ - $C_{30}$ -aromatischen Ring und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si kondensiert sind; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, bei dem eines oder mehrere von substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, einem substituierten oder unsubstituierten aromatischen  $C_6$ - $C_{30}$ -Ring und substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si kondensiert sind; substituiertes oder unsubstituiertes  $C_3$ - $C_{30}$ -Cycloalkyl; substituiertes oder unsubstituiertes  $C_3$ - $C_{30}$ -Cycloalkyl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, einem substituierten oder unsubstituierten aromatischen  $C_6$ - $C_{30}$ -Ring und substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si kondensiert sind; Cyano;  $-NR_{11}R_{12}$ ;  $-SiR_{13}R_{14}R_{15}$ ;  $-OR_{16}$ ;  $-SR_{17}$ ; substituiertes oder unsubstituiertes  $(C_6-C_{30})Ar(C_1-C_{30})alkyl$ ; substituiertes oder unsubstituiertes  $C_1$ - $C_{30}$ -Alkylamino;  $C_3$ - $C_{30}$ -Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, wobei  $-SiR_{18}R_{19}R_{20}$  substituiert ist; substituiertes oder unsubstituiertes  $C_6$ - $C_{30}$ -Arylamino; substituiertes oder unsubstituiertes  $C_2$ - $C_{30}$ -Alkenyl; sub-

stituiertes oder unsubstituiertes C<sub>2</sub>-C<sub>30</sub>-Alkynyl; Carboxyl; Nitro oder Hydroxy ist; oder einen monozyklischen oder multizyklischen aliphatischen Ring oder einen monozyklischen oder multizyklischen aromatischen Ring bildet, durch Verknüpfung an einen benachbarten Substituenten durch C<sub>3</sub>-C<sub>30</sub>-Alkylen oder C<sub>3</sub>-C<sub>30</sub>-Alkenylen, das einen kondensierten Ring einschließt oder nicht einschließt;

wobei die anderen von R<sub>1</sub> und R<sub>2</sub> Wasserstoff; Halogen; substituiertes oder unsubstituiertes C<sub>1</sub>-C<sub>30</sub>-Alkyl; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Aryl; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Aryl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si, und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si kondensiert sind; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, einem substituiertem oder unsubstituiertem aromatischen C<sub>6</sub>-C<sub>30</sub>-Ring und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si kondensiert sind; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si, einem substituierten oder unsubstituierten aromatischen C<sub>6</sub>-C<sub>30</sub>-Ring und substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si kondensiert sind; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heterocycloalkyl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si, einem substituiertem oder unsubstituiertem aromatischem C<sub>6</sub>-C<sub>30</sub>-Ring und substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O, S und Si kondensiert sind; Cyano; -NR<sub>11</sub>R<sub>12</sub>; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituiertes oder unsubstituiertes (C<sub>6</sub>-C<sub>30</sub>)Ar(C<sub>1</sub>-C<sub>30</sub>)alkyl; substituiertes oder unsubstituiertes C<sub>1</sub>-C<sub>30</sub>-Alkylamino; C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si, wobei -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> substituiert ist; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Arylamino; substituiertes oder unsubstituiertes C<sub>2</sub>-C<sub>30</sub>-Alkenyl; substituiertes oder unsubstituiertes C<sub>2</sub>-C<sub>30</sub>-Alkynyl; Carboxyl; Nitro oder Hydroxy sind; oder einen monozyklischen oder multizyklischen aliphatischen Ring oder einen monozyklischen oder multizyklischen aromatischen Ring bildet, durch Verknüpfung an einen benachbarten Substituenten durch C<sub>3</sub>-C<sub>30</sub>-Alkylen oder C<sub>3</sub>-C<sub>30</sub>-Alkenylen, das einen kondensierten Ring einschließt oder nicht; R<sub>11</sub> bis R<sub>20</sub> jeweils unabhängig Wasserstoff; substituiertes oder unsubstituiertes C<sub>1</sub>-C<sub>30</sub>-Alkyl; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Aryl; oder substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Heteroaryl einschließend ein oder mehrere Heteroatome ausgewählt aus N, O und Si ist, oder einen monozyklischen oder multizyklischen aliphatischen Ring oder einen monozyklischen oder multizyklischen aromatischen Ring bildet, durch Verknüpfung an einen benachbarten Substituenten durch C<sub>3</sub>-C<sub>30</sub>-Alkylen oder C<sub>3</sub>-C<sub>30</sub>-Alkenylen, das einen kondensierten Ring einschließt oder nicht; R<sub>3</sub> bis R<sub>10</sub> jeweils unabhängig Wasserstoff oder ein einwertiger organischer Substituent sind; und R<sub>3</sub> und R<sub>4</sub>, R<sub>4</sub> und R<sub>5</sub>, R<sub>5</sub> und R<sub>6</sub>, R<sub>7</sub> und R<sub>8</sub>, R<sub>8</sub> und R<sub>9</sub> oder R<sub>9</sub> und R<sub>10</sub> einen monozyklischen oder multizyklischen aliphatischen Ring oder einen monozyklischen oder multizyklischen aromatischen Ring bilden, durch Verknüpfung durch C<sub>3</sub>-C<sub>30</sub>-Alkylen oder C<sub>3</sub>-C<sub>30</sub>-Alkenylen, das einen kondensierten Ring einschließt oder nicht.

2. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei R<sub>3</sub> bis R<sub>10</sub> jeweils unabhängig Wasserstoff; Halogen; substituiertes oder unsubstituiertes C<sub>1</sub>-C<sub>30</sub>-Alkyl; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Aryl; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Aryl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl kondensiert sind; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Heteroaryl; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Heteroaryl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, einem substituiertem oder unsubstituiertem C<sub>6</sub>-C<sub>30</sub>-aromatischen Ring und substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl kondensiert sind; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl; substituiertes oder unsubstituiertes 5-gliedriges bis 7-gliedriges Heterocycloalkyl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-He-

terocycloalkyl, einem substituierten oder unsubstituierten aromatischen C<sub>6</sub>-C<sub>30</sub>-Ring und substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl kondensiert sind; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl; substituiertes oder unsubstituiertes C<sub>3</sub>-C<sub>30</sub>-Cycloalkyl, bei dem eines oder mehrere von substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heterocycloalkyl, einem substituierten oder unsubstituierten aromatischen C<sub>6</sub>-C<sub>30</sub>-Ring und substituiertem oder unsubstituiertem C<sub>3</sub>-C<sub>30</sub>-Heteroaryl kondensiert sind; Cyano; -NR<sub>11</sub>R<sub>12</sub>; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub>; -OR<sub>16</sub>; -SR<sub>17</sub>; substituiertes oder unsubstituiertes (C<sub>6</sub>-C<sub>30</sub>)Ar(C<sub>1</sub>-C<sub>30</sub>)alkyl; substituiertes oder unsubstituiertes C<sub>1</sub>-C<sub>30</sub>-Alkylamino; C<sub>3</sub>-C<sub>30</sub>-Heteroaryl, bei dem -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> substituiert ist; substituiertes oder unsubstituiertes C<sub>6</sub>-C<sub>30</sub>-Arylamino; substituiertes oder unsubstituiertes C<sub>2</sub>-C<sub>30</sub>-Alkenyl; substituiertes oder unsubstituiertes C<sub>2</sub>-C<sub>30</sub>-Alkynyl; Carboxyl; Nitro oder Hydroxy sind; oder einen monozyklischen oder multizyklischen aliphatischen Ring oder einen monozyklischen oder multizyklischen aromatischen Ring bilden, durch Verknüpfung mit einem benachbarten Substituenten durch C<sub>3</sub>-C<sub>30</sub>-Alkylen oder C<sub>3</sub>-C<sub>30</sub>-Alkenylen, das einen kondensierten Ring einschließt oder nicht.


3. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei R<sub>1</sub> bis R<sub>10</sub> jeweils unabhängig ausgewählt sind aus Wasserstoff; Halogen; Methyl; Ethyl; Propyl; Butyl; Pentyl; Hexyl; Ethylhexyl; Heptyl; Octyl; Phenyl; Naphthyl; Fluorenyl; Biphenyl; Phenanthryl; Terphenyl; Pyrenyl; Perylenyl; Spirobifluorenyl; Fluoranthenyl; Chrysenyl; Triphenylenyl; 1,2-Dihydroacenaphthyl; Dibenzothiophenyl; Dibenzofuryl; Carbazolyl; Pyridyl; Furyl; Thienyl; Chinolyl; Triazinyl; Pyrimidinyl; Pyridazinyl; Chinoxalanyl; Phenanthrolinyl; Benzopyrolidino; Benzopiperidino; Dibenzomorpholino; Dibenzazepino; Amino substituiert durch Phenyl, Naphthyl, Fluorenyl, Biphenyl, Phenanthryl, Terphenyl, Pyrenyl, Perylenyl, Spirobifluorenyl, Fluoranthenyl, Chrysenyl, Triphenylenyl, Dibenzothiophenyl, Dibenzofuryl, Carbazolyl, Pyridyl, Furyl, Thienyl, Chinolyl, Triazinyl, Pyrimidinyl, Pyridazinyl, Chinoxalanyl oder Phenanthrolinyl; Biphenyloxy; Biphenylthio; Biphenylmethyl; Triphenylmethyl; Carboxyl; Nitro oder Hydroxy.

4. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei wenigstens eines von R<sub>1</sub> und R<sub>2</sub> ein Substituent mit sieben oder mehreren Kohlenstoffen in Ringelementen, ein Substituent einschließend zwei oder mehrere Ringe oder C<sub>1</sub>-C<sub>30</sub>-Alkyl ist.


5. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei R<sub>1</sub> und R<sub>2</sub> voneinander verschieden sind.

6. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei chemische Formel 1 durch eine der chemischen Formeln 2 bis 9 dargestellt ist:


[Chemische Formel 2]




[Chemische Formel 3]




[Chemische Formel 4]




[Chemische Formel 5]




[Chemische Formel 6]




[Chemische Formel 7]



[Chemische Formel 8]



[Chemische Formel 9]



wobei in chemischen Formeln 2 bis 9


$R_1$ ,  $R_2$ ,  $R_3$  und  $R_4$  die Gleichen sind wie oben in Anspruch 1 definiert,

$p$  und  $q$  jeweils unabhängig eine ganze Zahl von 1 bis 4 darstellen,


$Y_1$  bis  $Y_4$  eines von substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Cycloalkyl, substituiertem oder unsubstituiertem  $C_3$ - $C_{30}$ -Heteroaryl, substituiertem oder unsubstituiertem 5-gliedrigem bis 7-gliedrigem Heterocycloalkyl und substituiertem oder unsubstituiertem  $C_6$ - $C_{30}$ -Aryl oder einen Ring, bei dem zwei oder mehrere dieser Ringe kondensiert sind, darstellen.

7. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei chemische Formel 1 aus den folgenden Strukturformeln ausgewählt ist:


5




1




2




3



4




5




6


10




7




8



9




10




11

15




12


20




13




14



15




16



17


25

30




18


35




19




20



21




22




23

40




24


45




25




26



27




28




29


50




30


55









5




133




134




135



136




137




138


10




139




140




141



142




143




144


15




145




146




147



148




149




150

20


25




151




152




153



154




155




156


35




157




158




159



160




161




162

40


45




163




164




165



166




167




168


50

55







5




241




242




243



244




245




246


10




247




248




249



250




251




252


20




253




254




255



256




257




258


30




259




260




261



262




263




264


40




265




266




267



268




269




270


45




271




272




273



274




275



276

55



8. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei die organische Materialschicht, die die Verbindung der chemischen Formel 1 einschließt, eine lichtemittierende Schicht ist.
9. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei die organische Materialschicht, die die Verbindung der chemischen Formel 1 einschließt, ferner einen Fluoreszenzdotanden oder einen Phosphoreszenzdotanden einschließt.
10. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei die organische Materialschicht, die die Verbindung der chemischen Formel 1 einschließt, ferner einen blauen Fluoreszenzdotanden einschließt.
11. Organische lichtemittierende Vorrichtung nach Anspruch 1, wobei die organische Materialschicht, die die Verbindung der chemischen Formel 1 einschließt, ferner eine oder mehrere Verbindungen einschließt, die ausgewählt sind aus der Gruppe bestehend aus Verbindungen auf Arylaminbasis und Verbindungen auf Styrylarylaminbasis, oder ein oder mehrere Metalle oder Komplexverbindungen ausgewählt aus der Gruppe bestehend aus Gruppe 1-, Gruppe 2-, Periode 4- und Periode 5-Übergangsmetallen, Metallen der Lanthanidserie und organischen Metallen von d-Übergangsatomen.
12. Organische lichtemittierende Vorrichtung nach Anspruch 1, weiter umfassend:
 


ein oder mehrere organische Materialien emittierend blaues, rotes oder grünes Licht, zusätzlich zu der Verbindung der chemischen Formel 1.
13. Organische lichtemittierende Vorrichtung nach Anspruch 1, weiter umfassend; ein oder mehrere organische Materialschichten, die blaues, rotes oder grünes Licht emittieren, zusätzlich zu der organischen Materialschicht, die die Verbindung der chemischen Formel 1 einschließt.
14. Organische lichtemittierende Vorrichtung nach Anspruch 1, die weißes Licht emittiert.

## Revendications

1. Dispositif électroluminescent organique comprenant :

une première électrode ;  
 une deuxième électrode ; et  
 dans lequel une ou plusieurs couches de matériau organique sont pourvues entre la première électrode et la deuxième électrode,  
 dans lequel une ou plusieurs couches du matériau organique renferment le composé de la formule chimique 1 suivante :

[Formule chimique 1]



où, dans la formule chimique 1,

au moins l'un de  $R_1$  et de  $R_2$  représente l'hydrogène ; l'halogène ; un alkyle en  $C_1$  à  $C_{30}$  substitué ou non substitué ; un aryle en  $C_6$  à  $C_{30}$  substitué ou non substitué ; un aryle en  $C_6$  à  $C_{30}$  substitué ou non substitué dans lequel un ou plusieurs d'un cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué, d'un hétéroalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si, et d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si sont fusionnés ; un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si ; un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si dans lequel un ou plusieurs d'un cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué, d'un cycle aromatique en  $C_6$  à  $C_{30}$  substitué ou non substitué et d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si sont fusionnés ; un hétérocycloalkyle de 5 à 7 membres substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si ; un hétérocycloalkyle de 5 à 7 membres substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si dans lequel un ou plusieurs d'un hétérocycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si, d'un cycle aromatique en  $C_6$  à  $C_{30}$  substitué ou non substitué ou d'un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, Si sont fusionnés ; un cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué ; un cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué dans lequel un ou plusieurs d'un hétérocycloalkyle en  $C_3$  à  $C_{30}$  renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si, d'un cycle aromatique en  $C_6$  à  $C_{30}$  substitué ou non substitué et d'un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si sont fusionnés ; un cyano ;  $-NR_{11}R_{12}$  ;  $-SiR_{13}R_{14}R_{15}$  ;  $-OR_{16}$  ;  $-SR_{17}$  ; un alkyle (en  $C_6$  à  $C_{30}$ ) aryle (en  $C_1$  à  $C_{30}$ ) ; un alkylamino en  $C_1$  à  $C_{30}$  substitué ou non substitué ; un hétéroaryle en  $C_3$  à  $C_{30}$  renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si dans lequel  $-SiR_{18}R_{19}R_{20}$  est substitué ; un arylamino en  $C_6$  à  $C_{30}$  substitué ou non substitué ; un alcényle en  $C_2$  à  $C_{30}$  substitué ou non substitué ; un alcynyle en  $C_2$  à  $C_{30}$  substitué ou non substitué ; un carboxyle ; un nitro ou un hydroxy ; ou forment un cycle aliphatique monocyclique ou multicyclique, ou un cycle aromatique monocyclique ou multicyclique, en étant liés à un substituant adjacent par le biais d'un alkylène en  $C_3$  à  $C_{30}$  ou d'un alcénylène en  $C_3$  à  $C_{30}$  pouvant ou non renfermer un cycle fusionné ;

l'autre de  $R_1$  et de  $R_2$  représente l'hydrogène ; l'halogène ; un alkyle en  $C_1$  à  $C_{30}$  substitué ou non substitué ; un aryle en  $C_6$  à  $C_{30}$  substitué ou non substitué ; un aryle en  $C_6$  à  $C_{30}$  substitué ou non substitué dans lequel un ou plusieurs du cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué, de l'hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si, et de l'hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si sont fusionnés ; un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si ; un hétéroaryle en  $C_3$  à  $C_{40}$  substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si dans lequel un ou plusieurs du cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué, d'un cycle aromatique en  $C_6$  à  $C_{30}$  substitué ou non substitué et d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si sont fusionnés ; un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si ; un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué renfermant un ou


plusieurs hétéroatomes sélectionnés parmi N, O, S et Si dans lequel un ou plusieurs d'un hétérocycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si, d'un cycle aromatique en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué et d'un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si sont fusionnés ; un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué ; un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué ou un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué dans lequel un ou plusieurs d'un hétérocycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si, d'un cycle aromatique en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué et d'un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si sont fusionnés ; un cyano ; -NR<sub>11</sub>R<sub>12</sub> ; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub> ; -OR<sub>16</sub> ; -SR<sub>17</sub> ; un alkyle (en C<sub>6</sub> à C<sub>30</sub>) aryle (en C<sub>1</sub> à C<sub>30</sub>) substitué ou non substitué ; un alkylamino en C<sub>1</sub> à C<sub>30</sub> substitué ou non substitué ; un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O, S et Si dans lequel -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> est substitué ; un arylamino en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ; un alcényle en C<sub>2</sub> à C<sub>30</sub> substitué ou non substitué ; un alcynyle en C<sub>2</sub> à C<sub>30</sub> substitué ou non substitué ; un carboxyle ; un nitro ou un hydroxy ; ou forment un cycle aliphatique monocyclique ou multicyclique, ou un cycle aromatique monocyclique ou multicyclique, en étant lié à un substituant adjacent par le biais de l'alkylène en C<sub>3</sub> à C<sub>30</sub> ou de l'alcénylène en C<sub>3</sub> à C<sub>30</sub> pouvant ou non renfermer un cycle fusionné ; R<sub>11</sub> à R<sub>20</sub> représentent chacun indépendamment l'hydrogène ; un alkyle en C<sub>1</sub> à C<sub>30</sub> substitué ou non substitué ; un aryle en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ; ou un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué renfermant un ou plusieurs hétéroatomes sélectionnés parmi N, O et Si, ou forment un cycle aliphatique monocyclique ou multicyclique, ou un cycle aromatique monocyclique ou multicyclique, en étant lié à un substituant adjacent par le biais de l'alkylène en C<sub>3</sub> à C<sub>30</sub> ou de l'alcénylène en C<sub>3</sub> à C<sub>30</sub> pouvant ou non renfermer un cycle fusionné ; R<sub>3</sub> à R<sub>10</sub> représentent chacun indépendamment l'hydrogène ou un substituant organique monovalent ; et R<sub>3</sub> et R<sub>4</sub>, R<sub>4</sub> et R<sub>5</sub>, R<sub>5</sub> et R<sub>6</sub>, R<sub>7</sub> et R<sub>8</sub>, R<sub>8</sub> et R<sub>9</sub> ou R<sub>9</sub> et R<sub>10</sub> forment un cycle aliphatique monocyclique ou multicyclique, en étant liés adjacent par le biais de l'alkylène en C<sub>3</sub> à C<sub>30</sub> ou de l'alcénylène en C<sub>3</sub> à C<sub>30</sub> pouvant ou non renfermer un cycle fusionné ;

2. Dispositif électroluminescent selon la revendication 1, dans lequel R<sub>3</sub> à R<sub>10</sub> représentent chacun indépendamment l'hydrogène ; l'halogène ; un alkyle en C<sub>1</sub> à C<sub>30</sub> substitué ou non substitué ; un aryle en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ; un aryle en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué dans lequel un ou plusieurs d'un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué, d'un hétéroalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué et d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué sont fusionnés ; un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué ; un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué dans lequel un ou plusieurs d'un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué, d'un cycle aromatique en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué et d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué sont fusionnés ; un hétérocycloalkyle de 5 à 7 membres substitué ou non substitué ; un hétérocycloalkyle de 5 à 7 membres substitué ou non substitué dans lequel un ou plusieurs d'un hétérocycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué, d'un cycle aromatique en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ou d'un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué sont fusionnés ; un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué, un cycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué dans lequel un ou plusieurs d'un hétérocycloalkyle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué, d'un cycle aromatique en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ou d'un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> substitué ou non substitué sont fusionnés ; un cyano ; -NR<sub>11</sub>R<sub>12</sub> ; -SiR<sub>13</sub>R<sub>14</sub>R<sub>15</sub> ; -OR<sub>16</sub> ; -SR<sub>17</sub> ; un alkyle (en C<sub>6</sub> à C<sub>30</sub>) aryle (en C<sub>1</sub> à C<sub>30</sub>) substitué ou non substitué ; un alkylamino en C<sub>1</sub> à C<sub>30</sub> substitué ou non substitué ; un hétéroaryle en C<sub>3</sub> à C<sub>30</sub> dans lequel -SiR<sub>18</sub>R<sub>19</sub>R<sub>20</sub> est substitué ; un arylamino en C<sub>6</sub> à C<sub>30</sub> substitué ou non substitué ; un alcényle en C<sub>2</sub> à C<sub>30</sub> substitué ou non substitué ; un alcynyle en C<sub>2</sub> à C<sub>30</sub> substitué ou non substitué ; un carboxyle ; un nitro ou un hydroxy ; ou forment un cycle aliphatique monocyclique ou multicyclique, ou un cycle aromatique monocyclique ou multicyclique, en étant liés à un substituant adjacent par le biais de l'alkylène en C<sub>3</sub> à C<sub>30</sub> ou de l'alcénylène en C<sub>3</sub> à C<sub>30</sub> pouvant ou non renfermer un cycle fusionné ;
3. Dispositif électroluminescent organique selon la revendication 1, dans lequel R<sub>1</sub> à R<sub>10</sub> sont chacun indépendamment sélectionnés parmi l'hydrogène ; l'halogène ; le méthyle ; l'éthyle ; le propyle ; le butyle ; le pentyle ; l'hexyle ; l'éthylhexyle ; l'heptyle ; l'octyle ; le phényle ; le naphthyle ; le fluorényle ; le biphenyle ; le phénanthryle ; le terphényle ; le pyrényle ; le pérylényle ; le spirobifluorényle, le fluoranthényle ; le chrysényle ; le triphénylényle ; le 1,2-dihydroacénaphthyle ; le dibenzothiophényle, le dibenzofuryle ; le carbozolye ; le pyridyle ; le furyle ; le thiényle ; le quinolye ; le triazinyle ; le pyrimidinyle ; le pyridazinyle ; le quinoxalinye ; le phénanthrolinyle ; le benzopyrolidino ; le banzopipéridino ; le dibenzomorpholino ; le dibenzoazépino ; l'amino substitué par le phényle, le naphthyle, le fluorényle, le biphenyle, le phénanthryle, le terphényle, le pyrényle, le pérylényle, le spirobifluorényle, le fluoranthé-


nyle, le chrysényle, le triphénylényle, le dibenzothiophényle, le dibenzofuryle, le carbozolye, le pyridyle, le furyle, le thiényle, le quinolye, le triazinyle, le pyrimidinyle, le pyridazinyle, le quinoxalinye ou le phénanthrolinye ; le biphényloxy ; le biphénylthio ; le biphénylméthyle ; le triphénylméthyle ; le carboxyle ; le nitro ou l'hydroxy.

4. Dispositif électroluminescent organique selon la revendication 1, dans lequel au moins un de  $R_1$  et de  $R_2$  est un substituant portant sept carbones ou davantage dans des chaînons cycliques, un substituant renfermant deux ou plusieurs cycles ou un alkyle en  $C_1$  à  $C_{30}$ .
5. Dispositif électroluminescent organique selon la revendication 1, dans lequel  $R_1$  et  $R_2$  sont différents l'un de l'autre.
6. Dispositif électroluminescent organique selon la revendication 1, dans lequel la formule chimique 1 est représentée par l'une des formules 2 à 9 :


[Formule chimique 2]




[Formule chimique 3]




[Formule chimique 4]




[Formule chimique 5]




[Formule chimique 6]




[Formule chimique 7]



[Formule chimique 8]



[Formule chimique 9]




où dans les formules chimiques 2 à 9,

$R_1$ ,  $R_2$ ,  $R_3$  et  $R_4$  sont identiques à ceux définis dans la revendication 1,

$p$  et  $q$  représentent chacun indépendamment un nombre entier valant de 1 à 4,

$Y_1$  à  $Y_4$  représentent l'un d'un cycloalkyle en  $C_3$  à  $C_{30}$  substitué ou non substitué, d'un hétéroaryle en  $C_3$  à  $C_{30}$  substitué ou non substitué, d'un hétérocycloalkyle de 5 à 7 chaînons substitué ou non substitué et d'un aryle en  $C_6$  à  $C_{30}$  substitué ou non substitué ou d'un cycle dans lequel deux ou plusieurs cycles sont fusionnés.

7. Dispositif électroluminescent organique selon la revendication 1, dans lequel la formule chimique 1 est sélectionnée parmi les formules structurales suivantes :



5

10

15

20

25

30


35

40


45

50


55




13




14




15




16




17




18




19




20




21




22




23




24




25




26




27




28




29




30




31




32




33




34




35




36




37




38




39



40




41




42


5




43




44




45



46




47




48


10




49




50




51



52




53




54

15


20




55




56




57



58




59




60

25


30




61




62




63



64




65




66

35


40




67




68




69



70



71









72

45







50

55







5









10



15









20









25

30









35

40




45


50




55



55




5




199




200




201



202




203




204


10




205




206




207



208




209




210


15




211




212




213



214




215




216

20


25




217




218




219



220




221




222

30


35




223




224




225



226




227




228

40


45




229




230




231



232




233




234

50


55




235




236




237



238




239




240

5




10




15

20




25

30




35

40







45



50


55






8. Dispositif électroluminescent organique selon la revendication 1, dans lequel la couche de matériau organique qui renferme le composé de la formule chimique 1 est une couche d'émission de lumière.
9. Dispositif électroluminescent organique selon la revendication 1, dans lequel la couche de matériau organique qui renferme le composé de la formule chimique 1 renferme en outre un dopant fluorescent ou un dopant phosphorescent.
10. Dispositif électroluminescent organique selon la revendication 1, dans lequel la couche de matériau organique qui renferme le composé de la formule chimique 1 renferme en outre un dopant fluorescent bleu.
11. Dispositif électroluminescent organique selon la revendication 1, dans lequel la couche de matériau organique qui renferme le composé de la formule chimique 1 renferme en outre un ou plusieurs composés sélectionnés dans le groupe constitué de composés à base d'arylamine et des composés à base de styrylarylamine, ou un ou plusieurs métaux ou composés complexes sélectionnés dans le groupe constitué de métaux de transition du groupe 1, du groupe 2, de la période 4 et de la période 5, de métaux de la série des lanthanides et des métaux organiques des atomes de transition d.
12. Dispositif électroluminescent organique selon la revendication 1, comprenant en outre :  
une ou plusieurs couches de matériau organique émettant de la lumière bleue, rouge ou verte, outre le composé de la formule chimique 1.
13. Dispositif électroluminescent organique selon la revendication 1, comprenant en outre :  
un ou plusieurs matériaux organiques émettant de la lumière bleue, rouge ou verte, outre la couche de matériau organique renfermant le composé de la formule chimique 1.
14. Dispositif électroluminescent organique selon la revendication 1, qui émet de la lumière blanche.


[Figure 1]



[Figure 2]



[Figure 3]



**REFERENCES CITED IN THE DESCRIPTION**

*This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.*

**Patent documents cited in the description**

- KR 20070101430 A [0007]
- KR 1020090037519 [0060]
- KR 1020080123276 [0061]
- KR 1020080107606 [0061]

|                |                                                                                                                                                                                                                                                                                                                                                                         |         |            |
|----------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------|------------|
| 专利名称(译)        | 多环芳族化合物和使用其的有机发光器件                                                                                                                                                                                                                                                                                                                                                      |         |            |
| 公开(公告)号        | <a href="#">EP2765832B1</a>                                                                                                                                                                                                                                                                                                                                             | 公开(公告)日 | 2018-04-04 |
| 申请号            | EP2013194341                                                                                                                                                                                                                                                                                                                                                            | 申请日     | 2013-11-26 |
| [标]申请(专利权)人(译) | 喜星素材股份有限公司                                                                                                                                                                                                                                                                                                                                                              |         |            |
| 申请(专利权)人(译)    | 喜星材料有限公司.                                                                                                                                                                                                                                                                                                                                                               |         |            |
| 当前申请(专利权)人(译)  | 喜星材料有限公司.                                                                                                                                                                                                                                                                                                                                                               |         |            |
| [标]发明人         | LEE DO HYUNG<br>KIM DONG JUN<br>NO YOUNG SEOK<br>CHUN HYUNDONG<br>LEE JOO DONG                                                                                                                                                                                                                                                                                          |         |            |
| 发明人            | LEE, DO-HYUNG<br>KIM, DONG-JUN<br>NO, YOUNG-SEOK<br>CHUN, HYUNDONG<br>LEE, JOO-DONG                                                                                                                                                                                                                                                                                     |         |            |
| IPC分类号         | H05B33/14 C09K11/06 C07F7/08 H01L51/00 C07C211/54 C07D263/57 C07D209/08 C07D277/66 C07D209/86 C07C13/62 C07C13/66                                                                                                                                                                                                                                                       |         |            |
| CPC分类号         | H01L51/0054 C07B2200/05 C07C13/62 C07C13/66 C07C211/54 C07C2602/08 C07C2603/18 C07C2603/20 C07C2603/24 C07C2603/26 C07C2603/28 C07C2603/40 C07C2603/50 C07C2603/54 C07D209/08 C07D209/86 C07D263/57 C07D277/66 C07F7/081 C09B1/00 C09B57/00 C09B57/001 C09B57/008 C09K11/06 C09K2211/1007 C09K2211/1011 C09K2211/1014 C09K2211/1029 C09K2211/1033 H01L51/0058 H05B33/14 |         |            |
| 优先权            | 1020120134761 2012-11-26 KR                                                                                                                                                                                                                                                                                                                                             |         |            |
| 其他公开文献         | EP2765832A1                                                                                                                                                                                                                                                                                                                                                             |         |            |
| 外部链接           | <a href="#">Espacenet</a>                                                                                                                                                                                                                                                                                                                                               |         |            |

摘要(译)

本说明书描述了具有新结构的多环芳族化合物和使用其的有机发光器件。

[Chemical Formula 1]

