



(11) **EP 3 144 996 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
22.03.2017 Bulletin 2017/12

(51) Int Cl.:
H01L 51/52 (2006.01)

(21) Application number: **16181621.0**

(22) Date of filing: **28.07.2016**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
MA MD

- **SONG, Ki-Woog**
10371 Goyang-si, Gyeonggi-do (KR)
- **AHN, SoYeon**
3714 Seoul (KR)
- **CHOI, Yongjoong**
8330 Seoul (KR)
- **LEE, Mingyu**
41458 Daegu (KR)

(30) Priority: **18.09.2015 KR 20150132531**

(74) Representative: **Viering, Jentschura & Partner mbB**
Patent- und Rechtsanwälte
Am Brauhaus 8
01099 Dresden (DE)


(71) Applicant: **LG Display Co., Ltd.**
Seoul 150-721 (KR)

(72) Inventors:
• **KUM, Taell**
10885 Paju-si, Gyeonggi-do (KR)

(54) **ORGANIC LIGHT EMITTING DISPLAY APPARATUS**

(57) Disclosed is an OLED apparatus (1000, 2000) that may include a reflection-anode (410, 1410), a transparent cathode (600, 1600), and a plurality of stacks (510, 520, 530, 1510, 1520) between the reflection-anode and the transparent cathode (600, 1600), wherein, among the plurality of stacks (510, 520, 530, 1510, 1520), a thickness of the stack (530, 1520) disposed relatively close to the transparent cathode (600, 1600) is larger than a thickness of the stack (510, 1510) disposed relatively close to the reflection-anode (410, 1410) so that it is possible to optimize a micro-cavity of light emitted from the plurality of stacks (510, 520, 530, 1510, 1520), thereby improving a light-emission efficiency and a color reproduction ratio and reducing a color change rate in accordance with a viewing angle.

FIG. 2



EP 3 144 996 A1

Description

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of the Korean Patent Application No. 10-2015-0132531, filed on September 18, 2015, which is hereby incorporated by reference as if fully set forth herein.

BACKGROUND

Field of the Disclosure

[0002] Embodiments of the present disclosure relate to an organic light emitting display apparatus (OLED apparatus), and more particularly, to a top emission type organic light emitting display apparatus (OLED apparatus) which is capable of realizing high emission efficiency, good color reproduction ratio, and improved color change rate by optimizing a thickness ratio in a plurality of stacks between two electrodes.

Discussion of the Related Art

[0003] An organic light emitting display apparatus (OLED apparatus) is a next generation display apparatus having self-luminance properties. In more detail, the OLED apparatus is a display apparatus of displaying an image by producing exciton through a recombination of hole and electron, which are injected from anode and cathode, in a light emitting layer, and generating light with a specific wavelength by an energy emission of the produced exciton.

[0004] Unlike a liquid crystal display apparatus (LCD apparatus), the OLED apparatus does not require an additional light source. Thus, the OLED apparatus has light weight and thin profile. In comparison to the LCD apparatus, the OLED apparatus has various advantages of wide viewing angle, good contrast ratio, rapid response time and low power consumption, whereby the OLED apparatus has attracted great attentions as the next generation display apparatus.

SUMMARY

[0005] According to a design, an OLED apparatus may have a patterned emission layer structure or a common emission layer structure.

[0006] In case of the OLED apparatus having the patterned emission layer structure, emission layers for emitting different colored light, for example, red, blue, and green emission layers are disposed between two electrodes, and are separately provided every pixel, wherein different monochromatic light is emitted from each pixel. The separated emission layers may be patterned and deposited by the use of a fine patterning mask whose opening is provided every pixel, for example, fine metal mask (FMM).

[0007] In case of the OLED apparatus having the common emission layer structure, a plurality of stacks for emitting white light are provided between two electrodes. Also, the plurality of stacks are connected or extended from one pixel to the neighboring pixel without disconnection, whereby the plurality of pixels are shared and white light is emitted from all pixels.

[0008] The OLED apparatus having the common emission layer structure may be formed by the use of common mask with open areas corresponding to all pixels, whereby all pixels may be formed in the same structure. Thus, in case of the OLED apparatus having the common emission layer structure, it is more appropriate for a large-sized product, in comparison to the OLED apparatus having the patterned emission layer structure. Also, the OLED apparatus having the common emission layer structure enables a simplified process, to thereby improve the yield.

[0009] In the OLED apparatus having the common emission layer structure, each of the plurality of stacks includes at least one emission layer. In this case, light emitted from each emission layer of each stack is mixed together, and white light is emitted through any one of the two electrodes. At this time, a micro-cavity of the light emitted from the emission layer disposed between the two electrodes may be optimized by a position or thickness of each of the plurality of stacks disposed between the two electrodes. Herein, the micro-cavity indicates that light-emission efficiency is improved by amplification and constructive interference of the light with a specific wavelength through repetitive reflection and re-reflection of the light emitted from the emission layer between the two electrodes.

[0010] Meanwhile, according to a direction of light, the OLED apparatus may be generally classified into a top emission type and a bottom emission type. In case of the bottom emission type, light emitted from the emission layer passes through the anode of the two electrodes, that is, light is emitted through a lower substrate with a thin film transistor. In case of the top emission type, light emitted from the emission layer passes through the cathode of the two electrodes, that is, light is emitted in an opposite direction to the lower substrate with the thin film transistor.

[0011] A structure of the two electrodes, that is, the anode and cathode in the OLED apparatus may be changed in accordance with the direction of light. In case of the top emission type OLED apparatus, light emitted from the emission layer is emitted to an upper direction through the cathode, whereby the anode has a structure with the reflection properties so as to prevent a light leakage in a lower direction, and the cathode has a structure with the transparent properties for a smooth light transmission. Meanwhile, in case of the bottom emission type OLED apparatus, light emitted from the emission layer is emitted to a lower direction through the anode, whereby the anode has a structure with the transparent properties for a smooth light transmission, and the cathode has a

structure with the reflection properties so as to prevent a light leakage in an upper direction.

[0012] The aforementioned micro-cavity, which might occur between the two electrodes, may be influenced by the structure of each of the two electrodes as well as the position or thickness of each of the plurality of stacks disposed between the two electrodes. That is, the position of electrode with the reflection properties is changed in accordance with the light emission type of the OLED apparatus. Thus, in order to optimize the micro-cavity between the two electrodes, the position or thickness of each of the plurality of stacks disposed between the two electrodes has to be changed in accordance with the position of electrode with the reflection properties.

[0013] Inventors of the present disclosure propose a top emission type OLED apparatus which is capable of realizing improved emission efficiency and color reproduction ratio, and reducing a color change rate by optimizing a thickness of each of a plurality of stacks disposed between two electrodes through various experiments.

[0014] To achieve these and other advantages and in accordance with the purpose of embodiments of the disclosure, as embodied and broadly described herein, there is provided a top emission type OLED apparatus which is capable of realizing improved emission efficiency and color reproduction ratio, and reducing a color change rate by optimizing a thickness in each of the plurality of stacks disposed between the two electrodes, or a thickness ratio in the plurality of stacks disposed between the two electrodes.

[0015] It is to be understood that both the foregoing general description and the following detailed description of embodiments of the present disclosure are exemplary and explanatory and are intended to provide further explanation of the disclosure as claimed.

[0016] According to one embodiment of the present disclosure, an OLED apparatus may comprise a reflection-anode; a transparent cathode; and a plurality of stacks disposed between the reflection-anode and the transparent cathode, wherein, among the plurality of stacks, a thickness of the stack disposed relatively close to the transparent cathode is larger than a thickness of the stack disposed relatively close to the reflection-anode. Accordingly, it is possible to optimize a micro-cavity of light emitted from the plurality of stacks, thereby improving light-emission efficiency and a color reproduction ratio and reducing a color change rate in accordance with a viewing angle.

[0017] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, the plurality of stacks include a first stack disposed on the reflection-anode; a first charge generation layer disposed on the first stack, wherein the first charge generation layer includes a first N-type charge generation layer, and a first P-type charge generation layer; a second stack disposed on the first charge generation layer; a second charge generation layer disposed on the second

stack, wherein the second charge generation layer includes a second N-type charge generation layer, and a second P-type charge generation layer; and a third stack disposed on the second charge generation layer, wherein, when 'T1' indicates a distance from an upper surface of the reflection-anode to the interface between the first N-type charge generation layer and the first P-type charge generation layer, 'T2' indicates a distance from the interface between the first N-type charge generation layer and the first P-type charge generation layer to the interface between the second N-type charge generation layer and the second P-type charge generation layer, and 'T3' indicates a distance from the interface between the second N-type charge generation layer and the second P-type charge generation layer to an upper surface of the transparent cathode, the above 'T1', 'T2', and 'T3' satisfy the following Equation 1,

[Equation 1]

$$T3 > T2 > T1$$

[0018] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, assuming that the total thickness of T1, T2, and T3 is 100%, T1 is within a range from 10% to 20%, T2 is within a range from 30% to 40%, and T3 is within a range from 45% to 60%.

[0019] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, each of the first stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the second stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0020] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, each of the second stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the first stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0021] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, light is emitted from the plurality of stacks, and is emitted through the transparent cathode, wherein a thickness ratio in the plurality of stacks is adjusted so as to obtain a color reproduction ratio of 99% or more than 99% and simultaneously to obtain $\Delta u'v'$ value of 0.05 or less than 0.05 within a range of a viewing angle from 0° to 60°.

[0022] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, the plurality of stacks include: a first stack; and a second stack between the first stack and the transparent cathode, wherein a thickness of the second stack is larger than a thickness of the first stack.

[0023] In an implementation of the OLED apparatus

according to one embodiment of the present disclosure, the plurality of stacks further include an N-type charge generation layer and a P-type charge generation layer between the first stack and the second stack, a thickness of the first stack is a distance from an upper surface of the reflection-anode to an interface between the N-type charge generation layer and the P-type charge generation layer, and a thickness of the second stack is a distance from the interface between the N-type charge generation layer and the P-type charge generation layer to an upper surface of the transparent cathode.

[0024] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, assuming that the total thickness of the first stack and the second stack is 100%, the thickness of the first stack is within a range from 15% to 35%, and the thickness of the second stack is within a range from 65% to 85%.

[0025] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, the first stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the second stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0026] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, the plurality of stacks include: a first stack closest to the reflection-anode; a third stack closest to the transparent cathode; and a second stack between the first stack and the third stack, wherein a thickness of the third stack is larger than a thickness of the first stack and a thickness of the second stack, and the thickness of the second stack is larger than the thickness of the first stack.

[0027] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, the plurality of stacks further include: a first charge generation layer between the first stack and the second stack, the first charge generation layer having a first N-type charge generation layer and a first P-type charge generation layer; and a second charge generation layer between the second stack and the third stack, the second charge generation layer having a second N-type charge generation layer and a second P-type charge generation layer, wherein a thickness of the first stack corresponds to a distance from an upper surface of the reflection-anode to an interface between the first N-type charge generation layer and the first P-type charge generation layer, a thickness of the second stack corresponds to a distance from the interface between the first N-type charge generation layer and the first P-type charge generation layer to an interface between the second N-type charge generation layer and the second P-type charge generation layer, and a thickness of the third stack corresponds to a distance from the interface between the second N-type charge generation layer and the second P-type charge generation layer to an upper surface of the transparent cathode.

[0028] In an implementation of the OLED apparatus according to one embodiment of the present disclosure,

assuming that the total thickness of the thickness of the first stack, the thickness of the second stack, and the thickness of the third stack is 100%, the thickness of the first stack is within a range from 10% to 20%, the thickness of the second stack is within a range from 30% to 40%, and the thickness of the third stack is within a range from 45% to 60%.

[0029] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, each of the first stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the second stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0030] In an implementation of the OLED apparatus according to one embodiment of the present disclosure, each of the second stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the first stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0031] According to another embodiment of the present disclosure, an OLED apparatus may comprise a reflection-anode, a transparent cathode, and a plurality of stacks disposed between the reflection-anode and the transparent cathode, wherein light is emitted from the plurality of stacks, and is emitted through the transparent cathode, wherein a thickness ratio in the plurality of stacks is adjusted so as to obtain a color reproduction ratio of 99% or more than 99% and simultaneously to obtain $\Delta u'v'$ value of 0.05 or less than 0.05 within a range of a viewing angle from 0° to 60°. Accordingly, it is possible to improve light-emission efficiency and a color reproduction ratio, and to reduce a color change ratio in accordance with a viewing angle.

[0032] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, the plurality of stacks include a first stack; and a second stack disposed between the first stack and the transparent cathode, wherein a thickness of the second stack is larger than a thickness of the first stack.

[0033] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, the plurality of stacks further include an N-type charge generation layer and a P-type charge generation layer between the first stack and the second stack, a thickness of the first stack is a distance from an upper surface of the reflection-anode to the interface between the N-type charge generation layer and the P-type charge generation layer, and a thickness of the second stack is a distance from the interface between the N-type charge generation layer and the P-type charge generation layer to an upper surface of the transparent cathode.

[0034] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, assuming that the total thickness of the first stack and the second stack is 100%, the thickness of the first stack is within a range from 15% to 35%, and the thick-

ness of the second stack is within a range from 65% to 85%.

[0035] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, the first stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the second stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0036] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, the plurality of stacks include a first stack disposed closest to the reflection-anode; a third stack disposed closest to the transparent cathode; and a second stack disposed between the first stack and the third stack, wherein a thickness of the third stack is larger than a thickness of the first stack and a thickness of the second stack, and the thickness of the second stack is larger than the thickness of the first stack.

[0037] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, the plurality of stacks further include a first charge generation layer disposed between the first stack and the second stack, wherein the first charge generation layer includes a first N-type charge generation layer and a first P-type charge generation layer; and a second charge generation layer disposed between the second stack and the third stack, wherein the second charge generation layer includes a second N-type charge generation layer and a second P-type charge generation layer, wherein a thickness of the first stack corresponds to a distance from an upper surface of the reflection-anode to the interface between the first N-type charge generation layer and the first P-type charge generation layer, a thickness of the second stack corresponds to a distance from the interface between the first N-type charge generation layer and the first P-type charge generation layer to the interface between the second N-type charge generation layer and the second P-type charge generation layer, and a thickness of the third stack corresponds to a distance from the interface between the second N-type charge generation layer and the second P-type charge generation layer to an upper surface of the transparent cathode.

[0038] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, assuming that the total thickness of the thickness of the first stack, the thickness of the second stack, and the thickness of the third stack is 100%, the thickness of the first stack is within a range from 10% to 20%, the thickness of the second stack is within a range from 30% to 40%, and the thickness of the third stack is within a range from 45% to 60%.

[0039] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, each of the first stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the second stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

[0040] In an implementation of the OLED apparatus according to another embodiment of the present disclosure, each of the second stack and the third stack includes at least one organic layer having light-emitting dopant for emitting blue light, and the first stack includes at least one organic layer having light-emitting dopant for emitting yellow-green light.

BRIEF DESCRIPTION OF THE DRAWINGS

[0041] The accompanying drawings, which are included to provide a further understanding of embodiments of the disclosure and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the disclosure and together with the description serve to explain the principle of embodiments of the disclosure. In the drawings:

FIG. 1 is a cross sectional view illustrating an OLED apparatus according to the first embodiment of the present disclosure;

FIG. 2 is a cross sectional view illustrating main components of the OLED apparatus according to the first embodiment of the present disclosure;

FIG. 3 is a table showing a light-emission efficiency in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples;

FIG. 4A is a graph showing a color change rate in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples;

FIG. 4B is a graph showing a color reproduction ratio in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples;

FIG. 5 is a cross sectional view illustrating main components of an OLED apparatus according to the second embodiment of the present disclosure;

FIG. 6 is a table showing a light-emission efficiency in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples;

FIG. 7A is a graph showing a color change rate in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples; and

FIG. 7B is a graph showing a color reproduction ratio in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0042] Reference will now be made in detail to the exemplary embodiments of the present disclosure, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers

will be used throughout the drawings to refer to the same or like parts. Advantages and features of the present disclosure, and implementation methods thereof will be clarified through following embodiments described with reference to the accompanying drawings. The present disclosure may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the present disclosure to those skilled in the art. Further, the present disclosure is only defined by scopes of claims.

[0043] A shape, a size, a ratio, an angle, and a number disclosed in the drawings for describing embodiments of the present disclosure are merely an example, and thus, the present disclosure is not limited to the illustrated details. Like reference numerals refer to like elements throughout. In the following description, when the detailed description of the relevant known function or configuration is determined to unnecessarily obscure the important point of the present disclosure, the detailed description will be omitted.

[0044] In a case where 'comprise', 'have', and 'include' described in the present specification are used, another part may be added unless 'only~' is used. The terms of a single form may include plural forms unless referred to the contrary.

[0045] In construing an element, the element is construed as including an error range although there is no explicit description.

[0046] In description of embodiments of the present disclosure, when a structure (for example, an electrode, a line, a wiring, a layer, or a contact) is described as being formed at an upper portion/lower portion of another structure or on/under the other structure, this description should be construed as including a case where the structures contact each other and moreover, a case where a third structure is disposed therebetween.

[0047] In describing a time relationship, for example, when the temporal order is described as 'after~', 'subsequent~', 'next~', and 'before~', a case which is not continuous may be included unless 'just' or 'direct' is used.

[0048] It will be understood that, although the terms "first", "second", etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another. For example, a first element could be termed a second element, and, similarly, a second element could be termed a first element, without departing from the scope of the present disclosure.

[0049] For convenience of explanation, a size and thickness of each element may show as exemplary in the drawings, but not limited to the shown size and thickness.

[0050] Features of various embodiments of the present disclosure may be partially or overall coupled to or combined with each other, and may be variously inter-operated with each other and driven technically as those

skilled in the art can sufficiently understand. The embodiments of the present disclosure may be carried out independently from each other, or may be carried out together in co-dependent relationship.

5 **[0051]** Hereinafter, an organic light emitting display apparatus (OLED apparatus) according to embodiments of the present disclosure will be described in detail with reference to the accompanying drawings.

10 **[0052]** FIG. 1 is a cross sectional view illustrating an OLED apparatus 1000 according to one embodiment of the present disclosure.

[0053] Referring to FIG. 1, the OLED apparatus 1000 may include a substrate 100, a thin film transistor 300, and a light-emitting device (ED).

15 **[0054]** The OLED apparatus 1000 may include a plurality of pixels (P). The pixel (P) indicates a minimum unit for emitting light, which is referred to as a sub-pixel or a pixel region. Also, the plurality of pixels (P) may constitute one group for expressing white light. For example, three
20 pixels including a red pixel, a green pixel, and a blue pixel may constitute one group, or four pixels including a red pixel, a green pixel, a blue pixel, and a white pixel may constitute one group. However, it is not limited to this structure, that is, various pixel designs are possible. For
25 convenience of explanation, FIG. 1 shows only one pixel (P).

[0055] The thin film transistor 300 is disposed on the substrate 100, and the thin film transistor 300 supplies various signals to the light-emitting device (ED). The thin
30 film transistor 300 shown in FIG. 1 may be a driving thin film transistor connected with an anode 400 of the light-emitting device (ED). Although not shown in the drawings, a switching thin film transistor or a capacitor for driving the light-emitting device (ED) may be additionally
35 disposed on the substrate 100.

[0056] The substrate 100 is formed of an insulating material. For example, the substrate 100 may be formed of a glass, or a flexible film of a polyimide-based material.

40 **[0057]** The thin film transistor 300 may include a gate electrode 310, an active layer 320, a source electrode 330, and a drain electrode 340. Referring to FIG. 1, the gate electrode 310 is disposed on the substrate 100, and a gate insulating layer 210 covers the gate electrode 310. Also, the active layer 320 is disposed on the gate insulating layer 210, and is overlapped with the gate electrode 310. The source electrode 330 and the drain electrode 340 are disposed on the active layer 320, and the source
45 electrode 330 and the drain electrode 340 are spaced apart from each other.

50 **[0058]** In description of embodiments of the present disclosure, if two elements are overlapped with each other, the two elements may be at least partially overlapped with each other regardless of another element interposed in-between, and they may be referred to as various
55 names.

[0059] The gate electrode 310, the source electrode 330, and the drain electrode 340 are formed of a conductive material, for example, molybdenum (Mo), alumi-

num (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), copper (Cu), and their alloys, but is not limited to these materials.

[0060] The active layer 320 may be formed of any one among amorphous silicon (a-Si), polycrystalline silicon (poly-Si), oxide, and organic materials, but is not limited to these materials.

[0061] The gate insulating layer 210 may be formed in a single layered structure or multi-layered structure of inorganic material, for example, silicon oxide (SiO_x), silicon nitride (SiN_x), and etc.

[0062] FIG. 1 shows the thin film transistor 300 having a staggered structure, but is not limited to this structure. The thin film transistor 300 may have a coplanar structure instead of the staggered structure.

[0063] Then, a planarization layer 220 for exposing a predetermined portion of the source electrode 330 is disposed on the thin film transistor 300. The planarization layer 220 may have a single layered structure or multi-layered structure, and the planarization layer 220 may be formed of an organic material. For example, the planarization layer 220 may be formed of polyimide, acryl, and etc.

[0064] A passivation layer may be additionally provided between the planarization layer 220 and the thin film transistor 300. The passivation layer is formed of an inorganic material. The passivation layer protects the thin film transistor 300. Like the planarization layer 220, the passivation layer may expose a predetermined portion of the source electrode 330.

[0065] The light-emitting device (ED) is disposed on the planarization layer 220, and the light-emitting device (ED) includes an anode 400, a light-emitting unit 500, and a cathode 600. The anode 400 of the light-emitting device (ED) is connected with the source electrode 330 of the thin film transistor 300, and various signals are supplied to the anode 400 of the light-emitting device (ED) through the thin film transistor 300. The anode 400 may be connected with the drain electrode 340 of the thin film transistor 300 according to the kind of the thin film transistor 300. According to the kind of the thin film transistor 300.

[0066] The OLED apparatus 1000 of FIG. 1 is a top emission type, wherein light (L) emitted from the light-emitting unit 500 may emit to an upper direction through the cathode 600. In case of the OLED apparatus 1000 of the top emission type, the light (L) emitted from the light-emitting unit 500 does not emit to a lower direction (or a direction passing through the substrate 100), so that it is possible to provide the thin film transistor 300 disposed between the light-emitting device (ED) and the substrate 100, and overlapped with the light-emitting device (ED). Accordingly, an aperture ratio of the top emission type OLED apparatus 1000 may be more improved in comparison to an aperture ratio of a bottom emission type OLED apparatus so that it facilitates a high resolution in the OLED apparatus 1000.

[0067] A bank 230 is provided to divide the pixel (P),

and the bank 230 covers an end of the anode 400. Referring to FIG. 1, the bank 230 exposes a predetermined portion of an upper surface of the anode 400. The bank 230 may be formed of an organic material, for example, any one among polyimide and photoacryl, but is not limited to these materials.

[0068] If white light (L) is emitted from the light-emitting unit 500 of the OLED apparatus 1000, the white light (L) emitted from the light-emitting unit 500 passes through a color filter disposed by each pixel (P), and it realizes a corresponding pixel (P). For example, if the white light (L) emitted from the light-emitting unit 500 passes through a red color filter, it realizes a red pixel. If the white light (L) emitted from the light-emitting unit 500 passes through a blue color filter, it realizes a blue pixel. If the white light (L) emitted from the light-emitting unit 500 passes through a green filter, it realizes a green pixel.

[0069] FIG. 2 is a cross sectional view illustrating main components of the OLED apparatus 1000 according to one embodiment of the present disclosure, which is a cross sectional view for explaining a stack structure of the plurality of light-emitting devices (ED) of the OLED apparatus 1000 shown in FIG. 1.

[0070] Referring to FIG. 2, each of the plurality of light-emitting devices (ED) included in the OLED apparatus 1000 includes the anode 400, the cathode 600, and the light-emitting unit 500 disposed between the anode 400 and the cathode 600. The light-emitting unit 500 indicates all layers disposed between the anode 400 and the cathode 600, or a stack structure of all layers disposed between the anode 400 and the cathode 600.

[0071] The light-emitting unit 500 of the OLED apparatus 1000 according to the first embodiment of the present disclosure includes a plurality of stacks, and a plurality of charge generation layers 540 and 550. In detail, as shown in FIG. 2, the light-emitting unit 500 may be formed in a sequential stack structure of a first stack 510 including a first emission layer 510E, a first charge generation layer 540 including a first N-type charge generation layer 540N and a first P-type charge generation layer 540P, a second stack 520 including a second emission layer 520E, a second charge generation layer 550 including a second N-type charge generation layer 550N and a second P-type charge generation layer 550P, and a third stack 530 including a third emission layer 530E.

[0072] The light-emitting unit 500 of the OLED apparatus 1000 according to one embodiment of the present disclosure shown in FIG. 2 has a common emission layer structure, wherein the light-emitting unit 500 emits the white light (L). The light-emitting unit 500 with the common emission layer structure may be formed by the use of common mask with open areas corresponding to all pixels (P). The light-emitting unit 500 may be deposited in the same structure for all pixels (P) without an individual pattern every pixel (P). That is, the light-emitting unit 500 is connected or disposed without disconnection from one pixel (P) to the neighboring pixel (P) so that the light-emitting unit 500 is shared by the plurality of pixels (P).

Also, the respective light emitted from the plurality of stacks 510, 520, and 530 of the light-emitting unit 500 may be mixed together, whereby the white light (L) may be emitted through the cathode 600.

[0073] The anode 400 is separately disposed by each pixel (P). The anode 400 is an electrode for supplying or transmitting a hole to the light-emitting unit 500, and the anode 400 is connected with the source or drain electrode of the thin film transistor.

[0074] The anode 400 is configured to have a structure with the reflection properties for smoothly reflecting the light (L) emitted from the light-emitting unit 500 to an upper direction (or a direction passing through the cathode 600).

[0075] For example, as shown in FIG. 2, the anode 400 may be formed in a dual-layered structure of a reflection layer 410 and a transparent layer 420. The transparent layer 420 supplies or transmits the hole to the light-emitting unit 500, and the reflection layer 410 reflects the light (L) emitted from the light-emitting unit 500, wherein the reflection layer 410 is disposed under the transparent layer 420. In this case, the reflection layer 410 may be referred to as a reflection-anode. The transparent layer 420 may be formed of TCO (transparent conductive oxide) material such as ITO (indium tin oxide) or IZO (indium zinc oxide), and the reflection layer 410 may be formed of a metal material such as copper (Cu), silver (Ag), and palladium (Pd).

[0076] The anode 400 may be formed of a single layered structure or three-layered structure of a material or structure having the properties for supplying or transmitting the hole to the light-emitting unit 500 and reflecting the light (L) emitted from the light-emitting unit 500. For example, the anode 400 may be formed in a three-layered structure including a transparent layer, a reflection layer, and another transparent layer deposited in sequence. In this case, the reflection layer disposed between the two transparent layers may be referred to as a reflection-anode. Also, if the anode 400 is formed of the single layered structure having the reflection properties, the single anode 400 may be referred to as a reflection-anode.

[0077] The cathode 600 is disposed on the light-emitting unit 500, wherein the cathode 600 is an electrode for supplying or transmitting an electron to the light-emitting unit 500. The cathode 600 may have the transparent properties to pass the light (L) emitted from the light-emitting unit 500 therethrough, and the cathode 600 may be formed in a single-layered structure or a multi-layered structure. The cathode 600 may be referred to as a transparent cathode. The cathode 600 may be formed of a metal material layer having a small thickness, for example, silver (Ag), magnesium (Mg), silver-magnesium (Ag-Mg), and etc. Also, the cathode 600 may be formed of TCO (transparent conductive oxide) material such as ITO (indium tin oxide) or IZO (indium zinc oxide).

[0078] The light-emitting unit 500 disposed between the anode 400 and the cathode 600 includes the plurality

of stacks 510, 520, and 530, and the first and second charge generation layers 540 and 550 disposed each of the stacks.

[0079] The first stack 510 is disposed on the anode 400. Among the plurality of stacks 510, 520, and 530, the first stack 510 is relatively close to the anode 400.

[0080] The first stack 510 may include at least one organic layer having light-emitting dopant for emitting blue light or yellow-green light. For example, as shown in FIG. 2, the first stack 510 may include the first emission layer 510E having light-emitting dopant for emitting blue light or yellow-green light.

[0081] The first emission layer 510E may be formed in a single-layered or multi-layered structure including the light-emitting dopant for emitting blue light or yellow-green light. In detail, the first emission layer 510E may include at least one host and at least one light-emitting dopant for emitting blue light or yellow-green light. The first emission layer 510E may include a mixed host having two hosts mixed together, and at least one light-emitting dopant for emitting blue light or yellow-green light. The mixed host may include a host having hole transporting properties, and a host having an electron transporting properties.

[0082] For example, the light-emitting dopant for emitting blue light may be formed of a pyrene-based compound replaced by an arylamine-based compound, but is not limited to this material.

[0083] For example, the light-emitting dopant for emitting yellow-green light may be formed of an iridium-based compound, but is not limited to this material.

[0084] The first stack 510 may further include at least one among a hole injecting layer (HIL), a hole transporting layer (HTL), an electron transporting layer (ETL), an electron injecting layer (EIL), a hole blocking layer (HBL), an electron blocking layer (EBL), and an auxiliary emission layer.

[0085] The hole injecting layer (HIL) enables a smooth injection of the hole from the anode 400. For example, the hole injecting layer (HIL) may be formed of MTDA- $TA(4,4',4''\text{-tris(3-methylphenylphenylamino)triphenylamine})$, CuPc(copper phthalocyanine), PE-DOT/PSS(poly(3,4-ethylenedioxythiophene, polystyrene sulfonate), and etc., but is not limited to these materials.

[0086] The hole transporting layer (HTL) enables a smooth transfer of the hole, which is supplied or transmitted from the anode 400, to the first emission layer 510E. For example, the hole transporting layer (HTL) may be formed of NPD(N,N'-bis(naphthalene-1-yl)-N,N'-bis(phenyl)-2,2'-dimethylbenzidine), TPD(N,N'-bis-(3-methylphenyl)-N,N'-bis(phenyl)-benzidine), Spiro-TAD(2,2',7,7'-tetrakis(N,N-diphenylamino)-9,9'-spirofluorene), and etc., but is not limited to these materials.

[0087] The electron transporting layer (ETL) enables a smooth transfer of the electron, which is supplied or transmitted from the first charge generation layer 540 or the cathode 600, to the first emission layer 510E. For example, the electron transporting layer (ETL) may be

formed of PBD(2-(4-biphenyl)-5-(4-tert-butylphenyl)-1,3,4-oxadiazole), TAZ(3-(4-biphenyl)-4-phenyl-5-tert-butylphenyl-1,2,4-triazole), Liq(8-hydroxyquinolinolato-lithium), BAlq(Bis(2-methyl-8-quinolinolate)-4-(phenyl-phenolato)aluminum), TPBi(2,2',2''-(1,3,5-benzinetiyl)-tris(1-phenyl-1-H-benzimidazole), and etc., but is not limited to these materials.

[0088] The electron injecting layer (EIL) enables a smooth injection of the electron from the first charge generation layer 540 or the cathode 600.

[0089] The hole blocking layer (HBL) prevents the hole injected into the first emission layer 510E from being diffused and getting out of the first emission layer 510E. The electron transporting layer (ETL) and the hole blocking layer (HBL) may be formed as one layer.

[0090] The electron blocking layer (EBL) prevents the electron injected into the first emission layer 510E from being diffused and getting out of the first emission layer 510E. The hole transporting layer (HTL) and the electron blocking layer (EBL) may be formed as one layer.

[0091] The auxiliary emission layer of the first stack 510 may include light-emitting dopant for emitting light whose color is different from that of the light emitted from the first emission layer 510E.

[0092] For example, if the first emission layer 510E of the first stack 510 includes light-emitting dopant for emitting blue light, the auxiliary emission layer of the first stack 510 may include light-emitting dopant for emitting yellow-green light or red light. If the first emission layer 510E of the first stack 510 includes light-emitting dopant for emitting yellow-green light, the auxiliary emission layer of the first stack 510 may include light-emitting dopant for emitting green light or red light. According as the auxiliary emission layer is additionally provided in the first stack 510, it is possible to improve light-emission efficiency of red or green color.

[0093] If the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting blue light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 440nm to 480nm.

[0094] If the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 440nm to 650nm. And, if the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting yellow-green light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 440nm to 590nm.

[0095] If the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting yellow-green light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 540nm to 580nm

[0096] If the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 540nm to 650nm. And, if the first stack 510 includes the first emission layer 510E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting green light, a peak wavelength of the light emitted from the first stack 510 may be within a range from 510nm to 590nm.

[0097] As described above, the first stack 510 further includes at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer, so that it is possible to improve light-emission efficiency or driving voltage properties of the OLED apparatus 1000. According to a design of the OLED apparatus 1000, the additional organic layers may be selectively disposed in the first stack 510. Also, a thickness (T1) of the first stack 510 and a position of the first emission layer 510E in the first stack 510 may be adjusted based on the position, the thickness, or the number of the additional organic layers included in the first stack 510.

[0098] The first charge generation layer 540 is disposed on the first stack 510, or disposed between the first stack 510 and the second stack 520, to thereby adjust a charge balance between the first stack 510 and the second stack 520. The first charge generation layer 540 includes the first N-type charge generation layer 540N and the first P-type charge generation layer 540P.

[0099] The first N-type charge generation layer 540N is provided to inject the electron into the first stack 510. The first N-type charge generation layer 540N may be formed of a layer doped with alkali-based metal such as lithium (Li), sodium (Na), potassium (K) or cesium (Cs), or a layer doped with alkali earth metal such as magnesium (Mg), strontium (Sr), barium (Ba) or radium (Ra), but is not limited to these materials.

[0100] The first P-type charge generation layer 540P is provided to inject the hole into the second stack 520. For example, the first P-type charge generation layer 540P may be formed of a layer including P-type dopant, but is not limited to this material.

[0101] The second stack 520 is disposed on the first charge generation layer 540.

[0102] The second stack 520 may include at least one organic layer having the light-emitting dopant for emitting yellow-green light or blue light. For example, as shown in FIG. 2, the second stack 520 may include the second emission layer 520E having the light-emitting dopant for emitting yellow-green light or blue light.

[0103] The second emission layer 520E may be formed in a single-layered structure or multi-layered structure having the light-emitting dopant for emitting yellow-green light or blue light.

low-green light or blue light. In detail, if the first emission layer 510E of the first stack 510 includes the light-emitting dopant for emitting blue light, the second emission layer 520E of the second stack 520 may include the light-emitting dopant for emitting yellow-green light. If the first emission layer 510E of the first stack 510 includes the light-emitting dopant for emitting yellow-green light, the second emission layer 520E of the second stack 520 may include the light-emitting dopant for emitting blue light.

[0104] The second emission layer 520E may include at least one host and at least one light-emitting dopant for emitting yellow-green light or blue light, or may include a mixed host including two hosts mixed together and at least one light-emitting dopant for emitting yellow-green light or blue light.

[0105] In the same manner as the first stack 510, the second stack 520 may include at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer.

[0106] The auxiliary emission layer of the second stack 520 may include light-emitting dopant for emitting light whose color is different from that of the light emitted from the second emission layer 520E. If the second emission layer 520E of the second stack 520 includes light-emitting dopant for emitting yellow-green light, the auxiliary emission layer of the second stack 520 may include light-emitting dopant for emitting green light or red light. If the second emission layer 520E of the second stack 520 includes light-emitting dopant for emitting blue light, the auxiliary emission layer of the second stack 520 may include light-emitting dopant for emitting yellow-green light or red light. According as the auxiliary emission layer is additionally provided in the second stack 520, it is possible to improve light-emission efficiency of red or green color.

[0107] If the second stack 520 includes the second emission layer 520E having the light-emitting dopant for emitting yellow-green light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 540nm to 580nm.

[0108] If the second stack 520 includes the second emission layer 520E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 540nm to 650nm. And, if the second stack 520 includes the second emission layer 520E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting green light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 510nm to 590nm.

[0109] If the second stack 520 includes the second emission layer 520E having the light-emitting dopant for

emitting blue light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 440nm to 480nm.

[0110] If the second stack 520 includes the second emission layer 520E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 440nm to 650nm. And, if the second stack 520 includes the second emission layer 520E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting green light, a peak wavelength of the light emitted from the second stack 520 may be within a range from 440nm to 580nm.

[0111] As described above, the second stack 520 further includes at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer, it is possible to improve light-emission efficiency or driving voltage properties of the OLED apparatus 1000. According to a design of the OLED apparatus 1000, the additional organic layers may be selectively disposed in the second stack 520. Also, a thickness (T2) of the second stack 520 and a position of the second emission layer 520E in the second stack 520 may be adjusted based on the position, the thickness, or the number of the additional organic layers included in the second stack 520.

[0112] The second charge generation layer 550 is disposed on the second stack 520, or disposed between the second stack 520 and the third stack 530, to thereby adjust a charge balance between the second stack 520 and the third stack 530. The second charge generation layer 550 includes the second N-type charge generation layer 550N and the second P-type charge generation layer 550P.

[0113] The second N-type charge generation layer 550N is provided to inject the electron into the second stack 520. The second N-type charge generation layer 550N may be formed of a layer doped with alkali-based metal such as lithium (Li), sodium (Na), potassium (K) or cesium (Cs), or a layer doped with alkali earth metal such as magnesium (Mg), strontium (Sr), barium (Ba) or radium (Ra), but not limited to these materials. According to a design, the second N-type charge generation layer 550N may be formed of the same material as that of the first N-type charge generation layer 540N.

[0114] The second P-type charge generation layer 550P is provided to inject the hole into the third stack 530. For example, the second P-type charge generation layer 550P may be formed of a layer including P-type dopant, but not limited to this material. According to a design, the second P-type charge generation layer 550P may be formed of the same material as that of the first P-type charge generation layer 540P.

[0115] The third stack 530 is disposed on the second

charge generation layer 550. Among the plurality of stacks 510, 520 and 530, the third stack 530 is relatively close to the cathode 600.

[0116] The third stack 530 may include at least one organic layer having the light-emitting dopant for emitting blue light. For example, as shown in FIG. 2, the third stack 530 may include the third emission layer 530E having the light-emitting dopant for emitting blue light.

[0117] The third emission layer 530E may be formed in a single-layered structure or multi-layered structure having the light-emitting dopant for emitting blue light. In detail, the third emission layer 530E may include at least one host and at least one light-emitting dopant for emitting blue light, or the third emission layer 530E may include a mixed host having two hosts mixed together, and at least one light-emitting dopant for emitting blue light.

[0118] In the same manner as the first stack 510 or second stack 520, the third stack 530 may include at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer.

[0119] The auxiliary emission layer of the third stack 530 may include light-emitting dopant for emitting light whose color is different from that of the light emitted from the third emission layer 530E. In detail, the auxiliary emission layer of the third stack 530 includes light-emitting dopant for emitting yellow-green light or red light. According as the auxiliary emission layer is additionally provided in the third stack 530, it is possible to improve light-emission efficiency of red or green color.

[0120] If the third stack 530 includes the third emission layer 530E having the light-emitting dopant for emitting blue light, a peak wavelength of the light emitted from the third stack 530 may be within a range from 440nm to 480nm.

[0121] If the third stack 530 includes the third emission layer 530E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting yellow-green light or red light, a peak wavelength of the light emitted from the third stack 530 may be within a range from 440nm to 650nm.

[0122] As described above, the third stack 530 further includes at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer, it is possible to improve light-emission efficiency or driving voltage properties of the OLED apparatus 1000. According to a design of the OLED apparatus 1000, the additional organic layers may be selectively disposed in the third stack 530. Also, a thickness (T3) of the third stack 530 or a position of the third emission layer 530E in the third stack 530 may be adjusted based on the position, the thickness, or the number of the additional organic layers included in the third stack 530.

[0123] In the top emission type OLED apparatus 1000 according to the first embodiment of the present invention, the thickness (T1, T2, T3) of each of the plurality of stacks 510, 520 and 530 is adjusted so as to control the properties of the OLED apparatus 1000, for example, light-emission efficiency, color reproduction ratio, or color change rate. In detail, in order to improve the properties of the OLED apparatus 1000, the thickness (T1, T2, T3) of each of the plurality of stacks 510, 520 and 530 is determined by an optimal ratio based on a micro-cavity between the anode 400 having the reflection properties and the cathode 600 having the transparent properties. As described above, the micro-cavity indicates that the light-emission efficiency is improved by amplification and constructive interference of the light with the specific wavelength through repetitive reflection and re-reflection of the light emitted from the emission layer between the two electrodes 400 and 600.

[0124] If the thickness (T1, T2, T3) of each of the plurality of stacks 510, 520 and 530 is not provided at the optimal ratio, it is difficult to optimize the micro-cavity of the light emitted from the emission layers 510E, 520E and 530E included in the plurality of stacks 510, 520 and 530, which causes problems of low light-emission efficiency, deteriorated color reproduction ratio, and increased color change rate. That is, if each emission layer 510E, 520E and 530E is not provided at the corresponding position enabling the optimal micro-cavity between the two electrodes 400 and 600, it may deteriorate the properties of the OLED apparatus 1000. The first emission layer 510E is disposed at the position enabling the micro-cavity of the light emitted from the first emission layer 510E between the two electrodes 400 and 600, the second emission layer 520E is disposed at the position enabling the micro-cavity of the light emitted from the second emission layer 520E between the two electrodes 400 and 600, and the third emission layer 530E is disposed at the position enabling the micro-cavity of the light emitted from the third emission layer 530E between the two electrodes 400 and 600.

[0125] The inventors of the present disclosure propose the OLED apparatus 1000 which facilitates to improve the properties of light-emission efficiency, color reproduction ratio and color change rate by adjusting the thickness of each of the plurality of stacks 510, 520 and 530 or the thickness ratio in the plurality of stacks 510, 520 and 530 so as to optimize the micro-cavity of the light emitted from each of the plurality of stacks 510, 520 and 530. This will be described in detail as follows.

[0126] In the first embodiment of the present disclosure, the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 may be expressed with respect to the distance of the micro-cavity between the two electrodes 400 and 600 of the OLED apparatus 1000. In the first embodiment of the present disclosure, the micro-cavity between the two electrodes 400 and 600 may occur between an upper surface of the reflection layer 410

of the anode 400 having the reflection properties and an upper surface of the cathode 600 having the transparent properties. Thus, the thickness (T1, T2, T3) of each of the plurality of stacks 510, 520 and 530 may be expressed with respect to the distance (T) from the upper surface of the reflection layer 410 of the anode 400 to the upper surface of the cathode 600 having the transparent properties.

[0127] Referring to FIG. 2, the thickness (T1) of the first stack 510 indicates the distance from the upper surface of the reflection layer 410 of the anode 400 to the interface between the first N-type charge generation layer 540N of the first charge generation layer 540 and the first P-type charge generation layer 540P of the first charge generation layer 540. In detail, the thickness (T1) of the first stack 510 may be expressed by the thickness including the thickness of the first N-type charge generation layer 540N and the thickness of the transparent layer 420 of the anode 400, as well as the total thickness of the layers included in the first stack 510. As described above, selectively, the first stack 510 may further include the additional organic layers of the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), or the auxiliary emission layer. In this case, with respect to the distance (T) enabling the occurrence of the micro-cavity between the two electrodes 400 and 600, the thickness (T1) of the first stack 510 may be adjusted by the thickness of the transparent layer 420 of the anode 400 and the thickness of the first N-type charge generation layer 540N as well as the position, the thickness or the number of the additional organic layers selectively included in the first stack 510. Accordingly, it is possible to determine the position of the first emission layer 510E of the first stack 510 between the two electrodes 400 and 600.

[0128] The thickness (T2) of the second stack 520 indicates the distance from the interface between the first N-type charge generation layer 540N of the first charge generation layer 540 and the first P-type charge generation layer 540P of the first charge generation layer 540 to the interface between the second N-type charge generation layer 550N of the second charge generation layer 550 and the second P-type charge generation layer 550P of the second charge generation layer 550. In detail, the thickness (T2) of the second stack 520 may be expressed by the thickness including the thickness of the first P-type charge generation layer 540P and the thickness of the second N-type charge generation layer 550N, as well as the total thickness of the layers included in the second stack 520. Also, the second stack 520 may further include the additional organic layers of the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), or the auxiliary emission layer, selectively. In this case, with respect to the distance (T) enabling the occur-

rence of the micro-cavity between the two electrodes 400 and 600, the thickness (T2) of the second stack 520 may be adjusted by the thickness of the first P-type charge generation layer 540P and the thickness of the second N-type charge generation layer 550N as well as the position, the thickness or the number of the additional organic layers selectively included in the second stack 520. Accordingly, it is possible to determine the position of the second emission layer 520E of the second stack 520 between the two electrodes 400 and 600.

[0129] The thickness (T3) of the third stack 530 indicates the distance from the interface between the second N-type charge generation layer 550N of the second charge generation layer 550 and the second P-type charge generation layer 550P of the second charge generation layer 550 to the upper surface of the cathode 600 having the transparent properties. In detail, the thickness (T3) of the third stack 530 may be expressed by the thickness including the thickness of the second P-type charge generation layer 550P and the thickness of the cathode 600, as well as the total thickness of the layers included in the third stack 530. Also, in the same manner as the first stack 510 or second stack 520, the third stack 530 may further include the additional organic layers of the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), or the auxiliary emission layer, selectively. In this case, with respect to the distance (T) enabling the occurrence of the micro-cavity between the two electrodes 400 and 600, the thickness (T3) of the third stack 530 may be adjusted by the thickness of the second P-type charge generation layer 550P and the thickness of the cathode 600 as well as the position, the thickness or the number of the additional organic layers selectively included in the third stack 530. Accordingly, it is possible to determine the position of the third emission layer 530E of the third stack 530 between the two electrodes 400 and 600.

[0130] In the first embodiment of the present disclosure, among the plurality of stacks 510, 520 and 530 disposed between the anode 400 having the reflection properties and the cathode 600 having the transparent properties, according as the stack becomes close to the cathode 600, its thickness becomes larger in comparison to the thickness of the stack disposed to the anode 400. In more detail, referring to FIG. 2, among the plurality of stacks 510, 520 and 530, the thickness (T3) of the third stack 530 disposed relatively close to the cathode 600 is relatively larger than the thickness (T2) of the second stack 520 disposed relatively close to the anode 400. Also, the thickness (T2) of the second stack 520 is relatively larger than the thickness (T1) of the first stack 510 disposed relatively close to the anode 400. The thickness (T1) of the first stack 510, the second thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 satisfy the following Equation 1.

[Equation 1]

$$T3 > T2 > T1$$

[0131] That is, the thickness (T3) of the third stack 530 is relatively larger than the thickness (T1) of the first stack 510 and the thickness (T2) of the second stack 520, and the thickness (T2) of the second stack 520 is relatively larger than the thickness (T1) of the first stack 510, whereby it is possible to optimize the micro-cavity of the light emitted from each of the first stack 510, the second stack 520 and the third stack 530 between the two electrodes 400 and 600. In other words, according as the stack becomes close to the cathode 600, its thickness becomes larger in comparison to the thickness of the stack disposed to the anode 400. Accordingly, the emission layers 510E, 520E and 530E included in the stacks 510, 520 and 530 may be disposed at the respective positions enabling the optimal micro-cavity between the two electrodes 400 and 600, to thereby improve the light-emission efficiency and color reproduction ratio of the OLED apparatus 1000, and also to lower the color change rate of the OLED apparatus 1000.

[0132] According to the first embodiment of the present disclosure, the first emission layer 510E of the first stack 510 includes the light-emitting dopant for emitting blue light or yellow-green light. Assuming that the total thickness of the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 is 100%, the thickness (T1) of the first stack 510 may be within a range from 10% to 20%, to thereby optimize the micro-cavity of the light emitted from the first stack 510 between the two electrodes 400 and 600. In this case, with respect to the thickness (T1) of the first stack 510, the thickness (T1') from the upper surface of the reflection layer 410 of the anode 400 to the lower surface of the first emission layer 510E may be within a range from 2% to 90%. That is, with respect to the distance (T1) from the upper surface of the reflection layer 410 of the anode 400 and the upper surface of the first N-type charge generation layer 540N, the first emission layer 510E may be disposed at the position corresponding to a range from 2% to 90%, to thereby optimize the micro-cavity of the light emitted from the first emission layer 510E between the two electrodes 400 and 600.

[0133] According to the first embodiment of the present disclosure, the second emission layer 520E of the second stack 520 includes the light-emitting dopant for emitting blue light or yellow-green light. Assuming that the total thickness of the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 is 100%, the thickness (T2) of the second stack 520 may be within a range from 30% to 40%, to thereby optimize the micro-cavity of the light emitted from the second stack 520 between the two electrodes 400 and 600. In this case, with respect to the thick-

ness (T2) of the second stack 520, the thickness (T2') from the upper surface of the first N-type charge generation layer 540N to the lower surface of the second emission layer 520E may be within a range from 2% to 90%.

5 That is, with respect to the distance (T2) from the upper surface of the first N-type charge generation layer 540N to the upper surface of the second N-type charge generation layer 550N, the second emission layer 520E may be disposed at the position corresponding to a range from 2% to 90%, to thereby optimize the micro-cavity of the light emitted from the second emission layer 520E between the two electrodes 400 and 600.

[0134] According to the first embodiment of the present disclosure, the third emission layer 530E of the third stack 530 includes the light-emitting dopant for emitting blue light. Assuming that the total thickness of the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 is 100%, the thickness (T3) of the third stack 530 may be within a range from 45% to 60%, to thereby optimize the micro-cavity of the light emitted from the third stack 530 between the two electrodes 400 and 600. In this case, with respect to the thickness (T3) of the third stack 530, the thickness (T3') from the upper surface of the second N-type charge generation layer 550N to the lower surface of the third emission layer 530E may be within a range from 2% to 90%. In other words, with respect to the distance (T3) from the upper surface of the second N-type charge generation layer 550N to the upper surface of the cathode 600, the third emission layer 530E may be disposed at the position corresponding to a range from 2% to 90%, to thereby optimize the micro-cavity of the light emitted from the third emission layer 530E between the two electrodes 400 and 600.

[0135] If the emission layer included in each of the stacks includes the plurality of layers, or the auxiliary emission layer is additionally provided in the stack, the thickness (T1', T2', T3') indicating the position of the emission layer in each stack may be defined with respect to the lowermost-positioned emission layer among the plurality of emission layers. For example, if the first stack 510 includes the first emission layer 510E, and the auxiliary emission layer disposed between the first emission layer 510E and the anode 400, the thickness (T1') from the upper surface of the reflection layer 410 of the anode 400 to the lower surface of the auxiliary emission layer may be within a range from 2% to 90% with respect to the thickness (T1) of the first stack 510.

[0136] As explained above, the OLED apparatus 1000 according to the first embodiment of the present disclosure includes the plurality of stacks 510, 520 and 530 between the reflection-anode 400 and the transparent cathode 600, and the thickness of the stack disposed close to the transparent cathode 600 is relatively larger than the thickness of the stack disposed close to the reflection-anode 400. Accordingly, the micro-cavity of the light emitted from each stack 510, 520 and 530 is optimized so that it is possible to improve the light-emission

efficiency, the color reproduction ratio, and the color change rate of the OLED apparatus 1000.

[0137] FIG. 3 is a table showing the light-emission efficiency in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples. FIG. 4A is a graph showing the color change rate in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples. FIG. 4B is a graph showing the color reproduction ratio in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples.

[0138] In case of the first embodiment of FIGs. 3, 4A and 4B, among the plurality of stacks, the thickness of the stack disposed close to the transparent cathode is relatively larger than the thickness of the stack disposed close to the reflection-anode. In detail, in case of the OLED apparatus 1000 described with reference to FIG. 2, among the plurality of stacks, the thickness (T3) of the third stack 530 is larger than the thickness (T1) of the first stack 510 and the thickness (T2) of the second stack 520, and the thickness (T2) of the second stack 520 is larger than the thickness (T1) of the first stack 510 ($T1 < T2 < T3$). Also, in case of the first embodiment, assuming that the total thickness (T) of the plurality of stacks 510, 520 and 530 is 100%, a thickness ratio in the plurality of stacks 510, 520 and 530 is at $T1 : T2 : T3 = 16\% : 36\% : 48\%$.

[0139] In case of the comparative example 1 of FIGs. 3, 4A and 4B, assuming that the total thickness (T) of the plurality of stacks 510, 520 and 530 is 100%, a thickness ratio in the plurality of stacks 510, 520 and 530 is at $T1 : T2 : T3 = 33.3\% : 33.3\% : 33.3\%$.

[0140] In case of the comparative example 2 of FIGs. 3, 4A and 4B, among the plurality of stacks, the thickness (T2) of the second stack 520 is the largest one, and the thickness (T1) of the first stack 510 is the same as the thickness (T3) of the third stack 530 ($T1 = T3 < T2$). In detail, in case of the comparative example 2, assuming that the total thickness (T) of the plurality of stacks 510, 520 and 530 is 100%, a thickness ratio in the plurality of stacks 510, 520 and 530 is at $T1 : T2 : T3 = 30\% : 40\% : 30\%$.

[0141] In case of the comparative example 3 of FIGs. 3, 4A and 4B, among the plurality of stacks, the thickness (T1) of the first stack 510 is the largest one, and the thickness (T2) of the second stack 520 is the same as the thickness (T3) of the third stack 530 ($T1 > T2 = T3$). In detail, in case of the comparative example 3, assuming that the total thickness (T) of the plurality of stacks 510, 520 and 530 is 100%, a thickness ratio in the plurality of stacks 510, 520 and 530 is at $T1 : T2 : T3 = 40\% : 30\% : 30\%$.

[0142] In the first embodiment, and the comparative examples 1, 2 and 3, each of the first stack 510 and the third stack 530 includes at least one organic layer having the light-emitting dopant for emitting blue light, and the

second stack 520 includes at least one organic layer having the light-emitting dopant for emitting yellow-green light.

[0143] In the first embodiment of the present disclosure, the thickness ratio in the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 satisfies the condition of $T1 < T2 < T3$, whereby it is possible to optimize the micro-cavity of the light emitted from each of the stacks 510, 520 and 530, thereby improving the light-emission efficiency of the OLED apparatus 1000.

[0144] In detail, referring to FIG. 3, in comparison to the first embodiment of the present disclosure, the comparative example 1 that the thickness ratio in the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 satisfies the condition of $T1 = T2 = T3$ cannot optimize the micro-cavity of the yellow-green light emitted from the second stack 520, whereby the red (R) light efficiency, green (G) light efficiency, and white (W) light efficiency are largely lowered.

[0145] Also, in comparison to the first embodiment of the present disclosure, the comparative example 2 that the thickness ratio in the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 satisfies the condition of $T1 = T3 < T2$ cannot optimize the micro-cavity of the blue light emitted from the stack 510 and the third stack 530, and the micro-cavity of the yellow-green light emitted from the second stack 520, whereby the red (R) light efficiency, green (G) light efficiency, blue (B) light efficiency, and white (W) light efficiency are largely lowered.

[0146] Also, in comparison to the first embodiment of the present disclosure, the comparative example 3 that the thickness ratio in the thickness (T1) of the first stack 510, the thickness (T2) of the second stack 520, and the thickness (T3) of the third stack 530 satisfies the condition of $T1 > T2 = T3$ cannot optimize the micro-cavity of the yellow-green light emitted from the second stack 520, whereby the red (R) light efficiency, green (G) light efficiency, and white (W) light efficiency are especially lowered.

[0147] That is, in comparison to the first embodiment of the present disclosure, the emission layers 510E, 520E and 530E included in each of the plurality of stacks 510, 520 and 530 for the comparative examples 1, 2 and 3 are not disposed at the corresponding positions for optimizing the micro-cavity between the two electrodes 400 and 600, whereby the light-emission efficiency of the OLED apparatus 1000 in each of the comparative examples 1, 2 and 3 is relatively lower than the light-emission efficiency of the OLED apparatus 1000 according to the first embodiment of the present disclosure.

[0148] FIG. 4A is a graph showing the color change rate in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples 1, 2 and 3. When the OLED apparatus is seen from the front, its viewing

angle is 0°. In detail, FIG. 4A is the graph obtained by measuring the value of $\Delta u'v'$ in accordance with the gradually-increased viewing angle from 0° to 60°. According as the change of color in accordance with the viewing angle becomes smaller, the value of $\Delta u'v'$ becomes smaller.

[0149] Referring to FIG. 4A, in case of the comparative example 1, the color change rate is gradually increased within the range of viewing angle from 0° to 60°, and the value of $\Delta u'v'$ is about 0.230 when the viewing angle is at 60°. In case of the comparative example 2, the color change rate is gradually increased within the range of viewing angle from 0° to 60°, and the value of $\Delta u'v'$ is about 0.200 when the viewing angle is at 60°. In case of the comparative example 3, the color change rate is gradually increased within the range of viewing angle from 0° to 60°, and the value of $\Delta u'v'$ is about 0.162 when the viewing angle is at 60°. That is, in case of the comparative examples 1, 2 and 3, the micro-cavity of the light emitted from the plurality of stacks 510, 520 and 530 is not optimized so that the color change is gradually increased by the spectrum change of the emitted light in accordance with the increase of viewing angle. Especially, if the value of $\Delta u'v'$ is larger than 0.05 within the range of viewing angle from 0° to 60°, a viewer discerns the color difference in accordance with the viewing angle, to thereby lower a picture quality of the OLED apparatus.

[0150] Meanwhile, in case of the first embodiment of the present disclosure, the color change rate is scarcely changed within the range of viewing angle from 0° to 60°, and the value of $\Delta u'v'$ is about 0.012 when the viewing angle is at 60°. That is, in case of the first embodiment of the present disclosure, the value of $\Delta u'v'$ is smaller than 0.05 within the range of viewing angle from 0° to 60°, so that it is possible to reduce the color difference in accordance with the viewing angle of the OLED apparatus, and furthermore to express a clear and realistic image. Accordingly, it is possible to provide a display device appropriate for a large-sized television.

[0151] FIG. 4B is a graph showing the color reproduction ratio in the OLED apparatus according to the first embodiment of the present disclosure and OLED apparatuses according to comparative examples 1, 2 and 3. In detail, FIG. 4B is the graph for explaining sRGB coverage.

[0152] Herein, 'sRGB' is CIE 1976 standard, which indicates the color reproduction ratio including red (R), green (G), and blue (B) colors. Also, a range of the color reproduction ratio may be changed in accordance with a consumer's request or product development, and the color reproduction ratio may be referred to as color gamut, color area, color realization area, color realization range, and etc. Also, 'sRGB coverage' indicates a range of covering entire colors. According as 'sRGB coverage' increases, it is possible to express more various colors, to thereby improve the color reproduction ratio.

[0153] In FIG. 4B, a dotted line indicates 'BT709', wherein 'BT709' indicates color gamut used for HDTV.

In detail, 'Cx' and 'Cy' corresponding to a red color is (0.640, 0.330), 'Cx' and 'Cy' corresponding to a green color is (0.300, 0.600), 'Cx' and 'Cy' corresponding to a blue color is (0.150, 0.060), and a triangle shape is obtained by connecting each corresponding area for the red, green, and blue colors. A method of expressing the color reproduction ratio may be changed to various ways in accordance with a consumer's request or product development, and the content of the present disclosure is not limited to FIG. 4B expressed by 'BT709'.

[0154] Referring to FIG. 4B, 'sRGB coverage' of the comparative example 1 is about 93.8%, 'sRGB coverage' of the comparative example 2 is about 98.5%, and 'sRGB coverage' of the comparative example 3 is about 95.8%. Meanwhile, 'sRGB coverage' of the first embodiment of the present disclosure is about 99.0%, that is, 'sRGB coverage' of the first embodiment of the present disclosure is improved in comparison to that of the comparative examples 1, 2, and 3. That is, the first embodiment of the present disclosure has the color gamut which is nearly similar to the area of 'BT709' expressed by the dotted line. Accordingly, in comparison to the comparative examples 1, 2, and 3, the first embodiment of the present disclosure may provide more realistic and clearer image.

[0155] As described above, the thickness ratio in the plurality of stacks disposed between the reflection-anode and the transparent cathode is adjusted so as to obtain the color reproduction ratio of 99% or more than 99% and simultaneously to obtain the $\Delta u'v'$ value of 0.05 or less than 0.05 within the range of viewing angle from 0° to 60° so that it is possible to improve the light-emission efficiency and the color reproduction ratio of the OLED apparatus, and to lower the color change rate.

[0156] FIG. 5 is a cross sectional view illustrating main components of an OLED apparatus 2000 according to the second embodiment of the present disclosure. For convenience of explanation, a detailed description for the same parts or similar parts to those of the first embodiment will be omitted or briefly explained.

[0157] The OLED apparatus 2000 according to the second embodiment of the present disclosure, which is shown in FIG. 5, may include an anode 1400 having a reflection properties and including a reflection layer 1410 and a transparent layer 1420, a cathode 1600 having a transparent properties, and a light-emission unit 1500 disposed between the anode 1400 and the cathode 1600. The light-emission unit 1500 may include a first stack 1510, a charge generation layer 1540, and a second stack 1520. Also, the OLED apparatus 2000 according to the second embodiment of the present disclosure is a top emission type, wherein white light (L) is emitted from the light-emission unit 1500, and is emitted through the cathode 1600 having the transparent properties.

[0158] The anode 1400 and the cathode 1600 shown in FIG. 5 are the same as the anode 400 and the cathode 600 shown in FIG. 2 according to the first embodiment of the present disclosure, whereby a detailed description for the anode 1400 and the cathode 1600 will be omitted.

[0159] The first stack 1510 is disposed on the anode 1400. Between the first and second stacks 1510 and 1520, the first stack 1510 is relatively close to the anode 1400.

[0160] The first stack 1510 may include at least one organic layer having light-emitting dopant for emitting blue light. For example, as shown in FIG. 5, the first stack 1510 may include a first emission layer 1510E having light-emitting dopant for emitting blue light.

[0161] The first emission layer 1510E may be formed in a single-layered or multi-layered structure including the light-emitting dopant for emitting blue light. In detail, the first emission layer 1510E may include at least one host and at least one light-emitting dopant for emitting blue light. The first emission layer 1510E may include a mixed host having two hosts mixed together, and at least one light-emitting dopant for emitting blue light. The mixed host may include a host having a hole transporting properties, and a host having an electron transporting properties.

[0162] For example, the light-emitting dopant for emitting blue light may be formed of a pyrene-based compound replaced by an arylamine-based compound, but is not limited to this material.

[0163] The first stack 1510 may further include at least one among a hole injecting layer (HIL), a hole transporting layer (HTL), an electron transporting layer (ETL), an electron injecting layer (EIL), a hole blocking layer (HBL), an electron blocking layer (EBL), and an auxiliary emission layer.

[0164] The auxiliary emission layer of the first stack 1510 may include light-emitting dopant for emitting light whose color is different from that of the light emitted from the first emission layer 1510E. For example, the auxiliary emission layer of the first stack 1510 may include light-emitting dopant for emitting yellow-green light or red light. According as the auxiliary emission layer is additionally provided in the first stack 1510, it is possible to improve light-emission efficiency of red or green color.

[0165] If the first stack 1510 includes the first emission layer 1510E having the light-emitting dopant for emitting blue light, a peak wavelength of the light emitted from the first stack 1510 may be within a range from 440nm to 480nm.

[0166] If the first stack 1510 includes the first emission layer 1510E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the first stack 1510 may be within a range from 440nm to 650nm. And, if the first stack 1510 includes the first emission layer 1510E having the light-emitting dopant for emitting blue light, and the auxiliary emission layer having the light-emitting dopant for emitting yellow-green light, a peak wavelength of the light emitted from the first stack 1510 may be within a range from 440nm to 580nm.

[0167] As described above, the first stack 1510 further includes at least one among the hole injecting layer (HIL),

the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer, so that it is possible to improve light-emission efficiency or driving voltage properties of the OLED apparatus 2000. According to a design of the OLED apparatus 2000, the additional organic layers may be selectively disposed in the first stack 1510. Also, a thickness (T1) of the first stack 1510 and a position of the first emission layer 1510E in the first stack 1510 may be adjusted based on the position, the thickness, or the number of the additional organic layers included in the first stack 1510.

[0168] The charge generation layer 1540 is disposed on the first stack 1510, or disposed between the first stack 1510 and the second stack 1520, to thereby adjust a charge balance between the first stack 1510 and the second stack 1520. The charge generation layer 1540 includes an N-type charge generation layer 1540N and a P-type charge generation layer 1540P. The N-type charge generation layer 1540N and the P-type charge generation layer 1540P are the same as the first N-type charge generation layer 540N and the first P-type charge generation layer 540P described in FIG. 2, or the second N-type charge generation layer 550N and the second P-type charge generation layer 550P described in FIG. 2, whereby a detailed description for the N-type charge generation layer 1540N and the P-type charge generation layer 1540P will be omitted.

[0169] The second stack 1520 is disposed on the charge generation layer 1540. In comparison to the first stack 1510, the second stack 1520 is relatively close to the cathode 1600. The second stack 1520 may be disposed between the first stack 1510 and the cathode 1600.

[0170] The second stack 1520 may include at least one organic layer having the light-emitting dopant for emitting yellow-green light. For example, as shown in FIG. 5, the second stack 1520 may include the second emission layer 1520E having the light-emitting dopant for emitting yellow-green light.

[0171] The second emission layer 1520E may be formed in a single-layered structure or multi-layered structure having the light-emitting dopant for emitting yellow-green light. In detail, the second emission layer 1520E may include at least one host and at least one light-emitting dopant for emitting yellow-green light, or may include a mixed host having two hosts mixed together, and at least one light-emitting dopant for emitting yellow-green light.

[0172] The light-emitting dopant for emitting yellow-green light may be formed of an iridium-based compound, but is not limited to this material.

[0173] The second stack 1520 may further include at least one among a hole injecting layer (HIL), a hole transporting layer (HTL), an electron transporting layer (ETL), an electron injecting layer (EIL), a hole blocking layer (HBL), an electron blocking layer (EBL), and an auxiliary emission layer.

[0174] The auxiliary emission layer of the second stack 1520 may include light-emitting dopant for emitting light whose color is different from that of the light emitted from the second emission layer 1520E. For example, the auxiliary emission layer of the second stack 1520 may include light-emitting dopant for emitting green light or red light. According as the auxiliary emission layer is additionally provided in the second stack 1520, it is possible to improve light-emission efficiency of red or green color.

[0175] If the second stack 1520 includes the second emission layer 1520E having the light-emitting dopant for emitting yellow-green light, a peak wavelength of the light emitted from the second stack 1520 may be within a range from 540nm to 580nm.

[0176] If the second stack 1520 includes the second emission layer 1520E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting red light, a peak wavelength of the light emitted from the second stack 1520 may be within a range from 540nm to 650nm. And, if the second stack 1520 includes the second emission layer 1520E having the light-emitting dopant for emitting yellow-green light, and the auxiliary emission layer having the light-emitting dopant for emitting green light, a peak wavelength of the light emitted from the second stack 1520 may be within a range from 510nm to 590nm.

[0177] As described above, the second stack 1520 further includes at least one among the hole injecting layer (HIL), the hole transporting layer (HTL), the electron transporting layer (ETL), the electron injecting layer (EIL), the hole blocking layer (HBL), the electron blocking layer (EBL), and the auxiliary emission layer, so that it is possible to improve light-emission efficiency or driving voltage properties of the OLED apparatus 2000. According to a design of the OLED apparatus 2000, the additional organic layers may be selectively disposed in the second stack 1520. Also, a thickness (T2) of the second stack 1520 and a position of the second emission layer 1520E in the second stack 1520 may be adjusted based on the position, the thickness, or the number of the additional organic layers included in the second stack 1520.

[0178] In the top emission type OLED apparatus 2000 according to the second embodiment of the present disclosure, the properties of the OLED apparatus 2000, for example, light-emission efficiency, color reproduction ratio or color change rate may be controlled by adjusting the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520. In more detail, in order to improve the properties of the OLED apparatus 2000, the thickness ratio in the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 has to be optimized in consideration of the micro-cavity between the anode 1400 having the reflection properties and the cathode 1600 having the transparent properties.

[0179] Referring to FIG. 5, the thickness (T1) of the first stack 1510 indicates the distance from the upper surface of the reflection layer 1410 of the anode 1400 to

the interface between the N-type charge generation layer 1540N and the P-type charge generation layer 1540P. In detail, the thickness (T1) of the first stack 1510 may be expressed by the thickness including the thickness of the N-type charge generation layer 1540N and the thickness of the transparent layer 1420 of the anode 1400, as well as the total thickness of the layers included in the first stack 1510.

[0180] The thickness (T2) of the second stack 1520 indicates the distance from the interface between the N-type charge generation layer 1540N and the P-type charge generation layer 1540P to the upper surface of the cathode 1600 having the transparent properties. In detail, the thickness (T2) of the second stack 1520 may be expressed by the thickness including the thickness of the P-type charge generation layer 1540P and the thickness of the cathode 1600, as well as the total thickness of the layers included in the second stack 1520.

[0181] In the second embodiment of the present disclosure, between the first stack 1510 and the second stack 1520, the thickness (T2) of the second stack 1520 disposed close to the cathode 1600 having the transparent properties is relatively larger than the thickness (T1) of the first stack 1510 disposed close to the anode 1400 having the reflection properties. That is, the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 satisfy the following Equation 2.

[Equation 2]

$$T2 > T1$$

[0182] As explained above, the thickness (T2) of the second stack 1520 is larger than the thickness (T1) of the first stack 1510, whereby it is possible to optimize the micro-cavity of the light emitted from each of the first stack 1510 and the second stack 1520 between the two electrodes 1400 and 1600. In other words, according as the thickness (T2) of the second stack 1520 disposed close to the cathode 1600 is relatively larger than the thickness (T1) of the first stack 1510 disposed close to the anode 1400, the emission layers 1510E and 1520E included in the stacks may be disposed at the respective positions enabling the optimal micro-cavity between the two electrodes 1400 and 1600, to thereby improve the light-emission efficiency and color reproduction ratio of the OLED apparatus 2000, and also to lower the color change rate of the OLED apparatus 2000.

[0183] According to the second embodiment of the present disclosure, the first emission layer 1510E of the first stack 1510 includes the light-emitting dopant for emitting blue light. Assuming that the total thickness of the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 is 100%, the thickness (T1) of the first stack 1510 may be within a range from 15% to 35%, to thereby optimize the micro-cavity of the light emitted from the first stack 1510 between the two

electrodes 1400 and 1600. In this case, with respect to the thickness (T1) of the first stack 1510, the thickness (T1') from the upper surface of the reflection layer 1410 of the anode 1400 to the lower surface of the first emission layer 1510E may be within a range from 5% to 90%. That is, with respect to the distance (T1) from the upper surface of the reflection layer 1410 of the anode 1400 to the upper surface of the N-type charge generation layer 1540N, the first emission layer 1510E may be disposed at the position corresponding to a range from 5% to 90%, to thereby optimize the micro-cavity of the light emitted from the first emission layer 1510E between the two electrodes 1400 and 1600.

[0184] According to the second embodiment of the present disclosure, the second emission layer 1520E of the second stack 1520 includes the light-emitting dopant for emitting yellow-green light. Assuming that the total thickness of the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 is 100%, the thickness (T2) of the second stack 1520 may be within a range from 65% to 85%, to thereby optimize the micro-cavity of the light emitted from the second stack 1520 between the two electrodes 1400 and 1600. In this case, with respect to the thickness (T2) of the second stack 1520, the thickness (T2') from the upper surface of the N-type charge generation layer 1540N to the lower surface of the second emission layer 1520E may be within a range from 5% to 90%. That is, with respect to the distance (T2) from the upper surface of the N-type charge generation layer 1540N to the upper surface of the cathode 1600, the second emission layer 1520E may be disposed at the position corresponding to a range from 5% to 90%, to thereby optimize the micro-cavity of the light emitted from the second emission layer 1520E between the two electrodes 1400 and 1600.

[0185] If the emission layer included in each of the stacks includes the plurality of layers, or the auxiliary emission layer is additionally provided in the stack, the thickness (T1', T2') indicating the position of the emission layer in each stack may be defined with respect to the lowermost-positioned emission layer among the plurality of emission layers. For example, if the first stack 1510 includes the first emission layer 1510E, and the auxiliary emission layer disposed between the first emission layer 1510E and the anode 1400, the thickness (T1') from the upper surface of the reflection layer 1410 of the anode 1400 to the lower surface of the auxiliary emission layer may be within a range from 5% to 90% with respect to the thickness (T1) of the first stack 1510.

[0186] As explained above, the OLED apparatus 2000 according to the second embodiment of the present disclosure includes the first stack 1510 and the second stack 1520 disposed between the reflection-anode 1400 and the transparent cathode 1600, wherein the thickness of the second stack 1520 disposed close to the transparent cathode 1600 is larger than the thickness of the first stack 1510. Accordingly, it is possible to optimize the micro-cavity of the light emitted from the first stack 1510 and

the second stack 1520, to thereby improve the light-emission efficiency and the color reproduction ratio, and to reduce the color change rate in the OLED apparatus 2000.

[0187] FIG. 6 is a table showing the light-emission efficiency in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples. FIG. 7A is a graph showing the color change rate in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples. FIG. 7B is a graph showing the color reproduction ratio in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples.

[0188] In case of the second embodiment of FIGs. 6, 7A and 7B, the thickness (T2) of the second stack 1520 is larger than the thickness (T1) of the first stack 1510 ($T1 < T2$) in the OLED apparatus 2000 described in FIG. 5. Also, in case of the second embodiment, assuming that the total thickness (T) of the first and second stacks 1510 and 1520 is 100%, a thickness ratio in the first and second stacks 1510 and 1520 is at $T1 : T2 = 32\% : 68\%$.

[0189] In case of the comparative example 4 of FIGs. 6, 7A and 7B, the thickness of the first stack 1510 is the same as the thickness of the second stack 1520 ($T1 = T2$). In detail, in case of the comparative example 4, assuming that the total thickness (T) of the first and second stacks 1510 and 1520 is 100%, a thickness ratio in the first and second stacks 1510 and 1520 is at $T1 : T2 = 50\% : 50\%$.

[0190] In case of the comparative example 5 of FIGs. 6, 7A and 7B, the thickness (T1) of the first stack 1510 is larger than the thickness (T2) of the second stack 1520 ($T1 > T2$). Also, in case of the second embodiment, assuming that the total thickness (T) of the first and second stacks 1510 and 1520 is 100%, a thickness ratio in the first and second stacks 1510 and 1520 is at $T1 : T2 = 68\% : 32\%$.

[0191] In the second embodiment, and the comparative examples 4 and 5, the first stack 1510 includes at least one organic layer having the light-emitting dopant for emitting blue light, and the second stack 1520 includes at least one organic layer having the light-emitting dopant for emitting yellow-green light.

[0192] In the second embodiment of the present disclosure, the thickness ratio in the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 satisfies the condition of $T1 < T2$, whereby it is possible to optimize the micro-cavity of the light emitted from each of the stacks 1510 and 1520, thereby improving the light-emission efficiency of the OLED apparatus 2000.

[0193] In detail, referring to FIG. 6, in comparison to the second embodiment of the present disclosure, the comparative example 4 wherein the thickness ratio in the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 satisfies the condition of $T1 = T2$ cannot optimize the micro-cavity of the yellow-

green light emitted from the second stack 1520, whereby the red (R) light efficiency, green (G) light efficiency, and white (W) light efficiency are largely lowered.

[0194] Also, in comparison to the second embodiment of the present disclosure, the comparative example 5 wherein the thickness ratio in the thickness (T1) of the first stack 1510 and the thickness (T2) of the second stack 1520 satisfies the condition of $T1 > T2$ cannot optimize the micro-cavity of the yellow-green light emitted from the second stack 1520, whereby the red (R) light efficiency, green (G) light efficiency, and white (W) light efficiency are largely lowered.

[0195] That is, in comparison to the second embodiment of the present disclosure, the first emission layer 1510E included in the first stack 1510, and the second emission layer 1520E included in the second stack 1520 for the comparative examples 4 and 5 are not disposed at the corresponding positions for optimizing the micro-cavity between the two electrodes 1400 and 1600, whereby the light-emission efficiency of the OLED apparatus 2000 in each of the comparative examples 4 and 5 is relatively lower than the light-emission efficiency of the OLED apparatus 2000 according to the second embodiment of the present disclosure.

[0196] FIG. 7A is a graph showing the color change rate in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples 4 and 5.

[0197] Referring to FIG. 7A, in case of the comparative example 4, the color change rate is gradually increased within the range of viewing angle from 0° to 60° , and the value of $\Delta u'v'$ is about 0.115 when the viewing angle is at 60° . In case of the comparative example 5, the color viewing angle is gradually increased within the range of viewing angle from 0° to 60° , and the value of $\Delta u'v'$ is about 0.061 when the viewing angle is at 60° . That is, in case of the comparative examples 4 and 5, the micro-cavity of the light emitted from the first stack 1510 and the second stack 1520 is not optimized so that the color change is gradually increased by the spectrum change of the emitted light in accordance with the increase of viewing angle. As described above, if the value of $\Delta u'v'$ is larger than 0.05 within the range of viewing angle from 0° to 60° , a viewer discerns the color difference in accordance with the viewing angle, to thereby lower a picture quality of the OLED apparatus.

[0198] Meanwhile, in case of the second embodiment of the present disclosure, the color change rate is scarcely changed within the range of viewing angle from 0° to 60° , and the value of $\Delta u'v'$ is about 0.012 when the viewing angle is at 60° . That is, in case of the second embodiment of the present disclosure, the value of $\Delta u'v'$ is smaller than 0.05 within the range of viewing angle from 0° to 60° , so that it is possible to reduce the color difference in accordance with the viewing angle of the OLED apparatus, and furthermore to express a clear and realistic image. Accordingly, it is possible to provide a display device appropriate for a large-sized television.

[0199] FIG. 7B is a graph showing the color reproduction ratio in the OLED apparatus according to the second embodiment of the present disclosure and OLED apparatuses according to comparative examples 4 and 5. In detail, FIG. 7B is the graph for explaining sRGB coverage.

[0200] Referring to FIG. 7B, 'sRGB coverage' of the comparative example 4 is about 92%, and 'sRGB coverage' of the comparative example 5 is about 98%. Meanwhile, 'sRGB coverage' of the second embodiment of the present disclosure is about 100%, that is, 'sRGB coverage' of the second embodiment of the present disclosure is improved in comparison to that of the comparative examples 4 and 5. That is, the second embodiment of the present disclosure has the color gamut which is nearly similar to the area of 'BT709' expressed by the dotted line, whereby the second embodiment of the present disclosure may provide more realistic and clearer image.

[0201] As described above, the thickness ratio in the first stack and the second stack disposed between the reflection-anode and the transparent cathode is adjusted so as to obtain the color reproduction ratio of 99% or more than 99% and simultaneously to obtain the $\Delta u'v'$ value of 0.05 or less than 0.05 within the range of a viewing angle from 0° to 60° so that it is possible to improve the light-emission efficiency and the color reproduction ratio of the OLED apparatus, and to reduce the color change rate of the OLED apparatus.

[0202] In the OLED apparatus according to the embodiment of the present disclosure, the thickness ratio in the plurality of stacks disposed between the reflection-anode and the transparent cathode is optimized so that it is possible to improve the light-emission efficiency and the color reproduction ratio, and to reduce the color change rate.

[0203] According to the embodiment of the present disclosure, among the plurality of stacks, the thickness of the stack disposed close to the cathode is relatively larger than the thickness of the stack disposed close to the anode, so that it is possible to improve the light-emission efficiency, to improve the color reproduction ratio for 'sRGB', and to reduce the color change rate of the light emitted via the cathode from the plurality of stacks.

[0204] It will be apparent to those skilled in the art that various modifications and variations can be made in the present disclosure without departing from the spirit or scope of the inventions. Thus, it is intended that the present disclosure covers the modifications and variations of this disclosure provided they come within the scope of the appended claims and their equivalents.

Claims

1. An organic light emitting display (OLED) apparatus (1000, 2000) comprising:

a reflection-anode (410, 1410);

- a transparent cathode (600, 1600); and
a plurality of stacks (510, 520, 530, 1510, 1520)
between the reflection-anode (410, 1410); and
the transparent cathode (600, 1600),
wherein, among the plurality of stacks (510, 520,
530, 1510, 1520), a thickness of the stack (530,
1520) disposed relatively close to the transpar-
ent cathode (600, 1600) is larger than a thick-
ness of the stack (510, 1510) disposed relatively
close to the reflection-anode (410, 1410).
2. The OLED apparatus (1000) according to claim 1,
wherein the plurality of stacks (510, 520, 530) in-
clude:

a first stack (510) on the reflection-anode (410);
a first charge generation layer (540) on the first
stack (510), wherein the first charge generation
layer (540) includes a first N-type charge gen-
eration layer (540N), and a first P-type charge
generation layer (540P);
a second stack (520) on the first charge gen-
eration layer (540);
a second charge generation layer (550) on the
second stack (520), wherein the second charge
generation layer (550) includes a second N-type
charge generation layer (550N), and a second
P-type charge generation layer (550P); and
a third stack (530) on the second charge gen-
eration layer (550),
wherein, when 'T1' indicates a distance from an
upper surface of the reflection-anode (410) to
an interface between the first N-type charge
generation layer (540N) and the first P-type
charge generation layer (540P), 'T2' indicates a
distance from the interface between the first N-
type charge generation layer (540N) and the first
P-type charge generation layer (540P) to an in-
terface between the second N-type charge gen-
eration layer (550N) and the second P-type
charge generation layer (550P), and 'T3' indi-
cates a distance from the interface between the
second N-type charge generation layer (550N)
and the second P-type charge generation layer
(550P) to an upper surface of the transparent
cathode (600), the 'T1', 'T2', and 'T3' satisfy the
following Equation 1,

[Equation 1]

$$T3 > T2 > T1.$$

3. The OLED apparatus (1000) according to claim 2,
wherein, assuming that the total thickness of T1, T2,
and T3 is 100%,

T1 is within a range from 10% to 20%,

T2 is within a range from 30% to 40%, and
T3 is within a range from 45% to 60%.

4. The OLED apparatus (1000) according to claim 2 or
3,
wherein each of the first stack (510) and the third
stack (530) includes at least one organic layer (510E,
530E) having light-emitting dopant for emitting blue
light, and
the second stack (520) includes at least one organic
layer (520E) having light-emitting dopant for emitting
yellow-green light.
5. The OLED apparatus (1000) according to claim 2 or
3,
wherein each of the second stack (520) and the third
stack (530) includes at least one organic layer (520E,
530E) having light-emitting dopant for emitting blue
light, and
the first stack (510) includes at least one organic
layer (510E) having light-emitting dopant for emitting
yellow-green light.
6. The OLED apparatus (1000, 2000) according to
claim 1, wherein light is emitted from the plurality of
stacks (510, 520, 530, 1520, 1530), and is emitted
through the transparent cathode (600, 1600),
wherein a thickness ratio in the plurality of stacks
(510, 520, 530, 1520, 1530), is adjusted so as to
obtain a color reproduction ratio of 99% or more than
99% and simultaneously to obtain $\Delta u'v'$ value of 0.05
or less than 0.05 within a range of a viewing angle
from 0° to 60°.
7. The OLED apparatus (2000) according to claim 6,
wherein the plurality of stacks (1510, 1520) include:

a first stack (1510); and
a second stack (1520) between the first stack
(1510) and the transparent cathode (1600),
wherein a thickness (T2) of the second stack
(1520) is larger than a thickness (T1) of the first
stack (1510).
8. The OLED apparatus (2000) according to claim 7,
wherein the plurality of stacks (1510, 1520) further
include an N-type charge generation layer (1540N)
and a P-type charge generation layer (1540P) be-
tween the first stack (1510) and the second stack
(1520),
a thickness (T1) of the first stack (1510) is a distance
from an upper surface of the reflection-anode (1400)
to an interface between the N-type charge genera-
tion layer (1540N) and the P-type charge genera-
tion layer (1540P), and
a thickness (T2) of the second stack (1520) is a dis-
tance from the interface between the N-type charge
generation layer (1540N) and the P-type charge gen-

eration layer (1540P) to an upper surface of the transparent cathode (1600).

9. The OLED apparatus (2000) according to claim 8, wherein, assuming that the total thickness (T) of the first stack (1510) and the second stack (1520) is 100%, the thickness (T1) of the first stack (1510) is within a range from 15% to 35%, and the thickness (T2) of the second stack (1520) is within a range from 65% to 85%. 5
10. The OLED apparatus (2000) according to claim 8 or 9, wherein the first stack (1510) includes at least one organic layer (1510E) having light-emitting dopant for emitting blue light, and the second stack (1520) includes at least one organic layer (1520E) having light-emitting dopant for emitting yellow-green light. 10
11. The OLED apparatus (1000) according to claim 6, wherein the plurality of stacks (510, 520, 530) include: 15
 - a first stack (510) closest to the reflection-anode (410);
 - a third stack (530) closest to the transparent cathode (600); and
 - a second stack (520) between the first stack (510) and the third stack (530), wherein a thickness (T3) of the third stack (530) is larger than a thickness (T1) of the first stack (510) and a thickness (T2) of the second stack (520), and 20
 - the thickness (T2) of the second stack (520) is larger than the thickness (T1) of the first stack (510). 25
12. The OLED apparatus (1000) according to claim 11, wherein the plurality of stacks (510, 520, 530) further include: 30
 - a first charge generation layer (540) between the first stack (510) and the second stack (520), the first charge generation layer (540) having a first N-type charge generation layer (540N) and a first P-type charge generation layer (540P); and 35
 - a second charge generation layer (550) between the second stack (520) and the third stack (530), the second charge generation layer (550) having a second N-type charge generation layer (550N) and a second P-type charge generation layer (550P), 40
 - wherein a thickness (T1) of the first stack (510) corresponds to a distance from an upper surface of the reflection-anode (410) to an interface be- 45
- tween the first N-type charge generation layer (540N) and the first P-type charge generation layer (540P), 50
- a thickness (T2) of the second stack (520) corresponds to a distance from the interface between the first N-type charge generation layer (540N) and the first P-type charge generation layer (540P) to an interface between the second N-type charge generation layer (550N) and the second P-type charge generation layer (550P), and 55
- a thickness (T3) of the third stack (530) corresponds to a distance from the interface between the second N-type charge generation layer (550N) and the second P-type charge generation layer (550P) to an upper surface of the transparent cathode (600).
13. The OLED apparatus (1000) according to claim 12, wherein, assuming that the total thickness (T) of the thickness (T1) of the first stack (510), the thickness (T2) of the second stack (520), and the thickness (T3) of the third stack (530) is 100%, the thickness (T1) of the first stack (510) is within a range from 10% to 20%, the thickness (T2) of the second stack (520) is within a range from 30% to 40%, and the thickness (T3) of the third stack (530) is within a range from 45% to 60%.
14. The OLED apparatus (1000) according to claim 12 or 13, wherein each of the first stack (510) and the third stack (530) includes at least one organic layer (510E, 530E) having light-emitting dopant for emitting blue light, and the second stack (520) includes at least one organic layer (520E) having light-emitting dopant for emitting yellow-green light.
15. The OLED apparatus (1000) according to claim 12 or 13, wherein each of the second stack (520) and the third stack (530) includes at least one organic layer (520E, 530E) having light-emitting dopant for emitting blue light, and the first stack (510) includes at least one organic layer (510E) having light-emitting dopant for emitting yellow-green light.

FIG. 1




FIG. 2




FIG. 3

		First embodiment (Embodiment 1)	Comparative example 1	Comparative example 2	Comparative example 3
Light-emission efficiency	R	100%	51%	20%	20%
	G	100%	9%	22%	26%
	B	100%	71%	63%	95%
	W	100%	17%	20%	25%

FIG. 4A




FIG. 4B





FIG. 5




FIG. 6

		Second embodiment (Embodiment 2)	Comparative example 4	Comparative example 5
Light-emission efficiency	R	100%	24%	45%
	G	100%	8%	87%
	B	100%	88%	99%
	W	100%	14%	78%

FIG. 7A





FIG. 7B



Application Number
EP 16 18 1621

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	US 2012/205685 A1 (SEO SATOSHI [JP] ET AL) 16 August 2012 (2012-08-16) * paragraphs [0198] - [0229]; figure 6; table 1 *	1,6-10	INV. H01L51/52
X A	US 2013/285039 A1 (ISHIHARA SHINGO [JP] ET AL) 31 October 2013 (2013-10-31) * paragraphs [0126] - [0135]; figure 5; example 7 *	1,2,6-9, 11,12 3-5, 13-15	
X	US 2015/155519 A1 (LEE SE HEE [KR]) 4 June 2015 (2015-06-04) * paragraphs [0132] - [0149]; figures 3,13 *	1,6-8	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (IPC)
			H01L H05B
Place of search		Date of completion of the search	Examiner
The Hague		20 January 2017	Bakos, Tamás
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 16 18 1621

5 This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-01-2017

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2012205685 A1	16-08-2012	JP 5996876 B2	21-09-2016
		JP 2012182122 A	20-09-2012
		JP 2016225313 A	28-12-2016
		KR 20120092510 A	21-08-2012
		TW 201242426 A	16-10-2012
		US 2012205685 A1	16-08-2012
		US 2015214506 A1	30-07-2015
		US 2016380236 A1	29-12-2016

US 2013285039 A1	31-10-2013	JP 5492798 B2	14-05-2014
		JP 2012155868 A	16-08-2012
		US 2013285039 A1	31-10-2013
		WO 2012102243 A1	02-08-2012

US 2015155519 A1	04-06-2015	CN 104681735 A	03-06-2015
		KR 20150062759 A	08-06-2015
		US 2015155519 A1	04-06-2015

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- KR 1020150132531 [0001]

专利名称(译)	有机发光显示装置		
公开(公告)号	EP3144996A1	公开(公告)日	2017-03-22
申请号	EP2016181621	申请日	2016-07-28
[标]申请(专利权)人(译)	乐金显示有限公司		
申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
当前申请(专利权)人(译)	LG DISPLAY CO. , LTD.		
[标]发明人	KUM TAEIL SONG KI WOOG AHN SOYEON CHOI YONGJOONG LEE MINGYU		
发明人	KUM, TAEIL SONG, KI-WOOG AHN, SOYEON CHOI, YONGJOONG LEE, MINGYU		
IPC分类号	H01L51/52		
CPC分类号	H01L27/3211 H01L51/5008 H01L51/52 H01L51/5265 H01L51/5278 H01L2251/5315 H01L51/504 H01L51/5218 H01L51/5234 H01L2251/558		
优先权	1020150132531 2015-09-18 KR		
外部链接	Espacenet		

摘要(译)

公开了一种OLED装置 (1000,2000) , 其可包括反射阳极 (410,1410) , 透明阴极 (600,1600) , 以及位于其间的多个堆叠 (510,520,530,1510,1520) 。反射阳极和透明阴极 (600,1600) , 其中, 在多个堆叠 (510,520,530,1510,1520) 中, 堆叠 (530,1520) 的厚度相对靠近透明阴极设置 (600,1600) 大于相对靠近反射阳极 (410,1410) 设置的叠层 (510,1510) 的厚度, 使得可以优化从多个叠层发射的光的微腔 (如图510,520,530,1510,1520所示, 从而提高了发光效率和颜色再现率, 并根据视角降低了颜色变化率。

