



(11) **EP 3 297 051 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
21.03.2018 Bulletin 2018/12

(51) Int Cl.:
H01L 51/00 (2006.01) H01L 51/50 (2006.01)

(21) Application number: **17190787.6**

(22) Date of filing: **13.09.2017**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
MA MD

(72) Inventors:
• **ZENG, Lichang**
Ewing, NJ 08618 (US)
• **Ji, Zhiqiang**
Ewing, NJ 08618 (US)
• **BARRON, Edward**
Ewing, NJ 08618 (US)

(30) Priority: **14.09.2016 US 201662394431 P**
23.08.2017 US 201715684411

(74) Representative: **Hansen, Norbert**
Maiwald Patentanwalts GmbH
Elisenhof
Elisenstraße 3
80335 München (DE)

(71) Applicant: **Universal Display Corporation**
Ewing, New Jersey 08618 (US)

(54) **ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES**

(57) A composition comprising a first compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature is provided. The first compound includes at least one substituent R, where each of the at least one substituent R has the formula of: $---G^1-G^2$, where the dashed line denotes the bond through which R is attached in the first compound; G^1 is a non-aromatic cyclic or polycyclic group; G^2 is selected from aryl and heteroaryl; and G^1 and G^2 are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof. Organic light emitting devices, consumer products, and formulations containing the first compound are also provided.




FIGURE 1

Description

FIELD

5 **[0001]** The present invention relates to compounds for use as emitters, and devices, such as organic light emitting diodes, including the same.

BACKGROUND


10 **[0002]** Opto-electronic devices that make use of organic materials are becoming increasingly desirable for a number of reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting diodes/devices (OLEDs), organic phototransistors, organic photovoltaic cells, and organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials. For example, the wavelength at which an organic emissive layer emits light may generally be readily tuned with appropriate dopants.

15 **[0003]** OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting. Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

20 **[0004]** One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as "saturated" colors. In particular, these standards call for saturated red, green, and blue pixels. Alternatively the OLED can be designed to emit white light. In conventional liquid crystal displays emission from a white backlight is filtered using absorption filters to produce red, green and blue emission. The same technique can also be used with OLEDs. The white OLED can be either a single EML device or a stack structure. Color may be measured using CIE coordinates, which are well known to the art.

25 **[0005]** One example of a green emissive molecule is tris(2-phenylpyridine) iridium, denoted Ir(ppy)₃, which has the following structure:

30



35

[0006] In this, and later figures herein, we depict the dative bond from nitrogen to metal (here, Ir) as a straight line.

40 **[0007]** As used herein, the term "organic" includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. "Small molecule" refers to any organic material that is not a polymer, and "small molecules" may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the "small molecule" class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a "small molecule," and it is believed that all dendrimers currently used in the field of OLEDs are small molecules.

45 **[0008]** As used herein, "top" means furthest away from the substrate, while "bottom" means closest to the substrate. Where a first layer is described as "disposed over" a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is "in contact with" the second layer. For example, a cathode may be described as "disposed over" an anode, even though there are various organic layers in between.

50 **[0009]** As used herein, "solution processible" means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

55 **[0010]** A ligand may be referred to as "photoactive" when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as "ancillary" when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter

the properties of a photoactive ligand.

[0011] As used herein, and as would be generally understood by one skilled in the art, a first "Highest Occupied Molecular Orbital" (HOMO) or "Lowest Unoccupied Molecular Orbital" (LUMO) energy level is "greater than" or "higher than" a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A "higher" HOMO or LUMO energy level appears closer to the top of such a diagram than a "lower" HOMO or LUMO energy level.

[0012] As used herein, and as would be generally understood by one skilled in the art, a first work function is "greater than" or "higher than" a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a "higher" work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a "higher" work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

[0013] More details on OLEDs, and the definitions described above, can be found in US Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

SUMMARY

[0014] According to an embodiment, a composition comprising a first compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature is described. The first compound includes at least one substituent R, where each of the at least one substituent R has the formula of : $\text{---G}^1\text{---G}^2$, where:

the dashed line denotes the bond through which R is attached in the first compound

G^1 is a non-aromatic cyclic or polycyclic group;

G^2 is selected from aryl and heteroaryl; and

G^1 and G^2 are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0015] In another embodiment, an organic light emitting device (OLED) comprising an anode; a cathode; and an organic layer, disposed between the anode and the cathode is provided. The organic layer can include a compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature, where the first compound has at least one substituent R and each of the at least one substituent R has the formula of: $\text{---G}^1\text{---G}^2$. In the formula $\text{---G}^1\text{---G}^2$, the dashed line denotes the bond through which R is attached in the first compound; G^1 is a non-aromatic cyclic or polycyclic group; G^2 is selected from aryl and heteroaryl; and G^1 and G^2 are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof. In some embodiments, a consumer product containing an OLED as described herein is described.

[0016] According to another aspect, an emissive region in an OLED is disclosed where the emissive region comprises a first compound capable of functioning as a phosphorescent emitter in the emissive region at room temperature is described. The first compound includes at least one substituent R, where each of the at least one substituent R has the formula of: $\text{---G}^1\text{---G}^2$, as provided herein.

[0017] According to yet another embodiment, a formulation containing a compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature, where the first compound has at least one substituent R and each of the at least one substituent R has the formula of $\text{---G}^1\text{---G}^2$ is provided herein.

BRIEF DESCRIPTION OF THE DRAWINGS

[0018]

FIG. 1 shows an organic light emitting device.

FIG. 2 shows an inverted organic light emitting device that does not have a separate electron transport layer.

DETAILED DESCRIPTION

[0019] Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

[0020] The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

[0021] More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), are incorporated by reference in their entireties. Phosphorescence is described in more detail in US Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

[0022] FIG. 1 shows an organic light emitting device 100. The figures are not necessarily drawn to scale. Device 100 may include a substrate 110, an anode 115, a hole injection layer 120, a hole transport layer 125, an electron blocking layer 130, an emissive layer 135, a hole blocking layer 140, an electron transport layer 145, an electron injection layer 150, a protective layer 155, a cathode 160, and a barrier layer 170. Cathode 160 is a compound cathode having a first conductive layer 162 and a second conductive layer 164. Device 100 may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in US 7,279,704 at cols. 6-10, which are incorporated by reference.

[0023] More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entireties, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

[0024] FIG. 2 shows an inverted OLED 200. The device includes a substrate 210, a cathode 215, an emissive layer 220, a hole transport layer 225, and an anode 230. Device 200 may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device 200 has cathode 215 disposed under anode 230, device 200 may be referred to as an "inverted" OLED. Materials similar to those described with respect to device 100 may be used in the corresponding layers of device 200. FIG. 2 provides one example of how some layers may be omitted from the structure of device 100.

[0025] The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of non-limiting example, and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device 200, hole transport layer 225 transports holes and injects holes into emissive layer 220, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an "organic layer" disposed between a cathode and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

[0026] Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al, which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entireties.

[0027] Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. Pat. No. 7,431,968, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processibility than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

[0028] Devices fabricated in accordance with embodiments of the present invention may further optionally comprise a barrier layer. One purpose of the barrier layer is to protect the electrodes and organic layers from damaging exposure to harmful species in the environment including moisture, vapor and/or gases, etc. The barrier layer may be deposited over, under or next to a substrate, an electrode, or over any other parts of a device including an edge. The barrier layer may comprise a single layer, or multiple layers. The barrier layer may be formed by various known chemical vapor deposition techniques and may include compositions having a single phase as well as compositions having multiple phases. Any suitable material or combination of materials may be used for the barrier layer. The barrier layer may incorporate an inorganic or an organic compound or both. The preferred barrier layer comprises a mixture of a polymeric material and a non-polymeric material as described in U.S. Pat. No. 7,968,146, PCT Pat. Application Nos. PCT/US2007/023098 and PCT/US2009/042829, which are herein incorporated by reference in their entireties. To be considered a "mixture", the aforesaid polymeric and non-polymeric materials comprising the barrier layer should be deposited under the same reaction conditions and/or at the same time. The weight ratio of polymeric to non-polymeric material may be in the range of 95:5 to 5:95. The polymeric material and the non-polymeric material may be created from the same precursor material. In one example, the mixture of a polymeric material and a non-polymeric material consists essentially of polymeric silicon and inorganic silicon.

[0029] Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of electronic component modules (or units) that can be incorporated into a variety of electronic products or intermediate components. Examples of such electronic products or intermediate components include display screens, lighting devices such as discrete light source devices or lighting panels, etc. that can be utilized by the end-user product manufacturers. Such electronic component modules can optionally include the driving electronics and/or power source(s). Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. Such consumer products would include any kind of products that include one or more light source(s) and/or one or more of some type of visual displays. Some examples of such consumer products include flat panel displays, computer monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, laser printers, telephones, mobile phones, tablets, phablets, personal digital assistants (PDAs), wearable devices, laptop computers, digital cameras, camcorders, viewfinders, micro-displays (displays that are less than 2 inches diagonal), 3-D displays, virtual reality or augmented reality displays, vehicles, video walls comprising multiple displays tiled together, theater or stadium screen, and a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25 degrees C), but could be used outside this temperature range, for example, from -40 degree C to + 80 degree C.

[0030] The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

[0031] The term "halo," "halogen," or "halide" as used herein includes fluorine, chlorine, bromine, and iodine.

[0032] The term "alkyl" as used herein contemplates both straight and branched chain alkyl radicals. Preferred alkyl groups are those containing from one to fifteen carbon atoms and includes methyl, ethyl, propyl, 1-methylethyl, butyl, 1-methylpropyl, 2-methylpropyl, pentyl, 1-methylbutyl, 2-methylbutyl, 3-methylbutyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 2,2-dimethylpropyl, and the like. Additionally, the alkyl group may be optionally substituted.

[0033] The term "cycloalkyl" as used herein contemplates cyclic alkyl radicals. Preferred cycloalkyl groups are those containing 3 to 10 ring carbon atoms and includes cyclopropyl, cyclopentyl, cyclohexyl, adamantyl, and the like. Additionally, the cycloalkyl group may be optionally substituted.

[0034] The term "alkenyl" as used herein contemplates both straight and branched chain alkene radicals. Preferred alkenyl groups are those containing two to fifteen carbon atoms. Additionally, the alkenyl group may be optionally substituted.

[0035] The term "alkynyl" as used herein contemplates both straight and branched chain alkyne radicals. Preferred alkynyl groups are those containing two to fifteen carbon atoms. Additionally, the alkynyl group may be optionally substituted.

[0036] The terms "aralkyl" or "arylalkyl" as used herein are used interchangeably and contemplate an alkyl group that has as a substituent an aromatic group. Additionally, the aralkyl group may be optionally substituted.

[0037] The term "heterocyclic group" as used herein contemplates aromatic and non-aromatic cyclic radicals. Hetero-aromatic cyclic radicals also means heteroaryl. Preferred hetero-non-aromatic cyclic groups are those containing 3 to 7 ring atoms which includes at least one hetero atom, and includes cyclic amines such as morpholino, piperidino, pyrrolidino, and the like, and cyclic ethers, such as tetrahydrofuran, tetrahydropyran, and the like. Additionally, the heterocyclic group may be optionally substituted.

[0038] The term "aryl" or "aromatic group" as used herein contemplates single-ring groups and polycyclic ring systems. The polycyclic rings may have two or more rings in which two carbons are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is aromatic, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Preferred aryl groups are those containing six to thirty carbon atoms, preferably six to twenty carbon atoms, more preferably six to twelve carbon atoms. Especially preferred is an aryl group having six carbons, ten carbons or twelve carbons. Suitable aryl groups include phenyl, biphenyl, triphenyl, triphenylene, tetraphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene, preferably phenyl, biphenyl, triphenyl, triphenylene, fluorene, and naphthalene. Additionally, the aryl group may be optionally substituted.

[0039] The term "heteroaryl" as used herein contemplates single-ring hetero-aromatic groups that may include from one to five heteroatoms. The term heteroaryl also includes polycyclic hetero-aromatic systems having two or more rings in which two atoms are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is a heteroaryl, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Preferred heteroaryl groups are those containing three to thirty carbon atoms, preferably three to twenty carbon atoms, more preferably three to twelve carbon atoms. Suitable heteroaryl groups include dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine, preferably dibenzothiophene, dibenzofuran, dibenzoselenophene, carbazole, indolocarbazole, imidazole, pyridine, triazine, benzimidazole, 1,2-azaborine, 1,3-azaborine, 1,4-azaborine, borazine, and aza-analogs thereof. Additionally, the heteroaryl group may be optionally substituted.

[0040] The alkyl, cycloalkyl, alkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl may be unsubstituted or may be substituted with one or more substituents selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, cyclic amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0041] As used herein, "substituted" indicates that a substituent other than H is bonded to the relevant position, such as carbon. Thus, for example, where R¹ is mono-substituted, then one R¹ must be other than H. Similarly, where R¹ is di-substituted, then two of R¹ must be other than H. Similarly, where R¹ is unsubstituted, R¹ is hydrogen for all available positions.

[0042] The "aza" designation in the fragments described herein, i.e. aza-dibenzofuran, aza-dibenzothiophene, etc.

means that one or more of the C-H groups in the respective fragment can be replaced by a nitrogen atom, for example, and without any limitation, azatriphenylene encompasses both dibenzo[*f,h*]quinoxaline and dibenzo[*f,h*]quinoline. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.

[0043] It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

[0044] According to one embodiment, a composition comprising a first compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature is described. The first compound includes at least one substituent R, where each of the at least one substituent R has the formula of : $---G^1-G^2$, where:

the dashed line denotes the bond through which R is attached in the first compound

G^1 is a non-aromatic cyclic or polycyclic group;

G^2 is selected from aryl and heteroaryl; and


G^1 and G^2 are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof. In some embodiments, none of the at least one substituents R includes a metal selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, Au, and Cu.


[0045] In some embodiments, the aryl and heteroaryl groups of G^2 are selected from 5- and 6- membered rings, which may be. In some embodiments, the heteroatom of the heteroaryl ring is N. In some embodiments, the heteroaryl ring can include one N atom. In some embodiments, the heteroaryl ring can include two N atoms. In some embodiments, the heteroaryl ring can include up to three N atoms.


[0046] In some embodiments, the first compound includes at least one aromatic ring, and each of the at least one substituent R is directly bonded to one of the at least one aromatic rings. In some embodiments, each aromatic ring to which the at least one substituent R is directly bonded to is selected from the group consisting of phenyl, pyridine, pyrimidine, pyrazine, imidazole derived carbene, benzimidazole derived carbene, quinoline, aza-quinoline, isoquinoline, aza-isoquinoline, dibenzofuran, aza-dibenzofuran, imidazole, benzimidazole, aza-benzimidazole.

[0047] In some embodiments, the first compound is capable of emitting light from a triplet excited state to a ground singlet state at room temperature (e.g., $\sim 22^\circ\text{C}$). In some embodiments, the first compound is a metal coordination complex having a metal-carbon bond. In some embodiments, the metal is selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, Au, and Cu. In some embodiments, the metal is Ir, while the metal is Pt in other embodiments.

[0048] In some embodiments, the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$, where L^1 , L^2 and L^3 can be the same or different; x is 1, 2, or 3; y is 0, 1, or 2; z is 0, 1, or 2; and $x+y+z$ is the oxidation state of the metal M. In some embodiments, L^1 , L^2 and L^3 are each independently selected from the group consisting of:








where each one of X¹ to X¹⁷ is independently selected from the group consisting of carbon and nitrogen;
 where X is selected from the group consisting of BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR'R'', SiR'R'', and GeR'R'';
 where R' and R'' are optionally fused or joined to form a ring;
 where each R_a, R_b, R_c, and R_d may represent from mono substitution to the maximum possible number of substitution, or no substitution;
 where R', R'', R_a, R_b, R_c, and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;


where any two or more substituents of R_a , R_b , R_c , and R_d are optionally fused or joined to form a ring or form a multidentate ligand; and

where at least one of the R_a , R_b , R_c , and R_d includes at least one R.


[0049] In some embodiments, the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$. In some such embodiments, L^1 has the formula selected from the group consisting of:



and L^2 has the formula:





In some such embodiments, L^2 has the formula:




where R_e , R_f , R_h , and R_i are independently selected from group consisting of alkyl, cycloalkyl, aryl, and heteroaryl; where at least one of R_e , R_f , R_h , and R_i has at least two carbon atoms; and where R_g is selected from group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof. In some such embodiments, at least two of R_e , R_f , R_h , and R_i have at least two carbon atoms. In some such embodiments, at least three of R_e , R_f , R_h , and R_i has at least two carbon atoms. In some such embodiments, each of R_e , R_f , R_h , and R_i has at least two carbon atoms.


[0050] In some embodiments where the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$, L^1 and L^2 are different and each independently selected from the group consisting of:






[0051] In some embodiments where the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$, L^1 and L^2 are each independently selected from the group consisting of:







[0052] In some embodiments where the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$, the first compound has the formula of $Pt(L^1)_2$ or $Pt(L^1)(L^2)$. In some such embodiments, L^1 is connected to the other L^1 or L^2 to form a tetradentate ligand. In some such embodiments, at least one of R_a , R_b , R_c , and R_d includes an alkyl or cycloalkyl group that includes CD , CD_2 , or CD_3 , wherein D is deuterium.

[0053] In some embodiments, G^1 is selected from the group consisting of:







and





[0054] In some embodiments, each of the at least one R is selected from the group consisting of:







[0055] In some embodiments, the first compound is selected from the group consisting of:









Compound 18




Compound 19




Compound 20




Compound 21




Compound 22




Compound 23




Compound 24




Compound 25




Compound 26




Compound 27





Compound 28



Compound 29









5

10



Compound 69

,




Compound 70

,


15

20



Compound 71

,




Compound 72

,

25


30

35




Compound 73

,



Compound 74

,




Compound 75

,


40

45




Compound 76

,



Compound 77

,




Compound 78

,

50

and

55



Compound 79


[0056] In another embodiment, an organic light emitting device (OLED) comprising an anode; a cathode; and an organic layer, disposed between the anode and the cathode is described. In some embodiments, a consumer product containing an OLED as described herein is described. The organic layer can include a compound capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature, where the first compound has at least one substituent R and each of the at least one substituent R has the formula of: ---G¹-G². In the formula ---G¹-G², the dashed line denotes the bond through which R is attached in the first compound; G¹ is a non-aromatic cyclic or polycyclic group; G² is selected from aryl and heteroaryl; and G¹ and G² are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0057] In some embodiments, the OLED has one or more characteristics selected from the group consisting of being flexible, being rollable, being foldable, being stretchable, and being curved. In some embodiments, the OLED is transparent or semi-transparent. In some embodiments, the OLED further comprises a layer comprising carbon nanotubes.

[0058] In some embodiments, the OLED further comprises a layer comprising a delayed fluorescent emitter. In some embodiments, the OLED comprises a RGB pixel arrangement or white plus color filter pixel arrangement. In some embodiments, the OLED is a mobile device, a hand held device, or a wearable device. In some embodiments, the OLED is a display panel having less than 10 inch diagonal or 50 square inch area. In some embodiments, the OLED is a display panel having at least 10 inch diagonal or 50 square inch area. In some embodiments, the OLED is a lighting panel.

[0059] According to another aspect, an emissive region in an OLED is disclosed where the emissive region comprises a first compound capable of functioning as a phosphorescent emitter in the emissive region at room temperature is described. The first compound includes at least one substituent R, where each of the at least one substituent R has the formula of: ---G¹-G². In the formula ---G¹-G², the dashed line denotes the bond through which R is attached in the first compound; G¹ is a non-aromatic cyclic or polycyclic group; G² is selected from aryl and heteroaryl; and G¹ and G² are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0060] In some embodiments of the emissive region, the compound is an emissive dopant or a non-emissive dopant. In some embodiments, the emissive region also includes a host comprising at least one selected from the group consisting of metal complex, triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, aza-triphenylene, aza-carbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene. In some embodiments, the emissive region also includes a host is selected from the group consisting of:



5

10

15

20

25

30


35

40

45

50

55




and combinations thereof.

[0061] In some embodiments, the compound can be an emissive dopant. In some embodiments, the compound can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence), triplet-triplet annihilation, or combinations of these processes.

[0062] The OLED disclosed herein can be incorporated into one or more of a consumer product, an electronic component module, and a lighting panel. The organic layer can be an emissive layer and the compound can be an emissive dopant in some embodiments, while the compound can be a non-emissive dopant in other embodiments.

[0063] The organic layer can also include a host. In some embodiments, two or more hosts are preferred. In some embodiments, the hosts used maybe a) bipolar, b) electron transporting, c) hole transporting or d) wide band gap materials that play little role in charge transport. In some embodiments, the host can include a metal complex. The host can be a triphenylene containing benzo-fused thiophene or benzo-fused furan. Any substituent in the host can be an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv C-C_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , and $C_nH_{2n}-Ar_1$, or the host has no substitutions. In the preceding substituents n can range from 1 to 10; and Ar_1 and Ar_2 can be independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof. The host can be an inorganic compound. For example a Zn containing inorganic material e.g. ZnS.

[0064] The host can be a compound comprising at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene. The host can include a metal complex. The host can be, but is not limited to, a specific compound selected from the group consisting of:



5

10

15

20

25

30


35

40

45

50

55



and combinations thereof.

Additional information on possible hosts is provided below.


[0065] In yet another aspect of the present disclosure, a formulation that comprises the novel compound disclosed herein is described. The formulation can include one or more components selected from the group consisting of a solvent, a host, a hole injection material, hole transport material, and an electron transport layer material, disclosed herein.


COMBINATION WITH OTHER MATERIALS

[0066] The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination. Conductivity Dopants:


[0067] A charge transport layer can be doped with conductivity dopants to substantially alter its density of charge carriers, which will in turn alter its conductivity. The conductivity is increased by generating charge carriers in the matrix material, and depending on the type of dopant, a change in the Fermi level of the semiconductor may also be achieved. Hole-transporting layer can be doped by p-type conductivity dopants and n-type conductivity dopants are used in the electron-transporting layer.

[0068] Non-limiting examples of the conductivity dopants that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: EP01617493, EP01968131, EP2020694, EP2684932, US20050139810, US20070160905, US20090167167, US2010288362, WO06081780, WO2009003455, WO2009008277, WO2009011327, WO2014009310, US2007252140, US2015060804 and US2012146012.






and



HIL/HTL:

[0069] A hole injecting/transporting material to be used in the present invention is not particularly limited, and any compound may be used as long as the compound is typically used as a hole injecting/transporting material. Examples of the material include, but are not limited to: a phthalocyanine or porphyrin derivative; an aromatic amine derivative; an indolocarbazole derivative; a polymer containing fluorohydrocarbon; a polymer with conductivity dopants; a conducting polymer, such as PEDOT/PSS; a self-assembly monomer derived from compounds such as phosphonic acid and silane derivatives; a metal oxide derivative, such as MoO_x ; a p-type semiconducting organic compound, such as 1,4,5,8,9,12-Hexaazatriphenylenehexacarbonitrile; a metal complex, and a crosslinkable compounds.


[0070] Examples of aromatic amine derivatives used in HIL or HTL include, but not limit to the following general structures:



[0071] Each of Ar^1 to Ar^9 is selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quina-


zoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Each Ar may be unsubstituted or may be substituted by a substituent selected from the group consisting of deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0072] In one aspect, Ar¹ to Ar⁹ is independently selected from the group consisting of:



wherein k is an integer from 1 to 20; X^{101} to X^{108} is C (including CH) or N; Z^{101} is NAr^1 , O, or S; Ar^1 has the same group defined above.

[0073] Examples of metal complexes used in HIL or HTL include, but are not limited to the following general formula:



wherein Met is a metal, which can have an atomic weight greater than 40; ($Y^{101}-Y^{102}$) is a bidentate ligand, Y^{101} and Y^{102} are independently selected from C, N, O, P, and S; L^{101} is an ancillary ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and $k'+k''$ is the maximum number of ligands that may be attached to the metal.

[0074] In one aspect, ($Y^{101}-Y^{102}$) is a 2-phenylpyridine derivative. In another aspect, ($Y^{101}-Y^{102}$) is a carbene ligand. In another aspect, Met is selected from Ir, Pt, Os, and Zn. In a further aspect, the metal complex has a smallest oxidation potential in solution vs. Fc^+/Fc couple less than about 0.6 V.

[0075] Non-limiting examples of the HIL and HTL materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN102702075, DE102012005215, EP01624500, EP01698613, EP01806334, EP01930964, EP01972613, EP01997799, EP02011790, EP02055700, EP02055701, EP1725079, EP2085382, EP2660300, EP650955, JP07-073529, JP2005112765, JP2007091719, JP2008021687, JP2014-009196, KR20110088898, KR20130077473, TW201139402, US06517957, US20020158242, US20030162053, US20050123751, US20060182993, US20060240279, US20070145888, US20070181874, US20070278938, US20080014464, US20080091025, US20080106190, US20080124572, US20080145707, US20080220265, US20080233434, US20080303417, US2008107919, US20090115320, US20090167161, US2009066235, US2011007385, US20110163302, US2011240968, US2011278551, US2012205642, US2013241401, US20140117329, US2014183517, US5061569, US5639914, WO05075451, WO07125714, WO08023550, WO08023759, WO2009145016, WO2010061824, WO2011075644, WO2012177006, WO2013018530, WO2013039073, WO2013087142, WO2013118812, WO2013120577, WO2013157367, WO2013175747, WO2014002873, WO2014015935, WO2014015937, WO2014030872, WO2014030921, WO2014034791, WO2014104514, WO2014157018.

5

10

15

20

25

30





35

40


45

50


55



5




10




15

20




25



30


35

40




+ MoO_x



45



50




55





5
10
15
20
25
30
35
40
45
50
55



5

10

15

20

25

30


35





40





45





50

55










and



EBL:


[0076] An electron blocking layer (EBL) may be used to reduce the number of electrons and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies, and or longer lifetime, as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and/or higher triplet energy than the emitter closest to the EBL interface. In some embodiments, the EBL material has a higher LUMO (closer to the vacuum level) and or higher triplet energy than one or more of the hosts

closest to the EBL interface. In one aspect, the compound used in EBL contains the same molecule or the same functional groups used as one of the hosts described below.

Host:


[0077] The light emitting layer of the organic EL device of the present invention preferably contains at least a metal complex as light emitting material, and may contain a host material using the metal complex as a dopant material. Examples of the host material are not particularly limited, and any metal complexes or organic compounds may be used as long as the triplet energy of the host is larger than that of the dopant. Any host material may be used with any dopant so long as the triplet criteria is satisfied.

[0078] Examples of metal complexes used as host are preferred to have the following general formula:



wherein Met is a metal; (Y¹⁰³-Y¹⁰⁴) is a bidentate ligand, Y¹⁰³ and Y¹⁰⁴ are independently selected from C, N, O, P, and S; L¹⁰¹ is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.

[0079] In one aspect, the metal complexes are:





wherein (O-N) is a bidentate ligand, having metal coordinated to atoms O and N.

[0080] In another aspect, Met is selected from Ir and Pt. In a further aspect, (Y¹⁰³-Y¹⁰⁴) is a carbene ligand.

[0081] Examples of other organic compounds used as host are selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, tetraphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Each option within each group may be unsubstituted or may be substituted by a substituent selected from the group consisting of deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.


[0082] In one aspect, the host compound contains at least one of the following groups in the molecule:






wherein each of R¹⁰¹ to R¹⁰⁷ is independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, and when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. k is an integer from 0 to 20 or 1 to 20; k''' is an integer from 0 to 20. X¹⁰¹ to X¹⁰⁸ is selected from C (including CH) or N. Z¹⁰¹ and Z¹⁰² is selected from NR¹⁰¹, O, or S.


[0083] Non-limiting examples of the host materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: EP2034538, EP2034538A, EP2757608, JP2007254297, KR20100079458, KR20120088644, KR20120129733, KR20130115564, TW201329200, US20030175553, US20050238919, US20060280965, US20090017330, US20090030202, US20090167162, US20090302743, US20090309488, US20100012931, US20100084966, US20100187984, US2010187984, US2012075273, US2012126221, US2013009543, US2013105787, US2013175519, US2014001446, US20140183503, US20140225088, US2014034914, US7154114, WO2001039234, WO2004093207, WO2005014551, WO2005089025, WO2006072002, WO2006114966, WO2007063754, WO2008056746, WO2009003898, WO2009021126, WO2009063833, WO2009066778, WO2009066779, WO2009086028, WO2010056066, WO2010107244, WO2011081423, WO2011081431, WO2011086863, WO2012128298, WO2012133644, WO2012133649, WO2013024872, WO2013035275, WO2013081315, WO2013191404, WO2014142472,



5




10




15

20




25

30




35

40




45

50




55

5




,




,

10




,




,

15




,




,

20

25




,




,

30

35




,




,

40

45




,



,

50

55



5

10

15

20

25

30
















35


40

45

50

55







Additional Emitters:


[0084] One or more additional emitter dopants may be used in conjunction with the compound of the present disclosure. Examples of the additional emitter dopants are not particularly limited, and any compounds may be used as long as the compounds are typically used as emitter materials. Examples of suitable emitter materials include, but are not limited to, compounds which can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence), triplet-triplet annihilation, or combinations of these processes.

[0085] Non-limiting examples of the emitter materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN103694277, CN1696137, EB01238981, EP01239526, EP01961743, EP1239526, EP1244155, EP1642951, EP1647554, EP1841834, EP1841834B, EP2062907, EP2730583, JP2012074444, JP2013110263, JP4478555, KR1020090133652, KR20120032054, KR20130043460, TW201332980, US06699599, US06916554, US20010019782, US20020034656,


US20030068526, US20030072964, US20030138657, US20050123788, US20050244673, US2005123791,
 US2005260449, US20060008670, US20060065890, US20060127696, US20060134459, US20060134462,
 US20060202194, US20060251923, US20070034863, US20070087321, US20070103060, US20070111026,
 US20070190359, US20070231600, US2007034863, US2007104979, US2007104980, US2007138437,
 5 US2007224450, US2007278936, US20080020237, US20080233410, US20080261076, US20080297033,
 US200805851, US2008161567, US2008210930, US20090039776, US20090108737, US20090115322,
 US20090179555, US2009085476, US2009104472, US20100090591, US20100148663, US20100244004,
 US20100295032, US2010102716, US2010105902, US2010244004, US2010270916, US20110057559,
 US20110108822, US20110204333, US2011215710, US2011227049, US2011285275, US2012292601,
 10 US20130146848, US2013033172, US2013165653, US2013181190, US2013334521, US20140246656,
 US2014103305, US6303238, US6413656, US6653654, US6670645, US6687266, US6835469, US6921915,
 US7279704, US7332232, US7378162, US7534505, US7675228, US7728137, US7740957, US7759489, US7951947,
 US8067099, US8592586, US8871361, WO06081973, WO06121811, WO07018067, WO07108362, WO07115970,
 WO07115981, WO08035571, WO2002015645, WO2003040257, WO2005019373, WO2006056418, WO2008054584,
 15 WO2008078800, WO2008096609, WO2008101842, WO2009000673, WO2009050281, WO2009100991,
 WO2010028151, WO2010054731, WO2010086089, WO2010118029, WO2011044988, WO2011051404,
 WO2011107491, WO2012020327, WO2012163471, WO2013094620, WO2013107487, WO2013174471,
 WO2014007565, WO2014008982, WO2014023377, WO2014024131, WO2014031977, WO2014038456,
 WO2014112450.








5




10

15




20

25




30

35



40

45



50

55

5

10

15

20

25

30


35


40


45

50

55








20 HBL:

[0086] A hole blocking layer (HBL) may be used to reduce the number of holes and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies and/or longer lifetime as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED. In some embodiments, the HBL material has a lower HOMO (further from the vacuum level) and or higher triplet energy than the emitter closest to the HBL interface. In some embodiments, the HBL material has a lower HOMO (further from the vacuum level) and or higher triplet energy than one or more of the hosts closest to the HBL interface.

[0087] In one aspect, compound used in HBL contains the same molecule or the same functional groups used as host
30 described above.

[0088] In another aspect, compound used in HBL contains at least one of the following groups in the molecule:





40 wherein k is an integer from 1 to 20; L¹⁰¹ is an another ligand, k' is an integer from 1 to 3.

FTL:

45 **[0089]** Electron transport layer (ETL) may include a material capable of transporting electrons. Electron transport layer may be intrinsic (undoped), or doped. Doping may be used to enhance conductivity. Examples of the ETL material are not particularly limited, and any metal complexes or organic compounds may be used as long as they are typically used to transport electrons.


[0090] In one aspect, compound used in ETL contains at least one of the following groups in the molecule:






wherein R^{101} is selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. Ar^1 to Ar^3 has the similar definition as Ar's mentioned above. k is an integer from 1 to 20. X^{101} to X^{108} is selected from C (including CH) or N.





[0091] In another aspect, the metal complexes used in ETL contains, but not limit to the following general formula:



wherein (O-N) or (N-N) is a bidentate ligand, having metal coordinated to atoms O, N or N, N; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal.

[0092] Non-limiting examples of the ETL materials that may be used in an OLED in combination with materials disclosed herein are exemplified below together with references that disclose those materials: CN103508940, EP01602648, EP01734038, EP01956007, JP2004-022334, JP2005149918, JP2005-268199, KR0117693, KR20130108183, US20040036077, US20070104977, US2007018155, US20090101870, US20090115316, US20090140637, US20090179554, US2009218940, US2010108990, US2011156017, US2011210320, US2012193612, US2012214993, US2014014925, US2014014927, US20140284580, US6656612, US8415031, WO2003060956, WO2007111263, WO2009148269, WO2010067894, WO2010072300, WO2011074770, WO2011105373, WO2013079217, WO2013145667, WO2013180376, WO2014104499, WO2014104535,





5

10

15

20

25

30


35


40

45

50

55





Charge generation layer (CGL)


[0093] In tandem or stacked OLEDs, the CGL plays an essential role in the performance, which is composed of an n-doped layer and a p-doped layer for injection of electrons and holes, respectively. Electrons and holes are supplied from the CGL and electrodes. The consumed electrons and holes in the CGL are refilled by the electrons and holes injected from the cathode and anode, respectively; then, the bipolar currents reach a steady state gradually. Typical CGL materials include n and p conductivity dopants used in the transport layers.

[0094] In any above-mentioned compounds used in each layer of the OLED device, the hydrogen atoms can be partially or fully deuterated. Thus, any specifically listed substituent, such as, without limitation, methyl, phenyl, pyridyl, etc. may be undeuterated, partially deuterated, and fully deuterated versions thereof. Similarly, classes of substituents such as, without limitation, alkyl, aryl, cycloalkyl, heteroaryl, etc. also may be undeuterated, partially deuterated, and fully deuterated versions thereof.

EXPERIMENTAL

Synthesis of 2-phenyl-4-(4-(4-phenylcyclohexyl)phenyl)pyridine


[0095]



[0096] A solution of 2-phenyl-4-(4,4,5,5-tetramethyl-1,3,2-dioxaborolan-2-yl)pyridine (4.67 g, 16.62 mmol), 1-chloro-4-(4-phenylcyclohexyl)benzene (3 g, 11.08 mmol), tris(dibenzylideneacetone)dipalladium(0) (Pd_2dba_3) (0.406 g, 0.443 mmol), 2-dicyclohexylphosphino-2',4',6'-triisopropylbiphenyl (XPhos) (0.845 g, 1.773 mmol) and K_3PO_4 (7.05 g, 33.2 mmol) in tetrahydrofuran (THF) (20 ml) was degassed for 30 min. The mixture was heated to reflux for 40 h. After the reaction was cooled to room temperature ($\sim 22^\circ\text{C}$), it was extracted with ethyl acetate (EtOAc). The combined organic phase was washed with brine. The solvent was removed. The residue was coated on diatomaceous earth (e.g., Celite®) and purified on a silica gel column eluted with 3% EtOAc to give the product (2.9 g, 67%).

Synthesis of 2-phenyl-4-(4-(4-phenylcyclohexyl-1,4-d₂)phenyl)pyridine


[0097]



[0098] 2-phenyl-4-(4-(4-phenylcyclohexyl)phenyl)pyridine (2.9 g, 7.44 mmol) was dissolved in a mixture of ((methyl-d₃)sulfinyl)methane-d₃ (15.80 ml, 223 mmol) and THF (25 ml). The mixture was heated at 50°C . Potassium 2-methylpropan-2-olate (0.418 g, 3.72 mmol) was then added in one portion. The mixture was heated at 70°C for 16 hours. After the reaction was cooled to room temperature ($\sim 22^\circ\text{C}$), it was extracted with EtOAc. The combined organic phase was washed with brine. The solvent was removed. The residue was coated on diatomaceous earth (e.g., Celite®) and purified on a silica gel column eluted with 3% EtOAc in dichloromethane (DCM) to yield 16 g of 2-phenyl-4-(4-(4-phenylcyclohexyl-1,4-d₂)phenyl)pyridine (85%).

Synthesis of Compound 53

[0099]




[0100] In an oven-dried 100 mL two-necked round-bottomed flask, 2-phenyl-4-(4-(4-phenylcyclohexyl-1,4-d₂)phe-




nyl)pyridine (1.602 g, 4.09 mmol) and iridium timer (1.6 g, 2.046 mmol) were suspended in ethanol (25 ml) and dimethyl formamide (DMF) (25 ml) under nitrogen to give a clear solution. The mixture was stirred at 80 °C for 4 days under nitrogen, after which the suspension was cooled and a yellow solid obtained via filtration. The crude product was purified using column chromatography on silica gel, eluting with a gradient mixture of toluene/heptanes 8/2 (v/v) and then crystallized from toluene, to afford a yellow solid of compound 53 (0.5 g).

DEVICE EXAMPLES

[0101] All devices were fabricated by high vacuum (~ 10⁻⁷ Torr) thermal evaporation. The anode electrode was 80 nm of indium tin oxide (ITO). The cathode electrode consisted of 1 nm of LiF followed by 100 nm of Al. All devices were encapsulated with a glass lid sealed with an epoxy resin in a nitrogen glove box (<1 ppm of H₂O and O₂) immediately after fabrication, and a moisture getter was incorporated inside the package.

[0102] A set of device examples have organic stacks consisting of, sequentially from the ITO surface, 10 nm of LG101 (from LG Chem) as the hole injection layer (HIL), 50 nm of PPh-TPD as the hole-transport layer (HTL), 40 nm of emissive layer (EML), followed by 35 nm of aDBT-ADN with 35 wt% LiQ as the electron-transport layer (ETL). The EML has three components: 88 wt% of the EML being mixture of Hosts (60 wt% H-1 and 40 wt% H-2); and 12 wt% of the EML being the invented compound (compound 53) or comparative compound (CC-1 and CC-2) as the emitter. The chemical structures of the compounds used are shown below.





[0103] Table 1 below provides a summary of the device data recorded at 9000 nits for the device examples. All device data are reported relative to the results of Device C-1 using CC-1 as the emitter.

Table 1

Device ID	Dopant	Color	Voltage [V]	LE [cd/A]	PE [lm/W]	EQE (%)
Device 1	Compound 53	Yellow	0.98	1.23	1.25	1.19
Device C-1	CC-1	Yellow	1.00	1.00	1.00	1.00
Device C-2	CC-2	Yellow	1.04	0.95	0.90	0.93


[0104] The data in Table 1 show that the device using the inventive compound as the emitter achieves the same color but higher efficiency and lower voltage in comparison with the comparative examples. In comparison with the comparative compound (CC-1), the inventive example (compound 53) is further substituted with an example of the inventive substitution R, a cylcohexylphenyl moiety. The emission color remains the same, however, the device of the inventive compound (compound 53) achieves higher device efficiency likely due to the decreased aggregation and enhanced alignment of emitter in the device.




It is understood that the various embodiments described herein are by way of example only, and are not intended to limit the scope of the invention. For example, many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. It is understood that various theories as to why the invention works are not intended to be limiting.


Claims

1. A composition comprising a first compound;
 wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature;
 wherein the first compound has at least one substituent R;
 wherein each of the at least one substituent R has the formula of: ---G¹-G² ;
 wherein the dashed line denotes the bond through which R is attached in the first compound;
 wherein G¹ is a non-aromatic cyclic or polycyclic group;
 wherein G² is selected from aryl and heteroaryl; and
 wherein G¹ and G² are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.
2. The composition of claim 1, wherein the first compound has at least one aromatic ring;
 wherein each of the at least one substituent R is directly bonded to one of the at least one aromatic rings.
3. The composition of claim 1 or 2, wherein the first compound is capable of emitting light from a triplet excited state to a ground singlet state at room temperature.

4. The composition of any one of claims 1 to 3, wherein the first compound is a metal coordination complex having a metal-carbon bond.
5. The composition of claim 4, wherein the metal is Ir or Pt.
6. The composition of any one of claims 1 to 5, wherein the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$; wherein L^1 , L^2 and L^3 can be the same or different; wherein x is 1, 2, or 3; wherein y is 0, 1, or 2; wherein z is 0, 1, or 2; wherein $x+y+z$ is the oxidation state of the metal M ; wherein L^1 , L^2 and L^3 are each independently selected from the group consisting of:







wherein each X^1 to X^{17} are independently selected from the group consisting of carbon and nitrogen;

wherein X is selected from the group consisting of BR' , NR' , PR' , O , S , Se , $C=O$, $S=O$, SO_2 , $CR'R''$, $SiR'R''$, and $GeR'R''$;

wherein R' and R'' are optionally fused or joined to form a ring;


wherein each R_a , R_b , R_c , and R_d may represent from mono substitution to the maximum possible number of substitution, or no substitution;

wherein R' , R'' , R_a , R_b , R_c , and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof;


wherein any two or more substituents of R_a , R_b , R_c , and R_d are optionally fused or joined to form a ring or form a multidentate ligand; and

wherein at least one of the R_a , R_b , R_c , and R_d includes at least one R .


7. The composition of claim 6, wherein the first compound has the formula of $Ir(L^1)_2(L^2)$, and wherein L^1 has the formula selected from the group consisting of:





15 and
wherein L² has the formula:




- 25 8. The composition of claim 6, wherein the first compound has the formula of Ir(L¹)₂(L²), and wherein L¹ and L² are different and each independently selected from the group consisting of:







and



or


L¹ and L² are each independently selected from the group consisting of:






9. The composition of claim 6, wherein the first compound has the formula of $\text{Pt}(\text{L}^1)_2$ or $\text{Pt}(\text{L}^1)(\text{L}^2)$.


10. The composition of any one of claims 1 to 9, wherein G¹ is selected from the group consisting of:



and




11. The composition of claim 1, wherein the first compound is selected from the group consisting of:



5


10



15

20


25



30


35

40







45

50




55



5

10



,

Compound 37


,

Compound 38

,

15

20



,

Compound 40


,

Compound 41

,

25

30



,

Compound 43


,

Compound 44

,

35

40



,

Compound 46

,


Compound 47

,

45

50

55



,

Compound 49


,

Compound 50

,


5

10




Compound 51

,



Compound 52

,




Compound 53

,


15

20




Compound 54

,



Compound 55

,




Compound 56

,

25


30

35




Compound 57

,



Compound 58

,




Compound 59

,


40

45




Compound 60

,



Compound 61

,





Compound 62

,

50

55






12. An organic light-emitting device (OLED) comprising:


40 an anode;
 a cathode; and
 an organic layer, disposed between the anode and the cathode, comprising a first compound as defined in any one of the previous claims;
 wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature;
 45 wherein the first compound has at least one substituent R;
 wherein each of the at least one substituent R has the formula of : $---G^1-G^2$;
 wherein the dashed line denotes the bond through which R is attached in the first compound;
 wherein G^1 is a non-aromatic cyclic or polycyclic group;
 50 wherein G^2 is selected from aryl and heteroaryl; and
 wherein G^1 and G^2 are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

13. The OLED of claim 12, wherein the organic layer is an emissive layer and the compound is an emissive dopant or a non-emissive dopant.


14. The OLED of claim 20, wherein the organic layer further comprises a host, wherein the host is selected from the group consisting of:



5




10




15

20



25

30



35

and combinations thereof.

15. A consumer product comprising an organic light-emitting device, wherein the organic light-emitting device comprising:

40

an anode;

a cathode; and

an organic layer, disposed between the anode and the cathode, comprising a first compound as defined in any one of claims 1 to 11;

wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature;

45

wherein the first compound has at least one substituent R;

wherein each of the at least one substituent R has the formula of : ---G¹-G² ;

wherein the dashed line denotes the bond through which R is attached in the first compound;

wherein G¹ is a non-aromatic cyclic or polycyclic group;

wherein G² is selected from aryl and heteroaryl; and

50

wherein G¹ and G² are independently, optionally further substituted with a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, iso-nitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

55




FIGURE 1




FIGURE 2



EUROPEAN SEARCH REPORT

Application Number
EP 17 19 0787

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	GAETANO GIUFFRIDA ET AL: "Mono- and dinuclear complexes of ruthenium(II) and osmium(II) with a 3,5-bis(2-pyridyl)-1,2,4-triazole cyclohexyl-bridged spacer. Absorption spectra, luminescence properties, and electrochemical behavior", INORGANIC CHEMISTRY, vol. 32, no. 7, 1 March 1993 (1993-03-01), pages 1179-1183, XP55444007, EASTON, US ISSN: 0020-1669, DOI: 10.1021/ic00059a025 * page 1179 - page 1183 *	1-4,10	INV. H01L51/00 H01L51/50
A	-----	5-9, 11-15	
X	EP 2 933 259 A1 (UNIVERSAL DISPLAY CORP [US]) 21 October 2015 (2015-10-21) * page 70; claims 1-19 *	1-6,10, 12,13,15 7-9,11, 14	
A	-----		
X	L DE COLA: "Photoinduced energy and electron transfer processes in rigidly bridged dinuclear Ru/Os complexes", COORDINATION CHEMISTRY REVIEWS, vol. 177, no. 1, 1 October 1998 (1998-10-01), pages 301-346, XP55443856, NL ISSN: 0010-8545, DOI: 10.1016/S0010-8545(98)00198-2 * page 301 - page 340 *	1-4,10	TECHNICAL FIELDS SEARCHED (IPC) H01L
A	-----	5-9, 11-15	
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 24 January 2018	Examiner Königstein, C
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03/82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 17 19 0787

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-01-2018

10

15

20

25

30

35

40

45

50

55

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 2933259 A1	21-10-2015	CN 104974190 A	14-10-2015
		EP 2933259 A1	21-10-2015
		JP 2015221780 A	10-12-2015
		KR 20150118549 A	22-10-2015
		TW 201602118 A	16-01-2016
		US 2015295190 A1	15-10-2015

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5844363 A [0003] [0023]
- US 6303238 B [0003] [0023] [0085]
- US 5707745 A [0003] [0023] [0026]
- US 7279704 B [0013] [0021] [0022] [0085]
- US 4769292 A [0020]
- US 20030230980 A [0023]
- US 5703436 A [0023]
- US 6097147 A [0023]
- US 20040174116 A [0023]
- US 5247190 A, Friend [0026]
- US 6091195 A, Forrest [0026]
- US 5834893 A, Bulovic [0026]
- US 6013982 A [0027]
- US 6087196 A [0027]
- US 6337102 B, Forrest [0027]
- US 7431968 B [0027]
- US 6294398 B [0027]
- US 6468819 B [0027]
- US 7968146 B [0028]
- US 2007023098 W [0028]
- US 2009042829 W [0028]
- EP 01617493 A [0068]
- EP 01968131 A [0068]
- EP 2020694 A [0068]
- EP 2684932 A [0068]
- US 20050139810 A [0068]
- US 20070160905 A [0068]
- US 20090167167 A [0068]
- US 2010288362 A [0068]
- WO 06081780 A [0068]
- WO 2009003455 A [0068]
- WO 2009008277 A [0068]
- WO 2009011327 A [0068]
- WO 2014009310 A [0068]
- US 2007252140 A [0068]
- US 2015060804 A [0068]
- US 2012146012 A [0068]
- CN 102702075 [0075]
- DE 102012005215 [0075]
- EP 01624500 A [0075]
- EP 01698613 A [0075]
- EP 01806334 A [0075]
- EP 01930964 A [0075]
- EP 01972613 A [0075]
- EP 01997799 A [0075]
- EP 02011790 A [0075]
- EP 02055700 A [0075]
- EP 02055701 A [0075]
- EP 1725079 A [0075]
- EP 2085382 A [0075]
- EP 2660300 A [0075]
- EP 650955 A [0075]
- JP 7073529 A [0075]
- JP 2005112765 B [0075]
- JP 2007091719 B [0075]
- JP 2008021687 B [0075]
- JP 2014009196 A [0075]
- KR 20110088898 [0075]
- KR 20130077473 [0075]
- TW 201139402 [0075]
- US 06517957 B [0075]
- US 20020158242 A [0075]
- US 20030162053 A [0075]
- US 20050123751 A [0075]
- US 20060182993 A [0075]
- US 20060240279 A [0075]
- US 20070145888 A [0075]
- US 20070181874 A [0075]
- US 20070278938 A [0075]
- US 20080014464 A [0075]
- US 20080091025 A [0075]
- US 20080106190 A [0075]
- US 20080124572 A [0075]
- US 20080145707 A [0075]
- US 20080220265 A [0075]
- US 20080233434 A [0075]
- US 20080303417 A [0075]
- US 2008107919 A [0075]
- US 20090115320 A [0075]
- US 20090167161 A [0075]
- US 2009066235 A [0075]
- US 2011007385 A [0075]
- US 20110163302 A [0075]
- US 2011240968 A [0075]
- US 2011278551 A [0075]
- US 2012205642 A [0075]
- US 2013241401 A [0075]
- US 20140117329 A [0075]
- US 2014183517 A [0075]
- US 5061569 A [0075]
- US 5639914 A [0075]
- WO 05075451 A [0075]
- WO 07125714 A [0075]
- WO 08023550 A [0075]
- WO 08023759 A [0075]
- WO 2009145016 A [0075]
- WO 2010061824 A [0075]
- WO 2011075644 A [0075]

EP 3 297 051 A1

- WO 2012177006 A [0075]
- WO 2013018530 A [0075]
- WO 2013039073 A [0075]
- WO 2013087142 A [0075]
- WO 2013118812 A [0075]
- WO 2013120577 A [0075]
- WO 2013157367 A [0075]
- WO 2013175747 A [0075]
- WO 2014002873 A [0075]
- WO 2014015935 A [0075]
- WO 2014015937 A [0075]
- WO 2014030872 A [0075]
- WO 2014030921 A [0075]
- WO 2014034791 A [0075]
- WO 2014104514 A [0075]
- WO 2014157018 A [0075]
- EP 2034538 A [0083]
- EP 2757608 A [0083]
- JP 2007254297 B [0083]
- KR 20100079458 [0083]
- KR 20120088644 [0083]
- KR 20120129733 [0083]
- KR 20130115564 [0083]
- TW 201329200 [0083]
- US 20030175553 A [0083]
- US 20050238919 A [0083]
- US 20060280965 A [0083]
- US 20090017330 A [0083]
- US 20090030202 A [0083]
- US 20090167162 A [0083]
- US 20090302743 A [0083]
- US 20090309488 A [0083]
- US 20100012931 A [0083]
- US 20100084966 A [0083]
- US 20100187984 A [0083]
- US 2010187984 A [0083]
- US 2012075273 A [0083]
- US 2012126221 A [0083]
- US 2013009543 A [0083]
- US 2013105787 A [0083]
- US 2013175519 A [0083]
- US 2014001446 A [0083]
- US 20140183503 A [0083]
- US 20140225088 A [0083]
- US 2014034914 A [0083]
- US 7154114 B [0083]
- WO 2001039234 A [0083]
- WO 2004093207 A [0083]
- WO 2005014551 A [0083]
- WO 2005089025 A [0083]
- WO 2006072002 A [0083]
- WO 2006114966 A [0083]
- WO 2007063754 A [0083]
- WO 2008056746 A [0083]
- WO 2009003898 A [0083]
- WO 2009021126 A [0083]
- WO 2009063833 A [0083]
- WO 2009066778 A [0083]
- WO 2009066779 A [0083]
- WO 2009086028 A [0083]
- WO 2010056066 A [0083]
- WO 2010107244 A [0083]
- WO 2011081423 A [0083]
- WO 2011081431 A [0083]
- WO 2011086863 A [0083]
- WO 2012128298 A [0083]
- WO 2012133644 A [0083]
- WO 2012133649 A [0083]
- WO 2013024872 A [0083]
- WO 2013035275 A [0083]
- WO 2013081315 A [0083]
- WO 2013191404 A [0083]
- WO 2014142472 A [0083]
- CN 103694277 [0085]
- CN 1696137 [0085]
- EP 01239526 A [0085]
- EP 01961743 A [0085]
- EP 1239526 A [0085]
- EP 1244155 A [0085]
- EP 1642951 A [0085]
- EP 1647554 A [0085]
- EP 1841834 A [0085]
- EP 1841834 B [0085]
- EP 2062907 A [0085]
- EP 2730583 A [0085]
- JP 2012074444 B [0085]
- JP 2013110263 B [0085]
- JP 4478555 B [0085]
- KR 1020090133652 [0085]
- KR 20120032054 [0085]
- KR 20130043460 [0085]
- TW 201332980 [0085]
- US 06699599 B [0085]
- US 06916554 B [0085]
- US 20010019782 A [0085]
- US 20020034656 A [0085]
- US 20030068526 A [0085]
- US 20030072964 A [0085]
- US 20030138657 A [0085]
- US 20050123788 A [0085]
- US 20050244673 A [0085]
- US 2005123791 A [0085]
- US 2005260449 A [0085]
- US 20060008670 A [0085]
- US 20060065890 A [0085]
- US 20060127696 A [0085]
- US 20060134459 A [0085]
- US 20060134462 A [0085]
- US 20060202194 A [0085]
- US 20060251923 A [0085]
- US 20070034863 A [0085]
- US 20070087321 A [0085]
- US 20070103060 A [0085]
- US 20070111026 A [0085]
- US 20070190359 A [0085]
- US 20070231600 A [0085]

EP 3 297 051 A1

- US 2007034863 A [0085]
- US 2007104979 A [0085]
- US 2007104980 A [0085]
- US 2007138437 A [0085]
- US 2007224450 A [0085]
- US 2007278936 A [0085]
- US 20080020237 A [0085]
- US 20080233410 A [0085]
- US 20080261076 A [0085]
- US 20080297033 A [0085]
- US 200805851 B [0085]
- US 2008161567 A [0085]
- US 2008210930 A [0085]
- US 20090039776 A [0085]
- US 20090108737 A [0085]
- US 20090115322 A [0085]
- US 20090179555 A [0085]
- US 2009085476 A [0085]
- US 2009104472 A [0085]
- US 20100090591 A [0085]
- US 20100148663 A [0085]
- US 20100244004 A [0085]
- US 20100295032 A [0085]
- US 2010102716 A [0085]
- US 2010105902 A [0085]
- US 2010244004 A [0085]
- US 2010270916 A [0085]
- US 20110057559 A [0085]
- US 20110108822 A [0085]
- US 20110204333 A [0085]
- US 2011215710 A [0085]
- US 2011227049 A [0085]
- US 2011285275 A [0085]
- US 2012292601 A [0085]
- US 20130146848 A [0085]
- US 2013033172 A [0085]
- US 2013165653 A [0085]
- US 2013181190 A [0085]
- US 2013334521 A [0085]
- US 20140246656 A [0085]
- US 2014103305 A [0085]
- US 6413656 B [0085]
- US 6653654 B [0085]
- US 6670645 B [0085]
- US 6687266 B [0085]
- US 6835469 B [0085]
- US 6921915 B [0085]
- US 7332232 B [0085]
- US 7378162 B [0085]
- US 7534505 B [0085]
- US 7675228 B [0085]
- US 7728137 B [0085]
- US 7740957 B [0085]
- US 7759489 B [0085]
- US 7951947 B [0085]
- US 8067099 B [0085]
- US 8592586 B [0085]
- US 8871361 B [0085]
- WO 06081973 A [0085]
- WO 06121811 A [0085]
- WO 07018067 A [0085]
- WO 07108362 A [0085]
- WO 07115970 A [0085]
- WO 07115981 A [0085]
- WO 08035571 A [0085]
- WO 2002015645 A [0085]
- WO 2003040257 A [0085]
- WO 2005019373 A [0085]
- WO 2006056418 A [0085]
- WO 2008054584 A [0085]
- WO 2008078800 A [0085]
- WO 2008096609 A [0085]
- WO 2008101842 A [0085]
- WO 2009000673 A [0085]
- WO 2009050281 A [0085]
- WO 2009100991 A [0085]
- WO 2010028151 A [0085]
- WO 2010054731 A [0085]
- WO 2010086089 A [0085]
- WO 2010118029 A [0085]
- WO 2011044988 A [0085]
- WO 2011051404 A [0085]
- WO 2011107491 A [0085]
- WO 2012020327 A [0085]
- WO 2012163471 A [0085]
- WO 2013094620 A [0085]
- WO 2013107487 A [0085]
- WO 2013174471 A [0085]
- WO 2014007565 A [0085]
- WO 2014008982 A [0085]
- WO 2014023377 A [0085]
- WO 2014024131 A [0085]
- WO 2014031977 A [0085]
- WO 2014038456 A [0085]
- WO 2014112450 A [0085]
- CN 103508940 [0092]
- EP 01602648 A [0092]
- EP 01734038 A [0092]
- EP 01956007 A [0092]
- JP 2004022334 A [0092]
- JP 2005149918 B [0092]
- JP 2005268199 A [0092]
- KR 0117693 [0092]
- KR 20130108183 [0092]
- US 20040036077 A [0092]
- US 20070104977 A [0092]
- US 2007018155 A [0092]
- US 20090101870 A [0092]
- US 20090115316 A [0092]
- US 20090140637 A [0092]
- US 20090179554 A [0092]
- US 2009218940 A [0092]
- US 2010108990 A [0092]
- US 2011156017 A [0092]
- US 2011210320 A [0092]
- US 2012193612 A [0092]

EP 3 297 051 A1

- US 2012214993 A [0092]
- US 2014014925 A [0092]
- US 2014014927 A [0092]
- US 20140284580 A [0092]
- US 6656612 B [0092]
- US 8415031 B [0092]
- WO 2003060956 A [0092]
- WO 2007111263 A [0092]
- WO 2009148269 A [0092]
- WO 2010067894 A [0092]
- WO 2010072300 A [0092]
- WO 2011074770 A [0092]
- WO 2011105373 A [0092]
- WO 2013079217 A [0092]
- WO 2013145667 A [0092]
- WO 2013180376 A [0092]
- WO 2014104499 A [0092]
- WO 2014104535 A [0092]

Non-patent literature cited in the description

- **BALDO et al.** Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices. *Nature*, 1998, vol. 395, 151-154 [0021]
- **BALDO et al.** Very high-efficiency green organic light-emitting devices based on electrophosphorescence. *Appl. Phys. Lett.*, 1999, vol. 75 (3), 4-6 [0021]

专利名称(译)	有机电致发光材料和器件		
公开(公告)号	EP3297051A1	公开(公告)日	2018-03-21
申请号	EP2017190787	申请日	2017-09-13
[标]申请(专利权)人(译)	环球展览公司		
申请(专利权)人(译)	通用显示器公司		
当前申请(专利权)人(译)	通用显示器公司		
[标]发明人	ZENG LICHANG JI ZHIQIANG BARRON EDWARD		
发明人	ZENG, LICHANG JI, ZHIQIANG BARRON, EDWARD		
IPC分类号	H01L51/00 H01L51/50		
CPC分类号	C07F15/0033 C09K11/06 C09K2211/185 H01L51/0085 H01L51/5012 H01L51/5024 H01L2251/30 H01L2251/50 H01L51/5016 H01L51/0062 H01L51/0072 H01L51/0074 H01L51/0094 H01L51/50 H01L2251/5376		
代理机构(译)	汉森NORBERT		
优先权	62/394431 2016-09-14 US 15/684411 2017-08-23 US		
外部链接	Espacenet		

摘要(译)

本发明提供一种组合物，其包含在室温下能够在有机发光器件中用作磷光发光体的第一化合物。第一化合物包括至少一个取代基R，其中至少一个取代基R中的每一个具有下式：--- G1-G2，其中虚线表示R在第一化合物中连接的键；G1是非芳香族环状或多环状基团；G2选自芳基和杂芳基；并且G1和G2独立地，任选地进一步被选自氢，氘，卤化物，烷基，环烷基，杂烷基，芳烷基，烷氧基，芳氧基，氨基，甲硅烷基，烯基，环烯基，杂烯基，炔基，芳基的取代基取代。，杂芳基，酰基，羰基，羧酸，酯，腈，异腈，硫烷基，亚磺酰基，磺酰基，膦基及其组合。还提供了有机发光器件，消费产品和含有第一化合物的配方。




FIGURE 1