



(11) **EP 2 179 459 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
08.04.2015 Bulletin 2015/15

(51) Int Cl.:
H01L 51/00 ^(2006.01) **H01L 51/52** ^(2006.01)

(21) Application number: **08794648.9**

(86) International application number:
PCT/US2008/008909

(22) Date of filing: **23.07.2008**

(87) International publication number:
WO 2009/014699 (29.01.2009 Gazette 2009/05)

(54) **PREVENTING STRESS TRANSFER IN OLED DISPLAY COMPONENTS**

VERHINDERUNG VON MECHANISCHER SPANNUNGSÜBERTRAGUNG IN ORGANISCHEN
ANZEIGEBAUERELEMENTEN

EMPECHER UN TRANSFERT DE CONTRAINTE DANS DES COMPOSANTS D’AFFICHAGE A
DIODE ELECTROLUMINESCENTE ORGANIQUE

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT
RO SE SI SK TR**

- **RICKS, Michele Lee**
Rochester, New York 14650 (US)
- **PALONE, Thomas William**
Rochester, New York 14650 (US)

(30) Priority: **25.07.2007 US 782797**

(74) Representative: **Wibbelmann, Jobst**
Wuesthoff & Wuesthoff
Patent- und Rechtsanwälte
Schweigerstrasse 2
81541 München (DE)

(43) Date of publication of application:
28.04.2010 Bulletin 2010/17

(60) Divisional application:
12004090.2 / 2 498 317

(56) References cited:
EP-A- 1 448 026 JP-A- 11 329 716
JP-A- 11 339 954 JP-A- 2001 118 674
US-A1- 2001 013 756

(73) Proprietor: **Global OLED Technology LLC**
Herndon, VA 20171 (US)

(72) Inventors:
• **BOROSON, Michael Louis**
Rochester, New York 14650 (US)

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 179 459 B1

Description**FIELD OF THE INVENTION**

5 **[0001]** The present invention relates to OLED displays and more particularly to providing moisture protection for the OLED in the display.

BACKGROUND OF THE INVENTION

10 **[0002]** An organic light-emitting diode device, also called an OLED device, commonly includes a substrate, an anode, a hole-transporting layer made of an organic compound, an organic luminescent layer with suitable dopants, an organic electron-transporting layer, and a cathode. OLED devices are attractive because of their low driving voltage, high luminance, wide-angle viewing, and capability for full-color flat emission displays. Tang et al. described this multilayer OLED device in their U.S. Patents 4,769,292 and 4,885,211.

15 **[0003]** A common problem with OLED displays is sensitivity to moisture. They can be particular highly moisture-sensitive electronic devices, and require humidity control to levels below about 1000 ppm and some require humidity control below even 100 ppm. Often, an encapsulation container encloses the OLED device and is secured to the substrate to form an enclosure. Desiccant material is formed on the inside surface of the enclosure to protect the OLED from moisture. A problem with this arrangement is that stress can be transferred between the substrate and the encapsulation container thereby causing mechanical damage to either or either of such elements (e.g. cracking) or to the adhesive used to secure the substrate and encapsulation container (e.g. delamination or cracking). This is particularly a problem as the OLED displays become larger and can flex during handling. This can also be a problem when the substrate and the encapsulation container comprise different materials with different coefficients of expansion.

25 **[0004]** Japanese patent application JP 11339954 A discloses an organic EL display device comprising a glass substrate, a first electrode layer, an organic EL luminous layer and a second electrode layer formed on a glass substrate. A sealing member is formed into a box shape from the glass substrate which is connected to the glass substrate by a sealant. An opening is provided at part of the upper face of the sealing member and a bag-shaped expansion section is airtightly connected to the edge section of the opening.

30 **[0005]** Japanese patent application JP 11329716 A discloses a gas sealing display device comprising an airtight member which is constituted with a bellows cylinder functioning as an expanding and contracting part capable of expanding and contracting in the thickness direction of a base plate and flat plate-shaped cover plate integrally installed at one end of the bellows cylinder.

35 **[0006]** Japanese patent application JP 2001118674 A discloses an organic EL display device which has an EL element deposited on a flexible film transparent substrate and a flexible film sealant is adhered to the transparent substrate so as to cover and seal the EL element.

[0007] US patent application US 2001/0013756 A1 discloses a hermetic encapsulation package in which a sealing cap for accommodating an organic EL element is bonded to a support substrate with ultraviolet curing resin to form a sealed space defined by the sealing cap and the support substrate.

40 **[0008]** European patent application EP 1 448 026 A1 discloses a light emitting apparatus for plain indicator lamps comprising a moisture impermeable substrate having a warped configuration, an EL light emitting laminated body formed on the inner surface of the warped substrate and a moisture impermeable opposing substrate joined in an impermeable manner at the edge portion of the warped substrate.

SUMMARY OF THE INVENTION

45 **[0009]** It is therefore an object of the present invention to provide an OLED display sealed against moisture that it reduces damage to a substrate and a perimeter seal.

[0010] This object is achieved by an OLED display according to claim 1.

50 **[0011]** It is an advantage of this invention that it reduces damage to the substrate, to an encapsulation container, and to a perimeter seal joining the substrate and encapsulation container in an OLED display. It is a further advantage of this invention that it permits the use of materials with different expansion characteristics for the substrate and encapsulation container. It is a further advantage of this invention that it reduces damage to the OLED display caused by other types of stress, such as flexing. It is a further advantage of this invention that the reduction in damage will increase yield in manufacturing and reduce the cost of OLED displays.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012]

FIG. 1 shows a cross-sectional view of one example of an encapsulated OLED display including compliant regions
 FIG. 2 shows a top view of an encapsulation container as used in FIG. 1;
 FIG. 3 shows a cross-sectional view of another example of an encapsulation container
 FIG. 4 shows a cross-sectional view of an encapsulated OLED display including compliant regions according to this invention; and
 FIG. 5 shows a cross-sectional view of another example of an encapsulated OLED display including compliant regions.

[0013] Since device feature dimensions such as layer thicknesses are frequently in sub-micrometer ranges, the drawings are scaled for ease of visualization rather than dimensional accuracy.

DETAILED DESCRIPTION OF THE INVENTION

[0014] The term "OLED device" or "organic light-emitting display" is used in its art-recognized meaning of a display device comprising organic light-emitting diodes as pixels. The term "bottom-emitting" refers to display devices that emit light and are viewed through the substrate upon which they are based. The term "top-emitting" refers to display devices in which light is primarily not emitted through the substrate but opposite to the substrate, and are viewed through the side opposite to the substrate. The term "desiccant" is employed to designate organic or inorganic materials used to physically or chemically absorb or react with moisture that would otherwise damage the highly moisture-sensitive electronic devices.

[0015] Turning now to FIG. 1, there is shown a cross-sectional view of one example of an encapsulated OLED display including compliant regions, not forming part of the present invention. OLED display **100** is formed over substrate **10**. OLED display **100** includes an OLED **25** disposed over substrate **10** and having organic layers **30** disposed between two spaced-apart electrodes **20** and **40**. An encapsulation container **70** is disposed over OLED **25** and is fixed to substrate **10** by perimeter seal **50**, providing enclosure **55**. A desiccant **60** can be located in enclosure **55** to protect the OLED display from moisture incursion around or through perimeter seal **50**. Encapsulation container **70** includes one or more compliant regions **75** that can flex, compress, or expand under stress. The compressing, expanding, or flexing of compliant regions **75** under stress reduces the stress transferred from encapsulation container **70** to substrate **10** or to perimeter seal **50**, and from substrate **10** to encapsulation container **70** or to perimeter seal **50**. Encapsulation container **70** can also include sealing base **85**, which is a region designed to form a seal with perimeter seal **50**, and a fitting region **80**, which is designed to shape the encapsulation container to fit over OLED **25**. Flexing, compressing, or expanding of the compliant regions also reduces the stress transferred from the inner portion of the encapsulation container **70** to the seal base **85**. The compliant regions can be formed by any way that provides for sufficient flexing, compressing, or expanding. The compliant regions can comprise multiple bends in a thin flexible material such as metal foils, polymer films, or rubbers to form accordion-like regions. Alternately, solid compliant materials such as polymers can form the compliant regions or rubbers that have sufficiently low modulus. These solid compliant materials can be a single material or composite materials including other organic or inorganic components.

[0016] Encapsulation container **70** can comprise an organic solid, an inorganic solid, or a combination of organic and inorganic solids. Encapsulation container **70** can be flexible, or can include a flexible portion and a rigid portion, and can be processed as separate individual pieces, such as sheets or wafers, or as continuous rolls. Typical encapsulation container materials include glass, plastic, metal, ceramic, semiconductor, metal oxide, metal nitride, metal sulfide, semiconductor oxide, semiconductor nitride, semiconductor sulfide, carbon or combinations thereof. Encapsulation container **70**, or a portion thereof, can be a flexible foil, e.g. a metal foil such as aluminum foil, a metal-coated polymer sheet, or a multi-layer laminated foil comprising a polymer layer, a graphite layer, and a layer of aluminum foil. One example of the latter material is eGraf, which is commercially available from GrafTech. In one desirable example, encapsulation container **70** is a metal foil. The portion of encapsulation container **70** over organic layers **30** is transparent if OLED display **100** is top-emitting, but portions that cover non-emitting regions can be opaque. Encapsulation container **70** can be a homogeneous mixture of materials, a composite of materials, multiple layers of materials, or an assembly of multiple materials such as a rigid transparent window with an opaque frame and flexible foil in the compliant regions.

[0017] Turning now to FIG. 2, there is shown a top view of an encapsulation container **70** as used in FIG. 1. Sealing base **85** encircles the entire encapsulation container, to provide a complete seal around the OLED display. To reduce stress transfer, compliant region **75** can be provided inside sealing base **85**. All or part of encapsulation container **70** can be formed of a flexible foil. Encapsulation container **70** is desirably formed of flexible foil in compliant region **75**, and the compliant regions can be provided by spaced-apart bends in the foil. Other regions of encapsulation container **70** can be flexible or rigid. Encapsulation container **70** can also include a rigid portion **90** disposed between or within the compliant regions. Rigid portion **90** can be transparent, e.g. for viewing a top-emitting OLED display.

[0018] Turning now to FIG. 3, there is shown a cross-sectional view of another example of an encapsulation container. Encapsulation container **150** has a compliant region **160** on the vertical portions of the encapsulation container.

[0019] Turning now to FIG. 4, there is shown a cross-sectional view of an encapsulated OLED display including compliant regions according to this invention. OLED display **200** includes a substrate **210** that is formed of a flexible material. The substrate **210** can be plastic with a moisture barrier coating or can be a transparent portion of glass or plastic with compliant regions and seal regions of metal foil, plastic, rubber, or other compliant materials. For top emitting OLED devices the substrate **210** can be opaque and can be formed of a metal foil or rigid metal with compliant regions of metal foil, plastic, rubber, or other compliant materials. Substrate **210** can include compliant regions **230** that are provided by spaced-apart bends in the substrate, by solid compliant materials as discussed in FIG. 1, or by flexures formed in the substrate as described below in FIG. 5. Encapsulation container **240** can be a rigid material or can include compliant regions as described above.

[0020] Turning now to FIG. 5, there is shown a cross-sectional view of another encapsulated OLED display **250** including compliant regions **270**, not forming part of the present invention. In this example the compliant regions are formed by flexures that comprise only one or two bends in a thin flexible material such as metal foils, polymer films, or rubbers. The flexure formed by the combination of the material and the geometry must be capable of reducing the stress transferred between encapsulation container **260** and substrate **10** through the perimeter seal.

[0021] A key design parameter for the flexure-type compliant regions of FIG. 5 and the compliant regions of FIG. 1, FIG. 2, FIG. 3, and FIG. 4 relates to the level of stress transferred between the substrate and the encapsulation container through the perimeter seal. The level of stress transferred due to thermal expansion or contraction, due to flexing of the OLED display, or due to any other forces applied to the substrate, encapsulation container, or the perimeter seal must remain less than the cohesive and adhesive strengths of the substrate, encapsulation container, and perimeter seal. Delamination of the encapsulation container from the perimeter seal or the substrate from the perimeter seal is particularly sensitive to peel forces between the perimeter seal and either the encapsulation container or the substrate. To insure robust encapsulation of the OLED display, the compliant regions must be designed to maintain peel stress levels below the peel strength of both the perimeter seal to substrate and the perimeter seal to encapsulation container. The specific level of compliance depends on the material choices for the substrate, encapsulation container, and perimeter seal, as well as the level of stress to which the OLED display will be exposed during the manufacturing and use of the display.

[0022] Perimeter seal **50** can be organic, inorganic, or a combination of organic and inorganic. The organic perimeter seal material can include epoxies, polyurethanes, acrylates, silicones, polyamides, polyolefins, and polyesters, or combinations thereof. The inorganic perimeter seal material can include glass, ceramic, metal, semiconductor, metal oxide, semiconductor oxide, and metal solder, or combinations thereof. The perimeter seal can be bonded between the substrate and the encapsulation container in a bonding step accomplished by pressing, by melting and cooling, by reaction curing, or by a combination thereof. Typical materials bonded by pressure include pressure-sensitive adhesives. Typical materials bonded by melting and cooling include glass; hot melt adhesives such as polyolefins, polyesters, polyamides, or combinations thereof; or inorganic solders such as indium, tin, lead, silver, gold, or combinations thereof. Typical reaction curing methods include reactions resulting from heat, radiation such as UV radiation, mixing of two or more components, removal of ambient oxygen, or combinations thereof. Typical materials bonded by reaction curing include acrylates, epoxies, polyurethanes, silicones, or combinations thereof. Other inorganic materials typically used in adhesive materials include glass, ceramic, metal, semiconductor, metal oxide, semiconductor oxide, or combinations thereof.

[0023] Stress in the OLED display can come from several sources. The substrate or the encapsulation container, or both, can flex. The stress from one (the substrate or the encapsulation container) can be transferred to the other through one or more parts of the perimeter seal. Alternatively, the temperature of the OLED display can change, either through changes in the environment of the OLED display, or through heating and cooling of the display itself by its own functioning. Such heating and cooling will cause expansion and contraction of the materials comprising the display. If the substrate and encapsulation container are formed from different materials with different coefficients of expansion, the different expansion rates can cause stress to be placed upon the perimeter seal, or cause stress to be transferred between the substrate and encapsulation container through the perimeter seal. Such stress can break the perimeter seal, or crack or break a fragile part of the OLED display, e.g. a glass substrate. Compliant regions that flex, expand, or compress under the stress can reduce the stress transferred to or through the perimeter seal.

[0024] The substrate can be an organic solid, an inorganic solid, or a combination of organic and inorganic solids. The substrate is flexible and can be processed as separate individual pieces, such as sheets or wafers, or as a continuous roll. If the substrate is flexible, it is meant that it is not rigid and provides no structural benefit, e.g. glass of 1 mm thickness or less. Typical substrate materials include glass, plastic, metal, ceramic, semiconductor, metal oxide, metal nitride, metal sulfide, semiconductor oxide, semiconductor nitride, semiconductor sulfide, carbon, or combinations thereof, or any other materials commonly used in the formation of OLED devices, which can be either passive-matrix devices or active-matrix devices. The substrate can be a homogeneous mixture of materials, a composite of materials, or multiple layers of materials. The substrate can be an OLED substrate, that is a substrate commonly used for preparing OLED devices, e.g. active-matrix low-temperature polysilicon or amorphous-silicon TFT substrate. For a top-emitting application, where the EL emission is viewed through the top electrode, the transmissive characteristic of the bottom support is immaterial, and therefore can be light transmissive, light absorbing or light reflective. For a bottom-emitting application,

where the EL emission is viewed through the bottom electrode and substrate, the substrate can be any transmissive material including, but not limited to, glass and plastic.

[0025] OLED devices that can be used in this invention have been well described in the art, and OLED display **100** can include layers commonly used for such devices. A bottom electrode **20** is formed over OLED substrate **10** and is most commonly configured as an anode, although the practice of this invention is not limited to this configuration. Example conductors for this application include, but are not limited to, indium-tin oxide, indium-zinc oxide, gold, iridium, molybdenum, palladium, platinum, aluminum or silver. If the device is bottom-emitting, the electrode must be transparent or nearly transparent. For such applications, metals must be thin (preferably less than 25 nm) or one must use transparent conductive oxides (e.g. indium-tin oxide, indium-zinc oxide), or a combination of these materials. Any suitable process such as evaporation, sputtering, chemical vapor deposition, or electrochemical deposition can deposit desired anode materials. Anode materials can be patterned using well-known photolithographic processes.

[0026] Organic layers **30** comprise several layers as described in the art. While not always necessary, it is often useful that a hole-transporting layer be formed and disposed over the anode. Any suitable process such as evaporation, sputtering, chemical vapor deposition, electrochemical deposition, thermal transfer, or laser thermal transfer from a donor material can deposit desired hole-transporting materials. Hole-transporting materials useful in hole-transporting layers are well known to include compounds such as an aromatic tertiary amine, where the latter is understood to be a compound containing at least one trivalent nitrogen atom that is bonded only to carbon atoms, at least one of which is a member of an aromatic ring. In one form the aromatic tertiary amine can be an arylamine, such as a monoarylamine, diarylamine, triarylamine, or a polymeric arylamine. Klupfel et al. in U.S. Patent 3,180,730 illustrate exemplary monomeric triarylamine. In U.S. Patents 3,567,450 and 3,658,520, Brantley et al. discloses other suitable triarylamine substituted with one or more vinyl radicals, or comprising at least one active hydrogen-containing group.

[0027] A more preferred class of aromatic tertiary amines are those which include at least two aromatic tertiary amine moieties as described in U.S. Patents 4,720,432 and 5,061,569. Such compounds include those represented by structural Formula A.




wherein:

Q₁ and Q₂ are independently selected aromatic tertiary amine moieties; and
G is a linking group such as an arylene, cycloalkylene, or alkylene group of a carbon-to-carbon bond.

[0028] In one embodiment, at least one of Q₁ or Q₂ contains a polycyclic fused ring structure, e.g., naphthalene. When G is an aryl group, it is conveniently a phenylene, biphenylene, or naphthalene moiety.

[0029] A useful class of triarylamine satisfying structural Formula A and containing two triarylamine moieties is represented by structural Formula B.



where:

R₁ and R₂ each independently represent a hydrogen atom, an aryl group, or an alkyl group or R₁ and R₂ together represent the atoms completing a cycloalkyl group; and


R₃ and R₄ each independently represent an aryl group, which is in turn substituted with a diaryl substituted amino group, as indicated by structural Formula C.



wherein R₅ and R₆ are independently selected aryl groups. In one embodiment, at least one of R₅ or R₆ contains

a polycyclic fused ring structure, e.g., naphthalene.

[0030] Another class of aromatic tertiary amines is the tetraaryldiamines. Desirable tetraaryldiamines include two diarylamino groups, such as indicated by Formula C, and linked through an arylene group. Useful tetraaryldiamines include those represented by Formula D.



wherein:

each Are is an independently selected arylene group, such as a phenylene or anthracene moiety;

n is an integer of from 1 to 4; and

Ar, R₇, R₈, and R₉ are independently selected aryl groups.

[0031] In a typical embodiment, at least one of Ar, R₇, R₈, and R₉ is a polycyclic fused ring structure, e.g., naphthalene.


[0032] The various alkyl, alkylene, aryl, and arylene moieties of the foregoing structural Formulae A, B, C, D, can each in turn be substituted. Typical substituents include alkyl groups, alkoxy groups, aryl groups, aryloxy groups, and halogens such as fluoride, chloride, and bromide. The various alkyl and alkylene moieties typically contain from 1 to about 6 carbon atoms. The cycloalkyl moieties can contain from 3 to about 10 carbon atoms, but typically contain five, six, or seven carbon atoms--e.g., cyclopentyl, cyclohexyl, and cycloheptyl ring structures. The aryl and arylene moieties are usually phenyl and phenylene moieties.

[0033] The hole-transporting layer in an OLED device can be formed of a single or a mixture of aromatic tertiary amine compounds. Specifically, one can employ a triarylamine, such as a triarylamine satisfying the Formula B, in combination with a tetraaryldiamine, such as indicated by Formula D. When a triarylamine is employed in combination with a tetraaryldiamine, the latter is positioned as a layer interposed between the triarylamine and the electron-injecting and transporting layer.

[0034] Another class of useful hole-transporting materials includes polycyclic aromatic compounds as described in EP 1 009 041. In addition, polymeric hole-transporting materials can be used such as poly(N-vinylcarbazole) (PVK), polythiophenes, polypyrrole, polyaniline, and copolymers such as poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate), also called PEDOT/PSS.

[0035] Light-emitting layers produce light in response to hole-electron recombination. The light-emitting layers are commonly disposed over the hole-transporting layer. Any suitable process such as evaporation, sputtering, chemical vapor deposition, electrochemical deposition, or radiation thermal transfer from a donor material can deposit desired organic light-emitting materials. Useful organic light-emitting materials are well known. As more fully described in U.S. Patents 4,769,292 and 5,935,721, the light-emitting layers of the OLED element comprise a luminescent or fluorescent material where electroluminescence is produced as a result of electron-hole pair recombination in this region. The light-emitting layers can be comprised of a single material, but more commonly include a host material doped with a guest compound or dopant where light emission comes primarily from the dopant. The dopant is selected to produce color light having a particular spectrum. The host materials in the light-emitting layers can be an electron-transporting material, as defined below, a hole-transporting material, as defined above, or another material that supports hole-electron recombination. The dopant is usually chosen from highly fluorescent dyes, but phosphorescent compounds, e.g., transition metal complexes as described in WO 98/55561, WO 00/18851, WO 00/57676, and WO 00/70655 are also useful. Dopants are typically coated as 0.01 to 10 % by weight into the host material. Host and emitting molecules known to be of use include, but are not limited to, those disclosed in U.S. Patents 4,768,292; 5,141,671; 5,150,006; 5,151,629; 5,294,870; 5,405,709; 5,484,922; 5,593,788; 5,645,948; 5,683,823; 5,755,999; 5,928,802; 5,935,720; 5,935,721; and 6,020,078.

[0036] Metal complexes of 8-hydroxyquinoline and similar derivatives (Formula E) constitute one class of useful host materials capable of supporting electroluminescence, and are particularly suitable for light emission of wavelengths longer than 500 nm, e.g., green, yellow, orange, and red.



wherein:

M represents a metal;

n is an integer of from 1 to 3; and

Z independently in each occurrence represents the atoms completing a nucleus having at least two fused aromatic rings.

[0037] From the foregoing it is apparent that the metal can be a monovalent, divalent, or trivalent metal. The metal can, for example, be an alkali metal, such as lithium, sodium, or potassium; an alkaline earth metal, such as magnesium or calcium; or an earth metal, such as boron or aluminum. Generally any monovalent, divalent, or trivalent metal known to be a useful chelating metal can be employed.

[0038] Z completes a heterocyclic nucleus containing at least two fused aromatic rings, at least one of which is an azole or azine ring. Additional rings, including both aliphatic and aromatic rings, can be fused with the two required rings, if required. To avoid adding molecular bulk without improving on function the number of ring atoms is usually maintained at 18 or less.

[0039] The host material in the light-emitting layers can be an anthracene derivative having hydrocarbon or substituted hydrocarbon substituents at the 9 and 10 positions. For example, derivatives of 9,10-di-(2-naphthyl)anthracene constitute one class of useful host materials capable of supporting electroluminescence, and are particularly suitable for light emission of wavelengths longer than 400 nm, e.g., blue, green, yellow, orange or red.

[0040] Benzazole derivatives constitute another class of useful host materials capable of supporting electroluminescence, and are particularly suitable for light emission of wavelengths longer than 400 nm, e.g., blue, green, yellow, orange or red. An example of a useful benzazole is 2, 2', 2''-(1,3,5-phenylene)tris[1-phenyl-1H-benzimidazole].

[0041] Desirable fluorescent dopants include perylene or derivatives of perylene, derivatives of anthracene, tetracene, xanthene, rubrene, coumarin, rhodamine, quinacridone, dicyanomethylenepyrans compounds, thiopyran compounds, polymethine compounds, pyrilium and thiapyrilium compounds, derivatives of distyrylbenzene or distyrylbiphenyl, bis(azanyl)methane boron complex compounds, and carbostyryl compounds.

[0042] Other organic emissive materials can be polymeric substances, e.g. polyphenylenevinylene derivatives, dialkoxy-polyphenylenevinylenes, poly-para-phenylene derivatives, and polyfluorene derivatives, as taught by Wolk et al. in commonly assigned U.S. Patent 6,194,119 B1 and references cited therein.

[0043] While not always necessary, it is often useful to include an electron-transporting layer disposed over the light-emitting layers. Any suitable process such as evaporation, sputtering, chemical vapor deposition, electrochemical deposition, thermal transfer, or laser thermal transfer from a donor material can deposit desired electron-transporting materials. Preferred electron-transporting materials for use in the electron-transporting layer are metal chelated oxinoid compounds, including chelates of oxine itself (also commonly referred to as 8-quinolinol or 8-hydroxyquinoline). Such compounds help to inject and transport electrons and exhibit both high levels of performance and are readily fabricated in the form of thin films. Exemplary of contemplated oxinoid compounds are those satisfying structural Formula E, previously described.


[0044] Other electron-transporting materials include various butadiene derivatives as disclosed in U.S. Patent 4,356,429 and various heterocyclic optical brighteners as described in U.S. Patent 4,539,507. Certain benzazoles are also useful electron-transporting materials. Other electron-transporting materials can be polymeric substances, e.g. polyphenylenevinylene derivatives, poly-para-phenylene derivatives, polyfluorene derivatives, polythiophenes, polyacetylenes, and other conductive polymeric organic materials known in the art.

[0045] An upper electrode 40 most commonly configured as a cathode is formed over the electron-transporting layer, or over the light-emitting layers if an electron-transporting layer is not used. If the device is top-emitting, the electrode must be transparent or nearly transparent. For such applications, metals must be thin (preferably less than 25 nm) or one must use transparent conductive oxides (e.g. indium-tin oxide, indium-zinc oxide), or a combination of these materials. Optically transparent cathodes have been described in more detail in U.S. Patent 5,776,623. Evaporation, sputtering, or chemical vapor deposition can deposit cathode materials. When needed, patterning can be achieved through many well known methods including, but not limited to, through-mask deposition, integral shadow masking as described in


U.S. Patent 5,276,380 and EP 0 732 868, laser ablation, and selective chemical vapor deposition.

[0046] OLED display **100** can include other layers as well. For example, a hole-injecting layer can be formed over the anode, as described in U.S. 4,720,432, U.S. 6,208,075, EP 0 891 121 A1, and EP 1 029 909 A1. An electron-injecting layer, such as alkaline or alkaline earth metals, alkali halide salts, or alkaline or alkaline earth metal-doped organic layers, can also be present between the cathode and the electron-transporting layer.


[0047] Desiccant **60** is used to physically or chemically absorb or react with moisture that would otherwise damage the highly moisture-sensitive OLED **25**. The level of moisture inside OLED display **100** must be kept below 1000 ppm, and in some cases even lower. Therefore, the second desiccant material has an equilibrium humidity level less than 1000 ppm. Typical moisture-absorbing materials meeting this requirement include metals such as alkali metals (e.g. Li, Na), alkaline earth metals (e.g. Ba, Ca), or other moisture-reactive metals (e.g. Al, Fe); alkaline metal oxides (e.g. Li₂O, Na₂O); alkaline earth metal oxides (e.g. MgO, CaO, BaO); sulfates (e.g. anhydrous MgSO₄); metal halides (e.g. CaCl₂); perchlorates (e.g. Mg(ClO₄)₂); molecular sieves; tris(8-quinolinolato)aluminum (Alq) and aluminum/Alq mixtures; organometallic compounds described by Takahashi et al. in U.S. Patent 6,656,609 and by Tsuruoka et al. in U.S. Patent Application 2003/0110981, including organometallic compounds of the type:



wherein R₁, R₂, and R₃ are selected from the group consisting of alkyl groups, aryl groups, cycloalkyl groups, heterocyclic groups, and acyl groups having one or more carbon atoms, and M is a trivalent metallic atom; organometallic compounds of the type:



wherein each of R₁, R₂, R₃, R₄, and R₅ is selected from the group consisting of alkyl groups, alkenyl groups, aryl groups, cycloalkyl groups, heterocyclic groups, and acyl groups having one or more carbon atoms, and M is a trivalent metal atom; organometallic compounds of the type:



wherein each of R₁, R₂, R₃, and R₄ is selected from the group consisting of alkyl groups, alkenyl groups, aryl groups, cycloalkyl groups, heterocyclic groups, and acyl groups having one or more carbon atoms, and M is a tetravalent metal atom;

and metals with work functions less than 4.5 eV and oxidizable in the presence of moisture, or combinations thereof.

Moisture-absorbing material can be packaged within moisture permeable containers or binders. Desiccant **60** can be a single material, a homogeneous mixture of materials, a composite of materials, or multiple layers of materials, and can be deposited from a vapor or from solution, or they can be provided in a porous matrix such as a permeable package or tape. Particularly useful desiccant materials include those that are particulate materials formed into a polymeric matrix that can be patterned, as described by Boroson et al. in U.S. Patent 6,226,890.

PARTS LIST

[0048]

10 10 substrate
 20 electrode
 25 OLED
 30 organic layers
 15 40 electrode
 50 perimeter seal
 55 enclosure
 60 desiccant
 70 encapsulation container
 20 75 compliant region
 80 fitting region
 85 sealing base
 90 rigid portion
 100 OLED display
 25 150 encapsulation container
 160 compliant region
 200 OLED display
 210 substrate
 230 compliant region
 30 240 encapsulation container
 250 OLED display
 260 encapsulation container
 270 compliant region

Claims

1. An OLED display (200), comprising:

- a. a substrate (210) formed of a flexible material;
- b. an OLED (25) having two spaced-apart electrodes (20, 40) and organic layers (30) disposed there between, and the OLED (25) formed on the substrate (210); and
- c. an encapsulation container (240) fixed by a perimeter seal (50) to the substrate (210) and disposed over the OLED (25) to provide an enclosure (55);

characterized in that

the substrate (210) includes compliant regions (230) that flex, compress, or expand under stress and reduce stress transfer between the substrate (210) or the encapsulation container (240) through the perimeter seal (50), wherein the compliant regions (230) are provided by spaced-apart bends or flexures in the substrate (210).

Patentansprüche

1. OLED-Anzeige (200) umfassend:

- a. ein Substrat (210), das aus einem flexiblen Material gebildet ist;
- b. eine OLED (25) mit zwei voneinander beabstandeten Elektroden (20, 40) und dazwischen angeordneten organischen Schichten (30), wobei die OLED (25) auf dem Substrat (210) gebildet ist; und

c. einen Kapselungsbehälter (240), der durch eine Umfangsdichtung (50) an dem Substrat (210) befestigt ist und über der OLED (25) angeordnet ist, um eine Umhüllung (55) bereitzustellen;

dadurch gekennzeichnet, dass

das Substrat (210) nachgiebige Bereiche (230) umfasst, die sich unter Spannung biegen, komprimieren oder ausdehnen und eine Spannungsübertragung zwischen dem Substrat (210) oder dem Kapselungsbehälter (240) durch die Umfangsdichtung (50) verringern, wobei die nachgiebigen Bereiche (230) durch voneinander beabstandete Krümmungen oder durch Biegungen in dem Substrat (210) bereitgestellt sind.

Revendications

1. Afficheur (200) à OLED, comprenant :

- a. un substrat (210) constitué d'un matériau flexible ;
- b. une OLED (25) ayant deux électrodes (20, 40) espacées et des couches organiques (30) disposées entre celles-ci, et l'OLED (25) formée sur le substrat (210) ; et
- c. un récipient (240) d'encapsulation fixé par un joint périphérique (50) au substrat (210) et disposé par-dessus l'OLED (25) pour créer une enceinte (55) ;

caractérisé en ce que

le substrat (210) inclut des régions élastiques (230) qui fléchissent, se compressent ou se détendent sous une contrainte et réduisent un transfert de contrainte entre le substrat (210) ou le récipient (240) d'encapsulation par l'intermédiaire du joint périphérique (50), dans lequel les régions élastiques (230) sont créées par des pliures ou des flexions espacées dans le substrat (210).




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 4769292 A [0002] [0035]
- US 4885211 A [0002]
- JP 11339954 A [0004]
- JP 11329716 A [0005]
- JP 2001118674 A [0006]
- US 20010013756 A1 [0007]
- EP 1448026 A1 [0008]
- US 3180730 A, Klupfel [0026]
- US 3567450 A [0026]
- US 3658520 A, Brantley [0026]
- US 4720432 A [0027] [0046]
- US 5061569 A [0027]
- EP 1009041 A [0034]
- US 5935721 A [0035]
- WO 9855561 A [0035]
- WO 0018851 A [0035]
- WO 0057676 A [0035]
- WO 0070655 A [0035]
- US 4768292 A [0035]
- US 5141671 A [0035]
- US 5150006 A [0035]
- US 5151629 A [0035]
- US 5294870 A [0035]
- US 5405709 A [0035]
- US 5484922 A [0035]
- US 5593788 A [0035]
- US 5645948 A [0035]
- US 5683823 A [0035]
- US 5755999 A [0035]
- US 5928802 A [0035]
- US 5935720 A [0035]
- US 6020078 A [0035]
- US 6194119 B1, Wolk [0042]
- US 4356429 A [0044]
- US 4539507 A [0044]
- US 5776623 A [0045]
- US 5276380 A [0045]
- EP 0732868 A [0045]
- US 6208075 B [0046]
- EP 0891121 A1 [0046]
- EP 1029909 A1 [0046]
- US 6656609 B, Takahashi [0047]
- US 20030110981 A, Tsuruoka [0047]
- US 6226890 B, Boroson [0047]

专利名称(译)	防止OLED显示器组件中的应力传递		
公开(公告)号	EP2179459B1	公开(公告)日	2015-04-08
申请号	EP2008794648	申请日	2008-07-23
[标]申请(专利权)人(译)	伊斯曼柯达公司		
申请(专利权)人(译)	伊士曼柯达公司		
当前申请(专利权)人(译)	全球OLED科技有限责任公司		
[标]发明人	BOROSON MICHAEL LOUIS RICKS MICHELE LEE PALONE THOMAS WILLIAM		
发明人	BOROSON, MICHAEL LOUIS RICKS, MICHELE LEE PALONE, THOMAS WILLIAM		
IPC分类号	H01L51/00 H01L51/52		
CPC分类号	H01L51/524 H01L51/0097 H01L2251/5315 H01L2251/5338 Y02E10/549 Y02P70/521		
优先权	11/782797 2007-07-25 US		
其他公开文献	EP2179459A1		
外部链接	Espacenet		

摘要(译)

一种OLED显示器，包括：基板；OLED，具有两个间隔开的电极和设置在其间的有机层，OLED设置在基板上；封装容器，通过周边密封固定到基板上，并设置在OLED上方以提供外壳；基板或封装容器或两者，包括在应力下弯曲，压缩或膨胀的柔顺区域，并通过周边密封减少基板和封装容器之间的应力传递。

