

(19)



(11)

EP 2 416 392 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
25.05.2016 Bulletin 2016/21

(51) Int Cl.:
H01L 51/54^(2006.01)

(21) Application number: **11176592.1**

(22) Date of filing: **04.08.2011**

(54) Light emitting device and display unit

Lichtemittierende Vorrichtung und Anzeigeeinheit

Dispositif électroluminescent et unité d'affichage

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **06.08.2010 JP 2010178148**
13.07.2011 JP 2011154838

(43) Date of publication of application:
08.02.2012 Bulletin 2012/06

(73) Proprietor: **Ricoh Company, Ltd.**
Tokyo 143-8555 (JP)

(72) Inventors:
• **Harada, Shigeyuki**
Ohta-ku, Tokyo 143-8555 (JP)
• **Sasaki, Masaomi**
Ohta-ku, Tokyo 143-8555 (JP)

• **Abe, Mikiko**
Ohta-ku, Tokyo 143-8555 (JP)

(74) Representative: **Lamb, Martin John Carstairs Marks & Clerk LLP**
90 Long Acre
London WC2E 9RA (GB)

(56) References cited:
EP-A2- 2 184 333

• **WANG, S., LI, Y.L., DU, C.M., SHI, Z.Q., XIAO, S.X., FANG, H.J., ZHU, D.B.: "Self-Organization of Gold Nanoparticles Protected by 9-(5-Thiophenyl)-carbazole", CHINESE CHEMICAL LETTERS, vol. 12, no. 12, 2001, pages 1141-1144, XP002694337,**

EP 2 416 392 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

BACKGROUND OF THE INVENTION

5 Technical Field

[0001] The present invention relates to a light emitting device and a display unit. Description of the Background

[0002] The behavior of nanomaterials is intermediate between those of an atom or a molecular and those of a macroscopic solid (bulk form). Nanomaterials having charge carriers and excitation confined in all three dimensional directions are referred to as quantum dots. Since a quantum dot has increased effective band gaps as its size decreases, a spectrum having its absorption wavelength and emission wavelength shifted to the short wavelength side can be obtained. In addition, by controlling both the composition of a quantum dot in addition to its size, a spectrum having a wide range of from infrared to ultraviolet can be obtained. Moreover, by controlling the size distribution, a spectrum having excellent color purity with a narrow half value width can be obtained.

[0003] For these reasons, it is expected that the quantum dot can find applications in labeling and imaging of biological molecules and light emitting devices such as a photoluminescent devices and electroluminescent device. However, insufficient luminance efficiency is a problem.

[0004] Therefore, Japanese patent application publication no. 2009-99545 (JP-2009-99545-A) describes an electroluminescence device having a pair of electrodes and an electroluminescent layer containing a luminous layer arranged between the pair of electrodes. Other documents in this technical field are EP 2 184 333A and Chinese Chemical Letters vol. 12, no. 12, 2001, Pages 1141-1144. The luminous layer in JP-2009-99545A has a structure in which quantum dots having a surface protected by a protective material are dispersed in a matrix material containing an organic compound. In addition, a first protective material is contained as the protective material that satisfies the following relationships (A), (B), and (C):

$$I_p(h) < I_p(m) + 0.1 \text{ eV} \quad \text{Relationship (A)}$$

$$E_a(h) > E_a(m) - 0.1 \text{ eV} \quad \text{Relationship (B)}$$

$$E_g(q) < E_g(h) < E_g(m) \quad \text{Relationship (C)}$$

[0005] In the relationships, $I_p(h)$ represents the absolute value of the ionization potential of the first protective material, $I_p(m)$ represents the absolute value of the ionization potential of the organic compound contained in the matrix material, $E_a(h)$ represents the absolute value of the electronic affinity of the first protective material, $E_a(m)$ represents the absolute value of the electronic affinity of the organic compound, $E_g(h)$ represents the bandgap of the first protective material, $E_g(m)$ represents the bandgap of the organic compound, and $E_g(q)$ represents the bandgap of the quantum dot.

[0006] Furthermore, when the first protective material has at least one remaining hydrophilic group and a hydrophobic group in one molecule, specific examples of the combination of the hydrophobic group of the protective material / organic compound / quantum dot include:

(1) remaining group of 3-(2-benzo thiazoleyl)-7-(diethylamino) coumalin / 4,4'-bis(carbazole-9-yl)biphenyl / CdSe / ZnS (luminous wavelength: 620 nm);

(2) remaining group of 5,6,11,12-tetraphenyl naphthacene / 4,4'-bis(carbazole-9-yl)biphenyl / CdSe / ZnS (luminous wavelength: 620 nm); and


(3) remaining group of 2,5,8,11-tetra-tert-butyl perylene / 4,4'-bis(carbazole-9-yl)-biphenyl / CdSe / ZnS (luminous wavelength: 520 nm).

[0007] However, even with these structures the luminance efficiency remains insufficient.

SUMMARY OF THE INVENTION

[0008] In view of the foregoing, the present invention provides a novel light emitting device having a substrate and a luminous layer provided overlying the substrate. The luminous layer is a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached. The carbazole derivative has aromatic rings of a compound represented

by the following chemical structure 1. The aromatic rings have one to three substitution groups represented by the following chemical structure 2:




Chemical Structure 1

15 where Ar₁ and Ar₂ independently represent substituted or non-substituted aryl groups that may share a linkage to form a ring with a benzene ring, heterocyclic groups, and hydrogen atoms and Ar₃ represents a substituted or non-substituted aryl group, and



where X represents a methylene group, a carbonyloxy group, an oxycarbonyl group, a carbonyl group, an oxygen atom, or a sulfur atom, Y represents a substituted or non-substituted alkylene group, and Z represents a carboxyl group, a hydroxyl group, or a thiol group.


25 **[0009]** It is preferred that, in the light emitting device described above, the carbazole derivative is represented by the following chemical structure 3:



Chemical Structure 3

where Ar₄ represents a substituted or non-substituted arylene group.

[0010] It is still further preferred that, in the light emitting device described above, Ar₁ and Ar₂ independently represent groups represented by the following chemical structure 4:




Chemical Structure 4

50 where R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

[0011] It is still further preferred that, in the light emitting device described above, the compound represented by the chemical structure 3 is a benzocarbazole derivative represented by the following chemical structure 5:


55



Chemical Structure 5

where R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

[0012] It is still further preferred that, in the light emitting device described above, the carbazol derivative is represented by the following chemical structure 6:



Chemical Structure 6.

[0013] As another aspect of the present invention, a display unit is provided which include the light emitting device described above.

BRIEF DESCRIPTION OF THE DRAWINGS

[0014] Various other objects, features and attendant advantages of the present invention will be more fully appreciated as the same becomes better understood from the detailed description when considered in connection with the accompanying drawings in which like reference characters designate like corresponding parts throughout and wherein:

- Fig. 1 is a graph illustrating the infra red spectrum of carbazole derivative 1 described later;
- Fig. 2 is a graph illustrating the infrared spectrum of carbazole derivative 2 described later;
- Fig. 3 is a graph illustrating the infra red spectrum of carbazole derivative 3 described later;
- Fig. 4 is a graph illustrating the infra red spectrum of carbazole derivative 4 described later;
- Fig. 5 is a graph illustrating the infra red spectrum of carbazole derivative 5 described later;
- Fig. 6 is a graph illustrating the infra red spectrum of carbazole derivative 6 described later;
- Fig. 7 is a graph illustrating the infra red spectrum of carbazole derivative 7 described later;
- Fig. 8 is a graph illustrating the infra red spectrum of carbazole derivative 8 described later;
- Fig. 9 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL (electroluminescence) device of Example 1 described later;
- Fig. 10 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 1 described later;
- Fig. 11 is a graph illustrating the luminescence spectrum of the EL device of Example 1 described later;
- Fig. 12 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 2 described later;
- Fig. 13 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 2 described later;
- Fig. 14 is a graph illustrating the luminescence spectrum of the EL device of Example 2 described later;
- Fig. 15 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Comparative Example 1 described later;
- Fig. 16 is a graph illustrating the relationship between the voltage and the current density of the EL device of Comparative Example 1 described later;
- Fig. 17 is a graph illustrating the luminescence spectrum of the EL device of Comparative Example 1 described later;
- Fig. 18 is a graph illustrating the relationship between the current density and the external quantum efficiency of the

EL device of Example 3 described later;

Fig. 19 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 3 described later;

Fig. 20 is a graph illustrating the luminescence spectrum of the EL device of Example 3 described later;

Fig. 21 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 4 described later;

Fig. 22 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 4 described later;

Fig. 23 is a graph illustrating the luminescence spectrum of the EL device of Example 4 described later;

Fig. 24 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 5 described later;

Fig. 25 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 5 described later;

Fig. 26 is a graph illustrating the luminescence spectrum of the EL device of Example 5 described later;

Fig. 27 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 6 described later;

Fig. 28 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 6 described later;

Fig. 29 is a graph illustrating the luminescence spectrum of the EL device of Example 6 described later;

Fig. 30 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 7 described later;

Fig. 31 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 7 described later;

Fig. 32 is a graph illustrating the luminescence spectrum of the EL device of Example 7 described later;

Fig. 33 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 8 described later;

Fig. 34 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 8 described later;

Fig. 35 is a graph illustrating the luminescence spectrum of the EL device of Example 8 described later;

Fig. 36 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 9 described later;

Fig. 37 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 9 described later;

Fig. 38 is a graph illustrating the luminescence spectrum of the EL device of Example 9 described later;

Fig. 39 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Comparative Example 2 described later;


Fig. 40 is a graph illustrating the relationship between the voltage and the current density of the EL device of Comparative Example 2 described later; and

Fig. 41 is a graph illustrating the luminescence spectrum of the EL device of Comparative Example 2 described later.

DETAILED DESCRIPTION OF THE INVENTION

[0015] Embodiments of the present disclosure are described with reference to accompanying drawings.

[0016] The light emitting device of the present disclosure has a substrate and a luminous layer provided overlying the substrate and containing a semiconductor nanocrystal. A carbazole derivative is coordination-bonded or attached to the semiconductor nanocrystal. In the carbazole derivative, the aromatic rings in the compound represented by the following chemical structure 1 have one to three substitution groups represented by the following chemical structure 2.



Chemical structure 1

[0017] In the chemical structure 1, Ar₁ and Ar₂ independently represent substituted or non-substituted aryl groups that

may share a linkage to form a ring with a benzene ring, heterocyclic groups, and hydrogen atoms and Ar₃ represents a substituted or non-substituted aryl group,

-X-Y-Z Chemical structure 2

5

[0018] In the chemical structure 2, X represents a methylene group, a carbonyloxy group, an oxycarbonyl group, a carbonyl group, an oxygen atom, or a sulfur atom, Y represents a substituted or non-substituted alkylene group, and Z represents a carboxyl group, a hydroxyl group, or a thiol group. When the aromatic rings in the compound represented by the chemical structure 1 are substituted by two or three groups represented by the chemical structure 2, the two or

10

three substitution groups may or may not be identical.

[0019] In the chemical structure 1, there is no specific limit to the selection of the non-substituted aryl group for Ar₁, Ar₂, and Ar₃. Specific examples thereof include, but are not limited to, a phenyl group, a naphthyl group, a biphenyl group, a terphenyl group, a pyrenyl group, a fluorenyl group, a 9,9-dimethyl-2-fluorenyl group, an azulenyl group, an anthryl group, a triphenylenyl group, a crycenyl group, a fluorenylidene phenyl group, and a 5H-dibenzo [a,d] cycloheptenyliene phenyl group.

15

[0020] In the chemical structure 1, there is no specific limit to the selection of the non-substituted heterocyclic group of Ar₁ and Ar₂. Specific examples thereof include, but are not limited to, a furyl group, a benzofuranyl group, a carbazoyl group, a pyridyl group, a pyrrolidyl group, a thiophenyl group, a methylthiophenyl group, and an oxazolyl group.

[0021] In addition, each of the non-substituted aryl group and the non-substituted heterocyclic group optionally has a straight chain, branch chain, or cyclic alkyl group having 1 to 25 carbon atoms such as a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, an s-butyl group, a t-butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, a decyl group, a 3,7-dimethyl octyl group, a 2-ethylhexyl group, a trifluoromethyl group, a 2-cyano ethyl group, a benzyl group, a 4-chlorobenzyl group, a 4-methyl benzyl group, a cyclopentyl group, and a cyclohexyl group.

20

[0022] In addition, there is no specific limit to the selection of the substitution group for the aryl group for Ar₁, Ar₂, and Ar₃. Specific examples thereof include, but are not limited to, a straight chain, branch chain, or cyclic substituted or non-substituted alkoxy group having 1 to 25 carbon atoms, a halogen atom such as a fluorine atom, a chlorine atom, and a bromine atom, a cyano group, a triphenyl silyl group, a furyl group, a benzofuranyl group, a carbazoyl group, a pyridyl group, a pyrrolidyl group, a thiophenyl group, a methylthiophenyl group, and an oxazolyl group. There is no specific limit to the selection of the substitution group for the alkoxy group. Specific examples thereof include, but are not limited to, a fluorine atom, a cyano group, and a substituted or non-substituted phenyl group. There is no specific limit to the selection of the substitution group for the phenyl group. Specific examples thereof include, but are not limited to, a halogen atom such as a fluorine atom, a chlorine atom, and a bromine atom and a straight-chained or cyclic alkyl group.

25

[0023] Specific examples of the substituted or non-substituted alkoxy groups include, but are not limited to, a methoxy group, an ethoxy group, an n-propoxy group, an isopropoxy group, an n-butoxy group, an isobutoxy group, an s-butoxy group, a t-butoxy group, a pentyloxy group, a hexyloxy group, a heptyloxy group, an octyloxy group, a nonyloxy group, a decyloxy group, a 3,7,-dimethyl octyloxy group, a 2-ethylhexyloxy group, a trifluoromethoxy group, a 2-cyanoethoxy group, a benzyloxy group, a 4-chlorobenzoyloxy group, a 4-methylbenzyloxy group, a cyclopentyloxy group, and a cyclohexyloxy group.

30

[0024] The number of carbon atoms in the aryl group and the heterocyclic group are from 6 to 30 and from 4 to 28, respectively.

[0025] Specific examples of the compound represented by the chemical structure 1 in which Ar₁ and/or Ar₂ are an aryl group(s) that shares a linkage to form a ring with the benzene ring include, but are not limited to, a derivative of benzocarbazole and a derivative of dibenzocarbazole.

45

[0026] In the chemical structure 2, the non-substituted alkylene group in Y preferably has 1 to 25 carbon atoms. There is no specific limit to the selection of the non-substituted alkylene group. Specific examples thereof include, but are not limited to, a methylene group, an ethylene group, a trimethylene group, a tetramethylene group, a pentamethylene group, a hexamethylene group, a heptamethylene group, an octamethylene group, a nonamethylene group, a decamethylene group, a undecamethylene group, dodecamethylene group, a tridecamethylene group, a tetradecamethylene group, a pentadecamethylene group, a hexadecamethylene group, a heptadecamethylene group, an octadecamethylene group, a nonadecamethylene group, an icosamethylene group, a henicosa methylene, a docosamethylene group, a tricosamethylene group, a tetracosamethylene group, and a pentacosamethylene group.





50

[0027] In addition, there is no specific limit to the selection of the substitution groups of the alkylene group in Y. Specific examples thereof include, but are not limited to, a halogen atom such as a fluorine atom, a chlorine atom, and a bromine atom and a straight chained, branch-chained, or cyclic alkyl group having 1 to 24 carbon atoms.





55

[0028] In the preset disclosure, there is no specific limit to the selection of the carbazole derivative. Specific examples thereof include, but are not limited to, the following compounds:

5







10



15




20



25



30

35




40


45






50

55








5






10

15



20




25



30




35

40






45

50






55

5






10






15

20






25

30



35

40





45



50

55

5





10



15




20

25






30

35




40

45




50

55




[0029] There is no specific limit to the selection of the group represented by the chemical structure 2. Specific examples thereof include, but are not limited to, the following:


25



35




40



45

[0030] In the present disclosure, the carbazole derivative is preferably the compound represented by the chemical structure 3 or 6. Ar_4 represents an arylene group deriving from Ar_3 .


50



55

Chemical Structure 3

[0031] In the chemical structure 3, Ar_4 represents a substituted or non-substituted arylene group.



Chemical Structure 6


[0032] In the chemical structure 3, Ar₁ and Ar₂ independently represent a group represented by the chemical structure 4.



Chemical Structure 4

[0033] In the chemical structure 4, R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

[0034] The compound represented by the chemical structure 3 is preferably a benzocarbazole derivative represented by the chemical structure 5.



Chemical Structure 5

[0035] In the chemical structure 5, R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

[0036] In the chemical structures 4 and 5, the non-substituted alkyl group in the R is preferably a straight-chained, a branch-chained, or cyclic alkyl group having 1 to 25 carbon atoms and the non-substituted alkoxy group in the R is preferably a straight-chained, a branch-chained, or cyclic alkoxy group having 1 to 25 carbon atoms. There is no specific limit to the selection of the substitution group for the alkyl group and the alkoxy group. Specific examples thereof include, but are not limited to, a fluorine atom, a cyano group, and a substituted or non-substituted phenyl group. There is no specific limit to the selection of the substitution group for the phenyl group. Specific examples thereof include, but are not limited to, a halogen atom such as a fluorine atom, a chlorine atom, and a bromine atom and a straight-chained or cyclic alkyl group.

[0037] Specific examples of the substituted or non-substituted alkyl group include, but are not limited to, a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, an s-butyl group, a t-butyl group, a pentyl group, a hexyl group, a heptyl group, an octyl group, a nonyl group, a decyl group, a 3,7-dimethyl octyl group, a 2-ethylhexyl group, a trifluoromethyl group, a 2-cyanoethyl group, a benzyl group, a 4-chlorobenzyl group, a 4-methylbenzyl group, a cyclopentyl group, and a cyclohexyl group.

[0038] Specific examples of the substituted or non-substituted alkoxy groups include, but are not limited to, a methoxy group, an ethoxy group, an n-propoxy group, an isopropoxy group, an n-butoxy group, an isobutoxy group, an s-butoxy group, a t-butoxy group, a pentyloxy group, a hexyloxy group, a heptyloxy group, an octyloxy group, a nonyloxy group, a decyloxy group, a 3,7-dimethyl octyloxy group, a 2-ethylhexyloxy group, a trifluoromethoxy group, a 2-cyanoethoxy group, a benzyloxy group, a 4-chlorobenzoyloxy group, a 4-methylbenzyloxy group, a cyclopentyloxy group, and a cyclohexyloxy group.

[0039] There is no specific limit to the selection of the halogen atom in the R. Specific examples thereof include, but are not limited to, a fluorine atom, a chlorine atom, and a bromine atom.

[0040] The aryl group in the R is the same as those for Ar₁, Ar₂, and Ar₃.

Synthesis Example 1 of Compound Represented by Chemical Structure 3

5 [0041] The compound represented by the chemical structure 3 can be synthesized as follows.



30 Chemical Reaction Formula 1

[0042] In the chemical reaction formula 1, Rx represents a halogen atom.

[0043] First, using a palladium catalyst, a carbazole derivative (A-2) is obtained in Suzuki-Miyaura Cross-coupling reaction between an organic halogen compound (A-1) and an aryl boronic acid Ar₁-B(OH)₂.

35 [0044] There is no specific limit to the selection of the palladium catalyst. Specific examples thereof include, but are not limited to, Pd(PPh₃)₄, PdCl₂(PPh₃)₂, Pd(OAc)₂, and PdCl₂. Among them, Pd(PPh₃)₄ is most commonly used.

[0045] An aryl boronic acid ester synthesized from bis(pinacolato)diboronium, which is thermally stable and easily handled in the air and a halogenated aryl can be used instead of aryl boronic acid.

40 [0046] In addition, Rx in the organic halogenated compound (A-1) is preferably an iodine atom or a bromine atom in terms of reactivity.

[0047] Suzuki-Miyaura cross coupling reaction requires a base and preferably a relatively weak base such as Na₂CO₃ and NaHCO₃. In addition, considering the impact of steric barrier, a strong base such as Ba(OH)₂ and K₃PO₄ is preferable. Specific examples of the other bases include, but are not limited to, sodium hydroxide, potassium hydroxide, and a metal alkoxide such as potassium t-butoxide, sodium t-butoxide, lithium t-butoxide, potassium 2-methyl-2-butoxide, sodium 2-methyl-2-butoxide, sodium methoxide, sodium ethoxide, potassium ethoxide, and potassium methoxide. In addition, an organic base such as triethyl amine can be used as the base.

[0048] Specific examples of the reaction solvent include, but are not limited to, alcohol- or ether-based solvents such as methanol, ethanol, isopropanol, butanol, 2-methoxyethanol, 1,2-dimethoxyethane, bis(2-methoxyethyl)ether, cyclic ether solvents such as dioxane and tetrahydrofuran, benzene, toluene, xylene, dimethylsulfoxide, N,N-dimethylformamide, N-methyl pyrrolidone, and 1,3-dimethyl-2-imidazolidinone.

50 [0049] Next, using a palladium catalyst and a phosphine coordinate, a carbazole derivative (A-3) is obtained by conducting Ullmann reaction or Buchwald-Hartwig amination reaction of the carbazole derivative (A-2) with a halogenated aryl Rx-Ar₄-X-Y-COOC₂H₅.

[0050] There is no specific limit to the selection of the palladium catalyst. Specific examples thereof include, but are not limited to, Pd₂(dba)₃ and Pd(OAc)₂.

55 [0051] There is no specific limit to the selection of the phosphine coordinate. Specific examples thereof include, but are not limited to, 2,2'-bis(diphenylphosphino)-1,1'-binaphthyl, pentaphenyl(di-t-butylphosphino)ferrocene, bis(1-adamantyl)-n-butylphosphine, bis(1-adamantyl)-n-butylphosphonium iodide, and bis(1-adamantyl)benzyl phosphine.


[0052] Rx in the halogenated aryl is preferably a bromine atom or a chlorine atom in terms of reactivity.

[0053] Ullmann reaction or Buchwald-Hartwig amination reaction requires a base and a relatively weak base such as K_2CO_3 , Cs_2CO_3 , Na_2CO_3 , and $NaHCO_3$ can be used.

[0054] Furthermore, using a base such as sodium hydroxide, a carbazole derivative (A-4) is obtained by hydrolyzing the carbazole derivative (A-3).

Synthesis Example 2 of Compound Represented by Chemical Structure 3

[0055] The compound represented by the chemical structure 3 can be synthesized as follows.



[0056] Chemical Reaction Formula 2 In the chemical reaction formula 2, Rx represents a halogen atom.


[0057] First, a carbazole derivative (B-2) is obtained by conducting Ullmann reaction or Buchwald-Hartwig amination reaction of a carbazole derivative (B-1) with a halogenated aryl Rx-Ar₄-OCH₃. The carbazole derivative (B-1) is identical to the carbazole derivative (A-2).

[0058] Next, using boron tribromide, a carbazole derivative (B-3) is obtained by demethylating the carbazole derivative (B-2).

[0059] Furthermore, a carbazole derivative (B-4) is obtained by etherifying the carbazole derivative (B-3) with bromo alcohol Br-Y-OH.

Synthesis Example 3 of Compound Represented by Chemical Structure 3

[0060] The compound represented by the chemical structure 3 can be synthesized as follows.



Chemical Reaction Formula 3

25

[0061] First, using chlorinated p-toluene sulphonyl under the presence of a base such as pyridine, a carbazole derivative (C-2) is obtained by tosylating the hydroxyl group of a carbazole derivative (C-1).

[0062] Next, using potassium thioacetate, a carbazole derivative (C-3) is obtained by thioacetylating the carbazole derivative (C-2).

30

[0063] Furthermore, using a base such as sodium hydroxide, a carbazole derivative (C-4) is obtained by hydrolyzing the carbazole derivative (C-3).

Synthesis Example 4 of Compound Represented by Chemical Structure 3

35


[0064] The compound represented by the chemical structure 5 can be synthesized as follows.

40

45

50

55



Chemical Reaction Formula 4

[0065] First, under the presence of protic acid, a hydrazone compound (D-3) is obtained in the reaction between a tetranone compound (D-1) and a phenyl hydrazine compound (D-2).

[0066] Next, under the presence of a Lewis acid such as $ZnCl_2$, a cyclic compound (D-4) is obtained by cyclizing the hydrazone compound (D-3).

[0067] Furthermore, using a catalyst such as Pd/C, a benzocarbazole derivative (D-5) is obtained by oxidizing the cyclic compound (D-4).

[0068] Next, a benzocarbazole derivative (D-6) is obtained by conducting Ullmann reaction or Buchwald-Hartwig amination reaction of the benzocarbazole derivative (D-5) with an iodized aryl $I-Ar_4-X-Y-OH$.


[0069] Furthermore, using chlorinated p-toluene sulphonyl under the presence of a base such as pyridine, a benzocarbazole derivative (D-7) is obtained by tosylating the hydroxyl group of the benzocarbazole derivative (D-6).

[0070] Next, using potassium thioacetate, a benzocarbazole derivative (D-8) is obtained by thioacetylating the benzocarbazole derivative (D-7).

[0071] Furthermore, using a base such as sodium hydroxide, a benzocarbazole derivative (D-9) is obtained by hydrolyzing the carbazole derivative (D-8).

Synthesis Example 1 of Compound Represented by Chemical Structure 6

[0072] The compound represented by the chemical structure 6 can be synthesized as follows.



25 **[0073]** In the chemical reaction formula 5, Rx represents a halogen atom.

[0074] First, using bromine under the presence of a base such as pyridine, 3-bromocarbazole (E-2) is obtained by brominating the carbazole (E-1).

[0075] Next, using sodium methoxide under the presence of copper iodine, 3-methoxycarbazole (E-3) is obtained by etherifying 3-bromocarbazole (E-2).

30 **[0076]** Furthermore, a carbazole derivative (E-4) is obtained by conducting Ullmann reaction or Buchwald-Hartwig amination reaction of 3-methoxycarbazole (E-3) with halogenated aryl Rx-Ar₃.

[0077] Next, using boron tribromide, a carbazole derivative (E-5) is obtained by demethylating the carbazole derivative (E-4).

35 **[0078]** Furthermore, a carbazole derivative (E-6) is obtained by conducting ether reaction of the carbazole derivative (E-5) with bromo alcohol Br-Y-OH.

[0079] Next, using chlorinated p-toluene sulphonyl under the presence of a base such as pyridine, a carbazole derivative (E-7) is obtained by tosylating a carbazole derivative (E-6).

[0080] Furthermore, using potassium thioacetate, a carbazole derivative (E-8) is obtained by thioacetylating the carbazole derivative (E-7).

40 **[0081]** Next, using a base such as sodium hydroxide, a carbazole derivative (E-9) is obtained by hydrolyzing the carbazole derivative (E-8).

[0082] In the present disclosure, there is no specific limit to the selection of the semiconductor nanocrystal. Specific examples thereof include, but are not limited to, III-V compounds formed of a group 13 element and a group 15 element in the periodic table, IIA-VIB compound formed of a group 2 element and a group 16 element in the periodic table, IIB-VIB compounds formed of a group 12 element and a group 16 element in the periodic table, II-V compounds formed of a group 12 element and a group 15 element in the periodic table, III-V compounds formed of a group 13 element and a group 15 element in the periodic table, III-IV compounds formed of a group 13 element and a group 14 element in the periodic table, III-VI compounds formed of a group 13 element and a group 16 element in the periodic table, IV-VI compounds formed of a group 14 element and a group 16 element in the periodic table, I-III-V compounds formed of a group 11 element, a group 13 element, and a group 15 element in the periodic table, and II-IV-VI compounds formed of a group 12 element, a group 14 element, and a group 16 element in the periodic table. These can be used alone or in combination.

[0083] In addition, the semiconductor nanocrystal may contain a third element, a fourth element, and a doping agent. There is no specific limit to the form of the semiconductor nanocrystal. Specific examples of such forms include, but are not limited to, spherical, semi-spherical, a bar form, a disc form, a tetrapot form, and a star form.

55 **[0084]** In addition, when the semiconductor nanocrystal is spherical, the primary average particle diameter of the semiconductor nanocrystal is from 0.5 nm to 30 nm and preferably from 1 nm to 15 nm. The particle size distribution of the semiconductor nanocrystal has an impact on the chromaticity of luminescence and preferably is narrow to obtain a

vivid luminescent color with a narrow half value width.

[0085] There is no specific limit to the method of manufacturing the semiconductor nanocrystal. Specific examples thereof are described in pages 27 and 28, and 48 to 180 of "Nano particle science - from basic principle to application -" (ISBN978-4-86043-175-4 C3040, published by N.T.S.), WO2005 / 106082, WO2007 / 020416, WO2007 / 049052, and WO2010 / 015824.

[0086] A semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached can be obtained by substituting a capping agent (surface active agent) existing on the surface of a semiconductor nanocrystal with the carbazole derivative. For example, a semiconductor nanocrystal is added to a solution in which a carbazole derivative is dissolved in a polar solvent such as methylene chloride, chloroform, and dichloroethane in an inert gas followed by mixing and stirring at 0 °C to 30 °C for 12 hours or longer and preferably 24 hours or longer. Whereafter, the solution is cleaned with a solvent having a relatively low boiling point such as methanol, ethanol, isopropyl alcohol, methylene chloride, chloroform, acetone, tetrahydrofuran, and hexane with ultrasonic to obtain a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached.

[0087] The substitution of a capping agent (surface active agent) existing on the surface of a semiconductor nanocrystal with a carbazole derivative can be confirmed by FT-IR (Infra-red spectroscopy) or XPS (X-ray photoemission spectroscopy).

[0088] The semiconductor nanocrystal may have a component present on the surface in addition to the carbazole derivative. There is no specific limit to the selection of the component other than the carbazole derivative. A specific example thereof is the capping agent (surface active agent) for use in manufacturing the semiconductor nanocrystal.

[0089] In addition, the carbazole derivative may be coordination-bonded to the semiconductor nanocrystal or attached to the semiconductor nanocrystal by mutual action such as intermolecular force with the carbazole derivative coordination-bonded to the semiconductor nanocrystal.

[0090] In the present disclosure, while the semiconductor nanocrystal functions as the luminous source, the carbazole derivative has a function of transferring the excitation energy to the semiconductor nanocrystal by dipolar interaction, i.e., a function of Forster energy transfer and/or directly infusing charges (positive hole and electron) into the semiconductor nanocrystal. Therefore, since the luminous quantum yield of the semiconductor nanocrystal increases, the light emitting device of the present disclosure has an excellent luminance efficiency.

[0091] To efficiently conduct Forster energy transfer to the semiconductor nanocrystal, the carbazole derivative that is coordination-bonded or attached to the semiconductor nanocrystal is required to have a smaller ionization potential (I_p) and a larger electron affinity (E_a) than the semiconductor nanocrystal. Therefore, Ar_1 , Ar_2 , and Ar_3 in the chemical structure 1 and R in the chemical structures 4 and 5 are suitably selected based on the semiconductor nanocrystal.

[0092] In addition, to efficiently conduct Forster energy transfer to the semiconductor nanocrystal and/or infuse charges thereto, it is preferable that the carbazole remaining group which is the main skeleton of the carbazole derivative is present close to the semiconductor nanocrystal. Therefore, X and Y in the chemical structure 2 are suitably selected.

[0093] Furthermore, in the chemical structure 2, Z is a group coordination-bonded or attached to the semiconductor nanocrystal and suitably selected based on the semiconductor nanocrystal.

[0094] As described above, the semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached functions as a luminous material of the light emitting device and a light emitting device having an excellent luminance efficiency can be obtained by suitably having a good combination of the size of the semiconductor nanocrystal, the size distribution, the form and the composition, and the structure of the carbazole derivative in terms of the objective of the light emitting device.

[0095] Any light emitting device that has a luminous layer containing a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached is suitably used in the present disclosure. Specific examples thereof include, but are not limited to, an electroluminescence (EL) device and a photoluminescence (PL) device.

[0096] The EL device as the light emitting device of the present disclosure is obtained by combining a luminous layer containing a semiconductor nanocrystal to which at least one carbazole derivative is coordination-bonded or attached and a carrier transport material for use in, for example, any known organic EL device. For example, an EL device can be obtained by suitably combining a luminous layer containing a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached with a hole infusion layer, a hole transport layer, a hole block layer, a charge transport layer, and an electron infusion layer. There is no specific limit to the structure of the electroluminescence device. Specific examples of laminate structures thereof include, but are not limited to, Positive electrode / hole transport layer / luminous layer / negative electrode

Positive electrode / hole infusion layer / hole transport layer / luminous layer / negative electrode Positive electrode / hole transport layer / luminous layer / electron transport layer / negative electrode Positive electrode / hole infusion layer / hole transport layer / luminous layer / electron transport layer / negative electrode

Positive electrode / hole transport layer / luminous layer / electron transport layer / electron infusion layer / negative electrode

Positive electrode / hole infusion layer / hole transport layer / luminous layer / electron transport layer / electron infusion

layer / negative electrode

Positive electrode / hole transport layer / luminous layer / hole block layer / electron transport layer / negative electrode

Positive electrode / hole infusion layer / hole transport layer / luminous layer / hole block layer / electron transport layer / negative electrode

5 Positive electrode / hole transport layer / luminous layer / hole block layer / electron transport layer / electron infusion layer / negative electrode

Positive electrode / hole infusion layer / hole transport layer / luminous layer / hole block layer / electron transport layer / electron infusion layer / negative electrode.

[0097] Optionally, a sealing layer can be formed on the negative electrode.

10 **[0098]** In the laminate structure described above, the luminous layer that contains semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached may further contain a hole transport material, an electron transport material and/or a dipolar material.

[0099] In addition, two or more luminous layers containing a semiconductor nanocrystal to which different carbazole derivatives are coordination-bonded or attached can be laminated in the laminate structure described above.

15 **[0100]** Furthermore, a laminate structure is also suitable in which a luminous layer containing a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached further contains a hole transport material, an electron transport material, and/or a dipolar material to form a positive electrode / luminous layer / negative electrode.

[0101] The EL device preferably has a laminate structure in which respective layers described above are laminated on a substrate.

20 **[0102]** The work function of the positive electrode is greater than 4 eV and preferably 4.8 eV.

[0103] Specific examples of the materials that form the positive electrode include, but are not limited to, metals such as gold, platinum, palladium, silver, tungsten, nickel, and cobalt, alloyed metals thereof, metal oxides such as ITO, SnO₂, and ZnO, and CuI.

25 **[0104]** The positive electrode formed of ITO preferably has a smooth surface and the surface is washed and/or cleaned before use. There is no specific limit to the washing (cleaning) method. Specific examples thereof include, but are not limited to, a method of irradiation of ultraviolet in ozone atmosphere and a method of plasma treatment in oxygen atmosphere.

[0105] The work function of the negative electrode is smaller than 4 eV. Metals and alloyed metals are used.

30 **[0106]** There is no specific limit to the selection of the material that forms the negative electrode. Specific examples thereof include, but are not limited to, metals such as cesium, sodium, calcium, magnesium, lithium, aluminum, and samarium and alloys thereof.

[0107] When the EL device is used as a surface light emitting device, at least one of the positive electrode and the negative electrode is sufficiently transparent in the luminous wavelength range and the other side has a sufficient reflectivity in the luminous wavelength range.

35 **[0108]** There is no specific limit to the selection of the transparent electrode. A specific example thereof is ITO. There is no specific limit to the selection of the substrate that forms a transparent electrode. A specific example thereof is a transparent board such as a glass board and a plastic board.

[0109] When the electroluminescence device is used as an edge light emitting device, it is not necessary that at least one of the positive electrode and the negative electrode is sufficiently transparent in the luminous wavelength range.

40 **[0110]** There is no specific limit to the selection of the material that forms the hole transport layer. Specific examples thereof include, but are not limited to, a low molecular weight triaryl amine derivative, a triaryl amine polymer, a low molecular weight 3,6-diaryl carbazole derivative and a 3,6-diaryl carbazole polymer described in JP-2005-154412-A and JP-2005-158691-A, and a polythiophene derivative.

45 **[0111]** There is no specific limit to the selection of the material to form the hole infusion layer. Specific examples thereof include, but are not limited to, a phthalocyanine derivative, a porphyrin derivative, an oxiazole derivative, a triazole derivative, a triaryl amine derivative, a polyphenylene diamine derivative, a polythiophene derivative, and a water-soluble PEDOT-PSS (polyethylene dioxathiophene-polystyrene sulphonic acid).

50 **[0112]** There is no specific limit to the selection of the electron transport material to form the electron transport layer and the hole block layer. Specific examples thereof include, but are not limited to, a fluorenone derivative, an anthraquinone dimethane derivative, a diphenylquinone derivative, a thiopyranedioxide derivative, a perylenetetracarboxylic acid derivative, a fluorenylidene methane derivative, an anthraquinone dimethane derivative, an anthrone derivative, a phenanthroline derivative, an oxadiazole derivative, and a triazole derivative.

55 **[0113]** There is no specific limit to the selection of the material to form the electron infusion layer. Specific examples thereof include, but are not limited to, lithium fluoride, 8-hydroxyquinolinolone lithium complex, a lithium complex of phenanthroline derivative, and a lithium complex of phenoxypyridine.

[0114] There is no specific limit to the selection of the method of forming each layer of the luminous layer, the hole infusion layer, the hole transport layer, the hole block layer, the electron transport layer, and the electron infusion layer. Specific examples thereof include, but are not limited to, a vacuum deposition method, an ion deposition method, a spin-

coating method, a cast method, an inkjet method, and a micro-contact method. There is no specific limit to the selection of the solvent for use in forming each layer by the spin-coating method, the cast method, the inkjet method, and the micro-contact method. Specific examples thereof include, but are not limited to, a hydrocarbon-based solvent, a halogen-based solvent, a ketone-based solvent, an ether-based solvent, an ester-based solvent, a non-protone solvent, and water.

[0115] The thickness of each layer of the luminous layer, the hole infusion layer, the hole transport layer, the hole block layer, the electron transport layer, and the electron infusion layer is from 1 nm to 5 μm .

[0116] The PL device as the light emitting device of the present disclosure can be obtained by combining a luminous layer that contains a semiconductor nanocrystal to which at least one carbazole derivative is coordination-bonded or attached as a color filter or a color change film with a liquid crystal layer, a liquid crystal molecular orientation layer, a transparent electrode, a transparent counter electrode, a light polarizer, and a backlight, which are used in a typical liquid crystal display device.

[0117] The light emitting device of the present disclosure can be applied to a display unit such as a liquid crystal display. Such a display unit may have a device to make the light emitting device luminous. Specific examples thereof include, but are not limited to, a light source or a circuit that generates exciting light.

[0118] Having generally described preferred embodiments of this invention, further understanding can be obtained by reference to certain specific examples which are provided herein for the purpose of illustration only and are not intended to be limiting. In the descriptions in the following examples, the numbers represent weight ratios in parts, unless otherwise specified.


EXAMPLES

[0119] The present disclosure is described with reference to Examples but not limited thereto.

Synthesis of Carbazole Derivative 1

[0120] Add 14.31 g (44.0 mmol) of 3,6-dibromo carbazole (A-1), 25.01 g (176.1 mmol) of 5-methyl-2-thiophen boronic acid, and 1.30 g of tetrakis(triphenylphosphine) palladium to a solvent mixture of 180 ml of toluene and 60 ml of ethanol; add an aqueous solution in which 37.3 g of sodium carbonate is dissolved in 90 ml of distilled water to the liquid mixture; reflux the mixture for 15 hours while heating in nitrogen atmosphere; next, filter the resultant with celite with heat to remove insoluble matters; separate the organic layer; distill away the solvent under a reduced pressure; subsequent to water-washing of the residual matter, dry the resultant to obtain a yellow brown solid; refine the resultant with silica gel column chromatography using a solvent mixture of methylene chloride and hexane as an eluting solution to obtain 12.25 g of 3,6-bis(5-methylthiophene-2-yl) carbazole (A-2); mix 8.07 g (22.4 mmol) of the thus obtained 3,6-bis(5-methylthiophene-2-yl) carbazole, 21.00 g (89.7 mmol) of 4-iodine anisole, 0.71 g of copper powder, and 12.40 g of potassium carbonate; reflux the mixture for six hours while heating in nitrogen atmosphere followed by cooling-down to 100°C; next, add 80 ml of toluene to the resultant; filter the resultant with celite with heat to remove insoluble matters; distill away the solvent under a reduced pressure; dissolve the residual in methylene chloride followed by water-washing; dry the resultant to obtain brown liquid; next, refine the resultant with silica gel column chromatography using a solvent mixture of methylene chloride and hexane as an eluting solution to obtain 4.39 g of 3,6-bis(5-methylthiophene-2-yl)-9-(4-methoxyphenyl)carbazole (B-2); dissolve 3.73 g (8.0 mmol) of the thus obtained 3,6-bis(5-methylthiophene-2-yl)-9-(4-methoxyphenyl)carbazole in 30 ml of methylene chloride; drip 8 ml of a methylene chloride solution of 1M boron tribromide to the resultant solution at -10 °C followed by stirring at room temperature; subsequent to water-washing, dry the resultant and thereafter remove the solvent to obtain a gray solid; furthermore, refine the resultant with silica gel column chromatography using a solvent mixture of methylene chloride and hexane as an eluting solution to obtain 3.47 g of 3,6-bis(5-methylthiophene-2-yl)-9-(4-hydroxyphenyl)carbazole (B-3); dissolve 1.81 g (4.0 mmol) of the thus obtained 3,6-bis(5-methylthiophene-2-yl)-9-(4-hydroxyphenyl)carbazole and 4.35 g (16.0 mmol) of 1,8-dibromooctane in 20 ml of methyl-ethyl ketone; add 0.83 g of potassium carbonate to the solution; reflux the solution for seven hours while heating; next, filter the resultant to remove insoluble matters; distill away the solvent under a reduced pressure; dissolve the residual in methylene chloride followed by water-washing; dry the resultant and thereafter remove the solvent to obtain pale yellow liquid; next, refine the resultant with silica gel column chromatography using a solvent mixture of methylene chloride and hexane as an eluting solution to obtain 1.83 g of 3,6-bis(5-methylthiophene-2-yl)-9-[4-(8-bromooctyloxy)phenyl]carbazole; dissolve 1.50 g (2.3 mmol) of the thus obtained 3,6-bis(5-methylthiophene-2-yl)-9-[4-(8-bromooctyloxy)phenyl]carbazole in a solvent mixture of 20 ml of tetrahydrofuran (THF) and 20 ml of ethanol; add 0.40 g (3.5 mmol) of potassium thioacetate to the solution in nitrogen atmosphere; reflux the solution for five hours while heating followed by cooling down to room temperature; pour water to the solution followed by extraction with methylene chloride; subsequent to water-washing, dry the resultant and thereafter remove the solvent to obtain a pale yellow white solid; furthermore, refine the resultant with silica gel column chromatography using a solvent mixture of methylene chloride and hexane as an eluting solution to obtain 1.22 g of 8-[4-[3,6-bis(5-methylthiophene-2-yl)-9-yl]phenoxy]octylester (C-3); dissolve 1.02

g(1.6 mmol) of the thus obtained 8-[4-[3,6-bis(5-methylthiophene-2-yl)-9-yl]phenoxy] octylester in a solvent mixture of 30 ml of tetrahydrofuran (THF) and 10 ml of ethanol in nitrogen atmosphere; add 0.5 ml of NaOH aqueous solution having 50 % by weight to the solution followed by stirring at room temperature for one hour; pour water to the solution followed by extraction with chloroform; subsequent to water-washing, dry the resultant and thereafter distill away the solvent to obtain a coarse product; next, refine the resultant with silica gel column chromatography using a solvent mixture of chloroform and hexane as an eluting solution to obtain 0.86 g of 8-[4-[3,6-bis(5-methylthiophene-2-yl)carbazole-9-yl]phenoxy] octane-1-thiol (C-4) (hereinafter referred to as carbazole derivative 1) represented by the following chemical structure 7.




Chemical Structure 7

[0121] Fig. 1 is a graph illustrating the infra red spectrum of carbazole derivative 1. The infra red spectrum is measured by KBr tablet method.

Synthesis of Carbazole Derivative 2

[0122] dissolve 4.20 g (9.9 mmol) of 3,6-diphenyl-9-(4-methoxyphenyl)carbazole (B-2) in 30 ml of methylene chloride; drip 10 ml of a methylene chloride solution of 1M boron tribromide to the resultant solution at -10°C followed by stirring at room temperature; next, subsequent to water-washing, dry the resultant and thereafter distill away the solvent to obtain 3.98 g of 3,6-diphenyl-9-(4-hydroxyphenyl)carbazole (B-3); dissolve 1.54 g (3.7 mmol) of the thus obtained 3,6-diphenyl-9-(4-hydroxyphenyl)carbazole in 20 ml of N,N-dimethylformamide; add 0.25 g (5.7 mmol) of hydrogenated sodium having 55 % by weight while cooling with iced water followed by stirring for one hour; next, add 1.16 g (5.5 mmol) of 8-bromo-1-octanol to the resultant followed by stirring at room temperature for three hours; pour water to the solution followed by extraction with ethylacetate; dry the resultant and thereafter distill away the solvent to obtain 1.90 g of 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy]octane-1-ol (B-4); dissolve 2.80 g (5.2 mmol) of the thus obtained 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy]octane-1-ol in a solvent mixture of 10 ml of methylene chloride and 5 ml of pyridine; add 1.20 g (6.3 mmol) of chlorinated p-toluene sulphonyl at -2°C to the solution followed by stirring at room temperature; pour water to the solution followed by extraction with ethylacetate; subsequent to washing with water and diluted hydrochloric acid, dry the resultant and thereafter distill away the solvent to obtain a coarse product; furthermore, refine the resultant with silica gel column chromatography using a solvent mixture of ethylacetate and toluene as an eluting solution to obtain 1.95 g of toluene-4-sulphonic acid 8-[4-(3,6-diphenylcarbazole-9-yl) phenoxy]octyl ester (C-2) having a colorless platelet; dissolve 1.90 g (2.7 mmol) of the thus obtained toluene-4-sulphonic acid 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy]octyl ester in a solvent mixture of 40 ml of tetrahydrofuran (THF) and 20 ml of ethanol; add 0.55 g (4.8 mmol) of potassium thioacetate to the solution in nitrogen atmosphere; reflux the solution for seven hours while heating followed by cooling down to room temperature; pour water to the solution followed by extraction with ethylacetate; furthermore, subsequent to washing with water, dry the resultant, and distill away the solvent to obtain a coarse product; next, refine the resultant with silica gel column chromatography using toluene as an eluting solution to obtain 1.32 g of pale orange oily matter of thioacetate 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy]octyl ester (C-3); dissolve 1.32 g (2.2 mmol) of the thus obtained thioacetate 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy]octyl ester in a solvent mixture of 25 ml of tetrahydrofuran (THF) and 10 ml of ethanol in nitrogen atmosphere; add 0.5 ml of NaOH aqueous solution having 50 % by weight to the solution followed by stirring at room temperature for 30 minutes; pour water to the solution followed by extraction with chloroform; furthermore, subsequent to washing with water, dry the resultant and thereafter distill away the solvent to obtain a coarse product; furthermore, subsequent to washing with water, dry the resultant and thereafter distill away the solvent to obtain a coarse product; and refine the resultant with silica gel column chromatography using a solvent mixture of chloroform and hexane as an eluting solution to obtain 0.82 g of 8-[4-(3,6-diphenylcarbazole-9-yl)phenoxy] octane-1-thiol (C-4) (hereinafter referred to as carbazole derivative 2) having a colorless needle-like crystal

represented by the following chemical structure 8.



15

Chemical Structure 8

[0123] Fig. 2 is a graph illustrating the infra red spectrum of carbazole derivative 2. The infra red spectrum is measured by KBr tablet method.

20 [0124] The analysis results of carbazole derivative 2 are shown below:


Melting point: 131.0 °C to 131.5 °C

Element analysis value [measured value (calculated value)]: C: 81.70 (82.12), H: 6.57 (6.71), N: 2.45 (2.52), S: 5.68 (5.77)

25

Synthesis of Carbazole Derivative 3

[0125] Demethylate 3-methoxy-9-phenylcarbazole (E-4) in the same manner as in Synthesis of Carbazole Derivative 1 to obtain 3-hydroxy-9-phenylcarbazole (E-5) having a colorless needle-like form with a yield of 91.8%; etherify the thus obtained 3-hydroxy-9-phenylcarbazole having a colorless needle-like form with 8-bromooctanol in the same manner as in Synthesis of Carbazole Derivative 2 to obtain 3-(8-hydroxyoctyloxy)-9-phenyl carbazole (E-6) having a colorless needle-like form with a yield of 84.3 %; tosylate, thioacetylate, and hydrololyze the thus obtained 3-(8-hydroxyoctyloxy)-9-phenyl carbazole in the same manner as in Synthesis of Carbazole Derivative 2 to obtain 3-(8-mercaptooctyloxy)-9-phenyl carbazole (E-9) (hereinafter referred to as carbazole derivative 3) having a colorless needle-like form represented by the chemical structure 9.



45

Chemical Structure 9

[0126] Fig. 3 is a graph illustrating the infra red spectrum of carbazole derivative 3. The infra red spectrum is measured by KBr tablet method.

[0127] The analysis results of carbazole derivative 3 are shown below:

50 Melting point: 52.5 °C to 55.5 °C


Element analysis value (%) [measured value (calculated value)]: C: 77.32 (77.38), H: 7.15 (7.24), N: 3.40 (3.47), S: 7.74 (7.95)

55

Synthesis of Carbazole Derivative 4

[0128] Stir a mixture of 2.17 g of benzo[a]carbazole (D-5), 3.50 g of 4-(8-hydroxyoctyloxy)iodine benzene, 2.80 g of potassium carbonate, 0.50 g of copper powder, and 15 ml of nitrobenzene for six hours at 190 °C to 200 °C in nitrogen atmosphere and then cool down the mixture to room temperature; next, remove insoluble matters by celite filtration and

then distill away the solvent by heat under a reduced pressure; next, refine the resultant with silica gel column chromatography using a liquid mixture of toluene and ethyl acetate as an eluting solution to obtain 3.3 g of a pale bark oily matter of N-[4-(8-hydroxyoctyloxyphenyl)]-11H-benzo[a] carbazole (D-6)); and then, tosylate, thioacetylate, and hydrolyze the thus obtained N-[4-(8-hydroxyoctyloxyphenyl)]-11H-benzo[a] carbazole in the same manner as in Synthesis of Carbazole Derivative 2 to obtain N-4[(8-mercaptooctyloxyphenyl)]-11H-benzo[a]carbazole (D-9) (hereinafter referred to as carbazole derivative 4) having a colorless prism crystal represented by the chemical structure 10;



Chemical Structure 10

[0129] Fig. 4 is a graph illustrating the infra red spectrum of carbazole derivative 4. The infra red spectrum is measured by KBr tablet method.


[0130] The analysis results of carbazole derivative 4 are shown below:

Melting point: 75.0 °C to 76.0 °C

Element analysis value (%) [measured value (calculated value)]: C: 79.48 (79.43), H: 6.76 (6.89), N: 2.78 (3.09), S: 6.99 (7.07)

Synthesis of Carbazole Derivative 5

[0131] Add 80 ml of toluene, 20 ml of ethanol, and 40 g of 2M sodium carbonate aqueous solution to 6.50 g of 2,7-dibromocarbazole, 7.32 g of phenyl boronic acid, 0.734 g of tetrakis triphenyl phosphine palladium; reflux the mixture for three hours while heating in nitrogen atmosphere followed by cooling down to room temperature; filter the mixture to remove insoluble matters; distill away the solvent to obtain 4.15 g of pale bark powder of 2,7-diphenyl carbazole; mix 4.01 g of the thus obtained 2,7-diphenyl carbazole, 4.37 g of 4-(8-hydroxyoctyloxy)iodine benzene, 3.45 g of potassium carbonate, 0.5 g of copper powder, and 20 ml of nitrobenzene; reflux the mixture for seven hours while heating in nitrogen atmosphere followed by cooling down to room temperature; filter the mixture to remove insoluble matters; distill away the solvent; next, refine the resultant with silica gel column chromatography using a liquid mixture of ethyl acetate and hexane as an eluting solution to obtain 2.0 g of a pale bark oily matter of 2,7-diphenyl-N-[4-(8-hydroxyoctyloxyphenyl)]carbazole; and then, tosylate, thioacetylate, and hydrolyze the thus obtained 2,7-diphenyl-N-[4-(8-hydroxyoctyloxyphenyl)]carbazole in the same manner as in Synthesis of Carbazole Derivative 2 to obtain 2,7-diphenyl-N-[4-(8-mercaptooctyloxyphenyl)]carbazole (hereinafter referred to as carbazole derivative 5) having a colorless needle-like crystal represented by the chemical structure 11.



Chemical Structure 11

[0132] Fig. 5 is a graph illustrating the infra red spectrum of carbazole derivative 5. The infra red spectrum is measured by KBr tablet method.


[0133] The analysis results of carbazole derivative 5 are shown below:

Melting point: 132.5 °C to 133.5 °C

Element analysis value (%) [measured value (calculated value)]: C: 82.37 (82.12), H: 6.66 (6.71), N: 2.43 (2.52), S: 5.70 (5.77)

Synthesis of Carbazole Derivative 6

[0134] A colorless viscous matter of 8-[3-(3,6-diphenylcarbazole-9-yl)phenoxy]octane-1-thiol (C-4) (hereinafter referred to as carbazole derivative 6) represented by the chemical structure 12 is obtained in the same manner as in preparation of Carbazole Derivative 1 except that 3,6-diphenyl-9-(3-methoxyphenyl)carbazole is used instead of 3,6-bis(5-methylthiophene-2-yl)-9-(4-methoxyphenyl)carbazole(B-2).




Chemical Structure 12

[0135] Fig. 6 is a graph illustrating the infra red spectrum of carbazole derivative 6. The infra red spectrum is measured by liquid membrane technique.

Synthesis of Carbazole Derivative 7

[0136] Mix 2.80 g (8.77 mmol) of 3,6-diphenylcarbazole, 22.18 g (87.7 mmol) of 1-bromo-3-iodine benzene, 0.279 g of copper powder, and 4.85 g of potassium carbonate; heat the mixture at 190°C for nine hours in nitrogen atmosphere followed by cooling down to room temperature; next, dilute the mixture with methylene chloride followed by water-washing and drying to obtain pale brown liquid; furthermore, refine the resultant with silica gel column chromatography using a liquid mixture of methylene chloride and hexane as an eluting solution to obtain 3.59 g of 9-(3-bromophenyl)-3,6-diphenyl carbazole; add 3.20 g (6.75 mmol) of the thus obtained 9-(3-bromophenyl)-3,6-diphenyl carbazole, 1.54 g (10.1 mmol) of 3-methoxyphenyl boronic acid, and 0.124 g of tetrakis (triphenyl phosphine)palladium to a liquid mixture of 30 ml of toluene and 10 ml of ethanol; add an aqueous solution in which 37.3 g of sodium carbonate is dissolved in 90 ml of distilled water to the mixture; reflux the mixture for nine hours while heating in nitrogen atmosphere followed by cooling down to room temperature; next, dilute the mixture with methylene chloride; remove insoluble matters by filtration; wash the organic layer with water for separation; distill away the solvent under a reduced pressure; and furthermore, refine the resultant with silica gel column chromatography using a liquid mixture of methylene chloride and hexane as an eluting solution to obtain 2.89 g of [3'-(3,6-diphenylcarbazole-9-yl)biphenyl-3-yloxy]methane; and prepare 8-[3'-(3,6-diphenylcarbazole-9-yl)biphenyl-3-yloxy] octane-1-thiol (C-4) (hereinafter referred to as carbazole derivative 7) represented by the chemical structure 13 in the same manner as in preparation of Carbazole Derivative 1 except that the thus obtained [3'-(3,6-diphenylcarbazole-9-yl)biphenyl-3-yloxy]methane is used instead of 3,6-bis(5-methylthiophene-2-yl)-9-(4-methoxyphenyl)carbazole (B-2).




Chemical Structure 13

[0137] Fig. 7 is a graph illustrating the infra red spectrum of carbazole derivative 7. The infra red spectrum is measured by KBr tablet method.

20 Synthesis of Carbazole Derivative 8

[0138] 8-{4-[3,6-bis(4-triphenyl silyl)phenyl]carbazole-9-yl] phenoxy}octane-1-thiol (C-4) (hereinafter referred to as carbazole derivative 8) represented by the chemical structure 14 is obtained in the same manner as in preparation of Carbazole Derivative 1 except that the 4-triphenylsilylbenzene boronic acid neopentyl glycol ester is used instead of 5-methyl-2-thiophene boronic acid.



Chemical Structure 14

45 [0139] Fig. 8 is a graph illustrating the infra red spectrum of carbazole derivative 8. The infra red spectrum is measured by KBr tablet method.

Manufacturing of Semiconductor NanoCrystal InP / ZnS / ZnO

50 [0140] As in the method described in Examples 4 and 5 of WO2010/015824, a semiconductor nanocrystal InP / ZnS / ZnO is obtained using 10-undecylenic acid as a capping agent (surface active agent). Manufacturing of Semiconductor Nano Crystal to Which Carbazole Derivative is Coordination-bonded or Attached

[0141] Dissolve 0.01 g of the carbazole derivative in 2 ml of methylene chloride at room temperature in argon atmosphere; next, add 0.5 ml of a liquid dispersion in which semiconductor nanocrystal InP / ZnS / ZnO is dispersed in toluene with a ratio of 10 mg/ml to the solution in argon atmosphere followed by stirring at room temperature for 24 hours; Furthermore, add 20 ml of dried tetrahydrofuran to the resultant; subsequent to ultrasonic cleaning for five minutes, centrifugal the resultant; next, isolate the precipitate; repeat this process twice; furthermore, isolate the precipitate; and air-dry the precipitate in argon atmosphere to obtain a semiconductor nanocrystal to which a carbazole derivative is

coordination-bonded or attached.

Example 1

5 **[0142]** Ultrasonic-clean an IOT substrate having a thickness of 110 nm with a neutral detergent, acetone, and isopropanol in that sequence followed by boil-washing with isopropanol and treatment in a UV-ozone chamber for 12 minutes; spin-coat Baytron® (PAI4083, manufactured by H.C. Starck) of PEDOT-PSS solution on the ITO substrate; dry the substrate at 150 °C for 30 minutes to form a hole infusion layer having a thickness of 40 nm; spin-coat a chloroform solution of a polycarbonate on the hole infusion layer in nitrogen atmosphere followed by drying at 100 °C for 30 minutes
10 to form a hole transport layer having a thickness of 40 nm; the used polycarbonate has the structure unit deriving from 3,6-bis(4-hydroxyphenyl)-N-phenylcarbazole described in Example 1 of JP-2005-54165-A and the structure unit deriving from 4,4'-isopropylidene diphenol with a molar ratio of 1 to 1; spin-coat a liquid dispersion in nitrogen atmosphere on the hole transport layer in which the semiconductor nanocrystal to which the carbazole derivative 1 is coordination-bonded or attached is dispersed in toluene followed by drying at 100 °C for 30 minutes to form a luminous layer having
15 a thickness of 15 nm; using a vacuum deposition device, deposit 3,5,3',5'-tetrakis(m-pyrido-3yl)phenyl- [1,1']biphenyl on the luminous layer under a pressure of 1×10^{-4} Pa to form an electron transport layer having a thickness of 50 nm; and next, deposit MgAg and Ag with a thickness of 100 nm and 10 nm, respectively via a shadow mask to form a negative electrode to obtain an EL device.

20 **[0143]** Fig. 9 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 1. As seen in Fig. 9, the external quantum efficiency of the EL device of Example 1 has a maximum value of 1.4 %.

[0144] Fig. 10 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 1;

25 **[0145]** Fig. 11 is a graph illustrating the luminescence spectrum when the current density of the EL device of Example 1 is 1 mA/cm². As seen in Fig. 11, the center wavelength of the luminescence of the EL device of Example 1 is found to be 624 nm.

Example 2

30 **[0146]** The EL device of Example 2 is obtained in the same manner as in Example 1 except that the semiconductor nanocrystal to which carbazole derivative 2 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 1 is coordination-bonded or attached.

35 **[0147]** Fig. 12 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 2. As seen in Fig. 12, the external quantum efficiency of the EL device of Example 2 has a maximum value of 2.3 %.

[0148] Fig. 13 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 2.

40 **[0149]** Fig. 14 is a graph illustrating the luminescence spectrum when the current density of the EL device of Example 2 is 1 mA/cm². As seen in Fig. 14, the center wavelength of the luminescence of the EL device of Example 2 is found to be 630 nm.

Comparative Example 1

45 **[0150]** The electroluminescence device of Comparative Example 1 is obtained in the same manner as in Example 1 except that the semiconductor nanocrystal InP / ZnS / ZnO is used instead of the semiconductor nanocrystal to which carbazole derivative 1 is coordination-bonded or attached.

[0151] Fig. 15 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Comparative Example 1. As seen in Fig. 15, the external quantum efficiency of the EL device of Comparative Example 1 has a maximum value of 0.3 %.

50 **[0152]** Fig. 16 is a graph illustrating the relationship between the voltage and the current density of the EL device of Comparative Example 1.

[0153] Fig. 17 is a graph illustrating the luminescence spectrum when the current density of the EL device of Comparative Example 1 is 1 mA/cm². As seen in Fig. 17, the center wavelength of the luminescence of the EL device of Comparative Example 1 is found to be 625 nm.

Example 3

55 **[0154]** Ultrasonic-clean an IOT substrate having a thickness of 110 nm with a neutral detergent, acetone, and isopro-

panol in that sequence followed by boil-washing with isopropanol and treatment in a UV-ozone chamber for 12 minutes; spin-coat PEDOT-PSS solution (conductive grade, manufactured by Sigma-Aldrich Corporation) on the ITO substrate; dry the substrate at 150°C for 30 minutes; form a hole infusion layer having a thickness of 40 nm; spin-coat a chloroform solution of a polycarbonate on the hole infusion layer in nitrogen atmosphere followed by drying at 100 °C for 30 minutes to form a hole transport layer having a thickness of 40 nm; the used polycarbonate has the structure unit deriving from 3,6-bis(4-hydroxyphenyl)-N-phenylcarbazole described in Example 1 of JP-2005-54165-A and the structure unit deriving from 4,4'-isopropylidene diphenol with a molar ratio of 1 to 1; spin-coat a liquid dispersion in nitrogen atmosphere on the hole transport layer in which the semiconductor nanocrystal to which the carbazole derivative 3 is coordination-bonded or attached is dispersed in toluene followed by drying at 100°C for 30 minutes to form a luminous layer having a thickness of 12 nm; using a vacuum deposition device, deposit 3,5,3',5'-tetrakis(m-pyrido-3-yl)phenyl-[1,1']biphenyl on the luminous layer under a pressure of 1×10^{-4} Pa to form an electron transport layer having a thickness of 50 nm; and next, deposit LiF and A1 with a thickness of 0.5 nm and 80 nm, respectively via a shadow mask to form a negative electrode to obtain an EL device.

[0155] Fig. 18 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 3. As seen in Fig. 18, the external quantum efficiency of the EL device of Example 3 has a maximum value of 0.74 %.

[0156] Fig.19 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 3.

[0157] Fig. 20 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 3 is 10 V, 12 V, and 14 V As seen in Fig. 20, the center wavelength of the luminescence of the EL device of Example 3 is found to be 621 nm.

Example 4

[0158] The EL device of Example 4 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 4 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole, derivative 3 is coordination-bonded or attached.

[0159] Fig. 21 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 4. As seen in Fig. 21, the external quantum efficiency of the EL device of Example 4 has a maximum value of 0.34 %.

[0160] Fig. 22 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 4.

[0161] Fig. 23 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 4 is 10 V, 12 V, and 14V. As seen in Fig. 23, the center wavelength of the luminescence of the EL device of Example 4 is found to be 622 nm.

Example 5

[0162] The EL device of Example 5 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 5 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0163] Fig. 24 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 5. As seen in Fig. 24, the external quantum efficiency of the EL device of Example 5 has a maximum value of 0.37 %.

[0164] Fig. 25 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 5.

[0165] Fig. 26 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 5 is 10 V, 12 V, and 14 V. As seen in Fig. 26, the center wavelength of the luminescence of the EL device of Example 5 is found to be 621 nm.

Example 6

[0166] The EL device of Example 6 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 6 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0167] Fig. 27 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 6. As seen in Fig. 27, the external quantum efficiency of the EL device of Example 6 has a maximum value of 0.52 %.

[0168] Fig. 28 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 6.

[0169] Fig. 29 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 6 is 10 V, 12 V, and 14 V. As seen in Fig. 29, the center wavelength of the luminescence of the EL device of Example 6 is found to be 622 nm.

Example 7

[0170] The EL device of Example 7 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 7 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0171] Fig. 30 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 7. As seen in Fig. 30, the external quantum efficiency of the EL device of Example 7 has a maximum value of 0.60 %.

[0172] Fig. 31 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 7.

[0173] Fig. 32 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 7 is 10 V, 12 V, and 14 V. As seen in Fig. 32, the center wavelength of the luminescence of the EL device of Example 7 is found to be 620 nm.

Example 8

[0174] The EL device of Example 8 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 8 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0175] Fig. 33 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 8. As seen in Fig. 33, the external quantum efficiency of the EL device of Example 8 has a maximum value of 1.2 %.

[0176] Fig. 34 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 8.

[0177] Fig. 35 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 8 is 10 V, 12 V, and 14 V. As seen in Fig. 35, the center wavelength of the luminescence of the EL device of Example 8 is found to be 620 nm.

Example 9

[0178] The EL device of Example 9 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal to which carbazole derivative 2 is coordination-bonded or attached is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0179] Fig. 36 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Example 9. As seen in Fig. 36, the external quantum efficiency of the EL device of Example 9 has a maximum value of 1.0 %.

[0180] Fig. 37 is a graph illustrating the relationship between the voltage and the current density of the EL device of Example 9.

[0181] Fig. 38 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Example 9 is 10 V, 12 V, and 14 V. As seen in Fig. 38, the center wavelength of the luminescence of the EL device of Example 9 is found to be 619 nm.

Comparative Example 2

[0182] The electroluminescence device of Comparative Example 2 is obtained in the same manner as in Example 3 except that the semiconductor nanocrystal InP / ZnS / ZnO is used instead of the semiconductor nanocrystal to which carbazole derivative 3 is coordination-bonded or attached.

[0183] Fig. 39 is a graph illustrating the relationship between the current density and the external quantum efficiency of the EL device of Comparative Example 2. As seen in Fig. 39, the external quantum efficiency of the EL device of Comparative Example 2 has a maximum value of 0.28 %.

[0184] Fig. 40 is a graph illustrating the relationship between the voltage and the current density of the EL device of Comparative Example 2.

[0185] Fig. 41 is a graph illustrating the luminescence spectrum when the voltage of the EL device of Comparative Example 2 is 10 V, 12 V, and 14 V. As seen in Fig. 41, the center wavelength of the luminescence of the EL device of Comparative Example 2 is found to be 622 nm.


[0186] This document claims priority and contains subject matter related to Japanese Patent Applications no. 2010-178148 and 2011-154838, filed on August 06, 2010, and September 13, 2011, respectively.

Claims

1. A light emitting device **characterized by** comprising:

a substrate; and

a luminous layer provided overlying the substrate and comprising a semiconductor nanocrystal to which a carbazole derivative is coordination-bonded or attached, the carbazole derivative having aromatic rings of a compound represented by a chemical structure 1, the aromatic rings having one to three substitution groups:




Chemical Structure 1

where Ar_1 and Ar_2 independently represent substituted or non-substituted aryl groups that may share a linkage to form a ring with a benzene ring, heterocyclic groups, and hydrogen atoms and Ar_3 represents a substituted or non-substituted aryl group, and the one to three substitution groups are Represented by a chemical structure 2:



where X represents a methylene group, a carbonyloxy group, an oxycarbonyl group, a carbonyl group, an oxygen atom, and a sulfur atom, Y represents a substituted or non-substituted alkylene group, and Z represents a carboxyl group, a hydroxyl group, and a thiol group.


2. The light emitting device according to Claim 1, **characterized in that** the carbazole derivative is represented by a chemical structure 3:



Chemical Structure 3

where Ar_4 represents a substituted or non-substituted arylene group.

3. The light emitting device according to Claim 2, **characterized in that** Ar_1 and Ar_2 independently represent groups represented by a chemical structure 4:




5

Chemical Structure 4

10 where R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

- 15 4. The light emitting device according to Claim 2, **characterized in that** wherein the compound represented by the chemical structure 3 is a benzocarbazole derivative represented by a chemical structure 5:

15



20

25


Chemical Structure 5

30 where R represents a hydrogen atom, a substituted or non-substituted alkyl group, a substituted or non-substituted alkoxy group, a halogen atom, or a substituted or non-substituted aryl group.

30

- 35 5. The light emitting device according to Claim 1, **characterized in that** the carbazol derivative is represented by a chemical structure 6:

35



40

Chemical Structure 6.

- 45 6. A display unit **characterized by** comprising the light emitting device of Claim 1.

45

Patentansprüche


- 50 1. Lichtemittierende Vorrichtung, **gekennzeichnet durch** das Umfassen:

50

eines Substrats; und
einer Licht ausstrahlenden Schicht, die das Substrat überlagernd bereitgestellt ist und einen Halbleiter-Nanokristall umfasst, an den ein Carbazolderivat koordinativ gebunden oder angelagert ist, wobei das Carbazolderivat aromatische Ringe einer Verbindung aufweist, repräsentiert **durch** eine chemische Struktur 1, wobei die aromatischen Ringe eine bis drei Substitutionsgruppen aufweisen:


55

EP 2 416 392 B1




Chemische Struktur 1

wobei Ar₁ und Ar₂ unabhängig substituierte oder nicht substituierte Arylgruppen, die eine Bindung teilen können, um einen Ring mit einem Benzenring zu bilden, heterozyklische Gruppen und Wasserstoffatome repräsentieren und Ar₃ eine substituierte oder nicht substituierte Arylgruppe repräsentiert, und die eine bis drei Substitutionsgruppen **durch** eine chemische Struktur 2 repräsentiert werden:



wobei X eine Methylengruppe, eine Carbonyloxygruppe, eine Oxycarbonylgruppe, eine Carbonylgruppe, ein Sauerstoffatom und ein Schwefelatom repräsentiert, Y eine substituierte oder nicht substituierte Alkylengruppe repräsentiert und Z eine Carboxylgruppe, eine Hydroxylgruppe und eine Thiolgruppe repräsentiert.

2. Lichtemittierende Vorrichtung nach Anspruch 1, **dadurch gekennzeichnet, dass** das Carbazolderivat durch eine chemische Struktur 3 repräsentiert wird:



Chemische Struktur 3

wobei Ar₄ eine substituierte oder nicht substituierte Arylengruppe repräsentiert.


3. Lichtemittierende Vorrichtung nach Anspruch 2, **dadurch gekennzeichnet, dass** Ar₁ und Ar₂ unabhängig Gruppen repräsentieren, die durch eine chemische Struktur 4 repräsentiert werden:



Chemische Struktur 4

wobei R ein Wasserstoffatom, eine substituierte oder nicht substituierte Alkylgruppe, eine substituierte oder nicht substituierte Alkoxygruppe, ein Halogenatom oder eine substituierte oder nicht substituierte Arylgruppe repräsentiert.


4. Lichtemittierende Vorrichtung nach Anspruch 2, **dadurch gekennzeichnet, dass** die durch die chemische Struktur 3 repräsentierte Verbindung ein Benzocarbazolderivat ist, repräsentiert durch eine chemische Struktur 5:



Chemische Struktur 5

wobei R ein Wasserstoffatom, eine substituierte oder nicht substituierte Alkylgruppe, eine substituierte oder nicht substituierte Alkoxygruppe, ein Halogenatom oder eine substituierte oder nicht substituierte Arylgruppe repräsentiert.

5. Lichtemittierende Vorrichtung nach Anspruch 1, **dadurch gekennzeichnet, dass** das Carbazolderivat durch eine chemische Struktur 6 repräsentiert wird:



Chemische Struktur 6


6. Anzeigeeinheit, **dadurch gekennzeichnet, dass** sie die lichtemittierende Vorrichtung nach Anspruch 1 umfasst.

Revendications

1. Dispositif électroluminescent **caractérisé par** le fait de comprendre:

un substrat; et

une couche lumineuse prévue sus-jacente au substrat et comprenant un nanocrystal semi-conducteur auquel un dérivé de carbazole est lié par coordination ou attaché, le dérivé de carbazole possédant des noyaux aromatiques d'un composé représenté par une structure chimique 1, les noyaux aromatiques possédant de un à trois groupes de substitution:




Structure chimique 1

dans laquelle Ar_1 et Ar_2 représentent indépendamment des groupes aryles substitués ou non substitués qui peuvent partager une liaison pour former un cycle avec un noyau de benzène, des groupes hétérocycliques et des atomes d'hydrogène et Ar_3 représente un groupe aryle substitué ou non substitué, et les un à trois groupes de substitution sont représentés par une structure chimique 2:



dans laquelle X représente un groupe méthylène, un groupe carbonyloxy, un groupe oxycarbonyle, un groupe carbonyle, un atome d'oxygène et un atome de soufre, Y représente un groupe alkylène substitué ou non substitué et Z représente un groupe carboxyle, un groupe hydroxyle et un groupe thiol.

2. Dispositif électroluminescent selon la revendication 1, **caractérisé en ce que** le dérivé de carbazole est représenté par une structure chimique 3:



Structure chimique 3

dans laquelle Ar_4 représente un groupe arylène substitué ou non substitué.

3. Dispositif électroluminescent selon la revendication 2, **caractérisé en ce que** Ar_1 et Ar_2 représentent indépendam-

ment des groupes représentés par une structure chimique 4:

5




Structure chimique 4

10

dans laquelle R représente un atome d'hydrogène, un groupe alkyle substitué ou non substitué, un groupe alcoxy substitué ou non substitué, un atome d'halogène ou un groupe aryle substitué ou non substitué.

4. Dispositif électroluminescent selon la revendication 2, **caractérisé en ce que** le composé représenté par la structure chimique 3 est un dérivé de benzocarbazole représenté par une structure chimique 5:

15



20


Structure chimique 5

25

dans laquelle R représente un atome d'hydrogène, un groupe alkyle substitué ou non substitué, un groupe alcoxy substitué ou non substitué, un atome d'halogène ou un groupe aryle substitué ou non substitué.

5. Dispositif électroluminescent selon la revendication 1, **caractérisé en ce que** le dérivé de carbazole est représenté par une structure chimique 6:

30



35

Structure chimique 6

40

6. Unité d'affichage **caractérisée par** le fait de comprendre le dispositif électroluminescent selon la revendication 1.

45

50

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31




FIG. 32




FIG. 33




FIG. 34




FIG. 35




FIG. 36




FIG. 37




FIG. 38




FIG. 39




FIG. 40





FIG. 41



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2009099545 A [0004]
- EP 2184333 A [0004]
- WO 2005106082 A [0085]
- WO 2007020416 A [0085]
- WO 2007049052 A [0085]
- WO 2010015824 A [0085] [0140]
- JP 2005154412 A [0110]
- JP 2005158691 A [0110]
- JP 2005054165 A [0142] [0154]
- JP 2010178148 A [0186]
- JP 2011154838 A [0186]

Non-patent literature cited in the description

- *Chinese Chemical Letters*, 2001, vol. 12 (12), 1141-1144 [0004]

| | | | |
|----------------|--|---------|------------|
| 专利名称(译) | 发光装置和显示单元 | | |
| 公开(公告)号 | EP2416392B1 | 公开(公告)日 | 2016-05-25 |
| 申请号 | EP2011176592 | 申请日 | 2011-08-04 |
| [标]申请(专利权)人(译) | 株式会社理光 | | |
| 申请(专利权)人(译) | RICOH COMPANY, LTD. | | |
| 当前申请(专利权)人(译) | RICOH COMPANY, LTD. | | |
| [标]发明人 | HARADA SHIGEYUKI SASAKI MASAOMI ABE MIKIKO | | |
| 发明人 | HARADA, SHIGEYUKI SASAKI, MASAOMI ABE, MIKIKO | | |
| IPC分类号 | H01L51/54 | | |
| CPC分类号 | H01L51/0072 H01L51/0035 H01L51/0037 H01L51/0068 H01L51/0094 H01L51/502 H01L2251/308 H05B33/14 | | |
| 优先权 | 2010178148 2010-08-06 JP 2011154838 2011-07-13 JP | | |
| 其他公开文献 | EP2416392A2 EP2416392A3 | | |
| 外部链接 | Espacenet | | |

摘要(译)

一种发光器件，具有基板和设置在基板上的发光层，其包括与咪唑衍生物配位键合或连接的半导体纳米晶体，具有由化学结构1表示的化合物的芳环的咪唑衍生物具有一个三个取代基：其中Ar1和Ar2独立地代表取代或未取代的芳基，它们可以共有连接以形成具有苯环，杂环基和氢原子的环，Ar3代表取代或未取代的芳基，由化学结构2表示的一至三个取代基：-XYZ化学结构2其中X代表亚甲基，羰氧基，氧羰基，羰基，氧原子和硫原子，Y代表取代的或未取代的亚烷基，Z表示羧基，羟基和硫醇组。

