



(11) **EP 3 040 396 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
06.07.2016 Bulletin 2016/27

(51) Int Cl.:
C09K 11/06 (2006.01) H01L 51/50 (2006.01)

(21) Application number: **15199296.3**

(22) Date of filing: **10.12.2015**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
MA MD

(30) Priority: **30.12.2014 US 201462097742 P**
27.10.2015 US 201514923942

(71) Applicant: **Universal Display Corporation**
Ewing, NJ 08618 (US)

(72) Inventors:
• **BOUDREAU, Pierre-Luc T.**
Ewing, NJ New Jersey 08618 (US)
• **XIA, Chuanjun**
Ewing, NJ New Jersey 08618 (US)
• **LIN, Chun**
Ewing, NJ New Jersey 08618 (US)

(74) Representative: **Hansen, Norbert**
Maiwald Patentanwalts GmbH
Elisenhof
Elisenstraße 3
80335 München (DE)

(54) **ORGANIC ELECTROLUMINESCENT MATERIALS AND DEVICES**

(57) A composition including a first compound is disclosed. The first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature; wherein the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.




FIG. 1

EP 3 040 396 A1

Description

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to U.S. Provisional Application Serial No. 62/097,742, filed December 30, 2014, the entire contents of which is incorporated herein by reference.

PARTIES TO A JOINT RESEARCH AGREEMENT

[0002] The claimed invention was made by, on behalf of, and/or in connection with one or more of the following parties to a joint university corporation research agreement: The Regents of the University of Michigan, Princeton University, University of Southern California, and Universal Display Corporation. The agreement was in effect on and before the date the claimed invention was made, and the claimed invention was made as a result of activities undertaken within the scope of the agreement.

FIELD OF THE INVENTION

[0003] The present invention relates to compounds for use as emitters and devices, such as organic light emitting diodes, including the same.


BACKGROUND

[0004] Opto-electronic devices that make use of organic materials are becoming increasingly desirable for a number of reasons. Many of the materials used to make such devices are relatively inexpensive, so organic opto-electronic devices have the potential for cost advantages over inorganic devices. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on a flexible substrate. Examples of organic opto-electronic devices include organic light emitting devices (OLEDs), organic phototransistors, organic photovoltaic cells, and organic photodetectors. For OLEDs, the organic materials may have performance advantages over conventional materials. For example, the wavelength at which an organic emissive layer emits light may generally be readily tuned with appropriate dopants.

[0005] OLEDs make use of thin organic films that emit light when voltage is applied across the device. OLEDs are becoming an increasingly interesting technology for use in applications such as flat panel displays, illumination, and backlighting. Several OLED materials and configurations are described in U.S. Pat. Nos. 5,844,363, 6,303,238, and 5,707,745, which are incorporated herein by reference in their entirety.

[0006] One application for phosphorescent emissive molecules is a full color display. Industry standards for such a display call for pixels adapted to emit particular colors, referred to as "saturated" colors. In particular, these standards call for saturated red, green, and blue pixels. Color may be measured using CIE coordinates, which are well known to the art.

[0007] One example of a green emissive molecule is tris(2-phenylpyridine) iridium, denoted Ir(ppy)₃, which has the following structure:



[0008] In this, and later figures herein, we depict the dative bond from nitrogen to metal (here, Ir) as a straight line.

[0009] As used herein, the term "organic" includes polymeric materials as well as small molecule organic materials that may be used to fabricate organic opto-electronic devices. "Small molecule" refers to any organic material that is not a polymer, and "small molecules" may actually be quite large. Small molecules may include repeat units in some circumstances. For example, using a long chain alkyl group as a substituent does not remove a molecule from the "small molecule" class. Small molecules may also be incorporated into polymers, for example as a pendent group on a polymer backbone or as a part of the backbone. Small molecules may also serve as the core moiety of a dendrimer, which consists of a series of chemical shells built on the core moiety. The core moiety of a dendrimer may be a fluorescent or phosphorescent small molecule emitter. A dendrimer may be a "small molecule," and it is believed that all dendrimers

currently used in the field of OLEDs are small molecules.

[0010] As used herein, "top" means furthest away from the substrate, while "bottom" means closest to the substrate. Where a first layer is described as "disposed over" a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is "in contact with" the second layer. For example, a cathode may be described as "disposed over" an anode, even though there are various organic layers in between.

[0011] As used herein, "solution processible" means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

[0012] A ligand may be referred to as "photoactive" when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as "ancillary" when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.

[0013] As used herein, and as would be generally understood by one skilled in the art, a first "Highest Occupied Molecular Orbital" (HOMO) or "Lowest Unoccupied Molecular Orbital" (LUMO) energy level is "greater than" or "higher than" a second HOMO or LUMO energy level if the first energy level is closer to the vacuum energy level. Since ionization potentials (IP) are measured as a negative energy relative to a vacuum level, a higher HOMO energy level corresponds to an IP having a smaller absolute value (an IP that is less negative). Similarly, a higher LUMO energy level corresponds to an electron affinity (EA) having a smaller absolute value (an EA that is less negative). On a conventional energy level diagram, with the vacuum level at the top, the LUMO energy level of a material is higher than the HOMO energy level of the same material. A "higher" HOMO or LUMO energy level appears closer to the top of such a diagram than a "lower" HOMO or LUMO energy level.

[0014] As used herein, and as would be generally understood by one skilled in the art, a first work function is "greater than" or "higher than" a second work function if the first work function has a higher absolute value. Because work functions are generally measured as negative numbers relative to vacuum level, this means that a "higher" work function is more negative. On a conventional energy level diagram, with the vacuum level at the top, a "higher" work function is illustrated as further away from the vacuum level in the downward direction. Thus, the definitions of HOMO and LUMO energy levels follow a different convention than work functions.

[0015] More details on OLEDs, and the definitions described above, can be found in US Pat. No. 7,279,704, which is incorporated herein by reference in its entirety.

SUMMARY OF THE INVENTION

[0016] According to an embodiment, a composition comprising a first compound is disclosed. The first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature; wherein the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.

[0017] According to another embodiment, a first organic light emitting device is disclosed. The first organic light emitting device can include an anode, a cathode, and an organic layer, disposed between the anode and the cathode, wherein the organic layer can include a first compound; wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature; wherein the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.

[0018] According to yet another embodiment, a formulation comprising the first compound is disclosed, wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature and the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings, is disclosed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0019]

FIG. 1 shows an organic light emitting device.

FIG. 2 shows an inverted organic light emitting device that does not have a separate electron transport layer.

DETAILED DESCRIPTION

[0020] Generally, an OLED comprises at least one organic layer disposed between and electrically connected to an anode and a cathode. When a current is applied, the anode injects holes and the cathode injects electrons into the organic layer(s). The injected holes and electrons each migrate toward the oppositely charged electrode. When an electron and hole localize on the same molecule, an "exciton," which is a localized electron-hole pair having an excited energy state, is formed. Light is emitted when the exciton relaxes via a photoemissive mechanism. In some cases, the exciton may be localized on an excimer or an exciplex. Non-radiative mechanisms, such as thermal relaxation, may also occur, but are generally considered undesirable.

[0021] The initial OLEDs used emissive molecules that emitted light from their singlet states ("fluorescence") as disclosed, for example, in U.S. Pat. No. 4,769,292, which is incorporated by reference in its entirety. Fluorescent emission generally occurs in a time frame of less than 10 nanoseconds.

[0022] More recently, OLEDs having emissive materials that emit light from triplet states ("phosphorescence") have been demonstrated. Baldo et al., "Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices," *Nature*, vol. 395, 151-154, 1998; ("Baldo-I") and Baldo et al., "Very high-efficiency green organic light-emitting devices based on electrophosphorescence," *Appl. Phys. Lett.*, vol. 75, No. 3, 4-6 (1999) ("Baldo-II"), which are incorporated by reference in their entirety. Phosphorescence is described in more detail in US Pat. No. 7,279,704 at cols. 5-6, which are incorporated by reference.

[0023] FIG. 1 shows an organic light emitting device **100**. The figures are not necessarily drawn to scale. Device **100** may include a substrate **110**, an anode **115**, a hole injection layer **120**, a hole transport layer **125**, an electron blocking layer **130**, an emissive layer **135**, a hole blocking layer **140**, an electron transport layer **145**, an electron injection layer **150**, a protective layer **155**, a cathode **160**, and a barrier layer **170**. Cathode **160** is a compound cathode having a first conductive layer **162** and a second conductive layer **164**. Device **100** may be fabricated by depositing the layers described, in order. The properties and functions of these various layers, as well as example materials, are described in more detail in US 7,279,704 at cols. 6-10, which are incorporated by reference.

[0024] More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F₄-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of emissive and host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entirety, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entirety. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

[0025] FIG. 2 shows an inverted OLED **200**. The device includes a substrate **210**, a cathode **215**, an emissive layer **220**, a hole transport layer **225**, and an anode **230**. Device **200** may be fabricated by depositing the layers described, in order. Because the most common OLED configuration has a cathode disposed over the anode, and device **200** has cathode **215** disposed under anode **230**, device **200** may be referred to as an "inverted" OLED. Materials similar to those described with respect to device **100** may be used in the corresponding layers of device **200**. FIG. 2 provides one example of how some layers may be omitted from the structure of device **100**.

[0026] The simple layered structure illustrated in FIGS. 1 and 2 is provided by way of nonlimiting example, and it is understood that embodiments of the invention may be used in connection with a wide variety of other structures. The specific materials and structures described are exemplary in nature, and other materials and structures may be used. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely, based on design, performance, and cost factors. Other layers not specifically described may also be included. Materials other than those specifically described may be used. Although many of the examples provided herein describe various layers as comprising a single material, it is understood that combinations of materials, such as a mixture of host and dopant, or more generally a mixture, may be used. Also, the layers may have various sublayers. The names given to the various layers herein are not intended to be strictly limiting. For example, in device **200**, hole transport layer **225** transports holes and injects holes into emissive layer **220**, and may be described as a hole transport layer or a hole injection layer. In one embodiment, an OLED may be described as having an "organic layer" disposed between a cathode

and an anode. This organic layer may comprise a single layer, or may further comprise multiple layers of different organic materials as described, for example, with respect to FIGS. 1 and 2.

[0027] Structures and materials not specifically described may also be used, such as OLEDs comprised of polymeric materials (PLEDs) such as disclosed in U.S. Pat. No. 5,247,190 to Friend et al., which is incorporated by reference in its entirety. By way of further example, OLEDs having a single organic layer may be used. OLEDs may be stacked, for example as described in U.S. Pat. No. 5,707,745 to Forrest et al, which is incorporated by reference in its entirety. The OLED structure may deviate from the simple layered structure illustrated in FIGS. 1 and 2. For example, the substrate may include an angled reflective surface to improve out-coupling, such as a mesa structure as described in U.S. Pat. No. 6,091,195 to Forrest et al., and/or a pit structure as described in U.S. Pat. No. 5,834,893 to Bulovic et al., which are incorporated by reference in their entireties.

[0028] Unless otherwise specified, any of the layers of the various embodiments may be deposited by any suitable method. For the organic layers, preferred methods include thermal evaporation, ink-jet, such as described in U.S. Pat. Nos. 6,013,982 and 6,087,196, which are incorporated by reference in their entireties, organic vapor phase deposition (OVPD), such as described in U.S. Pat. No. 6,337,102 to Forrest et al., which is incorporated by reference in its entirety, and deposition by organic vapor jet printing (OVJP), such as described in U.S. Pat. No. 7,431,968, which is incorporated by reference in its entirety. Other suitable deposition methods include spin coating and other solution based processes. Solution based processes are preferably carried out in nitrogen or an inert atmosphere. For the other layers, preferred methods include thermal evaporation. Preferred patterning methods include deposition through a mask, cold welding such as described in U.S. Pat. Nos. 6,294,398 and 6,468,819, which are incorporated by reference in their entireties, and patterning associated with some of the deposition methods such as ink-jet and OVJD. Other methods may also be used. The materials to be deposited may be modified to make them compatible with a particular deposition method. For example, substituents such as alkyl and aryl groups, branched or unbranched, and preferably containing at least 3 carbons, may be used in small molecules to enhance their ability to undergo solution processing. Substituents having 20 carbons or more may be used, and 3-20 carbons is a preferred range. Materials with asymmetric structures may have better solution processibility than those having symmetric structures, because asymmetric materials may have a lower tendency to recrystallize. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing.

[0029] Devices fabricated in accordance with embodiments of the present invention may further optionally comprise a barrier layer. One purpose of the barrier layer is to protect the electrodes and organic layers from damaging exposure to harmful species in the environment including moisture, vapor and/or gases, etc. The barrier layer may be deposited over, under or next to a substrate, an electrode, or over any other parts of a device including an edge. The barrier layer may comprise a single layer, or multiple layers. The barrier layer may be formed by various known chemical vapor deposition techniques and may include compositions having a single phase as well as compositions having multiple phases. Any suitable material or combination of materials may be used for the barrier layer. The barrier layer may incorporate an inorganic or an organic compound or both. The preferred barrier layer comprises a mixture of a polymeric material and a non-polymeric material as described in U.S. Pat. No. 7,968,146, PCT Pat. Application Nos. PCT/US2007/023098 and PCT/US2009/042829, which are herein incorporated by reference in their entireties. To be considered a "mixture", the aforesaid polymeric and non-polymeric materials comprising the barrier layer should be deposited under the same reaction conditions and/or at the same time. The weight ratio of polymeric to non-polymeric material may be in the range of 95:5 to 5:95. The polymeric material and the non-polymeric material may be created from the same precursor material. In one example, the mixture of a polymeric material and a non-polymeric material consists essentially of polymeric silicon and inorganic silicon.

[0030] Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of electronic component modules (or units) that can be incorporated into a variety of electronic products or intermediate components. Examples of such electronic products or intermediate components include display screens, lighting devices such as discrete light source devices or lighting panels, etc. that can be utilized by the end-user product manufacturers. Such electronic component modules can optionally include the driving electronics and/or power source(s). Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. Such consumer products would include any kind of products that include one or more light source(s) and/or one or more of some type of visual displays. Some examples of such consumer products include flat panel displays, computer monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, laser printers, telephones, cell phones, tablets, phablets, personal digital assistants (PDAs), laptop computers, digital cameras, camcorders, viewfinders, micro-displays, 3-D displays, vehicles, a large area wall, theater or stadium screen, or a sign. Various control mechanisms may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix. Many of the devices are intended for use in a temperature range comfortable to humans, such as 18 degrees C. to 30 degrees C., and more preferably at room temperature (20-25 degrees C), but could be used outside this temperature range, for example, from -40 degree

C to + 80 degree C.

[0031] The materials and structures described herein may have applications in devices other than OLEDs. For example, other optoelectronic devices such as organic solar cells and organic photodetectors may employ the materials and structures. More generally, organic devices, such as organic transistors, may employ the materials and structures.

[0032] The term "halo," "halogen," or "halide" as used herein includes fluorine, chlorine, bromine, and iodine.

[0033] The term "alkyl" as used herein contemplates both straight and branched chain alkyl radicals. Preferred alkyl groups are those containing from one to fifteen carbon atoms and includes methyl, ethyl, propyl, isopropyl, butyl, isobutyl, tert-butyl, and the like. Additionally, the alkyl group may be optionally substituted.

[0034] The term "cycloalkyl" as used herein contemplates cyclic alkyl radicals. Preferred cycloalkyl groups are those containing 3 to 7 carbon atoms and includes cyclopropyl, cyclopentyl, cyclohexyl, and the like. Additionally, the cycloalkyl group may be optionally substituted.

[0035] The term "alkenyl" as used herein contemplates both straight and branched chain alkene radicals. Preferred alkenyl groups are those containing two to fifteen carbon atoms. Additionally, the alkenyl group may be optionally substituted.

[0036] The term "alkynyl" as used herein contemplates both straight and branched chain alkyne radicals. Preferred alkynyl groups are those containing two to fifteen carbon atoms. Additionally, the alkynyl group may be optionally substituted.

[0037] The terms "aralkyl" or "arylalkyl" as used herein are used interchangeably and contemplate an alkyl group that has as a substituent an aromatic group. Additionally, the aralkyl group may be optionally substituted.

[0038] The term "heterocyclic group" as used herein contemplates aromatic and non-aromatic cyclic radicals. Hetero-aromatic cyclic radicals also means heteroaryl. Preferred hetero-non-aromatic cyclic groups are those containing 3 or 7 ring atoms which includes at least one hetero atom, and includes cyclic amines such as morpholino, piperidino, pyrrolidino, and the like, and cyclic ethers, such as tetrahydrofuran, tetrahydropyran, and the like. Additionally, the heterocyclic group may be optionally substituted.

[0039] The term "aryl" or "aromatic group" as used herein contemplates single-ring groups and polycyclic ring systems having 6 to 30 carbon atoms, preferably 6 to 18 carbons. The polycyclic rings may have two or more rings in which two carbons are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is aromatic, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Additionally, the aryl group may be optionally substituted.

[0040] The term "heteroaryl" as used herein includes hetero-aromatic groups that may include 3 to 30 carbon atoms, preferably 3 to 18 carbons in the ring and contemplates single-ring hetero-aromatic groups that may include from one to three heteroatoms, for example, pyrrole, furan, thiophene, imidazole, oxazole, thiazole, triazole, pyrazole, pyridine, pyrazine and pyrimidine, and the like. The term heteroaryl also includes polycyclic hetero-aromatic systems having two or more rings in which two atoms are common to two adjoining rings (the rings are "fused") wherein at least one of the rings is a heteroaryl, e.g., the other rings can be cycloalkyls, cycloalkenyls, aryl, heterocycles, and/or heteroaryls. Additionally, the heteroaryl group may be optionally substituted.

[0041] The alkyl, cycloalkyl, alkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl may be optionally substituted with one or more substituents selected from the group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, cyclic amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ether, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0042] As used herein, "substituted" indicates that a substituent other than H is bonded to the relevant position, such as carbon. Thus, for example, where R¹ is mono-substituted, then one R¹ must be other than H. Similarly, where R¹ is di-substituted, then two of R¹ must be other than H. Similarly, where R¹ is unsubstituted, R¹ is hydrogen for all available positions.

[0043] The "aza" designation in the fragments described herein, i.e. aza-dibenzofuran, aza-dibenzothiophene, etc. means that one or more of the C-H groups in the respective fragment can be replaced by a nitrogen atom, for example, and without any limitation, azatriphenylene encompasses both dibenzo[f,h]quinoxaline and dibenzo[f,h]quinoline. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.

[0044] The "silylated" or "germanylated" designation in the fragments described herein, i.e. silylated alkyl, germanylated alkyl, etc. means that one or more of the C atoms in the respective fragment can be replaced by a Si or Ge atom.

[0045] It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene, dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.

[0046] According to an aspect of the present disclosure, a composition comprising a first compound is disclosed. The first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room tem-

perature and the first compound has at least one aromatic ring and at least one substituent R;
 wherein each of the at least one R is an organic group having at least two atoms of X;
 wherein each X is independently selected from the group consisting of Si, and Ge; and
 wherein each of the at least one R is directly bonded to one of the aromatic rings.

[0047] In some embodiments of the first compound, each X is separated by at least one carbon atom from the aromatic ring. In some embodiments, each X is separated by at least two carbon atoms from the aromatic ring. In other embodiments, each X is separated by at least three carbon atoms from the aromatic ring.

[0048] In some embodiments, each X is Si. In some embodiments, each X is Ge. In some embodiments, each X connects to its adjacent atoms by X-C or X-F bond only. In other embodiments, each X connects to its adjacent atom by X-C bond only.

[0049] The first compound is capable of emitting light from a triplet excited state to a ground singlet state at room temperature.

[0050] In a preferred embodiment, the first compound is a metal coordination complex having a metal-carbon bond. The metal can be selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, Au, and Cu. In some embodiments, the metal is Ir. In some embodiments, the metal is Pt.

[0051] In some embodiments, each of the at least one R is an organic group having at least three atoms of X. In some embodiments, each of the at least one R is independently selected from the group consisting of partially or fully silylated alkyl, partially or fully silylated cycloalkyl, partially or fully germanylated alkyl, partially or fully germanylated cycloalkyl, and combinations thereof.

[0052] In one preferred embodiment, the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$;

wherein L^1 , L^2 and L^3 can be the same or different;


wherein x is 1, 2, or 3;

wherein y is 0, 1, or 2;

wherein z is 0, 1, or 2;

wherein M is a metal and $x+y+z$ is the oxidation state of the metal M;


wherein L^1 , L^2 and L^3 are each independently selected from the group consisting of:



5

10

15




20

25

30


35




40

45

50



55



wherein each X¹ to X¹³ are independently selected from the group consisting of carbon and nitrogen;
 wherein X is selected from the group consisting of BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR'R'', SiR'R'', and GeR'R'';

wherein R' and R'' are optionally fused or joined to form a ring;

wherein each R_a, R_b, R_c, and R_d may represent from mono substitution to the possible maximum number of substitution, or no substitution;


wherein R', R'', R_a, R_b, R_c, and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; and

wherein any two adjacent substituents of R_a, R_b, R_c, and R_d are optionally fused or joined to form a ring or form a multidentate ligand; and

wherein at least one of the R_a, R_b, R_c, and R_d includes at least one R.

[0053] In some embodiments of the first compound having the formula of M(L¹)_x(L²)_y(L³)_z defined above, the first compound has the formula of Ir(L¹)₂(L²).

[0054] In the embodiment of the first compound having the formula of Ir(L¹)₂(L²), L¹ can have the formula selected from the group consisting of:




and

15 wherein L² has the formula:




In other embodiments, L² has the formula:




35 wherein R_e, R_f, R_h, and R_i are independently selected from group consisting of alkyl, cycloalkyl, aryl, and heteroaryl;
 wherein at least one of R_e, R_f, R_h, and R_i has at least two carbon atoms;
 wherein R_g is selected from group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl,
 40 alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic
 acid, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.


40 **[0055]** In some embodiments of the first compound having the formula of Ir(L¹)₂(L²), L¹ and L² can be different and
 each of L¹ and L² are independently selected from the group consisting of:



and



[0056] In some embodiments of the first compound having the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$, each of L^1 and L^2 can be independently selected from the group consisting of:




[0057] In the embodiment where the first compound has the formula of $\text{M}(\text{L}^1)_x(\text{L}^2)_y(\text{L}^3)_z$ defined above, the first compound can have the formula of $\text{Pt}(\text{L}^1)_2$ or $\text{Pt}(\text{L}^1)(\text{L}^2)$.

[0058] Where the first compound has the formula of $\text{Pt}(\text{L}^1)_2$ or $\text{Pt}(\text{L}^1)(\text{L}^2)$, L^1 can be connected to the other L^1 or L^2 to form a tetradentate ligand.







[0059] In the embodiment where the first compound has the formula of $\text{M}(\text{L}^1)_x(\text{L}^2)_y(\text{L}^3)_z$ defined above, at least one of R_a , R_b , R_c , and R_d includes an alkyl or cycloalkyl group that includes CD , CD_2 , or CD_3 , wherein D is deuterium.




[0060] In some embodiments of the first compound, each of the at least one R is selected from the group consisting of:




wherein R_U , R_V , R_W , R_X , R_Y , and R_Z are each independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

[0061] In some embodiments of the first compound, each of the at least one R is independently selected from the group consisting of:










and












[0062] In some embodiments where the first compound has the formula of $\text{M}(\text{L}^1)_x(\text{L}^2)_y(\text{L}^3)_z$ defined above, at least one of L^1 , L^2 , and L^3 is selected from the group consisting of:

















(continued)

wherein in L_{A31} $R^5 = R^{A1}$, $R^1 = R^{B1}$ in L_{A32} $R^5 = R^{A2}$, $R^1 = R^{B1}$ in L_{A33} $R^5 = R^{A3}$, $R^1 = R^{B1}$ in L_{A34} $R^5 = R^{A4}$, $R^1 = R^{B1}$ in L_{A35} $R^5 = R^{A5}$, $R^1 = R^{B1}$ in L_{A36} $R^5 = R^{A1}$, $R^1 = R^{B2}$ in L_{A37} $R^5 = R^{A2}$, $R^1 = R^{B2}$ in L_{A38} $R^5 = R^{A3}$, $R^1 = R^{B2}$ in L_{A39} $R^5 = R^{A4}$, $R^1 = R^{B2}$ in L_{A40} $R^5 = R^{A5}$, $R^1 = R^{B2}$ L_{A61} to L_{A70} , each represented by the formulawherein in L_{A61} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A62} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A63} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A64} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A65} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A66} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A67} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A68} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A69} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A70} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A91} to L_{A100} , each represented by the formulawherein in L_{A41} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A42} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A43} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A44} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A45} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A46} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A47} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A48} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A49} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A50} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A71} to L_{A80} , each represented by the formulawherein in L_{A71} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A72} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A73} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A74} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A75} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A76} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A77} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A78} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A79} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A80} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A101} to L_{A110} , each represented by the formulawherein in L_{A51} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A52} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A53} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A54} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A55} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A56} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A57} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A58} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A59} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A60} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A81} to L_{A90} , each represented by the formulawherein in L_{A81} $R^2 = R^{A1}$, $R^1 = R^{B1}$ in L_{A82} $R^2 = R^{A2}$, $R^1 = R^{B1}$ in L_{A83} $R^2 = R^{A3}$, $R^1 = R^{B1}$ in L_{A84} $R^2 = R^{A4}$, $R^1 = R^{B1}$ in L_{A85} $R^2 = R^{A5}$, $R^1 = R^{B1}$ in L_{A86} $R^2 = R^{A1}$, $R^1 = R^{B2}$ in L_{A87} $R^2 = R^{A2}$, $R^1 = R^{B2}$ in L_{A88} $R^2 = R^{A3}$, $R^1 = R^{B2}$ in L_{A89} $R^2 = R^{A4}$, $R^1 = R^{B2}$ in L_{A90} $R^2 = R^{A5}$, $R^1 = R^{B2}$ L_{A111} to L_{A120} , each represented by the formulawherein in L_{A111} $R^3 = R^{A1}$


(continued)

wherein in L_{A91} $R^3 = R^{A1}$, R^1 $= R^{B1}$ wherein in L_{A101} $R^4 = R^{A1}$, R^1
 $= R^{B1}$ $R^1 = R^{B1}$ in L_{A92} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A93} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A94} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A95} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A96} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A97} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A98} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A99} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A100} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A121} to L_{A130} , each represented by
the formulawherein in L_{A121} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A122} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A123} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A124} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A125} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A126} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A127} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A128} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A129} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A130} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A151} to L_{A160} , each represented by
the formulawherein in L_{A151} $R^2 = R^{A1}$, $R^1 = R^{B1}$ in L_{A152} $R^2 = R^{A2}$, $R^1 = R^{B1}$ in L_{A153} $R^2 = R^{A3}$, $R^1 = R^{B1}$ in L_{A154} $R^2 = R^{A4}$, $R^1 = R^{B1}$ in L_{A155} $R^2 = R^{A5}$, $R^1 = R^{B1}$ in L_{A156} $R^2 = R^{A1}$, $R^1 = R^{B2}$ in L_{A157} $R^2 = R^{A2}$, $R^1 = R^{B2}$ in L_{A102} $R^4 = R^{A2}$, $R^1 = R^{B1}$ in L_{A103} $R^4 = R^{A3}$, $R^1 = R^{B1}$ in L_{A104} $R^4 = R^{A4}$, $R^1 = R^{B1}$ in L_{A105} $R^4 = R^{A5}$, $R^1 = R^{B1}$ in L_{A106} $R^4 = R^{A1}$, $R^1 = R^{B2}$ in L_{A107} $R^4 = R^{A2}$, $R^1 = R^{B2}$ in L_{A108} $R^4 = R^{A3}$, $R^1 = R^{B2}$ in L_{A109} $R^4 = R^{A4}$, $R^1 = R^{B2}$ in L_{A110} $R^4 = R^{A5}$, $R^1 = R^{B2}$, L_{A131} to L_{A140} , each represented by
the formulawherein in L_{A131} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A132} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A133} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A134} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A135} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A136} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A137} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A138} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A139} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A140} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A161} to L_{A170} , each represented by
the formulawherein in L_{A161} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A162} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A163} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A164} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A165} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A166} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A167} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A112} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A113} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A114} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A115} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A116} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A117} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A118} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A119} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A120} $R^3 = R^{A5}$, $R^1 = R^{B2}$, L_{A141} to L_{A150} , each represented by
the formulawherein in L_{A141} $R^3 = R^{A1}$, $R^1 = R^{B1}$ in L_{A142} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A143} $R^3 = R^{A3}$, $R^1 = R^{B1}$ in L_{A144} $R^3 = R^{A4}$, $R^1 = R^{B1}$ in L_{A145} $R^3 = R^{A5}$, $R^1 = R^{B1}$ in L_{A146} $R^3 = R^{A1}$, $R^1 = R^{B2}$ in L_{A147} $R^3 = R^{A2}$, $R^1 = R^{B2}$ in L_{A148} $R^3 = R^{A3}$, $R^1 = R^{B2}$ in L_{A149} $R^3 = R^{A4}$, $R^1 = R^{B2}$ in L_{A150} $R^3 = R^{A5}$, $R^1 = R^{B2}$ L_{A171} to L_{A180} , each represented by
the formulawherein in L_{A171} $R^4 = R^{A1}$, $R^1 = R^{B1}$ in L_{A172} $R^4 = R^{A2}$, $R^1 = R^{B1}$ in L_{A173} $R^4 = R^{A3}$, $R^1 = R^{B1}$ in L_{A174} $R^4 = R^{A4}$, $R^1 = R^{B1}$ in L_{A175} $R^4 = R^{A5}$, $R^1 = R^{B1}$ in L_{A176} $R^4 = R^{A1}$, $R^1 = R^{B2}$ in L_{A177} $R^4 = R^{A2}$, $R^1 = R^{B2}$


(continued)

in L_{A158} $R^2 = RA^3$, $R^1 = RB^2$ in L_{A159} $R^2 = RA^4$, $R^1 = RB^2$ in L_{A160} $R^2 = RA^5$, $R^1 = RB^2$ L_{A181} to L_{A190} , each represented by the formulawherein in L_{A181} $R^2 = RA^1$, $R^1 = RB^1$ in L_{A182} $R^2 = RA^2$, $R^1 = RB^1$ in L_{A183} $R^2 = RA^3$, $R^1 = RB^1$ in L_{A184} $R^2 = RA^4$, $R^1 = RB^1$ in L_{A185} $R^2 = RA^5$, $R^1 = RB^1$ in L_{A186} $R^2 = RA^1$, $R^1 = RB^2$ in L_{A187} $R^2 = RA^2$, $R^1 = RB^2$ in L_{A188} $R^2 = RA^3$, $R^1 = RB^2$ in L_{A189} $R^2 = RA^4$, $R^1 = RB^2$ in L_{A190} $R^2 = RA^5$, $R^1 = RB^2$ L_{A211} to L_{A220} , each represented by the formulawherein in L_{A211} $R^5 = RA^1$, $R^1 = RB^1$ in L_{A212} $R^5 = RA^2$, $R^1 = RB^1$ in L_{A213} $R^5 = RA^3$, $R^1 = RB^1$ in L_{A214} $R^5 = RA^4$, $R^1 = RB^1$ in L_{A215} $R^5 = RA^5$, $R^1 = RB^1$ in L_{A216} $R^5 = RA^1$, $R^1 = RB^2$ in L_{A217} $R^5 = RA^2$, $R^1 = RB^2$ in L_{A218} $R^5 = RA^3$, $R^1 = RB^2$ in L_{A219} $R^5 = RA^4$, $R^1 = RB^2$ in L_{A220} $R^5 = RA^5$, $R^1 = RB^2$ L_{A241} to L_{A250} , each represented by the formulain L_{A168} $R^3 = RA^3$, $R^1 = RB^2$ in L_{A169} $R^3 = RA^4$, $R^1 = RB^2$ in L_{A170} $R^3 = RA^5$, $R^1 = RB^2$ L_{A191} to L_{A200} , each represented by the formulawherein in L_{A191} $R^3 = RA^1$, $R^1 = RB^1$ in L_{A192} $R^3 = RA^2$, $R^1 = RB^1$ in L_{A193} $R^3 = RA^3$, $R^1 = RB^1$ in L_{A194} $R^3 = RA^4$, $R^1 = RB^1$ in L_{A195} $R^3 = RA^5$, $R^1 = RB^1$ in L_{A196} $R^3 = RA^1$, $R^1 = RB^2$ in L_{A197} $R^3 = RA^2$, $R^1 = RB^2$ in L_{A198} $R^3 = RA^3$, $R^1 = RB^2$ in L_{A199} $R^3 = RA^4$, $R^1 = RB^2$ in L_{A200} $R^3 = RA^5$, $R^1 = RB^2$ L_{A221} to L_{A230} , each represented by the formulawherein in L_{A221} $R^2 = RA^1$, $R^1 = RB^1$ in L_{A222} $R^2 = RA^2$, $R^1 = RB^1$ in L_{A223} $R^2 = RA^3$, $R^1 = RB^1$ in L_{A224} $R^2 = RA^4$, $R^1 = RB^1$ in L_{A225} $R^2 = RA^5$, $R^1 = RB^1$ in L_{A226} $R^2 = RA^1$, $R^1 = RB^2$ in L_{A227} $R^2 = RA^2$, $R^1 = RB^2$ in L_{A228} $R^2 = RA^3$, $R^1 = RB^2$ in L_{A229} $R^2 = RA^4$, $R^1 = RB^2$ in L_{A230} $R^2 = RA^5$, $R^1 = RB^2$ in L_{A178} $R^4 = RA^3$, $R^1 = RB^2$ in L_{A179} $R^4 = RA^4$, $R^1 = RB^2$ in L_{A180} $R^4 = RA^5$, $R^1 = RB^2$ L_{A201} to L_{A210} , each represented by the formulawherein in L_{A201} $R^4 = RA^1$, $R^1 = RB^1$ in L_{A202} $R^4 = RA^2$, $R^1 = RB^1$ in L_{A203} $R^4 = RA^3$, $R^1 = RB^1$ in L_{A204} $R^4 = RA^4$, $R^1 = RB^1$ in L_{A205} $R^4 = RA^5$, $R^1 = RB^1$ in L_{A206} $R^4 = RA^1$, $R^1 = RB^2$ in L_{A207} $R^4 = RA^2$, $R^1 = RB^2$ in L_{A208} $R^4 = RA^3$, $R^1 = RB^2$ in L_{A209} $R^4 = RA^4$, $R^1 = RB^2$ in L_{A210} $R^4 = RA^5$, $R^1 = RB^2$ L_{A231} to L_{A240} , each represented by the formulawherein in L_{A231} $R^2 = RA^1$, $R^1 = RB^1$ in L_{A232} $R^2 = RA^2$, $R^1 = RB^1$ in L_{A233} $R^2 = RA^3$, $R^1 = RB^1$ in L_{A234} $R^2 = RA^4$, $R^1 = RB^1$ in L_{A235} $R^2 = RA^5$, $R^1 = RB^1$ in L_{A236} $R^2 = RA^1$, $R^1 = RB^2$ in L_{A237} $R^2 = RA^2$, $R^1 = RB^2$ in L_{A238} $R^2 = RA^3$, $R^1 = RB^2$ in L_{A239} $R^2 = RA^4$, $R^1 = RB^2$ in L_{A240} $R^2 = RA^5$, $R^1 = RB^2$


(continued)

L_{A251} to L_{A260}, each represented by the formula


wherein in L_{A251} R³ = R^{A1}, R¹ = R^{B1}
 in L_{A252} R³ = R^{A2}, R¹ = R^{B1}
 in L_{A253} R³ = R^{A3}, R¹ = R^{B1}
 in L_{A254} R³ = R^{A4}, R¹ = R^{B1}
 in L_{A255} R³ = R^{A5}, R¹ = R^{B1}
 in L_{A256} R³ = R^{A1}, R¹ = R^{B2}
 in L_{A257} R³ = R^{A2}, R¹ = R^{B2}
 in L_{A258} R³ = R^{A3}, R¹ = R^{B2}
 in L_{A259} R³ = R^{A4}, R¹ = R^{B2}
 in L_{A260} R³ = R^{A5}, R¹ = R^{B2},

L_{A281} to L_{A290}, each represented by the formulawherein in L_{A281} R³ = R^{A1}, R¹

in L_{A282} R³ = R^{A2}, R¹ = R^{B1}
 in L_{A283} R³ = R^{A3}, R¹ = R^{B1}
 in L_{A284} R³ = R^{A4}, R¹ = R^{B1}
 in L_{A285} R³ = R^{A5}, R¹ = R^{B1}
 in L_{A286} R³ = R^{A1}, R¹ = R^{B2}
 in L_{A287} R³ = R^{A2}, R¹ = R^{B2}
 in L_{A288} R³ = R^{A3}, R¹ = R^{B2}
 in L_{A289} R³ = R^{A4}, R¹ = R^{B2}
 in L_{A290} R³ = R^{A5}, R¹ = R^{B2}

L_{A261} to L_{A270}, each represented by the formula


wherein in L_{A261} R³ = R^{A1}, R¹ = R^{B1}
 in L_{A262} R³ = R^{A2}, R¹ = R^{B1}
 in L_{A263} R³ = R^{A3}, R¹ = R^{B1}
 in L_{A264} R³ = R^{A4}, R¹ = R^{B1}
 in L_{A265} R³ = R^{A5}, R¹ = R^{B1}
 in L_{A266} R³ = R^{A1}, R¹ = R^{B2}
 in L_{A267} R³ = R^{A2}, R¹ = R^{B2}
 in L_{A268} R³ = R^{A3}, R¹ = R^{B2}
 in L_{A269} R³ = R^{A4}, R¹ = R^{B2}
 in L_{A270} R³ = R^{A5}, R¹ = R^{B2}
 L_{A291} to L_{A300}, each represented by the formula

= R^{B1} wherein in L_{A291} R³ = R^{A1}, R¹ = R^{B1}

in L_{A292} R³ = R^{A2}, R¹ = R^{B1}
 in L_{A293} R³ = R^{A3}, R¹ = R^{B1}
 in L_{A294} R³ = R^{A4}, R¹ = R^{B1}
 in L_{A295} R³ = R^{A5}, R¹ = R^{B1}
 in L_{A296} R³ = R^{A1}, R¹ = R^{B2}
 in L_{A297} R³ = R^{A2}, R¹ = R^{B2}
 in L_{A298} R³ = R^{A3}, R¹ = R^{B2}
 in L_{A299} R³ = R^{A4}, R¹ = R^{B2}
 in L_{A300} R³ = R^{A5}, R¹ = R^{B2}

(continued)

L_{A301} to L_{A310} , each represented by the formula



wherein in L_{A301} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A302} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A303} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A304} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A305} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A306} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A307} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A308} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A309} $R^3 = R^{A4}$, $R^1 = R^{B2}$


in L_{A310} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A331} to L_{A332} , each represented by the formula



wherein in L_{A331} $R^1 = R^{B1}$ in L_{A332} $R^1 = R^{B2}$,


L_{A337} to L_{A338} , each represented by the formula



wherein in L_{A337} $R^1 = R^{B1}$ and in L_{A338} $R^1 = R^{B2}$;

wherein R^{A1} to R^{A5} have the following structures:

L_{A311} to L_{A320} , each represented by the formula



wherein in L_{A311} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A312} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A313} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A314} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A315} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A316} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A317} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A318} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A319} $R^3 = R^{A4}$, $R^1 = R^{B2}$


in L_{A320} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A333} to L_{A334} , each represented by the formula



wherein in L_{A333} $R^1 = R^{B1}$ in L_{A334} $R^1 = R^{B2}$,

L_{A321} to L_{A330} , each represented by the formula



wherein in L_{A321} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A322} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A323} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A324} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A325} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A326} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A327} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A328} $R^3 = R^{A3}$, $R^1 = R^{B2}$



in L_{A329} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A330} $R^3 = R^{A5}$, $R^1 = R^{B2}$,


L_{A335} to L_{A336} , each represented by the formula




wherein in L_{A335} $R^1 = R^{B1}$ in L_{A336} $R^1 = R^{B2}$,



wherein R^{B1} and R^{B2} have the following structures:



[0064] In the embodiments where the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$ defined above and the ligand L^1 is selected from the group consisting of L_{A1} to L_{A338} , the first compound can be selected from the group consisting of Compound 1 through Compound 4,394; where each Compound x has the formula $Ir(L_{Ak})_2(L_{Bj})$; wherein $x = 338j + k$ - 338, k is an integer from 1 to 338, and j is an integer from 1 to 13; wherein L_{B1} through L_{B13} are defined as follows:



[0065] According to another aspect of the present disclosure, a first organic light emitting device is disclosed. The first organic light emitting device comprises:


an anode;
 a cathode; and
 an organic layer, disposed between the anode and the cathode, comprising a first compound;
 wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device
 at room temperature;
 wherein the first compound has at least one aromatic ring and at least one substituent R;
 wherein each of the at least one R is an organic group having at least two atoms of X;
 wherein each X is independently selected from the group consisting of Si, and Ge; and
 wherein each of the at least one R is directly bonded to one of the aromatic rings.






[0066] In some embodiments, the first compound can be an emissive dopant. In some embodiments, the compound can produce emissions via phosphorescence, fluorescence, thermally activated delayed fluorescence, i.e., TADF (also referred to as E-type delayed fluorescence), triplet-triplet annihilation, or combinations of these processes.


[0067] The first organic light emitting device can be incorporated into a device selected from the group consisting of a consumer product, an electronic component module, and a lighting panel. The organic layer can be an emissive layer and the compound can be an emissive dopant in some embodiments, while the compound can be a non-emissive dopant in other embodiments.

[0068] The organic layer can also include a host. In some embodiments, the host can include a metal complex. The host can be a triphenylene containing benzo-fused thiophene or benzo-fused furan. Any substituent in the host can be an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv C-C_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , and $C_nH_{2n}-Ar_1$, or no substitution. In the preceding substituents n can range from 1 to 10; and Ar_1 and Ar_2 can be independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.

[0069] The host can be a compound comprising at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and aza-dibenzoselenophene. The host can include a metal complex. The host can be a specific compound selected from the group consisting of:







and combinations thereof.

[0070] In yet another aspect of the present disclosure, a formulation comprising the first compound is disclosed, wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature and the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings. is disclosed. The formulation can include one or more components selected from the group consisting of a solvent, a host, a hole injection material, hole transport material, and an electron transport layer material, disclosed herein.


COMBINATION WITH OTHER MATERIALS

[0071] The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. For example, emissive dopants disclosed herein may be used in conjunction with a wide variety of hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The materials described or referred to below are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.

HIL/HTL:


[0072] A hole injecting/transporting material to be used in the present invention is not particularly limited, and any compound may be used as long as the compound is typically used as a hole injecting/transporting material. Examples of the material include, but are not limited to: a phthalocyanine or porphyrin derivative; an aromatic amine derivative; an indolocarbazole derivative; a polymer containing fluorohydrocarbon; a polymer with conductivity dopants; a conducting polymer, such as PEDOT/PSS; a self-assembly monomer derived from compounds such as phosphonic acid and silane derivatives; a metal oxide derivative, such as MoO_x ; a p-type semiconducting organic compound, such as 1,4,5,8,9,12-Hexaazatriphenylenehexacarbonitrile; a metal complex, and a cross-linkable compound.

[0073] Examples of aromatic amine derivatives used in HIL or HTL include, but are not limited to the following general structures:




[0074] Each of Ar¹ to Ar⁹ is selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofurofuryridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each Ar is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0075] In one aspect, Ar¹ to Ar⁹ is independently selected from the group consisting of:



wherein k is an integer from 1 to 20; X¹⁰¹ to X¹⁰⁸ is C (including CH) or N; Z¹⁰¹ is NAr¹, O, or S; Ar¹ has the same group defined above.

[0076] Examples of metal complexes used in HIL or HTL include, but are not limited to the following general formula:




wherein Met is a metal, which can have an atomic weight greater than 40; (Y¹⁰¹-Y¹⁰²) is a bidentate ligand, Y¹⁰¹ and Y¹⁰² are independently selected from C, N, O, P, and S; L¹⁰¹ is an ancillary ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.

[0077] In one aspect, (Y¹⁰¹-Y¹⁰²) is a 2-phenylpyridine derivative. In another aspect, (Y¹⁰¹-Y¹⁰²) is a carbene ligand. In another aspect, Met is selected from Ir, Pt, Os, and Zn. In a further aspect, the metal complex has a smallest oxidation potential in solution vs. Fc⁺/Fc couple less than about 0.6 V.

Host:


[0078] The light emitting layer of the organic EL device of the present invention preferably contains at least a metal complex as light emitting material, and may contain a host material using the metal complex as a dopant material. Examples of the host material are not particularly limited, and any metal complexes or organic compounds may be used as long as the triplet energy of the host is larger than that of the dopant. While the Table below categorizes host materials as preferred for devices that emit various colors, any host material may be used with any dopant so long as the triplet criteria is satisfied.

[0079] Examples of metal complexes used as host are preferred to have the following general formula:



wherein Met is a metal; (Y¹⁰³-Y¹⁰⁴) is a bidentate ligand, Y¹⁰³ and Y¹⁰⁴ are independently selected from C, N, O, P, and S; L¹⁰¹ is an another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal; and k'+k'' is the maximum number of ligands that may be attached to the metal.

[0080] In one aspect, the metal complexes are:





wherein (O-N) is a bidentate ligand, having metal coordinated to atoms O and N.

[0081] In another aspect, Met is selected from Ir and Pt. In a further aspect, (Y¹⁰³-Y¹⁰⁴) is a carbene ligand.

[0082] Examples of organic compounds used as host are selected from the group consisting of aromatic hydrocarbon cyclic compounds such as benzene, biphenyl, triphenyl, triphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene; the group consisting of aromatic heterocyclic compounds such as dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyrindine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoxaline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyrindine, benzothienopyridine, thienodipyrindine, benzoselenophenopyridine, and selenophenodipyrindine; and the group consisting of 2 to 10 cyclic structural units which are groups of the same type or different types selected from the aromatic hydrocarbon cyclic group and the aromatic heterocyclic group and are bonded to each other directly or via at least one of oxygen atom, nitrogen atom, sulfur atom, silicon atom, phosphorus atom, boron atom, chain structural unit and the aliphatic cyclic group. Wherein each group is further substituted by a substituent selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.

[0083] In one aspect, the host compound contains at least one of the following groups in the molecule:





wherein R¹⁰¹ to R¹⁰⁷ is independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, when it is aryl or heteroaryl, it has the similar definition as Ar's mentioned above. k is an integer from 0 to 20 or 1 to 20; k' is an integer from 0 to 20. X¹⁰¹ to X¹⁰⁸ is selected from C (including CH) or N.


Z¹⁰¹ and Z¹⁰² is selected from NR¹⁰¹, O, or S.

HBL:

[0084] A hole blocking layer (HBL) may be used to reduce the number of holes and/or excitons that leave the emissive layer. The presence of such a blocking layer in a device may result in substantially higher efficiencies as compared to a similar device lacking a blocking layer. Also, a blocking layer may be used to confine emission to a desired region of an OLED.

[0085] In one aspect, compound used in HBL contains the same molecule or the same functional groups used as host described above.

[0086] In another aspect, compound used in HBL contains at least one of the following groups in the molecule:




wherein k is an integer from 1 to 20; L¹⁰¹ is an another ligand, k' is an integer from 1 to 3.

ETL:


[0087] Electron transport layer (ETL) may include a material capable of transporting electrons. Electron transport layer may be intrinsic (undoped), or doped. Doping may be used to enhance conductivity. Examples of the ETL material are not particularly limited, and any metal complexes or organic compounds may be used as long as they are typically used to transport electrons.

[0088] In one aspect, compound used in ETL contains at least one of the following groups in the molecule:



wherein R^{101} is selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof, when it is aryl or heteroaryl, it has the similar definition as Ar 's mentioned above. Ar^1 to Ar^3 has the similar definition as Ar 's mentioned above. k is an integer from 1 to 20. X^{101} to X^{108} is selected from C (including CH) or N.

[0089] In another aspect, the metal complexes used in ETL include, but are not limited to the following general formula:



wherein (O-N) or (N-N) is a bidentate ligand, having metal coordinated to atoms O, N or N, N; L^{101} is another ligand; k' is an integer value from 1 to the maximum number of ligands that may be attached to the metal.






[0090] In any above-mentioned compounds used in each layer of the OLED device, the hydrogen atoms can be partially or fully deuterated. Thus, any specifically listed substituent, such as, without limitation, methyl, phenyl, pyridyl, etc. encompasses undeuterated, partially deuterated, and fully deuterated versions thereof. Similarly, classes of substituents such as, without limitation, alkyl, aryl, cycloalkyl, heteroaryl, etc. also encompass undeuterated, partially deuterated, and fully deuterated versions thereof.

[0091] In addition to and / or in combination with the materials disclosed herein, many hole injection materials, hole transporting materials, host materials, dopant materials, exciton/hole blocking layer materials, electron transporting and electron injecting materials may be used in an OLED. Non-limiting examples of the materials that may be used in an OLED in combination with materials disclosed herein are listed in Table A below. Table A lists non-limiting classes of materials, non-limiting examples of compounds for each class, and references that disclose the materials.






TABLE A

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Hole injection materials		
Phthalocyanine and porphyrin compounds		Appl. Phys. Lett. 69, 2160 (1996)







(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Starburst triarylamine		J. Lumin. 72-74, 985 (1997)
CF _x Fluorohydrocarbon polymer	$\left[\text{CH}_x\text{F}_y \right]_n$	Appl. Phys. Lett. 78, 673 (2001)
Conducting polymers (e.g., PEDOT:PSS, polyaniline, polythiophene)		Synth. Met. 87, 171 (1997) WO2007002683
Phosphonic acid and silane SAMs		US20030162053
Triarylamine or polythiophene polymers with conductivity dopants		EP1725079A1
Organic compounds with conductive inorganic compounds, such as molybdenum and tungsten oxides		US20050123751 SID Symposium Digest, 37, 923 (2006) WO2009018009







(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
n-type semiconducting organic complexes		US20020158242
Metal organometallic complexes		US20060240279
Cross-linkable compounds		US20080220265
Polythiophene based polymers and copolymers		WO 2011075644 EP2350216
Hole transporting materials		
Triarylamines (e.g., TPD, α -NPD)		Appl. Phys. Lett. 51, 913 (1987)

(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5 10 15		US5061569
		EP650955
20 25 30 35 40 45		J. Mater. Chem. 3, 319 (1993)
		Appl. Phys. Lett. 90, 183503 (2007)
		Appl. Phys. Lett. 90, 183503 (2007)
50 Triarylamine on spirofluorene core		Synth. Met. 91, 209 (1997)








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Arylamine carbazole compounds		Adv. Mater. 6, 677 (1994), US20080124572
Triarylamine with (di)benzothiophene/(di)benzofuran		US20070278938, US20080106190 US20110163302
Indolocarbazoles		Synth. Met. 111, 421 (2000)
Isoindole compounds		Chem. Mater. 15, 3148 (2003)
Metal carbene complexes		US20080018221
Phosphorescent OLED host materials		
Red hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)






(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Metal 8-hydroxyquinolates (e.g., Alq ₃ , BAlq)		Nature 395, 151 (1998)
		US20060202194
		WO2005014551
		WO2006072002
Metal phenoxybenzothiazole compounds		Appl. Phys. Lett. 90, 123509 (2007)
Conjugated oligomers and polymers (e.g., polyfluorene)		Org. Electron. 1, 15 (2000)
Aromatic fused rings		WO2009066779, WO2009066778, WO2009063833, US20090045731, US20090045730, WO2009008311, US20090008605, US20090009065
Zinc complexes		WO2010056066








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Chrysene based compounds		WO2011086863
Green hosts		
Arylcarbazoles		Appl. Phys. Lett. 78, 1622 (2001)
		US20030175553
		WO2001039234
Aryltriphenylene compounds		US20060280965
		US20060280965
		WO2009021126








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Poly-fused heteroaryl compounds		US20090309488 US20090302743 US20100012931
Donor acceptor type molecules		WO2008056746
		WO2010107244
Aza-carbazole/DBT/DBF		JP2008074939
		US20100187984








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Polymers (e.g., PVK)		Appl. Phys. Lett. 77, 2280 (2000)
Spirofluorene compounds		WO2004093207
Metal phenoxybenzoxazole compounds		WO2005089025
		WO2006132173
		JP200511610
Spirofluorene-carbazole compounds		JP2007254297
		JP2007254297








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Indolocarbazoles		WO2007063796
		WO2007063754
5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole)		J. Appl. Phys. 90, 5048 (2001)
		WO2004107822
Tetraphenylene complexes		US20050112407
Metal phenoxypyridine compounds		WO2005030900
Metal coordination complexes (e.g., Zn, Al with N^N ligands)		US20040137268, US20040137267
Blue hosts		








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Arylcarbazoles		Appl. Phys. Lett, 82, 2422 (2003)
		US20070190359
Dibenzothiophene/Dibenzofuran-carbazole compounds		WO2006114966, US20090167162
		US20090167162
		WO2009086028
		US20090030202, US20090017330
		US20100084966







(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Silicon aryl compounds		US20050238919
		WO2009003898
Silicon/Germanium aryl compounds		EP2034538A
Aryl benzoyl ester		WO2006100298
Carbazole linked by non-conjugated groups		US20040115476
Aza-carbazoles		US20060121308
High triplet metal organometallic complex		US7154114
Phosphorescent dopants		








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Red dopants		
Heavy metal porphyrins (e.g., PtOEP)		Nature 395, 151 (1998)
Iridium(III) organometallic complexes		Appl. Phys. Lett. 78, 1622 (2001)
		US20030072964
		US20030072964
		US20060202194
		US20060202194
		US20070087321






(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5 10 15 20 25		US20080261076 US20100090591
		US20070087321
		Adv. Mater. 19, 739 (2007)
30 35		WO2009100991
40 45		WO2008101842
50		US7232618








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Platinum(II) organometallic complexes		WO2003040257
		US20070103060
Osmium(III) complexes		Chem. Mater. 17, 3532 (2005)
Ruthenium(II) complexes		Adv. Mater. 17, 1059 (2005)
Rhenium (I), (II), and (III) complexes		US20050244673
Green dopants		
Iridium(III) organometallic complexes	 and its derivatives	Inorg. Chem. 40, 1704 (2001)
		US20020034656










(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5		US7332232
10 15 20		US20090108737
25 30		WO2010028151
35 40		EP1841834B
45 50		US20060127696







(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5		US20090039776
10		US6921915
15		US20100244004
20		US6687266
25		Chem. Mater. 16, 2480 (2004)
30		US20070190359
35		US 20060008670 JP2007123392






(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5		WO2010086089, WO2011044988
10		Adv. Mater. 16, 2003 (2004)
15		Angew. Chem. Int. Ed. 2006,45,7800
20		WO2009050290
25		US20090165846
30		US20080015355
35		US20010015432
40		
45		
50		
55		






(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20100295032
Monomer for polymeric metal organometallic compounds		US7250226, US7396598
Pt(II) organometallic complexes, including polydentate ligands		Appl. Phys. Lett. 86, 153505(2005)
		Appl. Phys. Lett. 86, 153505(2005)
		Chem. Lett. 34, 592 (2005)
		WO2002015645








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		US20060263635
		US20060182992 US20070103060
Cu complexes		WO2009000673
		US20070111026
Gold complexes		Chem. Commun. 2906 (2005)







(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Rhenium(III) complexes		Inorg. Chem. 42, 1248 (2003)
Osmium(II) complexes		US7279704
Deuterated organometallic complexes		US20030138657
Organometallic complexes with two or more metal centers		US20030152802
		US7090928
Blue dopants		








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Iridium(III) organometallic complexes		WO2002002714
		WO2006009024
		US20060251923 US20110057559 US20110204333
		US7393599, WO2006056418, US20050260441, WO2005019373
		US7534505
		WO2011051404
		US7445855








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5		US20070190359, US20080297033 US20100148663
10		US7338722
15		US20020134984
20		Angew. Chem. Int. Ed. 47, 4542 (2008)
25		Chem. Mater. 18, 5119 (2006)
30		Inorg. Chem. 46, 4308 (2007)





(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
		WO2005123873
		WO2005123873
		WO2007004380
		WO2006082742
Osmium(II) complexes		US7279704
		Organometallics 23, 3745 (2004)
Gold complexes		Appl. Phys. Lett. 74, 1361 (1999)








(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Platinum(II) complexes		WO2006098120, WO2006103874
Pt tetradentate complexes with at least one metal-carbene bond		US7655323
Exciton/hole blocking layer materials		
Bathocuproine compounds (e.g., BCP, BPhen)		Appl. Phys. Lett. 75, 4 (1999)
		Appl. Phys. Lett. 79, 449 (2001)
Metal 8-hydroxyquinolates (e.g., BAlq)		Appl. Phys. Lett. 81, 162 (2002)
5-member ring electron deficient heterocycles such as triazole, oxadiazole, imidazole, benzoimidazole		Appl. Phys. Lett. 81, 162 (2002)
Triphenylene compounds		US20050025993









(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5 10 15 Fluorinated aromatic compounds		Appl. Phys. Lett. 79, 156 (2001)
20 Phenothiazine-S-oxide		WO2008132085
25 30 Silylated five-membered nitrogen, oxygen, sulfur or phosphorus dibenzoheterocycles		WO2010079051
35 Aza-carbazoles		US20060121308
40 Electron transporting materials		



(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Anthracene-benzimidazole compounds		WO2003060956
		US20090179554
Aza triphenylene derivatives		US20090115316
Anthracene-benzothiazole compounds		Appl. Phys. Lett. 89, 063504 (2006)
Metal 8-hydroxyquinolates (e.g., Alq ₃ , Zrq ₄)		Appl. Phys. Lett. 51, 913 (1987) US7230107
Metal hydroxybenzoquinolates		Chem. Lett. 5, 905 (1993)
Bathocuproine compounds such as BCP, BPhen, etc		Appl. Phys. Lett. 91, 263503 (2007)

(continued)

MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
5		Appl. Phys. Lett. 79, 449 (2001)
10 15	5-member ring electron deficient heterocycles (e.g., triazole, oxadiazole, imidazole, benzoimidazole) 	Appl. Phys. Lett. 74, 865 (1999)
20		Appl. Phys. Lett. 55, 1489 (1989)
25		Jpn. J. Apply. Phys. 32, L917 (1993)
30 35	Silole compounds 	Org. Electron. 4, 113 (2003)
40	Arylborane compounds 	J. Am. Chem. Soc. 120, 9714 (1998)
45	Fluorinated aromatic compounds 	J. Am. Chem. Soc. 122, 1832 (2000)
50 55	Fullerene (e.g., C ₆₀) 	US20090101870

(continued)


MATERIAL	EXAMPLES OF MATERIAL	PUBLICATIONS
Triazine complexes		US20040036077
Zn (N^N) complexes		US6528187

Materials Synthesis

[0092] All reactions were carried out under nitrogen protections unless specified otherwise. All solvents for reactions are anhydrous and used as received from commercial sources.


Synthesis of Comparative Compound 1

[0093] Synthesis of 2-(3,5-dimethylphenyl)-5-(trimethylsilyl)quinoline.




A mixture of 5-bromo-2-(3,5-dimethylphenyl)quinoline (2.10 g, 6.73 mmol) and Tetrahydrofuran (20 mL) was cool in dry ice acetone bath and butyllithium (2.8 ml, 7.06 mmol) was added and stirred for 45 minutes. Chlorotrimethylsilane (0.88g, 8.07 mmol) was add and stirred for 20 min. The dry ice bath was removed and the reaction was stirred for 18 hours at room temperature. The reaction was quenched with methanol. The mixture was extracted with dichloromethane and then chromatographed residue on a silica gel column (hexanes: dichloromethane) and then rechromatographed on a C18 reverse phase column (90% acetonitrile: water). The acetonitrile was removed under vacuum to afford 2-(3,5-dimethylphenyl)-5-(trimethylsilyl)quinoline 1.2 g (58% yield).

[0094] Synthesis of the Ir(III) Dimer.



A mixture of 2-(3,5-dimethylphenyl)-5-(trimethylsilyl)quinoline (1.20 g, 3.93 mmol), Iridium Chloride (0.69 g, 1.87 mmol), ethoxyethanol (30 mL) and Water (10 mL) was refluxed under N₂ for 18 hours. The solids were filtered off and washed with methanol to give the Ir(III) Dimer (0.70 g, 45% yield).


15 **[0095] Synthesis of Comparative Compound 1.**



A mixture of Ir(III) Dimer (0.70 g, 0.42 mmol), pentane-2,4-dione (0.42 g, 4.18 mmol), potassium carbonate (0.58 g, 4.18 mmol) and ethoxyethanol (60 mL) was stirred at room temperature for 18 hours. The solids were filtered off and washed with methanol and then flash chromatographed (on a silica gel column that was pretreated with triethylamine) (80:20 % hexanes: dichloromethane). The resulting crystals were recrystallized by redissolving them in dichloromethane and 2-propanol and then removing the dichloromethane by rotoevaporation to afford the title compound (0.30g, 66% yield).


35 **Synthesis of Compound 196**

40 **[0096] Synthetic of (bis(trimethylsilyl)methyl)magnesium bromide**




Lithium chloride (2.21 g, 52.2 mmol) was placed in a dry nitrogen flushed flask and dried for 10 minutes with a heatgun. magnesium (turnings) (1.27 g, 52.2 mmol) were added and the flask was evacuated again and refilled with argon. Then, THF (40 mL) was added and after addition of chlorotrimethylsilane (0.05 mL, 0.42 mmol) and 1,2-dibromoethane (0.04 mL, 0.42 mmol), the suspension was heated until gas evolution occurred. The flask was cooled to 0 °C and (bromomethylene)bis(trimethylsilane) (10.0 g, 41.8 mmol) was added dropwise. After stirring for 30 minutes at this temperature, the solids were allowed to settle and the supernatant solution was carefully canulated and used as is.

55 **[0097] Synthetic of 2-(3,5-dimethylphenyl)-7-(4,4,4-trifluoro-3-(trifluoromethyl)butyl)quinoline**




5-bromo-2-(3,5-dimethylphenyl)quinoline (3.25 g, 10.41 mmol), diacetoxypalladium (0.09 g, 0.42 mmol), and dicyclohexyl(2',6'-dimethoxy-[1,1'-biphenyl]-2-yl)phosphane (Sphos) (0.34 g, 0.83 mmol) were inserted in a flask and solubilized in THF (40 mL). The solution was degassed by bubbling nitrogen gas for 15 minutes, the Grignard reagent (26 mL, 15.6 mmol) was added and the reaction was heated to 50 °C for 18 hours. Upon completion of the reaction, the mixture was extracted with ethyl acetate and washed with water and brine. The crude material was purified via column chromatography using heptanes/ethyl acetate (90/10) to afford 5-bis(trimethylsilyl)methyl-2-(3,5-dimethylphenyl)quinoline (3.80 g, 93 % yield).

[0098] Synthesis of Ir(III) Dimer.



5-bis(trimethylsilyl)methyl-2-(3,5-dimethylphenyl)quinoline (3.77 g, 9.61 mmol) was inserted in a RBF (round-bottom flask) and was solubilized in ethoxyethanol (32 mL) and water (11 mL). The mixture was degassed by bubbling nitrogen gas for 15 minutes and then chlorosyl(perchloryl)iridium(XI) chloride octahydride (0.95 g, 2.56 mmol) was inserted and the reaction was heated at 105 °C for 24 hours. The reaction was cooled down to room temperature. The Ir(III) Dimer was filtered and washed with MeOH to afford 1.50 g (58% yield) as a black powder.

[0099] Synthesis of Compound 196



Ir(III) Dimer (1.00 g, 0.50 mmol) was solubilized in ethoxyethanol (17 mL) and pentane-2,4-dione (0.51 mL, 4.96 mmol) was added. The mixture was degassed by bubbling nitrogen gas for 15 minutes. K₂CO₃ (0.69 g, 4.96 mmol) was then added and the reaction was stirred at room temperature. The reaction mixture was diluted with dichloromethane (DCM) and filtered through a plug of celite. After the solvents were evaporated, the product was redissolved in DCM and loaded on Celite®. The crude material was purified via column chromatography using TEA pre-treated column with heptanes/DCM (95/5) solvent system. Trituration from MeOH gave the pure product (0.75 g, 71 % yield).

Device examples

[0100] All example devices were fabricated by high vacuum ($<10^{-7}$ Torr) thermal evaporation. The anode electrode was 1200 Å of indium tin oxide (ITO). The cathode consisted of 10 Å of LiF followed by 1,000 Å of Al. All devices were encapsulated with a glass lid sealed with an epoxy resin in a nitrogen glove box (<1 ppm of H_2O and O_2) immediately after fabrication, and a moisture getter was incorporated inside the package. The organic stack of the device examples consisted of sequentially, from the ITO surface, 100 Å of LG101 (purchased from LG chem) as the hole injection layer (HIL); 400 Å of 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (NPD) as the hole transporting layer (HTL); 300 Å of an emissive layer (EML) containing Compound H as a host (79%), a stability dopant (SD) (18%), and Comparative Compound 1, and Compound 196 as an emitter; 100 Å of Compound H as a blocking layer; and 450 Å of AlQ_3 (tris-8-hydroxyquinoline aluminum) as the ETL. The emitter was selected to provide the desired color and the stability dopant (SD) was mixed with the electron-transporting host and the emitter to help transport positive charge in the emissive layer. The Comparative Example device was fabricated similarly to the device examples except that Comparative Compound 1 was used as the emitter in the EML.

[0101] Table 1 shows the composition of the EML in the device, while the device results and data are summarized in Table 2. As used herein, NPD, compound H, SD, and AlQ_3 have the following structures:




Table 1. Compounds of EML in the devices

Examples	Emitter
Device Example 1	Compound 196
Device Example 2	Comparative Example 1

Table 2. Device results of device examples 1, and 2.

Examples	1931 CIE		λ max [nm]	RelativeFWHM [nm]	Relative EQE at 1,000 nits [cd/A]	Relative LT95% at 1,000 nits [hours]
	x	y				
Device Example 1	0.65	0.34	618	0.97	1.11	1.15
Device Example 2	0.66	0.34	622	1.00	1.00	1.00

[0102] Table 2 summarizes the performance of the devices with relative values normalized to the comparative example.

The 1931 CIE values were measured at 10 mA/cm². The luminous efficiency was measured at 1000 cd/m². The inventive compounds showed a better EQE (external quantum efficiency) compared to the comparative compound (1.11 vs. 1.00) and also showed an improved device lifetime (LT95% at 1,000 nits) of 1.15 vs. 1.00. Moreover, the inventive compounds 196 showed an emission peak full width at half maximum (FWHM) that is narrower compared to the comparative compound (0.97 vs. 1.00) which helps to improve the emission color purity of the dopant.

[0103] It is understood that the various embodiments described herein are by way of example only, and are not intended to limit the scope of the invention. For example, many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. It is understood that various theories as to why the invention works are not intended to be limiting.

The invention is further described by the following numbered aspects:

1. A composition comprising a first compound; wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature; wherein the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.

2. The composition of aspect 1, wherein each X is separated by at least one carbon atom from the aromatic ring.

3. The composition of aspect 1, wherein each X is separated by at least two carbon atoms from the aromatic ring.

4. The composition of aspect 1, wherein each X is separated by at least three carbon atoms from the aromatic ring.

5. The composition of aspect 1, wherein each X is Si.

6. The composition of aspect 1, wherein each X is Ge.

7. The composition of aspect 1, wherein each X connects to its adjacent atoms by X-C or X-F bond only.

8. The composition of aspect 1, wherein each X connects to its adjacent atom by X-C bond only.

9. The composition of aspect 1, wherein the first compound is capable of emitting light from a triplet excited state to a ground singlet state at room temperature.

10. The composition of aspect 1, wherein the first compound is a metal coordination complex having a metal-carbon bond.

11. The composition of aspect 10, wherein the metal is selected from the group consisting of Ir, Rh, Re, Ru, Os, Pt, Au, and Cu.


12. The composition of aspect 10, wherein the metal is Ir.

13. The composition of aspect 10, wherein the metal is Pt.

14. The composition of aspect 1, wherein each of the at least one R is an organic group having at least three atoms of X.

15. The composition of aspect 1, wherein each of the at least one R is independently selected from the group consisting of partially or fully silylated alkyl, partially or fully silylated cycloalkyl, partially or fully germanylated alkyl, partially or fully germanylated cycloalkyl, and combinations thereof.


16. The composition of aspect 1, wherein the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$; wherein L^1 , L^2 and L^3 can be the same or different; wherein x is 1, 2, or 3; wherein y is 0, 1, or 2; wherein z is 0, 1, or 2; wherein M is a metal and $x+y+z$ is the oxidation state of the metal M ; wherein L^1 , L^2 and L^3 are each independently selected from the group consisting of:



5

10

15




20

25

30


35




40

45

50




55



wherein each X¹ to X¹³ are independently selected from the group consisting of carbon and nitrogen; wherein X is selected from the group consisting of BR', NR', PR', O, S, Se, C=O, S=O, SO₂, CR'R'', SiR'R'', and GeR'R''; wherein R' and R'' are optionally fused or joined to form a ring; wherein each R_a, R_b, R_c, and R_d may represent from mono substitution to the possible maximum number of substitution, or no substitution; wherein R', R'', R_a, R_b, R_c, and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; and wherein any two adjacent substituents of R_a, R_b, R_c, and R_d are optionally fused or joined to form a ring or form a multidentate ligand; and wherein at least one of the R_a, R_b, R_c, and R_d includes at least one R.

17. The composition of aspect 16, wherein the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$.

18. The composition of aspect 17, wherein L^1 has the formula selected from the group consisting of:



and

wherein L^2 has the formula:




19. The composition of aspect 18, wherein L^2 has the formula:




wherein R_e , R_f , R_h , and R_i are independently selected from group consisting of alkyl, cycloalkyl, aryl, and heteroaryl; wherein at least one of R_e , R_f , R_h , and R_i has at least two carbon atoms; wherein R_g is selected from group consisting of hydrogen, deuterium, halogen, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acid, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof.


20. The composition of aspect 17, wherein L^1 and L^2 are different and each independently selected from the group consisting of:



and



21. The composition of aspect 17, wherein L^1 and L^2 are each independently selected from the group consisting of:




22. The composition of aspect 16, wherein the first compound has the formula of $Pt(L^1)_2$ or $Pt(L^1)(L^2)$.

23. The composition of aspect 22, wherein L^1 is connected to the other L^1 or L^2 to form a tetradentate ligand.







24. The composition of aspect 16, wherein at least one of R_a , R_b , R_c , and R_d includes an alkyl or cycloalkyl group that includes CD , CD_2 , or CD_3 , wherein D is deuterium.




25. The composition of aspect 1, wherein each of the at least one R is selected from the group consisting of:




wherein R_U , R_V , R_W , R_X , R_Y , and R_Z are each independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.

26. The composition of aspect 1, wherein each of the at least one R is independently selected from the group consisting of:











and



27. The composition of aspect 16, wherein at least one of L^1 , L^2 , and L^3 is selected from the group consisting of:








and

wherein R_u , R_v , R_w , R_x , R_y , and R_z are each independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof. q is an integer from 1 to 5.

28. The first compound of aspect 16, wherein the ligand L^1 is L_A selected from the group consisting of:

L_{A1} to L_{A10} , each represented by the formula




wherein in L_{A1} , $R^2 = R^{A1}$,

$R^1 = R^{B1}$,

in L_{A2} , $R^2 = R^{A2}$, $R^1 = R^{B1}$,


L_{A11} to L_{A20} , each represented by the formula



wherein in L_{A11} , $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A12} $R^3 = R^{A2}$, $R^1 = R^{B1}$

L_{A21} to L_{A30} , each represented by the formula




wherein in L_{A21} $R^4 = R^{A1}$, $R^1 = R^{B1}$

in L_{A22} $R^4 = R^{A2}$, $R^1 = R^{B1}$


(continued)

in L_{A3} , $R^2 = RA^3$, $R^1 = RB^1$,
 in L_{A4} , $R^2 = RA^4$, $R^1 = RB^1$,
 in L_{A5} , $R^2 = RA^5$, $R^1 = RB^1$,
 in L_{A6} , $R^2 = RA^1$, $R^1 = RB^2$,
 in L_{A7} , $R^2 = RA^2$, $R^1 = RB^2$,
 in L_{A8} , $R^2 = RA^3$, $R^1 = RB^2$,
 in L_{A9} , $R^2 = RA^4$, $R^1 = RB^2$,
 in L_{A10} , $R^2 = RA^5$, $R^1 = RB^2$,
 L_{A31} to L_{A40} , each represented by
 the formula




wherein in L_{A31} $R^5 = RA^1$, $R^1 = RB^1$

in L_{A32} $R^5 = RA^2$, $R^1 = RB^1$
 in L_{A33} $R^5 = RA^3$, $R^1 = RB^1$
 in L_{A34} $R^5 = RA^4$, $R^1 = RB^1$
 in L_{A35} $R^5 = RA^5$, $R^1 = RB^1$
 in L_{A36} $R^5 = RA^1$, $R^1 = RB^2$
 in L_{A37} $R^5 = RA^2$, $R^1 = RB^2$
 in L_{A38} $R^5 = RA^3$, $R^1 = RB^2$
 in L_{A39} $R^5 = RA^4$, $R^1 = RB^2$
 in L_{A40} $R^5 = RA^5$, $R^1 = RB^2$,
 L_{A61} to L_{A70} , each represented by
 the formula




wherein in L_{A61} $R^3 = RA^1$, $R^1 = RB^1$
 in L_{A62} $R^3 = RA^2$, $R^1 = RB^1$
 in L_{A63} $R^3 = RA^3$, $R^1 = RB^1$
 in L_{A64} $R^3 = RA^4$, $R^1 = RB^1$
 in L_{A65} $R^3 = RA^5$, $R^1 = RB^1$
 in L_{A66} $R^3 = RA^1$, $R^1 = RB^2$
 in L_{A67} $R^3 = RA^2$, $R^1 = RB^2$
 in L_{A68} $R^3 = RA^3$, $R^1 = RB^2$
 in L_{A69} $R^3 = RA^4$, $R^1 = RB^2$
 in L_{A70} $R^3 = RA^5$, $R^1 = RB^2$,

in L_{A13} $R^3 = RA^3$, $R^1 = RB^1$
 in L_{A14} $R^3 = RA^4$, $R^1 = RB^1$
 in L_{A15} $R^3 = RA^5$, $R^1 = RB^1$
 in L_{A16} $R^3 = RA^1$, $R^1 = RB^2$
 in L_{A17} $R^3 = RA^2$, $R^1 = RB^2$
 in L_{A18} $R^3 = RA^3$, $R^1 = RB^2$
 in L_{A19} $R^3 = RA^4$, $R^1 = RB^2$
 in L_{A20} $R^3 = RA^5$, $R^1 = RB^2$,
 L_{A41} to L_{A50} , each represented by the
 formula



wherein in L_{A41} $R^3 = RA^1$, $R^1 = RB^1$


in L_{A42} $R^3 = RA^2$, $R^1 = RB^1$
 in L_{A43} $R^3 = RA^3$, $R^1 = RB^1$
 in L_{A44} $R^3 = RA^4$, $R^1 = RB^1$
 in L_{A45} $R^3 = RA^5$, $R^1 = RB^1$
 in L_{A46} $R^3 = RA^1$, $R^1 = RB^2$
 in L_{A47} $R^3 = RA^2$, $R^1 = RB^2$
 in L_{A48} $R^3 = RA^3$, $R^1 = RB^2$
 in L_{A49} $R^3 = RA^4$, $R^1 = RB^2$
 in L_{A50} $R^3 = RA^5$, $R^1 = RB^2$,
 L_{A71} to L_{A80} , each represented by the
 formula



wherein in L_{A71} $R^3 = RA^1$, $R^1 = RB^1$
 in L_{A72} $R^3 = RA^2$, $R^1 = RB^1$
 in L_{A73} $R^3 = RA^3$, $R^1 = RB^1$
 in L_{A74} $R^3 = RA^4$, $R^1 = RB^1$
 in L_{A75} $R^3 = RA^5$, $R^1 = RB^1$
 in L_{A76} $R^3 = RA^1$, $R^1 = RB^2$
 in L_{A77} $R^3 = RA^2$, $R^1 = RB^2$
 in L_{A78} $R^3 = RA^3$, $R^1 = RB^2$
 in L_{A79} $R^3 = RA^4$, $R^1 = RB^2$
 in L_{A80} $R^3 = RA^5$, $R^1 = RB^2$


L_{A101} to L_{A110} , each represented by the
 formula

in L_{A23} $R^4 = RA^3$, $R^1 = RB^1$
 in L_{A24} $R^4 = RA^4$, $R^1 = RB^1$
 in L_{A25} $R^4 = RA^5$, $R^1 = RB^1$
 in L_{A26} $R^4 = RA^1$, $R^1 = RB^2$
 in L_{A27} $R^4 = RA^2$, $R^1 = RB^2$
 in L_{A28} $R^4 = RA^3$, $R^1 = RB^2$
 in L_{A29} $R^4 = RA^4$, $R^1 = RB^2$
 in L_{A30} $R^4 = RA^5$, $R^1 = RB^2$,
 L_{A51} to L_{A60} , each represented by
 the formula



wherein in L_{A51} $R^3 = RA^1$, $R^1 = RB^1$


in L_{A52} $R^3 = RA^2$, $R^1 = RB^1$
 in L_{A53} $R^3 = RA^3$, $R^1 = RB^1$
 in L_{A54} $R^3 = RA^4$, $R^1 = RB^1$
 in L_{A55} $R^3 = RA^5$, $R^1 = RB^1$
 in L_{A56} $R^3 = RA^1$, $R^1 = RB^2$
 in L_{A57} $R^3 = RA^2$, $R^1 = RB^2$
 in L_{A58} $R^3 = RA^3$, $R^1 = RB^2$
 in L_{A59} $R^3 = RA^4$, $R^1 = RB^2$
 in L_{A60} $R^3 = RA^5$, $R^1 = RB^2$,
 L_{A81} to L_{A90} , each represented by
 the formula



wherein in L_{A81} $R^2 = RA^1$, $R^1 = RB^1$
 in L_{A82} $R^2 = RA^2$, $R^1 = RB^1$
 in L_{A83} $R^2 = RA^3$, $R^1 = RB^1$
 in L_{A84} $R^2 = RA^4$, $R^1 = RB^1$
 in L_{A85} $R^2 = RA^5$, $R^1 = RB^1$
 in L_{A86} $R^2 = RA^1$, $R^1 = RB^2$
 in L_{A87} $R^2 = RA^2$, $R^1 = RB^2$
 in L_{A88} $R^2 = RA^3$, $R^1 = RB^2$
 in L_{A89} $R^2 = RA^4$, $R^1 = RB^2$
 in L_{A90} $R^2 = RA^5$, $R^1 = RB^2$

(continued)

L_{A91} to L_{A100} , each represented by the formula



wherein in L_{A91} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A92} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A93} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A94} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A95} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A96} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A97} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A98} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A99} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A100} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A121} to L_{A130} , each represented by the formula



wherein in L_{A121} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A122} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A123} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A124} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A125} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A126} $R^3 = R^{A1}$, $R^1 = R^{B2}$

in L_{A127} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A128} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A129} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A130} $R^3 = R^{A5}$, $R^1 = R^{B2}$

wherein in L_{A101} $R^4 = R^{A1}$, $R^1 = R^{B1}$

in L_{A102} $R^4 = R^{A2}$, $R^1 = R^{B1}$

in L_{A103} $R^4 = R^{A3}$, $R^1 = R^{B1}$

in L_{A104} $R^4 = R^{A4}$, $R^1 = R^{B1}$

in L_{A105} $R^4 = R^{A5}$, $R^1 = R^{B1}$

in L_{A106} $R^4 = R^{A1}$, $R^1 = R^{B2}$


in L_{A107} $R^4 = R^{A2}$, $R^1 = R^{B2}$

in L_{A108} $R^4 = R^{A3}$, $R^1 = R^{B2}$

in L_{A109} $R^4 = R^{A4}$, $R^1 = R^{B2}$

in L_{A110} $R^4 = R^{A5}$, $R^1 = R^{B2}$

L_{A131} to L_{A140} , each represented by the formula



wherein in L_{A131} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A132} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A133} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A134} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A135} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A136} $R^3 = R^{A1}$, $R^1 = R^{B2}$

in L_{A137} $R^3 = R^{A2}$, $R^1 = R^{B2}$


in L_{A138} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A139} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A140} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A161} to L_{A170} , each represented by the formula

L_{A111} to L_{A120} , each represented by the formula



wherein in L_{A111} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A112} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A113} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A114} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A115} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A116} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A117} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A118} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A119} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A120} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A141} to L_{A150} , each represented by the formula



wherein in L_{A141} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A142} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A143} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A144} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A145} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A146} $R^3 = R^{A1}$, $R^1 = R^{B2}$

in L_{A147} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A148} $R^3 = R^{A3}$, $R^1 = R^{B2}$


in L_{A149} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A150} $R^3 = R^{A5}$, $R^1 = R^{B2}$

L_{A171} to L_{A180} , each represented by the formula

(continued)

LA₁₅₁ to LA₁₆₀, each represented by the formula



wherein in LA₁₅₁ R² = R^{A1}, R¹ = R^{B1}

in LA₁₅₂ R² = R^{A2}, R¹ = R^{B1}

in LA₁₅₃ R² = R^{A3}, R¹ = R^{B1}

in LA₁₅₄ R² = R^{A4}, R¹ = R^{B1}

in LA₁₅₅ R² = R^{A5}, R¹ = R^{B1}

in LA₁₅₆ R² = R^{A1}, R¹ = R^{B2}


in LA₁₅₇ R² = R^{A2}, R¹ = R^{B2}

in LA₁₅₈ R² = R^{A3}, R¹ = R^{B2}

in LA₁₅₉ R² = R^{A4}, R¹ = R^{B2}

in LA₁₆₀ R² = R^{A5}, R¹ = R^{B2},

LA₁₈₁ to LA₁₉₀, each represented by the formula



wherein in LA₁₈₁ R² = R^{A1}, R¹ = R^{B1}

in LA₁₈₂ R² = R^{A2}, R¹ = R^{B1}

in LA₁₈₃ R² = R^{A3}, R¹ = R^{B1}

in LA₁₈₄ R² = R^{A4}, R¹ = R^{B1}

in LA₁₈₅ R² = R^{A5}, R¹ = R^{B1}

in LA₁₈₆ R² = R^{A1}, R¹ = R^{B2}


in LA₁₈₇ R² = R^{A2}, R¹ = R^{B2}

in LA₁₈₈ R² = R^{A3}, R¹ = R^{B2}

in LA₁₈₉ R² = R^{A4}, R¹ = R^{B2}

in LA₁₉₀ R² = R^{A5}, R¹ = R^{B2},

LA₂₁₁ to LA₂₂₀, each formula represented by the



wherein in LA₁₆₁ R³ = R^{A1},

R¹ = R^{B1}

in LA₁₆₂ R³ = R^{A2}, R¹ = R^{B1}

in LA₁₆₃ R³ = R^{A3}, R¹ = R^{B1}

in LA₁₆₄ R³ = R^{A4}, R¹ = R^{B1}

in LA₁₆₅ R³ = R^{A5}, R¹ = R^{B1}

in LA₁₆₆ R³ = R^{A1}, R¹ = R^{B2}


in LA₁₆₇ R³ = R^{A2}, R¹ = R^{B2}

in LA₁₆₈ R³ = R^{A3}, R¹ = R^{B2}

in LA₁₆₉ R³ = R^{A4}, R¹ = R^{B2}

in LA₁₇₀ R³ = R^{A5}, R¹ = R^{B2},

LA₁₉₁ to LA₂₀₀, each represented by the formula



wherein in LA₁₉₁ R³ = R^{A1},

R¹ = R^{B1}

in LA₁₉₂ R³ = R^{A2}, R¹ = R^{B1}

in LA₁₉₃ R³ = R^{A3}, R¹ = R^{B1}

in LA₁₉₄ R³ = R^{A4}, R¹ = R^{B1}

in LA₁₉₅ R³ = R^{A5}, R¹ = R^{B1}

in LA₁₉₆ R³ = R^{A1}, R¹ = R^{B2}


in LA₁₉₇ R³ = R^{A2}, R¹ = R^{B2}

in LA₁₉₈ R³ = R^{A3}, R¹ = R^{B2}

in LA₁₉₉ R³ = R^{A4}, R¹ = R^{B2}

in LA₂₀₀ R³ = R^{A5}, R¹ = R^{B2},

LA₂₂₁ to LA₂₃₀, each represented by the formula



wherein in LA₁₇₁ R⁴ = R^{A1}, R¹ = R^{B1}

in LA₁₇₂ R⁴ = R^{A2}, R¹ = R^{B1}

in LA₁₇₃ R⁴ = R^{A3}, R¹ = R^{B1}

in LA₁₇₄ R⁴ = R^{A4}, R¹ = R^{B1}

in LA₁₇₅ R⁴ = R^{A5}, R¹ = R^{B1}

in LA₁₇₆ R⁴ = R^{A1}, R¹ = R^{B2}


in LA₁₇₇ R⁴ = R^{A2}, R¹ = R^{B2}

in LA₁₇₈ R⁴ = R^{A3}, R¹ = R^{B2}

in LA₁₇₉ R⁴ = R^{A4}, R¹ = R^{B2}

in LA₁₈₀ R⁴ = R^{A5}, R¹ = R^{B2},

LA₂₀₁ to LA₂₁₀, each represented by the formula



wherein in LA₂₀₁ R⁴ = R^{A1}, R¹ = R^{B1}

in LA₂₀₂ R⁴ = R^{A2}, R¹ = R^{B1}

in LA₂₀₃ R⁴ = R^{A3}, R¹ = R^{B1}

in LA₂₀₄ R⁴ = R^{A4}, R¹ = R^{B1}

in LA₂₀₅ R⁴ = R^{A5}, R¹ = R^{B1}

in LA₂₀₆ R⁴ = R^{A1}, R¹ = R^{B2}

in LA₂₀₇ R⁴ = R^{A2}, R¹ = R^{B2}


in LA₂₀₈ R⁴ = R^{A3}, R¹ = R^{B2}

in LA₂₀₉ R⁴ = R^{A4}, R¹ = R^{B2}

in LA₂₁₀ R⁴ = R^{A5}, R¹ = R^{B2},


LA₂₃₁ to LA₂₄₀, each represented by the formula

(continued)



wherein in L_{A211} $R^5 = R^{A1}$, $R^1 = R^{B1}$

15 in L_{A212} $R^5 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A213} $R^5 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A214} $R^5 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A215} $R^5 = R^{A5}$, $R^1 = R^{B1}$
 20 in L_{A216} $R^5 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A217} $R^5 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A218} $R^5 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A219} $R^5 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A220} $R^5 = R^{A5}$, $R^1 = R^{B2}$
 25 L_{A241} to L_{A250} , each represented by the formula




wherein in L_{A241} $R^2 = R^{A1}$, $R^1 = R^{B1}$

40 in L_{A242} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A243} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A244} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A245} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A246} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 45 in L_{A247} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A248} $R^2 = R^{A3}$, $R^1 = R^{B2}$


50 in L_{A249} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A250} $R^2 = R^{A5}$, $R^1 = R^{B2}$,

L_{A271} to L_{A280} , each represented by the formula



wherein in L_{A221} $R^2 = R^{A1}$, $R^1 = R^{B1}$


in L_{A222} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A223} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A224} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A225} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A226} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A227} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A228} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A229} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A230} $R^2 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A251} to L_{A260} , each represented by the formula



wherein in L_{A251} $R^3 = R^{A1}$, $R^1 = R^{B1}$


in L_{A252} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A253} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A254} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A255} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A256} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A257} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A258} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A259} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A260} $R^3 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A281} to L_{A290} , each represented by the formula



wherein in L_{A231} $R^2 = R^{A1}$, $R^1 = R^{B1}$

in L_{A232} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A233} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A234} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A235} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A236} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A237} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A238} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A239} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A240} $R^2 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A261} to L_{A270} , each represented by the formula




wherein in L_{A261} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A262} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A263} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A264} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A265} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A266} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A267} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A268} $R^3 = R^{A3}$, $R^1 = R^{B2}$, $R^1 = R^{B2}$

in L_{A269} $R^3 = R^{A4}$,
 in L_{A270} $R^3 = R^{A5}$, $R^1 = R^{B2}$,

L_{A291} to L_{A300} , each represented by the formula

(continued)



wherein in L_{A271} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A272} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A273} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A274} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A275} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A276} $R^3 = RA^1$, $R^1 = RB^2$


in L_{A277} $R^3 = RA^2$, $R^1 = RB^2$

in L_{A278} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A279} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A280} $R^3 = RA^5$, $R^1 = RB^2$

L_{A301} to L_{A310} , each represented by the formula



wherein in L_{A301} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A302} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A303} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A304} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A305} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A306} $R^3 = RA^1$, $R^1 = RB^2$


in L_{A307} $R^3 = RA^2$, $R^1 = RB^2$

in L_{A308} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A309} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A310} $R^3 = RA^5$, $R^1 = RB^2$

L_{A331} to L_{A332} , each represented by the formula



wherein in L_{A281} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A282} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A283} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A284} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A285} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A286} $R^3 = RA^1$, $R^1 = RB^2$


in L_{A287} $R^3 = RA^2$, $R^1 = RB^2$

in L_{A288} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A289} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A290} $R^3 = RA^5$, $R^1 = RB^2$,

L_{A311} to L_{A320} , each represented by the formula



wherein in L_{A311} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A312} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A313} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A314} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A315} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A316} $R^3 = RA^1$, $R^1 = RB^2$


in L_{A317} $R^3 = RA^2$, $R^1 = RB^2$

in L_{A318} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A319} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A320} $R^3 = RA^5$, $R^1 = RB^2$,

L_{A333} to L_{A334} , each represented by the formula



wherein in L_{A291} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A292} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A293} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A294} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A295} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A296} $R^3 = RA^1$, $R^1 = RB^2$


in L_{A297} $R^3 = RA^2$, $R^1 = RB^2$

in L_{A298} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A299} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A300} $R^3 = RA^5$, $R^1 = RB^2$,

L_{A321} to L_{A330} , each represented by the formula



wherein in L_{A321} $R^3 = RA^1$, $R^1 = RB^1$

in L_{A322} $R^3 = RA^2$, $R^1 = RB^1$

in L_{A323} $R^3 = RA^3$, $R^1 = RB^1$

in L_{A324} $R^3 = RA^4$, $R^1 = RB^1$

in L_{A325} $R^3 = RA^5$, $R^1 = RB^1$

in L_{A326} $R^3 = RA^1$, $R^1 = RB^2$

in L_{A327} $R^3 = RA^2$, $R^1 = RB^2$


in L_{A328} $R^3 = RA^3$, $R^1 = RB^2$

in L_{A329} $R^3 = RA^4$, $R^1 = RB^2$

in L_{A330} $R^3 = RA^5$, $R^1 = RB^2$,


L_{A335} to L_{A336} , each represented by the formula

(continued)




wherein in L_{A331} $R^1 = R^{B1}$ in L_{A332} $R^1 = R^{B2}$,

L_{A337} to L_{A338} , each represented by the formula




wherein in L_{A337} $R^1 = R^{B1}$ and in L_{A338} $R^1 = R^{B2}$;


wherein R^{A1} to R^{A5} have the following structures:




wherein R^{A1} to R^{A5} have the following structures:



wherein R^{B1} and R^{B2} have the following structures:



29. The first compound of aspect 28, wherein the first compound is selected from the group consisting of Compound 1 through Compound 4,394; where each Compound x has the formula $Ir(L_{Ak})_2(L_{Bj})$; wherein $x = 338j + k - 338$, k is an integer from 1 to 338, and j is an integer from 1 to 13; wherein L_{B1} through L_{B13} are defined as follows:



30. A first organic light emitting device comprising: an anode; a cathode; and an organic layer, disposed between the anode and the cathode, comprising a first compound; wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature; wherein the first compound has at least one aromatic ring and at least one substituent R; wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.


31. The first device of aspect 30, wherein the first device is incorporated into a device selected from the group consisting of a consumer product, an electronic component module, and a lighting panel.

32. The first device of aspect 30, wherein the organic layer is an emissive layer and the compound is an emissive dopant or a non-emissive dopant.


33. The first device of aspect 30, wherein the organic layer further comprises a host; wherein the host comprises a triphenylene containing benzo-fused thiophene or benzo-fused furan; wherein any substituent in the host is an unfused substituent independently selected from the group consisting of C_nH_{2n+1} , OC_nH_{2n+1} , OAr_1 , $N(C_nH_{2n+1})_2$, $N(Ar_1)(Ar_2)$, $CH=CH-C_nH_{2n+1}$, $C\equiv CC_nH_{2n+1}$, Ar_1 , Ar_1-Ar_2 , $C_nH_{2n}-Ar_1$, or no substitution; wherein n is from 1 to 10; and wherein Ar_1 and Ar_2 are independently selected from the group consisting of benzene, biphenyl, naphthalene, triphenylene, carbazole, and heteroaromatic analogs thereof.

34. The first device of aspect 30, wherein the organic layer further comprises a host, wherein the host comprises at least one chemical group selected from the group consisting of triphenylene, carbazole, dibenzothiophene, dibenzofuran, dibenzoselenophene, azatriphenylene, azacarbazole, aza-dibenzothiophene, aza-dibenzofuran, and azadibenzoselenophene.


35. The first device of aspect 30, wherein the organic layer further comprises a host and the host is selected from the group consisting of:



5




10



15


20



25


30

35




40


45



50

55








and combinations thereof.

36. The first device of aspect 30, wherein the organic layer further comprises a host and the host comprises a metal complex.


37. A formulation comprising a first compound of aspect 1.

Claims


1. A composition comprising a first compound;
wherein the first compound is capable of functioning as a phosphorescent emitter in an organic light emitting device at room temperature;
wherein the first compound has at least one aromatic ring and at least one substituent R;
wherein each of the at least one R is an organic group having at least two atoms of X; wherein each X is independently selected from the group consisting of Si, and Ge; and wherein each of the at least one R is directly bonded to one of the aromatic rings.
2. The composition of claim 1, wherein each X is separated by at least one carbon atom from the aromatic ring.
3. The composition of claim 1, wherein each X connects to its adjacent atoms by X-C or X-F bond only.
4. The composition of any one of claims 1 to 3, wherein each of the at least one R is independently selected from the group consisting of partially or fully silylated alkyl, partially or fully silylated cycloalkyl, partially or fully germanylated alkyl, partially or fully germanylated cycloalkyl, and combinations thereof.
5. The composition of claim 1, wherein the first compound has the formula of $M(L^1)_x(L^2)_y(L^3)_z$;
wherein L^1 , L^2 and L^3 can be the same or different;
wherein x is 1, 2, or 3;
wherein y is 0, 1, or 2;
wherein z is 0, 1, or 2;
wherein M is a metal and x+y+z is the oxidation state of the metal M;
wherein L^1 , L^2 and L^3 are each independently selected from the group consisting of:



5
10
15
20
25
30
35
40
45
50
55



and



wherein each X^1 to X^{13} are independently selected from the group consisting of carbon and nitrogen;
 wherein X is selected from the group consisting of BR' , NR' , PR' , O , S , Se , $C=O$, $S=O$, SO_2 , $CR'R''$, $SiR'R''$,
 and $GeR'R''$;

wherein R' and R'' are optionally fused or joined to form a ring;


wherein each R_a , R_b , R_c , and R_d may represent from mono substitution to the possible maximum number of substitution, or no substitution;

wherein R' , R'' , R_a , R_b , R_c , and R_d are each independently selected from the group consisting of hydrogen, deuterium, halide, alkyl, cycloalkyl, heteroalkyl, arylalkyl, alkoxy, aryloxy, amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, acyl, carbonyl, carboxylic acids, ester, nitrile, isonitrile, sulfanyl, sulfinyl, sulfonyl, phosphino, and combinations thereof; and

wherein any two adjacent substituents of R_a , R_b , R_c , and R_d are optionally fused or joined to form a ring or form a multidentate ligand; and


wherein at least one of the R_a , R_b , R_c , and R_d includes at least one R .

6. The composition of claim 5, wherein the first compound has the formula of $Ir(L^1)_2(L^2)$, wherein L^1 has the formula selected from the group consisting of:




and


wherein L^2 has the formula:




7. The composition of claim 5, wherein the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$, wherein L^1 and L^2 are different and each independently selected from the group consisting of:




and




8. The composition of claim 5, wherein the first compound has the formula of $\text{Ir}(\text{L}^1)_2(\text{L}^2)$, wherein L^1 and L^2 are each independently selected from the group consisting of:






9. The composition of claim 5, wherein the first compound has the formula of $\text{Pt}(\text{L}^1)_2$ or $\text{Pt}(\text{L}^1)(\text{L}^2)$.







10. The composition of claim 1, wherein each of the at least one R is selected from the group consisting of:




wherein R_u, R_v, R_w, R_x, R_y, and R_z are each independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof.


11. The composition of claim 1, wherein each of the at least one R is independently selected from the group consisting of:










and




12. The composition of claim 5, wherein at least one of L¹, L², and L³ is selected from the group consisting of:








and




wherein R_u , R_v , R_w , R_x , R_y , and R_z are each independently selected from the group consisting of alkyl, cycloalkyl, aryl, heteroaryl, partially or fully deuterated variants thereof, and combinations thereof. q is an integer from 1 to 5.

13. The first compound of claim 5, wherein the ligand L^1 is L_A selected from the group consisting of:


L_{A1} to L_{A10} , each represented by the formula



L_{A11} to L_{A20} , each represented by the formula



L_{A21} to L_{A30} , each represented by the formula



wherein in L_{A1} , $R^2 = R^{A1}$,
 $R^1 = R^{B1}$,

wherein in L_{A11} , $R^3 = R^{A1}$, $R^1 = R^{B1}$

wherein in L_{A21} $R^4 = R^{A1}$, $R^1 = R^{B1}$


in L_{A2} , $R^2 = R^{A2}$, $R^1 = R^{B1}$,
in L_{A3} , $R^2 = R^{A3}$, $R^1 = R^{B1}$,
in L_{A4} , $R^2 = R^{A4}$, $R^1 = R^{B1}$,
in L_{A5} , $R^2 = R^{A5}$, $R^1 = R^{B1}$,
in L_{A6} , $R^2 = R^{A1}$, $R^1 = R^{B2}$,
in L_{A7} , $R^2 = R^{A2}$, $R^1 = R^{B2}$,
in L_{A8} , $R^2 = R^{A3}$, $R^1 = R^{B2}$,
in L_{A9} , $R^2 = R^{A4}$, $R^1 = R^{B2}$,

in L_{A12} $R^3 = R^{A2}$, $R^1 = R^{B1}$
in L_{A13} $R^3 = R^{A3}$, $R^1 = R^{B1}$
in L_{A14} $R^3 = R^{A4}$, $R^1 = R^{B1}$
in L_{A15} $R^3 = R^{A5}$, $R^1 = R^{B1}$
in L_{A16} $R^3 = R^{A1}$, $R^1 = R^{B2}$
in L_{A17} $R^3 = R^{A2}$, $R^1 = R^{B2}$
in L_{A18} $R^3 = R^{A3}$, $R^1 = R^{B2}$
in L_{A19} $R^3 = R^{A4}$, $R^1 = R^{B2}$


in L_{A22} $R^4 = R^{A2}$, $R^1 = R^{B1}$
in L_{A23} $R^4 = R^{A3}$, $R^1 = R^{B1}$
in L_{A24} $R^4 = R^{A4}$, $R^1 = R^{B1}$
in L_{A25} $R^4 = R^{A5}$, $R^1 = R^{B1}$
in L_{A26} $R^4 = R^{A1}$, $R^1 = R^{B2}$
in L_{A27} $R^4 = R^{A2}$, $R^1 = R^{B2}$
in L_{A28} $R^4 = R^{A3}$, $R^1 = R^{B2}$
in L_{A29} $R^4 = R^{A4}$, $R^1 = R^{B2}$

(continued)

in L_{A10} , $R^2 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A31} to L_{A40} , each represented by the
 formula




wherein in L_{A31} $R^5 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A32} $R^5 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A33} $R^5 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A34} $R^5 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A35} $R^5 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A36} $R^5 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A37} $R^5 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A38} $R^5 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A39} $R^5 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A40} $R^5 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A61} to L_{A70} , each represented by the




wherein in L_{A61} $R^3 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A62} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A63} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A64} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A65} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A66} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A67} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A68} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A69} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A70} $R^3 = R^{A5}$, $R^1 = R^{B2}$

in L_{A20} $R^3 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A41} to L_{A50} , each represented by
 the formula




wherein in L_{A41} $R^3 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A42} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A43} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A44} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A45} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A46} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A47} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A48} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A49} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A50} $R^3 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A71} to L_{A80} , each represented by
 the formula




wherein in L_{A71} $R^3 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A72} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A73} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A74} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A75} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A76} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A77} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A78} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A79} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A80} $R^3 = R^{A5}$, $R^1 = R^{B2}$
 L_{A101} to L_{A110} , each represented
 by the formula

in L_{A30} $R^4 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A51} to L_{A60} , each represented
 by the formula




wherein in L_{A51} $R^3 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A52} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A53} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A54} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A55} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A56} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A57} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A58} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A59} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A60} $R^3 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A81} to L_{A90} , each represented
 by the formula



wherein in L_{A81} $R^2 = R^{A1}$, $R^1 = R^{B1}$
 in L_{A82} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A83} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A84} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A85} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A86} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A87} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A88} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A89} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A90} $R^2 = R^{A5}$, $R^1 = R^{B2}$

(continued)

L_{A91} to L_{A100}, each represented by the formula



wherein in L_{A91} R³ = R^{A1}, R¹ = R^{B1}

in L_{A92} R³ = R^{A2}, R¹ = R^{B1}

in L_{A93} R³ = R^{A3}, R¹ = R^{B1}

in L_{A94} R³ = R^{A4}, R¹ = R^{B1}

in L_{A95} R³ = R^{A5}, R¹ = R^{B1}

in L_{A96} R³ = R^{A1}, R¹ = R^{B2}


in L_{A97} R³ = R^{A2}, R¹ = R^{B2}

in L_{A98} R³ = R^{A3}, R¹ = R^{B2}

in L_{A99} R³ = R^{A4}, R¹ = R^{B2}

in L_{A100} R³ = R^{A5}, R¹ = R^{B2}

L_{A121} to L_{A130}, each represented by the formula



wherein in L_{A121} R³ = R^{A1}, R¹ = R^{B1}

in L_{A122} R³ = R^{A2}, R¹ = R^{B1}

in L_{A123} R³ = R^{A3}, R¹ = R^{B1}

in L_{A124} R³ = R^{A4}, R¹ = R^{B1}

in L_{A125} R³ = R^{A5}, R¹ = R^{B1}


in L_{A126} R³ = R^{A1}, R¹ = R^{B2}

in L_{A127} R³ = R^{A2}, R¹ = R^{B2}

in L_{A128} R³ = R^{A3}, R¹ = R^{B2}

in L_{A129} R³ = R^{A4}, R¹ = R^{B2}

in L_{A130} R³ = R^{A5}, R¹ = R^{B2}



wherein in L_{A101} R⁴ = R^{A1}, R¹ = R^{B1}

in L_{A102} R⁴ = R^{A2}, R¹ = R^{B1}

in L_{A103} R⁴ = R^{A3}, R¹ = R^{B1}

in L_{A104} R⁴ = R^{A4}, R¹ = R^{B1}

in L_{A105} R⁴ = R^{A5}, R¹ = R^{B1}

in L_{A106} R⁴ = R^{A1}, R¹ = R^{B2}


in L_{A107} R⁴ = R^{A2}, R¹ = R^{B2}

in L_{A108} R⁴ = R^{A3}, R¹ = R^{B2}

in L_{A109} R⁴ = R^{A4}, R¹ = R^{B2}

in L_{A110} R⁴ = R^{A5}, R¹ = R^{B2}

L_{A131} to L_{A140}, each represented by the formula



wherein in L_{A131} R³ = R^{A1}, R¹ = R^{B1}

in L_{A132} R³ = R^{A2}, R¹ = R^{B1}

in L_{A133} R³ = R^{A3}, R¹ = R^{B1}

in L_{A134} R³ = R^{A4}, R¹ = R^{B1}

in L_{A135} R³ = R^{A5}, R¹ = R^{B1}

in L_{A136} R³ = R^{A1}, R¹ = R^{B2}

in L_{A137} R³ = R^{A2}, R¹ = R^{B2}


in L_{A138} R³ = R^{A3}, R¹ = R^{B2}

in L_{A139} R³ = R^{A4}, R¹ = R^{B2}

in L_{A140} R³ = R^{A5}, R¹ = R^{B2}

L_{A161} to L_{A170}, each represented by the formula

L_{A111} to L_{A120}, each represented by the formula



wherein in L_{A111} R³ = R^{A1}, R¹ = R^{B1}

in L_{A112} R³ = R^{A2}, R¹ = R^{B1}

in L_{A113} R³ = R^{A3}, R¹ = R^{B1}

in L_{A114} R³ = R^{A4}, R¹ = R^{B1}

in L_{A115} R³ = R^{A5}, R¹ = R^{B1}

in L_{A116} R³ = R^{A1}, R¹ = R^{B2}


in L_{A117} R³ = R^{A2}, R¹ = R^{B2}

in L_{A118} R³ = R^{A3}, R¹ = R^{B2}

in L_{A119} R³ = R^{A4}, R¹ = R^{B2}

in L_{A120} R³ = R^{A5}, R¹ = R^{B2}

L_{A141} to L_{A150}, each represented by the formula



wherein in L_{A141} R³ = R^{A1}, R¹ = R^{B1}

in L_{A142} R³ = R^{A2}, R¹ = R^{B1}

in L_{A143} R³ = R^{A3}, R¹ = R^{B1}

in L_{A144} R³ = R^{A4}, R¹ = R^{B1}

in L_{A145} R³ = R^{A5}, R¹ = R^{B1}

in L_{A146} R³ = R^{A1}, R¹ = R^{B2}

in L_{A147} R³ = R^{A2}, R¹ = R^{B2}

in L_{A148} R³ = R^{A3}, R¹ = R^{B2}


in L_{A149} R³ = R^{A4}, R¹ = R^{B2}

in L_{A150} R³ = R^{A5}, R¹ = R^{B2}

L_{A171} to L_{A180}, each represented by the formula

(continued)

L_{A151} to L_{A160} , each represented by the formula



wherein in L_{A151} $R^2 = R^{A1}$, $R^1 = R^{B1}$

in L_{A152} $R^2 = R^{A2}$, $R^1 = R^{B1}$ $R^2 = R^{A3}$, $R^1 = R^{B1}$

in L_{A153} $R^2 = R^{A3}$, $R^1 = R^{B1}$

in L_{A154} $R^2 = R^{A4}$, $R^1 = R^{B1}$

in L_{A155} $R^2 = R^{A5}$, $R^1 = R^{B1}$


in L_{A156} $R^2 = R^{A1}$, $R^1 = R^{B2}$

in L_{A157} $R^2 = R^{A2}$, $R^1 = R^{B2}$

in L_{A158} $R^2 = R^{A3}$, $R^1 = R^{B2}$

in L_{A159} $R^2 = R^{A4}$, $R^1 = R^{B2}$ in L_{A160} $R^2 = R^{A5}$, $R^1 = R^{B2}$

L_{A181} to L_{A190} , each represented by the formula



wherein in L_{A181} $R^2 = R^{A1}$, $R^1 = R^{B1}$

in L_{A182} $R^2 = R^{A2}$, $R^1 = R^{B1}$

in L_{A183} $R^2 = R^{A3}$, $R^1 = R^{B1}$ $R^2 = R^{A3}$, $R^1 = R^{B1}$

in L_{A184} $R^2 = R^{A4}$, $R^1 = R^{B1}$

in L_{A185} $R^2 = R^{A5}$, $R^1 = R^{B1}$

in L_{A186} $R^2 = R^{A1}$, $R^1 = R^{B2}$


in L_{A187} $R^2 = R^{A2}$, $R^1 = R^{B2}$

in L_{A188} $R^2 = R^{A3}$, $R^1 = R^{B2}$

$R^2 = R^{A5}$, $R^1 = R^{B2}$

in L_{A190} $R^2 = R^{A5}$, $R^1 = R^{B2}$

L_{A211} to L_{A220} , each represented by the formula



wherein in L_{A161} $R^3 = R^{A1}$,

$R^1 = R^{B1}$

in L_{A162} $R^3 = R^{A2}$, $R^1 = R^{B1}$ in L_{A162} $R^3 = R^{A2}$, $R^1 = R^{B1}$

in L_{A163} $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A164} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A165} $R^3 = R^{A5}$, $R^1 = R^{B2}$

in L_{A166} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A167} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A168} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A169} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A170} $R^3 = R^{A5}$, $R^1 = R^{B2}$,

L_{A191} to L_{A200} , each represented by the formula



wherein in L_{A191} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A192} $R^3 = R^{A2}$, $R^1 = R^{B1}$ $R^1 = R^{B1}$

in L_{A193} $R^3 = R^{A3}$, $R^1 = R^{B1}$ $R^3 = R^{A3}$, $R^1 = R^{B1}$

in L_{A194} $R^3 = R^{A4}$, $R^1 = R^{B1}$

in L_{A195} $R^3 = R^{A5}$, $R^1 = R^{B1}$

in L_{A196} $R^3 = R^{A1}$, $R^1 = R^{B2}$


in L_{A197} $R^3 = R^{A2}$, $R^1 = R^{B2}$

in L_{A198} $R^3 = R^{A3}$, $R^1 = R^{B2}$

in L_{A199} $R^3 = R^{A4}$, $R^1 = R^{B2}$

in L_{A200} $R^3 = R^{A5}$, $R^1 = R^{B2}$,

L_{A221} to L_{A230} , each represented by the formula



wherein in L_{A201} $R^4 = R^{A1}$, $R^1 = R^{B1}$

in L_{A202} $R^4 = R^{A2}$, $R^1 = R^{B1}$ in L_{A202} $R^4 = R^{A3}$, $R^1 = R^{B1}$

in L_{A203} $R^4 = R^{A3}$, $R^1 = R^{B1}$

in L_{A204} $R^4 = R^{A4}$, $R^1 = R^{B1}$

in L_{A205} $R^4 = R^{A5}$, $R^1 = R^{B2}$

in L_{A206} $R^4 = R^{A1}$, $R^1 = R^{B2}$


in L_{A207} $R^4 = R^{A2}$, $R^1 = R^{B2}$

in L_{A208} $R^4 = R^{A3}$, $R^1 = R^{B2}$

in L_{A209} $R^4 = R^{A4}$, $R^1 = R^{B2}$

in L_{A210} $R^4 = R^{A5}$, $R^1 = R^{B2}$,

L_{A201} to L_{A210} , each represented by the formula



wherein in L_{A201} $R^4 = R^{A1}$, $R^1 = R^{B1}$

wherein $R^4 = R^{A2}$, $R^1 = R^{B1}$ in L_{A202} $R^4 = R^{A2}$

in L_{A203} $R^1 = R^{A3}$, $R^1 = R^{B1}$

in L_{A204} $R^4 = R^{A4}$, $R^1 = R^{B1}$

in L_{A205} $R^4 = R^{A5}$, $R^1 = R^{B1}$

in L_{A206} $R^1 = R^{A1}$, $R^1 = R^{B2}$

in L_{A207} $R^4 = R^{A2}$, $R^1 = R^{B2}$


in L_{A208} $R^4 = R^{A3}$, $R^1 = R^{B2}$

in L_{A209} $R^4 = R^{A5}$, $R^1 = R^{B2}$

in L_{A210} $R^4 = R^{A5}$, $R^1 = R^{B2}$,


L_{A231} to L_{A240} , each represented by the formula

(continued)




wherein in L_{A211} $R^5 = R^{A1}$, $R^1 = R^{B1}$

in L_{A212} $R^5 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A213} $R^5 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A214} $R^5 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A215} $R^5 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A216} $R^5 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A217} $R^5 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A218} $R^5 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A219} $R^5 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A220} $R^5 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A241} to L_{A250} , each represented by the
 formula




wherein in L_{A241} $R^2 = R^{A1}$, $R^1 = R^{B1}$

in L_{A242} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A243} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A244} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A245} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A246} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A247} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A248} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A249} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A250} $R^2 = R^{A5}$, $R^1 = R^{B2}$,



wherein in L_{A221} $R^2 = R^{A1}$,
 $R^1 = R^{B1}$


in L_{A222} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A223} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A224} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A225} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A226} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A227} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A228} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A229} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A230} $R^2 = R^{A5}$, $R^1 = R^{B2}$,
 L_{A251} to L_{A260} , each
 represented by the formula



wherein in L_{A251} $R^3 = R^{A1}$,

$R^1 = R^{B1}$


in L_{A252} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A253} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A254} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A255} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A256} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A257} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A258} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A259} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A260} $R^3 = R^{A5}$, $R^1 = R^{B2}$,



wherein in L_{A231} $R^2 = R^{A1}$, $R^1 = R^{B1}$

in L_{A232} $R^2 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A233} $R^2 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A234} $R^2 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A235} $R^2 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A236} $R^2 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A237} $R^2 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A238} $R^2 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A239} $R^2 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A240} $R^2 = R^{A5}$, $R^1 = R^{B2}$,

L_{A261} to L_{A270} , each represented by
 the formula by the




wherein in L_{A261} $R^3 = R^{A1}$, $R^1 = R^{B1}$

in L_{A262} $R^3 = R^{A2}$, $R^1 = R^{B1}$
 in L_{A263} $R^3 = R^{A3}$, $R^1 = R^{B1}$
 in L_{A264} $R^3 = R^{A4}$, $R^1 = R^{B1}$
 in L_{A265} $R^3 = R^{A5}$, $R^1 = R^{B1}$
 in L_{A266} $R^3 = R^{A1}$, $R^1 = R^{B2}$
 in L_{A267} $R^3 = R^{A2}$, $R^1 = R^{B2}$
 in L_{A268} $R^3 = R^{A3}$, $R^1 = R^{B2}$
 in L_{A269} $R^3 = R^{A4}$, $R^1 = R^{B2}$
 in L_{A270} $R^3 = R^{A5}$, $R^1 = R^{B2}$,

(continued)

L_{A271} to L_{A280}, each represented by the formula



wherein in L_{A271} R³ = R^{A1}, R¹ = R^{B1}

in L_{A272} R³ = R^{A2}, R¹ = R^{B1}

in L_{A273} R³ = R^{A3}, R¹ = R^{B1}

in L_{A274} R³ = R^{A4}, R¹ = R^{B1}

in L_{A275} R³ = R^{A5}, R¹ = R^{B1}

in L_{A276} R³ = R^{A1}, R¹ = R^{B2}


in L_{A277} R³ = R^{A2}, R¹ = R^{B2}

in L_{A278} R³ = R^{A3}, R¹ = R^{B2}

in L_{A279} R³ = R^{A4}, R¹ = R^{B2}

in L_{A280} R³ = R^{A5}, R¹ = R^{B2}

L_{A301} to L_{A310}, each represented by the formula



wherein in L_{A301} R³ = R^{A1}, R¹ = R^{B1}

in L_{A302} R³ = R^{A2}, R¹ = R^{B1}

in L_{A303} R³ = R^{A3}, R¹ = R^{B1}

in L_{A304} R³ = R^{A4}, R¹ = R^{B1}

in L_{A305} R³ = R^{A5}, R¹ = R^{B1}

in L_{A306} R³ = R^{A1}, R¹ = R^{B2}


in L_{A307} R³ = R^{A2}, R¹ = R^{B2}

in L_{A308} R³ = R^{A3}, R¹ = R^{B2}

in L_{A309} R³ = R^{A4}, R¹ = R^{B2}

in L_{A310} R³ = R^{A5}, R¹ = R^{B2}

L_{A281} to L_{A290}, each represented by the formula



wherein in L_{A281} R³ = R^{A1},

R¹ = R^{B1}

in L_{A282} R³ = R^{A2}, R¹ = R^{B1}

in L_{A283} R³ = R^{A3}, R¹ = R^{B1}

in L_{A284} R³ = R^{A4}, R¹ = R^{B1}

in L_{A285} R³ = R^{A5}, R¹ = R^{B1}

in L_{A286} R³ = R^{A1}, R¹ = R^{B2}


in L_{A287} R³ = R^{A1}, R¹ = R^{B2}

in L_{A288} R³ = R^{A3}, R¹ = R^{B2}

in L_{A289} R³ = R^{A4}, R¹ = R^{B2}

in L_{A290} R³ = R^{A5}, R¹ = R^{B2}

L_{A311} to L_{A320}, each represented by the formula



wherein in L_{A311} R³ = R^{A1},

R¹ = R^{B1}

in L_{A312} R³ = R^{A2}, R¹ = R^{B1}

in L_{A313} R³ = R^{A3}, R¹ = R^{B1}

in L_{A314} R³ = R^{A4}, R¹ = R^{B1}

in L_{A315} R³ = R^{A5}, R¹ = R^{B1}

in L_{A316} R³ = R^{A1}, R¹ = R^{B2}


in L_{A317} R³ = R^{A2}, R¹ = R^{B2}

in L_{A318} R³ = R^{A3}, R¹ = R^{B2}

in L_{A319} R³ = R^{A4}, R¹ = R^{B2}

in L_{A320} R³ = R^{A5}, R¹ = R^{B2}

L_{A291} to L_{A300}, each represented by the formula



wherein in L_{A291} R³ = R^{A1}, R¹ = R^{B1}

in L_{A292} R³ = R^{A2}, R¹ = R^{B1}

in L_{A293} R³ = R^{A3}, R¹ = R^{B1}

in L_{A294} R³ = R^{A4}, R¹ = R^{B1}

in L_{A295} R³ = R^{A5}, R¹ = R^{B1}

in L_{A296} R³ = R^{A1}, R¹ = R^{B2}


in L_{A297} R³ = R^{A2}, R¹ = R^{B2}

in L_{A298} R³ = R^{A3}, R¹ = R^{B2}

in L_{A299} R³ = R^{A4}, R¹ = R^{B2}

in L_{A300} R³ = R^{A5}, R¹ = R^{B2}

L_{A321} to L_{A330}, each represented by the formula



wherein in L_{A321} R³ = R^{A1}, R¹ = R^{B1}

in L_{A322} R³ = R^{A2}, R¹ = R^{B1}

in L_{A323} R³ = R^{A3}, R¹ = R^{B1}

in L_{A324} R³ = R^{A4}, R¹ = R^{B1}

in L_{A325} R³ = R^{A5}, R¹ = R^{B1}

in L_{A326} R³ = R^{A1}, R¹ = R^{B2}

in L_{A327} R³ = R^{A2}, R¹ = R^{B2}


in L_{A328} R³ = R^{A3}, R¹ = R^{B2}

in L_{A329} R³ = R^{A4}, R¹ = R^{B2}

in L_{A330} R³ = R^{A5}, R¹ = R^{B2}


(continued)

L_{A331} to L_{A332} , each represented by each formula represented by the formula




wherein in L_{A331} $R^1 = R^{B1}$ in L_{A332} $R^1 = R^{B2}$

L_{A333} to L_{A334} , each represented by the formula




wherein in L_{A333} $R^1 = R^{B1}$ in L_{A334} $R^1 = R^{B2}$

L_{A335} to L_{A336} , each represented by the formula





wherein in L_{A335} $R^1 = R^{B1}$ in L_{A336} $R^1 = R^{B2}$

L_{A337} to L_{A338} , each represented by the formula




wherein in L_{A337} $R^1 = R^{B1}$ and in L_{A338} $R^1 = R^{B2}$;


wherein R^{A1} to R^{A5} have the following structures:



wherein R^{B1} and R^{B2} have the following structures:



14. The first compound of claim 12, wherein the first compound is selected from the group consisting of Compound 1 through Compound 4,394; where each Compound x has the formula $\text{Ir}(\text{L}_{\text{Ak}})_2(\text{L}_{\text{Bj}})$; wherein $x = 338j + k - 338$, k is an integer from 1 to 338, and j is an integer from 1 to 13; wherein L_{B1} through L_{B13} are defined as follows:



15. A first organic light emitting device comprising:

an anode;
 a cathode; and
 an organic layer, disposed between the anode and the cathode, comprising a first compound as defined in any one of the previous claims.




FIG. 1




FIG. 2



EUROPEAN SEARCH REPORT

Application Number
EP 15 19 9296

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	WO 98/08845 A1 (CIBA GEIGY AG [CH]; STOLLER ANDRE [FR]; KUNZ WALTER [CH]; ZONDLER HELM) 5 March 1998 (1998-03-05) * page 115; compound 5.117 * * the whole document *	1-4	INV. C09K11/06 H01L51/50
X	WO 2011/136482 A1 (ROHM & HAAS ELECT MATERIALS [KR]; LEE HYO JUNG [KR]; CHO YOUNG JUN [KR]) 3 November 2011 (2011-11-03) * page 10 * * claim 1 * * the whole document *	1-4,15	
A	----- * page 10 * * claim 1 * * the whole document *	5-14	
X	EP 2 711 999 A2 (UNIVERSAL DISPLAY CORP [US]) 26 March 2014 (2014-03-26) * compound 29 * * table 2 * * the whole document *	1-5,10,12,15	
X	US 2013/334521 A1 (LEE JAEMIN [KR] ET AL) 19 December 2013 (2013-12-19) * paragraph [0045] * * claims 1,16 * * the whole document *	1,3-5,15	TECHNICAL FIELDS SEARCHED (IPC) C09K H01L
A	EP 2 568 774 A1 (SAMSUNG ELECTRONICS CO LTD [KR]) 13 March 2013 (2013-03-13) * compound 14 * * the whole document *	1-15	
A	US 2013/341600 A1 (LIN CHUN [US] ET AL) 26 December 2013 (2013-12-26) * paragraph [0074] * * the whole document *	1-15	
	----- -/--		
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 23 May 2016	Examiner Ziegler, Jan
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03.82 (P04C01)



EUROPEAN SEARCH REPORT

Application Number
EP 15 19 9296

5

10

15

20

25

30

35

40

45

50

55

1

EPO FORM 1503 03.82 (P04C01)

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A	US 2013/169148 A1 (ALLEYNE BERT [US] ET AL) 4 July 2013 (2013-07-04) * page 56 * * claims 1-20 * -----	1-15	
			TECHNICAL FIELDS SEARCHED (IPC)
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 23 May 2016	Examiner Ziegler, Jan
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 15 19 9296

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-05-2016

10

15

20

25

30

35

40

45

50

55

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9808845	A1	05-03-1998	AU 4618497 A	19-03-1998
			EP 0923579 A1	23-06-1999
			JP 2001500482 A	16-01-2001
			US 6268308 B1	31-07-2001
			WO 9808845 A1	05-03-1998

WO 2011136482	A1	03-11-2011	KR 20110119206 A	02-11-2011
			TW 201204809 A	01-02-2012
			WO 2011136482 A1	03-11-2011

EP 2711999	A2	26-03-2014	EP 2711999 A2	26-03-2014
			KR 20140040044 A	02-04-2014
			US 2014084261 A1	27-03-2014

US 2013334521	A1	19-12-2013	JP 5655165 B2	14-01-2015
			JP 2014509587 A	21-04-2014
			KR 20120114030 A	16-10-2012
			US 2013334521 A1	19-12-2013
			WO 2012138172 A2	11-10-2012

EP 2568774	A1	13-03-2013	CN 102993412 A	27-03-2013
			EP 2568774 A1	13-03-2013
			JP 5913016 B2	27-04-2016
			JP 2013060595 A	04-04-2013
			KR 20130028577 A	19-03-2013
			US 2013240843 A1	19-09-2013

US 2013341600	A1	26-12-2013	KR 20130143494 A	31-12-2013
			US 2013341600 A1	26-12-2013

US 2013169148	A1	04-07-2013	NONE	

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 62097742 A [0001]
- US 5844363 A [0005] [0024]
- US 6303238 B [0005] [0024]
- US 5707745 A [0005] [0024] [0027]
- US 7279704 B [0015] [0022] [0023] [0091]
- US 4769292 A [0021]
- US 20030230980 A [0024]
- US 5703436 A [0024]
- US 6097147 A [0024]
- US 20040174116 A [0024]
- US 5247190 A, Friend [0027]
- US 6091195 A, Forrest [0027]
- US 5834893 A, Bulovic [0027]
- US 6013982 A [0028]
- US 6087196 A [0028]
- US 6337102 B, Forrest [0028]
- US 7431968 B [0028]
- US 6294398 B [0028]
- US 6468819 B [0028]
- US 7968146 B [0029]
- US 2007023098 W [0029]
- US 2009042829 W [0029]
- WO 2007002683 A [0091]
- US 20030162053 A [0091]
- EP 1725079 A1 [0091]
- US 20050123751 A [0091]
- WO 2009018009 A [0091]
- US 20020158242 A [0091]
- US 20060240279 A [0091]
- US 20080220265 A [0091]
- WO 2011075644 A [0091]
- EP 2350216 A [0091]
- US 5061569 A [0091]
- EP 650955 A [0091]
- US 20080124572 A [0091]
- US 20070278938 A [0091]
- US 20080106190 A [0091]
- US 20110163302 A [0091]
- US 20080018221 A [0091]
- US 20060202194 A [0091]
- WO 2005014551 A [0091]
- WO 2006072002 A [0091]
- WO 2009066779 A [0091]
- WO 2009066778 A [0091]
- WO 2009063833 A [0091]
- US 20090045731 A [0091]
- US 20090045730 A [0091]
- WO 2009008311 A [0091]
- US 20090008605 A [0091]
- US 20090009065 A [0091]
- WO 2010056066 A [0091]
- WO 2011086863 A [0091]
- US 20030175553 A [0091]
- WO 2001039234 A [0091]
- US 20060280965 A [0091]
- WO 2009021126 A [0091]
- US 20090309488 A [0091]
- US 20090302743 A [0091]
- US 20100012931 A [0091]
- WO 2008056746 A [0091]
- WO 2010107244 A [0091]
- JP 2008074939 B [0091]
- US 20100187984 A [0091]
- WO 2004093207 A [0091]
- WO 2005089025 A [0091]
- WO 2006132173 A [0091]
- JP 200511610 B [0091]
- JP 2007254297 B [0091]
- WO 2007063796 A [0091]
- WO 2007063754 A [0091]
- WO 2004107822 A [0091]
- US 20050112407 A [0091]
- WO 2005030900 A [0091]
- US 20040137268 A [0091]
- US 20040137267 A [0091]
- US 20070190359 A [0091]
- WO 2006114966 A [0091]
- US 20090167162 A [0091]
- WO 2009086028 A [0091]
- US 20090030202 A [0091]
- US 20090017330 A [0091]
- US 20100084966 A [0091]
- US 20050238919 A [0091]
- WO 2009003898 A [0091]
- EP 2034538 A [0091]
- WO 2006100298 A [0091]
- US 20040115476 A [0091]
- US 20060121308 A [0091]
- US 7154114 B [0091]
- US 20030072964 A [0091]
- US 20070087321 A [0091]
- US 20080261076 A [0091]
- US 20100090591 A [0091]
- WO 2009100991 A [0091]
- WO 2008101842 A [0091]
- US 7232618 B [0091]
- WO 2003040257 A [0091]
- US 20070103060 A [0091]

- US 20050244673 A [0091]
- US 20020034656 A [0091]
- US 7332232 B [0091]
- US 20090108737 A [0091]
- WO 2010028151 A [0091]
- EP 1841834B A [0091]
- US 20060127696 A [0091]
- US 20090039776 A [0091]
- US 6921915 B [0091]
- US 20100244004 A [0091]
- US 6687266 B [0091]
- US 20060008670 A [0091]
- JP 2007123392 B [0091]
- WO 2010086089 A [0091]
- WO 2011044988 A [0091]
- WO 2009050290 A [0091]
- US 20090165846 A [0091]
- US 20080015355 A [0091]
- US 20010015432 A [0091]
- US 20100295032 A [0091]
- US 7250226 B [0091]
- US 7396598 B [0091]
- WO 2002015645 A [0091]
- US 20060263635 A [0091]
- US 20060182992 A [0091]
- WO 2009000673 A [0091]
- US 20070111026 A [0091]
- US 20030138657 A [0091]
- US 20030152802 A [0091]
- US 7090928 B [0091]
- WO 2002002714 A [0091]
- WO 2006009024 A [0091]
- US 20060251923 A [0091]
- US 20110057559 A [0091]
- US 20110204333 A [0091]
- US 7393599 B [0091]
- WO 2006056418 A [0091]
- US 20050260441 A [0091]
- WO 2005019373 A [0091]
- US 7534505 B [0091]
- WO 2011051404 A [0091]
- US 7445855 B [0091]
- US 20080297033 A [0091]
- US 20100148663 A [0091]
- US 7338722 B [0091]
- US 20020134984 A [0091]
- WO 2005123873 A [0091]
- WO 2007004380 A [0091]
- WO 2006082742 A [0091]
- WO 2006098120 A [0091]
- WO 2006103874 A [0091]
- US 7655323 B [0091]
- US 20050025993 A [0091]
- WO 2008132085 A [0091]
- WO 2010079051 A [0091]
- WO 2003060956 A [0091]
- US 20090179554 A [0091]
- US 20090115316 A [0091]
- US 7230107 B [0091]
- US 20090101870 A [0091]
- US 20040036077 A [0091]
- US 6528187 B [0091]

Non-patent literature cited in the description

- **BALDO et al.** Highly Efficient Phosphorescent Emission from Organic Electroluminescent Devices. *Nature*, 1998, vol. 395, 151-154 [0022]
- **BALDO et al.** Very high-efficiency green organic light-emitting devices based on electrophosphorescence. *Appl. Phys. Lett.*, 1999, vol. 75 (3), 4-6 [0022]
- *Appl. Phys. Lett.*, 1996, vol. 69, 2160 [0091]
- *J. Lumin.*, 1997, vol. 72-74, 985 [0091]
- *Appl. Phys. Lett.*, 2001, vol. 78, 673 [0091]
- *Synth. Met.*, 1997, vol. 87, 171 [0091]
- *Symposium Digest*, 2006, vol. 37, 923 [0091]
- *Appl. Phys. Lett.*, 1987, vol. 51, 913 [0091]
- *J. Mater. Chem.*, 1993, vol. 3, 319 [0091]
- *Appl. Phys. Lett.*, 2007, vol. 90, 183503 [0091]
- *Synth. Met.*, 1997, vol. 91, 209 [0091]
- *Adv. Mater.*, 1994, vol. 6, 677 [0091]
- *Synth. Met.*, 2000, vol. 111, 421 [0091]
- *Chem. Mater.*, 2003, vol. 15, 3148 [0091]
- *Appl. Phys. Lett.*, 2001, vol. 78, 1622 [0091]
- *Nature*, 1998, vol. 395, 151 [0091]
- *Appl. Phys. Lett.*, 2007, vol. 90, 123509 [0091]
- *Org. Electron.*, 2000, vol. 1, 15 [0091]
- *Appl. Phys. Lett.*, 2000, vol. 77, 2280 [0091]
- *J. Appl. Phys.*, 2001, vol. 90, 5048 [0091]
- *Appl. Phys. Lett.*, 2003, vol. 82, 2422 [0091]
- *Adv. Mater.*, 2007, vol. 19, 739 [0091]
- *Chem. Mater.*, 2005, vol. 17, 3532 [0091]
- *Adv. Mater.*, 2005, vol. 17, 1059 [0091]
- *Inorg. Chem.*, 2001, vol. 40, 1704 [0091]
- *Chem. Mater.*, 2004, vol. 16, 2480 [0091]
- *Adv. Mater.*, 2004, vol. 16, 2003 [0091]
- *Angew. Chem. Int. Ed.*, 2006, vol. 45, 7800 [0091]
- *Appl. Phys. Lett.*, 2005, vol. 86, 153505 [0091]
- *Chem. Lett.*, 2005, vol. 34, 592 [0091]
- *Chem. Commun.*, 2005, 2906 [0091]
- *Inorg. Chem.*, 2003, vol. 42, 1248 [0091]
- *Angew. Chem. Int. Ed.*, 2008, vol. 47, 4542 [0091]
- *Chem. Mater.*, 2006, vol. 18, 5119 [0091]
- *Inorg. Chem.*, 2007, vol. 46, 4308 [0091]
- *Organometallics*, 2004, vol. 23, 3745 [0091]
- *Appl. Phys. Lett.*, 1999, vol. 74, 1361 [0091]
- *Appl. Phys. Lett.*, 1999, vol. 75, 4 [0091]
- *Appl. Phys. Lett.*, 2001, vol. 79, 449 [0091]
- *Appl. Phys. Lett.*, 2002, vol. 81, 162 [0091]
- *Appl. Phys. Lett.*, 2001, vol. 79, 156 [0091]
- *Appl. Phys. Lett.*, 2006, vol. 89, 063504 [0091]

EP 3 040 396 A1

- *Chem. Lett.*, 1993, vol. 5, 905 [0091]
- *Appl. Phys. Lett.*, 2007, vol. 91, 263503 [0091]
- *Appl. Phys. Lett.*, 1999, vol. 74, 865 [0091]
- *Appl. Phys. Lett.*, 1989, vol. 55, 1489 [0091]
- *Jpn. J. Apply. Phys.*, 1993, vol. 32, L917 [0091]
- *Org. Electron.*, 2003, vol. 4, 113 [0091]
- *J. Am. Chem. Soc.*, 1998, vol. 120, 9714 [0091]
- *J. Am. Chem. Soc.*, 2000, vol. 122, 1832 [0091]

专利名称(译)	有机电致发光材料和器件		
公开(公告)号	EP3040396A1	公开(公告)日	2016-07-06
申请号	EP2015199296	申请日	2015-12-10
[标]申请(专利权)人(译)	环球展览公司		
申请(专利权)人(译)	通用显示器公司		
当前申请(专利权)人(译)	通用显示器公司		
[标]发明人	BOUDREAU LT PIERRE LUC T XIA CHUANJUN LIN CHUN		
发明人	BOUDREAU LT, PIERRE-LUC T. XIA, CHUANJUN LIN, CHUN		
IPC分类号	C09K11/06 H01L51/50		
CPC分类号	C07F15/0033 C09K11/06 C09K2211/1007 C09K2211/1029 C09K2211/185 H01L51/0085 H01L51/0094 C09K11/025 C09K2211/1096 H01L51/0067 H01L51/0072 H01L51/0081 H01L51/5016		
代理机构(译)	汉森NORBERT		
审查员(译)	齐格勒JAN		
优先权	62/097742 2014-12-30 US 14/923942 2015-10-27 US		
其他公开文献	EP3040396B1		
外部链接	Espacenet		

摘要(译)

公开了包含第一化合物的组合物。第一化合物能够在室温下用作有机发光器件中的磷光发光体;其中第一化合物具有至少一个芳环和至少一个取代基R;其中所述至少一个R中的每一个是具有至少两个X原子的有机基团;其中每个X独立地选自Si和Ge;并且其中至少一个R中的每一个直接键合到一个芳环上。




FIG. 1