



(11) **EP 3 089 230 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
09.01.2019 Bulletin 2019/02

(21) Application number: **14875046.6**

(22) Date of filing: **05.11.2014**

(51) Int Cl.:
H01L 51/54 ^(2006.01) **C07D 333/76** ^(2006.01)
C07D 409/04 ^(2006.01) **C07D 409/08** ^(2006.01)
C07D 409/14 ^(2006.01) **C09K 11/02** ^(2006.01)
H01L 51/50 ^(2006.01)

(86) International application number:
PCT/JP2014/079287

(87) International publication number:
WO 2015/098297 (02.07.2015 Gazette 2015/26)

(54) **MATERIAL FOR ORGANIC ELECTROLUMINESCENT ELEMENTS, AND ORGANIC ELECTROLUMINESCENT ELEMENT USING SAME**

MATERIAL FÜR ORGANISCHE ELEKTROLUMINESZIERENDE ELEMENTE UND ORGANISCHES ELEKTROLUMINESZIERENDES ELEMENT DARAUS

MATÉRIAU POUR ÉLÉMENTS ÉLECTROLUMINESCENTS ORGANIQUES ET ÉLÉMENT ÉLECTROLUMINESCENT ORGANIQUE L'UTILISANT

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **26.12.2013 JP 2013269272**

(43) Date of publication of application:
02.11.2016 Bulletin 2016/44

(73) Proprietor: **Nippon Steel & Sumikin Chemical Co.,
Ltd.
Chiyoda-ku
Tokyo 101-0021 (JP)**

(72) Inventors:
• **OGAWA, Junya
Kitakyushu-shi
Fukuoka 804-8503 (JP)**
• **TADA, Masashi
Kitakyushu-shi
Fukuoka 804-8503 (JP)**

• **UEDA, Tokiko
Kitakyushu-shi
Fukuoka 804-8503 (JP)**
• **KAI, Takahiro
Kitakyushu-shi
Fukuoka 804-8503 (JP)**

(74) Representative: **Vossius & Partner
Patentanwälte Rechtsanwälte mbB
Siebertstrasse 3
81675 München (DE)**

(56) References cited:
**WO-A1-2013/088934 WO-A1-2014/103910
US-A1- 2009 167 162**

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Technical Field

[0001] The present invention relates to an organic electroluminescent device using a carborane compound as a material for an organic electroluminescent device, and more specifically, to a thin film-type device that emits light by applying an electric field to a light-emitting layer containing an organic compound.

Background Art

[0002] In general, an organic electroluminescent device (hereinafter referred to as organic EL device) includes a light-emitting layer and a pair of counter electrodes interposing the light-emitting layer therebetween in its simplest structure. That is, the organic EL device uses the phenomenon that, when an electric field is applied between both the electrodes, electrons are injected from a cathode and holes are injected from an anode, and each electron and each hole recombine in the light-emitting layer to emit light.

[0003] In recent years, progress has been made in developing an organic EL device using an organic thin film. In order to enhance luminous efficiency particularly, the optimization of the kind of electrodes has been attempted for the purpose of improving the efficiency of injection of carriers from the electrodes. As a result, there has been developed a device in which a hole-transporting layer formed of an aromatic diamine and a light-emitting layer formed of an 8-hydroxyquinoline aluminum complex (Alq₃) are formed between electrodes as thin films, resulting in a significant improvement in luminous efficiency, as compared to related-art devices in which a single crystal of anthracene or the like is used. Thus, the development of the above-mentioned organic EL device has been promoted in order to accomplish its practical application to a high-performance flat panel having features such as self-luminescence and rapid response.

[0004] Further, investigations have been made on using phosphorescent light rather than fluorescent light as an attempt to raise the luminous efficiency of a device. Many kinds of devices including the above-mentioned device in which a hole-transporting layer formed of an aromatic diamine and a light-emitting layer formed of Alq₃ are formed emit light by using fluorescent light emission. However, by using phosphorescent light emission, that is, by using light emission from a triplet excited state, luminous efficiency is expected to be improved by from about three times to about four times, as compared to the case of using related-art devices in which fluorescent light (singlet) is used. In order to accomplish this purpose, investigations have been made on adopting a coumarin derivative or a benzophenone derivative as a light-emitting layer, but extremely low luminance has only been provided. Further, investigations have been made on using a europium complex as an attempt to use a triplet state, but highly efficient light emission has not been accomplished. In recent years, many investigations have been made mainly on an organic metal complex, such as an iridium complex, for the purpose of attaining high luminous efficiency and a long lifetime.

Citation List

Patent Literature

[0005]


[PTL 1] WO 01/041512 A1
 [PTL 2] JP 2001-313178 A
 [PTL 3] JP 2005-162709 A
 [PTL 4] JP 2005-166574 A
 [PTL 5] US 2012/0319088 A1
 [PTL 6] WO 2013/094834 A1
 [PTL 7] US 2009/0167162 A1

[0006] In order to obtain high luminous efficiency, host materials that are used with the dopant materials described above play an important role. A typical example of the host materials proposed is 4,4'-bis(9-carbazolyl)biphenyl (CBP) as a carbazole compound disclosed in Patent Literature 2. When CBP is used as a host material for a green phosphorescent light-emitting material typified by a tris (2-phenylpyridine) iridium complex (Ir(ppy)₃), the injection balance between charges is disturbed because CBP has the characteristic of facilitating the delivery of holes and not facilitating the delivery of electrons. Thus, excessively delivered holes flow out into an electron-transporting layer side, with the result that the luminous efficiency from Ir(ppy)₃ lowers.

[0007] In order to provide high luminous efficiency to an organic EL device as described above, it is necessary to use a host material that has high triplet excitation energy, and is striking a good balance in both charge (hole and electron)-in-

jecting/transporting property. Further desired is a compound that is electrochemically stable and has high heat resistance and excellent amorphous stability, and hence further improvement has been demanded.

[0008] In Patent Literatures 3, 4, 5, 6, and 7, there are disclosures of such carborane compounds as shown below.





[0009] However, such carborane compounds cannot show the effectiveness, such as shown by a carborane compound, in which a carborane skeleton is bonded to dibenzothiophene at position 1, 2, or 3.


Summary of Invention

[0010] In order to apply an organic EL device to a display device in a flat panel display or the like, it is necessary to improve the luminous efficiency of the device and also to ensure sufficiently the stability in driving the device. The present invention has an object to provide, in view of the above-mentioned circumstances, an organic EL device that has high efficiency and high driving stability and is practically useful and a compound suitable for the organic EL device.

[0011] The inventors of the present invention have made intensive investigations and have consequently found that, when a carborane compound in which a carborane skeleton is directly bonded to a dibenzothiophene skeleton at position 1, 2, or 3, and the carborane skeleton and the dibenzothiophene skeleton are linearly linked to each other is used in an organic EL device, the organic EL device exhibits excellent characteristics. As a result, the present invention has been completed.

[0012] The present invention relates to a material for an organic electroluminescent device, including a carborane compound represented by any one of the general formulae (1) to (3).





wherein,

a ring A represents a divalent carborane group $C_2B_{10}H_{10}$ represented by the formula (1a) or the formula (1b), and when a plurality of rings A are present in a molecule thereof, the rings may be identical to or different from each other; r represents a number of repetitions and represents an integer of 0 or 1;

L^1 and L^2 each represent a single bond, a divalent substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a divalent substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, or a divalent linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic hydrocarbon groups or the aromatic heterocyclic groups, when L^1 and L^2 each represent the linked aromatic group, the group may be linear or branched, and aromatic rings to be linked may be identical to or different from each other, and terminal L^1 and L^2 may each represent an alkyl group having 1 to 12 carbon atoms or an alkoxy group having 1 to 12 carbon atoms, provided that when r represents 0, the single bond is excluded, and when r represents 1, at least one of L^1 or L^2 represents a group including an aromatic heterocyclic group;

L^3 represents a hydrogen atom, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, a linked aromatic group formed by linking 2 to 6 of the substituted or unsubstituted aromatic rings, an alkyl group having 1 to 12 carbon atoms, or an alkoxy group having 1 to 12 carbon atoms, and when L^3 represents the linked aromatic group, the group may be linear or branched, and aromatic rings to be linked may be identical to or different from each other; and when the aromatic group in each of L^1 to L^3 has a substituent, the substituent is an alkyl group having 1 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, or an acetyl group, the aromatic group may have a plurality of substituents, and the plurality of substituents may be identical to or different from each other.

[0013] In each of the general formula (1), it is preferred that L^1 to L^3 each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic hydrocarbon groups and the aromatic heterocyclic groups. In addition, it is preferred that L^1 to L^3 each independently represent a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic heterocyclic rings. Further, in the general formula (1), it is preferred that r represent an integer of 0.

[0014] The present invention also relates to an organic electroluminescent device having a structure in which an anode, an organic layer, and a cathode are laminated on a substrate, in which the organic layer includes an organic layer containing the above-mentioned material for an organic electroluminescent device.

[0015] Further, it is preferred that the organic layer containing the material for an organic electroluminescent device include a phosphorescent light-emitting dopant. In addition, it is desired that the emission wavelength of the phosphorescent light-emitting dopant have an emission maximum wavelength at 550 nm or less.

[0016] A material for a phosphorescent device of the present invention has a structure in which the carborane skeleton is directly bonded to carbon of the dibenzothiophene skeleton at position 1, 2, or 3, and the carborane skeleton and the dibenzothiophene skeleton are linearly linked to each other. A carborane compound having such structural feature enables high-level control of the electron-injecting/transporting properties of a device because its lowest unoccupied molecular orbital (LUMO) that affects the electron-injecting/transporting properties is widely distributed in the entirety of a molecule thereof. Further, the compound enables efficient light emission from a dopant because the compound has the lowest triplet excitation energy (T1 energy) high enough to confine the T1 energy of the dopant. By virtue of the

foregoing features, the use of the compound in an organic EL device has achieved a reduction in driving voltage of the device and high luminous efficiency.

[0017] In addition, the material for an organic electroluminescent device of the present invention shows a satisfactory amorphous characteristic and high heat stability, and at the same time, is extremely stable in an excited state. Accordingly, an organic EL device using the material has a long driving lifetime and durability at a practical level.

Brief Description of Drawings

[0018]

FIG. 1 is a sectional view for illustrating an example of the structure of an organic EL device.

FIG. 2 is an NMR chart of a carborane compound 1 of the present invention.

Description of Embodiments

[0019] A material for an organic electroluminescent device of the present invention is a carborane compound represented by any one of the general formulae (1) to (3). The carborane compound exhibits such excellent effects as described above probably because the compound has a structure in which a carborane skeleton is directly bonded to a dibenzothiophene skeleton at position 1, 2, or 3, and the carborane skeleton and the dibenzothiophene skeleton are linearly linked to each other.

[0020] In each of the general formulae (1) to (3), L^1 and L^2 each represent a single bond, a divalent substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a divalent substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, or a divalent linked aromatic group. Herein, the "linked aromatic group" means a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic hydrocarbon groups and the aromatic heterocyclic groups. The linked aromatic group may be linear or branched, and aromatic rings to be linked may be identical to or different from each other. In addition, terminal L^1 and L^2 may each represent an alkyl group having 1 to 12 carbon atoms or an alkoxy group having 1 to 12 carbon atoms. That is, the terminal L^1 and L^2 each represent the aromatic hydrocarbon group, the aromatic heterocyclic group, the linked aromatic group, the alkyl group, or the alkoxy group. Herein, the "terminal" means that the group is not present between two rings A.

[0021] L^3 represents a hydrogen atom, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, a linked aromatic group formed by linking 2 to 6 of the substituted or unsubstituted aromatic rings, an alkyl group having 1 to 12 carbon atoms, or an alkoxy group having 1 to 12 carbon atoms.

[0022] It is understood that the descriptions of the aromatic hydrocarbon group, the aromatic heterocyclic group, and the linked aromatic group are common in the descriptions of L^1 to L^3 except that these groups are divalent groups in the cases of L^1 and L^2 and are monovalent groups in the case of L^3 .

[0023] In addition, part or the entirety of hydrogen atoms in the carborane compound represented by any one of the general formulae (1) to (3) may each be substituted with deuterium.

[0024] Specific examples of the unsubstituted aromatic hydrocarbon group include groups each produced by removing a hydrogen atom from an aromatic hydrocarbon compound, such as benzene, naphthalene, fluorene, anthracene, phenanthrene, triphenylene, tetraphenylene, fluoranthene, pyrene, or chrysene, or an aromatic hydrocarbon compound in which a plurality of those compounds are linked to each other. Of those, a group produced by removing a hydrogen atom from benzene, naphthalene, fluorene, phenanthrene, or triphenylene is preferred.

[0025] Specific examples of the unsubstituted aromatic heterocyclic group include linking groups each produced by removing a hydrogen atom from an aromatic heterocyclic compound, such as pyridine, pyrimidine, triazine, quinoline, isoquinoline, quinoxaline, naphthyridine, carbazole, acridine, azepine, tribenzazepine, phenazine, phenoxazine, phenothiazine, dibenzophosphole, or dibenzoborole, or an aromatic heterocyclic compound in which a plurality of those compounds are linked to each other, or dibenzothiophene at a position except position 1. Of those, a group produced by removing a hydrogen atom from pyridine, pyrimidine, triazine, carbazole, or dibenzothiophene at a position except position 1 is preferred.

[0026] A group produced by removing a hydrogen atom from an aromatic compound in which a plurality of aromatic hydrocarbon compounds or aromatic heterocyclic compounds are linked to each other is referred to as "linked aromatic group." The linked aromatic group is a group formed by linking 2 to 6 aromatic rings, the aromatic rings to be linked may be identical to or different from each other, and both an aromatic hydrocarbon group and an aromatic heterocyclic group may be included. The number of the aromatic rings to be linked is preferably from 2 to 4, more preferably 2 or 3.




[0027] Specific examples of the linked aromatic group include groups each produced by removing a hydrogen atom from biphenyl, terphenyl, phenylnaphthalene, diphenylnaphthalene, phenylantracene, diphenylantracene, diphenylfluorene, bipyridine, bipyrimidine, bitriazine, biscarbazole, phenylpyridine, phenylpyrimidine, phenyltriazine, phenylcarba-

zole, diphenylpyridine, diphenyltriazine, bis(carbazolyl)benzene, or the like.

[0028] The aromatic hydrocarbon group, the aromatic heterocyclic group, or the linked aromatic group may have a substituent. When the aromatic group in each of L^1 to L^3 has a substituent, the substituent is an alkyl group having 1 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, or an acetyl group, and the alkyl group and the alkoxy group may be linear, branched, or cyclic. The substituent is preferably an alkyl group having 1 to 4 carbon atoms, an alkoxy group having 1 or 2 carbon atoms, or an acetyl group.

[0029] Herein, the "alkyl group" means a non-aromatic hydrocarbon group, and includes a chain hydrocarbon group, and as well, a cyclic hydrocarbon group generated from a cycloalkane, a terpene, or the like. Specific examples of the alkyl group include: chain or branched alkyl groups, such as a methyl group, an ethyl group, a propyl group, an isopropyl group, a butyl group, a pentyl group, a hexyl group, and an octyl group; and cyclic alkyl groups, e.g., cycloalkyl groups, such as a cyclopentyl group and a cyclohexyl group. Specific examples of the alkoxy group include alkoxy groups, such as a methoxy group and an ethoxy group, which are derived from the alkyl groups, such as a methyl group and an ethyl group.

[0030] Here, when the linked aromatic group is a divalent group, the group is represented by, for example, any one of the following formulae, and its aromatic rings may be linked in a linear manner or a branched manner.



[0031] Ar^1 to Ar^6 each represent an unsubstituted aromatic hydrocarbon ring or aromatic heterocycle.

[0032] In addition, when L^3 and terminal L^1 and L^2 each represent an alkyl group having 1 to 12 carbon atoms or an alkoxy group having 1 to 12 carbon atoms, the alkyl group and the alkoxy group are the same as the alkyl group and the alkoxy group described as the substituent, respectively.

[0033] In the general formulae (1) to (3), r represents an integer of 0 or 1, preferably 0.


[0034] In the general formulae (1) to (3), a ring A represents a divalent carborane group $C_2B_{10}H_{10}$ represented by the formula (1a) or (1b). The ring A is preferably a carborane group represented by the formula (1a). The two bonding hands of the formula (1a) or (1b) may each be produced from C or may each be produced from B, but a bonding hand to be bonded to L^1 or L^2 is preferably produced from C.

[0035] Of the carborane compounds represented by the general formulae (1) to (3), a compound represented by the general formula (2) or (3) is preferred, and a compound represented by the general formula (2) is more preferred.

[0036] In the general formulae (1) to (3), it is understood that the same symbol has the same meaning and the same formula has the same meaning unless otherwise stated.


[0037] The carborane compound represented by any one of the general formulae (1) to (3) can be synthesized from raw materials selected in accordance with the structure of the target compound by using a known approach.

[0038] An intermediate (A-1) can be synthesized through the following reaction formula with reference to a synthesis example described in Journal of Organometallic Chemistry, 1993, 462, p19-29, and the target compound can be obtained from the resultant intermediate (A-1).




[A-1]


10 **[0039]** Specific examples of the carborane compound represented by any one of the general formulae (1) to (3) are shown below. However, the material for an organic electroluminescent device of the present invention is not limited thereto.




5



10




11




12


15



13




14




15


25



16




17




18


35



19




20




21


45



22




23




24


55




25




26




27




28




29




30




31




32




33




34




35




36




37




38




39




40




41




42




43




44




45




46




47




48




49




50




51




52




53




54




55




56




57




58




59




60




61




62



63




64




65


5



66




67




68


10



69




70




71


20



72




73




74


30



75




76




77


45



78




79



80

55



[0040] When the material for an organic electroluminescent device of the present invention is contained in at least one of a plurality of organic layers of an organic EL device having a structure in which an anode, the plurality of organic layers, and a cathode are laminated on a substrate, an excellent organic electroluminescent device is provided. A light-emitting layer, an electron-transporting layer, or a hole-blocking layer is suitable as the organic layer in which the compound of the present invention is contained. Here, when the compound of the present invention is used in the light-emitting layer, the compound can be used as a host material for the light-emitting layer containing a fluorescent light-emitting, delayed fluorescent light-emitting, or phosphorescent light-emitting dopant. In addition, the compound of the present invention can be used as an organic light-emitting material that radiates fluorescence and delayed fluorescence. When the compound of the present invention is used as an organic light-emitting material that radiates fluorescence and delayed fluorescence, any other organic compound having a value for at least one of excited singlet energy or excited triplet energy higher than that of the compound is preferably used as the host material. The compound of the present invention is particularly preferably incorporated as a host material for the light-emitting layer containing the phosphorescent light-emitting dopant.

[0041] Next, an organic EL device using the material for an organic electroluminescent device of the present invention is described.

[0042] The organic EL device of the present invention includes organic layers including at least one light-emitting layer between an anode and a cathode laminated on a substrate. In addition, at least one of the organic layers contains the material for an organic electroluminescent device of the present invention. The material for an organic electroluminescent device of the present invention is advantageously contained in the light-emitting layer together with a phosphorescent light-emitting dopant.

[0043] Next, the structure of the organic EL device of the present invention is described with reference to the drawings. However, the structure of the organic EL device of the present invention is by no means limited to one illustrated in the drawings.

[0044] FIG. 1 is a sectional view for illustrating an example of the structure of a general organic EL device used in the present invention. Reference numeral 1 represents a substrate, reference numeral 2 represents an anode, reference numeral 3 represents a hole-injecting layer, reference numeral 4 represents a hole-transporting layer, reference numeral 5 represents a light-emitting layer, reference numeral 6 represents an electron-transporting layer, and reference numeral 7 represents a cathode. The organic EL device of the present invention may include an exciton-blocking layer adjacent to the light-emitting layer, or may include an electron-blocking layer between the light-emitting layer and the hole-injecting layer. The exciton-blocking layer may be inserted on any of the anode side and the cathode side of the light-emitting layer, and may also be inserted simultaneously on both sides. The organic EL device of the present invention includes the substrate, the anode, the light-emitting layer, and the cathode as its essential layers. The organic EL device of the present invention preferably includes a hole-injecting/transporting layer and an electron-injecting/transporting layer in addition to the essential layers, and more preferably includes a hole-blocking layer between the light-emitting layer and the electron-injecting/transporting layer. The hole-injecting/transporting layer means any one or both of the hole-injecting layer and the hole-transporting layer, and the electron-injecting/transporting layer means any one or both of an electron-

injecting layer and the electron-transporting layer.

[0045] It is possible to adopt a reverse structure as compared to FIG. 1, that is, the reverse structure being formed by laminating the layers on the substrate 1 in the order of the cathode 7, the electron-transporting layer 6, the light-emitting layer 5, the hole-transporting layer 4, and the anode 2. In this case as well, some layers may be added or eliminated as required.

-Substrate-

[0046] The organic EL device of the present invention is preferably supported by a substrate. The substrate is not particularly limited, and any substrate that has long been conventionally used for an organic EL device may be used. For example, a substrate made of glass, a transparent plastic, quartz, or the like may be used.

-Anode-

[0047] Preferably used as the anode in the organic EL device is an anode formed by using, as an electrode substance, any of a metal, an alloy, an electrically conductive compound, and a mixture thereof, all of which have a large work function (4 eV or more). Specific examples of such electrode substance include metals such as Au and conductive transparent materials such as CuI, indium tin oxide (ITO), SnO_2 , and ZnO. In addition, a material such as IDIXO ($\text{In}_2\text{O}_3\text{-ZnO}$), which can produce an amorphous, transparent conductive film, may be used. In order to produce the anode, it may be possible to form any of those electrode substances into a thin film by using a method such as vapor deposition or sputtering and form a pattern having a desired shape thereon by photolithography. Alternatively, in the case of not requiring high pattern accuracy (about 100 μm or more), a pattern may be formed via a mask having a desired shape when any of the above-mentioned electrode substances is subjected to vapor deposition or sputtering. Alternatively, when a coatable substance, such as an organic conductive compound, is used, a wet film-forming method, such as a printing method or a coating method, may be used. When luminescence is taken out from the anode, the transmittance of the anode is desirably controlled to more than 10%. In addition, the sheet resistance of the anode is preferably several hundred ohms per square ($\Omega/\square$) or less. Further, the thickness of the film is, depending on its material, selected from the range of generally from 10 nm to 1,000 nm, preferably from 10 nm to 200 nm.

-Cathode-

[0048] On the other hand, used as the cathode is a cathode formed by using, as an electrode substance, any of a metal (electron-injecting metal), an alloy, an electrically conductive compound, and a mixture thereof, all of which have a small work function (4 eV or less). Specific examples of such electrode substance include sodium, a sodium-potassium alloy, magnesium, lithium, a magnesium/copper mixture, a magnesium/silver mixture, a magnesium/aluminum mixture, a magnesium/indium mixture, an aluminum/aluminum oxide (Al_2O_3) mixture, indium, a lithium/aluminum mixture, and a rare earth metal. Of those, for example, a mixture of an electron-injecting metal and a second metal, which is a stable metal having a larger work function value than the former metal, such as a magnesium/silver mixture, a magnesium/aluminum mixture, a magnesium/indium mixture, an aluminum/aluminum oxide (Al_2O_3) mixture, or a lithium/aluminum mixture, or aluminum, is suitable from the viewpoints of an electron-injecting property and durability against oxidation or the like. The cathode can be produced by forming any of those electrode substances into a thin film by using a method such as vapor deposition or sputtering. In addition, the sheet resistance of the cathode is preferably several hundred $\Omega/\square$ or less, and the thickness of the film is selected from the range of generally from 10 nm to 5 μm , preferably from 50 nm to 200 nm. In order for luminescence produced to pass through, any one of the anode and cathode of the organic EL device is preferably transparent or semi-transparent, because the light emission luminance improves.

[0049] In addition, after the above-mentioned metal has been formed into a film having a thickness of from 1 nm to 20 nm as a cathode, the conductive transparent material mentioned in the description of the anode is formed into a film on the cathode, thereby being able to produce a transparent or semi-transparent cathode. Through the application of this, a device in which both the anode and cathode have transparency can be produced.

-Light-emitting Layer-

[0050] The light-emitting layer is a layer that emits light after the production of an exciton by the recombination of a hole injected from the anode and an electron injected from the cathode, and the light-emitting layer contains an organic light-emitting material and a host material.

[0051] When the light-emitting layer is a fluorescent light-emitting layer, at least one kind of fluorescent light-emitting material may be used alone as the fluorescent light-emitting material. However, it is preferred that the fluorescent light-emitting material be used as a fluorescent light-emitting dopant and the host material be contained.

[0052] The carborane compound represented by any one of the general formulae (1) to (3) can be used as the fluorescent light-emitting material in the light-emitting layer. However, the fluorescent light-emitting material is known through, for example, many patent literatures, and hence can be selected therefrom. Examples thereof include a benzoxazole derivative, a benzothiazole derivative, a benzimidazole derivative, a styrylbenzene derivative, a polyphenyl derivative, a diphenylbutadiene derivative, a tetraphenylbutadiene derivative, a naphthalimide derivative, a coumarin derivative, a fused aromatic compound, a perinone derivative, an oxadiazole derivative, an oxazine derivative, an aldazine derivative, a pyrrolidine derivative, a cyclopentadiene derivative, a bisstyrylanthracene derivative, a quinacridone derivative, a pyrrolopyridine derivative, a thiadiazolopyridine derivative, a styrylamine derivative, a diketopyrrolopyrrole derivative, an aromatic dimethylidene compound, various metal complexes typified by a metal complex of an 8-quinolinol derivative, and a metal complex, rare earth complex, or transition metal complex of a pyrromethene derivative, polymer compounds such as polythiophene, polyphenylene, and polyphenylene vinylene, and an organic silane derivative. Of those, for example, the following compound is preferred: a fused aromatic compound, a styryl compound, a diketopyrrolopyrrole compound, an oxazine compound, or a pyrromethene metal complex, transition metal complex, or lanthanoid complex. For example, the following compound is more preferred: naphthacene, pyrene, chrysene, triphenylene, benzo[c]phenanthrene, benzo[a]anthracene, pentacene, perylene, fluoranthene, acenaphthofluoranthene, dibenzo[a,j]anthracene, dibenzo[a,h]anthracene, benzo[a]naphthacene, hexacene, anthanthrene, naphtho[2,1-f]isoquinoline, α -naphthaphenanthridine, phenanthroxazole, quinolino[6,5-f]quinoline, or benzothiophanthrene. Those compounds may each have an alkyl group, aryl group, aromatic heterocyclic group, or diarylamino group as a substituent.

[0053] The carborane compound represented by any one of the general formulae (1) to (3) can be used as a fluorescent host material in the light-emitting layer. However, the fluorescent host material is known through, for example, many patent literatures, and hence can be selected therefrom. For example, the following material can be used: a compound having a fused aryl ring, such as naphthalene, anthracene, phenanthrene, pyrene, chrysene, naphthacene, triphenylene, perylene, fluoranthene, fluorene, or indene, or a derivative thereof; an aromatic amine derivative, such as N,N'-dinaphthyl-N,N'-diphenyl-4,4'-diphenyl-1,1'-diamine; a metal chelated oxinoid compound typified by tris (8-quinolinato)aluminum(III); a bisstyryl derivative, such as a distyrylbenzene derivative; a tetraphenylbutadiene derivative; an indene derivative; a coumarin derivative; an oxadiazole derivative; a pyrrolopyridine derivative; a perinone derivative; a cyclopentadiene derivative; a pyrrolopyrrole derivative; a thiadiazolopyridine derivative; a dibenzofuran derivative; a carbazole derivative; an indolocarbazole derivative; a triazine derivative; or a polymer-based derivative, such as a polyphenylene vinylene derivative, a poly-p-phenylene derivative, a polyfluorene derivative, a polyvinyl carbazole derivative, or a polythiophene derivative. However, the fluorescent host material is not particularly limited thereto.

[0054] When the fluorescent light-emitting material is used as a fluorescent light-emitting dopant and the host material is contained, the content of the fluorescent light-emitting dopant in the light-emitting layer desirably falls within the range of from 0.01 wt% to 20 wt%, preferably from 0.1 wt% to 10 wt%.

[0055] An organic EL device typically injects charges from both of its electrodes, i.e., its anode and cathode into a light-emitting substance to produce a light-emitting substance in an excited state, and causes the substance to emit light. In the case of a charge injection-type organic EL device, it is said that 25% of the produced excitons are excited to a singlet excited state and the remaining 75% of the excitons are excited to a triplet excited state. As described in Advanced Materials 2009, 21, 4802-4806., it has been known that after a specific fluorescent light-emitting substance has undergone an energy transition to a triplet excited state as a result of intersystem crossing or the like, the substance is subjected to inverse intersystem crossing to a singlet excited state by triplet-triplet annihilation or the absorption of thermal energy to radiate fluorescence, thereby expressing thermally activated delayed fluorescence. The organic EL device of the present invention can also express delayed fluorescence. In this case, the light emission can include both fluorescent light emission and delayed fluorescent light emission. Light emission from the host material may be present in part of the light emission.


[0056] When the light-emitting layer is a delayed fluorescent light-emitting layer, at least one kind of delayed fluorescent light-emitting material may be used alone as a delayed fluorescent light-emitting material. However, it is preferred that the delayed fluorescent light-emitting material be used as a delayed fluorescent light-emitting dopant and the host material be contained.

[0057] Although the carborane compound represented by any one of the general formulae (1) to (3) can be used as the delayed fluorescent light-emitting material in the light-emitting layer, a material selected from known delayed fluorescent light-emitting materials can also be used. Examples thereof include a tin complex, an indolocarbazole derivative, a copper complex, and a carbazole derivative. Specific examples thereof include, but not limited to, compounds described in the following non patent literatures and patent literature.

(1) Adv. Mater. 2009, 21, 4802-4806, (2) Appl. Phys. Lett. 98, 083302 (2011), (3) JP 2011-213643 A, and (4) J. Am. Chem. Soc. 2012, 134, 14706-14709.

[0058] Specific examples of the delayed fluorescent light-emitting material are shown below, but the delayed fluorescent

light-emitting material is not limited to the following compounds.




[0059] When the delayed fluorescent light-emitting material is used as a delayed fluorescent light-emitting dopant and the host material is contained, the content of the delayed fluorescent light-emitting dopant in the light-emitting layer desirably falls within the range of from 0.01 wt% to 50 wt%, preferably from 0.1 wt% to 20 wt%, more preferably from 0.01% to 10%.

[0060] The carborane compound represented by any one of the general formulae (1) to (3) can be used as the delayed fluorescent host material in the light-emitting layer. However, the delayed fluorescent host material can also be selected from compounds except the carborane. For example, the following compound can be used: a compound having a fused aryl ring, such as naphthalene, anthracene, phenanthrene, pyrene, chrysene, naphthacene, triphenylene, perylene, fluoranthene, fluorene, or indene, or a derivative thereof; an aromatic amine derivative, such as N,N'-dinaphthyl-N,N'-diphenyl-4,4'-diphenyl-1,1'-diamine; a metal chelated oxinoid compound typified by tris(8-quinolino)aluminum(III); a bisstyryl derivative, such as a distyrylbenzene derivative; a tetraphenylbutadiene derivative; an indene derivative; a coumarin derivative; an oxadiazole derivative; a pyrrolopyridine derivative; a perinone derivative; a cyclopentadiene derivative; a pyrrolopyrrole derivative; a thiadiazolopyridine derivative; a dibenzofuran derivative; a carbazole derivative; an indolocarbazole derivative; a triazine derivative; or a polymer-based derivative, such as a polyphenylene vinylene derivative, a poly-p-phenylene derivative, a polyfluorene derivative, a polyvinyl carbazole derivative, a polythiophene derivative, or an arylsilane derivative. However, the delayed fluorescent host material is not particularly limited thereto.


[0061] When the light-emitting layer is a phosphorescent light-emitting layer, the light-emitting layer contains a phosphorescent light-emitting dopant and a host material. It is recommended to use, as a material for the phosphorescent light-emitting dopant, a material containing an organic metal complex including at least one metal selected from ruthenium, rhodium, palladium, silver, rhenium, osmium, iridium, platinum, and gold.

[0062] Preferred examples of the phosphorescent light-emitting dopant include complexes such as Ir(ppy)₃, complexes such as Ir(bt)₂·acac₃, and complexes such as PtOEt₃, the complexes each having a noble metal element, such as Ir, as a central metal. Specific examples of those complexes are shown below, but the complexes are not limited to the compounds described below.

5




10




15

20



25

30




35


40



45



50



[0063] It is desired that the content of the phosphorescent light-emitting dopant in the light-emitting layer fall within the range of from 2 wt% to 40 wt%, preferably from 5 wt% to 30 wt%.

[0064] When the light-emitting layer is a phosphorescent light-emitting layer, it is preferred to use, as a host material in the light-emitting layer, the carborane compound represented by any one of the general formulae (1) to (3) according to the present invention. However, when the carborane compound is used in any other organic layer except the light-emitting layer, the material to be used in the light-emitting layer may be another host material except the carborane compound, or the carborane compound and any other host material may be used in combination. Further, a plurality of kinds of known host materials may be used in combination.

[0065] It is preferred to use, as a usable known host compound, a compound that has a hole-transporting ability or an electron-transporting ability, is capable of preventing luminescence from having a longer wavelength, and has a high glass transition temperature.

[0066] Any such other host material is known through, for example, many patent literatures, and hence can be selected therefrom. Specific examples of the host material include, but are not particularly limited to, an indole derivative, a carbazole derivative, a triazole derivative, an oxazole derivative, an oxadiazole derivative, an imidazole derivative, a polyarylethane derivative, a pyrazoline derivative, a pyrazolone derivative, a phenylenediamine derivative, an arylamine derivative, an amino-substituted chalcone derivative, a styrylanthracene derivative, a fluorenone derivative, a hydrazone derivative, a stilbene derivative, a silazane derivative, an aromatic tertiary amine compound, a styrylamine compound, an aromatic dimethylidene-based compound, a porphyrin-based compound, an anthraquinodimethane derivative, an anthrone derivative, a diphenylquinone derivative, a thiopyran dioxide derivative, a heterocyclic tetracarboxylic acid anhydride, such as naphthalene perylene, a phthalocyanine derivative, various metal complexes typified by a metal complex of an 8-quinolinol derivative, a metal phthalocyanine, and metal complexes of benzoxazole and benzothiazole derivatives, and polymer compounds, such as a polysilane-based compound, a poly(N-vinylcarbazole) derivative, an aniline-based copolymer, a thiophene oligomer, a polythiophene derivative, a polyphenylene derivative, a polyphenylenevinylene derivative, and a polyfluorene derivative.

[0067] The light-emitting layer, which may be any one of a fluorescent light-emitting layer, a delayed fluorescent light-emitting layer, and a phosphorescent light-emitting layer, is preferably the phosphorescent light-emitting layer.

-Injecting Layer-

[0068] The injecting layer refers to a layer formed between an electrode and an organic layer for the purposes of lowering a driving voltage and improving light emission luminance, and includes a hole-injecting layer and an electron-injecting layer. The injecting layer may be interposed between the anode and the light-emitting layer or the hole-transporting layer, or may be interposed between the cathode and the light-emitting layer or the electron-transporting layer. The injecting layer may be formed as required.

-Hole-blocking Layer-

[0069] The hole-blocking layer has, in a broad sense, the function of an electron-transporting layer, and is formed of a hole-blocking material that has a remarkably small ability to transport holes while having a function of transporting electrons, and hence the hole-blocking layer is capable of improving the probability of recombining an electron and a hole by blocking holes while transporting electrons.

[0070] It is preferred to use the carborane compound represented by any one of the general formulae (1) to (3) according to the present invention for the hole-blocking layer. However, when the carborane compound is used in any other organic layer, a known material for a hole-blocking layer may be used. In addition, a material for the electron-transporting layer to be described later can be used as a material for the hole-blocking layer as required.

-Electron-blocking Layer-

[0071] The electron-blocking layer is formed of a material that has a remarkably small ability to transport electrons while having a function of transporting holes, and hence the electron-blocking layer is capable of improving the probability of recombining an electron and a hole by blocking electrons while transporting holes.

[0072] A material for the hole-transporting layer to be described later can be used as a material for the electron-blocking layer as required. The thickness of the electron-blocking layer is preferably from 3 nm to 100 nm, more preferably from 5 nm to 30 nm.

-Exciton-blocking Layer-

[0073] The exciton-blocking layer refers to a layer for blocking excitons produced by the recombination of a hole and an electron in the light-emitting layer from diffusing into charge-transporting layers. The insertion of this layer enables efficient confinement of the excitons in the light-emitting layer, thereby being able to improve the luminous efficiency of the device. The exciton-blocking layer can be inserted on any of the anode side and the cathode side of the adjacent light-emitting layer, and can also be inserted simultaneously on both sides.

[0074] Although the carborane compound represented by any one of the general formulae (1) to (3) can be used as a material for the exciton-blocking layer, as other materials therefor, there are given, for example, 1,3-dicarbazolylbenzene (mCP) and bis(2-methyl-8-quinolinolato)-4-phenylphenolatoaluminum(III) (BAIq).

-Hole-transporting Layer-

[0075] The hole-transporting layer is formed of a hole-transporting material having a function of transporting holes, and a single hole-transporting layer or a plurality of hole-transporting layers can be formed.

[0076] The hole-transporting material has a hole-injecting property or a hole-transporting property or has an electron-blocking property, and any of an organic material and an inorganic material can be used as the hole-transporting material. Although it is preferred to use the carborane compound represented by any one of the general formulae (1) to (3) as a known hole-transporting material that can be used, any compound selected from conventionally known compounds can be used. Examples of the known hole-transporting material that can be used include a triazole derivative, an oxadiazole derivative, an imidazole derivative, a polyaryllalkane derivative, a pyrazoline derivative, and a pyrazolone derivative, a phenylenediamine derivative, an arylamine derivative, an amino-substituted chalcone derivative, an oxazole derivative, a styrylanthracene derivative, a fluorenone derivative, a hydrazone derivative, a stilbene derivative, a silazane derivative, an aniline-based copolymer, and a conductive high-molecular weight oligomer, in particular, a thiophene oligomer. However, a porphyrin compound, an aromatic tertiary amine compound, or a styrylamine compound is preferably used, and an aromatic tertiary amine compound is more preferably used.

-Electron-transporting Layer-

[0077] The electron-transporting layer is formed of a material having a function of transporting electrons, and a single electron-transporting layer or a plurality of electron-transporting layers can be formed.

[0078] An electron-transporting material (which also serves as a hole-blocking material in some cases) only needs to have a function of transferring electrons injected from the cathode into the light-emitting layer. Although it is preferred to use the carborane compound represented by any one of the general formulae (1) to (3) according to the present invention for the electron-transporting layer, any compound selected from conventionally known compounds can be used. Examples thereof include a nitro-substituted fluorene derivative, a diphenylquinone derivative, a thiopyran dioxide derivative, a carbodiimide, a fluorenylidene methane derivative, anthraquinodimethane, an anthrone derivative, and an oxadiazole derivative. Further, a thiadiazole derivative prepared by substituting an oxygen atom on an oxadiazole ring with a sulfur atom in the oxadiazole derivative or a quinoxaline derivative that has a quinoxaline ring known as an electron withdrawing group can be used as the electron-transporting material. Further, a polymer material in which any such material is introduced in a polymer chain or is used as a polymer main chain can be used.


Examples


[0079] Now, the present invention is described in more detail by way of Examples. It should be appreciated that the present invention is not limited to Examples below and can be carried out in various forms as long as the various forms do not deviate from the gist of the present invention.

[0080] The route described below was used to synthesize a carborane compound to be used as a material for an organic electroluminescent device. The number of each compound corresponds to the number given to the chemical formula.

Example 1

[0081] A compound 1 is synthesized in accordance with the following reaction formulae.






[0082] Under a nitrogen atmosphere, 35.0 g (0.243 mol) of m-carborane and 200 mL of 1,2-dimethoxyethane (DME) were added, and the resultant DME solution was cooled to 0°C. 96.8 mL of a 2.69 M solution of n-butyllithium in hexane was dropped to the solution, and the mixture was stirred under ice cooling for 30 min. 70 mL of pyridine was added to the resultant and the mixture was stirred at room temperature for 10 min. After that, 75.6 g (0.763 mol) of copper(I) chloride was added to the resultant and the mixture was stirred at 65°C for 30 min. After that, 73.9 g (0.280 mol) of 2-bromodibenzothiophene was added to the resultant and the mixture was stirred at 95°C overnight. The reaction solution was cooled to room temperature, and then the precipitated crystal was taken by filtration and the solvent was distilled off under reduced pressure. The resultant residue was purified by silica gel column chromatography to provide 8.0 g (24.5 mmol, 10.0% yield) of an intermediate A.

[0083] Under a nitrogen atmosphere, 50.0 g (0.146 mol) of 2,8-dibromodibenzothiophene, 24.4 g (0.146 mol) of carbazole, 2.78 g (14.6 mmol) of copper iodide, 92.9 g (0.438 mol) of tripotassium phosphate, 5.3 mL (43.8 mmol) of trans-1,2-cyclohexanediamine, and 1 L of 1,4-dioxane were added, and the mixture was stirred at 115°C overnight. The reaction solution was cooled to room temperature, and then the precipitated crystal was taken by filtration and the solvent was distilled off under reduced pressure. The resultant residue was purified by silica gel column chromatography to provide 11.2 g (26.2 mmol, 18% yield) of an intermediate B as a white solid.


[0084] Under a nitrogen atmosphere, 8.0 g (0.0245 mol) of the intermediate A and 138 mL of DME were added, and the resultant DME solution was cooled to 0°C. 9.89 mL of a 2.69 M solution of n-butyllithium in hexane was dropped to the solution, and the mixture was stirred under ice cooling for 30 min. 6.7 mL of pyridine was added to the resultant and the mixture was stirred at room temperature for 10 min. After that, 7.5 g (76.0 mmol) of copper(I) chloride was added to the resultant and the mixture was stirred at 65°C for 30 min. After that, 11.2 g (0.0262 mol) of the intermediate B was added to the resultant and the mixture was stirred at 95°C for 2 d. The reaction solution was cooled to room temperature, and then the precipitated crystal was taken by filtration and the solvent was distilled off under reduced pressure. The resultant residue was purified by silica gel column chromatography to provide 3.7 g (5.50 mmol, 22% yield) of a compound 1. APCI-TOFMS, m/z 674 $[M]^+$. The measurement result of $^1\text{H-NMR}$ (measurement solvent: CDCl_3) is shown in FIG. 2.

[0085] Compounds 13, 25, 26, 29, 36, 45, and 57, and H-1, H-2, and H-3 were synthesized in conformity with the synthesis example and the synthesis method described herein.


[0086] In addition, organic EL devices were produced by using the compounds 1, 13, 25, 26, 29, 36, 45, and 57, and H-1, H-2, and H-3.



H-1



H-2



H-3

Example 2

[0087] Each thin film was laminated by a vacuum deposition method at a degree of vacuum of 2.0×10^{-5} Pa on a glass substrate on which an anode formed of indium tin oxide (ITO) having a thickness of 70 nm had been formed. First, copperphthalocyanine (CuPC) was formed into a layer having a thickness of 30 nm to serve as a hole-injecting layer on the ITO. Next, diphenyl naphthyl diamine (NPD) was formed into a layer having a thickness of 15 nm to serve as a hole-transporting layer. Next, the compound 1 serving as a host material for a light-emitting layer and an iridium complex [iridium(III) bis(4,6-di-fluorophenyl)-pyridinato-N,C2']picolinate] (FIrpic) serving as a blue phosphorescent material as a dopant were co-deposited from different deposition sources onto the hole-transporting layer to form a light-emitting layer having a thickness of 30 nm. The concentration of FIrpic was 20%. Next, Alq₃ was formed into a layer having a thickness of 25 nm to serve as an electron-transporting layer. Further, lithium fluoride (LiF) was formed into a layer having a thickness of 1.0 nm to serve as an electron-injecting layer on the electron-transporting layer. Finally, aluminum (Al) was formed into a layer having a thickness of 70 nm to serve as an electrode on the electron-injecting layer. The resultant organic EL device has such a layer construction that the electron-injecting layer is added between the cathode and the electron-transporting layer in the organic EL device illustrated in FIG. 1.

[0088] An external power source was connected to the resultant organic EL device to apply a DC voltage to the device. As a result, it was confirmed that the device had such light-emitting characteristics as shown in Table 2. The columns "luminance", "voltage", and "luminous efficiency" in Table 1 show values at 2.5 mA/cm² (initial characteristics). The maximum wavelength of the emission spectrum of the device was 475 nm, and hence the acquisition of light emission from FIrpic was found.

Examples 3 to 9

[0089] Organic EL devices were each produced in the same manner as in Example 2 except that the compound 13, 25, 26, 29, 36, 45, or 57 was used instead of the compound 1 as the host material for the light-emitting layer in Example 2.

Comparative Example 1

[0090] An organic EL device was produced in the same manner as in Example 2 except that mCP was used as the host material for the light-emitting layer in Example 2.

Comparative Examples 2 to 4

[0091] Organic EL devices were each produced in the same manner as in Example 2 except that the compound H-1, H-2, or H-3 was used as the host material for the light-emitting layer in Example 2.

[0092] The organic EL devices obtained in Examples 3 to 9 and Comparative Examples 1 to 4 were evaluated in the same manner as in Example 3. As a result, it was confirmed that the devices had such light-emitting characteristics as shown in Table 1. The maximum wavelength of each of the emission spectra of the organic EL devices obtained in Examples 3 to 9 and Comparative Examples 1 to 4 was 475 nm, and hence the acquisition of light emission from FIrpic was identified.

[Table 1]

	Host material compound	Luminance (cd/m ²)	Voltage (V)	Visual luminous efficiency (lm/W)
Example 2	1	200	6.8	3.7
Example 3	13	180	7.1	3.2
Example 4	25	210	7.4	3.6
Example 5	26	190	6.8	3.5
Example 6	29	195	6.8	3.6

(continued)

	Host material compound	Luminance (cd/m ²)	Voltage (V)	Visual luminous efficiency (lm/W)
Example 7	36	210	7.1	3.7
Example 8	45	180	6.8	3.3
Example 9	57	185	6.9	3.4
Comparative Example 1	mCP	140	8.7	2.0
Comparative Example 2	H-1	100	7.7	1.6
Comparative Example 3	H-2	140	7.5	2.3
Comparative Example 4	H-3	160	7.5	2.7

Example 10

[0093] Each thin film was laminated by a vacuum deposition method at a degree of vacuum of 2.0×10^{-5} Pa on a glass substrate on which an anode formed of indium tin oxide (ITO) having a thickness of 70 nm had been formed. First, copper phthalocyanine (CuPC) was formed into a layer having a thickness of 30 nm to serve as a hole-injecting layer on the ITO. Next, diphenyl naphthyl diamine (NPD) was formed into a layer having a thickness of 15 nm to serve as a hole-transporting layer. Next, the compound 1 serving as a host material for a light-emitting layer and Ir(ppy)₃ serving as a dopant were co-deposited from different deposition sources onto the hole-transporting layer to form a light-emitting layer having a thickness of 30 nm. The concentration of Ir(ppy)₃ was 10%. Next, Alq₃ was formed into a layer having a thickness of 25 nm to serve as an electron-transporting layer. Further, lithium fluoride (LiF) was formed into a layer having a thickness of 1 nm to serve as an electron-injecting layer on the electron-transporting layer. Finally, aluminum (Al) was formed into a layer having a thickness of 70 nm to serve as an electrode on the electron-injecting layer. Thus, an organic EL device was produced.

[0094] An external power source was connected to the resultant organic EL device to apply a DC voltage to the device. As a result, it was confirmed that the device had such light-emitting characteristics as shown in Table 2. The columns "luminance", "voltage", and "luminous efficiency" in Table 2 show values at the time of driving at 20 mA/cm² (initial characteristics). The maximum wavelength of the emission spectrum of the device was 530 nm, and hence the acquisition of light emission from Ir(ppy)₃ was found.

Examples 11 to 17

[0095] Organic EL devices were each produced in the same manner as in Example 10 except that the compound 13, 25, 26, 29, 36, 45, or 57 was used instead of the compound 1 as the host material for the light-emitting layer in Example 11.

Comparative Examples 5 to 8

[0096] Organic EL devices were each produced in the same manner as in Example 10 except that CBP, H-1, H-2, or H-3 was used as the host material for the light-emitting layer in Example 10.

[0097] The organic EL devices obtained in Examples 11 to 17 and Comparative Examples 5 to 8 were evaluated in the same manner as in Example 10. As a result, it was confirmed that the devices had such light-emitting characteristics as shown in Table 2. The maximum wavelength of each of the emission spectra of the organic EL devices obtained in Examples 11 to 17 and Comparative Examples 5 to 8 was 530 nm, and hence the acquisition of light emission from Ir(ppy)₃ was identified.

[Table 2]

	Host material compound	Luminance (cd/m ²)	Voltage (V)	Visual luminous efficiency (lm/W)
5	Example 10	1	2,000	8.5
	Example 11	13	2,000	8.9
	Example 12	25	2,100	9.3
10	Example 13	26	1,900	8.5
	Example 14	29	1,950	8.5
	Example 15	36	2,100	8.9
	Example 16	45	1,800	8.5
15	Example 17	57	1,850	8.6
	Comparative Example 5	CBP	1,120	8.7
20	Comparative Example 6	H-1	1,200	8.5
	Comparative Example 7	H-2	1,000	8.3
25	Comparative Example	H-3	1,600	9.2

Example 18

[0098] Each thin film was laminated by a vacuum deposition method at a degree of vacuum of 2.0×10^{-5} Pa on a glass substrate on which an anode formed of indium tin oxide (ITO) having a thickness of 70 nm had been formed. First, copper phthalocyanine (CuPC) was formed into a layer having a thickness of 30 nm to serve as a hole-injecting layer on the ITO. Next, diphenyl naphthyl diamine (NPD) was formed into a layer having a thickness of 15 nm to serve as a hole-transporting layer. Next, mCP serving as a host material for a light-emitting layer and FIrpic serving as a dopant were co-deposited from different deposition sources onto the hole-transporting layer to form a light-emitting layer having a thickness of 30 nm. The concentration of FIrpic was 20 wt%. Next, the compound 1 was formed into a layer having a thickness of 5 nm to serve as a hole-blocking layer on the light-emitting layer. Next, Alq₃ was formed into a layer having a thickness of 20 nm to serve as an electron-transporting layer. Further, lithium fluoride (LiF) was formed into a layer having a thickness of 1.0 nm to serve as an electron-injecting layer on the electron-transporting layer. Finally, aluminum (Al) was formed into a layer having a thickness of 70 nm to serve as an electrode on the electron-injecting layer. The resultant organic EL device has such a layer construction that the electron-injecting layer is added between the cathode and the electron-transporting layer and the hole-blocking layer is added between the light-emitting layer and the electron-transporting layer in the organic EL device illustrated in FIG. 1.

[0099] An external power source was connected to the resultant organic EL device to apply a DC voltage to the device. As a result, it was confirmed that the device had such light-emitting characteristics as shown in Table 3. The columns "luminance", "voltage", and "luminous efficiency" in Table 3 show values at the time of driving at 20 mA/cm² (initial characteristics). The maximum wavelength of the emission spectrum of the device was 475 nm, and hence the acquisition of light emission from FIrpic was found.

Examples 19 to 25

[0100] Organic EL devices were each produced in the same manner as in Example 18 except that the compound 13, 25, 26, 29, 36, 45, or 57 was used instead of the compound 1 as the hole-blocking material in Example 18.

Comparative Example 9

[0101] An organic EL device was produced in the same manner as in Example 18 except that the thickness of Alq₃ serving as the electron-transporting layer in Example 18 was changed to 25 nm and the hole-blocking layer was not

formed.

Comparative Examples 10 to 12

[0102] Organic EL devices were each produced in the same manner as in Example 18 except that the compound H-1, H-2, or H-3 was used as the hole-blocking material in Example 18.

[0103] The organic EL devices obtained in Examples 19 to 25 and Comparative Examples 9 to 12 were evaluated in the same manner as in Example 18. As a result, it was confirmed that the devices had such light-emitting characteristics as shown in Table 3. The maximum wavelength of each of the emission spectra of the organic EL devices obtained in Examples 19 to 25 and Comparative Examples 9 to 12 was 475 nm, and hence the acquisition of light emission from Flrpic was identified. Each of the host materials for the light-emitting layers used in Examples 19 to 25 and Comparative Examples 9 to 12 is mCP.

[Table 3]

	Hole-blocking material compound	Luminance (cd/m ²)	Voltage (V)	Visual luminous efficiency (lm/W)
Example 18	1	200	7.0	3.6
Example 19	13	190	7.1	3.4
Example 20	25	220	7.4	3.7
Example 21	26	200	6.8	3.7
Example 22	29	205	6.9	3.7
Example 23	36	220	7.2	3.8
Example 24	45	190	7.3	3.3
Example 25	57	195	7.2	3.4
Comparative Example 9	-	140	8.7	2.0
Comparative Example 10	H-1	170	8.2	2.6
Comparative Example 11	H-2	180	8.3	2.7
Comparative Example 12	H-3	200	9.0	2.8





[0104] All the examples showed improvements in initial characteristics as compared to Comparative Example 9 not using the hole-blocking material. Of those examples, however, the examples each using the carborane compound of the present invention in its hole-blocking layer show better characteristics.

Reference Signs List

[0105] 1 substrate, 2 anode, 3 hole-injecting layer, 4 hole-transporting layer, 5 light-emitting layer, 6 electron-transporting layer, 7 cathode

Claims

1. A material for an organic electroluminescent device, comprising a carborane compound represented by the general formula (1), (2), or (3) :



wherein,

a ring A represents a divalent carborane group $C_2B_{10}H_{10}$ represented by the formula (1a) or the formula (1b), and when a plurality of rings A are present in a molecule thereof, the rings may be identical to or different from each other;

r represents a number of repetitions and represents an integer of 0 or 1;

L^1 and L^2 each represent a single bond, a divalent substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a divalent substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, or a divalent linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic hydrocarbon groups or the aromatic heterocyclic groups, terminal L^1 and L^2 may each represent an alkyl group having 1 to 12 carbon atoms or an alkoxy group having 1 to 12 carbon atoms, and when L^1 and L^2 each represent the linked aromatic group, the group may be linear or branched, and aromatic rings to be linked may be identical to or different from each other, provided that when r represents 0, the single bond is excluded, and when r represents 1, at least one aromatic heterocyclic group is included;



L^3 represents a hydrogen atom, a substituted or unsubstituted aromatic hydrocarbon group having 6 to 30 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 30 carbon atoms, a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the substituted or unsubstituted aromatic hydrocarbon groups and the substituted or unsubstituted aromatic heterocyclic groups, an alkyl group having 1 to 12 carbon atoms, or an alkoxy group having 1 to 12 carbon atoms, and when L^3 represents the linked aromatic group, the group may be linear or branched, and aromatic rings to be linked may be identical to or different from each other; and


when the aromatic group in each of L^1 to L^3 has a substituent, the substituent is an alkyl group having 1 to 12 carbon atoms, an alkoxy group having 1 to 12 carbon atoms, or an acetyl group, the aromatic group may have a plurality of substituents, and the plurality of substituents may be identical to or different from each other.

2. A material for an organic electroluminescent device according to claim 1, wherein, in each of the general formulae (1) to (3), the ring A represents a divalent carborane group $C_2B_{10}H_8$ represented by the formula (1a).
3. A material for an organic electroluminescent device according to claim 1, wherein, in each of the general formulae (1) to (3), L^1 to L^3 each independently represent a substituted or unsubstituted aromatic hydrocarbon group having 6 to 18 carbon atoms, a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic hydrocarbon groups and the aromatic heterocyclic groups.
4. A material for an organic electroluminescent device according to claim 1, wherein, in each of the general formulae (1) to (3), L^1 to L^3 each independently represent a substituted or unsubstituted aromatic heterocyclic group having 3 to 17 carbon atoms, or a linked aromatic group formed by linking 2 to 6 aromatic groups selected from the aromatic heterocyclic groups.
5. A material for an organic electroluminescent device according to claim 1, wherein, in each of the general formulae (1) to (3), r represents an integer of 0.
6. An organic electroluminescent device having a structure in which an anode, at least one organic layer, and a cathode are laminated on a substrate, wherein the at least one organic layer comprises an organic layer containing the material for an organic electroluminescent device of any one of claims 1 to 5.
7. An organic electroluminescent device according to claim 6, wherein the organic layer containing the material for an organic electroluminescent device comprises at least one layer selected from the group consisting of a light-emitting layer, an electron-transporting layer, and a hole-blocking layer.
8. An organic electroluminescent device according to claim 6, wherein the organic layer containing the material for an organic electroluminescent device comprises a light-emitting layer containing a phosphorescent light-emitting dopant.
9. An organic electroluminescent device according to claim 8, wherein an emission wavelength of the phosphorescent light-emitting dopant has an emission maximum wavelength at 550 nm or less.

Patentansprüche

1. Ein Material für eine organische elektrolumineszierende Vorrichtung, umfassend eine Carboranverbindung, dargestellt durch die allgemeine Formel (1), (2) oder (3):





wobei

ein Ring A einen zweiwertigen Carboranrest $C_2B_{10}H_{10}$, dargestellt durch die Formel (1a) oder die Formel (1b), bedeutet und wenn mehrere Ringe A in einem Molekül davon vorhanden sind, die Ringe gleich oder voneinander verschieden sein können;

r eine Anzahl an Wiederholungen darstellt und eine ganze Zahl von 0 oder 1 bedeutet;

L^1 und L^2 jeweils eine Einfachbindung, einen zweiwertigen substituierten oder unsubstituierten aromatischen Kohlenwasserstoffrest mit 6 bis 30 Kohlenstoffatomen, einen zweiwertigen substituierten oder unsubstituierten aromatischen heterocyclischen Rest mit 3 bis 30 Kohlenstoffatomen oder einen zweiwertigen verknüpften aromatischen Rest, gebildet durch Verknüpfen von 2 bis 6 aromatischen Resten, ausgewählt aus den aromatischen Kohlenwasserstoffresten oder den aromatischen heterocyclischen Resten, bedeuten, die endständigen Reste L^1 und L^2 jeweils einen Alkylrest mit 1 bis 12 Kohlenstoffatomen oder einen Alkoxyrest mit 1 bis 12 Kohlenstoffatomen bedeuten können, und wenn L^1 und L^2 jeweils den verknüpften aromatischen Rest bedeuten, der Rest linear oder verzweigt sein kann, und zu verknüpfende aromatische Ringe gleich oder voneinander verschieden sein können, mit der Maßgabe, dass, wenn r 0 darstellt, die Einfachbindung ausgenommen ist, und wenn r 1 darstellt, mindestens ein aromatischer heterocyclischer Rest enthalten ist;




L^3 ein Wasserstoffatom, einen substituierten oder unsubstituierten aromatischen Kohlenwasserstoffrest mit 6 bis 30 Kohlenstoffatomen, einen substituierten oder unsubstituierten aromatischen heterocyclischen Rest mit 3 bis 30 Kohlenstoffatomen, einen verknüpften aromatischen Rest, gebildet durch Verknüpfen von 2 bis 6 aromatischen Resten, ausgewählt aus den substituierten oder unsubstituierten aromatischen Kohlenwasserstoffresten und den substituierten oder unsubstituierten aromatischen heterocyclischen Resten, einen Alkylrest mit 1 bis 12 Kohlenstoffatomen oder einen Alkoxyrest mit 1 bis 12 Kohlenstoffatomen bedeutet und wenn L^3 den verknüpften aromatischen Rest bedeutet, der Rest linear oder verzweigt sein kann, und zu verknüpfende aromatische Ringe gleich oder voneinander verschieden sein können; und wenn der aromatische Rest in jedem von L^1 bis L^3 einen Substituenten aufweist, der Substituent ein Alkylrest mit 1 bis 12 Kohlenstoffatomen, ein Alkoxyrest mit 1 bis 12 Kohlenstoffatomen oder ein Acetylrest ist, der aromatische Rest mehrere Substituenten aufweisen kann und die mehreren Substituenten gleich oder voneinander verschieden sein können.


2. Ein Material für eine organische elektrolumineszierende Vorrichtung nach Anspruch 1, wobei in jeder der allgemeinen Formeln (1) bis (3) der Ring A einen zweiwertigen Carboranrest $C_2B_{10}H_8$, dargestellt durch die Formel (1a), darstellt.
3. Ein Material für eine organische elektrolumineszierende Vorrichtung nach Anspruch 1, wobei in jeder der allgemeinen Formeln (1) bis (3) L^1 bis L^3 jeweils unabhängig einen substituierten oder unsubstituierten aromatischen Kohlenwasserstoffrest mit 6 bis 18 Kohlenstoffatomen, einen substituierten oder unsubstituierten aromatischen heterocyclischen Rest mit 3 bis 17 Kohlenstoffatomen oder einen verknüpften aromatischen Rest, gebildet durch Verknüpfen von 2 bis 6 aromatischen Resten, ausgewählt aus den aromatischen Kohlenwasserstoffresten und den aromatischen heterocyclischen Resten, bedeuten.
4. Ein Material für eine organische elektrolumineszierende Vorrichtung nach Anspruch 1, wobei in jeder der allgemeinen Formeln (1) bis (3) L^1 bis L^3 jeweils unabhängig einen substituierten oder unsubstituierten aromatischen heterocyclischen Rest mit 3 bis 17 Kohlenstoffatomen oder einen verknüpften aromatischen Rest, gebildet durch Verknüpfen von 2 bis 6 aromatischen Resten, ausgewählt aus den aromatischen heterocyclischen Resten, bedeuten.

5. Ein Material für eine organische elektrolumineszierende Vorrichtung nach Anspruch 1, wobei in jeder der allgemeinen Formeln (1) bis (3) r eine ganze Zahl 0 bedeutet.
6. Eine organische elektrolumineszierende Vorrichtung mit einer Struktur, bei der eine Anode, mindestens eine organische Schicht und eine Kathode auf ein Substrat laminiert sind, wobei die mindestens eine organische Schicht eine organische Schicht umfasst, die das Material für eine organische elektrolumineszierende Vorrichtung nach einem der Ansprüche 1 bis 5 enthält.
7. Eine organische elektrolumineszierende Vorrichtung nach Anspruch 6, wobei die organische Schicht, die das Material für eine organische elektrolumineszierende Vorrichtung enthält, mindestens eine Schicht, ausgewählt aus der Gruppe bestehend aus einer lichtemittierenden Schicht, einer elektronentransportierenden Schicht und einer Lochblockierenden Schicht, umfasst.
8. Eine organische elektrolumineszierende Vorrichtung nach Anspruch 6, wobei die organische Schicht, die das Material für eine organische elektrolumineszierende Vorrichtung enthält, eine lichtemittierende Schicht umfasst, die ein phosphoreszierendes lichtemittierendes Dotierungsmittel enthält.
9. Eine organische elektrolumineszierende Vorrichtung nach Anspruch 8, wobei eine Emissionswellenlänge des phosphoreszierenden lichtemittierenden Dotierungsmittels ein Emissionswellenlängenmaximum bei 550 nm oder weniger aufweist.

Revendications

1. Matériau pour un dispositif électroluminescent organique, comprenant un composé carborane représenté par la formule générale (1), (2) ou (3) :





dans lesquelles

le cycle A représente un groupe carborane divalent $C_2B_{10}H_{10}$ représenté par la formule (1a) ou la formule (1b) et, quand plusieurs cycles A sont présents dans une molécule de ce composé, les cycles peuvent être identiques entre eux ou différents les uns des autres ;

r représente le nombre de répétitions et représente l'entier 0 ou 1 ;

chacun de L^1 et L^2 représente une liaison simple, un groupe hydrocarboné aromatique divalent substitué ou non substitué ayant 6 à 30 atomes de carbone, un groupe hétérocyclique aromatique divalent substitué ou non substitué ayant 3 à 30 atomes de carbone, ou un groupe aromatique lié divalent formé par liaison de 2 à 6 groupes aromatiques choisis parmi les groupes hydrocarbonés aromatiques et les groupes hétérocycliques aromatiques, chacun des L^1 et L^2 terminaux peuvent représenter un groupe alkyle ayant 1 à 12 atomes de carbone ou un groupe alcoxy ayant 1 à 12 atomes de carbone, et quand chacun de L^1 et L^2 représente un groupe aromatique lié, le groupe peut être linéaire ou ramifié, et les cycles aromatiques devant être liés peuvent être identiques entre eux ou différents les uns des autres, sous réserve que, lorsque r vaut 0, la liaison simple soit exclue, et que lorsque r vaut 1, au moins un groupe hétérocyclique aromatique soit inclus ;

L^3 représente un atome d'hydrogène, un groupe hydrocarboné aromatique substitué ou non substitué ayant 6 à 30 atomes de carbone, un groupe hétérocyclique aromatique substitué ou non substitué ayant 3 à 30 atomes de carbone, un groupe aromatique lié formé par liaison de 2 à 6 groupes aromatiques choisis parmi les groupes hydrocarbonés aromatiques substitués ou non substitués et les groupes hétérocycliques aromatiques substitués ou non substitués, un groupe alkyle ayant 1 à 12 atomes de carbone, ou un groupe alcoxy ayant 1 à 12 atomes de carbone, et quand L^3 représente un groupe aromatique lié, le groupe peut être linéaire ou ramifié, et les cycles aromatiques devant être liés peuvent être identiques entre eux ou différents les uns des autres ; et quand le groupe aromatique dans chacun de L^1 à L^3 porte un substituant, le substituant est un groupe alkyle ayant 1 à 12 atomes de carbone, un groupe alcoxy ayant 1 à 12 atomes de carbone, ou un groupe acétyle, le groupe aromatique peut porter plusieurs substituants, et les plusieurs substituants peuvent être identiques entre eux ou différents les uns des autres.

2. Matériau pour un dispositif électroluminescent organique selon la revendication 1, dans lequel, dans chacune des formules générales (1) à (3), le cycle A représente un groupe carborane divalent $C_2B_{10}H_8$ représenté par la formule (1a).
3. Matériau pour un dispositif électroluminescent organique selon la revendication 1, dans lequel, dans chacune des formules générales (1) à (3), chacun de L^1 à L^3 représente indépendamment un groupe hydrocarboné aromatique substitué ou non substitué ayant 6 à 18 atomes de carbone, un groupe hétérocyclique aromatique substitué ou non substitué ayant 3 à 17 atomes de carbone, ou un groupe aromatique lié formé par liaison de 2 à 6 groupes aromatiques choisis parmi les groupes hydrocarbonés aromatiques et les groupes hétérocycliques aromatiques.
4. Matériau pour un dispositif électroluminescent organique selon la revendication 1, dans lequel, dans chacune des formules générales (1) à (3), chacun de L^1 à L^3 représente indépendamment un groupe hétérocyclique aromatique substitué ou non substitué ayant 3 à 17 atomes de carbone, ou un groupe aromatique lié formé par liaison de 2 à 6 groupes aromatiques choisis parmi les groupes hétérocycliques aromatiques.
5. Matériau pour un dispositif électroluminescent organique selon la revendication 1, dans lequel, dans chacune des formules générales (1) à (3), r représente l'entier 0.
6. Dispositif électroluminescent organique ayant une structure dans laquelle une anode, au moins une couche organique, et une cathode, sont stratifiées sur un substrat, dans lequel l'au moins une couche organique comprend une couche organique contenant le matériau pour un dispositif électroluminescent organique de l'une quelconque des revendications 1 à 5.
7. Dispositif électroluminescent organique selon la revendication 6, dans lequel la couche organique contenant le matériau pour un dispositif électroluminescent organique comprend au moins une couche choisie dans l'ensemble

constitué par une couche luminescente, une couche de transport d'électrons, et une couche de blocage de trous.

8. Dispositif électroluminescent organique selon la revendication 6, dans lequel la couche organique contenant le matériau pour un dispositif électroluminescent organique comprend une couche luminescente contenant un dopant luminescent phosphorescent.

9. Dispositif électroluminescent organique selon la revendication 8, dans lequel la longueur d'onde d'émission du dopant luminescent phosphorescent a une longueur d'onde d'émission maximale à 550 nm ou moins.

FIG. 1





FIG. 2



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO 01041512 A1 [0005]
- JP 2001313178 A [0005]
- JP 2005162709 A [0005]
- JP 2005166574 A [0005]
- US 20120319088 A1 [0005]
- WO 2013094834 A1 [0005]
- US 20090167162 A1 [0005]
- JP 2011213643 A [0057]

Non-patent literature cited in the description

- *Journal of Organometallic Chemistry*, 1993, vol. 462, 19-29 [0038]
- *Advanced Materials*, 2009, vol. 21, 4802-4806 [0055]
- *Adv. Mater.*, 2009, vol. 21, 4802-4806 [0057]
- *Appl. Phys. Lett.*, 2011, vol. 98, 083302 [0057]
- *J. Am. Chem. Soc.*, 2012, vol. 134, 14706-14709 [0057]

专利名称(译)	用于有机电致发光元件的材料和使用其的有机电致发光元件		
公开(公告)号	EP3089230B1	公开(公告)日	2019-01-09
申请号	EP2014875046	申请日	2014-11-05
[标]申请(专利权)人(译)	新日铁化学株式会社		
申请(专利权)人(译)	NIPPON STEEL住金化工有限公司.		
当前申请(专利权)人(译)	NIPPON STEEL住金化工有限公司.		
[标]发明人	OGAWA JUNYA TADA MASASHI UEDA TOKIKO KAI TAKAHIRO		
发明人	OGAWA, JUNYA TADA, MASASHI UEDA, TOKIKO KAI, TAKAHIRO		
IPC分类号	H01L51/54 C07D333/76 C07D409/04 C07D409/08 C07D409/14 C09K11/02 H01L51/50		
CPC分类号	C07D333/76 C07D409/04 C07D409/08 C07D409/14 C07F5/027 C09K11/025 C09K11/06 C09K2211/1007 C09K2211/1029 C09K2211/185 H01L51/0067 H01L51/0072 H01L51/0074 H01L51/008 H01L51/0081 H01L51/0085 H01L51/5016 C07D209/82 C09K2211/1092 H01L51/5072 H01L51/5092 H01L51/5024 H01L51/5096 H01L51/5206 H01L51/5234		
优先权	2013269272 2013-12-26 JP		
其他公开文献	EP3089230A4 EP3089230A1		
外部链接	Espacenet		

摘要(译)

本发明公开了一种有机电致发光器件（有机EL器件），其具有改进的发光效率，足够可靠的驱动稳定性和简单的结构，以及用于有机EL器件的材料。用于有机EL器件的材料包括碳硼烷化合物，其具有其中存在至少一个碳硼烷环和至少一个二苯并噻吩环的结构，并且所述至少一个碳硼烷环在位置1与至少一个二苯并噻吩环键合，此外，有机EL器件包括在层压在基板上的阳极和阴极之间的至少一个有机层，其中所述至少一个有机层包括碳硼烷化合物。

