



(11) **EP 2 166 583 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(43) Date of publication:
24.03.2010 Bulletin 2010/12

(51) Int Cl.:
H01L 51/50 (2006.01)

(21) Application number: **07832315.1**

(86) International application number:
PCT/JP2007/072585

(22) Date of filing: **21.11.2007**

(87) International publication number:
WO 2009/008099 (15.01.2009 Gazette 2009/03)

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE SI SK TR
Designated Extension States:
AL BA HR MK RS

- **ENDO, Jun**
Sodegaura-shi
Chiba 299-0293 (JP)
- **NUMATA, Masaki**
Sodegaura-shi
Chiba 299-0293 (JP)
- **FUKUOKA, Kenichi**
Sodegaura-shi
Chiba 299-0293 (JP)

(30) Priority: **10.07.2007 JP 2007181142**

(71) Applicant: **Idemitsu Kosan Co., Ltd.**
Chiyoda-ku
Tokyo 100-8321 (JP)

(74) Representative: **Vossius & Partner**
Siebertstraße 4
81675 München (DE)

(72) Inventors:
• **IWAKUMA, Toshihiro**
Sodegaura-shi
Chiba 299-0293 (JP)

(54) **MATERIAL FOR ORGANIC ELECTROLUMINESCENCE ELEMENT, AND ORGANIC ELECTROLUMINESCENCE ELEMENT PREPARED BY USING THE MATERIAL**

(57) A material for organic electroluminescence devices of the invention which is for use in combination with at least one phosphorescent metal complex has a specific heterocyclic structure. The material for organic electroluminescence devices is used as a host material or a hole transporting material. An organic electroluminescence device having an anode, a cathode and an organic

thin film layer having one or more layers which is interposed between the anode and cathode, in which at least one layer of the organic thin film layer contains the material for organic electroluminescence devices, has a high emitting efficiency, causes little pixel defects, is excellent in heat resistance, and shows a long lifetime.

EP 2 166 583 A1

Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to materials for organic electroluminescence devices and organic electroluminescence devices using the materials and, more particularly to materials for organic electroluminescence devices which realize electroluminescence devices exhibiting a high emitting efficiency, causing little pixel defects, exhibiting a high heat resistance and having a long lifetime.

10 BACKGROUND ART

[0002] An organic electroluminescence device (organic EL device) is a spontaneous emission device which utilizes the phenomenon of fluorescence which occurs by the energy of recombination between holes injected from an anode and electrons injected from a cathode by application of electric field. As the structure of organic EL devices, a two-layered structure having a hole transporting (injecting) layer and an electron transporting/light emitting layer and a three-layered structure having a hole transporting (injecting) layer, a light emitting layer and an electron transporting (injecting) layer are well known. To increase the efficiency of recombination of injected holes and electrons in laminated devices, the structure of the device and the process for forming the device have been studied

15 **[0003]** It is recently proposed to use a light emitting layer of a phosphorescent material in addition to a light emitting layer of a fluorescent material. A high efficiency of light emission is achieved by utilizing the excited singlet state and the excited triplet state of the organic phosphorescent material in the light emitting layer. It is considered that the singlet exciton and the triplet exciton are formed in a proportion of 1:3 due to the difference in the spin multiplicity when electrons and holes are recombined in an organic EL device. Therefore, it is expected that an efficiency of light emission 3 to 4 times as great as that of a device utilizing only the fluorescent material can be achieved by utilizing a phosphorescent material.

25 **[0004]** To prevent the excited triplet state or the triplet exciton from quenching, the organic EL devices described above are made into a laminate structure having an anode, a hole transporting layer, an organic light emitting layer, an electron transporting layer (a hole blocking layer), an electron transporting layer and a cathode in this order, while using an organic light emitting layer made of a host compound and a phosphorescent compound (for example, Patent Documents 1-6). In these Patent Documents, host materials having a dibenzofuran structure or a dibenzothiophene structure are described. However, there is nothing about their advantage in the device performance as compared with a host material having a carbazole structure.

Patent Documents 7 and 8 disclose compounds prepared by bonding a carbazole structure to dibenzo compounds. The proposed compounds are used in a host material for a blue phosphorescent device in examples thereof. The compounds of the present invention are not taught and the effect is uncertain.

35 Patent Documents 9, 10 and 11 disclose compounds prepared by bonding an anthracene structure to dibenzo compounds. However, the energy level of the excited triplet state of the proposed compounds is small because of the anthracene structure. Therefore, a blue phosphorescent material does not emit light even if any of the proposed compounds is used as a host material for the light emitting layer.

40 Patent Document 12 discloses dibenzofuran compounds essentially having at least two polymerizable functional groups. If the host material of a phosphorescent device has in its molecule a polymerizable group such as propenylene group, vinylene group and 4-propyl-2-pentenylene group which is formed by introducing an unsaturated bond such as double bond and triple bond, radicals are propagatedly generated in the device to adversely affect the emitting efficiency and lifetime.

45 **[0005]**

[Patent Document 1] WO 05/101912

[Patent Document 2] JP 5-109485A

[Patent Document 3] JP 2004-002351A

50 [Patent Document 4] WO 04/096945

[Patent Document 5] JP 2002-308837A

[Patent Document 6] WO 2005-113531

[Patent Document 7] JP 2005-112765A

[Patent Document 8] WO 2006-114966

55 [Patent Document 9] JP 2005-314239A

[Patent Document 10] JP 2007-77094A

[Patent Document 11] JP 2007-63501A


[Patent Document 12] JP 2007-110097A

DISCLOSURE OF THE INVENTION

[0006] The present invention has been made to overcome the above problems and has an object of providing a material for organic EL devices which realizes an EL device exhibiting a high efficiency of light emission, causing little pixel defects, exhibiting a high heat resistance and having a long lifetime.

[0007] As a result of extensive research in view of achieving the above object, the inventors have found that a compound represented by the following formula 1, which has a dibenzothiophene or dibenzofuran structure having at its 2-position substituted with an aromatic hydrocarbon group, creates an excited triplet state having a sufficient energy level enough to prevent the emitting efficiency of a blue phosphorescent complex from being reduced. It has been further found that the compound realizes a highly efficient and highly heat-resistant organic EL device causing little pixel defects and having a long lifetime. The present invention is based on these findings.

[0008] Thus, the present invention provides a material for organic electroluminescence devices for use in combination with at least one phosphorescent metal complex, which comprises a compound represented by the following formula 1:



wherein R_1 to R_3 are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that each of R_1 to R_3 is not carbazolyl group which is optionally substituted or not azacarbazolyl group having 2 or more nitrogen atoms which is optionally substituted;

R_6 and R_{10} are each independently hydrogen atom or alkyl group having 1 to 40 carbon atoms which is optionally substituted;

R_7 to R_9 are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that when R_8 and R_9 , or R_8 and R_7 are not bonded to each other thereby do not form a ring structure, at least one of R_7 to R_9 is 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is optionally substituted, dibenzothiophenyl group which is optionally substituted, or phenyl group or biphenyl group each being substituted by at least one group selected from the group consisting of 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is optionally substituted and dibenzothiophenyl group which is optionally substituted;

R_8 and R_9 , or R_8 and R_7 are optionally bonded to each other to form a ring structure which is optionally substituted, and R_7 or R_9 which does not form the ring structure is hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted,


substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that R₈ and R₉, or R₈ and R₇ together with a benzene ring to which R₇ to R₉ are bonded do not form carbazolyl group; I₁ to R₃ are all hydrogen atoms when at least one of R₇ to R₉ is dibenzofuranyl group which is optionally substituted or dibenzothiophenyl group which is optionally substituted; each of R₁ to R₃ and R₆ to R₁₀ does not have a polymerizable functional group at its terminal end; and X is sulfur atom or oxygen atom.

[0009] The present invention further provides an organic electroluminescence device which comprises a cathode, an anode and an organic thin film layer having one or more layers, the organic thin film layer being interposed between the cathode and the anode, at least one layer of the organic thin film being a light emitting layer which comprises a host material for use in combination with at least one phosphorescent metal complex, and at least one layer of the organic thin film containing the material for organic electroluminescence devices mentioned above.

[0010] The organic EL device made using the material for organic EL devices of the present invention is free from pixel defects, highly efficient, highly heat resistant and durable for a long period of time.

BEST MODE FOR CARRYING OUT THE INVENTION

[0011] The material for organic EL devices of the invention is represented by the following formula 1:




[0012] in the formula 1, R₁ to R₃ are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group. Preferably, R₁ to R₃ are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, or arylthio group having 6 to 20 carbon atoms which is optionally substituted.



[0013] R₆ and R₁₀ are each independently hydrogen atom or alkyl group having 1 to 40 carbon atoms which is optionally substituted.

[0014] R₇ to R₉ are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which





is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that when R_8 and R_9 , or R_8 and R_7 are not bonded to each other thereby do not form a ring structure, at least one of R_7 to R_9 is 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is optionally substituted, dibenzothiophenyl group which is optionally substituted, or phenyl group or biphenyl group each being substituted by at least one group selected from the group consisting of 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is optionally substituted and dibenzothiophenyl group which is optionally substituted. Preferably, at least one of R_7 to R_9 is 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, or phenyl group or biphenyl group each being substituted by at least one group selected from the group consisting of 9-carbazolyl group which is optionally substituted and azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted.

[0015] Examples of azacarbazoyl group having 2 to 5 nitrogen atoms which is optionally substituted are shown below, although not limited thereto. The optional substituents are omitted for conciseness and the position of free valence on the azacarbazole ring is not specifically limited.





[0016] R_8 and R_9 , or R_8 and R_7 are optionally bonded to each other to form a ring structure which is optionally substituted. When forming the ring structure, R_8 and R_9 , or and R_7 together with the benzene to which R_7 to R_9 are bonded preferably form, for example, the following azacarbazole structure having 2 to 5 nitrogen atoms, dibenzofuran structure, dibenzothiophene structure, or fluorene structure (substituents such as P_6 and optional substituents are omitted for conciseness). However, R_8 and R_9 , or R_8 and R_7 together with the benzene ring to which R_7 to R_9 are bonded do not form a carbazole structure.



[0017] When R_8 and R_9 , or R_8 and R_7 are bonded to form the ring structure which is optionally substituted, the remaining R_7 or R_9 which does not form the ring structure is hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed, aryl group having 10 to 18 carbon atoms which is optionally substituted, acyloxy group having 6 to

20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group.

[0018] Each of R_1 to R_3 and P_6 to R_{10} (inclusive of substituent if substituted) does not have a polymerizable functional group, for example, vinyl group, 1-methylvinyl group, 1-halovinyl group and 1-trihalomethylvinyl group, at its terminal end.

[0019] The halogen atom includes, for example, fluorine, chlorine, bromine and iodine.

[0020] Examples of the alkyl group having 1 to 40 carbon atoms which is optionally substituted include methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neopentyl group, 1-methylpentyl group, 2-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group, 1-heptyloctyl group, 3-methylpentyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl groups, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 1,2-dinitroethyl group, 2,3-dinitro-t-butyl group, and 1,2,3-trinitropropyl group. Preferred are methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neopentyl group, 1-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group, and 1-heptyloctyl group. The carbon number of the alkyl group (exclusive of substituent) is preferably from 1 to 10.

[0021] Examples of the cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted include cyclopentyl group, cyclohexyl group, cyclooctyl group, and 3,3,5,5-tetramethylcyclohexyl group, with cyclohexyl group, cyclooctyl group and 3,5-tetramethylcyclohexyl group being preferred. The carbon number of the cycloalkyl group (exclusive of substituent) is preferably from 3 to 12.

[0022] Examples of the heterocyclic group having 3 to 20 carbon atoms which is optionally substituted include 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 1-imidazolyl group, 2-imidazolyl group, 1-pyrazolyl group, 1-indolizinyll group, 2-indolizinyll group, 3-indolizinyll group, 5-indolizinyll group, 6-indolizinyll group, 7-indolizinyll group, 8-indolizinyll group, 2-imidazopyridinyl group, 3-imidazopyridinyl group, 5-imidazopyridinyl group, 6-imidazopyridinyl group, 7-imidazopyridinyl group, 8-imidazopyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalinyll group, 5-quinoxalinyll group, 6-quinoxalinyll group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, azacarbazole-1-yl group, azacarbazole-2-yl group, azacarbazole-3-yl group, azacarbazole-4-yl group, azacarbazole-5-yl group, azacarbazole-6-yl group, azacarbazole-7-yl group, azacarbazole-8-yl group, azacarbazole-9-yl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-8-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-

phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-8-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, 4-t-butyl-3-indolyl group, 1-dibenzofuranyl group, 2-dibenzofuranyl group, 3-dibenzofuranyl group, 4-dibenzofuranyl group, 1-dibenzothiophenyl group, 2-dibenzothiophenyl group, 3-dibenzothiophenyl group, 4-dibenzothiophenyl group, 1-silafluorenyl group, 2-silafluorenyl group, 3-silafluorenyl group, 4-silafluorenyl group, 1-germafluorenyl group, 2-germafluorenyl group, 3-germafluorenyl group, and 4-germafluorenyl group.

[0023] Of the above, preferred are 2-pyridinyl group, 1-indolizinyl group, 2-indolizinyl group, 3-indolizinyl group, 5-indolizinyl group, 6-indolizinyl group, 7-indolizinyl group, 8-indolizinyl group, 2-imidazopyridinyl group, 3-imidazopyridinyl group, 5-imidazopyridinyl group, 6-imidazopyridinyl group, 7-imidazopyridinyl group, 8-imidazopyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 9-carbazolyl group, 1-dibenzofuranyl group, 2-dibenzofuranyl group, 3-dibenzofuranyl group, 4-dibenzofuranyl group, 1-dibenzothiophenyl group, 2-dibenzothiophenyl group, 3-dibenzothiophenyl group, 4-dibenzothiophenyl group, 1-silafluorenyl group, 2-silafluorenyl group, 3-silafluorenyl group, 4-silafluorenyl group, 1-germafluorenyl group, 2-germafluorenyl group, 3-germafluorenyl group, 4-germafluorenyl group, azacarbazole-1-yl group, azacarbazole-2-yl group, azacarbazole-3-yl group, azacarbazole-4-yl group, azacarbazole-5-yl group, azacarbazole-6-yl group, azacarbazole-7-yl group, azacarbazole-8-yl group, and azacarbazole-9-yl group. The carbon number of the heterocyclic group (exclusive of substituent) is preferably from 3 to 14.

[0024] The alkoxy group having 1 to 40 carbon atoms which is optionally substituted is represented by -OY wherein Y and its preferred examples are the same as the alkyl groups mentioned above.

[0025] Examples of the non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted include phenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, o-cumenyl group, m-cumenyl group, p-cumenyl group, 2,3-xylyl group, 3,4-xylyl group, 2,5-xylyl group, mesityl group, and m-quaterphenyl group, with phenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, p-tolyl group, 3,4-xylyl group, and m-quaterphenyl-2-yl group being preferred. The carbon number of the non-condensed aryl group (exclusive of substituent) is preferably from 6 to 24.

[0026] Examples of the condensed aryl group having 10 to 18 carbon atoms which is optionally substituted include 1-naphthyl group, 2-naphthyl group, 1-phenanthrenyl group, 2-phenanthrenyl group, 3-phenanthrenyl group, 4-phenanthrenyl group, 9-phenanthrenyl group, 1-triphenylenyl group, 2-triphenylenyl group, 3-triphenylenyl group, 4-triphenylenyl group, 1-chrysenyl group, 2-chrysenyl group, 3-chrysenyl group, 4-chrysenyl group, 5-chrysenyl group, and 6-chrysenyl group.

[0027] The aryloxy group having 6 to 20 carbon atoms which is optionally substituted is represented by -OAr wherein Ar and its preferred examples are the same as the non-condensed aryl groups mentioned above.

[0028] Examples of the aralkyl group having 7 to 20 carbon atoms which is optionally substituted include benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, 1-pyrrolylmethyl group, 2-(1-pyrrolyl)ethyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-ami-

nobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, and 1-chloro-2-phenylisopropyl group, with benzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, and 2-phenylisopropyl group being preferred. The alkyl moiety of the aralkyl group has preferably

from 1 to 8 carbon atoms, and the aryl moiety (inclusive of heteroaryl) has preferably from 6 to 18 carbon atoms.


[0029] Each of the arylamino group having 6 to 40 carbon atoms which is optionally substituted, the alkylamino group having 1 to 40 carbon atoms which is optionally substituted and the aralkylamino group having 7 to 60 carbon atoms which is optionally substituted is represented by $-NQ_1Q_2$, wherein Q_1 and Q_2 are each independently selected from the alkyl groups, aryl groups and aralkyl groups described above. Similarly, preferred examples of Q_1 and Q_2 are the same as those described above.


[0030] The arylthio group having 6 to 20 carbon atoms which is optionally substituted is a group derived from the aryloxy group $-OAr$ by substituting sulfur atom for the oxygen atom. Preferred arylthio groups are derived from the preferred aryloxy groups in the same manner.

[0031] The arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted is represented by $-COAr_2$, wherein Ar_2 and its preferred examples are the same as the aryl groups mentioned above.

[0032] The alkyl halide group having 1 to 40 carbon atoms which is optionally substituted is, for example, derived from the alkyl group mentioned above by substituting halogen atom for at least one hydrogen atom. Preferred alkyl halide groups are derived from the preferred alkyl groups in the same manner.


[0033] The compound of the formula 1 is preferably represented by any of the following formulae 2 to 5:





[0038] In the formulae 7, R_6 , R_7 , R_9 , R_{10} , R_{20} to R_{24} and X are the same as defined above.

[0039] The compound of the formula 4 is preferably represented by the following formula 8:




[0040] In the formula 8, R_{18} , R_{19} , R_{22} , R_{23} and X are the same as defined above.


[0041] Examples of the substituent groups in the definitions of R_1 to R_3 , R_6 to R_{10} and R_{18} to R_{29} in the formulae 1 to 9 include alkyl group having 1 to 8 carbon atoms (methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group); hydroxyalkyl group having 1 to 5 carbon atoms (hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group); haloalkyl group having 1 to 4 carbon atoms (chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodomethyl group, 2-iodomethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triodopropyl group); aminoalkyl group having 1 to 4 carbon atoms (aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group); cyanoalkyl group having 1 to 4 carbon atoms (cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group); nitroalkyl group having 1 to 5 carbon atoms (nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, 1,2,3-trinitropropyl group); (alkyl)cycloalkyl group having 3 to 10 carbon atoms (cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group, 4-methylcyclohexyl group, 1-adamantyl group, 2-adamantyl group, 1-norbornyl group, 2-norbornyl group); having 1 to 60 carbon atoms alkoxy group (ethoxy group, methoxy group, isopropoxy group, n-propoxy group, s-butoxy group, t-butoxy group, pentoxy group, hexyloxy group); cycloalkoxy group having 3 to 6 carbon atoms (cyclopentoxy group, cyclohexyloxy group); aryl group having 5 to 40 ring atoms; amino group substituted with aryl group having 5 to 40 ring atoms; ester group having aryl group with 5 to 40 ring atoms; ester group having alkyl group with 1 to 60 carbon atoms; cyano group; nitro group; halogen atom; hydroxyl group; amino group; substituted or non-substituted carbazolyl group (1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group); substituted or non-substituted dibenzofuranyl group (1-dibenzofuranyl group, 2-dibenzofuranyl group, 3-dibenzofuranyl group, 4-dibenzofuranyl group); and substituted or non-substituted dibenzothiophenyl group (1-dibenzothiophenyl group, 2-dibenzothiophenyl group, 3-dibenzothiophenyl group, 4-dibenzothiophenyl group). The substituent groups for carbazolyl group, dibenzofuranyl group, and dibenzothiophenyl group are selected from the groups recited above.

[0042] At least one of R_7 , R_8 and R_{20} to R_{24} of the formula 2; at least one of R_7 , R_9 and R_{20} to R_{24} of the formula 3; at least one of R_7 and R_{21} to R_{23} of the formula 4; at least one of R_7 , R_8 , R_{20} and R_{22} to R_{29} of the formula 5; at least one of R_7 , R_8 and R_{20} to R_{24} of the formula 6; at least one of R_7 , R_9 and R_{20} to R_{24} of the formula 7; at least one of R_{22} and R_{23} of the formula 8; and at least one of R_7 , R_{21} and R_{23} of the formula 9 are preferably selected from substituted or non-substituted 9-carbazolyl group, substituted or non-substituted dibenzofuranyl group, substituted or non-substituted azacarbazolyl group having 2 to 5 nitrogen atoms and substituted or non-substituted dibenzothiophenyl group.


[0043] The compound represented by any of the formulae 1 to 9 has a triplet energy gap of 2.3 to 3.2 eV. Examples thereof are shown below, although not limited thereto.




No. 1




No. 2




No. 3




No. 4




No. 5




No. 6




No. 7




No. 8




No. 9




No. 10




No. 11




No. 12




No. 13



No. 14




No. 15




No. 16


5




No. 17



No. 18




No. 19




No. 20

10


15




No. 21



No. 22




No. 23




No. 24

20


25




No. 25



No. 26




No. 27




No. 28

30


35




No. 29



No. 30




No. 31




No. 32

40


45




No. 33



No. 34



























No. 35




No. 36


50

55







No. 61




No. 62




No. 63




No. 64




No. 65




No. 66




No. 67




No. 68




No. 69




No. 70




No. 71




No. 72




No. 73




No. 74




No. 75




No. 76




No. 77



No. 78
















No. 79




No. 80

5
10
15
20
25
30
35
40
45
50
55







No. 93




No. 94




No. 95




No. 96




No. 97




No. 98




No. 99




No. 100




No. 101




No. 102




No. 103




No. 104




No. 105




No. 106




No. 107



No.108




No.109



No.110

[0044] The compounds of the formula 1 may be easily synthesized by Suzuki-Miyaura reaction between an organic boronic acid and an aryl halide according to the following reaction scheme.














[0045] The material for organic EL devices of the present invention are preferably used as a host material for the light emitting layer and a hole transporting material.

[0046] The organic EL devices of the present invention will be described below. The organic EL devices have an organic thin film having one or more layers between the cathode and the anode. At least one layer of the organic thin film is a light emitting layer which comprises a host material for use in combination with at least one phosphorescent metal complex. At least one layer of the organic thin film contains the material for organic EL devices of the present invention.

[0047] The multi-layered organic EL devices have a multi-layered laminate structure such as anode/hole transporting layer (hole injecting layer)/light emitting layer/cathode, anode/light emitting layer/electron transporting layer (electron injecting layer)/cathode, anode/hole transporting layer (hole injecting layer)/light emitting layer/electron transporting layer (electron injecting layer)/cathode, and anode/hole transporting layer (hole injecting layer)/light emitting layer/hole barrier layer/electron transporting layer (electron injecting layer)/cathode.

[0048] The light emitting layer of the organic EL devices preferably contains the material for organic EL devices as the host material. Further, the light emitting layer comprises a host material, preferably the material for organic EL devices, and a phosphorescent light emitting material. Preferred examples of the phosphorescent light emitting material are compounds containing iridium (Ir), osmium (Os) or platinum (Pt) because of their high quantum yield of phosphorescence and their capability of enhancing the external quantum efficiency of light emitting devices, with metal complexes such as iridium complexes, osmium complexes and platinum complexes being more preferred, iridium complexes and platinum complexes being still more preferred, and ortho-metallated iridium complexes being most preferred. Preferred examples of the ortho-metallated iridium complexes are shown below.





[0049] In another preferred embodiment of the organic EL devices, the light emitting layer contains the host material and a phosphorescent light emitting material, for example, a blue-light emitting metal complex having a maximum emitting wavelength of 500 nm or less. Examples of the blue-light emitting metal complex include K-1, K-2, K-3, K-10, K-11, K-12, K-15, K-16, K-17, K-20, and K-21 described above.

[0050] Still another preferred organic EL device includes a hole transporting layer (hole injecting layer) which contains the material for organic EL devices of the invention as a hole transporting material.

[0051] In the organic EL devices of the invention, a reducing dopant is preferably added to the interfacial region between the cathode and the organic thin film layer. Examples of the reducing dopant include at least one compound selected from alkali metals, alkali metal complexes, alkali metal compounds, alkaline earth metals, alkaline earth metal complexes, alkaline earth metal compounds, rare earth metals, rare earth metal complexes, and rare earth metal compounds.

[0052] Examples of the alkali metals include Na (work function: 2.36 eV), K (work function: 2.28 eV), Rb (work function: 2.16 eV), and Cs (work function: 1.95 eV), with those having a work function of 2.9 eV or less being particularly preferred. Preferred is K, Rb or Cs, more preferred is Rb or Cs, and most preferred is Cs.

Examples of the alkaline earth metals include Ca (work function: 2.9 eV), Sr (work function: 2.0 to 2.5 eV), and Ba (work function: 2.52 eV), with those having a work function of 2.9 eV or less being particularly preferred.

Examples of the rare earth metals include Se, Y, Ce, Tb and Yb, with those having a work function of 2.9 eV or less being particularly preferred.

Particularly, the preferred metals mentioned above have a high reducing ability. Therefore, a relatively small amount of addition thereof to the electron injecting zone improves the luminance of emission and prolongs the lifetime.

[0053] Examples of the alkali metal compounds include alkali oxides such as Li_2O , Cs_2O and K_2O and alkali halides such as LiF, NaF, CsF and KF, with LiF, Li_2O and NaF being preferred.

Examples of the alkaline earth metal compounds include BaO, SrO, CaO and mixtures thereof such as $\text{Ba}_x\text{Sr}_{1-x}\text{O}$ ($0 < x < 1$) and $\text{Ba}_x\text{Ca}_{1-x}\text{O}$ ($0 < x < 1$), with BaO, SrO and CaO being preferred.

Examples of the rare earth metal compounds include YbF_3 , ScF_3 , ScO_3 , Y_2O_3 , Ce_2O_3 , GdF_3 and TbF_3 , with YbF_3 , ScF_3 and TbF_3 being preferred.

[0054] The alkali, metal complexes, alkaline earth metal complexes and rare earth metal complexes are not particularly limited as long as containing at least one metal ions selected from alkali metal ions, alkaline earth metal ions and rare earth metal ions. Examples of the ligand preferably include, but not limited to, quinolinol, benzoquinolinol, acridinol, phenanthridinol, hydroxyphenyloxazole, hydroxyphenylthiazole, hydroxydiaryloxadiazole, hydroxydiarylthiadiazole, hydroxyphenylpyridine, hydroxyphenylbenzimidazole, hydroxybenzotriazole, hydroxyfulborane, bipyridine, phenanthroline, phthalocyanine, porphyrin, cyclopentadiene, β -diketones, azomethines, and derivatives thereof.

[0055] The reducing dopant is added to the interfacial region preferably in the form of layers or islands by a resistance-heating vapor deposition in which the reducing dopant is vapor-deposited while vapor-depositing an organic material (a light emitting material or an electron injecting material for forming the interfacial region) at the same time, thereby dispersing the reducing dopant in the organic material. The dispersion concentration is 100:1 to 1:100, preferably 5:1 to 1:5 when expressed by a molar ratio of the organic material to the reducing dopant.


When adding the reducing dopant in the form of layer, the reducing dopant is solely vapor-deposited by the resistance-heating vapor deposition into a layer preferably having a thickness of 0.1 to 15 nm after forming an interfacial organic layer from a light emitting material or an electron injecting material.

When adding the reducing dopant in the form of islands, the reducing dopant is solely vapor-deposited by the resistance-heating vapor deposition into a form of islands preferably having a thickness of 0.05 to 1 nm after forming an interfacial organic layer from a light emitting material or an electron injecting material.

The molar ratio of the main components of the organic EL devices of the invention (light emitting material and electron injecting material) and the reducing dopant is preferably 5:1 to 1:5 and more preferably 2:1 to 1:2.

[0056] In still another preferred embodiment of the invention, the organic EL device has an electron injecting layer between the light emitting layer and the cathode, and the electron injecting layer mainly comprises a nitrogen-containing cyclic derivative which is different from the organic EL material of the present invention. The electron transporting material for the electron injecting layer is preferably an aromatic heterocyclic compound having one or more heteroatoms in its molecule, particularly an aromatic nitrogen-containing cyclic compound.

[0057] For example, the aromatic nitrogen-containing cyclic compound is preferably a nitrogen-containing, cyclic metal chelate complex represented by the following formula A:




[0058] In the formula A, R^2 to R^7 are each independently hydrogen atom, halogen atom, oxy group, or amino group or hydrocarbon group having 1 to 40 carbon atoms, each being optionally substituted.


Examples of the halogen atom are the same as mentioned above. Examples of the amino group which is optionally substituted include the same groups which are recited as the alkylamino group, arylamino group, and aralkylamino group mentioned above.

Example of the hydrocarbon group having 1 to 40 carbon atoms include alkyl group, alkenyl group, cycloalkyl group, alkoxy group, aryl group, heterocyclic group, aralkyl group, aryloxy group, and alkoxycarbonyl group, each being optionally substituted. Examples of the alkyl group, alkenyl group, cycloalkyl group, alkoxy group, aryl group, heterocyclic group, aralkyl group, and aryloxy group are the same as those mentioned above. The alkoxycarbonyl group is represented by $-COOY$ wherein Y is the same alkyl group as mentioned above.

[0059] M in the formula A is aluminum (Al), gallium (Ga) or indium (In), with In being preferred.

L in the formula A is a group represented by the following formula A' or A'':












wherein R^8 to R^{12} are each independently hydrogen atom or hydrocarbon group having 1 to 40 carbon atoms which is optionally substituted, the groups adjacent to each other optionally forming a ring structure. R^{13} to R^{27} are each independently hydrogen atom or hydrocarbon group having 1 to 40 carbon atoms which optionally substituted, the groups adjacent to each other optionally forming a ring structure.

[0060] Examples of the hydrocarbon group having 1 to 40 carbon atoms of the formulae A' and A'' are the same groups as those recited for R^2 to R^7 . Examples of the bivalent group which is formed by the adjacent groups of R^8 to R^{12} or R^{13} to R^{27} for forming a ring structure include tetramethyle group, pentamethyle group, hexamethyle group, diphenylmethane-2,2'-diyl group, diphenylethane-3,3'-diyl group, and diphenylpropane-4,4'-diyl group.


[0061] Specific examples of the nitrogen-containing, cyclic metal chelate complex are shown below, although not limited thereto.




5




10




15




20




25




30




35




40





45





















50



55








[0062] Another preferred example of the aromatic, nitrogen-containing cyclic compound includes a nitrogen-containing,


five-membered cyclic compound. The nitrogen-containing, five-membered ring may include imidazole ring, triazole ring, tetrazole ring, oxadiazole ring, thiadiazole ring, oxatriazole ring, and thiatriazole ring. The nitrogen-containing, five-membered cyclic compound has a skeletal structure such as benzimidazole ring, benzotriazole ring, pyridinoimidazole ring, pyrimidinoimidazole ring, and pyridazinoimidazole ring, and is preferably represented by the following formula B:




[0063] In the formula B, L^{B} is a mono- to tetravalent bonding group such as carbon atom, silicon atom, nitrogen atom, boron atom, oxygen atom, sulfur atom, metal (barium, beryllium, etc.), aromatic hydrocarbon ring, and heteroaromatic ring, with carbon atom, nitrogen atom, silicon atom, boron atom, oxygen atom, sulfur atom, aryl group and heteroaromatic group being preferred, and carbon atom, silicon atom, aryl group and heteroaromatic group being more preferred.

The aryl group or heteroaromatic group for L^{B} may be substituted. The substituent group is preferably alkyl group, alkenyl group, alkynyl group, aryl group, amino group, alkoxy group, aryloxy group, acyl group, alkoxycarbonyl group, aryloxy-carbonyl group, acyloxy group, acylamino group, alkoxycarbonylamino group, aryloxy carbonylamino group, sulfonylami-no group, sulfamoyl group, carbamoyl group, alkylthio group, arylthio group, sulfonyl group, halogen atom, cyano group, or heteroaromatic group; more preferably alkyl group, aryl group, alkoxy group, acyloxy group, halogen atom, cyano group, or heteroaromatic group; still more preferably alkyl group, aryl group, alkoxy group, aryloxy group, or heteroaromatic group; and particularly preferably alkyl group, aryl group, alkoxy group, or heteroaromatic group.

[0064] Preferred examples of L^{B} are shown below.





[0065] X^{B2} in the formula B is -O-, -S- or =N- R^{B2} , preferably -O- or =N- R^{B2} , and more preferably =N- R^{B2} . R^{B2} is hydrogen atom, aliphatic hydrocarbon group, aryl group or heterocyclic group.

The aliphatic hydrocarbon group for R^{B2} may be linear, branched or cyclic and includes alkyl groups having preferably 1 to 20 carbon atoms, more preferably 1 to 12 carbon atoms and particularly preferably 1 to 8 carbon atoms such as methyl, ethyl, isopropyl, t-butyl, n-octyl, n-dodecyl, n-hexadecyl, cyclopropyl, cyclopentyl, and cyclohexyl; alkenyl groups having preferably 2 to 20 carbon atoms, more preferably 2 to 12 carbon atoms and particularly preferably 2 to 8 carbon atoms such as vinyl, allyl, 2-butenyl, and 3-pentenyl; and alkynyl groups having preferably 2 to 20 carbon atoms, more preferably 2 to 12 carbon atoms and particularly preferably 2 to 8 carbon atoms such as propargyl and 3-pentynyl, with alkyl groups being preferred.

[0066] The aryl group for R^{B2} is a non-condensed or condensed aryl group and has preferably 6 to 30 carbon atoms, more preferably 6 to 20 carbon atoms and still more preferably 6 to 12 carbon atoms. Examples thereof include phenyl, 2-methylphenyl, 3-methylphenyl, 4-methylphenyl, 2-methoxyphenyl, 3-trifluoromethylphenyl, pentafluorophenyl, 1-naphthyl, and 2-naphthyl,

[0067] The heterocyclic group for R^{B2} is a non-condensed or condensed heterocyclic group, preferably a heteroaromatic group having at least one atom selected from nitrogen atom, oxygen atom, sulfur atom and selenium atom, and has preferably 1 to 20 carbon atoms, more preferably 1 to 12 carbon atoms and still more preferably 2 to 10 carbon atoms. Examples of the basic structure of the heterocyclic group include pyrrolidone, piperidine, piperazine, morpholine, thiophene, selenophene, furan, pyrrole, imidazole, pyrazole, pyridine, pyrazine, pyridazine, pyrimidine, triazole, triazine, indole, indazole, purine, thiazoline, thiazole, thiadiazole, oxazoline, oxazole, oxadiazole, quinoline, isoquinoline, phthalazine, naphthyridine, quinoxaline, quinazoline, cinnoline, pteridine, acridine, phenanthroline, phenazine, tetrazole, benzimidazole, benzoxazole, benzothiazole, benzotriazole, tetraazaindene, carbazole, and azepine, with furan, thiophene, pyridine, pyrazine, pyrimidine, pyridazine, triazine, quinoline, phthalazine, naphthyridine, quinoxaline, and quinazoline being preferred, furan, thiophene, pyridine, and quinoline being more preferred, and quinoline being still more preferred.

[0068] The aliphatic hydrocarbon group, aryl group and heterocyclic group for R^{B2} may be substituted. The substituent groups and preferred substituent groups are the same as the substituent groups for L^B mentioned above.

R^{B2} is preferably aliphatic hydrocarbon group, aryl group or heterocyclic group, more preferably aliphatic hydrocarbon group or aryl group (having preferably 6 to 30 carbon atoms, more preferably 6 to 20 carbon atoms, and still more preferably 6 to 12 carbon atoms), and still more preferably aliphatic hydrocarbon group (having preferably 1 to 20 carbon atoms, more preferably 1 to 12 carbon atoms, and still more preferably 2 to 10 carbon atoms).


[0069] Z^{B2} is a group of atoms to form an aromatic ring. The aromatic ring formed by Z^{B2} is either of an aromatic hydrocarbon ring or a heteroaromatic ring. Examples thereof include benzene ring, pyridine ring, pyrazine ring, pyrimidine ring, pyridazine ring, triazine ring, pyrrole ring, furan ring, thiophene ring, selenophene ring, tellurophene ring, imidazole ring, thiazole ring, selenazole ring, tellurazole ring, thiadiazole ring, oxadiazole ring, and pyrazole ring, with benzene ring, pyridine ring, pyrazine ring, pyrimidine ring, and pyridazine ring being preferred, benzene ring, pyridine ring, and pyrazine ring being more preferred, benzene ring and pyridine ring being still more preferred, and pyridine ring being particularly preferred.

[0070] The aromatic ring formed by Z^{B2} may be fused with another ring to form a condensed ring and may be substituted. Examples of the substituent group are the same as the substituent groups for L^B and preferably alkyl group, alkenyl

group, alkynyl group, aryl group, amino group, alkoxy group, aryloxy group, acyl group, alkoxycarbonyl group, aryloxy-carbonyl group, acyloxy group, acylamino group, alkoxycarbonylamino group, aryloxy carbonylamino group, sulfonylami-no group, sulfamoyl group, carbamoyl group, alkylthio group, arylthio group, sulfonyl group, halogen atom, cyano group, and heterocyclic group more preferably alkyl group, aryl group, alkoxy group, aryloxy group, halogen atom, cyano group, and heterocyclic group; still more preferably alkyl group, aryl group, alkoxy group, acyloxy group, and heteroaromatic group; and particularly preferably alkyl group, aryl group, alkoxy group, and heteroaromatic group.

n^{B2} is an integer of 1 to 6, preferably an integer of 1 to 4, and still more preferably 2 or 3.

[0071] The nitrogen-containing five-membered cyclic compound of the formula B is preferably represented by the following formula B':



[0072] In the formula B', R^{B71} , R^{B72} , R^{B73} and their preferred examples are each independently the same as defined in R^{B2} of the formula B.


Z^{B71} , Z^{B72} , Z^{B73} and their preferred examples are each independently the same as defined in Z^{B2} of the formula B.

L^{B71} , L^{B72} and L^{B73} are each independently single bond or bivalent group as defined in L^B of the formula B, preferably single bond, bivalent aromatic hydrocarbon group, bivalent heteroaromatic group or bivalent bonding group composed of a combination thereof, with single bond being preferred. T^{B71} , L^{B72} and L^{B73} may be substituted. The substituent groups and preferred substituent groups are the same as the substituent groups for L^B of the formula B.


Y is nitrogen atom, 1,3,5-benzenetriyl group or 2,4,6-triazinetriyl group. The 1,3,5-benzenetriyl group may be substituted at 2,4,6-position, for example, by alkyl group, aromatic hydrocarbon group or halogen atom.

[0073] Specific examples of the nitrogen-containing five-membered cyclic compound of the formula B or B' are shown below, although not limited thereto.


(B-1)




(B-5)




(B-2)




(B-6)




(B-3)




(B-7)




(B-4)




(B-8)









(B-9)



(B-13)








[0074] In addition to the aromatic, nitrogen-containing cyclic compound mentioned above, the compounds for forming the electron injecting layer and electron transporting layer may further include an electron-deficient, nitrogen-containing cyclic compound which has a structure combining an electron-deficient, nitrogen-containing 5- or 6-membered cyclic skeleton with a substituted or non-substituted indole skeleton, substituted or non-substituted carbazole skeleton, or substituted or non-substituted azacarbazole skeleton. Preferred electron-deficient, nitrogen-containing 5- or 6-membered cyclic skeleton includes each skeleton of pyridine, pyrimidine, pyrazine, triazine, triazole, oxadiazole, pyrazole, imidazole, quinoxaline, pyrrole, and a condensed skeleton thereof such as benzimidazole and imidazopyridine. The combination between the pyridine, pyrimidine, pyrazine or triazine skeleton with the carbazole, indole, azacarbazole or quinoxaline skeleton is preferred. Each skeleton may be either substituted or not substituted.




[0075] Examples of the electron-deficient, nitrogen-containing cyclic compound are shown below.

5



10




15



20

25




30



35







40

45



50

55



[0076] The electron injecting layer and electron transporting layer may be a single-layered structure or multi-layered structure of layers having the same composition or different compositions, each layer being made of one or more kinds of the materials mentioned above, preferably a compound having a nitrogen-containing heterocyclic group with a low π -electron density.

[0077] In addition to the nitrogen-containing cyclic compound and the electron-deficient, nitrogen-containing cyclic compound, the electron injecting layer is preferably incorporated with an inorganic compound such as insulating material and semiconductor. The insulating material or semiconductor incorporated into the electron injecting layer effectively prevents the leak of electric current to enhance the electron injecting properties.

[0078] The insulating material is preferably at least one metal compound selected from the group consisting of alkali metal chalcogenides, alkaline earth metal chalcogenides, alkali metal halides and alkaline earth metal halides. The metal compound incorporated into the electron injecting layer further enhances the electron injecting properties. Preferred examples of the alkali metal chalcogenides include Li_2O , K_2O , Na_2S , Na_2Se and Na_2O , and preferred examples of the alkaline earth metal chalcogenides include CaO , BaO , SrO , BeO , BaS and CaSe . Preferred examples of the alkali metal halides include LiF , NaF , KF , LiCl , KCl and NaCl . Examples of the alkaline earth metal halides include fluorides such as CaF_2 , BaF_2 , SrF_2 , MgF_2 and BeF_2 and halides other than fluorides.

[0079] Example of the semiconductor may include oxide, nitride or oxynitride each containing at least one element selected from the group consisting of Ba, Ca, Sr, Yb, Al, Ga, In, Li, Na, Cd, Mg, Si, Ta, Sb and Zn. The semiconductor may be used singly or in combination of two or more. The inorganic compound included in the electron injecting layer preferably forms a microcrystalline or amorphous insulating thin film. When the electron injecting layer is formed from such an insulating thin film, the thin is made more uniform to decrease the pixel defects such as dark spots. Examples of such inorganic compound include alkali metal chalcogenides, alkaline earth metal chalcogenides, alkali metalhalides and alkaline earth metalhalide, each being described above.

The electron injecting layer may be included with the reducing dopant described above.


[0080] Since the anode of the organic EL devices has a function of injecting holes into the hole transporting layer or light emitting layer, the anode preferably has a work function of 4.5 eV or more. Examples of the material for the anode include indium tin oxide (ITO), tin oxide (NESA), gold, silver, platinum and copper. Since the cathode has a function of injecting electrons into the electron injecting layer or light emitting layer, the material for the cathode preferably has a small work function. Examples of the material for the cathode include, but not limited to, indium, aluminum, magnesium, magnesium-indium alloy, magnesium-aluminum alloy, aluminum-lithium alloy, aluminum-scandium-lithium alloy, and magnesium-silver alloy.

[0081] The method of forming each layer of the organic EL devices is not critical, and a known method such as a vacuum vapor deposition method and a spin coating method may be employed. The organic thin film layer containing the material for organic EL devices of the invention can be formed by a known method such as a vacuum vapor deposition method, molecular beam epitaxy method (MBE method) and a solution coating method, for example, a dipping method,

spin coating method, a casting method, a bar coating method and a roll coating method.

The thickness of each organic layer of the organic EL devices is not particularly limited. Generally, an excessively thin layer likely causes defects such as pin holes, and an excessively thick layer requires a high applied voltage to decrease the efficiency. The thickness is preferably from several nanometers to 1 μm .

[0082] The hole injecting/transport layer is formed from an aromatic amine compound, preferably the aromatic amine derivative represented by the following formula I:



[0083] In the formula I, Ar^1 to Ar^4 are each independently aryl group (inclusive of heteroaryl group) having 5 to 50 ring atoms.

[0084] Examples of the aryl group having 5 to 50 ring atoms include phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, fluoranthenyl group, fluorenyl group, 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isindolyl group, 2-isindolyl group, 3-isindolyl group, 4-isindolyl group, 5-isindolyl group, 6-isindolyl group, 7-isindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, and 4-t-butyl-3-indolyl group, with phenyl group, naphthyl group, biphenyl group, anthranlyl group, phenanthryl group, pyrenyl

group, chrysenyl group, fluoranthenyl group, and fluorenyl group being preferred.

[0085] L is a bonding group such as arylene group (inclusive of heteroarylene group) having 5 to 50 ring atoms which is optionally substituted or a bivalent group composed of two or more arylene groups which are bonded to each other via a single bond, ether linkage, thioether linkage, alkylene group having 1 to 20 carbon atoms, alkenylene group having 2 to 20 carbon atoms or amino linkage. Examples of the arylene group having 5 to 50 ring atoms include 1,4-phenylene group, 1,2-phenylene group, 1,3-phenylene group, 1,4-naphthylene group, 2,6-naphthylene group, 1,5-naphthylene group, 9,10-anthranylene group, 9,10-phenanthrenylene group, 3,6-phenanthrenylene group, 1,6-pyrenylene group, 2,7-pyrenylene group, 6,12-chrysenylene group, 4,4'-biphenylene group, 3,3'-biphenylene group, 2,2'-biphenylene group, 2,7-fluorenylene group, 2,5-thiophenylene group, 2,5-silolylene group, and 2,5-oxadiazolylene group, with 1,4-phenylene group, 1,2-phenylene group, 1,3-phenylene group, 1,4-naphthylene group, 9,10-anthranylene group, 6,12-chrysenylene group, 4,4'-biphenylene group, 3,3'-biphenylene group, 2,2'-biphenylene group, and 2,7-fluorenylene group being preferred.

[0086] When L is a bonding group composed of two or more arylene groups, the adjacent couple of arylene groups may be bonded via a bivalent group to form a new ring. The bivalent group for forming such ring may include tetramethylene group, pentamethylene group, hexamethylene group, diphenylmethane-2,2'-diyl group, diphenylethane-3,3'-diyl group, and diphenylpropane-4,4'-diyl group.

[0087] Examples of the substituent group for Ar¹ to Ar⁴ and L include aryl group (inclusive of heteroaryl group) having 5 to 50 ring atoms which is optionally substituted, alkyl group having 1 to 50 carbon atoms which is optionally substituted, alkoxy group having 1 to 50 carbon atoms which is optionally substituted, aralkyl group having 7 to 50 carbon atoms which is optionally substituted, aryloxy group (inclusive of heteroaryloxy group) having 5 to 50 ring atoms which is optionally substituted, arylthio group (inclusive of heteroarylthio group) having 5 to 50 ring atoms which is optionally substituted, alkoxycarbonyl group having 2 to 50 carbon atoms which is optionally substituted, amino group substituted with aryl group (inclusive of heteroaryl group) having 5 to 50 ring atoms which is optionally substituted, halogen group, cyano group, nitro group, and hydroxyl group.

[0088] Examples of the aryl group having 5 to 50 ring atoms which is optionally substituted include phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-talyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, fluoranthenyl group, fluorenyl group, 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 2-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 9-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-

phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 10-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 10-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-anethylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, and 4-t-butyl-3-indolyl group.

[0089] Examples of the alkyl group having 1 to 50 carbon atoms which is optionally substituted include methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, 1,2,3-trinitropropyl group, cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group, 4-methylcyclohexyl group, 1-adamantyl group, 2-adamantyl group, 1-norbornyl group, and 2-norbornyl group.

[0090] The alkoxy group having 1 to 50 carbon atoms which is optionally substituted is represented by -OY, wherein Y is methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromomethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-ammoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitromethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, or 1,2,3-trinitropropyl group.

[0091] Examples of the aralkyl group having 7 to 50 carbon atoms which is optionally substituted include benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, α -naphthylmethyl group, 1- α -naphthylethyl group, 2- α -naphthylethyl group, 1- α -naphthylisopropyl group, 2- α -naphthylisopropyl group, β -naphthylmethyl group, 1- β -naphthylethyl group, 2- β -naphthylethyl group, 1- β -naphthylisopropyl group, 2- β -naphthylisopropyl group, 1-pyrrolylmethyl group, 2-(1-pyrrolyl)ethyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, and 1-chloro-2-phenylisopropyl group.

[0092] The acyloxy group having 5 to 50 ring atoms which is optionally substituted is represented by -OY', wherein Y' is phenol group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isindolyl group, 3-isindolyl group, 4-isindolyl group, 5-isindolyl group, 6-isindolyl group, and 7-isindolyl group.

group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-8-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, or 4-t-butyl-3-indolyl group,

[0093] The arylthio group having 5 to 50 ring atoms which is optionally substituted is represented by -SY", wherein Y" is phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-8-yl group,


2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, or 4-t-butyl-3-indolyl group.


[0094] The alkoxycarbonyl group having 2 to 50 carbon atoms which is optionally substituted is represented by -COOZ, wherein Z is methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxymethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-dihydroxyethyl group, 1,3-dihydroxyisopropyl group, 2,3-dihydroxy-t-butyl group, 1,2,3-trihydroxypropyl group, chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-dichloroethyl group, 1,3-dichloroisopropyl group, 2,3-dichloro-t-butyl group, 1,2,3-trichloropropyl group, bromomethyl group, 1-bromomethyl group, 2-bromoethyl group, 2-bromoisobutyl group, 1,2-dibromoethyl group, 1,3-dibromoisopropyl group, 2,3-dibromo-t-butyl group, 1,2,3-tribromopropyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodoisobutyl group, 1,2-diiodoethyl group, 1,3-diiodoisopropyl group, 2,3-diiodo-t-butyl group, 1,2,3-triiodopropyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-aminoisobutyl group, 1,2-diaminoethyl group, 1,3-diaminoisopropyl group, 2,3-diamino-t-butyl group, 1,2,3-triaminopropyl group, cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyanoisobutyl group, 1,2-dicyanoethyl group, 1,3-dicyanoisopropyl group, 2,3-dicyano-t-butyl group, 1,2,3-tricyanopropyl group, nitromethyl group, 1-nitroethyl group, 2-nitroethyl group, 2-nitroisobutyl group, 1,2-dinitroethyl group, 1,3-dinitroisopropyl group, 2,3-dinitro-t-butyl group, or 1,2,3-trinitropropyl group.

[0095] The amino group substituted with aryl group having 5 to 50 ring atoms which is optionally substituted is represented by -NPQ, wherein P and Q are each phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphthacenyl group, 2-naphthacenyl group, 9-naphthacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl group, 3-biphenyl group, 4-biphenyl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl)phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4-methylbiphenyl group, 4"-t-butyl-p-terphenyl-4-yl group, 2-pyrrolyl group, 3-pyrrolyl group, pyrazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 4-furyl groups, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxalyl group, 5-quinoxalyl group, 6-quinoxalyl group, 1-carbazolyl group, 2-carbazolyl group, 3-carbazolyl group, 4-carbazolyl group, 1-phenanthridinyl group, 2-phenanthridinyl group, 3-phenanthridinyl group, 4-phenanthridinyl group, 6-phenanthridinyl group, 7-phenanthridinyl group, 8-phenanthridinyl group, 9-phenanthridinyl group, 10-phenanthridinyl group, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-


5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-phenanthroline-5-yl group, 2,7-phenanthroline-6-yl group, 2,7-phenanthroline-8-yl group, 2,7-phenanthroline-9-yl group, 2,7-phenanthroline-10-yl group, 1-phenazinyl group, 2-phenazinyl group, 1-phenothiazinyl group, 2-phenothiazinyl group, 3-phenothiazinyl group, 4-phenothiazinyl group, 1-phenoxazinyl group, 2-phenoxazinyl group, 3-phenoxazinyl group, 4-phenoxazinyl group, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methylpyrrole-1-yl group, 2-methylpyrrole-3-yl group, 2-methylpyrrole-4-yl group, 2-methylpyrrole-5-yl group, 3-methylpyrrole-1-yl group, 3-methylpyrrole-2-yl group, 3-methylpyrrole-4-yl group, 3-methylpyrrole-5-yl group, 2-t-butylpyrrole-4-yl group, 3-(2-phenylpropyl)pyrrole-1-yl group, 2-methyl-1-indolyl group, 4-methyl-1-indolyl group, 2-methyl-3-indolyl group, 4-methyl-3-indolyl group, 2-t-butyl-1-indolyl group, 4-t-butyl-1-indolyl group, 2-t-butyl-3-indolyl group, or 4-t-butyl-3-indolyl group.

[0096] Examples of the compound of the formula I are shown below, although not limited thereto.






[0097] In addition, the aromatic amine of the following formula II is suitable as the material for the hole injecting/transport layer.



[0098] In the formula II, the definition of each of Ar₁ to Ar₃ is the same as those of the Ar¹ to Ar⁴ in the formula I. Examples of the compound of the formula II are shown below, although not limited thereto.




EXAMPLES

[0099] The present invention will be described in more detail with reference to the examples. However it should be noted that the scope of the present invention is not limited to the following examples.

SYNTHESIS EXAMPLE 1

[0100]

Synthesis of Compound No. 6



A three-necked flask was charged with 3.4 g (1.2 eq., 12 mmol) of compound 1, 3.2 g (1 eq., 10 mmol) of compound 2, 10 ml of 2M Na₂CO₃ aqueous solution (20 mmol), 50 ml of DME, and 0.58 g of 5 mol % Pd[PPh₃]₄ (0.5 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 50 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was dried over MgSO₄, filtrated and condensed. The condensate was dissolved in 300 ml toluene and purified by a column chromatography. The purified product was condensed, evaporated to dryness and washed with ethyl acetate (30 ml) three times, to obtain a white powder (No.6) which was then purified by sublimation to obtain 3.5 g of white solid.


FD Mass Spectroscopy Analysis

C₃₆H₂₃NO: calculated 485, found 485

SYNTHESIS EXAMPLE 2

[0101]

Synthesis of Compound No. 1



A three-necked flask was charged with 7.1 g (1 eq., 15 mmol) of compound 3, 3.8 g (1.2 eq., 18 mmol) of compound 4, 15 ml of 2M Na₂CO₃ aqueous solution (30 mmol), 50 ml of THF, and 0.87 g of 5 mol % Pd[PPh₃]₄ (0.75 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into 100 ml of methanol.

The precipitated solid was filtrate with suction and purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized twice, to obtain a white powder (No. 1) which was then purified by sublimation to obtain 2.6 g of white solid.


FD Mass Spectroscopy Analysis

C₄₂H₂₇NO: calculated 561, found 561

SYNTHESIS EXAMPLE 3

[0102]

Synthesis of Compound No. 12



A three-necked flask was charged with 3.4 g (1.2 eq., 16 mmol) of compound 4, 6.5 g (1 eq., 13 mmol) of compound 5, 13 ml of 2M Na₂CO₃ aqueous solution (26 mmol), 40 ml of DME, and 0.75 g of 5 mol % Pd[PPh₃]₄ (0.65 mol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 50 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized twice, to obtain a white powder (No. 12) which was then purified by sublimation to obtain 3.2 g of white solid.


FD Mass Spectroscopy Analysis

C₄₂H₂₅NO₂: calculated 575, found 575

SYNTHESIS EXAMPLE 4

[0103]

Synthesis of Compound No. 18



A three-necked flask was charged with 3.0 g (1.2 eq., 10 mmol) of compound 6, 4.3 g (1 eq., 8.7 mmol) of compound 7, 9 ml of 2M Na₂CO₃ aqueous solution (18 mmol), 40 ml of DME, and 0.51 g of 5 mol % Pd[PPh₃]₄ (0.44 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 50 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized twice, to obtain a white powder (No. 18) which was then purified by sublimation to obtain 3.2 g of white solid.


FD Mass Spectroscopy Analysis

C₄₈H₂₉NO₂: calculated 651, found 651

SYNTHESIS EXAMPLE 5

[0104]

Synthesis of Compound No. 72



A three-necked flask was charged with 4.0 g (1.2 eq., 17 mmol) of compound 8, 5.1 g (1 eq., 15 mmol) of compound 9, 15 ml of 2M Na₂CO₃ aqueous solution (30 mmol), 70 ml of DME, and 0.87 g of 5 mol % Pd[PPh₃]₄ (0.75 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 50 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized twice, to obtain a white powder (No. 72) which was then purified by sublimation to obtain 2.8 g of white solid.


FD Mass Spectroscopy Analysis

C₃₉H₂₆S₂: calculated 558, found 558

SYNTHESIS EXAMPLE 6

[0105]

Synthesis of Compound No. 66



A three-necked flask was charged with 6.1 g (1.2 eq., 21 mmol) of compound 10, 8.6 g (1 eq., 18 mmol) of compound 11, 18 ml of 2M Na₂CO₃ aqueous solution (36 mmol), 80 ml of DME, and 1.04 g of 5 mol % Pd[PPh₃]₄ (0.9 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 70 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized three times, to obtain a white powder (No. 66) which was then purified by sublimation to obtain 4.0 g of white solid.


FD Mass Spectroscopy Analysis

C₄₆H₂₈N₄O: calculated 652, found 652

SYNTHESIS EXAMPLE 7

[0106]

Synthesis of Compound No. 5



A three-necked flask was charged with 3.5 g (1.2 eq., 7.7 mmol) of compound 12, 3.1 g (1 eq., 6.4 mmol) of compound 5, 7 ml of 2M Na₂CO₃ aqueous solution (14 mmol), 50 ml of DME, 0.34 g of 5 mol % Pd[PPh₃]₄ (0.32 mmol). The contents were refluxed for 8 hrs in an argon atmosphere.

After the reaction, the reaction product mixture was cooled to room temperature and poured into a separatory funnel. After adding 50 ml of water, the reaction product mixture was extracted with CH₂Cl₂. The extract was purified by a column chromatography. The purified product was condensed, evaporated to dryness and recrystallized three times, to obtain a white powder (No. 5) which was then purified by sublimation to obtain 2.2 g of white solid.

FD Mass Spectroscopy Analysis

C₆₀H₃₆N₂O₂: calculated 816, found 816

The measuring conditions of FD-MS (field desorption mass spectrometry) used in Synthesis Examples 1 to 7 are shown below.

Apparatus: HX110 manufactured by JEOL, Ltd.

Acceleration Voltage: 8 kV

Scan range: m/z = 50 to 1500


Emitter material carbon

Emitter current: 0 mA → 2 mA/min → 40 mA (maintained for 10 min)


EXAMPLE 1

Preparation of Organic EL Device


[0107] A glass substrate of 25 mm x 75 mm x 1.1 mm thickness having ITO transparent electrode (manufactured by Asahi Glass Company Ltd.) was ultrasonically cleaned in isopropyl alcohol for 5 min and then UV ozone-cleaned for 30 min. The cleaned glass substrate having the transparent electrode lines was mounted to a substrate holder of a vacuum vapor deposition apparatus. On the surface having the transparent electrode lines, a film of HTM1 (see the formula below) having a thickness of 80 nm was first deposited by resistance heating so as to cover the transparent electrode. The HTM1 film functioned as the hole transporting/hole injecting layer. Then, Compound No. 5 as the host material and Complex K-21 as the dopant material were vapor co-deposited by resistance heating to successively form a film having a thickness of 30 nm on the HTM1 film. The concentration of Complex K-21 was 7.5 % by weight. The co-deposited film functions as the light emitting layer. Then, an ETM1 film having a thickness of 10 nm on the light emitting layer and an ETM2 film having a thickness of 20 nm on the ETM1 film were successively deposited in layers. The ETM1 film and ETM2 film functioned as the first and second electron transporting layer, respectively. Then, a LiF electron injecting electrode (cathode) having a thickness of 0.5 nm was deposited at a film-depositing speed of 0.1 Å/min. Finally, a metallic Al was deposited on the LiF film to form a metal cathode having a thickness of 150 nm, thereby obtaining an organic EL device.



HTM1



ETM1



ETM2

Evaluation of light emitting property of organic EL device

[0108] The organic EL device thus prepared was driven under a direct current to emit light and measured for the wave length (λ), the luminance (L) and the current density to determine the current efficiency (L/J). The results at a current density of 1 mA/cm² are shown in Table 1.

EXAMPLES 2-15


[0109] Each organic EL device was prepared in the same manner as in Example 1 except for using a host material listed in Table 1 in place of the host Compound No. 5 used in Example 1. The results are shown in Table 1.

COMPABATIVE EXAMPLE 1


[0110] An organic EL device was prepared in the same manner as in Example 1 except for using CBP as the host material in place of the host Compound No. 5 used in Example 1. The results are shown in Table 1.

COMPARATIVE EXAMPLE 2

[0111] An organic EL device was prepared in the same manner as in Example 1 except for using the following compound X-1 described in WO 2005/113531 in place of the host Compound No. 5 used in Example 1. The results are shown in Table 1.



CBP



X-1

Table 1


Host Compound	Voltage (V)	Luminance (cd/m ²)	L/J (cd/A)	EQE (%)	Wavelength (nm)
Examples					
1 No. 5	5.7	178	17.8	8.1	479
2 No. 1	5.5	147	14.7	6.3	481
3 No. 6	5.9	168	16.8	7.4	479
4 No. 12	5.9	140	14.0	5.9	481
5 No. 18	5.8	130	13.8	5.7	479
6 No. 35	5.6	138	13.2	5.6	481
7 No. 72	5.5	148	13.5	5.6	481
8 No. 8	5.9	145	14.5	6.3	479
9 No. 26	5.9	152	15.2	6.4	479
10 No. 38	5.8	146	14.6	6.1	479

(continued)

Host Compound	Voltage (V)	Luminance (cd/m ²)	L/J (cd/A)	EQE (%)	Wavelength (nm)
Examples					
11 No. 55	5.6	157	15.7	6.4	481
12 No. 69	5.9	148	14.8	6.2	480
13 No. 84	5.5	154	15.4	6.3	481
14 No. 96	5.9	138	13.8	5.8	481
15 No. 99	5.6	155	15.5	6.4	479
Comparative Examples					
1 CBP	6.0	125	8.2	3.7	480
2 X-1	no emission of light				

EXAMPLES 16-19

[0112] Each organic EL device was prepared in the same manner as in Example 1 except for using the compound of the present invention listed in Table 2 as the hole transporting/hole injecting layer in place of HTM1 and using the following compound H-1 as the host material. The results are shown in Table 2.



COMPARATIVE EXAMPLE 3

[0113] An organic EL device was prepared in the same manner as in Example 16 except for using NPD as the hole transporting material in place of Compound No. 5. The results are shown in Table 2.




Table 2

Hole Transporting Compound	Voltage (V)	Luminance (cd/m ²)	L/J (cd/A)	EQE (%)	Wavelength (nm)
Examples					
16 No.5	6.2	138	13.8	6.3	480
17 No.61	6.4	146	14.6	6.7	481
18 No.107	5.8	157	15.7	7.1	481
19 No.110	6.0	148	14.8	6.8	479

(continued)


Comparative Example						
3	NPD	6.5	101	10.1	4.6	480

[0114] As compared with the compounds used in examples, the compounds used in comparative examples were poor in the current efficiency and needed a high driving voltage.

[0115] As described above, by using the material for organic EL devices of the invention which is represented by the formulae 1 to 9, organic EL devices having a high emitting efficiency, causing little pixel defects, being excellent in the heat resistance, and having a long lifetime are obtained. Therefore, such organic EL devices are very useful as the display and light source for various electronic instruments.

Claims

1. A material for organic electroluminescence devices for use in combination with at least one phosphorescent metal complex, which comprises a compound represented by the following formula 1:



wherein R_1 to R_3 are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that each of R_1 to R_3 is not carbazolyl group which is optionally substituted or not azacarbazolyl group having 2 or more nitrogen atoms which is optionally substituted;

R_6 and R_{10} are each independently hydrogen atom of alkyl group having 1 to 40 carbon atoms which is optionally substituted;


R_7 to R_9 are each independently hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that when R_3 and R_9 , or R_8 and R_7 are not bonded to each other thereby do not form a ring structure, at least one of R_7 to R_9 is 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is optionally substituted, dibenzothiophenyl group which is optionally substituted, or phenyl group or biphenyl group each being optionally substituted by at least one group selected from the group consisting of 9-carbazolyl group which is optionally substituted, azacarbazolyl group having 2 to 5 nitrogen atoms which is optionally substituted, dibenzofuranyl group which is substituted and dibenzothiophenyl group which is optionally substituted

R_8 and R_9 , or R_8 and R_7 are optionally bonded to each other to form a ring structure which is optionally substituted, and R_7 or R_9 which does not form the ring structure is hydrogen atom, halogen atom, alkyl group having 1 to 40 carbon atoms which is optionally substituted, cycloalkyl group having 3 to 15 carbon atoms which is optionally substituted, heterocyclic group having 3 to 20 carbon atoms which is optionally substituted, alkoxy group having 1 to 40 carbon atoms which is optionally substituted, non-condensed aryl group having 6 to 40 carbon atoms which is optionally substituted, condensed aryl group having 10 to 18 carbon atoms which is optionally substituted, aryloxy group having 6 to 20 carbon atoms which is optionally substituted, aralkyl group having 7 to 20 carbon atoms which is optionally substituted, arylamino group having 6 to 40 carbon atoms which is optionally substituted, alkylamino group having 1 to 40 carbon atoms which is optionally substituted, aralkylamino group having 7 to 60 carbon atoms which is optionally substituted, arylcarbonyl group having 7 to 40 carbon atoms which is optionally substituted, arylthio group having 6 to 20 carbon atoms which is optionally substituted, alkyl halide group having 1 to 40 carbon atoms which is optionally substituted, or cyano group, with the proviso that R_8 and R_9 , or R_8 and R_7 together with a benzene ring to which R_7 to R_9 are bonded do not form carbazolyl group;

R_1 to R_3 are all hydrogen atoms when at least one of R_7 to R_9 is dibenzofuranyl group which is optionally substituted or dibenzothiophenyl group which is optionally substituted;


each of R_1 to R_3 and R_6 to R_{10} does not have a polymerizable functional group at its terminal end; and
X is sulfur atom or oxygen atom.

2. The material for organic electroluminescence devices according to claim 1, which is represented by the following formula 2:




wherein R_1 to R_3 , R_6 to R_8 , R_{10} and X are the same as defined above, and definitions of R_{20} to R_{24} are the same as the definitions of R_1 to R_3 except for the proviso.

3. The material for organic electroluminescence devices according to claim 1, which is represented by the following formula 3:




wherein R_1 to R_3 , R_6 , R_7 , R_9 , R_{10} and X are the same as defined above, and definitions of R_{20} to R_{24} are the same as the definitions of R_1 to R_3 except for the proviso.

4. The material for organic electroluminescence devices according to claim 1, which is represented by the following formula 4:




wherein R_1 to R_3 , P_6 , R_7 and X are the same as defined above, and definitions of R_{18} , R_{19} and R_{21} to R_{23} are the same as the definitions of R_1 to R_3 except for the proviso.

5. The material for organic electroluminescence devices according to claim 1, which is represented by the following formula 5:




wherein R_1 to R_3 , R_6 to R_8 , R_{10} and X are the same as defined above, and definitions of R_{20} , R_{22} to R_{24} and R_{25} to R_{29} are the same as the definitions of R_1 to R_3 except for the proviso.

6. The material for organic electroluminescence devices according to claim 2, which is represented by the following formula 6:




wherein R_6 to R_8 , R_{10} , R_{20} to R_{24} and X are the same as defined above.

7. The material for organic electroluminescence devices according to claim 3, which is represented by the following formula 7:




wherein R_6 , R_7 , R_9 , R_{10} , R_{20} to R_{24} and X are the same as defined above.

8. The material for organic electroluminescence devices according to claim 4, which is represented by the following formula 8:



wherein R_{18} , R_{19} , R_{22} , R_{23} and X are the same as defined above.

9. The material for organic electroluminescence devices according to claim 2, which is represented by the following formula 9:



wherein R_7 , R_{21} , R_{23} and X are the same as defined above.

- 15
10. The material for organic electroluminescence devices according to any one of claims 2 to 9, wherein at least one of R_7 , R_8 and R_{20} to R_{24} of the formula 2, at least one of R_7 , R_9 and R_{20} to R_{24} of the formula 3, at least one of R_7 and R_{21} to R_{23} of the formula 4, at least one of R_7 , R_8 , R_{20} and R_{22} to R_{24} of the formula 5, at least one of R_7 , R_8 and R_{20} to R_{24} of the formula 6, at least one of R_7 , R_9 and R_{20} to R_{24} of the formula 7, at least one of R_{22} and R_{23} of the formula 8, or at least one of R_7 , R_{21} and R_{23} of the formula 9 is a group selected from the group consisting of a substituted or non-substituted 9-carbazolyl group, a substituted or non-substituted dibenzofuranyl group, a substituted or non-substituted azacarbazolyl group having 2 to 5 nitrogen atoms and a substituted or non-substituted dibenzothiophenyl group.
- 20
11. The material for organic electroluminescence devices according to any one of claims 1 to 10, wherein the compound represented by any one of the formulae 1 to 9 has a triplet energy gap of 2.2 to 3.2 eV.
- 25
12. An organic electroluminescence device which comprises a cathode, an anode and an organic thin film layer having one or more layers, the organic thin film layer being interposed between the cathode and the anode, at least one layer of the organic thin film being a light emitting layer which comprises a host material for use in combination with at least one phosphorescent metal complex, and at least one layer of the organic thin film containing the material for organic electroluminescence devices as defined in any one of claims 1 to 11.
- 30
13. The organic electroluminescence device according to claim 12, wherein the host material contained in the light emitting layer is the material for organic electroluminescence devices.
- 35
14. The organic electroluminescence device according to claim 13, wherein the light emitting layer comprises the host material and a phosphorescent material and the host material is the material for organic electroluminescence devices.
- 40
15. The organic electroluminescence device according to claim 14, wherein the phosphorescent material is a compound containing iridium (Ir), osmium (Os) or platinum (Pt).
- 45
16. The organic electroluminescence device according to claim 14, wherein the light emitting layer contains a metal complex which emits blue light having a maximum peak wavelength of 500 nm or less.
- 50
17. The organic electroluminescence device according to claim 12, wherein at least one layer of the organic thin film layer is an electron injecting layer mainly comprising a nitrogen-containing cyclic derivative which is different from the material for organic electroluminescence devices.
- 55
18. The organic electroluminescence device according to claim 12, wherein at least one layer of the organic thin film layer is a hole transporting layer which comprises the material for organic electroluminescence devices.
19. The organic electroluminescence device according to claim 12, which further comprises a reducing dopant at an interface between the cathode and the organic thin film layer.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2007/072585

A. CLASSIFICATION OF SUBJECT MATTER H01L51/50 (2006.01) i		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) H01L51/50-51/56, 27/32		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1922-1996 Jitsuyo Shinan Toroku Koho 1996-2008 Kokai Jitsuyo Shinan Koho 1971-2008 Toroku Jitsuyo Shinan Koho 1994-2008		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) CAplus (STN)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	JP 2002-308837 A (Fuji Photo Film Co., Ltd.), 23 October, 2002 (23.10.02), Par. Nos. [0001], [0024] (exemplified compounds HT-8, HT-10); Par. No. [0052] (Family: none)	1, 11-15, 17 16, 18, 19
X Y	WO 2006/128800 A1 (CIBA SPECIALTY CHEMICALS HOLDING INC.), 07 December, 2006 (07.12.06), Page 45, line 11 to page 49, line 3; page 90 (compounds B-4, B-5) (Family: none)	1, 12-15, 17, 19 16
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 23 January, 2008 (23.01.08)		Date of mailing of the international search report 05 February, 2008 (05.02.08)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (April 2007)

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2007/072585

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP 2005-112765 A (Mitsui Chemicals, Inc.), 28 April, 2005 (28.04.05), Par. No. [0024] (exemplified compound 5); Par. No. [0029] (exemplified compound 25); Par. No. [0090] (Family: none)	1, 12-19
Y	JP 2004-214050 A (Konica Minolta Holdings, Inc.), 29 July, 2004 (29.07.04), Par. No. [0188] (Family: none)	16
Y	WO 2006/137210 A1 (Idemitsu Kosan Co., Ltd.), 28 December, 2006 (28.12.06), Par. Nos. [0053], [0066] (Family: none)	17, 19
P, X	WO 2007/111176 A1 (Idemitsu Kosan Co., Ltd.), 04 October, 2007 (04.10.07), Pages 20, 21 (exemplified compounds A-1 to B-19) (Family: none)	1, 2, 12-17, 19
P, X	WO 2007/119816 A1 (Konica Minolta Holdings, Inc.), 25 October, 2007 (25.10.07), Par. No. [0079] (exemplified compound 37) (Family: none)	1, 12-17, 19
P, X	JP 2007-189001 A (Konica Minolta Holdings, Inc.), 26 July, 2007 (26.07.07), Par. No. [0074] (exemplified compound 31) (Family: none)	1, 12-17, 19

Form PCT/ISA/210 (continuation of second sheet) (April 2007)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.


Patent documents cited in the description

- WO 05101912 A [0005]
- JP 5109485 A [0005]
- JP 2004002351 A [0005]
- WO 04096945 A [0005]
- JP 2002308837 A [0005]
- WO 2005113531 A [0005] [0111]
- JP 2005112765 A [0005]
- WO 2006114966 A [0005]
- JP 2005314239 A [0005]
- JP 2007077094 A [0005]
- JP 2007063501 A [0005]
- JP 2007110097 A [0005]

专利名称(译)	用于有机电致发光元件的材料和通过使用该材料制备的有机电致发光元件		
公开(公告)号	EP2166583A1	公开(公告)日	2010-03-24
申请号	EP2007832315	申请日	2007-11-21
[标]申请(专利权)人(译)	出光兴产株式会社		
申请(专利权)人(译)	出光兴产股份有限公司.		
当前申请(专利权)人(译)	出光兴产股份有限公司.		
[标]发明人	IWAKUMA TOSHIHIRO ENDO JUN NUMATA MASAKI FUKUOKA KENICHI		
发明人	IWAKUMA, TOSHIHIRO ENDO, JUN NUMATA, MASAKI FUKUOKA, KENICHI		
IPC分类号	H01L51/50		
CPC分类号	H01L51/0072 C07D405/14 C09K11/06 C09K2211/1029 C09K2211/1044 C09K2211/1059 C09K2211/1074 C09K2211/1088 C09K2211/185 C09K2211/186 H01L51/0059 H01L51/006 H01L51/0061 H01L51/0067 H01L51/0073 H01L51/0074 H01L51/0081 H01L51/5016 H01L51/5088 H05B33/14 Y10S428/917		
代理机构(译)	法思博事务所		
优先权	2007181142 2007-07-10 JP		
其他公开文献	EP2166583A4		
外部链接	Espacenet		

摘要(译)

用于与至少一种磷光金属配合物结合使用的本发明有机电致发光器件的材料具有特定的杂环结构。用于有机电致发光器件的材料用作主体材料或空穴传输材料。一种有机电致发光器件，具有阳极，阴极和具有一层或多层的有机薄膜层，所述有机薄膜层介于阳极和阴极之间，其中至少一层有机薄膜层含有有机电致发光器件的材料，发光效率高，像素缺陷少，耐热性优异，寿命长。



(1)