



(11)

EP 3 503 235 A1

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art. 153(4) EPC

(43) Date of publication:

26.06.2019 Bulletin 2019/26

(51) Int Cl.:

H01L 51/52^(2006.01) H01L 51/56^(2006.01)

(21) Application number: **17837931.9**

(86) International application number:

PCT/CN2017/097344

(22) Date of filing: **14.08.2017**

(87) International publication number:

WO 2018/033040 (22.02.2018 Gazette 2018/08)

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

Designated Extension States:

BA ME

Designated Validation States:

MA MD

(72) Inventors:

- **ZHANG, Can**
Beijing 100176 (CN)
- **LV, Jing**
Beijing 100176 (CN)

(74) Representative: **Gesthuysen Patent- und
Rechtsanwälte
Patentanwälte
Huyssenallee 100
45128 Essen (DE)**

(30) Priority: **18.08.2016 CN 201610686026**

(71) Applicant: **BOE Technology Group Co., Ltd.**
Beijing 100015 (CN)

(54) **TOP-EMISSION ORGANIC ELECTROLUMINESCENT COMPONENT, MANUFACTURING METHOD THEREFOR, AND DISPLAY DEVICE**

(57) The embodiments of the present disclosure provide a top-emitting type organic electroluminescent device, a manufacturing method thereof and a display apparatus, which can reduce damage to an organic functional layer when a transparent metal oxide layer is sputtered, thereby obtaining a cathode with high stability and high transparency. The top-emitting type organic electroluminescent device includes an anode, an organic functional layer and a cathode that are sequentially stacked. The cathode includes a transparent metal layer disposed on a surface of the organic functional layer facing away from the anode, and a transparent metal oxide layer disposed on a surface of the transparent metal layer

facing away from the organic functional layer. In the top-emitting type organic electroluminescent device provided by the embodiment of the present disclosure, the cathode includes a transparent metal layer disposed on a side of the organic functional layer facing away from the anode and a transparent metal oxide layer disposed on the transparent metal layer. The transparent metal layer can be formed on the organic functional layer by deposition, which causes less damage to the organic functional layer than sputtering. The transparent metal oxide layer can also be formed on the transparent metal layer by sputtering, thereby improving the light transmittance of the cathode.




Fig. 1

EP 3 503 235 A1

Description

RELATED APPLICATIONS

[0001] The present application claims the benefit of Chinese Patent Application No. 201610686026.5, filed on August 18, 2016, the entire disclosures of which are incorporated herein by reference.

TECHNICAL FIELD

[0002] The present disclosure relates to the field of display apparatus technology, in particular to a top-emitting type organic electroluminescent device, a manufacturing method thereof and a display apparatus.

BACKGROUND

[0003] Organic electroluminescent devices, as a new type of lighting and display technology, have unique advantages and are widely used. In order to improve the aperture ratio of organic electroluminescent devices, organic electroluminescent devices with a top-emitting structure are typically used.

[0004] Due to its strong microcavity effect, the organic electroluminescent device with the top-emitting structure has a strong selectivity for color of emitted light. In order to weaken or suppress the microcavity effect, in the manufacture process of the top-emitting type organic electroluminescent device, an effective method is to increase the light transmittance of the cathode, which can reduce the resonant cavity effect, thereby obtaining a stable broadband white light spectrum.

[0005] In order to increase the light transmittance of the cathode, a common approach in the prior art is to use metal oxides such as Indium-doped ZnO, indium tin oxide (ITO), and such metal oxides can only be deposited by sputtering method. However, a high-energy sputtering process can easily damage the underlying organic layer, which leads to reduction of the efficiency and lifetime of the device, as well as the yield. Moreover, the square resistance of metal oxide materials is large. To obtain a cathode with a small square resistance, it is necessary to increase the thickness of the film and increase the sputtering time, which in turn reduces the lifetime of the organic electroluminescent device.

SUMMARY

[0006] The embodiments of the present disclosure provide a top-emitting type organic electroluminescent device, a manufacturing method thereof and a display apparatus, which can reduce damage to the organic functional layer when a film layer is sputtered, thereby obtaining a cathode with high stability and high transparency.

[0007] To this end, an embodiment of the present disclosure provides a top-emitting type organic electrolumi-

nescent device, which includes an anode, an organic functional layer and a cathode stacked sequentially. The cathode includes: a transparent metal layer disposed on a surface of the organic functional layer facing away from the anode, and a transparent metal oxide layer disposed on a surface of the transparent metal layer facing away from the organic functional layer.

[0008] In the top-emitting type organic electroluminescent device provided by the embodiment of the present disclosure, the cathode includes a transparent metal layer disposed on a side of the organic functional layer facing away from the anode and a transparent metal oxide layer disposed on the transparent metal layer. The transparent metal layer can be formed on the organic functional layer by deposition, which causes less damage to the organic functional layer than sputtering. The transparent metal oxide layer can be formed on the transparent metal layer by sputtering, thereby improving the light transmittance of the cathode.

[0009] Therefore, the top-emitting type organic electroluminescent device provided by the embodiment of the present disclosure can reduce damage to the organic functional layer when a film layer is sputtered, thereby obtaining the cathode with high stability and high transparency.

[0010] In some optional implementations, the above top-emitting type organic electroluminescent device further includes a plurality of transparent metal strips disposed on a surface of the transparent metal oxide layer facing away from the organic functional layer, the plurality of transparent metal strips are located at least in a non-light emitting region of the organic electroluminescent device. The disposition of transparent metal strips can reduce the overall square resistance of the cathode and reduce the absorption efficiency of the cathode.

[0011] In some optional implementations, the plurality of transparent metal strips are located in a non-light emitting region and a light emitting region of the organic electroluminescent device.

[0012] In some optional implementations, the plurality of transparent metal strips are arranged in parallel, and a gap of $2.5\ \mu\text{m} \sim 5\ \mu\text{m}$ is between two directly adjacent transparent metal strips.

[0013] In some alternative embodiments, the plurality of transparent metal strips form a grid structure.

[0014] In some optional implementations, the transparent metal layer has a thickness of $5\ \text{nm} \sim 10\ \text{nm}$. Due to the poor light transparency of the transparent metal layer, the thickness of the transparent metal layer is set to be $5\ \text{nm} \sim 10\ \text{nm}$, which can improve the adhesion of the cathode and reduce the possibility of forming a resonant cavity with the transparent metal layer.

[0015] In some optional implementations, a material of the transparent metal layer is a magnesium-silver alloy. With a low work function of magnesium, the transparent metal layer obtains a low injecting energy barrier. The addition of silver can improve the stability of the transparent metal layer, and further improve the adhesion of

the transparent metal layer, and then improve the adhesion of the cathode.

[0016] In some optional implementations, the transparent metal oxide layer has a thickness of 2 nm ~ 20 nm. The transparent metal oxide layer can prevent the oxidation of the relatively thin transparent metal layer, and improve the light transmittance of the cathode. Since the organic functional layer may be damaged easily when the transparent metal oxide layer is sputtered, the thickness of the transparent metal oxide layer is set to be 2 nm ~ 20 nm.

[0017] In some optional implementations, a material of the transparent metal oxide layer is Indium-doped ZnO or indium tin oxide (ITO).

[0018] In some optional implementations, each transparent metal strip has a thickness of 50 nm ~ 80 nm.

[0019] In some optional implementations, a material of each transparent metal strip is silver.

[0020] An embodiment of the present disclosure further provides a display apparatus, which includes the top-emitting type organic electroluminescent device according to any one of the above embodiments.

[0021] An embodiment of the present disclosure further provides a method for manufacturing the top-emitting type organic electroluminescent device according to any one of the above embodiments.

[0022] The method includes: forming an anode on a substrate; forming an organic functional layer on a surface of the anode facing away from the substrate; forming a transparent metal layer on a surface of the organic functional layer facing away from the anode; and forming a transparent metal oxide layer on a surface of the transparent metal layer facing away from the organic functional layer.

[0023] In some optional implementations, the manufacturing method further includes: forming a plurality of transparent metal strips on a surface of the transparent metal oxide layer facing away from the organic functional layer. The plurality of transparent metal strips are located at least in a non-light emitting region of the organic electroluminescent device.

[0024] In some optional implementations, the plurality of transparent metal strips are arranged in parallel, and a gap of 2.5 μm ~ 5 μm is between two directly adjacent transparent metal strips; alternatively, the plurality of transparent metal strips form a grid structure.

BRIEF DESCRIPTION OF THE DRAWINGS

[0025] In order to more clearly illustrate the technical solutions in embodiments of the disclosure or in the prior art, the appended drawings needed to be used in the description of the embodiments or the prior art will be introduced briefly in the following. Obviously, the drawings in the following description are only some embodiments of the disclosure, and for those of ordinary skills in the art, other drawings may be obtained according to these drawings under the premise of not paying out cre-

ative work.

Fig. 1 is a structural schematic diagram of a top-emitting type organic electroluminescent device provided by an embodiment of the present disclosure;

Fig. 2a is a structural schematic diagram of a top-emitting type organic electroluminescent device provided by another embodiment of the present disclosure;

Fig. 2b is a top view of the top-emitting type organic electroluminescent device in the embodiment shown in Fig. 2a;

Fig. 3 is a structural schematic diagram of a top-emitting type organic electroluminescent device provided by yet another embodiment of the present disclosure;

Fig. 4 is a structural schematic diagram of a top-emitting type organic electroluminescent device provided by still another embodiment of the present disclosure;

Fig. 5 shows light transmittance curves of a cathode in a top-emitting type organic electroluminescent device provided by an embodiment of the present disclosure and a cathode in the prior art; and

Fig. 6 is a flow chart of a method for manufacturing a top-emitting type organic electroluminescent device provided by an embodiment of the present disclosure.

Reference signs:

[0026] 10-substrate; 1-anode; 2-organic functional layer; 3-cathode; 31-transparent metal layer; 32-transparent metal oxide layer; 33-transparent metal strip.

DETAILED DESCRIPTION OF THE PRESENT DISCLOSURE

[0027] In the following, the technical solutions in the embodiments of the disclosure will be described clearly and completely in connection with the drawings in the embodiments of the disclosure. Obviously, the described embodiments are only part of the embodiments of the disclosure, and not all of the embodiments. Based on the embodiments in the disclosure, all other embodiments obtained by those of ordinary skills in the art under the premise of not paying out creative work pertain to the protection scope of the disclosure.

[0028] As shown in Fig. 1, Fig. 1 is a structural schematic diagram of a top-emitting type organic electroluminescent device provided by an embodiment of the present disclosure. The top-emitting type organic elec-

troluminescent device can, for example, be arranged on a substrate 10. The top-emitting type organic electroluminescent device includes an anode 1, an organic functional layer 2, and a cathode 3 that are sequentially stacked. The cathode 3 includes: a transparent metal layer 31 disposed on a surface of the organic functional layer 2 facing away from the anode 1, and a transparent metal oxide layer 32 disposed on a surface of the transparent metal layer 31 facing away from the organic functional layer 2.

[0029] In the top-emitting type organic electroluminescent device provided by the embodiment of the present disclosure, the cathode 3 includes a transparent metal layer 31 disposed on a side of the organic functional layer 2 facing away from the anode and a transparent metal oxide layer 32 disposed on the transparent metal layer 31. The transparent metal layer 31 can be formed on the organic functional layer 2 by deposition, which causes less damage to the organic functional layer 2 than sputtering. The transparent metal oxide layer 32 can also be formed on the transparent metal layer 31 by sputtering, thereby improving the light transmittance of the cathode 3.

[0030] Therefore, the top-emitting type organic electroluminescent device provided by the embodiment of the present disclosure can reduce damage to the organic functional layer 2 when the transparent metal oxide layer is sputtered, thereby obtaining the cathode with high stability and high transparency.

[0031] For example, the above organic functional layer 2 can include a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer and an electron injection layer that are sequentially stacked in the direction from the anode 1 toward the cathode 3, but the present disclosure is not limited thereto.

[0032] As shown in Fig. 5, the light transmittance of the cathode 3 provided by the embodiment of the present disclosure is compared with that of a cathode 3 in the prior art. The abscissa represents the wavelength of light and the ordinate represents the light transmittance. L1 represents the light transmittance curve of the cathode 3 provided by the embodiment of the present disclosure, and L2 represents the light transmittance curve of the cathode in the prior art. As can be seen from Fig. 5, the maximum light transmittance of the cathode 3 provided by the embodiment of the present disclosure is about 85%, while the maximum light transmittance of the cathode in the prior art is about 55%. It can be seen that the cathode 3 provided by the embodiment of the present disclosure has a higher light transmittance. Moreover, due to the existence of the transparent metal layer 31, the cathode 3 provided by the embodiment of the present disclosure has a lower square resistance.

[0033] As shown in Fig. 2a, Fig. 2b, Fig. 3 and Fig. 4, the above top-emitting type organic electroluminescent device can further include a plurality of transparent metal strips 33 disposed on a surface of the transparent metal oxide layer 32 facing away from the organic functional

layer. The plurality of transparent metal strips 33 are located at least in a non-light emitting region of the organic electroluminescent device. The disposition of transparent metal strips 33 can reduce the overall square resistance of the cathode 3 and reduce the absorption efficiency of the cathode 3.

[0034] The plurality of transparent metal strips 33 located at least in the non-light emitting region of the organic electroluminescent device means that at least the non-light emitting region of the organic electroluminescent device is provided with the transparent metal strips 33, as shown in Fig. 2a, Fig. 2b and Fig. 3.

[0035] Optionally, as shown in Fig. 4, the plurality of transparent metal strips 33 are located in the non-light emitting region and the light emitting region of the organic electroluminescent device. That is, both the non-light emitting region and the light-emitting region of the organic electroluminescent device are provided with the transparent metal strips 33. As shown in Fig. 3 and Fig. 4, in some embodiments, the organic functional layer 2 and the cathode 3 can also have shapes of a groove or a curved surface, and the present disclosure is not limited thereto.

[0036] Optionally, the plurality of transparent metal strips 33 are arranged in parallel, and a gap of $2.5\ \mu\text{m} \sim 5\ \mu\text{m}$ is between two directly adjacent transparent metal strips 33. For example, the gap can be $2.5\ \mu\text{m}$, $3\ \mu\text{m}$, $3.5\ \mu\text{m}$, $4\ \mu\text{m}$, $4.5\ \mu\text{m}$, $5\ \mu\text{m}$, etc., which will not be enumerated herein.

[0037] There can be a plurality of specific arrangements for the plurality of transparent metal strips 33. Optionally, the plurality of transparent metal strips 33 form a grid structure.

[0038] Optionally, the transparent metal layer 31 has a thickness of $5\ \text{nm} \sim 10\ \text{nm}$. Due to the poor light transparency of the transparent metal layer 31, the thickness of the transparent metal layer 31 is set to be $5\ \text{nm} \sim 10\ \text{nm}$, for example, $5\ \text{nm}$, $5.3\ \text{nm}$, $5.5\ \text{nm}$, $6\ \text{nm}$, $6.5\ \text{nm}$, $7\ \text{nm}$, $8\ \text{nm}$, $9\ \text{nm}$, $10\ \text{nm}$, etc., which will not be enumerated herein. The transparent metal layer with the above thickness can improve the adhesion of the cathode 3 and reduce the possibility of forming a resonant cavity with the transparent metal layer 31.

[0039] Optionally, the material of the transparent metal layer 31 is a magnesium-silver alloy, it can also be Al, Li, Ca, In, or an alloy of Al, Li, Ca, In. With a low work function of magnesium, the transparent metal layer obtains a low injecting energy barrier. The addition of silver can improve the stability of the transparent metal layer 31, and can improve the adhesion of the transparent metal layer 31, and then improves the adhesion of the cathode 3.

[0040] Optionally, the transparent metal oxide layer 32 has a thickness of $2\ \text{nm} \sim 20\ \text{nm}$. For example, the thickness can be $2\ \text{nm}$, $3\ \text{nm}$, $5\ \text{nm}$, $10\ \text{nm}$, $13\ \text{nm}$, $16\ \text{nm}$, $18\ \text{nm}$, and $20\ \text{nm}$, etc., which will not be enumerated herein. The transparent metal oxide layer can prevent the oxidation of the relatively thin transparent metal layer 31, and can improve the light transmittance of the cathode

3. Since the organic layer 2 may be damaged easily when the transparent metal oxide layer is sputtered, the thickness of the transparent metal oxide layer is set to be 2 nm ~ 20 nm.

[0041] Optionally, the material of the transparent metal oxide layer 32 is Indium-doped ZnO or indium tin oxide (ITO).

[0042] Optionally, each transparent metal strip 33 has a thickness of 50 nm ~ 80 nm. Optionally, the material of each transparent metal strip 33 is silver.

[0043] An embodiment of the present disclosure further provides a display apparatus, which includes the top-emitting type organic electroluminescent device according to any one of the above embodiments. Since the above top-emitting type organic electroluminescent device can reduce the damage to the organic functional layer 2 when the transparent metal oxide layer is sputtered and obtain the cathode 3 with high stability and high transparency, the display apparatus provided by the embodiment of the present disclosure has a good display effect.

[0044] The display apparatus can be any product or component with a display function, such as a mobile phone, a tablet computer, a television, a display, a notebook computer, a digital photo frame, a navigator, etc. For the implementation of the display apparatus, reference can be made to the above embodiment of the top-emitting type organic electroluminescent device, which will not be described herein again.

[0045] As shown in Fig. 6, an embodiment of the present disclosure further provides a method for manufacturing a top-emitting type organic electroluminescent device embodiment the above embodiments. The method includes the following steps.

Step S601: forming an anode on a substrate. Specifically, a silver layer or an aluminum layer is sputter-deposited on the substrate, and the aluminum layer and the silver layer are highly reflective layers.

Step S602: forming an organic functional layer on a surface of the anode facing away from the substrate. The formed organic functional layer can include, for example, a hole injection layer, a hole transport layer, a light emitting layer, an electron transport layer, and an electron injection layer.

Step S603: forming a transparent metal layer on a surface of the organic functional layer facing away from the anode. The transparent metal layer can be formed by deposition. The formed transparent metal layer has a thickness of 5 nm ~ 10 nm. Due to the poor light transparency of the transparent metal layer, the thickness of the transparent metal layer is set to be 5 nm ~ 10 nm, for example, 5 nm, 5.3 nm, 5.5 nm, 6 nm, 6.5 nm, 7 nm, 8 nm, 9 nm, 10 nm, etc., which will not be enumerated herein. The transparent metal layer with the above thickness can improve

the adhesion of the cathode 3 and reduce the possibility of forming a resonant cavity with the transparent metal layer 31.

Step S604: forming a transparent metal oxide layer on a surface of the transparent metal layer facing away from the organic functional layer. Those skilled in the art can select the formation method of the transparent metal oxide layer (for example, deposition, sputtering, etc.) according to actual requirements. The formed transparent metal oxide layer can have a thickness of 2 nm ~ 20 nm. For example, the thickness can be 2 nm, 3 nm, 5 nm, 10 nm, 13 nm, 16 nm, 18 nm, and 20 nm, etc., which will not be enumerated herein. The transparent metal oxide layer can prevent the oxidation of the thin transparent metal layer and improve the light transmittance of the cathode. Since the organic layer 2 may be damaged easily when the transparent metal oxide layer is sputtered, the thickness of the transparent metal oxide layer is set to be 2 nm ~ 20 nm.

[0046] Optionally, the manufacturing method can further include: forming a plurality of transparent metal strips on a surface of the transparent metal oxide layer facing away from the organic functional layer. The plurality of transparent metal strips are located at least in a non-light emitting region of the organic electroluminescent device. Each transparent metal strip has a thickness of 50 nm ~ 80 nm. The material of each transparent metal strip is silver, and it can also be Al, Li, Ca, In, etc.

[0047] Optionally, the plurality of transparent metal strips are arranged in parallel, and a gap of 2.5 μm ~ 5 μm is between two directly adjacent transparent metal strips; alternatively, the plurality of transparent metal strips form a grid structure.

[0048] Apparently, the person skilled in the art can make various alterations and variations to the present disclosure without departing the spirit and scope of the present disclosure. As such, provided that these modifications and variations of the present disclosure pertain to the scope of the claims of the present disclosure and their equivalents, the present disclosure is intended to embrace these alterations and variations.

Claims

1. A top-emitting type organic electroluminescent device, comprising: an anode, an organic functional layer and a cathode stacked sequentially; wherein the cathode comprises:

a transparent metal layer disposed on a surface of the organic functional layer facing away from the anode; and

a transparent metal oxide layer disposed on a surface of the transparent metal layer facing

away from the organic functional layer.

2. The top-emitting type organic electroluminescent device according to claim 1, further comprising: a plurality of transparent metal strips disposed on a surface of the transparent metal oxide layer facing away from the organic functional layer; wherein the plurality of transparent metal strips are located at least in a non-light emitting region of the organic electroluminescent device. 5
3. The top-emitting type organic electroluminescent device according to claim 2, wherein the plurality of transparent metal strips are located in the non-light emitting region and a light emitting region of the organic electroluminescent device. 10
4. The top-emitting type organic electroluminescent device according to claim 3, wherein the plurality of transparent metal strips are arranged in parallel, and a gap between two directly adjacent transparent metal strips is $2.5\mu\text{m} \sim 5\mu\text{m}$. 15
5. The top-emitting type organic electroluminescent device according to claim 3, wherein the plurality of transparent metal strips form a grid structure. 20
6. The top-emitting type organic electroluminescent device according to claim 1, wherein the transparent metal layer has a thickness of $5\text{ nm} \sim 10\text{ nm}$. 25
7. The top-emitting type organic electroluminescent device according to claim 1, wherein a material of the transparent metal layer is a magnesium-silver alloy. 30
8. The top-emitting type organic electroluminescent device according to claim 1, wherein the transparent metal oxide layer has a thickness of $2\text{ nm} \sim 20\text{ nm}$. 35
9. The top-emitting type organic electroluminescent device according to claim 1, wherein a material of the transparent metal oxide layer is Indium-doped ZnO or indium tin oxide. 40
10. The top-emitting type organic electroluminescent device according to any one of claims 2-9, wherein each transparent metal strip has a thickness of $50\text{ nm} \sim 80\text{ nm}$. 45
11. The top-emitting type organic electroluminescent device according to claim 10, wherein a material of each transparent metal strip is silver. 50
12. A display apparatus, comprising the top-emitting type organic electroluminescent device according to any one of claims 1-11. 55

13. A method for manufacturing the top-emitting type organic electroluminescent device, comprising:

forming an anode on a substrate;
forming an organic functional layer on a surface of the anode facing away from the substrate;
forming a transparent metal layer on a surface of the organic functional layer facing away from the anode; and
forming a transparent metal oxide layer on a surface of the transparent metal layer facing away from the organic functional layer.

14. The method according to claim 13, further comprising:
forming a plurality of transparent metal strips on a surface of the transparent metal oxide layer facing away from the organic functional layer; wherein the plurality of transparent metal strips are located at least in a non-light emitting region of the organic electroluminescent device. 15
15. The method according to claim 14, wherein the plurality of transparent metal strips are arranged in parallel, and a gap of $2.5\mu\text{m} \sim 5\mu\text{m}$ is between two directly adjacent transparent metal strips; alternatively, the plurality of transparent metal strips form a grid structure. 20




Fig. 1




Fig. 2a




Fig. 2b




Fig. 3




Fig. 4




Fig. 5




Fig. 6

INTERNATIONAL SEARCH REPORT

International application No.
PCT/CN2017/097344

A. CLASSIFICATION OF SUBJECT MATTER

H01L 51/52 (2006.01) i; H01L 51/56 (2006.01) i
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

H01L; H05B 33

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CNABS; CNTXT; CNKI; VEN: 有机, 电致, 场致, 电场, 电激, 发光, oled, 阴极, 复合, 双层, 金属氧化物, 金属, organic, electroluminescent, luminescent, light emitting, cathode, complex, double, metal oxide, metal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CN 104835919 A (BOE TECHNOLOGY GROUP CO., LTD. et al.), 12 August 2015 (12.08.2015), description, paragraphs [0038]-[0118], and figures 2 and 6	1, 6-9, 12, 13
Y	CN 104835919 A (BOE TECHNOLOGY GROUP CO., LTD. et al.), 12 August 2015 (12.08.2015), description, paragraphs [0038]-[0118], and figures 2 and 6	2-5, 10, 11, 14, 15
Y	US 2013020564 A1 (DAINIPPON PRINTING CO., LTD.), 24 January 2013 (24.01.2013), description, paragraphs [0033], [0047], [0057] and [0085], and figure 5	2-5, 10, 11, 14, 15
X	CN 101222027 A (TSINGHUA UNIVERSITY et al.), 16 July 2008 (16.07.2008), description, page 1, lines 6-13 and page 4, line 3 to page 5, line 8	1, 6-9, 12, 13
PX	CN 106206984 A (BOE TECHNOLOGY GROUP CO., LTD.), 07 December 2016 (07.12.2016), claims 1-14, description, paragraphs [0043]-[0070], and figures 1-6	1-15

☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	
"E" earlier application or patent but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 25 October 2017	Date of mailing of the international search report 10 November 2017
Name and mailing address of the ISA State Intellectual Property Office of the P. R. China No. 6, Xitucheng Road, Jimenqiao Haidian District, Beijing 100088, China Facsimile No. (86-10) 62019451	Authorized officer ZHANG, Yue Telephone No. (86-10) 62089115

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/CN2017/097344

Patent Documents referred in the Report	Publication Date	Patent Family	Publication Date
CN 104835919 A	12 August 2015	US 2017170424 A1	15 June 2017
		WO 2016188042 A1	01 December 2016
US 2013020564 A1	24 January 2013	JP 5565047 B2	06 August 2014
		US 8759821 B2	24 June 2014
		WO 2011125442 A1	13 October 2011
		JP 2011216317 A	27 October 2011
CN 101222027 A	16 July 2008	CN 101222027 B	08 September 2010
CN 106206984 A	07 December 2016	None	

Form PCT/ISA/210 (patent family annex) (July 2009)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- CN 201610686026 [0001]

专利名称(译)	顶部有机发光组分，制备方法及其显示装置		
公开(公告)号	EP3503235A4	公开(公告)日	2020-03-11
申请号	EP2017837931	申请日	2017-08-14
[标]申请(专利权)人(译)	京东方科技集团股份有限公司		
申请(专利权)人(译)	京东方科技集团股份有限公司.		
当前申请(专利权)人(译)	京东方科技集团股份有限公司.		
[标]发明人	ZHANG CAN LV JING		
发明人	ZHANG, CAN LV, JING		
IPC分类号	H01L51/52 H01L51/56		
CPC分类号	H01L51/5234 H01L51/56 H01L51/5225 H01L2251/5315 H01L51/52		
优先权	201610686026.5 2016-08-18 CN		
其他公开文献	EP3503235A1		
外部链接	Espacenet		

摘要(译)

本公开的实施方式提供了一种顶部发射型有机电致发光器件，其制造方法和显示装置，其可以减少当溅射透明金属氧化物层时对有机功能层的损害，从而获得具有高稳定性的阴极。和高透明度。顶部发射型有机电致发光器件包括依次堆叠的阳极，有机功能层和阴极。阴极包括设置在有机功能层的背离阳极的表面的透明金属层和设置在透明金属层的背离有机功能层的表面的透明金属氧化物层。在本发明实施例提供的顶部发射型有机电致发光器件中，所述阴极包括：透明金属层，其设置在所述有机功能层的背离所述阳极的一侧；以及透明金属氧化物层，其设置在所述透明金属上层。可以通过沉积在有机功能层上形成透明金属层，与溅射相比，其对有机功能层的损害较小。也可以通过溅射在透明金属层上形成透明金属氧化物层，从而提高阴极的透光率。