



(11) **EP 2 443 213 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
23.04.2014 Bulletin 2014/17

(51) Int Cl.:
C09K 11/06 ^(2006.01) **H05B 33/22** ^(2006.01)
C07D 235/02 ^(2006.01) **C07D 403/14** ^(2006.01)
C07D 235/18 ^(2006.01)

(21) Application number: **10725130.8**

(86) International application number:
PCT/EP2010/058194

(22) Date of filing: **11.06.2010**

(87) International publication number:
WO 2010/145991 (23.12.2010 Gazette 2010/51)

(54) **PHENANTHROAZOLE COMPOUNDS AS HOLE TRANSPORTING MATERIALS FOR ELECTRO LUMINESCENT DEVICES**

PHENANTHROAZOLVERBINDUNGEN ALS LOCHTRANSPORTMATERIALIEN FÜR
ELEKTROLUMINESZENTE BAUELEMENTE

COMPOSÉS DE PHÉNANTHROAZOLE COMME MATIÈRES DE TRANSPORT DE TROUS POUR
DES DISPOSITIFS ÉLECTROLUMINESCENTS

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO SE SI SK SM TR**

(30) Priority: **18.06.2009 EP 09163085**

(43) Date of publication of application:
25.04.2012 Bulletin 2012/17

(73) Proprietor: **BASF SE**
67056 Ludwigshafen (DE)

(72) Inventors:
• **SCHILDKNECHT, Christian**
68307 Mannheim (DE)
• **LENNARTZ, Christian**
67105 Schifferstadt (DE)


- **WATANABE, Soichi**
68165 Mannheim (DE)
- **WAGENBLAST, Gerhard**
67157 Wachenheim (DE)
- **MURER, Peter**
CH-4104 Oberwil (CH)
- **SCHÄFER, Thomas**
CH-4410 Liestal (CH)
- **CHEBOTAREVA, Natalia**
F-68220 Hagenthal le Bas (FR)
- **RICCI, Andrea**
CH-8048 Zürich (CH)
- **BARDON, Kristina**
79761 Waldshut (DE)

(56) References cited:
WO-A1-2008/031743 WO-A1-2008/119666
JP-A- 2001 023 777 JP-A- 2001 118 683

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).


Description

[0001] The present invention relates to electroluminescent devices, comprising a compound of the formula




as a component of the hole transporting/injecting and/or electron blocking layer. The compounds of formula I may function alone, or in combination with dopants to provide improved efficiency, driving voltage and/or lifetime of electroluminescent devices.

[0002] JP9013025 relates to an electroluminescent element a quinoxaline derivative represented by the formula




wherein X is a C₂-C₅alkyl or the like; and R₁ to R₈, which are independent of each other, are each H, a halogen, a C₁-C₆alkyl or the like.

[0003] JP11251063 discloses triphenylene compounds expressed by the formula




which are used as a component material of an organic EL element. In the formula, R₁ to R₁₂ each independently represent an hydrogen atom, a halogen atom, a hydroxyl group, a substituted or unsubstituted amino group, a nitro group, a cyano group, a substituted or unsubstituted alkyl group, a substituted or unsubstituted alkenyl group, a substituted or unsubstituted cycloalkyl group, a substituted or unsubstituted alkoxy group, a substituted or unsubstituted aromatic hydrocarbon group, a substituted or unsubstituted aromatic heterocycle group, a substituted or unsubstituted aralkyl group, a substituted or unsubstituted aryloxy group, a substituted or unsubstituted alkoxy carbonyl group, or a carboxyl group. R₁ to R₁₂ may form two rings out of them.

[0004] JP2006143845 relates to compounds of formula




wherein Z_1 , Z_2 are an aromatic hydrocarbon ring, aromatic heterocyclic ring; R_1 to R_3 are H, substituent; $n_1 = 0$ to 3 ; n_2 , $n_3 = 0$ to 4 ; L_1 = linkage group, single bond).

[0005] JP2134644 relates to an electrophotographic sensitive body having a phenazine compound in a photosensitive layer. The phenazine compound is expressed by formula




wherein each R_1 - R_4 is an H atom, a (substituted)alkyl group, aralkyl group, aryl group, or heterocyclic group, wherein R_1 and R_2 , and R_3 and R_4 may form a 5-7 membered ring together with an N atom, respectively; each R_5 - R_7 is an H atom, (substituted)alkyl group, alkoxy group, halogen atom or nitro group.

[0006] US20060289882 relates to an organic electroluminescent device, wherein the electron extracting layer may be formed of a hexaazatriphenylene derivative represented by the following structural formula



wherein R represents hydrogen, an alkyl group having a carbon number of 1 to 10, an alkyloxy group having a carbon number of 1 to 10, a dialkylamine group having a carbon number of 1 to 10, F, Cl, Br, I or CN.


US20070029927 discloses aromatic amine derivative represented by the following general formula (1):



wherein Ar_1 to Ar_4 each independently represents a substituted or unsubstituted aryl group having 6 to 30 ring carbon atoms or a substituted or unsubstituted heteroaryl group having 5 to 30 ring carbon atoms;


L_1 and L_2 each independently represents a single bond, a substituted or unsubstituted arylene group having 6 to 30 ring carbon atoms or a substituted or unsubstituted heteroarylene group having 5 to 30 ring carbon atoms; when both L_1 and L_2 are single bonds, however, a case where both Ar_1 and Ar_3 each represents a substituted or unsubstituted phenyl group and further, where both Ar_2 and Ar_4 each represents a substituted or unsubstituted biphenyl group or a substituted or unsubstituted phenyl group is excluded; R represents a substituent and when R exists two or more, they may bond each other to form a ring; and n represents an integer of 0 to 8 and their use in organic electroluminescence devices.

[0007] JP2134644 relates to phenazine compounds of formula




wherein each of R_1 - R_4 is an H atom, a (substituted)alkyl group, aralkyl group, aryl group, or heterocyclic group, wherein R_1 and R_2 , and R_3 and R_4 may form a 5-7 membered ring together with an N atom, respectively; each of R_5 - R_7 is an H atom, (substituted)alkyl group, alkoxy group, halogen atom or nitro group. When the phenazine compounds are incorporated into a photosensitive layer of an electrophotographic sensitive body.

[0008] JP2000323278 relates to an emitter including an organic phosphor having an imidazole structure of the formula



wherein R_1 may be either same or different respectively and selected from hydrogen, an alkyl group, a cycloalkyl group, an aralkyl group, an alkenyl group, a cycloalkenyl group, etc., X_1 is a bonding unit and selected from a substituted or non-substituted aromatic ring, heterocycle, a saturated fat chain, etc., Y_1 is selected from a single bond or a combination of either of single bond, an alkyl chain, an alkylene chain, an ether chain, etc., and Ar is selected from a substituted or non-substituted aromatic ring, heterocycle, etc. and z expresses a natural number. The organic phosphor is preferably a light emitting material having a guest material doped in a host material.


[0009] JP 2001023777 describes compounds of the formula




wherein R_1 to R_9 represent bonding, hydrogen, an alkyl group, a cycloalkyl group, an aralkyl group, an alkenyl group, a cycloalkenyl group, an alkoxy group, an alkylthio group, an arylother group, an aryl thioether group, an aryl group, a heterocyclic group, halogen, a cyano group, an aldehyde group, a carbonyl group, an ester group, a carbamoyl group, an amino group, a nitro group, a silyl group, a siloxyanyl group, and ring structure formed between adjacent substituting

groups, and Z_1 represents oxygen, sulfur, nitrogen, or saturated hydrocarbon. The compounds having a phenanthroazole skeleton are suitable as a host material or a dopant material in a material of a hole transport layer, an electron transport layer, and a luminescent layer. No compounds, wherein any of R_1 to R_9 is an aryl substituted amino group are disclosed.


[0010] JP2001118683 relates to a luminescent element, wherein the luminescent material is at least composed of a guest material and a host material and the peak of the emission spectrum of the host material is more than 300 nm and less than 460 nm. The following phenanthroazole compound is explicitly disclosed:




[0011] JP2002050473 describes an element, in which a light emitting substance exists between a positive electrode and a negative electrode and which emits light by electric energy, and the element contains at least one kind of product formed by a photoreaction. The following phenanthroazole compound is explicitly disclosed:




[0012] JP2003059670 describes a light-emitting element having a structure in which at least a positive electrode, a luminous layer, an electron carrier layer, and a negative electrode are laminated in order, the electron carrier layer has an ionization potential 0.1 eV or more larger than the ionization potential of the luminous layer, and the material that mainly constitutes the luminous layer and the electron carrier layer is made of an organic compound having sublimation performance, and further, the organic compound that mainly constitutes the electron carrier layer has a molecular weight of 400 or more and a glass transition temperature of 90 °C or more. The following phenanthroazole compound is explicitly disclosed:



[0013] JP2002367786 describes a luminous element having a sequentially laminated structure of at least a positive electrode, a luminous layer, a hole transport layer, an electron transport layer and a negative electrode, the relation between the luminous layer and the electron transport layer is $(Ip(ETL)-Ip(EML)) > (Ea(ETL)-Ea(EML))$. The main material composing the luminous layer and the electron transport layer is made of an organic compound with sublimatic nature, and the main material composing the electron transport layer is an organic compound with molecular mass of not less than 400. [Ea: electron affinity (eV), Ip: ionization potential (eV), EML: luminous layer, and ETL: electron transport layer]. The following phenanthroazole compound is explicitly disclosed:




[0014] WO08/031743 describes electroluminescent devices, comprising a compound of the formula



especially as host for phosphorescent compounds. The hosts may function with phosphorescent materials to provide improved efficiency, stability, manufacturability, or spectral characteristics of electroluminescent devices.

[0015] Notwithstanding these developments, there remains a need for EL devices comprising materials for hole transporting materials that will function to provide improved efficiency, stability, manufacturability, or spectral characteristics of electroluminescent devices, especially as an material for an electron blocking layer and/or an optionally doped hole transporting/injecting layer, which provides improved efficiency, driving voltage and/or lifetime.

[0016] Accordingly, the present invention provides an electroluminescent (EL) device, comprising an anode, a hole transporting/injecting layer, optionally an electron blocking layer, a light-emitting layer, optionally a hole- or exciton-blocking layer, an electron-transporting layer, and a cathode, characterized in that the hole transporting/injecting layer and/or the electron blocking layer comprises a compound of the formula




wherein R_1 and R_4 are independently of each other hydrogen, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E

and/or interrupted by D, C₁-C₁₈perfluoroalkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, CN, or -CO-R²⁸,





R², R³, R⁵ and R⁶ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₁-C₁₈perfluoroalkyl, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, C₇-C₂₅aralkyl, CN, or -CO-R²⁸,

R⁸ is C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₁-C₁₈perfluoroalkyl, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, or C₂-C₂₀heteroaryl which is substituted by G,


R⁹ is H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₁-C₁₈perfluoroalkyl, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, or C₂-C₂₀heteroaryl which is substituted by G, two substituents R² and R³, and/or R⁵ and R⁶, which are adjacent to each other, together form a group




R¹⁰⁵, R¹⁰⁶, R¹⁰⁷, R¹⁰⁸, R^{106'} and R^{108'} are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, and A¹, A², A^{1'} and A^{2'} are independently of each other a group of formula



or



or A¹ and A^{1'}, and/or A² and A^{2'} together with the nitrogen atom to which they are bonded form a heteroaromatic ring, or ring system, such as



m' is 0, 1, or 2;

m can be the same or different at each occurrence and is 0, 1, 2, or 3, especially 0, 1, or 2, very especially 0, or 1; R⁴¹ can be the same or different at each occurrence and is Cl, F, CN, N(R⁴⁵)₂, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, a C₁-C₂₅alkoxy group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -NR⁴⁵-, -O-, -S-, or -C(=O)-O-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by one or more non-aromatic groups R⁴¹, or two or more groups R⁴¹ form a ring system;

R⁴⁵ is H, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -NR⁴⁵-, -O-, -S-, -C(=O)-O-, or -O-C(=O)-O-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by one or more non-aromatic groups R⁴¹, and

R^{45'} is H, a C₁-C₂₅alkyl group, or a C₄-C₁₈cycloalkyl group,

R^{65'} is H, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -O-, or -S-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by G,

R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, halogen, -CN, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, C₇-C₂₅aralkyl, -C(=O)-R^{127'}, -C(=O)OR^{127'}, or -C(=O)NR^{127'}R¹²⁶, or substituents R¹¹⁶, R¹¹⁷ and R^{117'}, which are adjacent to each other, can form a ring,

R¹¹⁹ and R¹²⁰ are independently of each other C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, or C₇-C₂₅aralkyl, or

R¹¹⁹ and R¹²⁰ together form a group of formula =CR¹²¹R¹²², wherein

R¹²¹ and R¹²² are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, or C₂-C₂₀heteroaryl, or C₂-C₂₀heteroaryl which is substituted by G, or

R¹¹⁹ and R¹²⁰ together form a five or six membered ring, which optionally can be substituted by C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, C₇-C₂₅aralkyl, or -C(=O)-R^{127'}, and

R¹²⁶, R¹²⁷ and R^{127'} are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-,

D is -CO-; -COO-; -S-; -SO-; -SO₂-; -O-; -NR²⁵-; -SiR³⁰R³¹-; -POR³²-; -CR²³=CR²⁴-; or -C≡C-; and

E is -OR²⁹; -SR²⁹; -NR²⁵R²⁶; -COR²⁸; -COOR²⁷; -CONR²⁵R²⁶; -CN; or halogen; G is E, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is interrupted by D, C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, wherein

R²³ and R²⁴ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-;

R²⁵ and R²⁶ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-; or

R²⁵ and R²⁶ together form a five or six membered ring, R²⁷ and R²⁸ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-;

R²⁹ is C₆-C₁₈aryl; C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-;

R³⁰ and R³¹ are independently of each other C₁-C₁₈alkyl, C₆-C₁₈aryl, or C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl, and

R³² is C₁-C₁₈alkyl, C₆-C₁₈aryl, or C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl.

[0017] The compounds of formula I are used alone, or in combination with other materials as material (component) for the hole transporting layer of electroluminescent devices in organic light emitting diodes (OLEDs). The compounds of formula I may function alone, or in combination with dopants to provide improved efficiency, driving voltage and/or lifetime of electroluminescent devices.

[0018] Alternatively, the compounds of formula I can be used as material for the electron blocking layer. The compounds of formula I may function alone, to provide improved efficiency, driving voltage and/or lifetime of electroluminescent devices.

[0019] The term "hole transporting/injecting layer" as herein employed refers to a layer which is positioned between a light-emitting layer and an anode, preferably adjacent to the anode, and mainly injects/transportes holes.

[0020] Preferably, R¹¹⁶ and R¹¹⁷ are independently of each other H, C₁-C₁₂alkyl, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, or n-heptyl, C₁-C₁₂alkyl which is substituted by E and/or interrupted by D, such as -CH₂OCH₃, -CH₂OCH₂CH₃, -CH₂OCH₂CH₂OCH₃, or -CH₂OCH₂CH₂OCH₂CH₃, C₆-C₁₄aryl, such as phenyl, naphthyl, or biphenyl, C₅-C₁₂cycloalkyl, such as cyclohexyl, C₆-C₁₄aryl which is substituted by G, such as -C₆H₄OCH₃, -C₆H₄OCH₂CH₃, -C₆H₃(OCH₃)₂, or -C₆H₃(OCH₂CH₃)₂, -C₆H₄CH₃, -C₆H₃(CH₃)₂, -C₆H₂(CH₃)₃, or -C₆H₄tBu.

Preferably, R¹¹⁹ and R¹²⁰ are independently of each other C₁-C₁₂alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, C₁-C₁₂alkyl which is substituted by E and/or interrupted by D, such as -CH₂(OCH₂CH₂)_wOCH₃, w = 1, 2, 3, or 4, C₆-C₁₄aryl, such as phenyl, naphthyl, or biphenyl, C₆-C₁₄aryl which is substituted by G, such as -C₆H₄OCH₃, -C₆H₄OCH₂CH₃, -C₆H₃(OCH₃)₂, -C₆H₃(OCH₂CH₃)₂, -C₆H₄CH₃, -C₆H₃(CH₃)₂, -C₆H₂(CH₃)₃, or -C₆H₄tBu, or R¹¹⁹ and R¹²⁰ together form a 4 to 8 membered ring, especially a 5 or 6 membered ring, such as cyclohexyl, or cyclopentyl, which can optionally be substituted by C₁-C₈alkyl.

[0021] D is preferably -CO-, -COO-, -S-, -SO-, -SO₂-, -O-, -NR²⁵-, wherein R²⁵ is C₁-C₁₂alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, or sec-butyl, or C₆-C₁₄aryl, such as phenyl, tolyl, naphthyl, or biphenyl.

[0022] E is preferably -OR²⁹; -SR²⁹; -NR²⁵R²⁵; -COR²⁸; -COOR²⁷; -CONR²⁵R²⁵; or -CN; wherein R²⁵, R²⁷, R²⁸ and R²⁹ are independently of each other C₁-C₁₂alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, or C₆-C₁₄aryl, such as phenyl, tolyl, naphthyl, or biphenyl, which may optionally be substituted.

[0023] G has the same preferences as E, or is C₁-C₁₈alkyl, especially C₁-C₁₂alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, or is C₁-C₁₈perfluoroalkyl, such, for example, -CF₃.

[0024] Compounds of the formula I are even more preferred, wherein R¹ and R⁴ are hydrogen, R², R³, R⁵ and R⁶ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is interrupted by D, C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is interrupted by D, or C₇-C₂₅aralkyl;

R⁸ is C₁-C₁₈alkyl, C₁-C₁₈alkyl which is interrupted by D; C₁-C₁₈perfluoroalkyl, C₆-C₁₈aryl, which may optionally be substituted by C₁-C₁₈alkyl, C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy, which is interrupted by D;

R⁹ is H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is interrupted by D, C₁-C₁₈perfluoroalkyl, C₆-C₁₈aryl, which may optionally be substituted by C₁-C₁₈alkyl, C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy, which is interrupted by D, wherein D is -CO-; -COO-; -S-; -SO-; -SO₂-; -O-; -NR²⁵-; -CR²³=CR²⁴-; or -C≡C-; wherein

R²³ and R²⁴ are independently of each other H; and

R²⁵ is C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₈alkyl, or C₁-C₈alkoxy; C₁-C₈alkyl; or C₁-C₈alkyl which is interrupted by -O-.

[0025] R⁸ is more preferably C₆-C₁₈aryl, which may optionally be substituted by C₁-C₁₈alkyl, C₁-C₁₈perfluoroalkyl, or C₁-C₁₈alkoxy;


R⁹ is more preferably C₆-C₁₈aryl, which may optionally be substituted by C₁-C₁₈alkyl or C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy which is interrupted by D.

D is -S-, -O-, or -NR²⁵-;

R²⁵ is C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-.


[0026] In a preferred embodiment of the present invention R¹, R², R³, R⁴, R⁵ and R⁶ are hydrogen.

[0027] Examples of




(m' = 2).


[0028] Preferably, A¹, A², A^{1'} and A^{2'} are independently of each other a group of formula




more preferably A¹, A², A^{1'} and A^{2'} are independently of each other a group of formula



A¹ and A^{1'} and/or A² and A^{2'} together with the nitrogen atom to which they are bonded form a group of formula




wherein R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, or C₁-C₁₈alkyl. Specific examples of A¹, A², A^{1'} and A^{2'} are




Preferably, A¹ has the meaning of A², and A^{1'} has the meaning of A^{2'}.

15 **[0029]** In a preferred embodiment the present invention is directed to compounds of formula



wherein A¹ and A^{1'} are independently of each other a group of formula




wherein R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, or C₁-C₁₈alkyl; or A¹ and A^{1'} together with the nitrogen atom to which they are bonded form a group of formula



R⁸ is a group of formula




and
R⁹ is a group of formula




wherein


R¹²⁸, R¹²⁹, R¹³⁰ and R¹³¹ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, or C₁-C₁₈perfluoroalkyl. In said embodiment A¹ and A^{1'} are preferably independently of each other a group of formula





and R⁹ is preferably a group of formula




[0030] In another preferred embodiment the present invention is directed to compounds of formula




wherein A¹ and A^{1'} are independently of each other a group of formula




or A¹ and A^{1'} together with the nitrogen atom to which they are bonded form a group of formula




wherein R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, or C₁-C₁₈alkyl;
R⁸ is a group of formula




and
R⁹ is a group of formula




wherein
R¹²⁸, R¹²⁹, R¹³² and R¹³³ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, or C₁-C₁₈perfluoroalkyl. In said
embodiment A¹ and A^{1'} are preferably independently of each other a group of formula




and R⁹ is preferably a group of formula




[0031] Examples of particularly preferred compounds are compounds A-1 to A-45 shown in claim 10. At present,
compounds of formula




such as, for example, compounds A-1, A-5, A-7, A-11, A-31 and A-35, are most preferred, wherein A¹ and A^{1'} are independently of each other




and R⁹ is




or



[0032] The compounds of the formula I, can, for example, be prepared according to a process, which comprises reacting a compound of formula



wherein X¹⁰ stands for halogen, such as bromo or iodo, preferably iodo, with a compound of formula HNA¹A^{1'}, or



in the presence of a base, such as sodium hydride, potassium carbonate, or sodium carbonate, and a catalyst, such as copper (0) or copper (I) (such as copper, copper-bronze, copper bromide iodide, or copper bromide) in a solvent, such as toluene, dimethyl formamide, or dimethyl sulfoxide, wherein m', A¹, A^{1'}, R¹, R², R³, R⁴, R⁵, R⁶, R⁸, R⁹, R⁴¹ and m are as defined above (WO08/031743). This reaction, referred to as an Ullmann condensation, is described by Yamamoto & Kurata, Chem. and Industry, 737-738 (1981), J. Mater. Chem. 14 (2004) 2516, H. B. Goodbrand et al., J. Org. Chem. 64 (1999) 670 and k. D. Belfield et al., J. Org. Chem. 65 (2000) 4475 using copper as catalyst. Additionally palladium catalysts can be used for the coupling of aryl halogen compounds with amines, as described in M. D. Charles et al., Organic Lett. 7 (2005) 3965, A. F. Littke et. al., Angew. Chem. Int. Ed. 41 (2002) 4176 and literature cited therein.

[0033] The compounds of formula II are known from WO06/097419, or WO08/031743, or can be prepared according, or in analogy to the methods described therein.

[0034] Halogen is fluorine, chlorine, bromine and iodine.

[0035] C₁-C₁₈alkyl is typically linear or branched, where possible. Examples are methyl, ethyl, n-propyl, isopropyl, n-butyl, sec.-butyl, isobutyl, tert.-butyl, n-pentyl, 2-pentyl, 3-pentyl, 2,2-dimethylpropyl, 1,1,3,3-tetramethylpentyl, n-hexyl,

1-methylhexyl, 1,1,3,3,5,5-hexamethylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 1,1,3,3-tetramethylbutyl and 2-ethylhexyl, n-nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, or octadecyl. C₁-C₈alkyl is typically methyl, ethyl, n-propyl, isopropyl, n-butyl, sec.-butyl, isobutyl, tert.-butyl, n-pentyl, 2-pentyl, 3-pentyl, 2,2-dimethyl-propyl, n-hexyl, n-heptyl, n-octyl, 1,1,3,3-tetramethylbutyl and 2-ethylhexyl. C₁-C₄alkyl is typically methyl, ethyl, n-propyl, isopropyl, n-butyl, sec.-butyl, isobutyl, tert.-butyl.


[0036] C₁-C₁₈alkoxy groups are straight-chain or branched alkoxy groups, e.g. methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec-butoxy, tert-butoxy, amyloxy, isoamyloxy or tert-amyloxy, heptyloxy, octyloxy, isooctyloxy, nonyloxy, decyloxy, undecyloxy, dodecyloxy, tetradecyloxy, pentadecyloxy, hexadecyloxy, heptadecyloxy and octadecyloxy. Examples of C₁-C₈alkoxy are methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec.-butoxy, isobutoxy, tert.-butoxy, n-pentyloxy, 2-pentyloxy, 3-pentyloxy, 2,2-dimethylpropoxy, n-hexyloxy, n-heptyloxy, n-octyloxy, 1,1,3,3-tetramethylbutoxy and 2-ethylhexyloxy, preferably C₁-C₄alkoxy such as typically methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec.-butoxy, isobutoxy, tert.-butoxy. The term "alkylthio group" means the same groups as the alkoxy groups, except that the oxygen atom of the ether linkage is replaced by a sulfur atom.

[0037] C₂-C₁₈alkenyl groups are straight-chain or branched alkenyl groups, such as e.g. vinyl, allyl, methallyl, isopropenyl, 2-butenyl, 3-butenyl, isobutenyl, n-penta-2,4-dienyl, 3-methyl-but-2-enyl, n-oct-2-enyl, n-dodec-2-enyl, isododec-enyl, n-dodec-2-enyl or n-octadec-4-enyl.


[0038] C₂-C₁₈alkynyl is straight-chain or branched and preferably C₂-C₈alkynyl, which may be unsubstituted or substituted, such as, for example, ethynyl, 1-propyn-3-yl, 1-butyne-4-yl, 1-pentyne-5-yl, 2-methyl-3-butyne-2-yl, 1,4-pentadiyn-3-yl, 1,3-pentadiyn-5-yl, 1-hexyn-6-yl, cis-3-methyl-2-penten-4-yn-1-yl, trans-3-methyl-2-penten-4-yn-1-yl, 1,3-hexadiyn-5-yl, 1-octyn-8-yl, 1-nonyne-9-yl, 1-decyn-10-yl, or 1-tetracosyn-24-yl.

[0039] C₁-C₁₈perfluoroalkyl, especially C₁-C₄perfluoroalkyl, is a branched or unbranched radical such as for example -CF₃, -CF₂CF₃, -CF₂CF₂CF₃, -CF(CF₃)₂, -(CF₂)₃CF₃, and -C(CF₃)₃.


[0040] The term "cycloalkyl group" is typically C₄-C₁₈cycloalkyl, such as cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclononyl, cyclodecyl, cycloundecyl, cyclododecyl, preferably cyclopentyl, cyclohexyl, cycloheptyl, or cyclooctyl, which may be unsubstituted or substituted. The term "cycloalkenyl group" means an unsaturated alicyclic hydrocarbon group containing one or more double bonds, such as cyclopentenyl, cyclopentadienyl, cyclohexenyl and the like, which may be unsubstituted or substituted. The cycloalkyl group, in particular a cyclohexyl group, can be condensed one or two times by phenyl which can be substituted one to three times with C₁-C₄-alkyl, halogen and cyano. Examples of such condensed cyclohexyl groups are:



or



in particular



wherein R⁵¹, R⁵², R⁵³, R⁵⁴, R⁵⁵ and R⁵⁶ are independently of each other C₁-C₈-alkyl, C₁-C₈-alkoxy, halogen and cyano,

in particular hydrogen.

[0041] Aryl is usually C₆-C₂₄aryl (C₆-C₁₈aryl), which optionally can be substituted, such as, for example, phenyl, 4-methylphenyl, 4-methoxyphenyl, naphthyl, especially 1-naphthyl, or 2-naphthyl, biphenyl, terphenyl, pyrenyl, 2- or 9-fluorenyl, phenanthryl, anthryl, tetracyl, pentacyl, hexacyl, or quaterphenyl, which may be unsubstituted or substituted.

[0042] The term "aralkyl group" is typically C₇-C₂₅aralkyl, such as benzyl, 2-benzyl-2-propyl, β-phenyl-ethyl, α,α-dimethylbenzyl, ω-phenyl-butyl, ω,ω-dimethyl-ω-phenyl-butyl, ω-phenyl-dodecyl, ω-phenyl-octadecyl, ω-phenyl-eicosyl or ω-phenyl-docosyl, preferably C₇-C₁₈aralkyl such as benzyl, 2-benzyl-2-propyl, β-phenyl-ethyl, α,α-dimethylbenzyl, ω-phenyl-butyl, ω,ω-dimethyl-ω-phenyl-butyl, ω-phenyl-dodecyl or ω-phenyl-octadecyl, and particularly preferred C₇-C₁₂aralkyl such as benzyl, 2-benzyl-2-propyl, β-phenyl-ethyl, α,α-dimethylbenzyl, ω-phenyl-butyl, or ω,ω-dimethyl-ω-phenyl-butyl, in which both the aliphatic hydrocarbon group and aromatic hydrocarbon group may be unsubstituted or substituted.

[0043] Heteroaryl is typically C₂-C₂₀heteroaryl, i.e. a ring with five to seven ring atoms or a condensed ring system, wherein nitrogen, oxygen or sulfur are the possible hetero atoms, and is typically an unsaturated heterocyclic group with five to 30 atoms having at least six conjugated π-electrons such as thienyl, benzo[b]thienyl, dibenzo[b,d]thienyl, thianthrenyl, furyl, furfuryl, 2H-pyran, benzofuran, isobenzofuran, dibenzofuran, phenoxythienyl, pyrrolyl, imidazolyl, pyrazolyl, pyridyl, bipyridyl, triazinyl, pyrimidinyl, pyrazinyl, pyridazinyl, indolizyl, isoindolyl, indolyl, indazolyl, purinyl, quinolizyl, chinolyl, isochinolyl, phthalazinyl, naphthyridinyl, chinoxalyl, chinazolyl, cinnolyl, pteridinyl, carbazolyl, carbolinyl, benzotriazolyl, benzoxazolyl, phenanthridinyl, acridinyl, pyrimidinyl, phenanthrolinyl, phenazinyl, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl or phenoxazinyl, which can be unsubstituted or substituted.

[0044] Possible substituents of the above-mentioned groups are C₁-C₈alkyl, a hydroxyl group, a mercapto group, C₁-C₈alkoxy, C₁-C₈alkylthio, halogen, halo-C₁-C₈alkyl, a cyano group, an aldehyde group, a ketone group, a carboxyl group, an ester group, a carbamoyl group, an amino group, a nitro group or a silyl group. Preferred substituents of the above-mentioned groups are C₁-C₈alkyl, C₁-C₈alkoxy, C₁-C₈alkylthio, and a cyano group.

[0045] If a substituent, such as, for example R⁴¹ occurs more than one time in a group, it can be different in each occurrence.

[0046] The wording "substituted by G" means that one, or more, especially one to three substituents G might be present.

[0047] As described above, the aforementioned groups may be substituted by E and/or, if desired, interrupted by D. Interruptions are of course possible only in the case of groups containing at least 2 carbon atoms connected to one another by single bonds; C₆-C₂₄aryl is not interrupted; interrupted arylalkyl or alkylaryl contains the unit D in the alkyl moiety. C₁-C₁₈alkyl substituted by one or more E and/or interrupted by one or more units D is, for example, (CH₂CH₂O)₁₋₉-R^x, where R^x is H or C₁-C₁₀alkyl or C₂-C₁₀alkanoyl (e.g. CO-CH(C₂H₅)C₄H₉), CH₂-CH(OR^y)-CH₂-O-R^y, where R^y is C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl, phenyl, C₇-C₁₅phenylalkyl, and R^y embraces the same definitions as R^y or is H; C₁-C₈alkylene-COO-R^z, e.g. CH₂COOR^z, CH(CH₃)COOR^z, C(CH₃)₂COOR^z, where R^z is H, C₁-C₁₈alkyl, (CH₂CH₂O)₁₋₉-R^x, and R^x embraces the definitions indicated above; CH₂CH₂-O-CO-CH=CH₂; CH₂CH(OH)CH₂-O-CO-C(CH₃)=CH₂.

General Device Architecture

[0048] The compounds of formula I can be employed in many OLED device configurations using small molecule materials, oligomeric materials, polymeric materials, or combinations thereof. These include very simple structures comprising a single anode and cathode to more complex devices, such as passive matrix displays comprised of orthogonal arrays of anodes and cathodes to form pixels, and active-matrix displays where each pixel is controlled independently, for example, with thin film transistors (TFTs).

[0049] The organic light-emitting device of the present invention has a pair of electrodes composed of an anode and a cathode, and layers each containing an organic compound including at least a light-emitting layer and a hole-transporting/injecting layer, disposed between the pair of electrodes.

[0050] A first constitution comprises sequentially on the substrate, the anode, the hole-transporting/injecting layer, the light-emitting layer, the electron-transporting layer, and the cathode. In this constitution, a carrier-transporting function and a light-emitting function are separated from each other, and a region in which holes and electrons recombine is present in the light-emitting layer.

[0051] A second constitution differs from the above first constitution in that the hole-transporting/injecting layer comprises a hole injecting layer and a hole-transporting layer. The layer has an improving effect on hole injection property, and is effective for reducing the drive voltage.

[0052] A third constitution differs from the above first constitution in that a layer (hole-blocking layer) for inhibiting holes from penetrating toward the cathode side is further provided between the light-emitting layer and the electron-transporting layer. The constitution is effective for an improvement in emission efficiency when a compound having a large ionization potential (that is, a deep HOMO) is used in the hole-blocking layer.

[0053] The compounds of formula I can be employed as a component of the hole transport/injecting layer. It is preferable that the compounds of formula I as a main component of the hole-transporting layer facilitates injection of holes from an anode and has an excellent mobility for transporting the injected holes to a light-emitting layer.

[0054] Alternatively, the compounds of formula I can be employed as a component of the electron blocking layer.

[0055] A typical structure, especially useful for of a small molecule device, is comprised of a substrate, an anode, a hole transporting/injecting layer, optionally an electron blocking layer, a light-emitting layer, optionally a hole- or exciton-blocking layer, an electron-transporting layer, and a cathode. A preferred structure, especially useful for of a small molecule device, is comprised of a substrate, an anode, a hole transporting/injecting layer, an electron blocking layer, a light-emitting layer, a hole-blocking layer, an electron-transporting layer, and a cathode.

[0056] These layers are described in detail below. Note that the substrate may alternatively be located adjacent to the cathode, or the substrate may actually constitute the anode or cathode. The organic layers between the anode and cathode are conveniently referred to as the organic EL element. Also, the total combined thickness of the organic layers is desirably less than 500 nm.

Host Materials for Phosphorescent Materials

[0057] The compounds of formula I can also be used in organic light emitting diodes (OLEDs) as hosts for phosphorescent compounds. Reference is made to WO08/031743.

[0058] Suitably, the light-emitting layer of the OLED device comprises a host material and one or more guest materials for emitting light. The light-emitting guest material(s) is usually present in an amount less than the amount of host materials and is typically present in an amount of up to 15 wt % of the host, more typically from 0.1 to 10 wt % of the host, and commonly from 5 to 10% of the host. For convenience, the phosphorescent complex guest material may be referred to herein as a phosphorescent material. The emissive layer may comprise a single material, that combines transport and emissive properties. Whether the emissive material is a dopant or a major constituent, emissive layer may comprise other materials, such as dopants that tune the emission of the emissive layer. The emissive layer may include a plurality of emissive materials capable of, in combination, emitting a desired spectrum of light.

[0059] The host material useful in the invention may be used alone or in combination with other host materials. The host materials should be selected so that the triplet exciton can be transferred efficiently from the host material to the phosphorescent material. Suitable host materials are described in WO00/70655; WO01/39234; WO01/93642; WO02/074015; WO02/15645, US20020117662 and WO08/031743. Suitable hosts include certain aryl amines, triazoles, indoles and carbazole compounds. Examples of hosts are 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (α -NPD), 4,4'-N,N'-dicarbazole-biphenyl (CBP), 2,2'-dimethyl-4,4'-N,N'-dicarbazole-biphenyl, m-(N,N'-dicarbazole)benzene, and poly(N-vinylcarbazole), including their derivatives.

[0060] Desirable host materials are capable of forming a continuous film. The light-emitting layer may contain more than one host material in order to improve the device's film morphology, electrical properties, light emission efficiency, and lifetime. The light emitting layer may contain a first host material that has good hole-transporting properties, and a second host material that has good electron-transporting properties.

Phosphorescent Materials

[0061] Phosphorescent materials may be used alone or, in certain cases, in combination with each other, either in the same or different layers. Examples of phosphorescent and related materials are described in WO00/57676, WO00/70655, WO01/41512, WO02/15645, US2003/0017361, WO01/93642, WO01/39234, US6,458,475, WO02/071813, US6,573,651, US2002/0197511, WO02/074015, US6,451,455, US2003/0072964, US2003/0068528, US6,413,656, 6,515,298, 6,451,415, 6,097,147, US2003/0124381, US2003/0059646, US2003/0054198, EP1239526, EP1238981, EP1244155, US2002/0100906, US2003/0068526, US2003/0068535, JP2003073387, JP2003073388, US2003/0141809, US2003/0040627, JP2003059667, JP2003073665 and US2002/0121638.

The emission wavelengths of cyclometallated Ir(III) complexes of the type

[0062] IrL_3 and $\text{IrL}_2\text{L}'$, such as the green-emitting fac-tris(2-phenylpyridinato-N,C^{2'})iridium(III) and bis(2-phenylpyridinato-N,C^{2'})iridium(III) (acetylacetonate) may be shifted by substitution of electron donating or withdrawing groups at appropriate positions on the cyclometallating ligand L, or by choice of different heterocycles for the cyclometallating ligand L. The emission wavelengths may also be shifted by choice of the ancillary ligand L'. Examples of red emitters are the bis(2-(2'-benzothienyl)pyridinato-N,C^{3'})iridium(III)(acetylacetonate), iridium(III)bis(2-methyldibenzo[f,h]quinoxaline) (acetylacetonate), and tris(1-phenylisoquinolinato-N,C)iridium(III). A blue-emitting example is bis(2-(4,6-difluorophenyl)-pyridinato-N,C^{2'})iridium(III)(picolinate).

[0063] Red electrophosphorescence has been reported, using bis(2-(2'-benzo[4,5-a]thienyl)pyridinato-N, C^{3'})irid-

ium(acetylacetonate)[Btp₂Ir(acac)] as the phosphorescent material (Adachi, C., Lamansky, S., Baldo, M. A., Kwong, R. C., Thompson, M. E., and Forrest, S. R., *App. Phys. Lett.*, 78, 1622 1624 (2001).

[0064] Other important phosphorescent materials include cyclometallated Pt(II) complexes such as cis-bis(2-phenylpyridinato-N,C^{2'})platinum(II), cis-bis(2-(2'-thienyl)pyridinato-N,C^{3'}) platinum(II), cis-bis(2-(2'-thienyl)quinolinato-N,C^{5'}) platinum(II), or (2-(4,6-difluorophenyl)pyridinato-NC^{2'}) platinum(II)acetylacetonate. Pt(II)porphyrin complexes such as 2,3,7,8,12,13,17,18-octaethyl-21 H, 23H-porphine platinum(H) are also useful phosphorescent materials.

[0065] Still other examples of useful phosphorescent materials include coordination complexes of the trivalent lanthanides such as Th³⁺ and Eu³⁺ (J. Kido et al, *Appl. Phys. Lett.*, 65, 2124 (1994)).

[0066] Other important phosphorescent materials are described in WO06/000544 and WO08/101842.

Blocking Layers

[0067] In addition to suitable hosts, an OLED device employing a phosphorescent material often requires at least one exciton or hole blocking layer to help confine the excitons or electron-hole recombination centers to the light-emitting layer comprising the host and phosphorescent material, or to reduce the number of charge carriers (electrons or holes). In one embodiment, such a blocking layer would be placed between the electron-transporting layer and the light-emitting layer. In this case, the ionization potential of the blocking layer should be such that there is an energy barrier for hole migration from the host into the electron-transporting layer, while the electron affinity should be such that electrons pass more readily from the electron-transporting layer into the light-emitting layer comprising host and phosphorescent material. It is further desired, but not absolutely required, that the triplet energy of the blocking material be greater than that of the phosphorescent material. Suitable hole-blocking materials are described in WO00/70655 and WO01/93642. Two examples of useful materials are bathocuproine (BCP) and bis(2-methyl-8-quinolinolato)(4-phenylphenolato)aluminum(III) (BALq), which may be doped by, for example, caesium. Metal complexes other than Balq are also known to block holes and excitons as described in US20030068528. US20030175553 describes the use of fac-tris(1-phenylpyrazolato-N,C 2)iridium(III) (Irppz) in an electron/exciton blocking layer. Alternatively, 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (α -NPD) may be used in an electron/exciton blocking layer.

[0068] Alternatively, the compounds of formula I can be used as material for the electron blocking layer. The compounds of formula I may function alone, to provide improved efficiency, driving voltage and/or lifetime of electroluminescent devices.

Substrate

[0069] The substrate can either be light transmissive or opaque, depending on the intended direction of light emission. The light transmissive property is desirable for viewing the EL emission through the substrate. Transparent glass or plastic is commonly employed in such cases. The substrate can be a complex structure comprising multiple layers of materials. This is typically the case for active matrix substrates wherein TFTs are provided below the OLED layers. It is still necessary that the substrate, at least in the emissive pixilated areas, be comprised of largely transparent materials such as glass or polymers. For applications where the EL emission is viewed through the top electrode, the transmissive characteristic of the bottom support is immaterial, and therefore can be light transmissive, light absorbing or light reflective. Substrates for use in this case include, but are not limited to, glass, plastic, semiconductor materials, silicon, ceramics, and circuit board materials. Again, the substrate can be a complex structure comprising multiple layers of materials such as found in active matrix TFT designs. It is necessary to provide in these device configurations a light-transparent top electrode.

Anode

[0070] When the desired electroluminescent light emission (EL) is viewed through the anode, the anode should be transparent or substantially transparent to the emission of interest. Common transparent anode materials used in this invention are indium-tin oxide (ITO), indiumzinc oxide (IZO) and tin oxide, but other metal oxides can work including, but not limited to, aluminum- or indium-doped zinc oxide, magnesium-indium oxide, and nickel-tungsten oxide. In addition to these oxides, metal nitrides, such as gallium nitride, and metal selenides, such as zinc selenide, and metal sulfides, such as zinc sulfide, can be used as the anode. For applications where EL emission is viewed only through the cathode, the transmissive characteristics of the anode are immaterial and any conductive material can be used, transparent, opaque or reflective. Example conductors for this application include, but are not limited to, gold, iridium, molybdenum, palladium, and platinum. Desired anode materials are commonly deposited by any suitable means such as evaporation, sputtering, chemical vapor deposition, or electrochemical means. Anodes can be patterned using well-known photolithographic processes. Optionally, anodes may be polished prior to application of other layers to reduce surface roughness so as to minimize shorts or enhance reflectivity.


Cathode

[0071] When light emission is viewed solely through the anode, the cathode used in this invention can be comprised of nearly any conductive material. Desirable materials have good film-forming properties to ensure good contact with the underlying organic layer, promote electron injection at low voltage, and have good stability. Useful cathode materials often contain a low work function metal (<4.0 eV) or metal alloy. One useful cathode material is comprised of a Mg:Ag alloy wherein the percentage of silver is in the range of 1 to 20%, as described in US-A-4,885,221. Another suitable class of cathode materials includes bilayers comprising the cathode and a thin electron-injection layer (EIL) in contact with an organic layer (e.g., an electron transporting layer (ETL)) which is capped with a thicker layer of a conductive metal. Here, the EIL preferably includes a low work function metal or metal salt, and if so, the thicker capping layer does not need to have a low work function. One such cathode is comprised of a thin layer of LiF followed by a thicker layer of Al as described in US-A-5,677,572. An ETL material doped with an alkali metal, for example, Li-doped Alq, is another example of a useful EIL. Other useful cathode material sets include, but are not limited to, those disclosed in US-A-5,059,861, 5,059,862 and 6,140,763.


[0072] When light emission is viewed through the cathode, the cathode must be transparent or nearly transparent. For such applications, metals must be thin or one must use transparent conductive oxides, or a combination of these materials. Optically transparent cathodes have been described in more detail in US-A-4,885,211, 5,247,190, JP 3,234,963, U.S. Pat. Nos. 5,703,436, 5,608,287, 5,837,391, 5,677,572, 5,776,622, 5,776,623, 5,714,838, 5,969,474, 5,739,545, 5,981,306, 6,137,223, 6,140,763, 6,172,459, EP1076368, US-A-6,278,236 and 6,284,3936. Cathode materials are typically deposited by any suitable method such as evaporation, sputtering, or chemical vapor deposition. When needed, patterning can be achieved through many well known methods including, but not limited to, through-mask deposition, integral shadow masking as described in US-A-5,276,380 and EP0732868, laser ablation, and selective chemical vapor deposition.

Hole Transporting/Injecting Layer (HTL)

[0073] The hole transporting/injecting layer is not limited to a single layer, and two, or more layers, in which at least one layer is made of a compound of formula I may be stacked. If the hole transporting/injecting layer consists of two, or more layers (hole injecting layer/hole transport layer), the compound of formula I is contained in the layer next to the anode (hole injecting layer). The hole transporting/injecting layer of the organic EL device contains at least one compound of formula I. The hole transporting/injecting layer can be formed of a single compound of formula I, or a mixture of compounds of formula I, or a mixture of compounds of formula I with other compounds (so-called "dopants"). hole transporting/injecting layer is preferably a single layer, comprising a compound of formula I and a dopant. The dopant(s) is used in an amount 0.001 to 20 % by weight, especially 1 to 20% by weight based on the weight of compound of formula I and dopant. Examples of dopants are, for example, mentioned in K. Walzer, B. Maennig, M. Pfeiffer, and K. Leo, Chem. Rev. 107 (2007) 1233-1271, EP1596445A1, WO2009/003455A1, DE100357044, WO2008/058525, WO2008/138580, US20080171228 and US2008/0265216. Specific examples of dopants, which can be used in combination of compounds of formula I are: titanium oxide (TiO_x), vanadium oxide (VO_x), especially V₂O₅, molybdenum oxide (MoO_x), especially MoO₃, tungsten oxide (WO_x), especially WO₃, ruthenium oxide (RuO_x), chromium oxide (CrO_x), zirconium oxide (ZrO_x), hafnium oxide (HfO_x), tantalum oxide (TaO_x), silver oxide (AgO_x), manganese oxide (MnO_x), iron trichloride (FeCl₃), antimony pentachloride (SbCl₅), metal phthalocyanine compounds as described in WO2008/058525, dicyano(phthalocyanato(-1)cobalt(III)), the oxocarbon-, pseudooxocarbon- and radialene compounds described in US2008/0265216, dicyano(phthalocyanato(-1)ruthenium(III)) as described in WO2008/138580, especially MO₃, 2-(6-dicyanomethylene-1,3,4,5,7,8-hexafluoro-6H-naphthalen-2-ylidene)-malononitrile,



2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F₄-TCNQ),



and

[0074] Specifically, one may employ especially MoO_3 as dopant of the hole transporting/injecting layer in an amount of 1 to 20 % by weight based on the weight of compound of formula I and dopant. Alternatively, one can employ a mixture of compounds of formula I with 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane ($\text{F}_4\text{-TCNQ}$) as dopant in an amount 1 to 20% by weight based on the weight of compound of formula I and dopant.

[0075] Doping of the respective compound of formula I (matrix material) with the dopants to be used according to the present invention may be produced by one or a combination of the following methods: a) mixed evaporation under vacuum with one source for the matrix material and one for the dopant; b) sequential deposition of the matrix material and dopant with subsequent in-diffusion of the dopant by heat treatment; c) doping of a matrix material layer by a solution of dopant with subsequent evaporation of the solvent by heat treatment; and d) superficial doping of a matrix material layer by a layer of dopant applied to the surface.

[0076] Alternative materials for use in the hole-injecting layer include porphyrinic compounds as described in US-A-4,720,432, plasma-deposited fluorocarbon polymers as described in US-A-6,208,075, and some aromatic amines, for example, m-MTDATA (4,4',4"-tris[(3-methylphenyl)phenylamino]triphenylamine). Alternative hole-injecting materials reportedly useful in organic EL devices are described in EP0891121 and EP1029909.

[0077] As an alternative substance for the hole transporting layer the following aromatic amine compounds can be used for example: 4,4'-bis[N-(1-naphthyl)-N-phenylamino]biphenyl (abbreviation: NPB); N,N'-bis(3-methylphenyl)-N,N'-diphenyl-[1,1'-biphenyl]-4,4'-diamine (ab-breviation TPD); 4,4',4"-tris(N,N-diphenylamino)triphenylamine (abbreviation TDATA); 4,4',4"-tris[N-(3-methylphenyl)-N-phenylamino]triphenylamine (abbreviation MTDATA); and 4,4'-bis[N-(spiro-9,9'-bifluoren-2-yl)-N-phenylamino]biphenyl (abbreviation: BSPB).


Fluorescent Light-Emitting Materials and Layers (LEL)

[0078] In addition to the phosphorescent materials, other light emitting materials may be used in the OLED device, including fluorescent materials. Although the term "fluorescent" is commonly used to describe any light emitting material, in this case we are referring to a material that emits light from a singlet excited state. Fluorescent materials may be used

in the same layer as the phosphorescent material, in adjacent layers, in adjacent pixels, or any combination. Care must be taken not to select materials that will adversely affect the performance of the phosphorescent materials. One skilled in the art will understand that triplet excited state energies of materials in the same layer as the phosphorescent material or in an adjacent layer must be appropriately set so as to prevent unwanted quenching. As more fully described in US-A-4,769,292 and 5,935,721, the light-emitting layer (LEL) of the organic EL element includes a luminescent fluorescent or phosphorescent material where electroluminescence is produced as a result of electron-hole pair recombination in this region. The light-emitting layer can be comprised of a single material, but more commonly consists of a host material doped with a guest emitting material or materials where light emission comes primarily from the emitting materials and can be of any color. The host materials in the light-emitting layer can be an electron-transporting material, as defined below, a hole-transporting material, as defined above, or another material or combination of materials that support hole-electron recombination. Fluorescent emitting materials are typically incorporated at 0.01 to 10% by weight of the host material. The host and emitting materials can be small non-polymeric molecules or polymeric materials such as polyfluorenes and polyvinylarylenes (e.g., poly(p-phenylenevinylene), PPV). In the case of polymers, small molecule emitting materials can be molecularly dispersed into a polymeric host, or the emitting materials can be added by copolymerizing a minor constituent into a host polymer. Host materials may be mixed together in order to improve film formation, electrical properties, light emission efficiency, lifetime, or manufacturability. The host may comprise a material that has good hole-transporting properties and a material that has good electron-transporting properties.

[0079] Host and emitting materials known to be of use include, but are not limited to, those disclosed in US-A-4,768,292, 5,141,671, 5,150,006, 5,151,629, 5,405,709, 5,484,922, 5,593,788, 5,645,948, 5,683,823, 5,755,999, 5,928,802, 5,935,720, 5,935,721, and 6,020,078.

[0080] Metal complexes of 8-hydroxyquinoline and similar derivatives (Formula E) constitute one class of useful host compounds capable of supporting electroluminescence, and are particularly suitable for light emission of wavelengths longer than 500 nm, e.g., green, yellow, orange, and red.



wherein M represents a metal; v is an integer of from 1 to 4; and ZZ independently in each occurrence represents the atoms completing a nucleus having at least two fused aromatic rings. From the foregoing it is apparent that the metal can be monovalent, divalent, trivalent, or tetravalent metal. The metal can, for example, be an alkali metal, such as lithium, sodium, or potassium; an alkaline earth metal, such as magnesium or calcium; an earth metal, such as aluminum or gallium, or a transition metal such as zinc or zirconium. Generally any monovalent, divalent, trivalent, or tetravalent metal known to be a useful chelating metal can be employed. ZZ completes a heterocyclic nucleus containing at least two fused aromatic rings, at least one of which is an azole or azine ring. Additional rings, including both aliphatic and aromatic rings, can be fused with the two required rings, if required. To avoid adding molecular bulk without improving on function the number of ring atoms is usually maintained at 18 or less.

[0081] Illustrative of useful chelated oxinoid compounds are the following:

- CO-1: Aluminum trisoxine [alias, tris(8-quinolinolato)aluminum(III)]
- CO-2: Magnesium bisoxine [alias, bis(8-quinolinolato)magnesium(II)]
- CO-3: Bis[benzo{f}-8-quinolinolato]zinc(II)
- CO-4: Bis(2-methyl-8-quinolinolato)aluminum(III)-μ-oxo-bis(2-methyl-8-quinolinolato)aluminum(III)
- CO-5: Indium trisoxine [alias, tris(8-quinolinolato)indium]
- CO-6: Aluminum tris(5-methyloxine) [alias, tris(5-methyl-8-quinolinolato) aluminum(III)]
- CO-7: Lithium oxine [alias, (8-quinolinolato)lithium(I)]
- CO-8: Gallium oxine [alias, tris(8-quinolinolato)gallium(III)]
- CO-9: Zirconium oxine [alias, tetra(8-quinolinolato)zirconium(IV)]

[0082] Useful fluorescent emitting materials include, but are not limited to, derivatives of anthracene, tetracene, xanthene, perylene, rubrene, coumarin, rhodamine, and quinacridone, dicyanomethylenepyran compounds, thiopyran compounds, polymethine compounds, pyrilium and thiapyrilium compounds, fluorene derivatives, perflanthene derivatives, indenoperylene derivatives, bis(aziny)amine boron compounds, bis(aziny)methane compounds, and carbostyryl compounds. Illustrative examples of useful materials include, but are not limited to, compounds L1 to L52 described in US7,090,930B2.

Electron-Transporting Layer (ETL)

[0083] Preferred thin film-forming materials for use in forming the electron-transporting layer of the organic EL devices of this invention are metal chelated oxinoid compounds, including chelates of oxine itself (also commonly referred to as 8-quinolinol or 8-hydroxyquinoline). Such compounds help to inject and transport electrons and exhibit both high levels of performance and are readily fabricated in the form of thin films. Exemplary of contemplated oxinoid compounds are those satisfying structural formula (E), previously described. Other electron-transporting materials include various butadiene derivatives as disclosed in US4,356,429 and various heterocyclic optical brighteners as described in US4,539,507. Benzazoles satisfying structural formula (G) are also useful electron transporting materials. Triazines are also known to be useful as electron transporting materials. Doping may be used to enhance conductivity. Alq₃ is an example of an intrinsic electron transport layer. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in US 6,337,102.

Deposition of Organic Layers

[0084] The organic materials mentioned above are suitably deposited by any means suitable for the form of the organic materials. In the case of small molecules, they are conveniently deposited through thermal evaporation, but can be deposited by other means such as from a solvent with an optional binder to improve film formation. If the material is soluble or in oligomeric/polymeric form, solution processing is usually preferred e.g. spin-coating, ink-jet printing. Dendrimer substituents may be used to enhance the ability of small molecules to undergo solution processing. Patterned deposition can be achieved using shadow masks, integral shadow masks (US5,294,870), spatially-defined thermal dye transfer from a donor sheet (US5,688,551, 5,851,709 and 6,066,357) and inkjet method (US6,066,357).

Encapsulation


[0085] Most OLED devices are sensitive to moisture or oxygen, or both, so they are commonly sealed in an inert atmosphere such as nitrogen or argon, along with a desiccant such as alumina, bauxite, calcium sulfate, clays, silica gel, zeolites, alkaline metal oxides, alkaline earth metal oxides, sulfates, or metal halides and perchlorates. Methods for encapsulation and desiccation include, but are not limited to, those described in US6,226,890. In addition, barrier layers such as SiO_x, Teflon, and alternating inorganic/polymeric layers are known in the art for encapsulation.

[0086] Devices fabricated in accordance with embodiments of the invention may be incorporated into a wide variety of consumer products, including flat panel displays, computer monitors, televisions, billboards, lights for interior or exterior illumination and/or signalling, fully transparent displays, flexible displays, laser printers, cell phones, personal digital assistants (PDAs), laptop computers, digital cameras, camcorders, viewfinders, micro-displays, vehicles, theatre or stadium screen, or a sign. Various control mechanism may be used to control devices fabricated in accordance with the present invention, including passive matrix and active matrix.

[0087] Various features and aspects of the present invention are illustrated further in the examples that follow. While these examples are presented to show one skilled in the art how to operate within the scope of this invention, they are not to serve as a limitation on the scope of the invention where such scope is only defined in the claims. Unless otherwise indicated in the following examples and elsewhere in the specification and claims, all parts and percentages are by weight, temperatures are in degrees centigrade and pressures are at or near atmospheric.


Examples

Example 1

[0088]

a) 30.0 g (82.0 mmol) 2,7-dibromo-phenanthrene-9,10-dione, 14.1 g (90.2 mmol) 1-naphthalene carboxaldehyde,

15.3 g (164 mmol) aniline and 19.0 g (246 mmol) ammonium acetate in 500 ml glacial acetic acid are refluxed for 4 h under nitrogen. The product is filtered off, washed with glacial acetic acid, water, a sodium hydrogen carbonate solution and water and then decocted in toluene and methyl ethyl ketone.




b) 3.66 g (38.0 mmol) sodium tert-butyrate are added to 10.00 g (17.3 mmol) of the product of example 1a in 200 ml toluene. The reaction mixture is degassed with argon. 190 mg (0.86 mmol) palladium(II) acetate are added. The reaction mixture is degassed with argon. 350 mg (1.73 mmol) tri-tert-butylphosphine are added. A degassed solution of 7.96 g (36.3 mmol) N-phenyl-1-naphthylamine in 40 ml toluene is added. The reaction mixture is stirred for 15 h at 90 °C under argon and is filtered on silica gel with toluene. The solvent is removed in vacuum and the product is crystallized from diethyl ether. The product has a glass transition point of 158 °C.

¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.57 (d, J = 9.2 Hz, 1H), 8.50 (d, J = 9.1 Hz, 1H), 8.41 (d, J = 2.5 Hz, 1H), 8.08 (d, J = 8.4 Hz, 1H), 7.73-7.94 (m, 8H), 6.65-7.53 (m, 30H).

Example 2

[0089]




[0090] The synthesis is carried out in analogy to example 1 b. The product has a melting point of 334 °C.

¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.48 (d, J = 9.2 Hz, 1H), 8.44 (d, J = 9.1 Hz, 1H), 8.29 (d, J = 2.4 Hz, 1 H), 7.82-7.85 (m, 1 H), 7.63-7.68 (m, 2H), 6.77-7.31 (m, 32H).


Example 3

[0091]



3a) 10.0 g (82.0 mmol) 2,7-dibromo-phenanthrene-9,10-dione, 3.19 g (30.1 mmol) benzaldehyde, 5.09 g (54.6 mmol) aniline and 6.32 g (82.0 mmol) ammonium acetate in 150 ml glacial acetic acid are refluxed for 23 h under

nitrogen. The product is filtered off, washed with glacial acetic acid, water, a sodium hydrogen carbonate solution and water, then decocted in isopropanol and filtered on silica gel with toluene.



3b) 2.73 g (28.4 mmol) sodium tert-butyrate are added to 5.00 g (9.46 mmol) of the product of example 3a in 50 ml toluene. The reaction mixture is degassed with argon. 106 mg (0.47 mmol) palladium(II) acetate are added. The reaction mixture is degassed with argon. 0.95 ml (0.95 mmol) of a 1M solution of tri-tert-butylphosphine in toluene are added. A degassed solution of 5.60 g (28.4 mmol) di-p-tolyl-amine is added. The reaction mixture is stirred for 20 h at 100 °C under argon. The reaction mixture is washed with 60 ml 1 % sodium cyanide solution. The organic solvent is removed in vacuum. The product is decocted with ethanol, dissolved in dichloromethane and ethanol is added. The dichloromethane is distilled off. The product is filtered off (melting point: 239 °C).

¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.48 (t, J = 9.6 Hz, 2H), 8.42 (d, J = 2.4 Hz, 2H), 6.46-7.49 (m, 2H), 7.02-7.33 (m, 22H), 6.81-6.87 (m, 5H), 3.36 (s, 6H), 3.33 (s, 6H).

Device fabrication and Application Examples

[0092] Devices are fabricated by thermal evaporation in high vacuum (<10⁻⁶ mbar). The anode consists of ca. 1200 Å of indium tin oxide (ITO) previously deposited on a glass substrate. The cathode consists of 1000 Å of Al. All devices are tested immediately after preparation, without encapsulation, in the nitrogen atmosphere of a glove box (<1 ppm of H₂O and O₂). All materials used are of sublimed quality.

Application Example 1

[0093] The organic stack consists sequentially, from the ITO surface, of 600 Å compound A-11 co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ as hole transport layer, followed by 10 Å compound A-11 as the electron blocking layer. The emissive layer consists of 200 Å of compound A-11 as host doped with 10% of red emitter, iridium(III)bis(2-methyldibenzo[f,h]quinoxaline) (acetylacetonate), followed by 100 Å of BAlq (bis(2-methyl-8-quinolinolato)-4-(phenyl-phenolato)aluminium-(III)) as the hole blocking layer and 600 Å of electron transport material composed of BPhen (4,7 diphenyl-1,10-phenanthroline) doped with 6% Cs.

Application Example 2

[0094] The same as application example 1, except that 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α-NPD) is used as host instead of compound A-11.

Application Example 3

[0095] The same as application example 2, except that 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α-NPD) is used as the electron blocking layer instead of compound A-11.

Application Example 4

[0096] The same as application example 1, except that 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α-NPD) doped with 4F-TCNQ (10:1) is used as hole transport layer instead of compound A-11.

Application Example 5

[0097] The same as application example 4, except that 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α-NPD) is

used as host instead of compound A-11.

Application Example 6

- 5 **[0098]** The same as application example 4, except that 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) is used as the electron blocking layer instead of compound A-11.

Comparative Application Example 1

- 10 **[0099]** The organic stack consisted sequentially, from the ITO surface, of 600 Å 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ as hole transport layer, followed by 100 Å α -NPD as the electron blocking layer. The emissive layer consists of 200 Å of α -NPD as host doped with 10% of red emitter, iridium(III)bis(2methyldibenzo[f,h]quinoxaline) (acetylacetonate), followed by 100 Å of BAlq (bis(2-methyl-8-quinolinolato)-4-(phenyl-phenolato)aluminium-(III) as the hole blocking layer and 600 Å of electron transport material composed of BPhen (4,7 diphenyl-1,10-phenantroline) doped with 6% Cs.


15 **[0100]** The luminous efficiency, along with the onset voltage (@1000 cd/m²) and maximum luminance measured for devices prepared as above is reported in the table below:

	C.Eff@ 1000 [cd/m ²]	V@ 1000 [cd/m ²]	Max Lum/[cd/m ²]	T ₅₀ (4500 cd/m ²) ¹⁾
20 Appl. Ex. 1	13	2.5	18700	1000
Appl. Ex. 2	16	2.8	23300	3300
Appl. Ex. 3	16	2.7	21700	2100
25 Appl. Ex. 4	12	2.5	19000	3300
Appl. Ex. 5	14	2.8	21000	5000
Appl. Ex. 6	16	2.5	20000	1100
30 Comp. Appl. Ex. 1	16	3	24500	3000
¹⁾ Time after which an OLED device with a luminance of 4500 cd/m ² achieves 50% of the initial luminance.				

35 **[0101]** Depending on the device architecture the devices of the present invention have a lower onset voltage and can show a superior lifetime in comparison to the device of the Comparative Application Example 1 at comparable luminous efficiency and maximum luminance.


Example 4

[0102]



a) 5.0 g (13.6 mmol) 2,7-dibromo-phenanthrene-9,10-dione, 2.35 g (15.0 mmol) 2-naphthalene carboxaldehyde, 2.54 g (27.3 mmol) aniline and 3.16 g (41.0 mmol) ammonium acetate in 80 ml glacial acetic acid are refluxed for 18 h under nitrogen. The product is filtered off, washed with glacial acetic acid, water, a sodium hydrogen carbonate solution and water and then decocted in diethyl-ether.

55




b) 1.75 g (18.3 mmol) sodium tert-butoxide are added to 4.80 g (17.3 mmol) of the product of example 4a in 100 ml toluene. 3.82 g (17.4 mmol) N-phenyl-1-naphthylamine are added.

[0103] The reaction mixture is degassed with argon. 93 mg (0.42 mmol) palladium(II) acetate are added. The reaction mixture is degassed with argon. 170 mg (83 mmol) tri-tert-butylphosphine are added. The reaction mixture is degassed with argon. The reaction mixture is stirred for 21 h at 90 °C under argon and is filtered on silica gel with toluene. The solvent is removed in vacuum and the product is decoced in diethyl-ether. Column chromatography on silica gel with toluene/cyclohexane 1/1 and than toluene/cyclohexane 7/3 results in the compound A-43 (yield: 51 %).

¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.52 (d, J = 2.4 Hz, 1H), 8.49 (d, J = 9.3 Hz, 1H), 8.42 (d, J = 9.1 Hz, 1 H), 8.42 (d, J = 9.1 Hz, 1 H), 8.06 (d, J = 8.5 Hz, 1 H), 6.87-7.95 (m, 36H), 6,74 (d, J = 2.3 Hz, 1 H).

Example 5


[0104]



[0105] Cpd. A-5 is prepared in analogy to example 1 b starting from the product of example 3a and N-phenyl-1-naphthylamine. Melting point: 290 °C. ¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.45-8.48 (m, 2H), 8.41 (d, J = 9.1 Hz, 1 H), 8.05 (d, J = 8.5 Hz, 1 H), 7.91 (t, J = 8.8 Hz, 2H), 7.76-7.81 (m, 2H), 7.70 (d, J = 8.5 Hz, 1 H), 7.05-7.53 (m, 23H), 6.85-6.94 (m, 7H), 6.68 (d, J = 2.4 Hz, 1 H).

Example 6

[0106]




[0107] Cpd. A-1 is prepared in analogy to example 1 b starting from the product of example 3a and N,N-diphenylamine. Melting point: 277 °C. ¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.57 (t, J = 9.7 Hz, 2H), 8.49 (d, J = 2.5 Hz, 1 H), 7.48-7.52

(m, 2H), 7.15-7.35 (m, 22H), 7.89-7.06 (m, 9H).

Example 6


[0108]



[0109] Cpd. A-44 is prepared in analogy to example 1 b starting from the product of example 1 a and N-phenyl-2-naphthylamine. Melting point: 268 °C. ¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.63 (d, J = 9.2 Hz, 1 H), 8.59 (d, J = 9.1 Hz, 1 H), 8.45 (d, J = 2.5 Hz, 1 H), 6.88-7.96 (m, 35H), 6.47-6.56 (m, 4H), 7.77-7.82 (m, 2H), 6.80-7.45 (m, 40H).

Example 7


[0110]



[0111] Cpd. A-8 is prepared in analogy to example 1 b starting from the product of example 1 a and N,N-bis(4-methylphenyl)amine. Melting point: 286 °C. ¹H NMR (300 MHz, THF-d₈, ppm): δ = 8.54 (d, J = 9.2 Hz, 1 H), 8.50 (d, J = 9.2 Hz, 1 H), 8.36 (d, J = 2.5 Hz, 1 H), 7.94-7.97 (m, 1H), 7.94-7.97 (m, 2H), 7.77-7.82 (m, 2H), 6.80-7.45 (m, 40H).

Example 8

[0112]



[0113] Cpd. A-45 is prepared in analogy to example 1 b starting from the product of example 1 a and carbazole. Xylene is used as solvent for this reaction. Melting point: 286 °C.

¹H NMR (300 MHz, THF-d₈, ppm): δ = 9.18 (d, J = 2.2 Hz, 1H), 9.09 (d, J = 9.1 Hz, 1H), 9.04 (d, J = 9.0 Hz, 1 H), 8.20 (d, J = 7.7 Hz, 2H), 8.14 (d, J = 7.07 Hz, 2H), 7.05-8.06 (m, 27H).

Application Example 7

[0114] The organic stack consists sequentially, from the ITO surface, of 600 Å compound NPD co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ as hole transport layer, followed by 100 Å compound cpd. A-44 as the electron blocking layer. The emissive layer consists of 200 Å of 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) as host doped with 10% of red emitter, iridium(III)bis(2methyldibenzo[f,h]quinoxaline) (acetylacetonate), followed by 100 Å of BALq (bis(2-methyl-8-quinolinolato)-4-(phenyl-phenolato)aluminium-(III)) as the hole blocking layer and 600 Å of electron transport material composed of BPhen (4,7 diphenyl-1,10-phenantroline) doped with 6% Cs.

Comparative Application Example 2

[0115] The organic stack consisted sequentially, from the ITO surface, of 600 Å 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ as hole transport layer, followed by 100 Å α -NPD as the electron blocking layer. The emissive layer consists of 200 Å of α -NPD as host doped with 10% of red emitter, iridium(III)bis(2methyldibenzo[f,h]quinoxaline) (acetylacetonate), followed by 100 Å of BALq (bis(2-methyl-8-quinolinolato)-4-(phenyl-phenolato)aluminium-(III)) as the hole blocking layer and 600 Å of electron transport material composed of BPhen (4,7 diphenyl-1,10-phenantroline) doped with 6% Cs.

Application Example 8

[0116] The same as comparative example 1, except that cpd. A-44 co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ is used as the hole transport layer instead of 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ.

Application Example 9

[0117] The organic stack consists sequentially, from the ITO surface, of 600 Å compound NPD co-evaporated in a 10:1 evaporation rate ratio with 4F-TCNQ as hole transport layer, followed by 100 Å compound A-2 as the electron blocking layer. The emissive layer consists of 200 Å of 4,4'-bis[N-(1-naphtyl)-N-phenylamino]biphenyl (α -NPD) as host doped with 10% of red emitter, iridium(III)bis(2methyldibenzo[f,h]quinoxaline) (acetylacetonate), followed by 100 Å of BALq (bis(2-methyl-8-quinolinolato)-4-(phenyl-phenolato)aluminium-(III)) as the hole blocking layer and 600 Å of electron transport material composed of BPhen (4,7 diphenyl-1,10-phenantroline) doped with 6% Cs.


[0118] The luminous efficiency, along with the onset voltage (@1000 cd/m²) and maximum luminance measured for devices prepared as above is reported in the table below:

	C.Eff@1000 [cd/m ²]	V@1000 [cd/m ²]	Max Lum/[cd/m ²]	T ₅₀ (4500 cd/m ²) ¹⁾
Appl. Ex. 7	15.1	3.3	20200	1800
Appl. Ex. 8	15.1	2.6	21000	780
Appl. Ex. 9	15.2	3.1	23600	2100
Comp. Appl. Ex. 2	15.6	2.7	21900	840
¹⁾ Time after which an OLED device with a luminance of 4500 cd/m ² achieves 50% of the initial luminance.				

[0119] Depending on the device architecture the devices of the present invention have a lower voltage or can show a superior lifetime in comparison to the device of the Comparative Application Example 2 at comparable luminous efficiency and maximum luminance.

Claims

1. An electroluminescent (EL) device, comprising an anode, a hole transporting/injecting layer, optionally an electron blocking layer, a light-emitting layer, optionally a hole- or exciton-blocking layer, an electron-transporting layer, and a cathode, **characterized in that** the hole transporting/injecting layer and/or the electron blocking layer comprises a compound of the formula




wherein R^1 and R^4 are independently of each other hydrogen, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_1 - C_{18} perfluoroalkyl, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, CN, or $-CO-R^{28}$,

R^2 , R^3 , R^5 and R^6 are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_1 - C_{18} perfluoroalkyl, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by G, C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by G, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, C_7 - C_{25} aralkyl, CN, or $-CO-R^{28}$,

R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_1 - C_{18} perfluoroalkyl, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by G, C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by G,


R^9 is H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_1 - C_{18} perfluoroalkyl, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by G, C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by G, or


two substituents R^2 and R^3 , and/or R^5 and R^6 , which are adjacent to each other, together form a group




R^{105} , R^{106} , R^{107} , R^{108} , $R^{106'}$ and $R^{108'}$ are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_1 - C_{18} alkoxy, or C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, and

A^1 , A^2 , $A^{1'}$ and $A^{2'}$ are independently of each other a group of formula





or A¹ and A^{1'}, and/or A² and A^{2'} together with the nitrogen atom to which they are bonded form a heteroaromatic ring, or ring system, such as



m' is 0, 1, or 2;

m can be the same or different at each occurrence and is 0, 1, 2, or 3, especially 0, 1, or 2, very especially 0, or 1; R⁴¹ can be the same or different at each occurrence and is Cl, F, CN, N(R⁴⁵)₂, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, a C₁-C₂₅alkoxy group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -NR⁴⁵-, -O-, -S-, or -C(=O)-O-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by one or more non-aromatic groups R⁴¹, or two or more groups R⁴¹ form a ring system;

R⁴⁵ is H, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -NR⁴⁵-, -O-, -S-, -C(=O)-O-, or, -O-C(=O)-O-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by one or more non-aromatic groups R⁴¹, and

R^{45'} is H, a C₁-C₂₅alkyl group, or a C₄-C₁₈cycloalkyl group,

R^{65'} is H, a C₁-C₂₅alkyl group, a C₄-C₁₈cycloalkyl group, in which one or more carbon atoms which are not in neighbourhood to each other could be replaced by -O-, or -S-, and/or wherein one or more hydrogen atoms can be replaced by F, a C₆-C₂₄aryl group, or a C₆-C₂₄aryloxy group, wherein one or more carbon atoms can be replaced by O, S, or N, and/or which can be substituted by G,

R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, halogen, -CN, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which

is substituted by E and/or interrupted by D, C₇-C₂₅alkyl, -C(=O)-R^{127'}, -C(=O)OR^{127'}, or -C(=O)NR¹²⁷R¹²⁶, or substituents R¹¹⁶, R¹¹⁷ and R^{117'}, which are adjacent to each other, can form a ring, R¹¹⁹ and R¹²⁰ are independently of each other C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, or C₇-C₂₅aralkyl, or

R¹¹⁹ and R¹²⁰ together form a group of formula =CR¹²¹R¹²², wherein

R¹²¹ and R¹²² are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, or C₂-C₂₀heteroaryl, or C₂-C₂₀heteroaryl which is substituted by G, or

R¹¹⁹ and R¹²⁰ together form a five or six membered ring, which optionally can be substituted by C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by G, C₂-C₂₀heteroaryl, C₂-C₂₀heteroaryl which is substituted by G, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, C₇-C₂₅aralkyl, or -C(=O)-R^{127'}, and R¹²⁶, R¹²⁷ and R^{127'} are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-,

D is -CO-; -COO-; -S-; -SO-; -SO₂-; -O-; -NR²⁵-; -SiR³⁰R³¹-; -POR³²-; -CR²³=CR²⁴-; or -C≡C-; and

E is -OR²⁹; -SR²⁹; -NR²⁵R²⁶; -COR²⁸; -COOR²⁷; -CONR²⁵R²⁶; -CN; or halogen; G is E, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is interrupted by D, C₁-C₁₈perfluoroalkyl, C₁-C₁₈alkoxy, or C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, wherein

R²³ and R²⁴ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-;

R²⁵ and R²⁶ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-; or

R²⁵ and R²⁶ together form a five or six membered ring, R²⁷ and R²⁸ are independently of each other C₆-C₁₈aryl; C₆-C₁₈aryl which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-,


R²⁹ is C₆-C₁₈aryl; C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl, or C₁-C₁₈alkoxy; C₁-C₁₈alkyl; or C₁-C₁₈alkyl which is interrupted by -O-,

R³⁰ and R³¹ are independently of each other C₁-C₁₈alkyl, C₆-C₁₈aryl, or C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl, and


R³² is C₁-C₁₈alkyl, C₆-C₁₈aryl, or C₆-C₁₈aryl, which is substituted by C₁-C₁₈alkyl.

2. The EL device according to claim 1, wherein R¹, R², R³, R⁴, R⁵ and R⁶ are hydrogen.

3. The EL device according to claim 1, or 2, wherein A¹, A^{1'}, A² and A^{2'} are independently of each other a group of formula




or A¹ and A^{1'} together with the nitrogen atom to which they are bonded form a group of formula





wherein R^{116} , R^{117} and $R^{117'}$ are independently of each other H, or C_1 - C_{18} alkyl.

4. The EL device according to any of claims 1 to 3, wherein R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is interrupted by D, C_1 - C_{18} perfluoroalkyl, C_6 - C_{18} aryl, which may optionally be substituted by C_1 - C_{18} alkyl, C_1 - C_{18} perfluoroalkyl, C_1 - C_{18} alkoxy, or C_1 - C_{18} alkoxy which is interrupted by D; R^9 is H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl, which is interrupted by D, C_1 - C_{18} perfluoroalkyl, C_6 - C_{18} aryl, which may optionally be substituted by C_1 - C_{18} alkyl, C_1 - C_{18} perfluoroalkyl, C_1 - C_{18} alkoxy, or C_1 - C_{18} alkoxy which is interrupted by D; D is -O-, -S-, or -NR²⁵-, and R^{25} is C_6 - C_{18} aryl; C_6 - C_{18} aryl which is substituted by C_1 - C_{18} alkyl, or C_1 - C_{18} alkoxy; C_1 - C_{18} alkyl; or C_1 - C_{18} alkyl which is interrupted by -O.


5. The EL device according to any of claims 1 to 4, wherein the compound of formula I is a compound of formula




wherein A^1 and $A^{1'}$ are independently of each other a group of formula




wherein R^{116} , R^{117} and $R^{117'}$ are independently of each other H, or C_1 - C_{18} alkyl; or A^1 and $A^{1'}$ together with the nitrogen atom to which they are bonded form a group of formula



R^8 is a group of formula




and
R⁹ is a group of formula




wherein
R¹²⁸, R¹²⁹, R¹³⁰ and R¹³¹ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, or C₁-C₁₈perfluoroalkyl.


6. The EL device according to any of claims 1 to 4, wherein the compound of formula I is a compound of formula



wherein A¹ and A^{1'} are independently of each other a group of formula




or A¹ and A^{1'} together with the nitrogen atom to which they are bonded form a group of formula




wherein R¹¹⁶, R¹¹⁷ and R^{117'} are independently of each other H, or C₁-C₁₈alkyl;

R⁸ is a group of formula




and
R⁹ is a group of formula























































wherein R¹²⁸, R¹²⁹, R¹³² and R¹³³ are independently of each other H, C₁-C₁₈alkyl, C₁-C₁₈alkoxy, or C₁-C₁₈perfluoroalkyl.

7. The EL device according to any of claims 1 to 6, wherein the compound of formula I is a compound of formula



Cpd.	A ¹	A ^{1'}	R ⁸	R ⁹
A-1				
A-2				
A-3				
A-4				
A-5				
A-6				

(continued)

Cpd.	A ¹	A ^{1'}	R ⁸	R ⁹
A-7				
A-8				
A-9				
A-10				
A-11				
A-12				
A-13				
A-14				
A-15				
A-16				
A-17				
A-18				
A-19				







(continued)

Cpd.	A ¹	A ^{1'}	R ⁸	R ⁹
A-20				
A-21				
A-22				
A-23				
A-24				
A-25				
A-26				
A-27				
A-28				
A-29				
A-30				
A-31				
A-32				



(continued)

Cpd.	A ¹	A ^{1'}	R ⁸	R ⁹
A-33				
A-34				
A-35				
A-36				
A-37				
A-38				
A-39				
A-40				
A-41				
A-42				
A-43				


(continued)


Cpd.	A ¹	A ^{1'}	R ⁸	R ⁹
A-44				
A-45	¹⁾	¹⁾		
 ¹⁾ -NA ¹ A ^{1'} is				

8. The EL device according to any of claims 1 to 7, wherein the hole transporting/injecting layer comprises a compound of formula I and a dopant, wherein the dopant is selected from titanium oxide (TiO_x), vanadium oxide (VO_x), molybdenum oxide (MoO₃), especially MO₃, tungsten oxide (WO_x), ruthenium oxide (RuO_x), chromium oxide (CrO_x), zirconium oxide (ZrO_x), hafnium oxide (HfO_x), tantalum oxide (TaO_x), silver oxide (AgO_x), manganese oxide (MnO_x), iron trichloride (FeCl₃), antimony pentachloride (SbCl₅), metal phthalocyanine compounds, dicyano(phthalocyanato(-1)cobalt(III), oxocarbon-, pseudooxocarbon- and radialene compounds, dicyano(phthalocyanato(-1)ruthenium(III) compounds, 2-(6-dicyanomethylene-1,3,4,5,7,8-hexafluoro-6H-naphthalen-2-ylidene)-malononitrile,




2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F₄-TCNQ),





and




9. The EL device according to any of claims 1 to 8, wherein the electron blocking layer comprises a compound of formula I.

10. Use of the compounds of formula I according to claim 1 as material for the hole transporting/injecting and/or electron blocking layer of electroluminescent devices.

Patentansprüche

1. Elektrolumineszenzvorrichtung (EL-Vorrichtung), umfassend eine Anode, eine Lochtransport-/injektionsschicht, gegebenenfalls eine Elektronenblöckschicht, eine lichtemittierende Schicht, gegebenenfalls eine Loch- oder Exzitonblöckschicht, eine Elektronentransportschicht und eine Kathode, **dadurch gekennzeichnet, dass** die Lochtransport-/injektionsschicht und/oder die Elektronenblöckschicht eine Verbindung der Formel




umfasst, wobei R^1 und R^4 unabhängig voneinander für Wasserstoff, C_1 - C_{18} -Alkyl, C_1 - C_{18} -Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C_1 - C_{18} -Perfluoralkyl, C_2 - C_{18} -Alkenyl, C_2 - C_{18} -Alkinyl, C_1 - C_{18} -Alkoxy, C_1 - C_{18} -Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, CN oder $-CO-R^{28}$ stehen, R^2 , R^3 , R^5 und R^6 jeweils unabhängig voneinander für H, C_1 - C_{18} -Alkyl, C_1 - C_{18} -Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C_1 - C_{18} -Perfluoralkyl, C_6 - C_{24} -Aryl, C_6 - C_{24} -Aryl, das durch G substituiert ist, C_2 - C_{20} -Heteroaryl, C_2 - C_{20} -Heteroaryl, das durch G substituiert ist, C_2 - C_{18} -Alkenyl, C_2 - C_{18} -Alkinyl, C_1 - C_{18} -Alkoxy, C_1 - C_{18} -Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, C_7 - C_{25} -Aralkyl, CN oder $-CO-R^{28}$ stehen, R^8 für C_1 - C_{18} -Alkyl, C_1 - C_{18} -Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C_1 - C_{18} -Perfluor-

alkyl, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl oder C₂-C₂₀-Heteroaryl, das durch G substituiert ist, steht,

R⁹ für H, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₁-C₁₈-Perfluoralkyl, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl oder C₂-C₂₀-Heteroaryl, das durch G substituiert ist, steht, oder


zwei Substituenten R² und R³ und/oder R⁵ und R⁶, die einander benachbart sind, zusammen eine Gruppe




bilden,

R¹⁰⁵, R¹⁰⁶, R¹⁰⁷, R¹⁰⁸, R^{106'} und R^{108'} jeweils unabhängig voneinander für H, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₁-C₁₈-Alkoxy oder C₁-C₁₈-Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, stehen und

A¹, A², A^{1'} und A^{2'} unabhängig voneinander für eine Gruppe der Formel



stehen oder A¹ und A^{1'} und/oder A² und A^{2'} zusammen mit dem Stickstoff-atom, an das sie gebunden sind, einen hetero-aromatischen Ring oder ein heteroaromatisches Ringsystem, wie



bilden;

m' für 0, 1 oder 2 steht;

m jeweils gleich oder verschieden sein kann und für 0, 1, 2 oder 3, speziell 0, 1 oder 2, ganz speziell 0 oder 1, steht; R⁴¹ jeweils gleich oder verschieden sein kann und für Cl, F, CN, N(R⁴⁵)₂, eine C₁-C₂₅-Alkylgruppe, eine C₄-C₁₈-Cycloalkylgruppe, eine C₁-C₂₅-Alkoxy-gruppe, in der ein oder mehrere Kohlenstoffatome, die einander nicht benachbart sind, durch -NR⁴⁵-, -O-, -S- oder -C(=O)-O- ersetzt sein können und/oder worin ein oder mehrere Wasserstoffatome durch F ersetzt sein können, eine C₆-C₂₄-Arylgruppe oder eine C₆-C₂₄-Aryloxygruppe, worin ein oder mehrere Kohlenstoffatome durch O, S oder N ersetzt sein können und/oder die durch eine oder mehrere nichtaromatische Gruppen R⁴¹ substituiert sein kann, steht, oder

zwei oder mehr Gruppen R⁴¹ ein Ringsystem bilden; R⁴⁵ für H, eine C₁-C₂₅-Alkylgruppe, eine C₄-C₁₈-Cycloalkylgruppe, in der ein oder mehrere Kohlenstoffatome, die einander nicht benachbart sind, durch -NR⁴⁵-, -O-, -S-, -C(=O)-O- oder -O-C(=O)-O- ersetzt sein können und/oder worin ein oder mehrere Wasserstoffatome durch F ersetzt sein können, eine C₆-C₂₄-Arylgruppe oder eine C₆-C₂₄-Aryloxygruppe, worin ein oder mehrere Kohlenstoffatome durch O, S oder N ersetzt sein können und/oder die durch eine oder mehrere nichtaromatische Gruppen R⁴¹ substituiert sein kann, steht,

R⁴⁵ für H, eine C₁-C₂₅-Alkylgruppe oder eine C₄-C₁₈-Cycloalkylgruppe steht,

R⁶⁵ für H, eine C₁-C₂₅-Alkylgruppe, eine C₄-C₁₈-Cycloalkylgruppe, in der ein oder mehrere Kohlenstoffatome, die einander nicht benachbart sind, durch -O- oder -S- ersetzt sein können und/oder worin ein oder mehrere Wasserstoffatome durch F ersetzt sein können, eine C₆-C₂₄-Arylgruppe oder eine C₆-C₂₄-Aryloxygruppe, worin ein oder mehrere Kohlenstoffatome durch O, S oder N ersetzt sein können und/oder die durch G substituiert sein kann, steht,

R¹¹⁶, R¹¹⁷ und R^{117'} unabhängig voneinander für H, Halogen, -CN, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl, C₂-C₂₀-Heteroaryl, das durch G substituiert ist, C₂-C₁₈-Alkenyl, C₂-C₁₈-Alkynyl, C₁-C₁₈-Alkoxy, C₁-C₁₈-Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, C₇-C₂₅-Aralkyl, -C(=O)-R¹²⁷, -C(=O)OR¹²⁷ oder -C(=O)NR¹²⁷R¹²⁶ stehen oder

Substituenten R¹¹⁶, R¹¹⁷ und R^{117'}, die einander benachbart sind, einen Ring bilden können,

R¹¹⁹ und R¹²⁰ unabhängig voneinander für C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl, C₂-C₂₀-Heteroaryl, das durch G substituiert ist, C₂-C₁₈-Alkenyl, C₂-C₁₈-Alkynyl, C₁-C₁₈-Alkoxy, C₁-C₁₈-Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, oder C₇-C₂₅-Aralkyl stehen oder

R¹¹⁹ und R¹²⁰ zusammen eine Gruppe der Formel =CR¹²¹R¹²² bilden, worin

R¹²¹ und R¹²² unabhängig voneinander für H, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl oder C₂-C₂₀-Heteroaryl, das durch G substituiert ist, stehen oder

R¹¹⁹ und R¹²⁰ zusammen einen fünf- oder sechsgliedrigen Ring bilden, der gegebenenfalls durch C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch E substituiert und/oder durch D unterbrochen ist, C₆-C₂₄-Aryl, C₆-C₂₄-Aryl, das durch G substituiert ist, C₂-C₂₀-Heteroaryl, C₂-C₂₀-Heteroaryl, das durch G substituiert ist, C₂-C₁₈-Alkenyl, C₂-C₁₈-Alkynyl, C₁-C₁₈-Alkoxy, C₁-C₁₈-Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, C₇-C₂₅-Aralkyl oder -C(=O)-R¹²⁷ substituiert sein kann, und

R¹²⁶, R¹²⁷ und R^{127'} unabhängig voneinander für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, stehen, D für -CO-, -COO-, -S-, -SO-, -SO₂-, -O-, -NR²⁵-, -SiR³⁰R³¹-, -POR³²-, -CR²³=CR²⁴- oder -C=C- steht und E für -OR²⁹-, -SR²⁹-, -NR²⁵R²⁶-, -COR²⁸-, -COOR²⁷-, -CONR²⁵R²⁶-, -CN oder Halogen steht;


G für E, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch D unterbrochen ist, C₁-C₁₈-Perfluoralkyl, C₁-C₁₈-Alkoxy oder C₁-C₁₈-Alkoxy, das durch E substituiert und/oder durch D unterbrochen ist, steht, wobei R²³ und R²⁴ unabhängig voneinander für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, stehen;

R²⁵ und R²⁶ unabhängig voneinander für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy


substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, stehen; oder R²⁵ und R²⁶ zusammen einen fünf- oder sechs-gliedrigen Ring bilden, R²⁷ und R²⁸ jeweils unabhängig voneinander für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, stehen, R²⁹ für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, steht, R³⁰ und R³¹ unabhängig voneinander für C₁-C₁₈-Alkyl, C₆-C₁₈-Aryl oder C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl substituiert ist, stehen und R³² für C₁-C₁₈-Alkyl, C₆-C₁₈-Aryl oder C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl substituiert ist, steht.

2. EL-Vorrichtung nach Anspruch 1, wobei R¹, R², R³, R⁴, R⁵ und R⁶ für Wasserstoff stehen.

3. EL-Vorrichtung nach Anspruch 1 oder 2, wobei A¹, A^{1'}, A² und A^{2'} unabhängig voneinander für eine Gruppe der Formel




stehen oder A¹ und A^{1'} zusammen mit dem Stickstoffatom, an das sie gebunden sind, eine Gruppe der Formel



bilden; wobei R¹¹⁶, R¹¹⁷ und R^{117'} unabhängig voneinander für H oder C₁-C₁₈-Alkyl stehen.



4. EL-Vorrichtung nach einem der Ansprüche 1 bis 3, wobei R⁸ für C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch D unterbrochen ist, C₁-C₁₈-Perfluoralkyl, C₆-C₁₈-Aryl, das gegebenenfalls durch C₁-C₁₈-Alkyl, C₁-C₁₈-Perfluoralkyl, C₁-C₁₈-Alkoxy oder C₁-C₁₈-Alkoxy, das durch D unterbrochen ist, substituiert sein kann, steht, R⁹ für H, C₁-C₁₈-Alkyl, C₁-C₁₈-Alkyl, das durch D unterbrochen ist, C₁-C₁₈-Perfluoralkyl, C₆-C₁₈-Aryl, das gegebenenfalls durch C₁-C₁₈-Alkyl, C₁-C₁₈-Perfluoralkyl, C₁-C₁₈-Alkoxy oder C₁-C₁₈-Alkoxy, das durch D unterbrochen ist, substituiert sein kann, steht, D für -O-, -S- oder -NR²⁵- steht und R²⁵ für C₆-C₁₈-Aryl; C₆-C₁₈-Aryl, das durch C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkoxy substituiert ist; C₁-C₁₈-Alkyl oder C₁-C₁₈-Alkyl, das durch -O- unterbrochen ist, steht.

5. EL-Vorrichtung nach einem der Ansprüche 1 bis 4, wobei es sich bei der Verbindung der Formel I um eine Verbindung der Formel




(Ia)


handelt, wobei A¹ und A^{1'} unabhängig voneinander für eine Gruppe der Formel




stehen, wobei R¹¹⁶, R¹¹⁷ und R^{117'} unabhängig voneinander für H oder C₁-C₁₈-Alkyl stehen; oder A¹ und A^{1'} zusammen mit dem Stickstoffatom, dass sie gebunden sind, eine Gruppe der Formel




bilden;
R⁸ für eine Gruppe der Formel



steht und
R⁹ für eine Gruppe der Formel




oder



steht, wobei


R^{128} , R^{129} , R^{130} und R^{131} unabhängig voneinander für H, C_1 - C_{18} -Alkyl, C_1 - C_{18} -Alkoxy oder C_1 - C_{18} -Perfluoralkyl stehen.

6. EL-Vorrichtung nach einem der Ansprüche 1 bis 4, wobei es sich bei der Verbindung der Formel I um eine Verbindung der Formel




(Ia)


handelt, wobei A^1 und $A^{1'}$ unabhängig voneinander für eine Gruppe der Formel



stehen oder A^1 und $A^{1'}$ zusammen mit dem Stickstoffatom, dass sie gebunden sind, eine Gruppe der Formel




bilden; wobei R^{116} , R^{117} und $R^{117'}$ unabhängig voneinander für H oder C_1 - C_{18} -Alkyl stehen; R^8 für eine Gruppe der Formel




steht und

R^9 für eine Gruppe der Formel




oder



steht, wobei

R^{128} , R^{129} , R^{132} und R^{133} unabhängig voneinander für H, C_1 - C_{18} -Alkyl, C_1 - C_{18} -Alkoxy oder C_1 - C_{18} -Perfluoralkyl stehen.

7. EL-Vorrichtung nach einem der Ansprüche 1 bis 6, wobei es sich bei der Verbindung der Formel I um eine Verbindung der folgenden Formel handelt:



































Verb.	A ¹	A ^{1'}	R ⁸	R ⁹
A-1				
A-2				
A-3				
A-4				
A-5				
A-6				
A-7				

(fortgesetzt)

Verb.	A ¹	A ^{1'}	R ⁸	R ⁹
A-8				
A-9				
A-10				
A-11				
A-12				
A-13				
A-14				
A-15				
A-16				
A-17				
A-18				
A-19				
A-20				
A-21				
A-22				


(fortgesetzt)

Verb.	A ¹	A ^{1'}	R ⁸	R ⁹
A-23				
A-24				
A-25				
A-26				
A-27				
A-28				
A-29				
A-30				
A-31				
A-32				
A-33				
A-34				
A-35				
A-36				
A-37				


(fortgesetzt)

Verb.	A ¹	A ^{1'}	R ⁸	R ⁹
A-38				
A-39				
A-40				
A-41				
A-42				
A-43				
A-44				
A-45	1)	1)		
1) -NA¹A^{1'} steht für				


8. EL-Vorrichtung nach einem der Ansprüche 1 bis 7, wobei die Lochtransport-/injektionsschicht eine Verbindung der Formel I und einen Dotierstoff umfasst, wobei der Dotierstoff aus Titanoxid (TiO_x), Vanadiumoxid (VO_x), Molybdänoxid (MoO₃), insbesondere MO₃, Wolframoxid (WO_x), Rutheniumoxid (RuO_x), Chromoxid (CrOs_x), Zirkoniumoxid (ZrO_x), Hafniumoxid (HfO_x), Tantaloxid (TaO_x), Silberoxid (AgO_x), Manganoxid (MnO_x), Eisentrichlorid (FeCl₃), Antimonpentachlorid (SbCl₅), Metallphthalocyaninverbindungen, Dicyano(phthalocyanato(-1)cobalt(III)-, Oxokohlenstoff-, Pseudooxokohlenstoff- und Radialenverbindungen, Dicyano(phthalocyanato(-1)ruthenium(III)-Verbindungen, 2-(6-Dicyanomethylen-1,3,4,5,7,8-hexafluor-6H-naphthalin-2-yliden)malonsäurenitril,



2,3,5,6-Tetrafluor-7,7,8,8-tetracyanochinodimethan (F₄-TCNQ),



und




ausgewählt ist.

9. EL-Vorrichtung nach einem der Ansprüche 1 bis 8, wobei die Elektronenblockschicht eine Verbindung der Formel I umfasst.
10. Verwendung der Verbindungen der Formel I nach Anspruch 1 als Material für die Lochtransport-/injectionsschicht und/oder Elektronenblockschicht von Elektrolumineszenzvorrichtungen.

Revendications


1. Dispositif électroluminescent (EL), comprenant une anode, une couche de transport/injection de trous, éventuelle-

ment une couche de blocage d'électrons, une couche émettrice de lumière, éventuellement une couche de blocage de trous ou d'excitons, une couche de transport d'électrons, et une cathode, **caractérisé en ce que** la couche de transport/injection de trous et/ou la couche de blocage d'électrons comprennent un composé de formule





dans laquelle


R¹ et R⁴ représentent, indépendamment l'un de l'autre, un hydrogène, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un perfluoroalkyle en C₁-C₁₈, un alcényle en C₂-C₁₈, un alcynyle en C₂-C₁₈, un alcoxy en C₁-C₁₈, un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, CN, ou -CO-R²⁸, R², R³, R⁵ et R⁶ représentent, indépendamment les uns des autres, H, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un perfluoroalkyle en C₁-C₁₈, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, un hétéroaryle en C₂-C₂₀ qui est substitué par G, un alcényle en C₂-C₁₈, un alcynyle en C₂-C₁₈, un alcoxy en C₁-C₁₈, un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un aralkyle en C₇-C₂₅, CN, ou -CO-R²⁸, R⁸ représente un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un perfluoroalkyle en C₁-C₁₈, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, ou un hétéroaryle en C₂-C₂₀ qui est substitué par G, R⁹ représente H, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un perfluoroalkyle en C₁-C₁₈, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, ou un hétéroaryle en C₂-C₂₀ qui est substitué par G, ou deux substituants R² et R³ et/ou R⁵ et R⁶ qui sont adjacents l'un à l'autre forment conjointement un groupe




dans lesquels

R¹⁰⁵, R¹⁰⁶, R¹⁰⁷, R¹⁰⁸, R^{106'} et R^{108'} représentent, indépendamment les uns des autres, H, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un alcoxy en C₁-C₁₈, ou un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, et A¹, A², A^{1'} et A^{2'} représentent, indépendamment les uns des autres, un groupe de formule





ou A^1 et $A^{1'}$ et/ou A^2 et $A^{2'}$, conjointement avec l'atome d'azote auquel ils sont liés, forment un cycle hétéroaromatique, ou un système cyclique tel que



dans lequel

m' vaut 0, 1 ou 2 ;

m peut être identique ou différent à chaque occurrence et vaut 0, 1, 2 ou 3, en particulier 0, 1 ou 2, tout particulièrement 0 ou 1 ;

R^{41} peut être identique ou différent à chaque occurrence et représente Cl, F, CN, $N(R^{45})_2$, un groupe alkyle en C_1-C_{25} , un groupe cycloalkyle en C_4-C_{18} , un groupe alcoxy en C_1-C_{25} , dans lesquels un ou plusieurs atomes de carbone qui ne sont pas au voisinage les uns des autres pourraient être remplacés par $-NR^{45'}$, $-O-$, $-S-$ ou $-C(=O)-O-$, et/ou dans lesquels un ou plusieurs atomes d'hydrogène peuvent être remplacés par F, un groupe aryle en C_6-C_{24} , ou un groupe aryloxy en C_6-C_{24} , dans lesquels un ou plusieurs atomes de carbone peuvent être remplacés par O, S ou N, et/ou qui peuvent être substitués par un ou plusieurs groupes non aromatiques R^{41} , ou

au moins deux groupes R^{41} forment un système cyclique, R^{45} représente H, un groupe alkyle en C_1-C_{25} , un groupe cycloalkyle en C_4-C_{18} , dans lesquels un ou plusieurs atomes de carbone qui ne sont pas au voisinage les uns des autres pourraient être remplacés par $-NR^{45'}$, $-O-$, $-S-$, $-C(=O)-O-$ ou $-O-C(=O)-O-$, et/ou dans lesquels un ou plusieurs atomes d'hydrogène peuvent être remplacés par F, un groupe aryle en C_6-C_{24} , ou un groupe aryloxy en C_6-C_{24} , dans lesquels un ou plusieurs atomes de carbone peuvent être remplacés par O, S ou N, et/ou qui peuvent être substitués par un ou plusieurs groupes non aromatiques R^{41} , et


$R^{45'}$ représente H, un groupe alkyle en C_1-C_{25} , ou un groupe cycloalkyle en C_4-C_{18} ,

$R^{65'}$ représente H, un groupe alkyle en C_1-C_{25} , un groupe cycloalkyle en C_4-C_{18} , dans lesquels un ou plusieurs atomes de carbone qui ne sont pas au voisinage les uns des autres pourraient être remplacés par $-O-$ ou $-S-$, et/ou dans lesquels un ou plusieurs atomes d'hydrogène peuvent être remplacés par F, un groupe aryle en C_6-C_{24} , ou un groupe aryloxy en C_6-C_{24} , dans lesquels un ou plusieurs atomes de carbone peuvent être remplacés par O, S ou N, et/ou qui peuvent être substitués par G,


R^{116} , R^{117} et $R^{117'}$ représentent, indépendamment les uns des autres, H, un halogène, $-CN$, un alkyle en C_1-C_{18} , un alkyle en C_1-C_{18} qui est substitué par E et/ou interrompu par D, un aryle en C_6-C_{24} , un aryle en C_6-C_{24} qui est substitué par G, un hétéroaryle en C_2-C_{20} , un hétéroaryle en C_2-C_{20} qui est substitué par G, un alcényle en C_2-C_{18} , un alcynyle en C_2-C_{18} , un alcoxy en C_1-C_{18} , un alcoxy en C_1-C_{18} qui est substitué par E et/ou

interrompu par D, un aralkyle en C₇-C₂₅, -C(=O)-R^{127'}, -C(=O)OR^{127'}, ou -C(=O)-R¹²⁷R¹²⁶, ou les substituants R¹¹⁶, R¹¹⁷ et R^{117'} qui sont adjacents les uns aux autres peuvent former un cycle, R¹¹⁹ et R¹²⁰ représentent, indépendamment l'un de l'autre, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, un hétéroaryle en C₂-C₂₀ qui est substitué par G, un alcényle en C₂-C₁₈, un alcynyle en C₂-C₁₈, un alcoxy en C₁-C₁₈, un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, ou un aralkyle en C₇-C₂₅, ou R¹¹⁹ et R¹²⁰ forment conjointement un groupe de formule =CR¹²¹R¹²² dans lequel R¹²¹ et R¹²² représentent, indépendamment l'un de l'autre, H, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, ou un hétéroaryle en C₂-C₂₀ qui est substitué par G, ou R¹¹⁹ et R¹²⁰ forment conjointement un cycle à cinq ou six chaînons, qui peut éventuellement être substitué par un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un aryle en C₆-C₂₄, un aryle en C₆-C₂₄ qui est substitué par G, un hétéroaryle en C₂-C₂₀, un hétéroaryle en C₂-C₂₀ qui est substitué par G, un alcényle en C₂-C₁₈, un alcynyle en C₂-C₁₈, un alcoxy en C₁-C₁₈, un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, un aralkyle en C₇-C₂₅, ou -C(=O)-R^{127'}, et R¹²⁶, R¹²⁷ et R^{127'} représentent, indépendamment les uns des autres, un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-, D représente -CO-, -COO-, -S-, -SO-, -SO₂-, -O-, -NR²⁵-, -SiR³⁰R³¹-, -POR³²-, -CR²³=CR²⁴-, ou -C≡C-, et E représente -OR²⁹-, -SR²⁹-, -NR²⁵R²⁶-, -COR²⁸-, -COOR²⁷-, -CONR²⁵R²⁶-, -CN, ou un halogène, G représente E, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est interrompu par D, un perfluoroalkyle en C₁-C₁₈, un alcoxy en C₁-C₁₈, ou un alcoxy en C₁-C₁₈ qui est substitué par E et/ou interrompu par D, dans lesquels R²³ et R²⁴ représentent, indépendamment l'un de l'autre, un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-, R²⁵ et R²⁶ représentent, indépendamment l'un de l'autre, un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-, ou R²⁵ et R²⁶ forment conjointement un cycle à cinq ou six chaînons, R²⁷ et R²⁸ représentent, indépendamment l'un de l'autre, un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-, R²⁹ représente un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-, R³⁰ et R³¹ représentent, indépendamment l'un de l'autre, un alkyle en C₁-C₁₈, un aryle en C₆-C₁₈, ou un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈, et R³² représente un alkyle en C₁-C₁₈, un aryle en C₆-C₁₈, ou un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈.

2. Dispositif EL selon la revendication 1, dans lequel R¹, R², R³, R⁴, R⁵ et R⁶ représentent un hydrogène.
3. Dispositif EL selon la revendication 1 ou 2, dans lequel A¹, A^{1'}, A² et A^{2'} représentent, indépendamment les uns des autres, un groupe de formule




ou A¹ et A^{1'}, conjointement avec l'atome d'azote auquel ils sont liés, forment un groupe de formule





dans lesquels R¹¹⁶, R¹¹⁷ et R^{117'} représentent, indépendamment les uns des autres, H ou un alkyle en C₁-C₁₈.


4. Dispositif EL selon l'une quelconque des revendications 1 à 3, dans lequel R⁸ représente un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est interrompu par D, un perfluoroalkyle en C₁-C₁₈, un aryle en C₁-C₁₈ qui peut éventuellement être substitué par un alkyle en C₁-C₁₈, un perfluoroalkyle en C₁-C₁₈, un alcoxy en C₁-C₁₈, ou un alcoxy en C₁-C₁₈ qui est interrompu par D, R⁹ représente H, un alkyle en C₁-C₁₈, un alkyle en C₁-C₁₈ qui est interrompu par D, un perfluoroalkyle en C₁-C₁₈, un aryle en C₆-C₁₈ qui peut éventuellement être substitué par un alkyle en C₁-C₁₈, un perfluoroalkyle en C₁-C₁₈, un alcoxy en C₁-C₁₈, ou un alcoxy en C₁-C₁₈ qui est interrompu par D, D représente -O-, -S-, ou -NR²⁵-, et R²⁵ représente un aryle en C₆-C₁₈, un aryle en C₆-C₁₈ qui est substitué par un alkyle en C₁-C₁₈ ou un alcoxy en C₁-C₁₈, un alkyle en C₁-C₁₈, ou un alkyle en C₁-C₁₈ qui est interrompu par -O-.
5. Dispositif EL selon l'une quelconque des revendications 1 à 4, dans lequel le composé de formule I est un composé de formule




dans laquelle A¹ et A^{1'} représentent, indépendamment l'un de l'autre, un groupe de formule




dans lesquels R¹¹⁶, R¹¹⁷ et R^{117'} représentent, indépendamment les uns des autres, H ou un alkyle en C₁-C₁₈, ou A¹ et A^{1'}, conjointement avec l'atome d'azote auquel ils sont liés, forment un groupe de formule




R⁸ représente un groupe de formule



et
R⁹ représente un groupe de formule




ou





dans lesquels R¹²⁸, R¹²⁹, R¹³⁰ et R¹³¹ représentent, indépendamment les uns des autres, H, un alkyle en C₁-C₁₈, un alcoxy en C₁-C₁₈, ou un perfluoroalkyle en C₁-C₁₈.


6. Dispositif EL selon l'une quelconque des revendications 1 à 4, dans lequel le composé de formule I est un composé de formule




dans laquelle A¹ et A^{1'} représentent, indépendamment l'un de l'autre, un groupe de formule




ou A¹ et A^{1'}, conjointement avec l'atome d'azote auquel ils sont liés, forment un groupe de formule




dans lesquels R^{116} , R^{117} et $R^{117'}$ représentent, indépendamment les uns des autres, H ou un alkyle en C_1 - C_{18} ,
 R^8 représente un groupe de formule



et
 R^9 représente un groupe de formule




ou



dans lesquels R^{128} , R^{129} , R^{132} et R^{133} représentent, indépendamment les uns des autres, H, un alkyle en C_1 - C_{18} ,
 un alcoxy en C_1 - C_{18} , ou un perfluoroalkyle en C_1 - C_{18} .

7. Dispositif EL selon l'une quelconque des revendications 1 à 6, dans lequel le composé de formule I est un composé de formule







































Cps.	A ¹	A ^{1'}	R ⁸	R ⁹
A-1				
A-2				
A-3				

(suite)

Cps.	A ¹	A ^{1'}	R ⁸	R ⁹
5				
10				
15				
20				
25				
30				
35				
40				
45				
50				
55				


(suite)

Cps.	A ¹	A ^{1'}	R ⁸	R ⁹
5				
				
10				
15				
				
20				
25				
				
30				
35				
40				
45				
				
50				
				
55				


(suite)

Cps.	A ¹	A ^{1'}	R ⁸	R ⁹
5				
10				
15				
20				
25				
30				
35				
40				
45				
50				
55				
	1)	1)		
 1) -NA ¹ A ^{1'} est				


8. Dispositif EL selon l'une quelconque des revendications 1 à 7, dans lequel la couche de transport/injection de trous comprend un composé de formule I et un dopant, le dopant étant choisi parmi un oxyde de titane (TiO_x), un oxyde de vanadium (VO_x), l'oxyde de molybdène (MoO_3), en particulier MO_3 , un oxyde de tungstène (WO_x), un oxyde de ruthénium (RuO_x), un oxyde de chrome (CrO_x), un oxyde de zirconium (ZrO_x), un oxyde de hafnium (HfO_x), un oxyde de tantale (TaO_x), un oxyde d'argent (AgO_x), un oxyde de manganèse (MnO_x), le trichlorure de fer (FeCl_3), le pentachlorure d'antimoine (SbCl_5), les composés de phthalocyanine de métaux, les dicyano(phthalocyanato(-1)co-balt(III)), les composés d'oxocarbène, de pseudo-oxocarbène et de radialène, les composés de dicyano(phthalocyanato(-1)ruthénium(III), le 2-(6-dicyanométhylène-1,3,4,5,7,8-hexafluoro-6H-naphtalène-2-ylidène)-malonitrile,



le 2,3,5,6-tétrafluoro-7,7,8,8-tétracyanoquinodiméthane (F₄-TCNQ),



et



9. Dispositif EL selon l'une quelconque des revendications 1 à 8, dans lequel la couche de blocage d'électrons comprend un composé de formule I.

- 10.** Utilisation des composés de formule I selon la revendication 1 comme matériau pour la couche de transport/injection de trous et/ou de blocage d'électrons de dispositifs électroluminescents.

5

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 9013025 B [0002]
- JP 11251063 B [0003]
- JP 2006143845 B [0004]
- JP 2134644 A [0005] [0007]
- US 20060289882 A [0006]
- US 20070029927 A [0006]
- JP 2000323278 B [0008]
- JP 2001023777 B [0009]
- JP 2001118683 B [0010]
- JP 2002050473 B [0011]
- JP 2003059670 B [0012]
- JP 2002367786 B [0013]
- WO 08031743 A [0014] [0032] [0033] [0057] [0059]
- WO 06097419 A [0033]
- WO 0070655 A [0059] [0061] [0067]
- WO 0139234 A [0059] [0061]
- WO 0193642 A [0059] [0061] [0067]
- WO 02074015 A [0059] [0061]
- WO 0215645 A [0059] [0061]
- US 20020117662 A [0059]
- WO 0057676 A [0061]
- WO 0141512 A [0061]
- US 20030017361 A [0061]
- US 6458475 B [0061]
- WO 02071813 A [0061]
- US 6573651 B [0061]
- US 20020197511 A [0061]
- US 6451455 B [0061]
- US 20030072964 A [0061]
- US 20030068528 A [0061] [0067]
- US 6413656 B [0061]
- US 6515298 B [0061]
- US 6451415 B [0061]
- US 6097147 A [0061]
- US 20030124381 A [0061]
- US 20030059646 A [0061]
- US 20030054198 A [0061]
- EP 1239526 A [0061]
- EP 1238981 A [0061]
- EP 1244155 A [0061]
- US 20020100906 A [0061]
- US 20030068526 A [0061]
- US 20030068535 A [0061]
- JP 2003073387 B [0061]
- JP 2003073388 B [0061]
- US 20030141809 A [0061]
- US 20030040627 A [0061]
- JP 2003059667 B [0061]
- JP 2003073665 B [0061]
- US 20020121638 A [0061]
- WO 06000544 A [0066]
- WO 08101842 A [0066]
- US 20030175553 A [0067]
- US 4885221 A [0071]
- US 5677572 A [0071] [0072]
- US 5059861 A [0071]
- US 5059862 A [0071]
- US 6140763 A [0071] [0072]
- US 4885211 A [0072]
- US 5247190 A [0072]
- JP 3234963 B [0072]
- US 5703436 A [0072]
- US 5608287 A [0072]
- US 5837391 A [0072]
- US 5776622 A [0072]
- US 5776623 A [0072]
- US 5714838 A [0072]
- US 5969474 A [0072]
- US 5739545 A [0072]
- US 5981306 A [0072]
- US 6137223 A [0072]
- US 6172459 B [0072]
- EP 1076368 A [0072]
- US 6278236 A [0072]
- US 62843936 A [0072]
- US 5276380 A [0072]
- EP 0732868 A [0072]
- EP 1596445 A1 [0073]
- WO 2009003455 A1 [0073]
- DE 100357044 [0073]
- WO 2008058525 A [0073]
- WO 2008138580 A [0073]
- US 20080171228 A [0073]
- US 20080265216 A [0073]
- US 4720432 A [0076]
- US 6208075 A [0076]
- EP 0891121 A [0076]
- EP 1029909 A [0076]
- US 4769292 A [0078]
- US 5935721 A [0078] [0079]
- US 4768292 A [0079]
- US 5141671 A [0079]
- US 5150006 A [0079]
- US 5151629 A [0079]
- US 5405709 A [0079]
- US 5484922 A [0079]
- US 5593788 A [0079]
- US 5645948 A [0079]

EP 2 443 213 B1

- US 5683823 A [0079]
- US 5755999 A [0079]
- US 5928802 A [0079]
- US 5935720 A [0079]
- US 6020078 A [0079]
- US 7090930 B2 [0082]
- US 4356429 A [0083]
- US 4539507 A [0083]
- US 6337102 B [0083]
- US 5294870 A [0084]
- US 5688551 A [0084]
- US 5851709 A [0084]
- US 6066357 A [0084]
- US 6226890 B [0085]

Non-patent literature cited in the description

- **YAMAMOTO ; KURATA.** *Chem. and Industry*, 1981, 737-738 [0032]
- *J. Mater. Chem.*, 2004, vol. 14, 2516 [0032]
- **H. B. GOODBRAND et al.** *J. Org. Chem.*, 1999, vol. 64, 670 [0032]
- **K. D. BELFIELD et al.** *J. Org. Chem.*, 2000, vol. 65, 4475 [0032]
- **M. D. CHARLES et al.** *Organic Lett.*, 2005, vol. 7, 3965 [0032]
- **A. F. LITKE.** *Angew. Chem. Int. Ed.*, 2002, vol. 41, 4176 [0032]
- **ADACHI, C. ; LAMANSKY, S. ; BALDO, M. A. ; KWONG, R. C. ; THOMPSON, M. E. ; FORREST, S. R.** *App. Phys. Lett.*, 2001, vol. 78, 1622-1624 [0063]
- **J. KIDO et al.** *Appl. Phys. Lett.*, 1994, vol. 65, 2124 [0065]
- **K. WALZER ; B. MAENNIG ; M. PFEIFFER ; K. LEO.** *Chem. Rev.*, 2007, vol. 107, 1233-1271 [0073]

专利名称(译)	Phenanthroazole化合物作为电致发光器件的空穴传输材料		
公开(公告)号	EP2443213B1	公开(公告)日	2014-04-23
申请号	EP2010725130	申请日	2010-06-11
[标]申请(专利权)人(译)	巴斯夫欧洲公司		
申请(专利权)人(译)	BASF SE		
当前申请(专利权)人(译)	BASF SE		
[标]发明人	SCHILDKNECHT CHRISTIAN LENNARTZ CHRISTIAN WATANABE SOICHI WAGENBLAST GERHARD MURER PETER SCHAFFER THOMAS CHEBOTAREVA NATALIA RICCI ANDREA BARDON KRISTINA		
发明人	SCHILDKNECHT, CHRISTIAN LENNARTZ, CHRISTIAN WATANABE, SOICHI WAGENBLAST, GERHARD MURER, PETER SCHÄFFER, THOMAS CHEBOTAREVA, NATALIA RICCI, ANDREA BARDON, KRISTINA		
IPC分类号	C09K11/06 H05B33/22 C07D235/02 C07D403/14 C07D235/18		
CPC分类号	C07D235/02 C07D403/14 H01L51/0061 H01L51/0072 H01L51/0081 H01L51/5052 H01L51/5056 H01L51/5096 Y10S428/917 C09K11/06 H05B33/22 H01L51/5048		
优先权	2009163085 2009-06-18 EP		
其他公开文献	EP2443213A1		
外部链接	Espacenet		

摘要(译)

本发明涉及电致发光器件，其包含式 (I) 化合物作为传输/注入和/或电子阻挡层的组分。式 (I) 化合物可以单独起作用，或与掺杂剂组合起作用，以提供电致发光器件的改进的效率，驱动电压和/或寿命。

