



(11) **EP 1 696 709 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
24.10.2012 Bulletin 2012/43

(21) Application number: **04799796.0**

(22) Date of filing: **17.11.2004**

(51) Int Cl.:
H01L 51/54 (2006.01)

(86) International application number:
PCT/JP2004/017440

(87) International publication number:
WO 2005/051047 (02.06.2005 Gazette 2005/22)

(54) **ORGANO-ELECTRONIC FUNCTIONAL MATERIAL AND USE THEREOF**

ORGANOELEKTRONISCHES FUNKTIONALMATERIAL UND VERWENDUNG DAVON
MATERIAU FONCTIONNEL ORGANO-ELECTRIQUE ET UTILISATION ASSOCIEE

(84) Designated Contracting States:
DE FR GB

(30) Priority: **21.11.2003 JP 2003391882**
03.12.2003 JP 2003404721

(43) Date of publication of application:
30.08.2006 Bulletin 2006/35

(73) Proprietor: **Nippon Steel Chemical Co., Ltd.**
Chiyoda-ku
Tokyo 101-0021 (JP)

(72) Inventors:
• **Akashi, N.,**
c/o Bando Chemical Industries, Ltd.
Kobe-shi,
Hyogo 652-0883 (JP)
• **Shirota, Yasuhiko**
Toyonaka-shi,
Osaka 561-0827 (JP)

(74) Representative: **Benson, John Everett et al**
J A Kemp
14 South Square
Gray's Inn
London WC1R 5JJ (GB)

(56) References cited:

EP-A1- 0 611 148 **JP-A- 7 033 717**
JP-A- 7 033 717 **JP-A- 2003 068 470**
JP-A- 2003 178 883 **JP-A- 2004 095 491**
US-A1- 2003 157 365

- **STICKLEY K R ET AL: "Cation Radicals of 1,3,5-Tris(diarylamino)benzenes" TETRAHEDRON LETTERS, ELSEVIER, AMSTERDAM, vol. 36, no. 10, 6 March 1995 (1995-03-06), pages 1585-1588, XP004028538 ISSN: 0040-4039**
- **THELAKKAT M ET AL: "SYNTHESIS AND PROPERTIES OF NOVEL DERIVATIVES OF 1,3,5-TRIS(DIARYLAMINO)BENZENES FOR ELECTROLUMINESCENT DEVICES" ADVANCED MATERIALS, WILEY VCH, WEINHEIM, DE, vol. 10, no. 3, 11 February 1998 (1998-02-11), pages 219-223, XP000732696 ISSN: 0935-9648**
- **PLATER J., MCKAY M., JACKSON T.: "Synthesis of 1,3,5-tris[4-(diarylamino)phenyl]benzene and 1,3,5-tris(diarylamino)benzene derivatives" J. CHEM. SOC., PERKIN TRANS. 1, 24 July 2000 (2000-07-24), pages 2695-2701, XP002498371**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 696 709 B1

Description

FIELD OF THE INVENTION

[0001] The invention relates to an organo-electronic functional material and use thereof. More particularly, the invention relates to an organo-electronic functional material which comprises a tris(arylamino)benzene and is superior in repeated oxidation-reduction process and is hence suitable for use as, for example, a hole transporting agent. The invention further relates to such a hole transporting agent which comprises the organo-electronic functional material and an organic electroluminescence element having a hole transporting layer formed of the hole transporting agent.

BACKGROUND ART

[0002] In recent years, a variety of electronic devices such as organic semiconductors or light-emitting elements in which an organic compound which has photoelectric function as well as reversible oxidation-reduction characteristics and can form amorphous film in itself is used as an organo-electronic material, for example, as a hole transporting agent, have attracted considerable attention. Such an amorphous film of organic substances are formed by preparing a coating composition comprised of a binder resin such as polycarbonate resin and the organic compound dissolved in a suitable organic solvent and then by coating and drying the composition, as described in JP-A-11-174707. An organic amorphous film is also formed by preparing a coating composition comprised of a multinuclear aromatic tertiary amine called a "star-burst" compound dissolved in a suitable organic solvent and then by coating the composition on a substrate and drying it, as described in JP-A-08-291115.

[0003] According to a method using a binder resin among the methods mentioned above, the organic compound is diluted with the binder resin in the resulting amorphous film and influenced by the binder resin so that the organic compound cannot exhibit sufficiently the functions that it originally has as an organo-electronic functional material. In addition, if the organic compound forms an amorphous film that is stable at normal temperature with the aid of a binder resin, the organic compound has a low glass transition temperature so that the film is poor in heat resistance and has a problem in stability and life.

[0004] Under these circumstances, polynuclear aromatic tertiary amine compounds called the "star-burst" molecules are attracting considerable attention since they are capable of forming amorphous film in themselves at normal temperatures, as described above. The star-burst molecules are divided into three groups based on their molecular structures: compounds having a triphenylamine structure (triphenylamines), compounds having a triaminobenzene structure (triaminobenzenes) and compounds having a triphenylbenzene structure (triphenylbenzenes).

[0005] Examples of the triphenylamines include, for example, 4,4',4"-tris-(N,N-diphenylamino)triphenylamine (TDATA) and 4,4',4"-tris(N-phenyl-N-m-tolylamino)triphenylamine (m-MTDATA), as described in JP-A-01-224353, and in addition, 4,4',4"-tris(N-(2-naphthyl)-N-phenylamino)triphenylamine (2-TNATA), as described in JP-A-08-291115.

[0006] These triphenylamines are reversible in oxidation-reduction process and can form amorphous film by a vapor deposition method, however, TDATA and m-MTDATA have a problem in heat resistance. TNATA has a glass transition temperature of about 110°C and is superior in heat resistance, but it is readily crystallized so that the amorphous film formed therewith is lacking in stability.

[0007] Examples of the triphenylbenzenes include, for example, 1,3,5-tris(4-(N,N-diphenylaminophenyl)benzene (TDAPB) and 1,3,5-tris(4-(N-tolyl-N-phenylaminophenyl)benzene (MTDAPB), as described in Bando Technical Report, Vol. 2, pp. 9-18, 1998 (Bando Chemical Industries, Ltd.). These triphenylbenzenes also can form amorphous film and have oxidation potentials in the range of 0.6-0.7V, but they are irreversible in oxidation-reduction process so that they are not suitable for practical use as an organo-electronic functional material such as a hole transporting agent.

[0008] On the other hand, examples of the triaminobenzenes include 1,3,5-tris(N-methylphenyl-N-phenylamino)benzene (MTDAB). The triaminobenzenes also have oxidation potentials in the range of 0.6-0.7V, but they are irreversible in oxidation-reduction process so that they are also not suitable for practical use as an organo-electronic function material.

[0009] The present inventors have presented 1,3,5-tris(N-(p-methylphenyl)-N-(-1-naphthyl)aminobenzene (p-MTPNAB) and 1,3,5-tris(N-(p-methylphenyl)-N-(4-biphenyl)amino)benzene (p-MTPBAB) as such organic compounds that are reversible in oxidation-reduction process, have oxidation potentials in the range of 0.5-0.7V, are superior in heat-resistance, and can form amorphous film by a vapor deposition method, as described in Japanese Patent Application No.2003-079441.

[0010] The above-mentioned p-MTPNAB and p-MTPBAB are reversible in oxidation-reduction process and have high oxidation potentials as well as high glass transition temperature, i.e., 87°C and 98°C, respectively. However, when they are subjected to repeated oxidation-reduction process, peak currents of oxidation curves tend to fall, and accordingly, there is a fear that they have not enough stability and durability for use as organo-electronic functional material.

[0011] On the other hand, a hole transporting agent comprising a polynuclear aromatic tertiary amine compound having a biphenyl skeleton is also known. Examples of such polynuclear aromatic tertiary amine compounds include 4,4'-bis


(N-(3-methylphenyl)-N-phenylamino)-biphenyl (TPD), as described in JP-A-10-090256, and 4,4'-bis(N-(1-naphthyl)-N-phenylamino)biphenyl (α -NPD), as described in JP-A-05-234681. However, an organic electroluminescence element manufactured by using these compounds as a hole transporting agent needs a high voltage to be driven.

[0012] STICKLEY K R ET AL: "Cation Radicals of 1,3,5-Tris(diarylamino)benzenes", TETRAHEDRON LETTERS, ELSEVIER, AMSTERDAM, vol. 36, no. 10, 6 March 1995 (1995-03-06), pages 1585-1588, ISSN: 0040-4039, discloses a N,N,N',N',N'',N''-hexakis-(4-methylphenyl)-1,3,5-triaminobenzene (p-MPTAB) compound.


[0013] The invention has been completed to solve the problem involved in the known organo-electronic functional materials as mentioned above. Therefore, it is an object of the invention to provide an organo-electronic functional material which has an opto-electronic function, is reversible in oxidation-reduction process, can form amorphous film in itself, and has a high glass transition temperature, and shows only a slight change of peak current when being subjected to repeated oxidation-reduction process, and is hence superior in stability.

SUMMARY OF THE INVENTION

[0014] The invention provides an organo-electronic functional material comprising a tris(arylamino)benzene represented by the general formula (I)



wherein A and B may be the same or different from each other and are each a group represented by the general formula (II)



in which R is an alkyl group of 1-6 carbons or a cycloalkyl group of 5 or 6 carbon atoms and n is 1, 2 or 3 in A and n is 0, 1, 2 or 3 in B; same or and exhibiting a cyclic voltamogram in which a deviation of peak current of cyclic curves measured 50 times at a sweep rate of 20 mV/s falls within $\pm 10\%$ of the average of peak current.

[0015] The invention further provides a hole transporting agent comprising the above-mentioned organo-electronic functional material, and an organic electroluminescence element having a hole transporting layer containing the above-mentioned hole transporting agent.

BRIEF DESCRIPTION OF DRAWINGS

[0016]

FIG. 1 is a cross section showing an example of an organic electroluminescence element;

FIG. 2 is a differential scanning calorimetry (DSC) curve of 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene (p-MBTAB), one of the organo-electronic functional material according to the invention;

FIG. 3 is a cyclic voltamogram of 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene (p-MBTAB), one of the organo-electronic functional material according to the invention;

FIG. 4 is a differential scanning calorimetry (DSC) curve of 1,3,5-tris(N-(4-biphenyl)-N-(1-naphthyl)amino)benzene (TBNAB), one of the organo-electronic functional materials of comparative example;

FIG. 5 is a cyclic voltamogram of 1,3,5-tris(N-(4-biphenyl)-N-(1-naphthyl)amino)benzene (TBNAB), one of the organo-electronic functional materials of comparative examples;


FIG. 6 is a graph showing time-luminance characteristic of an organic electroluminescence element having a hole

transporting layer formed of a hole transporting agent, 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene (p-MBTAB), one of the organo-electronic functional material of the invention (Example 2) and time-luminance characteristic of an organic electroluminescence element having a hole transporting layer formed of 1,3,5-tris(p-N-phenyl-N-m-tolyl)phenyl)benzene (m-MTDAPB), one of hole transporting agents of comparative examples (Comparative Example 2);


FIG. 7 is a graph showing a voltage-luminance characteristics of each of an organic electroluminescence element having a hole injecting layer formed of copper phthalocyanine and a hole transporting layer formed of an organo-electronic functional material according to the invention (Example 2), an organic electroluminescence element having a hole injecting layer formed of 2-TNATA and a hole transporting layer formed of p-MBTAB, one of the organo-electronic functional material according to the invention (Example 3), an organic electroluminescence element having a hole injecting layer formed of 2-TNATA and a hole transporting layer formed of 4,4'-bis[N-(1-naphthyl)-N-phenylamino]-biphenyl (α -NPD) (Comparative Example 3), and an organic electroluminescence element having a hole injecting layer formed of copper phthalocyanine and a hole transporting layer formed of α -NPD) (Comparative Example 4).

THE BEST MODE FOR CARRYING OUT THE INVENTION

[0017] The organo-electronic functional material of the invention comprises a tris(arylamino)benzene represented by the general formula (I)



wherein A and B may be the same or different from each other and are each a group represented by the general formula (II)



in which R is an alkyl group of 1-6 carbons or a cycloalkyl group of 5 or 6 carbon atoms and n is 1, 2 or 3 in A and n is 0, 1, 2 or 3 in B.


[0018] In the tris(arylamino)benzenes represented by the general formula (I), the group A and B are each a biphenyl group having the alkyl group or cycloalkyl group at the terminal, a terphenyl group having the alkyl group or cycloalkyl group at the terminal, or a quaterphenyl group having the alkyl group or cycloalkyl group at the terminal, and the group A and B may be the same or different from each other. The group B may also be a phenyl group having the alkyl group or cycloalkyl group.

[0019] It is particularly preferred that the tris(arylamino)benzenes represented by the general formula (I) have a biphenyl group having the alkyl group or cycloalkyl group at the para-position of the terminal phenyl group as the group A and a phenyl group having the alkyl group or cycloalkyl group at the para-position as the group B since these tris(arylamino)benzenes are excellent in reversibility of oxidation-reduction process, oxidation-reduction potential and heat resistance when being used as organo-electronic functional materials.

[0020] The alkyl group is methyl, propyl, butyl, pentyl or hexyl group, and may be linear or branched, while the cycloalkyl group is cyclopentyl or cyclohexyl group.

[0021] Among the tris(arylamino)benzenes, an organo-electron functional material comprising 1,3,5-tris(N-(4'-methyl-


4-biphenyl)-N-(p-tolyl)amino)benzene represented by the formula (IV)



(IV)

is superior in stability in repeated oxidation-reduction process and is suitable for use as hole transporting agent in various electronic devices.

[0022] As shown in the scheme below, 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene can be obtained by, for example, reacting 1,3,5-tris(p-tolyl)aminobenzene (V) with 4-iodo-4'-methylbiphenyl (VI).



[0023] As described above, the organo-electronic functional material of the invention comprises such a tris(arylamino) benzene in which each of the chemically active sites at the terminal of the aryl groups of the arylamino groups, preferably a carbon atom of para-position of phenyl group, is substituted or capped with a stable substituent such as an alkyl or a cycloalkyl mentioned hereinabove, so that the tris(arylamino)benzene is provided with improved reversibility in repeated oxidation-reduction process while retaining oxidation-reduction characteristics, high oxidation potential and high glass transition temperature of tris(arylamino)benzene, one of the "star-burst" molecules,. Accordingly, the organo-electronic functional material of the invention shows only a slight change in the values of peak current in the repeated oxidation-reduction process, and can be used as a stable and durable organo-electronic functional material in various electronic devices.

[0024] The organic electroluminescence element is driven by a direct current at a low electric voltage with high efficiency to emit light at a high luminance, as well as it can be made thin. Accordingly, in recent years, the investigation to put the

organic electroluminescence element to practical use as display devices as well as backlights or illumination devices is pushed forward.

[0025] As an example is shown in Fig. 1, the electroluminescence element is comprised of a transparent substrate 1 made of glass, for example, having an anode 2 made of a transparent electrode such as an ITO membrane (indium oxide-tin oxide membrane) laminated thereon, and a hole injecting layer 3a, a hole transporting layer 3, an emitting layer 4 and a cathode 5 made of a metal or a compound thereof laminated on the anode in this order. The anode and the cathode are connected with an external power source 6. In some cases, a hole injecting layer 3a may be omitted, and an electron transporting layer may be laminated between the emitting layer and the cathode. An electroconductive polymer layer (a buffer layer) may be laminated between the anode and the hole transporting layer. Many other layer structures to form organic electroluminescence elements are already known.

[0026] The electroluminescence element of the invention is featured in that it has a hole transporting layer formed of a tris(aryl amino)benzene represented by the general formula (I), a hole transporting agent of the invention, but is not specifically limited in layer structures. The thickness of hole transporting layer is usually in the range of 10 nm to 200 nm.


[0027] In such an organic electroluminescence element as mentioned above, the hole transporting layer adheres to the anode, and transports holes from the anode to the emitting layer while blocking electrons, whereas the electron transporting layer adheres to a cathode, and transports electrons from the cathode to the emitting layer. Thus, when an electron injected from the cathode and a hole injected from the anode recombine in the emitting layer, light is emitted and radiated outside through the transparent electrode (anode) and the transparent substrate.

[0028] In the organic electroluminescence element of the invention, the layers except the hole transporting layer mentioned above, that is, a transparent substrate, an anode, an emitting layer, an electron transporting layer and a cathode, may be made of any conventionally known materials. For example, an anode or transparent electrode may be made of indium oxide-tin oxide (ITO), and a cathode may be made of a metal such as aluminum, magnesium or silver, or an alloy of these metals, such as Al-Mg alloy, Ag-Mg alloy, or a metal compound. A transparent substrate is usually made of glass.

[0029] The emitting layer is usually formed of tris(8-quinolinol) aluminum (Alq_3) and has a thickness in the range of 10 nm to 200 nm. The electron transporting layer has also a thickness in the range of 10 nm to 200 nm. When an electroconductive polymer layer is employed, it has also a thickness in the range of 10 nm to 200 nm.

[0030] When the organo-electronic functional material of the invention is used as a hole transporting agent, a hole injecting layer that is formed of copper phthalocyanine (CuPC), a known hole injecting agent, may be placed between the anode and the hole transporting layer so that the energy gap between the anode and hole transporting layer is made small and holes are readily transported from the anode to the hole transporting layer.

[0031] Further according to the invention, an organic electroluminescence element that is driven by a direct current at a lower electric voltage to emit light at a high luminance is obtained by using the organo-electronic functional material of the invention as a hole transporting agent in conjunction with a tris(4-(N,N-diarylamino)-phenyl)amine represented by the general formula (III)



wherein X and Y are each an aryl group and may be the same or may be different from each other. That is, according to the invention, the voltage-luminance characteristics of an organic electroluminescence element is much more improved by laminating a hole injecting layer formed of the tris(4-(N,N-diarylamino)phenyl)amine represented by the general formula (III) as a hole injecting agent and a hole transporting layer formed of the organo-electronic functional material of the invention as a hole transporting agent.

[0032] If necessary, a uniform mixture of tris(4-(N,N-diarylamino)-phenyl)amine represented by the general formula (III) and the organo-electronic functional material of the invention may be used as a hole transporting agent in manufacture

of organic electroluminescence elements.

[0033] In the tris(4-(N,N-diarylamino)phenyl)amine represented by the general formula (III), X and Y are each an aryl group and may be the same or different from each other. Examples of such aryl groups include phenyl, o-, m- or p-tolyl, 1- or 2-naphthyl, 4-p-biphenyl and 4-p-terphenyl. Thus, Examples of the tris(4-(N,N-diarylamino)-phenyl)amine include, as mentioned hereinbefore, 4,4',4''-tris(N,N-diphenylamino)triphenylamine (TDATA), 4,4',4''-tris(N-phenyl-N-m-tolylamino)triphenylamine (m-MTDATA) and 4,4',4''-tris (N-(2-naphthyl)-N-phenylamino)triphenyl amine (2-TNATA), although the tris(4-(N,N-diarylamino)phenyl)amine usable are not limited to those exemplified.

INDUSTRIAL APPLICABILITY

[0034] The organo-electronic functional material of the invention has reversible oxidation-reduction characteristics as well as high oxidation potential and high glass transition temperature, and further it forms amorphous film stable at room temperature in itself by vapor deposition, etc. In addition, the organo-electronic functional material of the invention exhibits a deviation of peak current of cyclic curves as measured 50 times at a sweep rate of 20 mV/s falls within $\pm 10\%$, and in a preferred embodiment, within $\pm 5\%$, of the average of peak current in the measurement of voltamogram to illustrate the reversibility of oxidation-reduction process. The organo-electronic functional material of the invention is thus superior in reversibility in oxidation-reduction process so that it shows only slight change of peak current in repeated oxidation-reduction process and maintains the initial performance over a long period of time. Therefore, the organo-electronic functional material of the invention is suitable for use as an organo-electronic functional material such as a hole transporting agent in various electronic devices, for instance, in an organic electroluminescence element.

EXAMPLES

[0035] The invention is described in more detail with reference to examples, however, the invention is not limited thereto.

Example 1

(Synthesis of 1,3,5-tris(p-tolylamino)benzene)

[0036] 11.8 g of phloroglucinol, 50 g of p-toluidine and 0.5 g of iodine were placed in a 300 mL capacity three necked flask and the reaction was carried out at a temperature of 150°C with stirring under a nitrogen atmosphere. After the reaction, the resultant reaction mixture was washed with methanol, hexane and methanol in this order, followed by drying to provide 31.9 g of the desired 1,3,5-tris(p-tolylamino)benzene as slightly reddish solid. The yield was 86.5%. (Synthesis of 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)-benzene (p-MBTAB))

[0037] 2.0 g of 1,3,5-tris(p-tolylamino)benzene, 7.0 g of 4-iodo-4'-methylbiphenyl, 6.9 g of potassium carbonate, 1.0 g of copper powder, 0.7 g of 18-crown-6 (or 1,4,7,10,13,16-hexaoxacyclooctadecane) and 15 mL of mesitylene (reaction solvent) were placed in a 100 mL capacity glass flask and the reaction was carried out at a temperature of 170°C for 15 hours under a nitrogen atmosphere. After the reaction, the resultant reaction mixture was extracted with toluene and the toluene solution was subjected to silica gel chromatography to fractionate the reaction product. The reaction product was then purified by recrystallization and then by sublimation to provide the desired 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene (p-MBTAB). The yield was 15.6%.

Elemental analysis (%):

	C	H	N
Calculated:	88.89	6.40	4.71
Measured:	88.69	6.55	4.76

Mass analysis: 892 (M^+)

Differential scanning calorimetry (DSC):

[0038] About 5 mg of p-MBTAB was weighed as a sample, and it was melted in a differential scanning calorimetric device and cooled to room temperature at a rate of 50°C per minute. The sample did not crystallized, but it became amorphous glass. Subsequently, the thermal characteristics of the sample were measured by heating at a rate of 5°C per minute by using an aluminum plate as a reference. As the DSC chart is shown in Fig. 2, the compound was found to have a glass transition temperature (T_g) of 103.4°C, a crystallization temperature (T_c) of 138.7°C and 180.1°C, and a melting point of 277.9°C.

Cyclic voltammetry (CV):

[0039] p-MBTAB was dissolved in dichloromethane and the solution was arranged at a concentration of 10^{-3} M. The oxidation-reduction characteristics of the sample were measured using tetrabutylammonium perchlorate ((n-C₄H₉)₄NClO₄ (0.1M)) as a supporting electrolyte and Ag/Ag⁺ as a reference electrode at a scan speed of 20 mV/s. As the CV chart is shown in Fig. 3, the oxidation potential defined as an average of peak potential of oxidation curve and peak potential of reduction curve is 0.49 V (vs. Ag/Ag⁺), and the oxidation-reduction process was found to be reversible in 50 times measurement. In addition, the peak current of oxidation curve had an average of 2.565×10^{-6} A, a maximum of 2.596×10^{-6} A and a minimum of 2.533×10^{-6} A, and hence the deviation was only within ± 1.21 %. Thus, p-MBTAB had stable oxidation-reduction characteristics and was almost free from deterioration in repeated oxidation-reduction process.

Comparative Example 1

(Preparation of 1,3,5-tris(1-naphthylamino)benzene)

[0040] 4.4 g of phloroglucinol, 25 g of 1-naphthylamine and 0.5 g of iodine were placed in a 100 mL capacity three necked flask and the reaction was carried out at a temperature of 140°C for 4 hours with stirring under a nitrogen atmosphere. After the reaction, the resultant reaction mixture was washed with methanol, hexane and methanol in this order, followed by drying to provide 4.4 g of the desired 1,3,5-tris(1-naphthylamino)benzene as slightly reddish solid. The yield was 25%.

(Preparation of 1,3,5-tris(N-(4-biphenyl)-N-(1-naphthyl)amino)-benzene (TBNAB))

[0041] 2.0 g of 1,3,5-tris(1-naphthylamino)benzene, 5.0 g of 4-iodobiphenyl, 3.7 g of potassium carbonate, 2 g of copper powder, 0.3 g of 18-crown-6 (or 1,4,7,10,13,16-hexaoxacyclooctadecane) and 10 mL of mesitylene (reaction solvent) were placed in a 100 mL capacity glass flask and the reaction was carried out at a temperature of 170°C for 17 hours under a nitrogen atmosphere. After the reaction, the resultant reaction mixture was extracted with toluene and the toluene solution was subjected to silica gel chromatography to fractionate the reaction product. The reaction product was then purified by recrystallization from a mixed solvent of toluene/hexane and then by sublimation to provide 1.2 g of the desired 1,3,5-tris(N-(4-biphenyl)-N-(1-naphthyl)amino)benzene (TBNAB). The yield was 32%.
Elemental analysis (%):

	C	H	N
Calculated:	90.25	5.36	4.39
Measured:	89.96	5.44	4.32

Mass analysis: 957 (M⁺)

Differential scanning calorimetry (DSC):

[0042] About 5mg of TBNAB was weighed as a sample, and it was melted in a differential scanning calorimetric device and cooled to room temperature at a rate of 50°C per minute. The sample did not crystallized, but it became amorphous glass. Subsequently, the thermal characteristics of the sample were measured by heating at a rate of 5°C per minute by using an aluminum plate as a reference. As the DSC chart is shown in Fig. 4, the compound was found to have a glass transition temperature (T_g) of 130°C, a crystallization temperature (T_c) of 204°C and a melting point (T_m) of 271°C.

Cyclic voltammetry (CV):

[0043] TBNAB was dissolved in dichloromethane and the solution was subjected to measurement of oxidation-reduction characteristics in the same manner as Example 1. As the CV chart is shown in Fig. 5, the compound had an oxidation potential of 0.6 V (vs. Ag/Ag⁺). It was found that the compound had reversibility in oxidation-reduction process after 50 times measurements. However, it was found that the peak current of oxidation curve had an average of 4.257×10^{-4} A, a maximum of 4.687×10^{-4} A and a minimum of 3.816×10^{-4} A, and the deviation was as large as ± 10.1 %.

Example 2

[0044] A sheet of plate glass having an ITO coating on one face (available from Sanyo Vacuum K.K.) was subjected to ultrasonic cleaning using acetone and then steam cleaning using methanol, followed by irradiation with ultraviolet rays by using a low-pressure mercury lamp for 10 minutes. Immediately after the irradiation, copper phthalocyanine (CuPC) was vapor deposited to form a hole injecting layer 20 nm thick and then p-MBTAB was vapor deposited to form a hole transporting layer 40 nm thick in this order on the ITO coating by using a vacuum deposition apparatus. Subsequently, an emission layer 75 nm thick was formed of tris(8-quinolinol)aluminum (Alq₃) on the hole transporting layer, and then a lithium fluoride layer 0.5 nm thick and an aluminum layer 100 nm thick were layered in this order on the emission layer to form a cathode, thereby providing an organic electroluminescence element.

[0045] The change of luminance with time was examined by applying voltage across the electrodes of the organic electroluminescence element, letting the initial luminance (1000 cd/m²) be 100%. The results are shown in FIG. 6. The voltage-luminance characteristics of the organic electroluminescence element were also examined by applying voltage across the electrodes. The results are shown in FIG. 7.

Comparative example 2

[0046] 1,3,5-Tris(p-N-phenyl-N-m-tolyl)aminophenyl)benzene (m-MTDAPB) was used in place of p-MBTAB, and otherwise in the same manner as Example 1, an organic electroluminescence element was obtained. The change of luminance with time was examined by applying voltage across the electrodes of the organic electroluminescence element, letting the initial luminance (1000 cd/m²) be 100%.

[0047] As the results are shown in FIG. 6, the organic electroluminescence element having a hole transporting layer formed of p-MBTAB, a hole transporting agent of the invention, is superior in life to the organic electroluminescence element having a hole transporting layer formed of m-MTDAPB, a hole transporting agent of Comparative Example.

Example 3

[0048] A sheet of plate glass having an ITO coating on one face (available from Sanyo Vacuum K.K.) was subjected to ultrasonic cleaning using acetone and then steam cleaning using methanol, followed by irradiation with ultraviolet rays by using a low-pressure mercury lamp for 10 minutes. Immediately after the irradiation, 4,4',4"-tris(N-(2-naphthyl)-N-phenylamino)triphenylamine (2-TNATA) was vapor deposited to form a hole injecting layer 50 nm thick and then p-MBTAB was vapor deposited to form a hole transporting layer 10 nm thick in this order on the ITO coating by using a vacuum deposition apparatus. Subsequently, an emission layer 75 nm thick was formed of tris(8-quinolinol)aluminum (Alq₃) on the hole transporting layer, and then a lithium fluoride layer 0.5 nm thick and an aluminum layer 100 nm thick were layered in this order on the emission layer to form a cathode, thereby providing an organic electroluminescence element.

[0049] The voltage-luminance characteristics of the organic electroluminescence element were examined by applying voltage across the electrodes. The results are shown in FIG. 7.

Comparative example 3

[0050] 4,4'-bis[N-(2-naphthyl)-N-phenylamino]biphenyl (α -NPD) was used in place of p-MBTAB, and otherwise in the same manner as Example 1, an organic electroluminescence element was obtained. The voltage-luminance characteristics of the organic electroluminescence element were examined by applying voltage across the electrodes. The results are shown in FIG. 7.


Comparative example 4

[0051] Copper phthalocyanine (CuPC) was used in place of 2-TNATA to form a hole injecting layer 20 nm thick and then α -NPD was used in place of p-MBTAB to form a hole transporting layer 40 nm thick on the hole injecting layer, and otherwise in the same manner as Example 3, an organic electroluminescence element was obtained. The voltage-luminance characteristics of the organic electroluminescence element was examined by applying voltage across the electrodes.


[0052] As the results are shown in FIG. 7, the organic electroluminescence elements each having the hole transporting layer formed of p-MBTAB, a hole transporting agent of the invention, and a hole injecting layer formed of the known hole injecting agent (Examples 2 and 3) had a higher luminance than the organic electroluminescence elements each having a hole transporting layer formed of the known hole transporting agent and a hole injecting layer formed of the known hole injecting agent (Comparative Examples 3 and 4) when the same voltage was applied.

Claims

1. An organo-electronic functional material comprising a tris(arylamino)benzene represented by the general formula (I)




wherein A and B may be the same or different from each other and are each a group represented by the general formula (II)



in which R is an alkyl group of 1-6 carbons or a cycloalkyl group of 5 or 6 carbon atoms and n is 1, 2 or 3 in A and n is 0, 1, 2 or 3 in B;

and exhibiting a cyclic voltamogram in which a deviation of peak current of cyclic curves as measured 50 times at a sweep rate of 20 mV/s falls within $\pm 10\%$ of the average of peak current.


2. An organo-electronic functional material as claimed in claim 1 which comprises a tris(arylamino)benzene wherein the group A is a biphenyl or a terphenyl group which has an alkyl group of 1-6 carbon atoms or a cycloalkyl group of 5 or 6 carbon atoms at the terminal phenyl group thereof and the group B is a phenyl group which has an alkyl group of 1-6 carbons or a cycloalkyl group having 5 or 6 carbons.
3. An organo-electronic functional material as claimed in claim 1 in which the tris(arylamino)benzene is 1,3,5-tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzene.
4. A hole transporting agent comprising an organo-electronic functional material as claimed in any one of claims 1 to 3.
5. An organic electroluminescence element having a hole transporting layer containing the hole transporting agent as claimed in claim 4.
6. The organic electroluminescence element having a hole transporting layer containing a hole transporting agent according to claim 5 further comprising a hole injecting layer containing a hole injecting agent comprising a tris (4-(N, N-diarylamino)phenyl)amine represented by the general formula (III)




wherein X and Y are each an aryl group and may be the same or different from each other.

Patentansprüche

1. Organo-elektronisches, funktionales Material, welches ein Tris(arylamino)benzol, dargestellt durch die allgemeine Formel (I)



worin A und B gleich oder unterschiedlich zueinander sein können und jeweils eine Gruppe sind, dargestellt durch die allgemeine Formel (II)




in welcher R eine Alkylgruppe mit 1-6 Kohlenstoff, oder eine Cycloalkylgruppe mit 5 oder 6 Kohlenstoffatomen ist und n ist 1, 2 oder 3 in A und n ist 0, 1, 2 oder 3 in B, umfasst;
und ein zyklisches Voltammogramm, in welchem eine Abweichung des Spitzenstroms von zyklischen Kurven, 50-Mal bei einer Geschwindigkeit des Potentialvorschubs von 20 mV/s gemessen, innerhalb von $\pm 10\%$ des durchschnittlichen Spitzenstroms fällt, aufweist.

2. Ein organo-elektronisches, funktionales Material wie in Anspruch 1 beansprucht, welches ein Tris(arylamino)benzol

umfasst, worin die Gruppe A eine Biphenyl-, oder eine Terphenylgruppe ist, welche eine Alkylgruppe mit 1-6 Kohlenstoffatomen, oder eine Cycloalkylgruppe mit 5 oder 6 Kohlenstoffatomen an der terminalen Phenylgruppe davon aufweist, und die Gruppe B eine Phenylgruppe ist, welche eine Alkylgruppe mit 1-6 Kohlenstoffen oder eine Cycloalkylgruppe mit 5 oder 6 Kohlenstoffatomen aufweist.


3. Ein organo-elektronisches, funktionales Material wie in Anspruch 1 beansprucht, in welchem das Tris(arylamino)benzol ein 1,3,5-Tris(N-(4'-methyl-4-biphenyl)-N-(p-tolyl)amino)benzol ist.
4. Ein Loch-transportierendes Agens, umfassend ein organo-elektronisches, funktionales Material wie in einem der Ansprüche 1 bis 3 beansprucht.
5. Ein organisches Elektrolumineszenzelement mit einer Loch-transportierenden Schicht, enthaltend das Loch-transportierende Agens wie in Anspruch 4 beansprucht.
6. Das organische Elektrolumineszenzelement mit einer Loch-transportierenden Schicht, enthaltend ein Loch-transportierendes Agens gemäß Anspruch 5, weiterhin umfassend eine Loch-injizierende Schicht, enthaltend ein Loch-injizierendes Agens, umfassend ein Tris(4-(N,N-diarylamino)phenyl)amin, dargestellt durch die allgemeine Formel (III)




worin X und Y jeweils eine Arylgruppe sind und gleich oder unterschiedlich zueinander sein können.

Revendications

1. Matériau fonctionnel organo-électronique comprenant un tris-(aryl-amino)-benzène représenté par la formule générale (I) :




dans laquelle les symboles A et B représentent des entités qui peuvent être identiques ou différentes les unes des autres, et représentent chacun un groupe représenté par la formule générale (II) :



10 dans laquelle R représente un groupe alkyle comportant de 1 à 6 atomes de carbone ou un groupe cycloalkyle comportant 5 ou 6 atomes de carbone, et l'indice n vaut 1, 2 ou 3 dans les groupes symbolisés par A, mais vaut 0, 1, 2 ou 3 dans les groupes symbolisés par B, et présentant un voltamogramme cyclique dans lequel l'écart du courant de pic des courbes cycliques, mesurées 50 fois avec une vitesse de balayage de 20 mV/s, se situe à ± 10 % de la valeur moyenne du courant de pic.

- 15 2. Matériau fonctionnel organo-électronique conforme à la revendication 1, qui comprend un tris(aryl-amino)-benzène dans lequel le groupe symbolisé par A est un groupe biphenyle ou terphenyle qui porte, sur son groupe phényle terminal, un groupe alkyle comportant de 1 à 6 atomes de carbone ou un groupe cycloalkyle comportant 5 ou 6 atomes de carbone, et le groupe symbolisé par B est un groupe phényle qui porte un groupe alkyle comportant de 1 à 6 atomes de carbone ou un groupe cycloalkyle comportant 5 ou 6 atomes de carbone.
- 20 3. Matériau fonctionnel organo-électronique conforme à la revendication 1, dans lequel le tris(aryl-amino)-benzène est du 1,3,5-tris-[N-(4'-méthyl-biphényl-4-yl)-N-(para-tolyl)-amino]-benzène.
- 25 4. Agent de transport de trous, comprenant un matériau fonctionnel organo-électronique conforme à l'une des revendications 1 à 3.
5. Élément électroluminescent organique comportant une couche à transport de trous qui contient un agent de transport de trous conforme à la revendication 4.
- 30 6. Élément électroluminescent organique comportant une couche à transport de trous qui contient un agent de transport de trous, conforme à la revendication 5, et comportant en outre une couche à injection de trous qui contient un agent d'injection de trous, lequel comprend une tris[4-(N,N-diaryl-amino)-phényl]-amine représentée par la formule générale (III) :



50 dans laquelle les symboles X et Y représentent chacun un groupe aryle, lesquels groupes peuvent être identiques ou différents les uns des autres.

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6





FIG. 7



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 11174707 A [0002]
- JP 8291115 A [0002] [0005]
- JP 1224353 A [0005]
- JP 2003079441 A [0009]
- JP 10090256 A [0011]
- JP 5234681 A [0011]

Non-patent literature cited in the description

- Bando Technical Report. Bando Chemical Industries, Ltd, 1998, vol. 2, 9-18 [0007]
- Cation Radicals of 1,3,5-Tris(diarylamino)benzenes. **STICKLEY K R et al.** TETRAHEDRON LETTERS. ELSEVIER, vol. 36, 1585-1588 [0012]

专利名称(译)	有机电子功能材料及其用途		
公开(公告)号	EP1696709A4	公开(公告)日	2009-01-07
申请号	EP2004799796	申请日	2004-11-17
[标]申请(专利权)人(译)	邦多化学株式会社		
申请(专利权)人(译)	BANDO CHEMICAL INDUSTRIES , LTD		
当前申请(专利权)人(译)	BANDO CHEMICAL INDUSTRIES , LTD		
[标]发明人	AKASHI N C O BANDO CHEM IND LTD SHIROTA YASUHIKO		
发明人	AKASHI, N., C/O BANDO CHEMICAL INDUSTRIES, LTD. SHIROTA, YASUHIKO		
IPC分类号	H05B33/22 H01L51/54 C09K11/06 H01L51/00 H01L51/50 H05B33/14		
CPC分类号	H01L51/0059 H01L51/0081 H01L51/5048 H01L51/5088 H01L2251/308 Y10S428/917		
优先权	2003404721 2003-12-03 JP 2003391882 2003-11-21 JP		
其他公开文献	EP1696709B1 EP1696709A1		
外部链接	Espacenet		

摘要(译)

本发明提供一种有机电子功能材料，其包含通式 (I) 表示的三 (芳基氨基) 苯，其中A和B各自为通式 (II) 表示的基团，其中R为1-的烷基。6个碳或5或6个碳原子的环烷基且n为0,1,2或3，并且A和B可以彼此相同或不同，并且显示出其中峰值电流的偏差的循环伏安图。在20mV / s的扫描速率下测量50次的循环曲线落在峰值电流平均值的±10%范围内。有机电子功能材料具有光电交换功能，可逆氧化还原性和高玻璃化转变温度，并且可以自身形成非晶膜。另外，它是稳定的并且在重复氧化还原过程中仅表现出峰值电流的轻微变化，因此它适合用作例如包括有机电致发光元件的各种电子器件中的空穴传输材料。

