

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 July 2008 (10.07.2008)

PCT

(10) International Publication Number
WO 2008/082249 A1

(51) International Patent Classification:

C09K 11/06 (2006.01)

(21) International Application Number:

PCT/KR2008/000008

(22) International Filing Date: 2 January 2008 (02.01.2008)

(25) Filing Language:

Korean

(26) Publication Language:

English

(30) Priority Data:

10-2007-0000904 4 January 2007 (04.01.2007) KR

(71) Applicants (for all designated States except US): **GRA-**

CEL DISPLAY INC. [KR/KR]; 5Floor, Samyang Techno Town, 284-25 Seongsoo-dong 2ga, Seondong-gu, Seoul 133-833 (KR). **KIM, Nam Kyun** [KR/KR]; 103-1305, Hyundai Apt., Pungnap 2-dong, Songpa-gu, Seoul 138-785 (KR). **KIM, Sung Min** [KR/KR]; 102-ho, Salremhouse, 392-27 Hwagok-8 dong, Kangseo-gu, Seoul 157-886 (KR).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KIM, Hyun**

[KR/KR]; 273, Hagye 2-dong, Nowon-gu, Seoul 139-873 (KR). **LEE, Ho Joon** [KR/KR]; 72-25, Sangsu-dong,

Mapo-gu, Seoul 121-282 (KR). **KWON, Hyuck Joo** [KR/KR]; 224-2001, Samsung Raemian 2 Cha Apt., Jang-gan dong, Dongdaemun-gu, Seoul 130-100 (KR). **CHO, Young Jun** [KR/KR]; 31-203, Sindonga Apt., Banghak 3-dong, Dobong-gu, Seoul 132-739 (KR). **KIM, Bong Ok** [—/KR]; 101-1108, Hansol Apt., 4 Samseong-dong, Gangnam-gu, Seoul 135-090 (KR). **YOON, Seung Soo** [KR/KR]; 405-1409, Samik Apt., Suseo-dong, Gangnam-gu, Seoul 135-884 (KR).

(74) Agents: **KWON, Oh-Sig** et al.; 4f, Joeeunleaderstel, 921 Dunsan-dong, Seo-gu, Daejeon 302-120 (KR).


(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH,

[Continued on next page]

(54) Title: ORGANOMETALIC COMPOUNDS FOR ELECTROLUMINESCENCE AND ORGANIC ELECTROLUMINESCENT DEVICE USING THE SAME



(57) Abstract: The present invention relates to organic electroluminescent compounds and electroluminescent devices comprising the same as host material. The electroluminescent compounds according to the invention are characterized by having three ligands, two bivalent metals and a monovalent anion derived from an inorganic or an organic acid.

WO 2008/082249 A1



GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report*

ORGANOMETALIC COMPOUNDS FOR ELECTROLUMINESCENCE AND ORGANIC
ELECTROLUMINESCENT DEVICE USING THE SAME

【Technical Field】




5 The present invention relates to electroluminescent compounds consisting of metal complex exhibiting excellent electric conductivity and highly efficient electroluminescent properties, and electroluminescent devices using the same as host material.

10





【Background Art】

 The most important factor to determine luminous efficiency in an OLED is the type of electroluminescent material. Though a fluorescent material has been widely used
15 as an electroluminescent material up to the present, development of phosphorescent material is one of the best methods to improve luminous efficiency theoretically up to four (4) times, in view of electroluminescent mechanism.

Up to now, iridium (III) complexes are widely known as
20 phosphorescent material, including (acac)Ir(btp)₂, Ir(ppy)₃ and Firpic, as the red, green and blue one, respectively. In particular, a number of phosphorescent materials have been recently investigated in Japan, Europe and America.

**(acac)Ir(btp)₂****Ir(ppy)₃****Firpic**


As a host material for phosphorescent light emitting material, CBP is most widely known up to the present, and
 5 OLEDs having high efficiency to which a hole blocking layer (such as BCP and BALq) has been applied have been known. Pioneer (Japan) or the like reported OLEDs having high efficiency using a BALq derivative as the host.

**CBP****BCP****BALq****BALq derivative**

Though the materials in prior art are advantageous in view of light emitting property, they have low glass

transition temperature and very poor thermal stability, so that the materials tend to be changed during high temperature vapor-deposition in vacuo. In an organic electroluminescent device (OLED), it is defined that power efficiency =
5 (π/voltage) x current efficiency. Thus, the power efficiency is inversely proportional to the voltage, while the power efficiency should be higher in order to obtain lower power consumption of an OLED. In practice, an OLED employing phosphorescent electroluminescent (EL) material shows
10 significantly higher current efficiency (cd/A) than an OLED employing fluorescent EL material. However, in case that a conventional material such as BA1q and CBP as host material of the phosphorescent EL material is employed, no significant advantage can be obtained in terms of power efficiency (lm/w)
15 because of higher operating voltage as compared to an OLED employing a fluorescent material.

The present inventors invented EL compounds of the structures represented below, including the skeletal of a mixed-type ligand metal complex, which has far better EL
20 properties and physical properties than those of conventional organic host materials or aluminum complexes; and filed as Korean Patent Application No. 2006-7467.



Conventional complexes of this type have been already investigated extensively since the middle of 1990's, as an EL material such as blue EL material. However, those materials have been simply applied as an EL material, with rare examples known to be applied as a host material for a phosphorescent EL material.

According to the present invention, developed was a metal complex material exhibiting excellent material stability, better electric conductivity and highly efficient EL properties as compared to conventional materials. A heteroatom included in an aromatic ring or in a side chain substituent having unpaired electron pair, has a high tendency of being coordinated with metal. Such a coordinate bond with very stable electrochemical property is a widely known property of the complex. By means of such a property, the present invention have developed various ligands, and prepared metal complexes, which were applied as host material.


【Technical Problem】

The object of the present invention is to overcome the disadvantages as described above, and to provide EL compounds having the skeletal of a novel ligand metal complex to give more excellent electroluminescent properties and physical properties as compared to conventional organic host material or aluminum complexes. Another object of the present invention is to provide novel EL devices comprising the EL compounds thus prepared as host material.

【Technical Solution】


The present invention relates to EL compounds represented by Chemical Formula (1), and EL devices comprising the EL compounds thus prepared as host material. The EL compound according to the present invention is characterized in that the compound consists of three ligands, two bivalent metals and a monovalent anion derived from an inorganic or an organic acid.

[Chemical Formula 1]




In the Formula, the ligands (L1, L2 and L3) are independently selected from the structures represented by following chemical structure; M is a bivalent metal; and Q is

a monovalent anion derived from an inorganic or an organic acid.




5 In the ligands, X is O, S or Se; ring A is oxazole, thiazole, imidazole, oxadiazole, thiadiazole, benzoxazole, benzothiazole, benzoimidazole, pyridine or quinoline; R1 through R4 independently represent hydrogen, C1-C5 alkyl, halogen, silyl group or C6-C20 aryl, or they may be bonded to
10 an adjacent substituent via alkylene or alkenylene to form a fused ring; the pyridine and quinoline may chemically bonded to R1 to form a fused ring; and the ring A and aryl group of R1 through R7 may be further substituted by C1-C5 alkyl, halogen, C1-C5 alkyl having halogen substituent(s), phenyl,
15 naphthyl, silyl or amino group.


Preferably, the ligands (L1, L2 and L3) are independently selected from one of the following chemical structures:



In the ligands, X and R₁ through R₄ are defined as in Chemical Formula (1); Y is O, S or NR₂₁, Z is CH or N; R₁₁ through R₁₆ independently represent hydrogen, C₁-C₅ alkyl, halogen, C₁-C₅ alkyl having halogen substituent(s), phenyl, naphthyl, silyl or amino group, R₁₁ through R₁₄ may be bonded to an adjacent substituent via alkylene or alkenylene to form a fused ring, and R₂₁ is C₁-C₅ alkyl, substituted or unsubstituted phenyl or naphthyl group.









In particular, the ligands (L1, L2 and L3) of the EL compounds according to the present invention may be identical, and selected from one of the following chemical structures:























wherein, X is O, S or Se, and R₂, R₃, R₁₂ and R₁₃ independently represent hydrogen, methyl, ethyl, n-propyl, isopropyl, fluorine, chlorine, trifluoromethyl, phenyl, naphthyl, fluorenyl, trimethylsilyl, triphenylsilyl, t-butyl-
5 dimethyldimethylsilyl, dimethylamine, diethylamine or diphenylamine; and the phenyl, naphthyl or fluorenyl may be further substituted by fluorine, chlorine, trimethylsilyl, triphenylsilyl, t-butyl-
10 dimethyldimethylsilyl, dimethylamine, diethylamine or diphenylamine.





The electroluminescent compounds according to the present invention can be specifically exemplified by the compounds represented by one of the following compounds, but not being
15 restricted thereto:


















5 The electroluminescent device according to the present invention is characterized in that it employs the EL compound of the present invention as the host material for electroluminescent layer.

 The EL compounds according to the present invention can
10 be prepared by reacting the ligand with metal salt under basic

aqueous condition in a molar ratio of 3:2.



5 【Brief Description of Drawings】

Fig. 1 is a cross-sectional view of an OLED device;

Fig. 2 shows voltage-luminance property of the OLED's manufactured according to Example 15 and Comparative Example 1;

Fig. 3 shows luminance-current efficiency of the OLED's manufactured according to Example 15 and Comparative Example 1;

Fig. 4 shows an EL spectrum of the OLED's manufactured according to Example 15 and Comparative Example 1.

15 【Description of important parts of the drawings】

- 1 - glass
- 2 - transparent electrode
- 3 - a hole injection layer
- 4 - a hole transportation layer

- 5 - an electroluminescent layer
- 6 - an electron transportation layer
- 7 - an electron injection layer
- 8 - Al cathode

5

【Best Mode】

[Preparation Examples]

[Preparation Example 1] Preparation of Compound (1)

In ethanol (1.2 L, 0.05 M), dissolved were 2-(2-hydroxyphenyl)benzothiazole (40.0 g, 176 mmol) and ZnCl₂ (16.0 g, 117.3 mmol), and the solution was stirred. To the solution, NH₄OH (20 mL, 235 mmol) was added dropwise, and the resultant mixture was stirred at 60°C under reflux for 30 minutes. After cooling the mixture to room temperature, additional NH₄OH (20 mL) was added dropwise thereto, and the resultant mixture was stirred at room temperature for 12 hours. Water (400 mL) was then added, and the mixture was stirred for 6 hours, washed with water (1 L), EtOH (1.5 L) and hexane (500 mL), filtered and dried to obtain Compound (1) (35 g, 43.2 mmol, 74%).

20 mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55(m, 2H), 7.31(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.4 Hz, 1H), 6.88(t, J = 7.7 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB: 805.96 (found), 809.6 (calculated)

[Preparation Example 2] Preparation of Compound (2)

In ethanol (100 mL, 0.07 M), dissolved were 2-(2-hydroxyphenyl)benzothiazole (5 g, 22 mmol) and ZnCN_2 (1.7 g, 14.6 mmol), and the solution was stirred at room temperature for 30 minutes. Then, NH_4OH (2.89 mL) was slowly added and the resultant mixture was stirred for 12 hours, and then washed with water (300 mL), EtOH (300 mL) and hexane (200 mL). Filtration and drying gave Compound (2) (2.0 g, 2.5 mmol, 34%).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.22-8.12(m, 2H), 7.56(m, 2H), 7.30(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.2 Hz, 1H), 6.88(t, J = 7.7 Hz, 1H), 6.80(d, J = 7.2 Hz, 1H),

MS/FAB: 805.96 (found), 809.6 (calculated)

[Preparation Example 3] Preparation of Compound (3)

Compound (3) (1.8 g, 2.2 mmol, 75%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), $\text{ZnBr}_2 \cdot \text{H}_2\text{O}$ (1.54 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH_4OH (2.0 mL) and water (20 mL).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.22-8.12(m, 2H), 7.55(m, 2H), 7.31(d, J = 7.7 Hz, 1H), 7.04(t, J = 7.2 Hz, 1H), 6.88(t, J =

7.6 Hz, 1H), 6.81(d, $J = 7.2$ Hz, 1H)

MS/FAB : 805.96(found), 809.6(calculated)

[Preparation Example 4] Preparation of Compound (4)

5 Compound (4) (1.6 g, 2.0 mmol, 60%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), $\text{ZnClO}_4 \cdot 6\text{H}_2\text{O}$ (2.2 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH_4OH (2.0 mL) and water (20 mL).

10 mp. > 300°C

^1H NMR (300 MHz, CDCl_3): $\delta = 8.22\text{--}8.12$ (m, 2H), 7.55 (m, 2H), 7.31 (d, $J = 7.7$ Hz, 1H), 7.05 (t, $J = 7.2$ Hz, 1H), 6.89 (t, $J = 7.6$ Hz, 1H), 6.79 (d, $J = 7.2$ Hz, 1H)

MS/FAB : 805.96(found), 809.6(calculated)

15

[Preparation Example 5] Preparation of Compound (5)

Compound (5) (1.6 g, 2.0 mmol, 60%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), $\text{Zn}(\text{BF}_4)_2$ (1.4 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH_4OH (2.0 mL) and water (20 mL).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): $\delta = 8.23\text{--}8.12$ (m, 2H), 7.55 (m, 2H), 7.31 (d, $J = 7.7$ Hz, 1H), 7.01 (t, $J = 7.2$ Hz, 1H), 6.89 (t, $J =$

7.7 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB: 805.96 (found), 809.6 (calculated)

[Preparation Example 6] Preparation of Compound (6)

5 Compound (6) (1.2 g, 1.5 mmol, 42%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), Zn(p-OTs)₂ (2.4 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH₄OH (2.0 mL) and water (20 mL).

10 mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55(m, 2H), 7.31(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.2 Hz, 1H), 6.88(t, J = 7.7 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB: 805.96 (found), 809.6 (calculated)

15

[Preparation Example 7] Preparation of Compound (7)

20 Compound (7) (1.3 g, 1.6 mmol, 42%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), Zn(CF₃COO)₂ (1.3 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.22-8.12(m, 2H), 7.55(m, 2H), 7.31(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.2 Hz, 1H), 6.88(t, J =

7.4 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB : 805.96(found), 809.6(calculated)

[Preparation Example 8] Preparation of Compound (8)

5 Compound (8) (2 g, 2.5 mmol, 85%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), $\text{Zn}(\text{CF}_3\text{SO}_3)_2$ (2.1 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH_4OH (2.0 mL) and water (20 mL).

10 mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.23-8.12(m, 2H), 7.55(m, 2H), 7.31(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.2 Hz, 1H), 6.88(t, J = 7.7 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB: 805.96 (found), 809.6 (calculated)

15

[Preparation Example 9] Preparation of Compound (9)

In dimethoxyethane (DME) (200 mL, 0.5 M) and H_2O (66 mL), dissolved were 5-bromosalicylaldehyde (20 g, 99.5 mmol) and phenylboronic acid (13.4 g, 109.5 mmol), and the solution was
20 stirred. To the solution, added were $\text{Pd}(\text{PPh}_3)_4$ (5.8 g, 5.0 mmol) and aqueous 2M K_2CO_3 solution (66 mL), and the mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL), the reaction mixture was washed, and extracted with ethylacetate (EA) (200 mL). Drying under

reduced pressure and purification via silica gel column chromatography (n-hexane: methylene chloride (MC) = 1:5) gave 5-phenylsalicylaldehyde (12 g, 61 mmol, 61%).

The compound, 5-phenylsalicylaldehyde (5.0 g, 25.2 mmol) thus obtained and 2-aminobenzenethiol (3.8 g, 30.2 mmol) were dissolved in 1,4-dioxane (12 mL, 2.1 M), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (100 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-phenylphenol (4.5 g, 14.8 mmol, 59%).

Compound (9) (2 g, 2.5 mmol, 85%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-phenylphenol (2.0 g, 6.6 mmol), ZnCl₂ (600 mg, 4.4 mmol), EtOH (100 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55(m, 2H), 7.53(s, 1H), 7.48(d, J = 7.3 Hz, 2H), 7.32(m, 2H), 7.27(d, J = 7.1 Hz, 1H), 7.27(t, J = 6.2 Hz, 1H), 6.85(d, J = 7.3 Hz, 1H)

MS/FAB : 1034.05(found), 1037.89(calculated)

[Preparation Example 10] Preparation of Compound (10)

The compound, 2-aminobenzenethiol (5.3 g, 42.4 mmol) and 5-methylsalicylaldehyde (4.8 g, 35.3 mmol) were dissolved in 1,4-dioxane (12 mL, 2.1 M), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (100 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-methylphenol (3.1 g, 13.0 mmol, 37%).

Compound (10) (2 g, 2.35 mmol, 84%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-methylphenol (2.0 g, 8.3 mmol) thus obtained, ZnCl₂ (750 mg, 5.5 mmol), EtOH (130 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55(m, 2H), 7.11(s, 1H), 6.75(m, 2H), 2.35(s, 1H)

MS/FAB : 848.0(found), 851.68(calculated)

[Preparation Example 11] Preparation of Compound (11)

The compound, 2-aminobenzenethiol (7.27 g, 58.08 mmol) and 2-hydroxy-1-naphthaldehyde (10 g, 58.08 mmol) were dissolved in 1,4-dioxane (20 mL, 2.9 M), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to

room temperature, the reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 1-(benzo[d]thiazol-2-yl)-4-naphthalen-2-ol (10 g, 36.1 mmol, 62%).

Compound (11) (1.5 g, 1.6 mmol, 66%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 1-(benzo[d]thiazol-2-yl)naphthalen-2-ol (2.0 g, 7.2 mmol) thus obtained, ZnCl₂ (654 mg, 4.8 mmol), EtOH (120 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.21-8.12(m, 2H), 7.60-7.48(m, 5H), 7.31-7.2(m, 2H), 7.0(d, J = 7.2 Hz, 1H)

MS/FAB : 956(found), 959.78(calculated)

[Preparation Example 12] Preparation of Compound (12)

In 1,4-dioxane (50 mL, 4.0 M), dissolved were 2-aminobenzenethiol (24.8 g, 198 mmol) and 5-bromosalicylaldehyde (40 g, 198 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (300 mL), washed with water (200 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 2:1) gave 2-(benzo[d]thiazol-2-yl)-4-

bromophenol (34 g, 118.4 mmol, 60%).

Under argon atmosphere, 2-(benzo[d]thiazol-2-yl)-4-bromophenol (4 g, 13.1 mmol) was dissolved in THF (50 mL, 0.03 M), and the solution was cooled to -78°C. To the solution, n-BuLi (2.5 M in hexane, 7.9 mL, 19.7 mmol) was added dropwise, and the mixture was stirred for 30 minutes. Trimethylsilylchloride (TMSCl) (1.4 g, 13.1 mmol) dissolved in THF (25 mL, 0.5 M) was slowly added thereto, and the reaction mixture was stirred for 12 hours while slowly raising the temperature to room temperature. After quenching with water (100 mL), the reaction mixture was extracted with MC (50 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-trimethylsilylphenol (3 g, 10.1 mmol, 62%).

Compound (12) (1.3 g, 1.3 mmol, 58%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-trimethylsilylphenol (2.0 g, 6.7 mmol) thus obtained, ZnCl₂ (613 mg, 4.5 mmol), EtOH (110 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.22-8.12 (m, 2H), 7.55-7.27 (m, 4H), 6.77 (d, J = 7.2 Hz, 1H)

MS/FAB : 1022(found), 1026.15(calculated)

[Preparation Example 13] Preparation of Compound (13)

In 1,4-dioxane (30 mL, 2.1 M), dissolved were 2-
5 aminobenzenethiol (8.9 g, 71.4 mmol) and 5-
fluorosalicylaldehyde (10 g, 71.4 mmol), and the solution was
stirred at 100°C under pressure for 12 hours. After cooling to
room temperature, the reaction mixture was extracted with MC
(150 mL), washed with water (100 mL) and dried under reduced
10 pressure. Purification via silica gel column chromatography
(n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-
fluorophenol (7 g, 50.0 mmol, 70%).

Compound (13) (1.8 g, 2.1 mmol, 44%) was obtained by
repeating the same procedure as described in Preparation
15 Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-fluorophenol
(2.0 g, 14.3 mmol) thus obtained, ZnCl₂ (1.3 g, 9.5 mmol), EtOH
(200 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55(m, 2H),
20 7.02(s, 1H), 6.77-6.70(m, 2H)

MS/FAB : 860(found), 863.58(calculated)

[Preparation Example 14] Preparation of Compound (14)

In 1,4-dioxane (50 mL, 4.0 M), dissolved were 2-

aminobenzenethiol (24.8 g, 198 mmol) and 5-bromosalicylaldehyde (40 g, 198 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (300 mL), washed with water (200 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 2:1) gave 2-(benzo[d]thiazol-2-yl)-4-bromophenol (34 g, 118.4 mmol, 60%).

The compound, 2-(benzo[d]thiazol-2-yl)-4-bromophenol (5 g, 16.33 mmol) thus obtained and 4-bromophenylboronic acid (3.94 g, 19.6 mmol) were dissolved in toluene (40 mL), EtOH (27 mL) and H₂O (13 mL), and the solution was stirred. To the solution, added were PdCl₂(PPh₃)₂ (573 mg, 0.82 mmol) and K₂CO₃ (4.51 g, 32.66 mmol), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:4) gave 2-(benzo[d]thiazol-2-yl)-4-(4-bromophenyl)phenol (5.5 g, 14.5 mmol, 89%).

The compound, 2-(Benzo[d]thiazol-2-yl)-4-(4-bromophenyl)phenol (3 g, 7.89 mmol) thus obtained and diphenylamine (1.47 g, 8.68 mmol) were dissolved in toluene (30 mL), and the solution was stirred. To the solution, added

were $\text{Pd}(\text{OAc})_2$ (1.33 g, 0.006 mmol), $t\text{-BuONa}$ (1.14 g, 11.8 mmol), $\text{P}(t\text{-BuO})_3$ (4.79 mg, 0.024 mmol), and the mixture was stirred at 100°C under reflux for 6 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with
5 EA (100 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:2) gave 2-(benzo[d]thiazol-2-yl)-4-(4-diphenylaminophenyl)phenol (2.9 g, 6.2 mmol, 79%).

Compound (14) (1.7 g, 1.1 mmol, 79%) was obtained by
10 repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-diphenylaminophenyl)phenol (2.0 g, 4.25 mmol) thus obtained, ZnCl_2 (386 mg, 2.83 mmol), EtOH (200 mL, 0.02 M), NH_4OH (2.0 mL) and water (20 mL).

15 mp. $> 300^\circ\text{C}$

^1H NMR (300 MHz, CDCl_3): δ = 8.23-8.12 (m, 2H), 7.55-7.02 (m, 10H), 6.85-6.46 (m, 8H)

MS/FAB : 1535.27(found), 1539.51(calculated)

20 [Preparation Example 15] Preparation of Compound (15)

The compound, 5-bromosalicylaldehyde (20 g, 99.5 mmol) and 2-naphthyl boronic acid (18.8 g, 109.5 mmol) were dissolved in toluene (300 mL), and the solution was stirred. To the solution, added were $\text{Pd}(\text{PPh}_3)_4$ (5.8 g, 4.98 mmol) and 2M

K₂CO₃ (100 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:5) gave 5-(2-naphthyl)salicylaldehyde (14.4 g, 58 mmol, 58.3%).

In 1,4-dioxane (7 mL, 2.1 M), dissolved were 5-(2-naphthyl)salicylaldehyde (3.0 g, 12.1 mmol) and 2-aminobenzenethiol (1.8 g, 14.5 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (100 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-(2-naphthyl)phenol (2.8 g, 7.92 mmol, 65%).

Compound (15) (1.2 g, 1.01 mmol, 53%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(2-naphthyl)phenol (2.0 g, 5.7 mmol) thus obtained, ZnCl₂ (518 mg, 3.8 mmol), EtOH (100 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.9-7.53(m, 8H), 7.3-7.2(m, 3H), 6.85(d, J = 5.5 Hz, 1H)

MS/FAB : 1184.1(found), 1188.07(calculated)

[Preparation Example 16] Preparation of Compound (16)

The compound, 5-bromosalicylaldehyde (20 g, 99.5 mmol) and 9,9-dimethyl-9H-fluoren-2-yl-2-boronic acid (26.1 g, 109.5 mmol) were dissolved in toluene (300 mL, 0.33 M), and the solution was stirred. To the solution, added were Pd(PPh₃)₄ (5.8 g, 4.98 mmol) and 2M K₂CO₃ (100 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:5) gave 5-(9,9-dimethyl-9H-fluoren-2-yl)salicylaldehyde (19.2 g, 61 mmol, 61.3%).

In 1,4-dioxane (7 mL, 2.1 M), dissolved were 5-(9,9-dimethyl-9H-fluoren-2-yl)salicylaldehyde (3.8 g, 12.1 mmol) thus obtained and 2-aminobenzenethiol (1.8 g, 14.5 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (100 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-(9,9-dimethyl-9H-fluoren-2-yl)phenol (2.1 g, 5.01 mmol, 41%).

Compound (16) (1.0 g, 0.72 mmol, 45%) was obtained by

repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(9,9-dimethyl-9H-fluoren-2-yl)phenol (2.0 g, 4.8 mmol) thus obtained, ZnCl₂ (436 mg, 3.2 mmol), EtOH (80 mL, 0.02 M), NH₄OH (2.0 mL) and
5 water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.9-7.53(m, 8H), 7.38-7.0(m, 4H), 1.67(s, 6H)

MS/FAB : 1382.24(found), 1386.37(calculated)

10

[Preparation Example 17] Preparation of Compound (17)

Under argon atmosphere, 2-amino-6-bromobenzothiazole (20 g, 87.3 mmol) and 10 N KOH (100 mL) were added to ethylene glycol (20 mL), and the mixture was stirred at 125°C under
15 reflux for 15 hours. After cooling to room temperature, 12 N HCl (30 mL) was added to the reaction mixture to quench the reaction. The reaction mixture was then washed with water (100 mL) and extracted with EA (100 mL). Recrystallization from MeOH (200 mL) gave 2-amino-5-bromobenzenethiol (14 g, 68.6
20 mmol, 79%).

In 1,4-dioxane (35 mL, 2.0 M), dissolved were 2-amino-5-bromobenzenethiol (14 g, 68.6 mmol) and salicylaldehyde (7.0 g, 57.2 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the

reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 5:2) gave 2-(6-bromobenzo[d]thiazol-2-yl) phenol (15.5 g, 50.5 mmol, 88.3%).

Under argon atmosphere, 2-(6-bromobenzo[d]thiazol-2-yl)phenol (15.5 g, 50.5 mmol) was dissolved in THF (160 mL, 0.3 M), and the solution was cooled to -78°C. To the solution, t-BuLi (1.7 M in hexane, 44.6 mL, 75.8 mmol) was added dropwise, and the mixture was stirred for 30 minutes. Triphenylsilyl chloride (TPSCl) (22.3 g, 75.8 mmol) dissolved in THF (50 mL) was slowly added thereto. The reaction mixture was stirred for 12 hours while slowly raising the temperature to room temperature. After quenching the reaction by adding water (100 mL), the reaction mixture was extracted with MC (80 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(6-triphenylsilylbenzo[d]thiazol-2-yl)phenol (20.4 g, 42 mmol, 83%).

Compound (17) (1.0 g, 0.72 mmol, 45%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(6-triphenylsilylbenzo[d]thiazol-2-yl)phenol (2.0 g, 4.1 mmol), ZnCl₂ (375 mg, 2.7 mmol), EtOH (70 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.40–8.34 (m, 2H), 7.83–7.55 (m, 7H), 7.35 (s, 9H), 7.31 (d, J = 5.1 Hz, 1H), 7.0–6.7 (m, 3H)

MS/FAB : 1580.22 (found), 1584.77 (calculated)

5

[Preparation Example 18] Preparation of Compound (18)

In 1,4-dioxane (7 mL, 2.1 M), dissolved were 2-aminobenzenethiol (1.8 g, 14.5 mmol) and 3,5-dimethylsalicylaldehyde (1.64 g, 12.1 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (50 mL), washed with water (30 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4,6-dimethylphenol (2.3 g, 9.2 mmol, 76%).

Compound (18) (1.3 g, 1.5 mmol, 58%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4,6-dimethylphenol (2.0 g, 7.8 mmol), ZnCl₂ (709 mg, 5.2 mmol), EtOH (120 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23–8.12 (m, 2H), 7.53 (m, 2H), 6.92 (s, 1H), 6.65 (s, 1H), 4.6 (s, 1H)

MS/FAB : 1580.22 (found), 1584.77 (calculated)

[Preparation Example 19] Preparation of Compound (19)

The compound, 4-bromosalicylaldehyde (20 g, 99.5 mmol) and phenylboronic acid (26.1 g, 109.5 mmol) were dissolved in toluene (300 mL, 0.33 M), and the solution was stirred. To the solution, added were Pd(PPh₃)₄ (5.8 g, 4.98 mmol) and 2M K₂CO₃ (100 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:5) gave 4-phenyl salicylaldehyde (18.2 g, 60 mmol, 60%).

In 1,4-dioxane (7 mL, 2.1 M), dissolved were 2-aminobenzenethiol (1.8 g, 14.5 mmol) and 4-phenyl salicylaldehyde (1.64 g, 12.1 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (50 mL), washed with water (30 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-5-phenylphenol (2.3 g, 9.2 mmol, 76%).

Compound (19) (1.3 g, 1.5 mmol, 58%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-5-phenylphenol

(2.0 g, 7.8 mmol), ZnCl_2 (709 mg, 5.2 mmol), EtOH (120 mL, 0.02 M), NH_4OH (2.0 mL) and water (20 mL).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.21-8.10 (m, 2H), 7.55-7.32 (m, 7H), 7.22-7.10 (m, 2H), 7.01 (d, J = 5.3 Hz, 1H)

MS/FAB : 1034.1 (found), 1037.89 (calculated)

[Preparation Example 20] Preparation of Compound (20)

The compound, 3,5-dibromosalicylaldehyde (20 g, 71.5 mmol) and phenylboronic acid (13.1 g, 107.3 mmol) were dissolved in toluene (250 mL, 0.29 M), and the solution was stirred. To the solution, added were $\text{Pd}(\text{PPh}_3)_4$ (2.5 g, 2.15 mmol) and 2M K_2CO_3 (83 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:5) gave 3,5-diphenyl salicylaldehyde (15.9 g, 58 mmol, 81%).

In 1,4-dioxane (28 mL, 2.1 M), dissolved were 2-aminobenzenethiol (8.7 g, 69.6 mmol) and 3,5-diphenyl salicylaldehyde (15.9 g, 58 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC

(150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4,6-diphenylphenol (17.1 g, 45 mmol, 78%).

5 Compound (20) (1.3 g, 1.0 mmol, 57%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4,6-diphenylphenol (2.0 g, 5.3 mmol), ZnCl₂ (477.1 mg, 3.5 mmol), EtOH (85 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

10 mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.11(m, 2H), 7.55-7.48(m, 8H), 7.35-7.31(m, 3H), 7.23-7.2(m, 2H)

MS/FAB : 1262.14(found), 1266.18(calculated)

15 [Preparation Example 21] Preparation of Compound (21)

20 In 1,4-dioxane (28 mL, 2.1 M), dissolved were 2-aminobenzenethiol (8.7 g, 69.6 mmol) and 1-hydroxy-2-naphthalaldehyde (10.0 g, 58 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)naphthalen-1-ol (8.9 g, 32 mmol, 55%).

Compound (21) (1.5 g, 1.6 mmol, 67%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)naphthalen-1-ol (2.0 g, 7.2 mmol), ZnCl₂ (477.1 mg, 4.8 mmol), EtOH (120 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.1(m, 3H), 7.7-7.5(m, 3H), 7.4-7.3(m, 4H)

MS/FAB : 956(found), 956.78(calculated)

[Preparation Example 22] Preparation of Compound (22)

In 1,4-dioxane (50 mL, 4.0 M), dissolved were 2-aminobenzenethiol (24.8 g, 198 mmol) and 5-bromosalicylaldehyde (40 g, 198 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (300 mL), washed with distilled water (200 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 2:1) gave 2-(benzo[d]thiazol-2-yl)-4-bromophenol (34 g, 118.4 mmol, 60%).

Under argon atmosphere, 2-(benzo[d]thiazol-2-yl)-4-bromophenol (4 g, 13.1 mmol) was dissolved in THF (50 mL, 0.03 M), and the solution was cooled to -78°C. To the solution, n-BuLi (2.5 M in hexane, 7.9 mL, 19.7 mmol) was added dropwise,

and the mixture was stirred for 30 minutes. Triphenylsilyl chloride (TPSCl) (3.9 g, 13.1 mmol) dissolved in THF (25 mL, 0.5 M) was slowly added thereto. The reaction mixture was stirred for 12 hours while slowly raising the temperature to
5 room temperature. After quenching the reaction by adding distilled water (100 mL), the reaction mixture was extracted with MC (50 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 5:1) gave 2-(benzo[d]thiazol-2-yl)-4-triphenylsilylphenol
10 (3.9 g, 8.0 mmol, 61%).

Compound (22) (1.6 g, 1.0 mmol, 75%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-triphenylsilylphenol (2.0 g, 4.1 mmol), ZnCl₂ (368 mg, 2.7
15 mmol), EtOH (70 mL, 0.02 M), NH₄OH (2.0 mL) and distilled water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.59-7.5(m, 9H), 7.3-6.8(m, 11H)

20 MS/FAB : 1584.22(found), 1584.77(calculated)

[Preparation Example 23] Preparation of Compound (23)

In 1,4-dioxane (50 mL, 4.0 M), dissolved were 2-aminobenzenethiol (24.8 g, 198 mmol) and 5-

bromosalicylaldehyde (40 g, 198 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (300 mL), washed with distilled water (200 mL) and dried under
5 reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 2:1) gave 2-(benzo[d]thiazol-2-yl)-4-bromophenol (34 g, 118.4 mmol, 60%).

The compound, 2-(benzo[d]thiazol-2-yl)-4-bromophenol (5 g, 16.33 mmol) and 4-bromophenylboronic acid (3.94 g, 19.6 mmol)
10 were dissolved in toluene (40 mL), EtOH (27 mL) and H₂O (13 mL), and the solution was stirred. To the solution, added were PdCl₂(PPh₃)₂ (573 mg, 0.82 mmol) and K₂CO₃ (4.51 g, 32.66 mmol), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the
15 reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:4) gave 2-(benzo[d]thiazol-2-yl)-4-(4-bromophenyl)phenol (5.5 g, 14.5 mmol, 89%).

Under argon atmosphere, 2-(benzo[d]thiazol-2-yl)-4-(4-bromophenyl)phenol (4 g, 13.1 mmol) was dissolved in THF (50
20 mL, 0.03 M), and the solution was cooled to -78°C. To the solution, n-BuLi (2.5 M in hexane, 7.9 mL, 19.7 mmol) was added dropwise, and the mixture was stirred for 30 minutes. Triphenylsilyl chloride (TPSCl) (3.9 g, 13.1 mmol) dissolved

in THF (25 mL, 0.5 M) was slowly added thereto. The reaction mixture was stirred for 12 hours while slowly raising the temperature to room temperature. After quenching the reaction by adding distilled water (100 mL), the reaction mixture was
5 extracted with MC (50 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 5:1) gave 2-(benzo[d]thiazol-2-yl)-4-(4-triphenylsilylphenyl)phenol (4.8 g, 8.5 mmol, 65%).

Compound (23) (1.8 g, 1.0 mmol, 83%) was obtained by
10 repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-triphenylsilylphenyl)phenol (2.0 g, 3.6 mmol), ZnCl₂ (327 mg, 2.4 mmol), EtOH (60 mL, 0.02 M), NH₄OH (2.0 mL) and distilled water (20 mL).

15 mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.6-7.5(m, 13H), 7.4-6.8(m, 11H)

MS/FAB : 1808.31(found), 1813.06(calculated)

20 [Preparation Example 24] Preparation of Compound (24)

The compound, 5-bromosalicylaldehyde (15 g, 74.6 mmol) and 4-fluorophenylboronic acid (11.5 g, 82.1 mmol) were dissolved in toluene (250 mL, 0.30 M), and the solution was stirred. To the solution, added were Pd(PPh₃)₄ (2.6 g, 2.24

mmol) and 2M K_2CO_3 (83 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and
5 purification via silica gel column chromatography (n-hexane: MC = 1:4) gave 5-(4-fluorophenyl)salicylaldehyde (14.2 g, 32.8 mmol, 88%).

In 1,4-dioxane (18 mL, 1.82 M), dissolved were 2-aminobenzenethiol (4.9 g, 39.4 mmol) and 5-(4-
10 fluorophenyl)salicylaldehyde (7.1 g, 32.8 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel
15 column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-(4-fluorophenyl)phenol (8.4 g, 26 mmol, 79%).

Compound (24) (1.3 g, 1.2 mmol, 58%) was obtained by repeating the same procedure as described in Preparation
20 Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-fluorophenyl)phenol (2.0 g, 6.2 mmol), $ZnCl_2$ (558.8 mg, 4.1 mmol), EtOH (100 mL, 0.02 M), NH_4OH (2.0 mL) and water (20 mL).

mp. > 300°C

1H NMR (300 MHz, $CDCl_3$): δ = 8.23-8.12 (m, 2H), 7.56-7.27 (m,

6H), 7.03-6.98(m, 2H), 6.85(d, $J = 7.3$ Hz, 1H)

MS/FAB : 1088(found), 1091.86(calculated)

[Preparation Example 25] Preparation of Compound (25)

5 In 1,4-dioxane (25 mL, 2.6 M), dissolved were
salicylaldehyde (8.0 g, 65.3 mmol) and 2-amino-5-
(trifluoromethyl)benzenethiol (15.0 g, 65.3 mmol). After
adding triethylamine (6.6 g, 65.3 mmol) thereto, the mixture
was stirred at 100°C under pressure for 12 hours. After
10 cooling to room temperature, the reaction mixture was
extracted with MC (150 mL), washed with water (100 mL) and
dried under reduced pressure. Purification via silica gel
column chromatography (n-hexane: MC = 3:1) gave 2-(6-
trifluoromethyl)benzo[d]thiazol-2-yl)phenol (9.7 g, 32.9 mmol,
15 50%).

Compound (25) (1.0 g, 0.98 mmol, 82%) was obtained by
repeating the same procedure as described in Preparation
Example 1, but using 2-(6-(trifluoromethyl)benzo[d]thiazol-2-
yl)phenol (1.1 g, 3.6 mmol), ZnCl_2 (327 mg, 2.4 mmol), EtOH (61
20 mL, 0.02 M), NH_4OH (1.2 mL) and water (12 mL).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.42(s, 1H), 8.05(d, $J = 6.4$
Hz, 1H), 7.69-7.45(m, 2H), 7.03-6.76(m, 3H)

MS/FAB : 1009.92(found), 1013.60(calculated)

[Preparation Example 26] Preparation of Compound(26)

Compound (26) (1.8 g, 2.2 mmol, 75%) was obtained by repeating the same procedure as described in Preparation
5 Example 1, but using 2-(2-hydroxyphenyl)benzothiazole (2.0 g, 8.8 mmol), ZnI₂ (1.9 g, 5.9 mmol), EtOH (100 mL, 0.03 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.22-8.12(m, 2H), 7.55(m, 2H),
10 7.31(d, J = 7.7 Hz, 1H), 7.05(t, J = 7.2 Hz, 1H), 6.89(t, J = 7.6 Hz, 1H), 6.79(d, J = 7.2 Hz, 1H)

MS/FAB : 805.96(found), 809.6(calculated)

[Preparation Example 27] Preparation of Compound (27)

15 Under argon atmosphere, 2-amino-6-bromobenzothiazole (20 g, 87.3 mmol) and 10 N KOH (100 mL) were added to ethylene glycol (20 mL), and the mixture was stirred at 125°C under reflux for 15 hours. After cooling to room temperature, 12 N HCl (30 mL) was added to the reaction mixture to quench the
20 reaction. The reaction mixture was then washed with water (100 mL) and extracted with EA (100 mL). Recrystallization from MeOH (200 mL) gave 2-amino-5-bromobenzenethiol (14 g, 68.6 mmol, 79%).

In 1,4-dioxane (35 mL, 2.0 M), dissolved were 2-amino-5-

bromobenzenethiol (14 g, 68.6 mmol) and salicylaldehyde (7.0 g, 57.2 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel column chromatography (n-hexane: MC = 5:2) gave 2-(6-bromobenzo[d]thiazol-2-yl)phenol (15.5 g, 50.5 mmol, 88.3%).

Under argon atmosphere, 2-(6-bromobenzo[d]thiazol-2-yl)phenol (15.5 g, 50.5 mmol) and phenylboronic acid (9.2 g, 75.8 mmol) were dissolved in DME (200 mL, 0.25 M) and H₂O (66 mL), and the solution was stirred. To the solution, added were Pd(PPh₃)₄ (1.8 g, 1.5 mmol) and 2M K₂CO₃ (66 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:5) gave 2-(6-phenylbenzo[d]thiazol-2-yl)phenol (20.4 g, 42 mmol, 83%).

Compound (27) (2 g, 2.5 mmol, 85%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(6-phenylbenzo[d]thiazol-2-yl)phenol (2.0 g, 6.6 mmol), ZnCl₂ (600 mg, 4.4 mmol), EtOH (100 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.35-8.27(m, 2H), 7.77-7.22(m, 7H), 7.05-6.79(m, 1H)

MS/FAB : 1034.05(found), 1037.89(calculated)

5

[Preparation Example 28] Preparation of Compound (28)

The compound, 5-bromosalicylaldehyde (15 g, 74.6 mmol) and 4-tert-butylphenylboronic acid (14.6 g, 82.1 mmol) were dissolved in toluene (250 mL, 0.30 M), and the solution was stirred. To the solution, added were Pd(PPh₃)₄ (2.6 g, 2.24 mmol) and 2M K₂CO₃ (83 mL), and the resultant mixture was stirred at 90°C under reflux for 4 hours. After quenching with water (100 mL) and washing, the reaction mixture was extracted with EA (200 mL). Drying under reduced pressure and purification via silica gel column chromatography (n-hexane: MC = 1:3) gave 5-(4-tert-butylphenyl)salicylaldehyde (10.6 g, 41.7 mmol, 56%).

In 1,4-dioxane (18 mL, 1.82 M), dissolved were 2-aminobenzenethiol (4.9 g, 39.4 mmol) and 5-(4-tert-butylphenyl)salicylaldehyde (8.3 g, 32.8 mmol), and the solution was stirred at 100°C under pressure for 12 hours. After cooling to room temperature, the reaction mixture was extracted with MC (150 mL), washed with water (100 mL) and dried under reduced pressure. Purification via silica gel

column chromatography (n-hexane: MC = 3:1) gave 2-(benzo[d]thiazol-2-yl)-4-(4-tert-butylphenyl)phenol (8.3 g, 23 mmol, 70%).

Compound (28) (1.81 g, 1.5 mmol, 73%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-tert-butylphenyl)phenol (2.0 g, 5.6 mmol), ZnCl₂ (558.8 mg, 4.1 mmol), EtOH (100 mL, 0.02 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55-7.23(m, 8H), 6.98-6.85(d, J = 5.3 Hz, 1H), 6.85(d, J = 7.3 Hz, 1H)

MS/FAB : 1202.24(found), 1206.21(calculated)

[Preparation Example 29] Preparation of Compound (29)

In polyphosphoric acid (20 g), dissolved were 2-aminobenzenethiol (4.9 g, 39.4 mmol) and 2-mercaptobenzoic acid (5.1 g, 32.8 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing with water and drying under reduced pressure gave 2-(benzo[d]thiazol-2-yl)benzenethiol (6.1 g, 25 mmol, 76%).

Compound (29) (1.5 g, 1.7 mmol, 62%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)benzenethiol (2.0

g, 8.2 mmol), ZnCl_2 (749.7 mg, 5.5 mmol), EtOH (100 mL, 0.028 M), NH_4OH (2.0 mL) and water (20 mL).

mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.23-8.12(m, 2H), 7.55-7.06(m,

5 6H)

MS/FAB : 853.89(found), 857.80(calculated)

[Preparation Example 30] Preparation of Compound (30)

In DME (600 mL, 0.305 M), dissolved were 5-iodoisatin (50
10 g, 183 mmol) and phenylboronic acid (24.5 g, 201.3 mmol), and
the solution was stirred. After adding $\text{Pd}(\text{PPh}_3)_4$ (6.34 g, 5.49
mmol) and 2M NaHCO_3 (200 mL) thereto, the resultant mixture was
stirred at 100°C under reflux for 12 hours. The reaction
mixture containing 5-phenylisatin was dried under low vacuum,
15 and 5% NaOH (120 mL) was added to the residual aqueous
solution. After removing the impurities by extracting with
 CH_2Cl_2 , added was H_2O_2 (120 mL) to the aqueous layer, and the
resultant mixture was stirred at 50°C for 30 minutes. The
mixture was cooled to room temperature, and filtered. The
20 filtrate was adjusted to have pH of 4. Filtration of the solid
compound gave 2-amino-5-phenylbenzoic acid (24.3 g, 114 mmol,
62%).

While maintaining the temperature at 5°C, NaNO_2 (7.9 g,
114 mmol) was dissolved in water (30 mL), and a solution of 2-

amino-5-phenylbenzoic acid (24.3 g, 114 mmol) dissolved in water (60 mL), and concentrated HCl (23 mL) were slowly added thereto. At the same time, $\text{Na}_2\text{S}_9\text{H}_2\text{O}$ (28.8 g, 120 mmol) and refined sulfur (3.85 g, 120 mmol) were dissolved in water (30 mL), and 10 M NaOH (11 mL) was added thereto. The mixture was cooled to 5°C, and added to the solution containing 2-amino-5-phenylbenzoic acid. The resultant mixture was stirred while slowly raising the temperature to room temperature. Concentrated HCl was added to generate solid, and the mixture was washed with NaHCO_3 (250 mL). The solid generated was filtered and dried, and then added to glacial acetic acid (100 mL) along with Zn dust (7 g, 107 mmol). The mixture was stirred under reflux for 48 hours. After quenching with concentrated HCl, the solid was filtered and washed with EtOH (100 mL) to obtain 2-mercapto-5-phenylbenzoic acid (17.3 g, 75 mmol, 66%).

In polyphosphoric acid (40 g), dissolved were 2-mercapto-5-phenylbenzoic acid (17.3 g, 75 mmol) and 2-aminobenzenethiol (10.3 g, 82.5 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing with water and drying under reduced pressure gave 2-(benzo[d]thiazol-2-yl)-4-phenylbenzenethiol (12.8 g, 40 mmol, 53%).

Compound (30) (1.7 g, 1.6 mmol, 76%) was obtained by

repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-phenylbenzenethiol (2.0 g, 6.3 mmol), ZnCl_2 (558.8 mg, 4.1 mmol), EtOH (80 mL, 0.026 M), NH_4OH (2.0 mL) and water (20 mL).

5 mp. > 300°C

^1H NMR (300 MHz, CDCl_3): δ = 8.23-8.10 (m, 2H), 7.55-7.22 (m, 12H)

MS/FAB : 1081.98(found), 1086.09(calculated)

10 [Preparation Example 31] Preparation of Compound (31)

In DME (600 mL, 0.305 M), dissolved were 5-iodoisatin (50 g, 183 mmol) and naphthalen-2-yl-2-boronic acid (34.6 g, 201.3 mmol), and the solution was stirred. After adding $\text{Pd}(\text{PPh}_3)_4$ (6.34 g, 5.49 mmol) and 2M NaHCO_3 (200 mL) thereto, the
15 resultant mixture was stirred at 100°C under reflux for 12 hours. The reaction mixture containing 5-(naphthalen-3-yl)isatin thus produced was dried under low vacuum, and 5% NaOH (120 mL) was added to the residual aqueous solution. After removing the impurities by extracting with CH_2Cl_2 , added was
20 H_2O_2 (120 mL) to the aqueous layer, and the resultant mixture was stirred at 50°C for 30 minutes. The mixture was cooled to room temperature, and filtered. The filtrate was adjusted to have pH of 4. Filtration of the solid compound gave 2-amino-5-(naphthalen-3-yl)benzoic acid (32.9 g, 125 mmol, 68%).

While maintaining the temperature at 5°C, NaNO₂ (8.3 g, 120 mmol) was dissolved in water (40 mL), and a solution of 2-amino-5-(naphthalen-3-yl) benzoic acid (32.9 g, 125 mmol) dissolved in water (70 mL), and concentrated HCl (30 mL) were slowly added thereto. At the same time, Na₂S₉H₂O (30.0 g, 125 mmol) and refined sulfur (4.01 g, 125 mmol) were dissolved in water (40 mL), and 10 M NaOH (15 mL) was added thereto. The mixture was cooled to 5°C, and added to the solution containing 2-amino-5-(naphthalen-3-yl) benzoic acid dissolved therein. The resultant mixture was stirred while slowly raising the temperature to room temperature. Concentrated HCl was added to generate solid, and the mixture was washed with NaHCO₃ (250 mL). The solid generated was filtered and dried, and then added to glacial acetic acid (100 mL) along with Zn dust (7 g, 107 mmol). The mixture was stirred under reflux for 48 hours. After quenching with concentrated HCl, the solid was filtered and washed with EtOH (100 mL) to obtain 2-mercapto-5-(naphthalen-3-yl)benzoic acid (22.4 g, 80 mmol, 64%).

In polyphosphoric acid (40 g), dissolved were 2-mercapto-5-(naphthalen-3-yl)benzoic acid (22.4 g, 80 mmol) and 2-aminobenzenethiol (11.0 g, 88 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing with water and drying under reduced pressure gave 2-

(benzo[d]thiazol-2-yl)-4-(naphthalen-3-yl)benzenethiol (15.5 g, 42 mmol, 53%).

Compound (31) (1.4 g, 1.13 mmol, 63%) was obtained by repeating the same procedure as described in Preparation
5 Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(naphthalen-3-yl)benzenethiol (2.0 g, 5.4 mmol), ZnCl₂ (490.7 mg, 3.6 mmol), EtOH (70 mL, 0.026 M), NH₄OH (2.0 mL) and water (20 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.14(m, 2H), 7.9-7.3(m,
10 12H)

MS/FAB : 1232.03(found), 1236.27(calculated)

[Preparation Example 32] Preparation of Compound (32)

In DME (600 mL, 0.305 M), dissolved were 5-iodoisatin (50
15 g, 183 mmol) and 9,9-dimethyl-9H-fluoren-2-yl-2-boronic acid (47.9 g, 201.3 mmol), and the solution was stirred. After adding Pd(PPh₃)₄ (6.34 g, 5.49 mmol) and 2M NaHCO₃ (200 mL) thereto, the resultant mixture was stirred at 100°C under reflux for 12 hours. The reaction mixture containing 5-(9,9-
20 dimethyl-9H-fluoren-2-yl)isatin thus produced was dried under low vacuum, and 5% NaOH (120 mL) was added to the residual aqueous solution. After removing the impurities by extracting with CH₂Cl₂, added was H₂O₂ (120 mL) to the aqueous layer, and the resultant mixture was stirred at 50°C for 30 minutes. The

mixture was cooled to room temperature, and filtered. The filtrate was adjusted to have pH of 4. Filtration of the solid compound gave 2-amino-5-(9,9-dimethyl-9H-fluoren-2-yl)benzoic acid (24.0 g, 110 mmol, 57%).

5 While maintaining the temperature at 5°C, NaNO₂ (6.9 g, 100 mmol) was dissolved in water (40 mL), and a solution of 2-amino-5-(9,9-dimethyl-9H-fluoren-2-yl)benzoic acid (36.2 g, 110 mmol) dissolved in water (70 mL), and concentrated HCl (30 mL) were slowly added thereto. At the same time, Na₂S₉H₂O
10 (26.4 g, 110 mmol) and refined sulfur (3.53 g, 110 mmol) were dissolved in water (40 mL), and 10 M NaOH (15 mL) was added thereto. The mixture was cooled to 5°C, and added to the solution containing 2-amino-5-(9,9-dimethyl-9H-fluoren-2-yl)benzoic acid dissolved therein. The resultant mixture was
15 stirred while slowly raising the temperature to room temperature. Concentrated HCl was added to generate solid, and the mixture was washed with NaHCO₃ (250 mL). The solid generated was filtered and dried, and then added to glacial acetic acid (100 mL) along with Zn dust (7 g, 107 mmol). The
20 mixture was stirred under reflux for 48 hours. After quenching with concentrated HCl, the solid was filtered and washed with EtOH (100 mL) to obtain 2-mercapto-5-(9,9-dimethyl-9H-fluoren-2-yl)benzoic acid (26.0 g, 75 mmol, 68%).

In polyphosphoric acid (40 g), dissolved were 2-mercapto-

5-(9,9-dimethyl-9H-fluoren-2-yl)benzoic acid (26.0 g, 75 mmol) and 2-aminobenzenethiol (10.3 g, 82.5 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing
5 with water and drying under reduced pressure gave 2-(benzo[d]thiazol-2-yl)-4-(9,9-dimethyl-9H-fluoren-2-yl)benzenethiol (22.2 g, 51 mmol, 68%).

Compound (32) (1.1 g, 0.77 mmol, 50.3%) was obtained by repeating the same procedure as described in Preparation
10 Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(9,9-dimethyl-9H-fluoren-2-yl)benzenethiol (2.0 g, 4.6 mmol), ZnCl₂ (417.1 mg, 3.06 mmol), EtOH (60 mL, 0.026 M), NH₄OH (2.0 mL) and water (2.0 mL).

mp. > 300°C

15 ¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.9-7.54(m, 8H), 1.67(s, 6H)

MS/FAB : 1432.19(found), 1436.59(calculated)

[Preparation Example 33] Preparation of Compound (33)

20 In DME (600 mL, 0.305 M), dissolved were 5-iodoisatin (50 g, 183 mmol) and 4-fluorophenylboronic acid (28.2 g, 201.3 mmol), and the solution was stirred. After adding Pd(PPh₃)₄ (6.34 g, 5.49 mmol) and 2M NaHCO₃ (200 mL) thereto, the resultant mixture was stirred at 100°C under reflux for 12

hours. The reaction mixture containing 5-(4-fluorophenyl)isatin thus produced was dried under low vacuum, and 5% NaOH (120 mL) was added to the residual aqueous solution. After removing the impurities by extracting with 5 CH₂Cl₂, added was H₂O₂ (120 mL) to the aqueous layer, and the resultant mixture was stirred at 50°C for 30 minutes. The mixture was cooled to room temperature, and filtered. The filtrate was adjusted to have pH of 4. Filtration of the solid compound gave 2-amino-5-(4-fluorophenyl)benzoic acid (24.0 g, 10 104 mmol, 57%).

While maintaining the temperature at 5°C, NaNO₂ (6.8 g, 98 mmol) was dissolved in water (40 mL), and a solution of 2-amino-5-(4-fluorophenyl)benzoic acid (24.0 g, 104 mmol) dissolved in water (70 mL), and concentrated HCl (30 mL) were 15 slowly added thereto. At the same time, Na₂S₉H₂O (25.0 g, 104 mmol) and refined sulfur (3.33 g, 104 mmol) were dissolved in water (40 mL), and 10 M NaOH (15 mL) was added thereto. The mixture was cooled to 5°C, and added to the solution containing (33-2). The resultant mixture was stirred while slowly raising 20 the temperature to room temperature. Concentrated HCl was added to generate solid, and the mixture was washed with NaHCO₃ (150 mL). The solid generated was filtered and dried, and then added to glacial acetic acid (80 mL) along with Zn dust (6.5 g, 100 mmol). The mixture was stirred under reflux for 48 hours.

After quenching with concentrated HCl, the solid was filtered and washed with EtOH (100 mL) to obtain 2-mercapto-5-(4-fluorophenyl)benzoic acid (16.9 g, 68 mmol, 65%).

In polyphosphoric acid (30 g), dissolved were 2-mercapto-5-(4-fluorophenyl)benzoic acid (16.9 g, 68 mmol) and 2-aminobenzenethiol (9.4 g, 74.8 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing with water and drying under reduced pressure gave 2-(benzo[d]thiazol-2-yl)-4-(4-fluorophenyl)benzenethiol (13.8 g, 41 mmol, 68%).

Compound (33) (1.74 g, 1.53 mmol, 78%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-fluorophenyl)benzenethiol (2.0 g, 5.9 mmol), ZnCl₂ (535.7 mg, 3.93 mmol), EtOH (80 mL, 0.025 M), NH₄OH (2.0 mL) and water (2.0 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12(m, 2H), 7.55-7.2(m, 9H)

MS/FAB : 1135.95(found), 1140.06(calculated)

[Preparation Example 34] Preparation of Compound (34)

In DME (600 mL, 0.305 M), dissolved were 5-iodoisatin (50

g, 183 mmol) and 4-tert-butylphenylboronic acid (35.8 g, 201.3 mmol), and the solution was stirred. After adding $\text{Pd}(\text{PPh}_3)_4$ (6.34 g, 5.49 mmol) and 2M NaHCO_3 (200 mL) thereto, the resultant mixture was stirred at 100°C under reflux for 12 hours. The reaction mixture containing 5-(4-tert-butylphenyl)isatin thus produced was dried under low vacuum, and 5% NaOH (120 mL) was added to the residual aqueous solution. After removing the impurities by extracting with CH_2Cl_2 , added was H_2O_2 (120 mL) to the aqueous layer, and the resultant mixture was stirred at 50°C for 30 minutes. The mixture was cooled to room temperature, and filtered. The filtrate was adjusted to have pH of 4. Filtration of the solid compound gave 2-amino-5-(4-tert-butylphenyl)benzoic acid (29.9 g, 111 mmol, 61%).

While maintaining the temperature at 5°C, NaNO_2 (6.8 g, 98 mmol) was dissolved in water (40 mL), and a solution of 2-amino-5-(4-tert-butylphenyl)benzoic acid (29.9 g, 111 mmol) dissolved in water (80 mL) and concentrated HCl (40 mL) were slowly added thereto. At the same time, $\text{Na}_2\text{S}_9\text{H}_2\text{O}$ (26.7 g, 111 mmol) and refined sulfur (3.56 g, 104 mmol) were dissolved in water (40 mL), and 10 M NaOH (15 mL) was added thereto. The mixture was cooled to 5°C, and added to the solution containing 2-amino-5-(4-tert-butylphenyl)benzoic acid dissolved therein. The resultant mixture was stirred while slowly raising the

temperature to room temperature. Concentrated HCl was added to generate solid, and the mixture was washed with NaHCO₃ (150 mL). The solid generated was filtered and dried, and then added to glacial acetic acid (80 mL) along with Zn dust (6.9 g, 105
5 mmol). The mixture was stirred under reflux for 48 hours. After quenching with concentrated HCl, the solid was filtered and washed with EtOH (100 mL) to obtain 2-mercapto-5-(4-tert-butylphenyl)benzoic acid (20.0 g, 70 mmol, 63%).

In polyphosphoric acid (30 g), dissolved were 2-mercapto-
10 5-(4-tert-butylphenyl)benzoic acid (20.0 g, 70 mmol) and 2-aminobenzenethiol (9.6 g, 77 mmol), and the solution was stirred at 140°C for 12 hours. After cooling to room temperature, the reaction was quenched by adding NaOH. Washing with water and drying under reduced pressure gave 2-
15 (benzo[d]thiazol-2-yl)-4-(4-tert-butylphenyl)benzenethiol (19.9 g, 53 mmol, 76%).

Compound (34) (1.73 g, 1.38 mmol, 78%) was obtained by repeating the same procedure as described in Preparation Example 1, but using 2-(benzo[d]thiazol-2-yl)-4-(4-tert-
20 butylphenyl)benzenethiol (2.0 g, 5.3 mmol), ZnCl₂ (481.1 mg, 3.53 mmol), EtOH (70 mL, 0.025 M), NH₄OH (2.0 mL) and water (2.0 mL).

mp. > 300°C

¹H NMR (300 MHz, CDCl₃): δ = 8.23-8.12 (m, 2H), 7.55-7.28 (m,

9H), 1.35(s, 9H)


MS/FAB : 1250.17(found), 1254.41(calculated)

[Example 1-34] Manufacture of an OLED using the compound
5 according to the present invention.

An OLED device was manufactured by using the compound according to the present invention as a host, and a red phosphorescent material as an EL dopant. The cross-sectional view of the OLED device is shown in Fig. 1.


10 First, a substrate prepared by coating a transparent electrode ITO thin film (2) ($15 \Omega/\square$, produced by Samsung Corning) on glass (1) was subjected to ultrasonic washing with trichloroethylene, acetone, ethanol and distilled water, subsequently, and stored in isopronanol before use.

15 Then, an ITO substrate was equipped in a substrate folder of a vacuum vapor-deposit device, and 4,4',4''-tris(N,N-(2-naphthyl)-phenylamino)triphenylamine (2-TNATA) was placed in a cell of the vacuum vapor-deposit device, which was then vented to reach 10^{-6} torr of vacuum in the chamber. Electric current
20 was applied to the cell to evaporate 2-TNATA to vapor-deposit a hole injection layer (3) having 60 nm of thickness on the ITO substrate.



2-TNATA


Then, another cell of the vacuum vapor-deposit device was charged with N,N'-bis(α -naphthyl)-N,N'-diphenyl-4,4'-diamine (NPB), and electric current was applied to the cell to
5 evaporate NPB to vapor-deposit a hole transportation layer (4) with 20 nm of thickness on the hole injection layer.



NPB


One cell of the vacuum deposition device was charged with
10 a selected EL compound (from Compounds (1) to (34) prepared from Preparation Examples 1 to 34) which had been purified by vacuum sublimation under 10^{-6} torr, as a host material. Another cell of said device was charged with (pip) 2Ir(acac) or (pq-F1) 2Ir(acac) , respectively. The two materials were

evaporated at different rates to carry out doping in a concentration of 4 to 10 mol%, to vapor-deposit an electroluminescent layer (5) with 30 nm of thickness on the hole transportation layer.



5


Then, tris(8-hydroxyquinoline)-aluminum (III) (Alq) was vapor-deposited with a thickness of 20 nm, as an electron transportation layer (6), followed by lithium quinolate (Liq) with a thickness of from 1 to 2 nm as an electron injection layer (7). Thereafter, an Al cathode (8) was vapor-deposited in a thickness of 150 nm by using another vacuum vapor-deposit device to manufacture an OLED.



15

[Comparative Example 1]

An OLED device was manufactured according to the same procedure as described in Example 1, except that another cell in the vapor-deposition device was charged with bis(2-methyl-8-quinolinato)(p-phenylphenolato)aluminum (III) (BALq) instead of the EL compound according to the present invention, as EL host material, and still another cell were charged with (piq)₂Ir(acac) or (pq-Fl)₂Ir(acac), respectively, as the EL dopant material identical to that of Example 1. By evaporating the two substances in different rates, an EL layer was vapor-deposited by doping in a concentration of 4 to 10 mol% on the basis of BALq, with a thickness of 30 nm on the hole transportation layer.

**BALq**

15

[Example 35] Determination of properties of OLED

Current luminous efficiency and power efficiency of OLED's containing the EL compounds according to the present invention (Examples 1 to 34) and a conventional EL compound (Comparative Example 1) were measured at 1,000 cd/m². The

20

results are shown in Table 1:

[Table 1]

	Host material	El material	Operation Voltage (V) @1,000 cd/m ²	Luminous Efficiency (cd/A) @1,000 cd/m ²	Power Efficiency (lm/W) @1,000 cd/m ²	Color Coordinate (x, y)
Ex.1	1	(piq) ₂ Ir(acac)	5.55	7.65	4.3	(0.671, 0.328)
Ex.2	2	(piq) ₂ Ir(acac)	5.8	7.6	4.1	(0.673, 0.325)
Ex.3	3	(pq-Fl) ₂ Ir(acac)	5.8	7.5	4.1	(0.672, 0.327)
Ex.4	4	(piq) ₂ Ir(acac)	5.4	5.1	3.0	(0.673, 0.325)
Ex.5	5	(pq-Fl) ₂ Ir(acac)	5.7	7.6	4.2	(0.671, 0.327)
Ex.6	6	(pq-Fl) ₂ Ir(acac)	5.3	6.0	3.6	(0.672, 0.325)
Ex.7	7	(pq-Fl) ₂ Ir(acac)	5.0	7.0	4.4	(0.672, 0.325)
Ex.8	8	(pq-Fl) ₂ Ir(acac)	5.0	6.1	3.8	(0.671, 0.328)
Ex.9	9	(pq-Fl) ₂ Ir(acac)	5.5	7.2	4.1	(0.669, 0.329)
Ex.10	10	(pq-Fl) ₂ Ir(acac)	5.2	7.3	4.4	(0.670, 0.328)
Ex.11	11	(piq) ₂ Ir(acac)	5.3	7.8	4.6	(0.673, 0.325)
Ex.12	12	(piq) ₂ Ir(acac)	5.4	8.0	4.7	(0.673, 0.325)
Ex.13	13	(piq) ₂ Ir(acac)	5.3	7.2	4.3	(0.673, 0.325)
Ex.14	14	(piq) ₂ Ir(acac)	4.9	6.8	4.4	(0.673, 0.325)
Ex.15	15	(piq) ₂ Ir(acac)	5.1	7.5	4.6	(0.673, 0.325)
Ex.16	16	(piq) ₂ Ir(acac)	5.2	7.3	4.4	(0.674, 0.324)
Ex.17	17	(piq) ₂ Ir(acac)	4.8	7.5	4.9	(0.673, 0.325)
Ex.18	18	(piq) ₂ Ir(acac)	5.4	7.7	4.5	(0.673, 0.325)
Ex.19	19	(piq) ₂ Ir(acac)	5.5	7.0	4.0	(0.673, 0.325)
Ex.20	20	(piq) ₂ Ir(acac)	5.3	7.2	4.3	(0.673, 0.325)
Ex.21	21	(piq) ₂ Ir(acac)	5.0	7.0	4.4	(0.673, 0.325)
Ex.22	22	(piq) ₂ Ir(acac)	4.9	7.7	4.9	(0.673, 0.325)
Ex.23	23	(piq) ₂ Ir(acac)	5.2	7.5	4.5	(0.673, 0.325)
Ex.24	24	(piq) ₂ Ir(acac)	5.4	6.8	3.9	(0.673, 0.325)
Ex.25	25	(piq) ₂ Ir(acac)	5.4	6.5	3.8	(0.673, 0.325)
Ex.26	26	(piq) ₂ Ir(acac)	5.5	7.5	4.3	(0.673, 0.325)
Ex.27	27	(piq) ₂ Ir(acac)	5.3	7.6	4.5	(0.673, 0.325)
Ex.28	28	(piq) ₂ Ir(acac)	5.1	7.1	4.4	(0.673, 0.325)
Ex.29	29	(piq) ₂ Ir(acac)	5.2	7.8	4.7	(0.673, 0.325)
Ex.30	30	(piq) ₂ Ir(acac)	5.0	7.4	4.6	(0.673, 0.325)
Ex.31	31	(piq) ₂ Ir(acac)	5.3	6.9	4.1	(0.672, 0.326)
Ex.32	32	(piq) ₂ Ir(acac)	5.3	6.7	4.0	(0.673, 0.325)
Ex.33	33	(piq) ₂ Ir(acac)	5.0	7.6	4.8	(0.673, 0.325)

Ex.34	34	(piq) ₂ Ir(acac)	5.3	7.7	4.6	(0.674,0.324)
Comp. Ex.1	BAIq	(piq) ₂ Ir(acac)	7.5	6.2	2.6	(0.675,0.323)

As can be seen from Table 1, the complexes developed according to the present invention show superior EL properties in view of performances as compared to conventional materials.

5 In particular, the improvement in power consumption due to the lowered operation voltage is not simply resulted from the improvement in luminous efficiency, but from the improvement of the current properties, as can be seen from Table 1.

These are resulted from specific structure of the
10 molecule of host material according to the present invention and the effect of metal ion complex, and it is interpreted that properties of the thin film are improved due to these structural feature of the molecule. Table 1 shows that, the properties of thin film and EL properties are more prominently
15 improved as comprising a soft element having larger atomic number, and an aromatic ring as the side chain.

It is confirmed that the host material according to the present invention has excellent energy transmission property from the phenomenon of maintaining the EL properties of the
20 dopant itself, regardless of the electroluminescent wavelength range of the host itself. This is a very important property required for a host material, providing advantage from the viewpoint of ensuring the process margin to the doping

concentration of the dopant.

【Industrial Applicability】


The electroluminescent compounds according to the present
5 invention provide advantages, when they are employed as host
material of phosphorescent material in an OLED device, of
noticeably lowering the operation voltage, enhancing current
efficiency, and thus improving the power efficiency as
compared to conventional host material. These EL compounds are
10 expected to significantly contribute to reduce power
consumption of an OLED.

【CLAIMS】


【Claim 1】

An electroluminescent compound represented by Chemical Formula (1):

5 [Chemical Formula 1]



wherein, the ligands (L1, L2 and L3) are independently selected from the structures represented by following chemical structure; M is a bivalent metal; and Q is a monovalent anion
10 derived from an inorganic or an organic acid.




[In the ligands, X is O, S or Se; ring A is oxazole, thiazole, imidazole, oxadiazole, thiadiazole, benzoxazole, benzothiazole, benzoimidazole, pyridine or quinoline; R1 through R4
15 independently represent hydrogen, C1-C5 alkyl, halogen, silyl group or C6-C20 aryl, or they may be bonded to an adjacent substituent via alkylene or alkenylene to form a fused ring; and the pyridine and quinoline may chemically bonded to R1 to
20 form a fused ring; and the ring A and aryl group of R1 through

R4 may be further substituted by C1-C5 alkyl, halogen, C1-C5 alkyl having halogen substituent(s), phenyl, naphthyl, silyl or amino group.]

5 【Claim 2】

An electroluminescent compound according to claim 1, wherein L1, L2 and L3 are selected from one of the following chemical structures:




10 wherein, X and R1 through R4 are defined as in claim 1; Y is O, S or NR21, Z is CH or N; R11 through R16 independently represent hydrogen, C1-C5 alkyl, halogen, C1-C5 alkyl having halogen substituent(s), phenyl, naphthyl, silyl or amino group, 15 R11 through R14 may be bonded to an adjacent substituent via alkylene or alkenylene to form a fused ring, and R21 is C1-C5 alkyl, substituted or unsubstituted phenyl or naphthyl group.

【Claim 3】


An electroluminescent compound according to claim 1, wherein M is selected from Be, Zn, Mg, Cu and Ni.

【Claim 4】

- 5 An electroluminescent compound according to claim 2, wherein the ligands (L1, L2 and L3) are identical, and selected from the structures represented by one of the following chemical formulas:



10















wherein, X is O, S or Se, and R2, R3, R12 and R13 independently represent hydrogen, methyl, ethyl, n-propyl,







isopropyl, fluorine, chlorine, trifluoromethyl, phenyl, naphthyl, fluorenyl, trimethylsilyl, triphenylsilyl, t-butyl dimethylsilyl, dimethylamine, diethylamine or diphenylamine; and the phenyl, naphthyl or fluorenyl may be
5 further substituted by fluorine, chlorine, trimethylsilyl, triphenylsilyl, t-butyl dimethylsilyl, dimethylamine, diethylamine or diphenylamine.









【Claim 5】







10 An electroluminescent compound according to claim 4, which is selected from the compounds represented by one of the following chemical formulas:















【Claim 6】

An electroluminescent compound according to claim 1, wherein Q
 5 is selected from Cl^- , Br^- , I^- , CN^- , ClO_4^- , CF_3COO^- , CF_3SO_3^- ,
 $\text{p}-(\text{CH}_3)\text{PhSO}_3^-$ and BF_4^- .

【Claim 7】


An electroluminescent device which comprises an
 10 electroluminescent compound according to any one of claims 1
 to 6.

【Claim 8】


An electroluminescent device according to claim 7, wherein the
 15 compound is employed as the host material for
 electroluminescent layer.

【DRAWINGS】


【Figure 1】




【Figure 2】



【Figure 3】



【Figure 4】



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR2008/000008**A. CLASSIFICATION OF SUBJECT MATTER***C09K 11/06(2006.01)i*

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 8 : C09K, H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS (KIPO internal), USPAT, PAJ, Registry & CAPLUS(STN)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 2005-2101 A (SEMICONDUCTOR ENERGY LAB. CO., LTD) 06 January 2005 See the abstract, claims, formula(1).	1-8
A	US 6936716 B1 (LIN) 30 August 2005 See the abstract, claims, formula (1).	1-8
A	JP 2003-252888 A (MITSUBISHI CHEMICALS CORP) 10 September 2003 See the whole document.	1-8
A	JP 2003-192691 A (MITSUBISHI CHEMICALS CORP) 09 July 2003 See the whole document.	1-8
A	JP 2005-163036 A (CHI MEI ELECTRONICS CORP et al.) 23 June 2005 See the whole document.	1-8

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

31 MARCH 2008 (31.03.2008)

Date of mailing of the international search report

31 MARCH 2008 (31.03.2008)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
Government Complex-Daejeon, 139 Seonsa-ro, Seo-
gu, Daejeon 302-701, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

OH, Se Zu

Telephone No. 82-42-481-8156



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/KR2008/000008

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2005-2101 A	06.01.2005	CN1609101A KR1020040099161A US2004230061A1 US2005033054A1 US6998492B2	27.04.2005 26.11.2004 18.11.2004 10.02.2005 14.02.2006
US 6936716 B1	30.08.2005	None	
JP 2003-252888 A	10.09.2003	None	
JP 2003-192691 A	09.07.2003	None	
JP 2005-163036 A	23.06.2005	TW245068B US2005116626A US7193088B2	11.12.2005 02.06.2005 20.03.2007

专利名称(译)	用于电致发光的有机金属化合物和使用其的有机电致发光器件		
公开(公告)号	EP2092040A1	公开(公告)日	2009-08-26
申请号	EP2008704549	申请日	2008-01-02
[标]申请(专利权)人(译)	金南筠 KIM MIN SUNG		
申请(专利权)人(译)	GRACEL显示增量. KIM , NAM筠 KIM , 晟敏		
当前申请(专利权)人(译)	GRACEL显示增量. KIM , NAM筠 KIM , 晟敏		
[标]发明人	KIM HYUN LEE HO JOON KWON HYUCK JOO CHO YOUNG JUN KIM BONG OK YOON SEUNG SOO		
发明人	KIM, HYUN LEE, HO JOON KWON, HYUCK JOO CHO, YOUNG JUN KIM, BONG OK YOON, SEUNG SOO		
IPC分类号	C09K11/06 H01L51/50		
CPC分类号	C09K11/06 C07D277/66 C07F3/003 C09K2211/1037 C09K2211/1048 C09K2211/1051 C09K2211/188 H01L51/006 H01L51/0081 H01L51/009 H01L51/0092 H01L51/5012 H05B33/14		
优先权	1020070000904 2007-01-04 KR		
其他公开文献	EP2092040A4		
外部链接	Espacenet		

摘要(译)

本发明涉及有机电致发光化合物和包含其作为主体材料的电致发光器件。根据本发明的电致发光化合物的特征在于具有三种配体，两种二价金属和一种衍生自无机或有机酸的一价阴离子。