



US008183763B2

(12) **United States Patent**
Song

(10) **Patent No.:** **US 8,183,763 B2**
(45) **Date of Patent:** **May 22, 2012**

(54) **ORGANIC LIGHT EMITTING DISPLAY AND METHOD OF FABRICATING THE SAME**

(75) Inventor: **Myung-Won Song**, Suwon-si (KR)

(73) Assignee: **Samsung Mobile Display Co., Ltd.**,
Yongin (KR)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 89 days.

(21) Appl. No.: **12/401,465**

(22) Filed: **Mar. 10, 2009**

(65) **Prior Publication Data**

US 2010/0231124 A1 Sep. 16, 2010

Related U.S. Application Data

(60) Provisional application No. 61/079,023, filed on Jul. 8, 2008.

(51) **Int. Cl.**
H01L 51/00 (2006.01)

(52) **U.S. Cl.** **313/504; 313/506; 257/40**

(58) **Field of Classification Search** **313/504, 313/506; 257/40, 98-100**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,977,464 B2 12/2005 Yoshikawa
7,056,180 B2 6/2006 Morii

7,682,851 B2* 3/2010 Lee et al. 438/26
2004/0262613 A1 12/2004 Maekawa et al.
2005/0285987 A1 12/2005 Azumada et al.
2007/0194699 A1 8/2007 Lee et al.
2009/0215350 A1* 8/2009 Takei et al. 445/23

FOREIGN PATENT DOCUMENTS

EP 1 505 666 A2 2/2005
JP 2007-108469 4/2007
JP 2007108469 * 4/2007
KR 10-0793859 1/2008
WO WO 2007/148540 A1 12/2007

OTHER PUBLICATIONS

European Search Report dated Oct. 15, 2009, for corresponding European application 09164876.6, noting listed references in this IDS.

KIPO Office action dated Sep. 30, 2010, for priority Korean Patent application 10-2009-0022655, noting Japanese reference 2007-108469, previously filed in an IDS dated Jan. 6, 2010.

* cited by examiner

Primary Examiner — Karabi Guharay

(74) *Attorney, Agent, or Firm* — Christie, Parker & Hale, LLP

(57) **ABSTRACT**

An organic light emitting display and a method of fabricating the same, in which the resistance of a cathode electrode is reduced by applying a conductive ink material on the cathode electrode. A pixel defining layer is formed on a substrate, with a recess or depression in a non-light emitting region of the pixel defining layer. An electrode on the substrate includes a portion within the recess of the pixel defining layer. The conductive ink is in the portion of the electrode in the recess.

16 Claims, 5 Drawing Sheets





FIG. 1
(PRIOR ART)

FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 4A




FIG. 4B




FIG. 4C





FIG. 4D



ORGANIC LIGHT EMITTING DISPLAY AND METHOD OF FABRICATING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priority to and the benefit of U.S. Provisional Patent Application No. 61/079,023, filed on Jul. 8, 2008, the entire content of which is incorporated herein by reference.

BACKGROUND

1. Field of the Invention

The present invention relates to an organic light emitting display, and a method of fabricating the same.

2. Discussion of Related Art

Generally, electroluminescence displays, which are self-luminous displays, electrically excite fluorescent materials to emit light. These electroluminescence displays have generated significant interest as next-generation displays due to advantages such as low voltage operation, a very slim form factor, a wide viewing angle, a high speed response, etc., which are advantages that generally cannot be achieved in liquid crystal displays.

Electroluminescence displays include inorganic light emitting displays and organic light emitting displays, depending on whether the material that makes up the light emitting layer is an inorganic material or an organic material.

Organic light emitting displays have an organic layer in a pattern (e.g., a predetermined pattern) formed on a glass substrate or other transparent insulating substrate. An anode electrode layer and a cathode electrode layer are formed on an upper part and a lower part of the organic layer, respectively. The organic layer includes organic compounds that form a light emitting layer.

In the organic light emitting display configured as described above, a positive voltage and a negative voltage are applied to an anode electrode and a cathode electrode, respectively, such that holes move from the anode electrode with the positive voltage to the light emitting layer via a hole transportation layer, and electrons move from the cathode electrode with the negative voltage to the light emitting layer via an electron transportation layer. Accordingly, the electrons and the holes are recombined in the light emitting layer to generate excitons, and the excitons change from an excited state to a ground state, so that fluorescent molecules of the light emitting layer emit light to form an image.

FIG. 1 is a circuit diagram showing a conventional pixel of an organic light emitting display. Referring to FIG. 1, the pixel 4 of the organic light emitting display includes a pixel circuit 2 coupled to an organic light emitting diode OLED, a data line Dm, and a scan line Sn to control light emission of the organic light emitting diode OLED.

An anode electrode of the organic light emitting diode OLED is coupled to the pixel circuit 2 and a cathode electrode of the organic light emitting diode OLED is coupled to a second power supply ELVSS. The organic light emitting diode OLED emits light corresponding to a current supplied from the pixel circuit 2.

The pixel circuit 2 controls the amount of current supplied to the organic light emitting diode OLED in accordance with to a data signal supplied to the data line Dm when a scan signal is supplied to the scan line Sn.

To this end, the pixel circuit 2 includes a second transistor M2 coupled between a first power supply ELVDD and the organic light emitting diode OLED; a first transistor M1

coupled between the second transistor M2 and the data line Dm, and coupled to the scan line Sn to receive the scan signal; and a storage capacitor Cst coupled between a first electrode and a gate electrode of the second transistor M2.

A gate electrode of the first transistor M1 is coupled to the scan line Sn and a first electrode of the first transistor M1 is coupled to the data line Dm. A second electrode of the first transistor M1 is coupled to one terminal of the storage capacitor Cst.

Herein, the first electrode is one of a source electrode and a drain electrode, and the second electrode is the other one of the source electrode and the drain electrode. For example, if the first electrode is the source electrode, the second electrode is the drain electrode. The first transistor M1 coupled to the scan line Sn and the data line Dm is turned on when the scan signal is supplied from the scan line Sn to supply the data signal supplied from the data line Dm to the storage capacitor Cst. At this time, the storage capacitor Cst charges a voltage corresponding to the data signal.

The gate electrode of the second transistor M2 is coupled to one terminal of the storage capacitor Cst and the first electrode of the second transistor M2 is coupled to the other terminal of the storage capacitor Cst and the first power supply ELVDD. The second electrode of the second transistor M2 is coupled to the anode electrode of the organic light emitting diode OLED.

The second transistor M2 controls the amount of current flowing from the first power supply ELVDD to the second power supply ELVSS via the organic light emitting diode OLED, where the amount of current corresponds to a voltage value stored in the storage capacitor Cst. According to this configuration, the organic light emitting diode OLED generates light corresponding to the amount of current supplied from the second transistor M2.

The organic light emitting display may be a top emission type, a bottom emission type, or both, according to a light emitting direction. Recently, as flat displays have become bigger in size, the adoption of the top emission type has been preferred.

In top emission type organic light emitting displays, the lower part of the organic layer is coupled to the anode electrode and the upper part of the organic layer transmitting light is coupled to the cathode electrode.

In some organic light emitting displays, the cathode electrode includes a transmissive layer (i.e., a layer that both transmits and reflects light), and in the case of the top emission type, a cathode electrode having a low work function and a transmissive characteristic is frequently utilized.

Accordingly, the cathode electrode may be very thin to implement the transmissive characteristic. In this case, the cathode electrode has a high resistance.

In particular, in the case where the organic light emitting display is driven with current, a voltage drop (i.e., an IR drop) occurs by resistance of a line and/or an electrode. Here, in the case of the top emission type organic light emitting display, the voltage drop is caused by the high resistance of the thin, transmissive cathode electrode, making it difficult to properly implement the display.

In other words, a cathode electrode having a high resistance can result in a serious luminance non-uniformity in the inside of the panel and, particularly in large-area organic light emitting displays, a voltage drop (IR drop) occurs between the center portion and the outer portion of the panel, restricting current injection for high luminance emission in a high definition display.

SUMMARY OF THE INVENTION

An organic light emitting display and a method of fabricating the same, in which the resistance of a cathode electrode

is reduced by applying a conductive ink material on the cathode electrode, is provided in embodiments according to the present invention.

An organic light emitting display according to an exemplary embodiment of the present invention includes a pixel defining layer on a substrate, with a recess in a non-light emitting region of the pixel defining layer. An electrode on the substrate includes a portion within the recess of the pixel defining layer. A conductive ink is in the portion of the electrode in the recess. The non-light emitting region may be between a thin film transistor region of a pixel and a data line region. Further, to provide for a deeper recess, and thus an increased amount of conductive ink, the recess may extend into a planarization layer under the pixel defining layer. The electrode may be a transreflective cathode electrode. Further, the conductive ink may include a high-conductivity material.

Another exemplary embodiment of the present invention is a method of fabricating an organic light emitting display. According to this embodiment, a pixel defining layer is formed on a substrate. A recess is formed in a non-light emitting region of the pixel defining layer. An electrode is formed on the pixel defining layer, the electrode having a portion in the recess. A conductive ink is placed on the portion of the electrode in the recess. The non-light emitting region may be between a thin film transistor region of a pixel and a data line region. Forming the recess may include extending the recess into a planarization layer under the pixel defining layer. The electrode may be a transreflective cathode electrode. The conductive ink may be placed in the recess by using an inkjet printing method, and may include a solvent with a boiling point less than 100° C. The solvent may be one or more of alcohol, ether, benzene, ethyl acetate, and chloroform.

In another embodiment, a display device includes a plurality of light emitting regions and a plurality of non-light emitting regions. Each non-light emitting region is between adjacent ones of the light emitting regions. A cathode electrode is on the light emitting regions and the non-light emitting regions, the cathode electrode having a recess at at least one of the non-light emitting regions. A conductive ink is in the recess. A pixel defining layer may be under the cathode electrode, the pixel defining layer defining the plurality of pixels having the plurality of light emitting regions, and having a first depression corresponding to the recess, such that a portion of the cathode electrode is on an inner wall of the first depression. A planarization layer may further be under the pixel defining layer, the planarization layer having a second depression corresponding to the recess, such that another portion of the cathode electrode is on an inner wall of the second depression.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, together with the specification, illustrate exemplary embodiments of the present invention, and, together with the description, serve to explain the principles of the present invention.

FIG. 1 is a circuit diagram illustrating a pixel in a conventional organic light emitting display;

FIGS. 2A and 2B are cross-sectional views of an organic light emitting display according to exemplary embodiments of the present invention;

FIGS. 3A to 3D are cross-sectional views illustrating a method of fabricating an organic light emitting display according to an exemplary embodiment of the present invention; and

FIGS. 4A to 4D are plan views of an organic light emitting display according to exemplary embodiments of the present invention.

DETAILED DESCRIPTION

In the following detailed description, only certain exemplary embodiments of the present invention are shown and described, simply by way of illustration. Here, when a first element is described as being coupled to a second element, the first element may be directly coupled to the second element, or may be indirectly coupled to the second element via a third element. Further, some of the elements that are not essential to obtain a complete understanding of the invention have been omitted for clarity. Like reference numerals refer to like elements throughout.

Hereinafter, exemplary embodiments of the present invention will be described in more detail with reference to the accompanying drawings.

FIGS. 2A and 2B are cross-sectional views of an organic light emitting display according to exemplary embodiments of the present invention.

FIG. 2A illustrates a pixel region including a storage capacitor region and a thin film transistor region, a conductive ink forming region, and a data line region in an organic light emitting display according to an exemplary embodiment of the present invention.

In order to reduce the resistance of a thin, transreflective cathode electrode 255, which has high resistance, a conductive ink forming region is provided between the thin film transistor region and the data line region. The conductive ink forming region is implemented in a concave shape so that a conductive ink 260 with a low resistance is placed on the cathode electrode 255 in the conductive ink forming region by an inkjet printing method.

In other words, the conductive ink forming region, which is a non-light emitting region, has a concave shape, formed by an etching of a pixel defining layer (PDL) 245 and/or a planarization layer 235 below the cathode electrode 255 (referring to FIG. 2B).

Thus, if a portion of the cathode electrode 255 is formed in the concave shaped portion (e.g., the depression or recess) of the pixel defining layer 245, the concave shape serves as a guide line for the conductive ink 260 to be applied later. The conductive ink 260 with low resistance is applied within the concave shaped portion, thereby reducing the resistance of the cathode electrode 255.

Referring to FIG. 2A, a buffer layer 205 is first formed on a substrate 200. The substrate 200 may be a substrate of glass, plastic, quartz, silicon, or metal, and the buffer layer 205 may be a silicon dioxide film (SiO₂), a silicon nitride film (SiN_x), a silicon oxynitride film (SiO₂N_x), or a multilayer thereof.

A semiconductor pattern 208 is formed on the buffer layer 205 and is formed in the thin film transistor region as shown in FIG. 2A. The semiconductor pattern 208 may be an amorphous silicon film (a-Si) or a polycrystalline silicon film (poly-Si) fabricated by crystallizing an amorphous silicon film. In one embodiment, the semiconductor pattern 208 is a polycrystalline silicon film having high charge mobility.

A gate insulating layer 210 is formed on the substrate 200 including the semiconductor layer 208. The gate insulating layer 210 may be a silicon dioxide film (SiO₂), a silicon nitride film (SiN_x), a silicon oxynitride film (SiO₂N_x), or a multilayer that includes two or more of these films and/or other suitable materials.

A first electrode 212 of a storage capacitor Cst is formed in the storage capacitor region on the gate insulating layer 210,

and a gate electrode **214** overlapping the semiconductor layer **208** is formed in the thin film transistor region. At this time, scan lines (not shown) may concurrently be formed with the formation of the first electrode **212** and the gate electrode **214**.

Then, source/drain regions **208a** and **208b** are formed in a region not overlapped with the gate electrode **214** on the semiconductor layer **208**, by implanting conductive impurities (n- ion or p+ ion) in the semiconductor layer **208** of the thin film transistor region using the gate electrode **214** as a mask. At this time, a channel region **208c** is defined between the source/drain regions **208a/208b**.

Next, an interlayer insulating layer **220** is formed on the substrate on the first electrode **212** of the storage capacitor Cst and the gate electrode **214**, and one or more contact holes are formed within the interlayer insulating layer **220** and the gate insulating layer **210** to expose the semiconductor layer **208**.

A conductive layer is stacked and patterned on the substrate in the region of the contact holes so that source/drain electrodes **221** and **223** are formed in the thin film transistor region. A data line **225** is formed in a data line region and a second electrode **229** of the storage capacitor Cst is formed in the region overlapping the first electrode **212** of the storage capacitor Cst in the storage capacitor region.

Here, the semiconductor layer **208**, the gate insulating layer **210**, the gate electrode **214**, the source electrode **221**, and the drain electrode **223**, which are in the thin film transistor region, form the thin film transistor. The thin film transistor may be a driving transistor such as M2 in FIG. 1 for generating a driving current within the pixel, or in alternate embodiments, the thin film transistor may be a light emission control transistor (not illustrated in FIG. 1) for supplying the driving current to an EL element.

A stacked structure including the first electrode **212**, the interlayer insulating layer **220**, and the second electrode **229**, which are in the storage capacitor region, forms the storage capacitor Cst illustrated in FIG. 1.

Thereafter, a passivation layer **230** is formed on the substrate **200** including the source electrode **221**, the drain electrode **223**, the data line **225**, and the second electrode **229** patterned with the conductive layer. The passivation layer **230** may be formed of a silicon dioxide film (SiO₂), a silicon nitride film (SiN_x), or a multilayer including these two films and/or other suitable materials. In one embodiment, the passivation layer **230** is the silicon nitride film (SiN_x) that can protect the thin film transistor below it by effectively shielding gas and moisture, and can protect an incomplete binding that occurs at a grain boundary of the polycrystalline silicon film containing rich hydrogen.

A first via hole **232** is formed through the passivation layer **230** to expose the drain electrode **223** of the thin film transistor, and a planarization layer **235** for smoothing out any steps in lower layers is formed on the passivation layer **230**. The planarization layer **235** may be formed of an organic layer such as a benzocyclobutene (BCB) film, a polyimide film, or a polyacrylic film. A second via hole **237** is formed within the thin film transistor region through the planarization layer **235** to expose the drain electrode **223** of the thin film transistor.

A first electrode **240** is formed in the storage capacitor region and the thin film transistor region, on the planarization layer **235**. The first electrode **240** is coupled to the drain electrode **223** exposed by the first via hole **232** and the second via hole **237** in the thin film transistor region.

Because the pixel illustrated in FIG. 2A is a top emission type, the first electrode **240** serves as the anode electrode. The first electrode **240** may be formed of a reflective, conductive layer. The light reflective, conductive layer may include materials with a high work function such as Ag, Al, Ni, Pt, and/or

Pd, or an alloy layer of two or more of these materials. In alternate embodiments, the light reflective, conductive layer may include materials with a low work function such as Mg, Ca, Al, Ag, and/or Ba, or an alloy layer thereof. In yet other embodiments, a reflective layer **242** is formed first, followed by forming the first electrode **240**, such that the first electrode **240** is a light transmitting conductive layer formed on the reflective film **242**. In this embodiment, the light transmitting conductive layer may be an indium tin oxide (ITO) film or an indium zinc oxide (IZO). In certain embodiments, the reflective film pattern **242** has a reflectivity above 60%. The reflective film pattern **242** may be aluminum (Al), an aluminum alloy, silver (Ag), a silver alloy, or an alloy layer of one or more of these materials. Such a reflective pattern **242** may be formed to be spaced at an interval, e.g., a predetermined interval, from the via hole **237**.

The first electrode **240** may be formed of an ITO film or an IZO film, and may be formed of Mg, Ca, Al, Ag, and Ba or an alloy layer of two or more of these materials that is thin enough to transmit light.

Next, a pixel defining layer (PDL) **245** is formed on the first electrode **240**. The pixel defining layer **245** may be formed, for example, of benzocyclobutene (BCB), acyclic based photoresist, phenol based photoresist, or imide based photoresist.

In one embodiment, the conductive ink forming region and an opening part **247** are defined in the pixel defining layer **245**. According to this embodiment, a recess **249** is made by etching or otherwise forming a depression or an opening in the pixel defining layer **245** between the thin film transistor region and the data line region (part of the non-light emitting region). The opening part **247** is similarly formed by etching or otherwise forming an opening in the pixel defining layer **245** to expose at least a portion of the first electrode **240** in a light emitting region of the pixel.

The recess **249** is in the conductive ink forming region, where the conductive ink is to be placed, as described later. The recess **249** may extend only through the pixel defining layer **245**, or, in another embodiment as illustrated in FIG. 2B, the recess **249'** may extend at least partially through the planarization layer **235** in so that it has a deeper valley in a concave shape.

The recess **249** or **249'** serves as a guide line for the conductive ink **260** to be applied later, and the conductive ink **260** with low resistance is applied to the region so that the resistance of the cathode electrode is reduced.

An organic light emitting layer **250** is formed on the first electrode **240** exposed within the opening part **247**. The organic light emitting layer **250** may be formed, for example, using a vapor deposition method, an ink jet printing method, or a laser thermal transfer method. Furthermore, a hole injection layer, a hole transportation layer, a hole suppression layer, an electron transportation layer, or an electron injection layer may be formed on or under the organic light emitting layer **250**.

The second electrode **255** is formed on the entire surface of the substrate including the organic light emitting layer **250** and the pixel defining layer **245**. The second electrode **255** serves as a cathode electrode and, in one embodiment, is formed of a transmissive conductive layer. The transmissive conductive layer may be an ITO film or an IZO film, and may include Mg, Ca, Al, Ag, Ba, or an alloy layer of two or more of these materials that is thin enough to transmit light.

Because the second electrode **255** is formed on the entire surface of the substrate, it is formed in the recess **249** as well. That is, a portion of the second electrode **255** is on an inner wall of the depression or recess **249**.

In the case of the top emission display, the second electrode **255** (the cathode electrode in this embodiment) is made of a material having a low work function and is thin enough to exhibit a transfective characteristic. Without any structure to reduce the resistance, this cathode electrode **255** exhibits a high resistance.

To reduce the resistance of the cathode electrode **255**, an exemplary embodiment of the present invention further utilizes the recess **249** having a concave shape in the non-light emitting region as a conductive ink forming region. A conductive ink **260** with a low resistance is applied on the upper side of the cathode electrode **255** by an inkjet printing method.

In the embodiments shown in FIGS. 2A-2B, the conductive ink forming region is shown as formed between the thin film transistor region and the data line region for illustrative purposes only, and the present invention is not limited thereto. In alternative embodiments, the conductive ink forming region may be formed in the non-light emitting region overlapping a portion or all of the data line region.

FIGS. 3A to 3D are cross-sectional views showing a process of fabricating an organic light emitting display according to an exemplary embodiment of the present invention.

In this embodiment, the conductive ink forming region is formed in the non-light emitting region between the thin film transistor region and the data line region, as described above. Accordingly, for convenience of explanation, FIGS. 3A-3D only illustrate a fabrication process in the conductive ink forming region.

First, as shown in FIG. 3A, a gate insulating layer **310**, an interlayer insulating layer **320**, a passivation layer **330**, a planarization layer **335**, and a pixel defining layer **345** are sequentially formed on a first substrate **300** having a buffer layer **305** formed thereon, similar to the embodiment illustrated in FIG. 2A.

The planarization layer **335** may be formed of a benzocyclobutene (BCB) layer, a polyimide layer, or a polyacrylic layer, and the pixel defining layer **345** may be formed of a benzocyclobutene (BCB), acyclic based photoresist, phenol-based photoresist, or imide-based photoresist.

Next, referring to FIG. 3B, an etch is performed on the pixel defining layer **345** to form a recess **349** in a portion of the pixel defining layer **345**.

The region where the recess **349** is formed is where the conductive ink will be placed, as described later. At this time, the recess **349** may extend more deeply into the planarization layer **335** in addition to the pixel defining layer **345**, creating a deeper valley in a concave shape.

In other words, the recess **349** serves as a guide line for the conductive ink **360** to be applied later and the conductive ink **360** with a low resistance is applied to the region to reduce the resistance of the cathode electrode.

Then, as shown in FIG. 3C, the second electrode **355** as the cathode electrode is formed on the substrate **300** including the recess **349**.

In the case of the top emission display, the second electrode **355** (the cathode electrode in this embodiment) is made of a material having a low work function and is thin enough to exhibit a transfective characteristic. Without any structure to reduce the resistance, this cathode electrode **355** exhibits a high resistance.

To reduce the resistance of the cathode electrode **355**, as shown in FIG. 3D, an embodiment of the present invention places a conductive ink **360** with a low resistance on the cathode electrode **355** in the region formed with a valley in a concave shape by the recess **349** by utilizing an inkjet printing method.

According to an exemplary embodiment, the conductive ink contains high-conductivity materials, for example, Ag or carbon nanotubes. A solvent in the conductive ink may be a material with a boiling point less than 100° C., such as alcohol, ether, benzene, ethyl acetate, chloroform, etc. In this way, further wiring may be formed through low temperature firing after applying the conductive ink.

FIGS. 4A to 4D are plan views of an organic light emitting display according to exemplary embodiments of the present invention illustrating various configurations of the conductive ink forming regions. In each of the embodiments illustrated in FIGS. 4A to 4D, the conductive ink is placed in a recess to reduce the resistance of a surface electrode.

FIG. 4A illustrates one embodiment having conductive ink forming regions extending as continuous segments along a plurality of pixels. In this embodiment, the conductive ink forming regions extend vertically across the display region. As in the embodiments illustrated in FIGS. 2A and 2B, the conductive ink forming regions are placed between the pixels and the data line regions, without overlapping the data line regions.

FIG. 4B illustrates an embodiment having conductive ink forming regions extending as continuous segments along a plurality of pixels. Unlike the embodiment illustrated in FIG. 4A, here the conductive ink forming regions are shown as partially overlapping the data line regions. One skilled in the art will comprehend that alternate embodiments are possible that are still within the scope of this invention. For example, the conductive ink forming regions may completely overlap with the data line regions, or the conductive ink forming regions may extend horizontally or in any other suitable direction.

FIG. 4C illustrates an embodiment having conductive ink forming regions as short segments that each extend vertically only partially across the length of a single pixel. Here, the conductive ink forming regions are located near the crossings of the data lines and the scan lines, but not overlapping with the data line regions.

FIG. 4D illustrates an embodiment having conductive ink forming regions as short segments that each extend vertically only partially across the length of a single pixel. Unlike the embodiment illustrated in FIG. 4C, here the conductive ink forming regions are shown partially overlapping the data line regions. One skilled in the art will comprehend that alternate embodiments are possible that are still within the scope of this invention. For example, the conductive ink forming regions may completely overlap with the data line regions, or the conductive ink forming regions may be placed in essentially any non-light emitting region on the surface electrode.

While the present invention has been described in connection with certain exemplary embodiments, it is to be understood that the invention is not limited to the disclosed embodiments, but, on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and scope of the appended claims, and equivalent thereof.

What is claimed is:

1. An organic light emitting display comprising:
 - a pixel defining layer on a substrate;
 - a recess at a non-light emitting region of the pixel defining layer;
 - an electrode on the substrate, the electrode including a portion in the recess of the pixel defining layer; and
 - a conductive ink on only some portions of the electrode, including the portion of the electrode in the recess, wherein the electrode separates the conductive ink from

9

each layer of the organic light emitting display between the electrode and the substrate.

2. The organic light emitting display according to claim 1, wherein the non-light emitting region is between a thin film transistor region of a pixel and a data line region.

3. The organic light emitting display according to claim 1, wherein the recess extends into a planarization layer under the pixel defining layer.

4. The organic light emitting display according to claim 1, wherein the electrode is a cathode electrode comprising a transfective layer.

5. The organic light emitting display according to claim 1, wherein the conductive ink comprises a high-conductivity material.

6. The organic light emitting display according to claim 1, wherein the pixel defining layer has at least one recess at the non-light emitting region, the electrode includes portions in each of the at least one recess, and the conductive ink is only on the portions of the electrode in each of the at least one recess.

7. A method of fabricating an organic light emitting display comprising:

forming a pixel defining layer on a substrate;

forming a recess in a non-light emitting region of the pixel defining layer;

forming an electrode on the pixel defining layer, the electrode having a portion in the recess; and

placing a conductive ink on only some portions of the electrode, including the portion of the electrode in the recess, wherein the electrode separates the conductive ink from each layer of the organic light emitting display formed between the electrode and the substrate.

8. The method of fabricating an organic light emitting display according to claim 7, wherein the non-light emitting region is between a thin film transistor region of a pixel and a data line region.

9. The method of fabricating an organic light emitting display according to claim 7, wherein forming the recess further comprises extending the recess into a planarization layer under the pixel defining layer.

10

10. The method of fabricating an organic light emitting display according to claim 7, wherein the electrode is a cathode electrode comprising a transfective layer.

11. The method of fabricating an organic light emitting display according to claim 7, wherein placing the conductive ink comprises inkjet printing.

12. The method of fabricating an organic light emitting display according to claim 11, wherein inkjet printing utilizes a solvent comprising a material with a boiling point less than 100° C.

13. The method of fabricating an organic light emitting display according to claim 12, wherein the solvent comprises a material selected from the group consisting of alcohol, ether, benzene, ethyl acetate, chloroform, and combinations thereof.

14. A display device comprising:

a plurality of light emitting regions;

a plurality of non-light emitting regions, each non-light emitting region between adjacent ones of the light emitting regions;

a cathode electrode on the light emitting regions and the non-light emitting regions, the cathode electrode having a recess at at least one of the non-light emitting regions; and

a conductive ink on only some portions of the cathode electrode, including in the recess, wherein the cathode electrode separates the conductive ink from portions of the at least one of the non-light emitting regions positioned on a side of the cathode electrode opposite the side on which the conductive ink is positioned.

15. The display device of claim 14, further comprising a pixel defining layer under the cathode electrode, the pixel defining layer defining the plurality of pixels having the plurality of light emitting regions and having a first depression corresponding to the recess, such that a portion of the cathode electrode is on an inner wall of the first depression.

16. The display device of claim 15, further comprising a planarization layer under the pixel defining layer, the planarization layer having a second depression corresponding to the recess, such that another portion of the cathode electrode is on an inner wall of the second depression.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 8,183,763 B2
APPLICATION NO. : 12/401465
DATED : May 22, 2012
INVENTOR(S) : Myung-Won Song

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

In the Claims

Column 9, Claim 7, line 26

Delete "a"

Insert -- an --

Signed and Sealed this
Twenty-seventh Day of August, 2013



Teresa Stanek Rea
Acting Director of the United States Patent and Trademark Office

专利名称(译)	有机发光显示器及其制造方法		
公开(公告)号	US8183763	公开(公告)日	2012-05-22
申请号	US12/401465	申请日	2009-03-10
[标]申请(专利权)人(译)	三星显示有限公司		
申请(专利权)人(译)	三星移动显示器有限公司.		
当前申请(专利权)人(译)	三星移动显示器有限公司.		
[标]发明人	SONG MYUNG WON		
发明人	SONG, MYUNG-WON		
IPC分类号	H01L51/00		
CPC分类号	H01L27/3276 H01L51/0022		
优先权	61/079023 2008-07-08 US		
其他公开文献	US20100231124A1		
外部链接	Espacenet USPTO		

摘要(译)

一种有机发光显示器及其制造方法，其中通过在阴极上施加导电油墨材料来降低阴极电阻。像素限定层形成在基板上，在像素限定层的非发光区域中具有凹陷或凹陷。基板上的电极包括像素限定层的凹陷内的部分。导电墨水位于凹槽中的电极部分中。

