



US006822257B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 6,822,257 B2**
(45) **Date of Patent:** **Nov. 23, 2004**

(54) **ORGANIC LIGHT EMITTING DIODE
DEVICE WITH ORGANIC HOLE
TRANSPORTING MATERIAL AND
PHOSPHORESCENT MATERIAL**

(75) Inventors: **Yung-Chih Lee**, Taipei (TW); **Wei-Su
Chen**, Hsinchu Hsien (TW); **Chi-Chih
Liao**, Taipei (TW); **Jiun-Haw Lee**,
Taipei (TW)

(73) Assignee: **RiTdisplay Corporation**, Hsinchu
(TW)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **10/248,553**

(22) Filed: **Jan. 29, 2003**

(65) **Prior Publication Data**

US 2004/0144974 A1 Jul. 29, 2004

(51) **Int. Cl.**⁷ **H01L 35/24**

(52) **U.S. Cl.** **257/40; 257/79; 257/98;
257/99; 257/102; 257/103**

(58) **Field of Search** **257/40, 79, 98,
257/99, 102, 103; 313/503, 504, 506**

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,097,147 A * 8/2000 Baldo et al. 313/506

6,573,651 B2 * 6/2003 Adachi et al. 313/504
2002/0074935 A1 * 6/2002 Kwong et al. 313/504
2002/0096995 A1 * 7/2002 Mishima et al. 313/506
2002/0180347 A1 * 12/2002 Adachi et al. 313/503
2003/0068525 A1 * 4/2003 Bellmann et al. 428/690
2003/0138657 A1 * 7/2003 Li et al. 428/621
2003/0162299 A1 * 8/2003 Hsieh et al. 436/84
2003/0218418 A9 * 11/2003 Sato et al. 313/504
2004/0028944 A1 * 2/2004 Mori et al. 428/691

* cited by examiner

Primary Examiner—Nathan J. Flynn


Assistant Examiner—Remmon R. Fordé

(74) *Attorney, Agent, or Firm*—Jiang Chyun IP Office

(57) **ABSTRACT**

An organic light emitting diode (OLED) device comprises a substrate, an anode layer, a luminescence layer, a hole blocking layer and a cathode layer. The anode layer is disposed on the substrate; the luminescence layer is disposed on the anode layer; the hole blocking layer is disposed on the luminescence layer; the cathode layer is disposed on the hole blocking layer. In addition the luminescence layer comprises a hole transporting material and a phosphorescent material, wherein the weight percentage of the hole transporting material and the phosphorescent material is between 40%~60%.

24 Claims, 2 Drawing Sheets






FIG. 1




FIG. 2




FIG. 3

**ORGANIC LIGHT EMITTING DIODE
DEVICE WITH ORGANIC HOLE
TRANSPORTING MATERIAL AND
PHOSPHORESCENT MATERIAL**

BACKGROUND OF INVENTION

1. Field of Invention

The present invention relates to organic light emitting diode (OLED) device. More particularly, the present invention relates to an organic light emitting diode (OLED) device having a light emitting layer fabricated by doping an organic material layer with hole transporting material and phosphorescent material.

2. Description of Related Art

Due to rapid growth in the communication industry, portable equipment is a major center of development. Flat displays have become the principal human-machine interface. In general, flat panel displays are divided according to the types of techniques into plasma display panel (PDP), liquid crystal display (LCD), electro-luminescent display, light emitting diode (LED), vacuum fluorescent display, field emission display (FED), electro-chromic display and organic light emitting diode (OLED) display. Among various types of displays, organic light emitting diode (OLED) display has the greatest potential to become the dominant flat panel display in the next generation. An OLED display has many advantages including self-illuminating, no viewing angle retention, low energy consumption, easy to fabricate, low production cost, low operating temperature, quick response and full coloration.

An OLED device utilizes the self-illuminating property of organic functional materials to form images. According to the molecular weight of the organic functional material, OLED displays can be classified into small molecule OLED (SM-OLED) and polymer light-emitting device (PLED).

In general, luminance and light-emitting efficiency are the two major criteria for determining the quality of an OLED device. Researchers are always trying to increase the luminance and efficiency of OLED devices.

At present, the light-emitting layer inside the OLED display is made using fluorescent materials. However, fluorescent materials can hardly reach the desired level of luminance and efficiency. As a result, techniques making use of phosphorescent materials are proposed. Devices that utilize phosphorescent materials can roughly be divided into two major categories:

(1) Phosphorescent materials are directly used in the light-emitting layer. In this type of display device, light-emitting efficiency (cd/A) will rapidly increase or decrease according to the applied voltage or current. However, the color index may change as luminance increases. Furthermore, most devices using phosphorescent material as the light-emitting layer is hardly able to produce the desired luminance at a low applied voltage;

(2) Phosphorescent material is doped as a guest material inside a host light-emitting material at 1% to 10%. Through the energy transfer of the host material, the guest phosphorescent material is illuminated to produce light. However, the color index may change as the luminance is increased. Ultimately, the degree of increase in luminance and light-emitting efficiency is quite limited.

SUMMARY OF INVENTION

Accordingly, one object of the present invention is to provide a light-emitting layer and an organic light emitting

diode (OLED) device having such a light-emitting layer for increasing the luminance and light-emitting efficiency of the device.

A second object of this invention is to provide a light-emitting layer and an organic light emitting diode (OLED) device having such a light-emitting layer such that color index and light-emitting efficiency can be maintained at a constant level as applied voltage or current is increased. Hence, attenuation of the color index and light-emitting efficiency of the device is minimized.

To achieve these and other advantages and in accordance with the purpose of the invention, as embodied and broadly described herein, the invention provides a luminescence layer. The luminescence layer is an organic material layer comprising hole transporting material and phosphorescent material. The concentration of hole transporting material and phosphorescent material in the luminescence layer is between 40%~60% by weight. The organic material is either small molecule organic material or polymer organic material such as, for example, an iridium complex compound having an isoquinoline substituted radical. The hole transporting material is a compound having a tribenzamide structure including, for example, NPB, TPD and TCTA. A hole blocking layer may also be formed over the luminescence layer. The hole blocking layer is fabricated from a material such as BCP, Balq, TAZ or TPBI.

This invention also provides an organic light emitting diode (OLED) device having a substrate, an anode layer, a luminescence layer, a hole blocking layer and a cathode layer. The anode layer is disposed on the substrate and the luminescence layer is disposed on the anode layer. The hole blocking layer is disposed on the luminescence layer and the cathode layer is disposed on over the hole blocking layer. In addition, the luminescence layer is an organic material layer comprising hole transporting material and phosphorescent material. The concentration of hole transporting material and phosphorescent material in the luminescence layer is between 40%~60% by weight.

In the OLED device of this embodiment, a hole injecting layer and a hole transporting layer may be inserted between the anode layer and the light-emitting layer by selection. The hole injecting layer is positioned between the anode layer and the light-emitting layer while the hole transporting layer is positioned between the hole injecting layer and the light-emitting layer. In addition, an electron injecting layer and an electron transporting layer may be inserted between the hole blocking layer and the cathode layer by selection. The electron injecting layer is positioned between the hole blocking layer and the cathode layer while the electron transporting layer is positioned between the electron injecting layer and the cathode layer.

In the OLED device of this embodiment, the hole injecting layer is fabricated from a material such as CuPc or m-MTDATA. The hole transporting layer is fabricated from a material having a tribenzamide structure such as NPB, TPD or TCTA. The electron transporting layer is fabricated from a metal complex compound such as AIQ or BeBq2 or a mixture of cyclic compounds including PBD, TAZ or TPBI.

Furthermore, the anode layer on the substrate is a plurality of transparent electrodes each shaped into a longitudinal strip. The anode layer is fabricated using a transparent material such as indiumtin oxide, indiumzinc oxide or aluminumzinc oxide. The cathode layer is a plurality of metallic electrode each shaped into a longitudinal strip. The cathode layer is fabricated using a conductive material such

as aluminum, calcium or magnesium-silver alloy. The hole blocking layer is fabricated from a material such as BCP, Balq, TAZ or TPBI.

It is to be understood that both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF DRAWINGS

The accompanying drawings are included to provide a further understanding of the invention, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments of the invention and, together with the description, serve to explain the principles of the invention. In the drawings,

FIG. 1 is a schematic cross-sectional diagram of an organic light emitting diode device according to one preferred embodiment of this invention;

FIG. 2 is a graph showing the relationship between luminance and light-emitting efficiency of an organic light emitting diode device fabricated according to one preferred embodiment of this invention; and

FIG. 3 is a graph showing the relationship between color index and applied voltage of an organic light emitting diode device fabricated according to one preferred embodiment of this invention.

DETAILED DESCRIPTION

Reference will now be made in detail to the present preferred embodiments of the invention, examples of which are illustrated in the accompanying drawings. Wherever possible, the same reference numbers are used in the drawings and the description to refer to the same or like parts.

In most electro-luminescent systems, the light emission occurs under a singlet spinning of electron excited states or a triplet spinning of electron excited states. When the singlet spinning of electron excited state drops back to an unexcited state is referred to as fluorescence. The emission can be summarized using the formula:

$$S_1 \rightarrow S_0 + h\nu$$

On the other hand, when the triplet spinning of electron excited state drops back to the unexcited state is referred to as phosphorescence. The emission can be summarized using the formula:

$$T_1 \rightarrow S_0 + h\nu$$

The external quantum efficiency of an electro-luminescent process is given by the formula: $\phi_{EL} = X\phi_f\eta_i\eta_r\eta_e$, where X is the fraction of re-combinations that result in excitons, ϕ_f is the efficiency of injecting charges into the light-emitting layer, η_r is the electron-hole recombination efficiency and η_e is the transition efficiency.

When the singlet spinning of electron is in an excited state, the fraction of re-combinations that result in excitons X is 0.25. Assume all other efficiencies are 100% in the light emission process, the largest external quantum efficiency is actually only 25%. On the contrary, when the triplet spinning of electron is in a excited state, the fraction of recombinations that result in excitons X is 0.75. In other words, assume all other efficiencies are 100% in the light emission process, the largest external quantum efficiency reaches 75%.

Accordingly, using phosphorescent material to serve as a light-emitting material is guaranteed a higher light emission efficiency.

The OLED device in this embodiment uses phosphorescent material to produce light so that an optimal light-emitting efficiency is obtained. In addition, this invention also provides some improvements to rapid attenuation of light-emitting efficiency (cd/A) after an increase in applied voltage or current, change in color index that results from an increase in the luminance and the intrinsic low luminance and light-emitting efficiency of a conventional OLED device.

FIG. 1 is a schematic cross-sectional diagram of an organic light emitting diode device according to one preferred embodiment of this invention. As shown in FIG. 1, the OLED device is constructed over a substrate **100**. The substrate **100** is a transparent substrate such as a glass substrate, a plastic substrate or a flexible substrate. An anode **102**, a light-emitting layer **104**, a cathode layer **106**, a hole injecting layer (HIL) **108**, a hole transporting layer (HTL) **110**, an electron injecting layer (EIL) **112**, an electron transporting layer (ETL) **114** and a hole blocking layer (HBL) **116** are sequentially positioned over the substrate **100**. Note that the aforementioned hole injecting layer **108**, the hole transporting layer **110**, the electron injecting layer **112**, the electron transporting layer **114** and the hole blocking layer **116** can be positioned on demand. In the following, relative positioning, states and material constituents of various film layers are described in more detail.

The anode layer **102** on the substrate **100** includes of plurality transparent electrodes each shaped into a longitudinal strip. The anode layer **102** is fabricated using a transparent material such as indiumtin oxide, indiumzinc oxide or aluminumzinc oxide. The hole injecting layer **108** is positioned to cover the anode layer **102** and is made from a material such as CuPr or m-MTDATA. The hole transporting layer **110** is positioned over the hole injecting layer **108** and is made from a material having a tribenzoamide structure such as NPB, TPD or TCTA.

The luminescence layer **104** is disposed on the hole transporting layer **110**. The luminescence layer **104** is an organic material layer comprising hole transporting material **104b** and phosphorescent material **104a**. The luminescence layer **104** is fabricated using small molecule organic material or polymer organic material such as an iridium complex with isoquinoline substituted radical. The hole transporting material **104b** is fabricated from a material having a tribenzoamide structure such as NPB, TPD or TCTA. In addition, the concentration of hole transporting material and phosphorescent material in the luminescence layer **104** is between 40%~60% by weight.

The hole blocking layer **116** is positioned over the light-emitting layer **104** and is fabricated from a material such as BCP, Balq, TAZ or TPBI. The principal function of the hole blocking layer **116** is to limit the movement of holes within the light-emitting layer **104** so that light-emitting efficiency is increased. The electron transporting layer **114** is positioned over the hole blocking layer **116** and is fabricated from a metal complex compound such as AlQ or BeBq2 or a mixture of cyclic compounds including PBD, TAZ or TPBI. The electron injecting layer **112** is positioned over the electron transporting layer **114** and the cathode layer **106** is positioned over the electron injecting layer **112**. The cathode layer **106** includes plurality of metal electrodes each shaped

into a longitudinal strip. The cathode layer **106** is fabricated using a conductive material such as aluminum, calcium or magnesium-silver alloy.

After the anode layer **102** and the cathode layer **106** of the OLED device are connected to a voltage, electrons will be injected from the cathode layer **106** into the LUMO layer inside the light-emitting layer **104** in the presence of an electric field to form negative ions. Similarly, holes will be injected from the anode layer **102** into the HOMO layer inside the light-emitting layer **104** to form positive ions. The positive ions and the negative ions move in opposite direction and recombine in the light-emitting layer **104** to form excitons. A portion of the excitons in the light-emitting layer **104** releases excess energy as photons by returning the ground state.

In this embodiment, the hole transporting material **104b** has a lower concentration of HOMO compared with the phosphorescent organic material **104a**. Hence, excess holes that has not recombined with electrons will be trapped in the hole transporting material **104b** within the light-emitting layer **104** leading to the so-called hole trapping phenomena. Due to hole trapping, the probability of recombination between the holes and electrons constrained within the light-emitting layer **104** will increase (an increased probability of producing excitons). Therefore, using hole transporting material **104b** in the light-emitting layer **104** to constrain the holes, color index of the phosphorescent material is improved and attenuation of the light-emitting efficiency is reduced aside from an increase in light-emitting efficiency and luminance of the OLED device. Additionally, a drastic increase in the color index due to an increase in voltage is also prevented.

FIG. 2 is a graph showing the relationship between luminance and light-emitting efficiency of an organic light emitting diode device fabricated according to one preferred embodiment of this invention. FIG. 3 is a graph showing the relationship between color index and applied voltage of an organic light emitting diode device fabricated according to one preferred embodiment of this invention. As shown in FIG. 2, this invention increases the light-emitting efficiency of the device to the highest level and reduces the attenuation rate of the light-emitting efficiency at the same time. As shown in FIG. 3, the color index remains constant despite an increase in the applied voltage.

In conclusion, the OLED device has at least the following advantages:

1. Using hole transporting material and phosphorescent material to serve as the light-emitting layer in the OLED device, both the luminance and light-emitting efficiency of the device is increased.

2. Using hole transporting material and phosphorescent material to serve as the light-emitting layer in the OLED device, the attenuation rate of both color index and light-emitting efficiency of the device is reduced.

3. The hole blocking layer in the OLED device is able to constrain holes in the light-emitting layer so that the probability of electron/hole recombination is increased. Ultimately, light-emitting efficiency is increased.

It will be apparent to those skilled in the art that various modifications and variations can be made to the structure of the present invention without departing from the scope or spirit of the invention. In view of the foregoing, it is intended that the present invention cover modifications and variations of this invention provided they fall within the scope of the following claims and their equivalents.

What is claimed is:

1. An organic light-emitting diode (OLED) device, comprising:

a substrate;

an anode layer disposed on the substrate;

a luminescence layer disposed on the anode layer, wherein the luminescence layer is an organic material layer is comprising hole transporting material and phosphorescent material, and that the concentration of hole transporting material and phosphorescent material is between 40~60% by weight;

a hole blocking layer disposed on the luminescence layer; and

a cathode layer disposed on the hole blocking layer.

2. The OLED device of claim 1, wherein the substrate includes a transparent substrate.

3. The OLED device of claim 1, wherein the anode layer includes a plurality of transparent electrodes each shaped into a longitudinal strip.

4. The OLED device of claim 3, wherein material constituting the transparent electrodes is selected from a group consisting of indiumtin oxide, indiumzinc oxide and aluminumzinc oxide.

5. The OLED device of claim 1, wherein the organic material includes small molecule organic material.

6. The OLED device of claim 1, wherein the organic material includes polymer organic material.

7. The OLED device of claim 1, wherein the organic material includes an iridium complex compound having an isoquinoline substituted radical.

8. The OLED device of claim 1, wherein the hole transporting material has a tribenzoamide structure selected from a group consisting of NPB, TPD and TCTA.

9. The OLED device of claim 1, wherein material constituting the hole blocking layer is selected from a group consisting of BCP, Balq, TAZ and TPBI.

10. The OLED device of claim 1, wherein the cathode layer includes a plurality of metallic electrodes each shaped into a longitudinal strip.

11. The OLED device of claim 10, wherein material constituting the metallic electrodes is selected from a group consisting of aluminum, calcium and magnesium-silver alloy.

12. The OLED device of claim 1, wherein the device may further include a hole injecting layer between the anode layer and the luminescence layer.

13. The OLED device of claim 12, wherein the device may further include a hole transporting layer between the hole injecting layer and the luminescence layer.

14. The OLED device of claim 13, wherein material constituting the hole injecting layer is selected from a group consisting of CuPc and m-MTDATA.

15. The OLED device of claim 13, wherein material constituting the hole transporting layer has a tribenzoamide structure selected from a group consisting of NPB, TPD and TCTA.

16. The OLED device of claim 1, wherein the device may further include an electron transporting layer between the hole blocking layer and the cathode layer.

17. The OLED device of claim 16, wherein the device may further include an electron injecting layer between the electron transporting layer and the cathode layer.

18. The OLED device of claim 17, wherein material constituting the electron transporting layer is a metal complex selected from a group consisting of AIQ and BeBq2 or

7

a complex cyclic compound selected from a group consisting of PBD, TAZ and TPBI.

19. A luminescence layer in an organic light emitting diode (OLED) device, wherein the luminescence layer is an organic material layer comprising hole transporting material and phosphorescent material and that the concentration of hole transporting material and phosphorescent material is between 40~60% by weight.

20. The light-emitting layer of claim 19, wherein the organic material includes small molecule organic material.

21. The light-emitting layer of claim 19, wherein the organic material includes polymer organic material.

8

22. The light-emitting layer of claim 19, wherein the organic material includes art iridium complex compound having an isoquinoline substituted radical.

23. The light-emitting layer of claim 19, wherein the hole transporting material has a tribenzoamide structure selected from a group consisting of NPB, TPD and TCTA.

24. The light-emitting layer of claim 19, wherein material constituting the hole blocking layer is selected from a group consisting of BCP, Balq, TAZ and TPBI.

* * * * *

| | | | |
|----------------|---|---------|------------|
| 专利名称(译) | 有机发光二极管器件，具有有机空穴传输材料和磷光材料 | | |
| 公开(公告)号 | US6822257 | 公开(公告)日 | 2004-11-23 |
| 申请号 | US10/248553 | 申请日 | 2003-01-29 |
| [标]申请(专利权)人(译) | 李容志 陈韦SU 廖继春CHIH 李骏HAW | | |
| 申请(专利权)人(译) | 李容志 陈伟SU 廖智 李骏，HAW | | |
| 当前申请(专利权)人(译) | 铼宝科技股份有限公司 | | |
| [标]发明人 | LEE YUNG CHIH CHEN WEI SU LIAO CHI CHIH LEE JIUN HAW | | |
| 发明人 | LEE, YUNG-CHIH CHEN, WEI-SU LIAO, CHI-CHIH LEE, JIUN-HAW | | |
| IPC分类号 | H01L51/05 H01L51/30 H01L51/00 H01L51/50 H01L35/24 | | |
| CPC分类号 | H01L51/5016 H01L51/0059 H01L51/0062 H01L51/5096 H01L51/0081 H01L51/0077 | | |
| 其他公开文献 | US20040144974A1 | | |
| 外部链接 | Espacenet USPTO | | |

摘要(译)

有机发光二极管 (OLED) 器件包括基板，阳极层，发光层，空穴阻挡层和阴极层。阳极层设置在基板上；发光层设置在阳极层上；空穴阻挡层设置在发光层上；阴极层设置在空穴阻挡层上。此外，发光层包括空穴传输材料和磷光材料，其中伯氏传输材料和磷光材料的重量百分比在40%~60%之间。

